

DECCAN CORRUGATED BOXES LLP - QUALITY CONTROL LABORATORY

Test Report No. DCB/QC/BCT/2609 | Date of test: 18-09-2026 | Sample: 5-ply RSC 400x300x300 mm

Parameter	Method	Spec (NHPC L06)	BF 22 sample	BF 20 sample
Combined GSM	IS 1060	~800	812	796
Bursting strength (kg/cm2)	IS 1060 Pt II	≥ 17.6	18.4	16.3
Edge crush test ECT (kN/m)	TAPPI T811	≥ 7.0	7.6	7.1
Box compression BCT (kgf)	ASTM D642	≥ 420	468	436
Moisture (%)	IS 1060	≤ 9	7.9	8.1
Cobb 60 (g/m2)	ISO 535	≤ 150	128	131

Remarks: BF 20 sample meets BCT requirement with 3.8% margin; bursting strength below BF 22 spec (as expected).

Tested by: P. Deshmukh (QC Executive) Approved: A. Kale (QC Head)