

CERTIFICATE OF CONFORMANCE / MILL TEST REPORT (CONSOLIDATED - MULTI-HEAT)

Certificate No: RGM-CERT-2026-0498

Supplier ID: RGM-TX-01

Supplier: Rio Grande Magnetism, LLC

--- Heat 1 ---

Melt Ref.: RGM-NDFEB-2026-0491

Alloy Composition (wt%): Nd 29.8, Fe 67.9, B 1.1, Dy 1.2

Test Results: Br (kG) 13.4 PASS, Hci (kOe) 12.0 PASS, BHmax (MGOe) 43.1 PASS

Nonconformance: None

Feedstock Sub-Lots:

Sub-lot A1: 100% blend, Origin: United States, Confidence: High,

Notes: domestically collected scrap

Segregation Attested: Yes

Segregation Note: Dedicated line, purged between runs.

Batch Mass: 210.0 kg

--- Heat 2 ---

Melt Ref.: RGM-NDFEB-2026-0492

Alloy Composition (wt%): Nd 29.2, Fe 68.5, B 1.0, Dy 1.1

Test Results: Br (kG) 13.0 MARGINAL, Hci (kOe) 11.5 PASS, BHmax (MGOe) 41.0 PASS

Nonconformance: NCR-2026-014 (Br marginally below target, disposition: use-as-is)

Feedstock Sub-Lots:

Sub-lot B1: 65% blend, Origin: United States, Confidence: High,

Notes: domestically collected scrap

Sub-lot B2: 35% blend, Origin: Unconfirmed, Confidence: Low,

Notes: broker-sourced, bonded warehouse, documentation pending

Segregation Attested: No

Segregation Note: (none provided)

Batch Mass: 95.0 kg

--- Heat 3 ---

Melt Ref.: RGM-NDFEB-2026-0493

Alloy Composition (wt%): Nd 30.1, Fe 67.5, B 1.0, Dy 1.4

Test Results: Br (kG) 13.5 PASS, Hci (kOe) 12.2 PASS, BHmax (MGOe) 43.5 PASS

Nonconformance: None

Feedstock Sub-Lots:

Sub-lot C1: 80% blend, Origin: United States, Confidence: High,

Notes: domestically collected scrap

Sub-lot C2: 20% blend, Origin: China, Confidence: High,

Notes: broker-sourced alloy addition

Segregation Attested: Yes

Segregation Note: Dedicated line; however Heat 3 includes a broker-sourced addition per sub-lot C2.

Batch Mass: 120.0 kg

Signed: Maria Alvarez, QA Lead, Rio Grande Magnetism, LLC (Issuer)

Witnessed: James Okafor, Plant Manager, Rio Grande Magnetism, LLC (Witness)