

INCH-POUND

MIL-DTL-5886H

30 January 2009

SUPERSEDING

MIL-DTL-5886G

19 June 2000

DETAIL SPECIFICATION

CYLINDER, AIRCRAFT OXYGEN, LOW PRESSURE, NONSHATTERABLE

This document remains Inactive for New Design.



Comments, suggestions, or questions on this document should be addressed to: Oklahoma City Air Logistics Center/ENSDAA, 3001 Staff Drive, Tinker AFB, OK. 73145-3036 or emailed to af71@tinker.af.mil. Since contact information can change, you may want to verify the currency of this address information using ASSIST Online database at <http://assist.daps.dla.mil>.


MIL-DTL-5886H

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers low pressure storage cylinders for compressed gas with a working pressure of 450 psi for aerospace application.

1.2 Part or Identifying Number (PIN). PINs to be used for cylinders acquired to this specification are created as follows:



2. APPLICABLE DOCUMENTS

2.1 General. The documents listed in this section are specified in sections 3, 4, or 5 of this specification. This section does not include documents cited in other sections of this specification or recommended for additional information or as examples. While every effort has been made to ensure the completeness of these lists, document users are cautioned that they must meet all specified requirements of documents cited in sections 3, 4, or 5 of this specification, whether or not they are listed.

2.2 Government documents.

2.2.1 Specifications, and standards. The following specifications and standards form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

FEDERAL SPECIFICATIONS

BB-A-1034 - Compressed Air, Breathing

FEDERAL STANDARDS

FED-STD-595/13655 - Yellow, Gloss

COMMERCIAL ITEM DESCRIPTIONS

A-A-58092 - Tape, Antiseize, Polytetrafluorethylene

A-A-59503 - Nitrogen, Technical

MIL-DTL-5886H

DEPARTMENT OF DEFENSE SPECIFICATIONS

MIL-PRF-27210 - Oxygen, Aviator's Breathing, Liquid and Gas

(Copies of these documents are available online at <http://assist.daps.dla.mil/quicksearch/> or from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.3 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those cited in the solicitation or contract.

AEROSPACE INDUSTRIES ASSOCIATION of AMERICA, INC. (AIA)

AIA NAS847 - Caps and Plugs, Protective, Dust and Moisture Seal

(NA/NAS documents may be obtained at www.aia-aerospace.org/ or from Aerospace Industries Association 1000 Wilson Boulevard, Suite 1700 Arlington, VA 22209-3928.)

AMERICAN SOCIETY FOR QUALITY (ASQ)

ANSI/ASQ-Z1.4 - Sampling Procedures and Tables For Inspections By Attributes

(ASQC documents may be obtained at <http://asq.org> or addressed to the American Society for Quality P.O. Box 3005 Milwaukee, WI 53201-3005 or 600 North Plankinton Avenue, Milwaukee, Wisconsin, 53203, USA)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 7091 - Standard Practice for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to Ferrous Metals and Nonmagnetic, Nonconductive Coatings Applied to Non-Ferrous Metals

ASTM D 2247 - Testing Water Resistance of Coatings in 100% Relative Humidity

ASTM D 3359 - Standard Test Methods for Measuring Adhesion by Tape Test

ASTM E 8 - Standard Test Methods for Tension Testing of Metallic Materials

MIL-DTL-5886H

(ASTM documents may be obtained at <<http://www.astm.org>> or addressed to the American Society for Testing and Materials, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959)

AMERICAN WELDING SOCIETY (AWS)

AWS D17.1	Specification with Fusion Welding for Aerospace Applications
-----------	--

(AWS documents may be obtained at <<http://www.aws.org/w/a/>> or from American Welding Society, 550 N.W. LeJeune Road, Miami, Florida 33126.)

METALS AND ALLOYS IN THE UNIFIED NUMBERING SYSTEM (UNS)

S30403	-	Austenitic Cr-Ni Stainless Steel (Low Carbon)
S31600	-	Austenitic Cr-Ni Mo Stainless Steel

(SAE documents may be obtained at <<http://www.sae.org/>> or from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale PA 15096.)

SOCIETY OF AUTOMOTIVE ENGINEERS (SAE)

SAE ARP1176	-	Oxygen System and Component Cleaning and Packaging
SAE AS4863	-	Plug, Pipe, External Thread

(SAE documents may be obtained at <<http://www.sae.org/>> or from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale PA 15096.)

2.4 Order of Precedence. Unless otherwise noted herein or in the contract, in the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection in accordance with 4.3.

3.2 Materials. The materials used in all parts of the cylinders shall be in accordance with Metals And Alloys in The Unified Numbering System S30403, S31600, or stainless maraging steel conforming to the following chemical composition:

C	0.05 percent max
---	------------------

MIL-DTL-5886H

Mn	0.5 percent max
Si	0.3 percent max
P	0.03 percent max
S	0.02 percent max
Cr	14.0 – 18.0 percent
Ni	6.0 – 7.0 percent
Ti	0.70 – 0.95 percent
Fe	Remainder

3.2.1 Recycled, recovered, or environmentally preferable materials. Recycled, recovered, or environmentally preferable materials should be used to the maximum extent possible, provided that the material meets or exceeds the operational and maintenance requirements, and promotes economically advantageous life cycle costs.

3.3 Design and construction. The design and construction of the cylinders shall be in accordance with the applicable part number of Table IV and Figure 2, as specified in the contract or order (see 6.2).

3.3.1 Welding. Welding shall be performed in accordance with AWS D17.1, Class A (see 4.5.7).

3.3.2 Closures. Cylinders with two openings shall have one plug conforming to SAE-AS4863, CRES type 304 or 316, while the other opening shall be closed with a removable metal threaded plug or cap conforming to NAS847. The cylinder with one opening shall be closed with a removable metal threaded plug or cap conforming to NAS847 or a commercially equivalent metal plug or cap. These plugs or caps shall protect the threads and prevent entrance of foreign matter or moisture (see 4.5.1).

3.3.3 Forming by pressurization. Forming by pressurization up to 900 psi as a manufacturing process is allowed. The permanent volumetric expansion test (see 4.5.4) is a separate requirement.

3.4 Performance.

3.4.1 Cleanliness. The cylinders, when tested as specified (see 4.5.1), shall pass the requirements in Table I as specified (see 4.5.2).

3.4.2 Leakage. The cylinder shall show no evidence of leaks when tested as specified (see 4.5.3).

3.4.3 Permanent volumetric expansion. The cylinder shall have a permanent volumetric

MIL-DTL-5886H

expansion not greater than 10 percent of the total volumetric expansion when tested as specified (see 4.5.4).

3.4.4 Burst pressure. The cylinder shall burst at a pressure not less than 1,000 PSI when tested as specified (see 4.5.5).

3.4.4.1 Cyclic endurance. The cylinder shall hold pressure during the cyclic endurance portion of the test as specified (see 4.5.5.1).

3.4.5 Macrostructure defects. The cylinder shall show no evidence of abnormal segregation, pipes, cracks, carbide defects, seams or abnormal change in structure from the surface to the center when tested as specified (see 4.5.6).

3.4.6 Fragmentation. The cylinder shall remain in one piece and exhibit no evidence of shattering when tested as specified (see 4.5.8).

3.4.7 Physical properties. The cylinder material sample shall have an ultimate tensile strength that is not greater than 165,000 pounds per square inch and the elongation shall be not less than 12 percent when tested as specified (see 4.5.10).

3.5 Weight. The weight of the cylinders shall be not greater than the values specified in Table IV (see 4.5.1).

3.6 Exterior finish. The color of the finish shall be gloss yellow in accordance with color number 13655 of FED-STD-595. The .375 X .750 hexagonal, wrench-flat surfaces and the adjacent end of the bottle between the threads and these wrench flats may be left unpainted. The external finish of all cylinders shall have a paint thickness not less than 0.001 inches. The paint shall not crack, chip, or scale during normal service life or under extreme environmental conditions (see 4.5.9).

3.6.1 Humidity. The exterior finish when exposed to humidity shall not show evidence of corrosion, blistering, wrinkling or loss of adhesion (see 4.5.9.1).

3.6.2 Adhesion. The cured film coating shall have a classification not less than 4B as specified in ASTM-D2247 (see 4.5.9.2).

3.7 Identification of product. Decals, if used in lieu of paint, shall be approved by the procuring activity. The cylinders shall be marked for identification in accordance with MIL-STD-130 and shall include the following information (see 4.5.1) and the color shall be a durable dull (lusterless) black:

Oxygen Cylinder, Nonshatterable
M5886- *¹
MIL-DTL-5886
Volume & Pressure *²

MIL-DTL-5886H

Manufacturer's Part Number *¹
 Contract Number *¹
 Manufacturer's Name or Trademark *¹
 Date of Manufacture *¹

*¹ The manufacturer shall include the applicable information

*² Maximum fill pressure in psi and kg/cm²

3.7.1 Additional marking. The cylinders shall be permanently and legibly marked on the neck, spud, wrench flats, or fitting of the cylinder, in figures not less than 0.060 inch in height, with the date of manufacture or hydrostatic test (month and year), such as 7-79, for July 1979. Each cylinder shall also be marked by painting or decals in two places diametrically opposite each other with the following information: "BREATHING OXYGEN AV". The height of the letters shall be not less than 0.375 inch and the color shall be a durable dull (lusterless) black. Paint material used shall be as specified (see 3.7) and decals, if used in lieu of paint, shall be approved by the procuring activity.

4. VERIFICATION

4.1 Classification of inspections. The inspection requirements specified herein are classified as follows:

- a. First article inspection (see 4.3).
- b. Quality conformance inspection (see 4.4).

4.2 Inspection conditions.

4.2.1 Gas. Unless otherwise specified, the gas used in testing shall be oxygen conforming to MIL-PRF-27210, type I, nitrogen conforming to A-A-59503, type I, class 1, grade B, or air conforming to BB-A-1034.

4.2.2 Cleaning. Cleaning and cleanliness verification shall conform to SAE-ARP1176.

4.2.3 Temperature and pressure. Unless otherwise specified, tests shall be conducted at local ambient temperature and barometric pressure. The temperature and barometric pressure shall be recorded at the time of inspection. This information shall be available for computation of test data, when required, to normal temperature and pressure (NTP) conditions. Computations are not required unless required by contract. NTP conditions are 29.92 inches of mercury and 70°F (21.1°C). Test instruments shall be calibrated or adjusted according to their required usage in performing individual tests.

4.2.4 Antiseize tape. The male pipe threads of fittings installed in cylinders during tests shall be wrapped with antiseize tape conforming to A-A-58092 before being installed in the cylinders. The tape shall be applied according to instructions specified in A-A-58092. Tape shall be prevented from entering the inside of the fittings.

MIL-DTL-5886H

4.3 First article inspection. First article inspection shall consist of all the examinations and tests of this specification. Each sample shall be subjected to all the inspections and tests of this specification with the exception of the fragmentation test, the burst test, and the physical properties test as further explained (see 4.3.1).

4.3.1 First article samples. Unless otherwise specified, as soon as practicable after award of a contract or order, the manufacturer shall submit five sample cylinders of each MS part number specified in the contract or order to the first article tests specified, and two material samples cut from the walls in unaffected areas of two separate cylinders at the completion of the burst test specified (see 4.5.5) with additional samples to be made available if necessary. Three sample cylinders shall be used for the fragmentation test and the remaining two cylinders shall be used for the burst test. The samples shall be representative of the construction, workmanship, components, and materials to be used during production. When a contractor is in continuous production of these cylinders from contract to contract, submission of further first article samples on the new contract may be waived at the discretion of the procuring activity. Approval of the first article samples or the waiving of the first article inspection does not preclude the requirements of submitting to the quality conformance inspection. The first article samples shall be tested at a facility approved by the procuring activity (see 6.2). The first article samples shall be plainly identified by securely attached durable tags marked with the following information:

“Sample submitted by (name) (date) for first article inspection in accordance with MIL-DTL-5886 under contract no _____.”

The samples which are used for the first article inspection shall not be considered as part of the quantity to be delivered under contract. The tested samples shall be forwarded as directed by the procuring activity.

4.4 Conformance inspection. The conformance inspection shall consist of the following examinations and tests:

- a. Visual examination (4.5.1)
- b. Dimensions (4.5.1.1)
- c. Cleanliness (4.5.2)
- d. Leakage (4.5.3)
- e. Permanent volumetric expansion (4.5.4)
- f. Burst pressure (4.5.5)
- g. Macrostructure (deep acid etch) (4.5.6)
- h. Welding (radiographic inspection) (4.5.7)
- i. Physical properties (4.5.10)

Any defects detected by these tests may be corrected by rework. However, the macrostructure (see 4.5.6), radiographic inspection (see 4.5.7), and the physical properties (see 4.5.9) tests may reveal defects which are impracticable to rework. If the quantity of cylinders warrants the expense involved, the manufacturer may choose to accomplish the cyclic endurance test (see 4.5.5.1) to the particular cylinder or cylinders which fail (see 4.5.6, 4.5.7 or 4.5.9). Then the results of the failed test along with the results of the cyclic endurance test with appropriate

MIL-DTL-5886H

recommendations/remedies shall be submitted to the procuring activity for consideration.

4.4.1 Inspection lot.

4.4.1.1 Cylinder. An inspection lot size shall be expressed in units of cylinders of the same size, made under similar conditions and from the same materials and components. The sample unit shall be one cylinder.

4.4.1.2 Packaged lot. An inspection lot size shall be expressed in units of one fully prepared shipping container, containing cylinders fully prepared for delivery, made from essentially the same materials and components. The sample unit shall be one shipping container, containing cylinders fully prepared for delivery with the exception that it need not be sealed. When a manufacturer is in continuous production, the inspection lot or sample lot quantities shall be considered on a continuous run basis rather than on procurement order quantities. Breaks in production in excess of 1 year will require re-initializing the run or lot.

4.4.2 Sampling.

4.4.2.1 Sampling for test and examinations of cylinders. The sample size, acceptance criteria, tests, and examinations required for the cylinders shall be as specified in Table I. The sampling plan of this specification shall take precedence over the AWS D17.1 sampling plans required for weld or radiographic inspections.

4.4.2.1.1 Alternate sample size procedure. The purpose of this alternate sampling size procedure is to minimize the quantity of cylinders destroyed during quality conformance testing. Except for the determination of the quantity of samples to be tested, all other criteria listed in Table I shall still apply. If any units are rejected under this reduced sampling size procedures, the manufacturer shall use Table I sampling procedure for the remainder of the cylinders subject to conformance testing. This alternative is mandatory if the previous delivery requirements (see 4.4.2.1.2) have been met, otherwise, the standard sampling plan shall be used. To use the alternate procedure the cylinders must be manufactured under the same processes, from the same materials, be the same size and be manufactured at the same facilities. There is no requirement that production be continuous or that materials shall be delivered from the same lot. For simplicity, the variables shall be defined as follows:

- A4 - the number of cylinders delivered to the Department of Defense in the last 4 years.
- A3 - the number of cylinders delivered to the Department of Defense in the last 3 years.
- A2 - the number of cylinders delivered to the Department of Defense in the last 2 years.
- B - the current order quantity subject to quality conformance testing.
- C4 - the quantity previously tested in the past 4 years.
- C3 - the quantity previously tested in the past 3 years.
- C2 - the quantity previously tested in the past 2 years.
- D - the quantity to be tested on the current order.

4.4.2.1.1.1 Exception. If the procedure of 4.4.2.1.1 would cause more than 2% of

MIL-DTL-5886H

the cylinders to be destructively tested (see 4.5.5, 4.5.6 and 4.5.9), then the following procedure shall be used for these 3 tests only:

a. One out of each 50 cylinders manufactured, regardless of order quantity, the quantity to be delivered or the lot size shall be randomly selected and subjected to these tests (see 4.5.5, 4.5.6 and 4.5.9).

4.4.2.1.2 Computations.

a. Four year plan. The following formula applies if $A4+B>500$ cylinders and $A4>200$ cylinders:

$$\frac{C4 + D}{A4 + B} > 1\%$$

If a value of $D = 0$ causes the number on the left side of the equation to exceed 1%, then 1 cylinder shall be tested. Otherwise D shall be the smallest number that causes the left side of the equation to exceed 1%.

b. Three year plan. The following formula applies if $A3+B>90$ cylinders and $A3>40$ cylinders:

$$\frac{C3 + D}{A3 + B} > 2\%$$

If a value of $D = 0$ causes the number on the left side of the equation to exceed 2%, then 1 cylinder shall be tested. Otherwise D shall be the smallest number that causes the left side of the equation to exceed 2%.

c. The following formula applies if $A2+B>25$ cylinders and $A2>15$ cylinders:

$$\frac{C2 + D}{A2 + B} > 3\%$$

If a value of $D = 0$ causes the number on the left side of the equation to exceed 3%, then 1 cylinder shall be tested. Otherwise D shall be the smallest number that causes the left side of the equation to exceed 3%.

4.5 Methods of inspection.

4.5.1 Visual examination. The cylinders shall be examined to determine conformance to configuration of type specified, internal cleanliness, finish, color markings, and other requirements not covered by specific examinations or tests. Examination of the internal surface shall be accomplished by inserting an inspection light into the cylinder. The defects discovered by examination of product shall be classified in accordance with Table II.

MIL-DTL-5886H

4.5.1.1 Dimensions. The cylinder shall be checked dimensionally to determine conformance to Table IV and Figure 2.

4.5.2 Cleanliness. Cleaning shall be accomplished in accordance with SAE-ARP1176 (see 3.4.1).

4.5.3 Leakage. The cylinder shall be charged with a test gas (see 4.2.1) to a pressure of 500 psig. With this pressure maintained, the cylinder shall be submerged in water for 2 minutes. All parts of the cylinder shall be covered with not less than 1 inch of water. Constraints necessary to hold the cylinder in place shall not cover the welded seams of the pressure vessel. Cylinders with two openings shall be tested after the SAE-AS4863 plug has been installed and properly torqued. The cylinder shall pass the requirements specified (see 3.4.2). This test shall not apply to cylinders greater than 2200 cubic inches.

4.5.4 Permanent volumetric expansion. The permanent volumetric expansion shall be determined by hydrostatically testing the cylinder in a water jacket to a pressure of 750 psig for a period of not less than 1 minute. The expansion shall be determined to an accuracy of 1 percent or 0.1 of a cubic centimeter, and shall be recorded in cubic centimeters. The cylinder shall meet the requirements specified (see 3.4.3).

4.5.5 Burst pressure. The cylinders shall be hydrostatically pressurized for 3 minutes to within 95 percent of the pressure specified (see 3.4.4). Pressure shall be applied at the rate of $25,000 \pm 10,000$ psi per minute. The cylinders shall then be tested hydrostatically to destruction and the bursting pressure recorded. The cylinders shall pass the requirements specified (see 3.4.4). At the supplier's option a cylinder tested for cyclic endurance (see 4.5.5.1) may be used for this test.

4.5.5.1 Cyclic endurance. The setup for this test is identical to that used during the burst test (see 4.5.5). The test cylinder shall be hydrostatically pressurized to the pressure specified ± 50 psi (see 3.4.4). Pressure shall be applied at a rate of $25,000 \pm 10,000$ psi per minute for 1000 cycles. The pressure shall drop below 50 psig each cycle. After completion of this test, the cylinder shall then be subjected to the burst pressure test (see 4.5.5). The cylinder shall pass the requirements (see 3.4.4.1).

4.5.6 Macrostructure (deep acid etch). Longitudinal sections from the cylinder, taken from the burst cylinder (see 4.5.4), shall be etched in an aqueous solution containing 50 percent hydrochloric acid by volume and maintained at a temperature of approximately 160 F (71 C) for sufficient time to show the presence of defects. The sections shall then be visually examined by a metallographist and shall pass the requirements specified (see 3.4.5).

4.5.7 Welding (radiographic inspection). The longitudinal and circumferential sections of cylinders shall pass the inspection requirements of AWS D17.1. This shall be done prior to the installation of any strapping which otherwise would cover the weld. The welds of each end fitting (if required) and the welds used to attach reinforcing strapping shall not require radiographic inspection. The welded sections shall pass the requirements specified (see 3.3.1).

MIL-DTL-5886H

4.5.8 Fragmentation resistance. Oxygen conforming to MIL-PRF-27210, type I shall be the charging gas for oxygen cylinders. Cylinders shall be subjected to gunfire under the following conditions:

- a. The cylinder shall be charged to rated pressure at gun range ambient air temperature.
- b. The cylinder may be supported but not constrained.
- c. The ammunition shall be .50 caliber M-2, armor piercing, with muzzle velocity of $2,800 \pm 100$ feet per second (853 ± 30 m/s).
- d. The range shall be 50 yards (45.7 m) maximum.
- e. The various cylinders taken for test shall be tested, each progressively, in a different position, as follows:
 - (1) With the longitudinal axis of the cylinder normal to line of fire.
 - (2) With the longitudinal axis of the cylinder 45° degrees (.785 rad) from normal toward the gun position.
 - (3) With the longitudinal axis of the cylinder parallel to the line of fire with inlet port face away from the gun position.
- f. All shots shall be tumbled utilizing the method shown in Figure 1.
- g. The tumbled projectile shall have a minimum velocity of 2,600 ft/sec (792 m/s) at the point of impact with the cylinder.
- h. The minimum size entry hole made by the tumbled projectile shall be 0.50 inch by 1.50 inch (13mm by 39mm).
- i. Verify that the projectile trajectory and tumble are satisfactory. This may be determined by the location and visual appearance of a hole made by the passage of the projectile through vertically suspended sheets of paper at the target area.

The cylinder shall pass the requirements specified (see 3.4.6).

4.5.9 Exterior finish. Paint thickness shall be verified in accordance with ASTM D 7091, method B, to determine the total thickness of the film coating applied to the cylinder. The minimum allowable thickness shall be as specified (see 3.6).

4.5.9.1 Humidity. Humidity resistance shall be verified using ASTM D 2247. Cylinders shall be exposed to $120 \pm 5^{\circ}$ F and 100% relative humidity for 7 days before performing the test. The film coating after the test shall be as specified (see 3.6.1).

4.5.9.2 Adhesion. Adhesion shall be verified in accordance with ASTM D 3359, method B, and have a classification of 4B (see 3.6.2).

4.5.10 Physical properties. Material samples taken from burst cylinder (see 4.5.5), as specified (see 4.3.1) and Table I shall be tested for tensile strength and elongation in accordance ASTM E8. The samples shall meet the requirements specified (see 3.4.7).

MIL-DTL-5886H

5. PACKAGING.

5.1 Packaging. For acquisition purposes, the packaging requirements shall be as specified in the contract or order (see 6.2). When packaging of materiel is to be performed by DoD or in-house contractor personnel, these personnel need to contact the responsible packaging activity to ascertain packaging requirements. Packaging requirements are maintained by the Inventory Control Point's packaging activities within the Military Service or Defense Agency, or within the military service's system commands. Packaging data retrieval is available from the managing Military Department's or Defense Agency's automated packaging files, CD-ROM products, or by contacting the responsible packaging activity.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The cylinders covered by this specification are intended for use in storing aviator's breathing oxygen in aircraft having low pressure oxygen systems.

6.2 Acquisition requirements. Acquisition documents must specify the following:

- a. Title, number, and date of this specification.
- b. Applicable part number (see 3.3).
- c. Where the samples should be delivered (see 4.3.1).
- d. When first article is required. Cylinders subjected to destructive tests (see Table I) should not be shipped or considered as part of the contract or order.
- e. Additional marking, Oxygen Components – All oil, grease, shop residue, or other contaminants have been removed. Do not open until ready for use.

6.3 Supersession data. This specification supersedes the following specifications:

Type A-6, MIL-C-5435A, dated 21 May 1951
 Type B-3, MIL-C-5436A, dated 21 May 1951
 Type D-2, MIL-C-5887 (USAF), dated 21 February 1951
 Type F-1, MIL-C-5888 (USAF), dated 21 February 1951
 Type F-2, MIL-C-5889 (USAF), dated 21 February 1951
 Type G-1, MIL-C-5890 (USAF), dated 21 February 1951
 Type J-1, MIL-C-5891 (ASG) dated 10 April 1953

6.4 Subject term (key word) listing.

Burst pressure
 Cleanliness
 Closures
 Cyclic endurance
 Forming by pressurization

MIL-DTL-5886H

Fragmentation
Leakage
Macrostructure
Radiographic

6.5 International standardization agreement. This specification implements international standardization agreement STANAG 3056. When amendment, revision, or cancellation of this specification is proposed, the preparing activity must coordinate the action with the U.S. National Point of Contact for the international standardization agreement, as identified in the ASSIST database at <http://assist.daps.dla.mil>.

6.6 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

MIL-DTL-5886H

TABLE I. Sample size, acceptance criteria, tests and examination of cylinders.

Inspection	Method paragraph	Sample size	Acceptance criteria
Visual examination (see classification of defects)	4.5.1	Every cylinder for critical defects. 1/ Inspection level S-2 for minor defects	Reject all units with any. critical defects. Acceptance number zero, rejection number 1 for minor defects.
Dimensions	4.5.1.1	1/ Inspection level S-2	Acceptance number zero, rejection number 1.
Cleanliness	4.5.2	1/ Inspection level S-2	Acceptance number zero, rejection number 1
Leakage	4.5.3	Every cylinder	Reject all defective units.
Permanent volumetric expansion	4.5.4	Every cylinder	Reject all defective units.
Burst pressure 2/	4.5.5	1/ Inspection level S-2	Acceptance number zero, rejection number 1.
Macrostructure	4.5.6	1/ Inspection level S-2 3/	Acceptance number zero, rejection number 1.
Radiographic inspection	4.5.7	1/ Inspection level S-2	Acceptance number zero, rejection number 1.
Physical properties	4.5.10	1/ Inspection level S-2 4/	Acceptance number zero, rejection number 1.

1/ The sample size shall be based only on the applicable sample size code letter corresponding to the specified inspection level of ASQ-Z1.4.

2/ This is a destructive test (see 6.2).

3/ The burst pressure sample may be used. However, the longitudinal section shall be taken at locations not affected by the burst point.

4/ One sample from unaffected area of burst pressure sample unit.

MIL-DTL-5886H

TABLE II. Classification of defects for visual examination of the cylinder.

Defects	Minor	Critical
Incorrect outlet configuration		X
Incorrect or defective threads		X
Incorrect, incomplete, or faulty finish	X	
Flaw in the material		X
Incorrect or incomplete marking	X	
Incorrect color	X	
Abnormally distorted or nonuniform weld		X
Loose particles inside the cylinder		X
Rust or scale		X
Irregularities in the internal surface greater than 1/16 inch		X
Existence of any foreign material, solid or liquid		X

TABLE III. List of defects for preparation for delivery.

Item	Defects
Exterior and interior markings	Missing, incorrect, incomplete, illegible, improper size, location, sequence; or method of application; markings not the same on the interior and exterior containers.
Packaging and packing materials	Any non-conforming component; any component missing, damaged, or otherwise defective.
Workmanship	Inadequate application of the components such as incomplete closure of the unit package, intermediate package, container flaps, loose strapping's, etc.; bulging or distortion of the containers.
Exterior and interior weight or content	Number per container is more or less than required; gross or net weight exceeds the requirements

MIL-DTL-5886H

TABLE IV. Cylinder characteristics

PIN (Superseded Type)	INTERNAL VOLUME IN ³ (MIN)	WEIGHT POUNDS (MAX)	LENGTH INCHES (MAX)	DIAMETER INCHES (MAX)	NUMBER OF OPENINGS
M5886-1 (A-6)	280	3.75	14.500	5.750	1
M5886-2 (B-3)	280	3.75	15.000	5.750	2
M5886-3 (D-2)	500	5.75	23.500	5.750	2
M5886-4 (F-1)	1000	10.00	18.000	10.125	2
M5886-5 (F-2)	1000	11.00	44.500	5.750	2
M5886-6 (G-1)	2100	18.00	24.500	12.562	2
M5886-7 (J-1)	18000	155.00	49.250	24.500	2

MIL-DTL-5886H





FIGURE 1. Projectile tumbling method

MIL-DTL-5886H




- 1/ Lumber, 2 x 4 - normal size
- 2/ Board, plywood - grade A-A, exterior, 3 ply.
- 3/ Sheet, rubber-styrene-butadiene (RSB) 55 +/-5 durometer (shore A). Pad shall be cemented to entire length of tumbling board using a commercial contact cement.
- 4/ Tumbling board may be moved in the support rails for repeated firings.
- 5/ Mounting holes may be used to support tumbling board as required to ensure the board is rigidly mounted.

NOTES:

1. Dimensions are in inches.
2. Tolerance: decimals +/- 0.1.

FIGURE 1. Projectile tumbling method (continued)

MIL-DTL-5886H



(Double outlet design shown)

Figure 2. Cylinder characteristics

MIL-DTL-5886H

Custodians:

Air Force - 71

Army - AV

Navy - AS

Preparing activity

Air Force - 71

(Project 1660-2008-003)

Reviewer activities:

Air Force - 11

DLA - GS

NOTE: The activities listed above were interested in this document as of the date of this document. Since organizations and responsibilities can change, you should verify the currency of the information above using the ASSIST database at <http://assist.daps.dla.mil/>.