

Table 1. Electrochemical performance.

Sample	Temp (C)	Capacity (mAh/g)	D (cm ² /s)
Li ₂ FeTiO ₄	700 C	121.3 mAh/g	1.096 x 10 ⁻¹² cm ² /s