

Table 2. LFTO electrochemical results.

Sample	Temperature (degC)	Capacity (mAh/g)	Resistance (Ohm)	Diffusion coefficient (cm ² /s)
LFTO-600	600 degC	67.0 mAh/g	1258.6 Ohm	1.096 x 10 ⁻¹² cm ² /s
LFTO-700	700 degC	121.3 mAh/g	1258.6 Ohm	1.096 x 10 ⁻¹² cm ² /s
LFTO-800	800 degC	58.7 mAh/g	1258.6 Ohm	1.096 x 10 ⁻¹² cm ² /s