Table 1. Electrochemical performance.

Sample	Temp (C)	Capacity (mAh/g)	D (cm2/s)
Li2FeTiO4	700 C	121.3 mAh/g	1.096 x 10-12 cm2/s