

Article: 30,1
Nominal count: 30 Nec (f/y:1)
Force limit: not used
Comments: Autocoro-1

Speed: 5000 mm/min
Elong. limit: not used

N. samples: 5 each 10 tests
Init. lenght: 500 mm
Customer: KHIVA TEXTIL

Material:
Pretension: 0.5 cN/tex

Material type: Weaving

Bobbin	Machine's name	Count Abs. [Nec]	Out of lim.	Time [sec]	TEN. Min. [RKM]	TEN. Avg. [RKM]	TEN. Max. [RKM]	TEN. CV%	TEN. Q95%	TEN. Q99%	TEN. Min. [cN/tex]	TEN. Avg. [cN/tex]	TEN. Max. [cN/tex]	TEN. CV%	TEN. Q95%	TEN. Q99%
1/5	571	0.00	0	0.42	9.14	10.52	12.19	8.76	0.57	0.75	8.97	10.31	11.96	8.76	0.56	0.74
2/5	572	0.00	0	0.38	9.09	10.70	11.63	8.10	0.54	0.71	8.92	10.49	11.41	8.10	0.53	0.69
3/5	573	0.00	0	0.43	8.53	11.04	13.11	13.94	0.95	1.26	8.37	10.83	12.85	13.94	0.94	1.23
4/5	574	0.00	0	0.35	8.79	10.33	11.23	7.09	0.45	0.60	8.62	10.13	11.01	7.09	0.45	0.59
5/5	575	0.00	0	0.36	10.21	11.11	11.94	6.04	0.42	0.55	10.01	10.89	11.71	6.04	0.41	0.54
Min.				0.35	8.53	10.33	11.23	6.04	0.42	0.55	8.37	10.13	11.01	6.04	0.41	0.54
Avg.				0.39	9.15	10.74	12.02	8.79	0.59	0.77	8.98	10.53	11.79	8.79	0.58	0.76
Max.				0.43	10.21	11.11	13.11	13.94	0.95	1.26	10.01	10.89	12.85	13.94	0.94	1.23
CV%				9.40	7.00	3.11	5.88	34.83	36.29	36.62	6.97	3.11	5.86	34.83	36.53	36.34
Q95%				0.03	0.56	0.29	0.62	2.68	0.19	0.25	0.55	0.29	0.61	2.68	0.19	0.24
Q99%				0.04	0.74	0.38	0.82	3.53	0.25	0.33	0.72	0.38	0.80	3.53	0.24	0.32

Bobbin	Machine's name	Count Abs. [Nec]	Out of lim.	Time [sec]	FORCE Min. [gf]	FORCE Avg. [gf]	FORCE Max. [gf]	FORCE CV%	FORCE Q95%	FORCE Q99%	ELONGA. Min. [%]	ELONGA. Avg. [%]	ELONGA. Max. [%]	ELONGA. CV%	ELONGA. Q95%	ELONGA. Q99%
1/5	571	0.00	0	0.42	180.00	207.00	240.00	8.76	11.24	14.79	4.52	5.11	5.79	6.91	0.22	0.29
2/5	572	0.00	0	0.38	179.00	210.60	229.00	8.10	10.57	13.92	4.40	5.05	5.72	7.98	0.25	0.33
3/5	573	0.00	0	0.43	168.00	217.40	258.00	13.94	18.78	24.72	3.59	4.82	5.45	13.16	0.39	0.52
4/5	574	0.00	0	0.35	173.00	203.40	221.00	7.09	8.94	11.77	3.97	4.71	5.01	6.03	0.18	0.23
5/5	575	0.00	0	0.36	201.00	218.70	235.00	6.04	8.18	10.77	4.30	4.67	5.10	5.99	0.17	0.23
Min.				0.35	168.00	203.40	221.00	6.04	8.18	10.77	3.59	4.67	5.01	5.99	0.17	0.23
Avg.				0.39	180.20	211.42	236.60	8.79	11.54	15.19	4.16	4.87	5.41	8.01	0.24	0.32
Max.				0.43	201.00	218.70	258.00	13.94	18.78	24.72	4.52	5.11	5.79	13.16	0.39	0.52
CV%				9.40	6.99	3.11	5.88	34.83	36.63	36.62	9.06	4.08	6.52	37.30	36.66	37.37
Q95%				0.03	11.04	5.77	12.19	2.68	3.71	4.88	0.33	0.17	0.31	2.62	0.08	0.10
Q99%				0.04	14.54	7.59	16.04	3.53	4.88	6.42	0.43	0.23	0.41	3.45	0.10	0.14

Article: 30,1
Nominal count: 30 Nec (f/y:1)
Force limit: not used
Comments: Autocoro-1

Speed: 5000 mm/min
Elong. limit: not used

N. samples: 5 each 10 tests
Init. lenght: 500 mm
Customer: KHIVA TEXTIL

Material:
Pretension: 0.5 cN/tex

Material type: Weaving

