



KIRLOSKAR CHILLERS PRIVATE LIMITED

A Kirloskar Group Company

Enriching Lives

ENGINEERING SPECIFICATIONS

Document Name: Etch Primer Specifications & Painting Procedure		
Document No: ESP-15-16-103	Revision: 00	Date: 10/06/15
Prepared By: SNM	Approved By: SSN	Sheet: 1 OF 2

Etch Primer Specifications

Etch primer specification shall be as per IS: 5666 -1970.

Painting Procedure

1. Surface preparation:

Round off all rough welds, sharp edges and remove weld spatter.

Remove all dust, grease, oil and other contaminants, rust, mill scale, oxide deposits and old paint on surfaces by wire brush / sand paper.

All surfaces to be painted shall be properly degreased with thinner.

2. Mixing of base & accelerator components:

Base component & accelerator shall be stirred thoroughly.

Mixing — when the thoroughly stirred base and the accelerator components are mixed in equal proportions by volume or mixing proportion shall be verified from paint manufacturer.

The resulting paint, after thorough stirring, shall be smooth and uniform and suitable for application by the appropriate method.



Enriching Lives

KIRLOSKAR CHILLERS PRIVATE LIMITED

A Kirloskar Group Company

3. Method of applying:

1. Conventional Spray
2. Brush/Roller (Recommended only for spot patching)

4. Thickness of coat:

Recommended thickness of Etch primer is 10~15 micron, refer individual component drawing for actual thickness.

5. Precaution:

Do not apply at temperatures below 5°C.

Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dew point.

Excessive dry film thickness should be avoided as this may result in delamination.

6. Drying:

Environment –

Temperature - 25° C

Humidity - 50%

Drying time –

120 Minutes (minimum) to full cure.