



KIRLOSKAR CHILLERS PRIVATE LIMITED

A Kirloskar Group Company

Enriching Lives

ENGINEERING SPECIFICATIONS

Description: Paint Specification & Painting Procedure.		
Document No: ESP-20-21-001	Revision: R00	Date: 01/09/2020
Prepared By: PSM	Approved By: SNM	Sheet: 1 of 3

1. Paint Specification:

1.1 Etch Primer – (Note – 2)

Types – Etch Primer Z/C Yellow.

Shade – Z/C Yellow

Finish – Matt & smooth

Pot life @ 27°C: 3-4 hrs.

Thinner – Suitable.

Make – Pioneer Coats. (Note – 4)

Standard - (IS: 5666)

1.2 Epoxy Primer -

Epoxy types – Cipoxy 23 Epoxy Zinc Phosphate Primer.

Shade - Grey

Finish – Matt

Pot life @ 27°C: 2-3 hrs.

Thinner – PUT 508

Make – Cipy. (Note – 4)

1.3 Finish Paint (Top Coat) –

FPG 700 is a two component, cold cured, aromatic polyurethane pigmented glossy coating.

Shade – RAL 7035

Finish – Smooth glossy



KIRLOSKAR CHILLERS PRIVATE LIMITED

A Kirloskar Group Company

Enriching Lives

Description: Paint Specification & Painting Procedure.		
Document No: ESP-20-21-001	Revision: R00	Date: 01/09/2020
Prepared By: PSM	Approved By: SNM	Sheet: 2 of 3

Pot life @ 27°C: 2-3 hrs.

Thinner – PUT 509

Make – Cipy. (Note – 4)

2. Painting Procedure (Direction to Use)

2.1 Surface preparation

Refer notes provided on the individual part / assembly drawings.

2.2 Painting Procedure – Etch Primer (Note -2)

Mixing ratio with Etch primer and hardener – 1:1 by volume.

The resulting paint, after thorough stirring, shall be smooth and uniform and suitable for application by the appropriate method. Applying using Conventional Spray & Brush/Roller (Recommended only for spot patching) Recommended thickness of Etch primer is 10~15 micron, refer individual component drawing for actual thickness. Do not apply at temperatures below 5°C, Do not apply at relative humidity above 85% or when the surface is less than 3°C above the dew point and Excessive dry film thickness should be avoided as this may result in delamination. Drying at 25°C, humidity – 50% and 120 minutes (Minimum) to full cure.

2.3 Painting Procedure – Epoxy Primer.

Mixing ratio for Cipoxy 23 Primer (Resin: Hardener) – 4:1 by volume.

Stir resin thoroughly and then mix four parts of resin with one part of hardener by volume. Mix in small portions enough to last for 2 hours or less.



KIRLOSKAR CHILLERS PRIVATE LIMITED

A Kirloskar Group Company

Enriching Lives

Description: Paint Specification & Painting Procedure.		
Document No: ESP-20-21-001	Revision: R00	Date: 01/09/2020
Prepared By: PSM	Approved By: SNM	Sheet: 3 of 3

Apply by brush or spray and allow to cure for 6-7 hours & hard dry time 24 hours. The primed surface is now ready to receive epoxy intermediate or top coat. Dry Film Thickness (DFT) – 50 ~ 60 microns.

2.4 Painting procedure – Finish Paint (Top Coat)

Mixing ratio for FPG 700 (Top Coat) – 10:1 by volume.

Ensure that the primed surface is totally dry, free from dust and other foreign particles. Mix FPG 700 resin and FPG 700 hardener in 10:1 ratio by volume. Agitate the mixture for 2-3 minutes. Apply by spray, airless or air assisted. Allow to cure for 3-4 hours. Apply second coat & hard dry time 24 hours. Ensure that the dry film thickness achieved is 70~80 microns all over. If the dry film thickness is less than 70 micron, one more coat of finish paint shall applied where ever required. Again recheck the DFT to ensure required paint thicknesses is achieved.

Notes –

1. This specification is applicable for all painted items used in Water cooled and Air cooled chillers.
2. Etch primer shall be applicable for base frame and sheet metal components of Air cooled chiller. The requirement of etch primer shall be given on the respective component drawings.
3. The requirement of primer and painting is given on the individual part / assembly drawings.
4. DO NOT USE other make paint than specified.