USE OF AGRICULTURAL WASTE AS ADSORBENT

A Project Report

Submitted in partial fulfilment for the award of degree of

BACHELOR OF TECHNOLOGY

In

CHEMICAL ENGINEERING

By

ANGADI ABHIRAM	**23011A0820**
POLU HIMAVANTH	**23011A0827**
MAHANKALI KRISHNAPRASAD	**23011A0835**
KATHI AJAY	**23011A0838**
MOHAMMED YOUSUF EBTESAM	**24015A0811**

UNDER THE HONORED GUIDANCE OF
Dr. V NAGAMANI
Assistant Professor

JAWAHARLAL NEHRU TECHNOLOGICAL UNIVERSITY, HYDERABAD

UNIVERSITY COLLEGE OF ENGINEERING SCIENCE G TECHNOLOGY

HYDERABAD, Kukatpally-500085

JAWAHARLAL NEHRU TECHNOLOGICAL UNIVERSITY, HYDERABAD

UNIVERSITY COLLEGE OF ENGINEERING SCIENCE G TECHNOLOGY

HYDERABAD, Kukatpally-500085

CERTIFICATE

A project report on **"USE OF AGRICULTURAL WASTE AS ADSORBENT"** done by **ANGADI ABHIRAM (23011A0820), POLU HIMAVANTH (23011A0827), MAHANKALI KRISHNAPRASAD (23011A0835), KATHI AJAY (23011A0838), MOHAMMED YOUSUF EBTESAM (24015A0811),** submitted to the faculty of CHEMICAL ENGINEERING, in partial fulfilment of the requirements for the Degree of **BACHELOR OF TECHNOLOGY** with specialization in **CHEMICAL ENGINEERING** from Jawaharlal Nehru Technological University Hyderabad University College of Engineering Science and Technology Hyderabad.

Signature of Guide:

Dr.V.Nagamani

Assistant Professor

Department of Chemical Engineering

JNTUHUCESTH

JAWAHARLAL NEHRU TECHNOLOGICAL UNIVERSITY, HYDERABAD

UNIVERSITY COLLEGE OF ENGINEERING SCIENCE G TECHNOLOGY

HYDERABAD, Kukatpally-500085

A project report on "USE OF AGRICULTURAL WASTE AS ADSORBENT" **done by ANGADI ABHIRAM (23011A0820), POLU HIMAVANTH (23011A0827), MAHANKALI KRISHNAPRASAD (23011A0835), KATHI AJAY (23011A0838), MOHAMMED YOUSUF EBTESAM (24015A0811), submitted to the faculty of CHEMICAL ENGINEERING, in partial fulfilment of the requirements for the Degree of BACHELOR OF TECHNOLOGY with specialization in CHEMICAL ENGINEERING from Jawaharlal Nehru Technological University Hyderabad University College of Engineering Science and Technology Hyderabad.**

Signature of HOD:

Dr. K. Vidya

Associate Professor and Head of Department

Department of Chemical Engineering

JNTUHUCEHSTH

ACKNOWLEDGEMENTS

We would like to express our deep sense of gratitude to **Dr. G. VENKATA NARSIMHA REDDY** (Principal) and all Assistant Professors of Department of Chemical Engineering, Hyderabad, who gave us opportunity to do this project. Then we would like to express our deep sense of gratitude to **Dr. K. VIDYA** (Professor and Head of Chemical Engineering Department) who gave us an excellent opportunity to do this project.

Then we would like to express our deep sense of gratitude to **Dr. V. NAGAMANI** (Assistant Professor of Chemical Engineering Department) who gave us an excellent guidance to do this project .

We are grateful to **Dr. KOTAIAH NAIK, Dr. CH. RAMESH,** and **MRS. P SOWMYA** whose constant encouragement and support made our project successful.

ANGADI ABHIRAM (23011A0820)

POLU HIMAVANTH (23011A0827)

MAHANKALI KRISHNAPRASAD (23011A0829)

KATHI AJAY (23011A0838)

MOHAMMED YOUSUF EBTESAM (24015A0812)

DECLARATION

We here by declare that the project report entitled **"Use of agricultural waste as adsorbent"** is submitted in the Department of Chemical Engineering, JNTUH-UCESTH in partial fulfilment of the award of Bachelor of Technology in Chemical.

Also, we declare that matter embedded in this project report has not been submitted for the award of any degree of any other Institution or University.

Date:

Place: HYDERABAD

ANGADI ABHIRAM (Roll No: 23011A0820)

POLU HIMAVANTH (Roll No: 23011A0827)

MAHANKALI KRISHNAPRASAD (Roll No: 23011A0835)

KATHI AJAY (Roll No: 23011A0838)

MOHAMMED YOUSUF EBTESAM (Roll No: 24015A0811)

ABSTRACT

This project explores the potential of agricultural waste as a low-cost, eco-friendly adsorbent for removing pollutants from water and air. Agricultural residues such as rice husk, sugarcane bagasse, coconut shells, and corn cobs are investigated for their adsorption efficiency after physical or chemical activation.

The report evaluates the adsorption mechanisms involved, the effect of various process parameters, and the environmental implications of using biomass-derived adsorbents. Characterization techniques such as FTIR and SEM surface analysis are used to analyze the structural and surface properties of the prepared adsorbents.

This study aims to contribute to sustainable waste management and pollution control by converting agricultural by-products into valuable materials for environmental remediation.

CONTENTS

1. Introduction
1.1 Agricultural Waste as a Resource
1.2 Adsorption Mechanism and Pollutant Removal
1.3 Advantages of Biomass-Based Adsorbents
1.4 Limitations and Challenges

2. Objectives

3. Literature Review
3.1 Overview of Adsorption Principles
    3.1.1 Physisorption
    3.1.2 Chemisoprtion
3.2 Common Agricultural Wastes Used as Adsorbents
3.3 Surface Modification and Activation Techniques
    3.3.1 Physical Activation
    3.3.2 Chemical Activation
    3.3.3 Microwave and Ultrasound Treatments
    3.3.4 Functional Group Modification
    3.3.5 Surface Oxidation
    3.3.6 Composite Formation
3.4 Isotherm and Kinetic Models
    3.4.1 Adsorption Isotherms
    3.4.1.1 Langmuir Isotherm
    3.4.1.2 Frendulich Isotherm
    3.4.2 Adsorption Kinetics
    3.4.2.1 Pseudo-First-Order Model
    3.4.2.2 Pseudo-Second-Order Model
    3.4.3 Intraparticle Diffusion Model
3.5 Environmental Impact and Waste Valorization

4. Methodology
4.1 Selection and Collection of Agricultural Waste
4.2 Pre-treatment and Activation of Adsorbent
    4.2.1 Pre-treatment
    4.2.2 Activation
4.3 Analytical Techniques (UV-Vis, FTIR, SEM)
    4.3.1 UV-Vis Spectroscopy (Ultraviolet-Visible Spectroscopy)
    4.3.2. FTIR (Fourier Transform Infrared Spectroscopy)
    4.3.3. SEM (Scanning Electron Microscopy)

5. Results and Discussion
5.1 Effect of pH, Temperature, and Contact Time
    5.1.1 Effect of pH
    5.1.2 Effect of Temperature
    5.1.3 Effect of Contact Time
5.2 Adsorption Capacity and Efficiency
    5.2.1 Adsorption Capacity (q_e)
    5.2.2 Removal Efficiency (%)
    5.2.3 Comparison among Agricultural Wastes
    5.2.4 Influencing Factors
5.3 Comparison with Conventional Adsorbents

5.3.1 Adsorption Capacity and Efficiency
5.3.2 Cost-Effectiveness
5.3.3 Environmental Implications/Sustainability
5.3.4 Regeneration and Reusability
5.3.5 Selectivity
5.3.6 Practical Application and Scalability

6. Characterization of Adsorbents
6.1 BET Surface Area and Pore Volume
6.2 FTIR Functional Group Analysis
6.3 SEM Morphology Studies
6.4 Thermal Stability (TGA/DSC)

7. Applications of Agricultural Waste-Based Adsorbents
7.1 Heavy Metal Removal (e.g., Pb^{2+}, Cd^{2+}, Cr^{6+})
7.2 Dye and Organic Pollutant Adsorption
7.3 Use in Air Purification and Gas Capture
7.4 Potential in Industrial Wastewater Treatment

8. Environmental and Economic Considerations
8.1 Waste Minimization and Resource Recovery
8.2 Cost Comparison with Commercial Adsorbents
8.3 Life Cycle Analysis and Environmental Benefits
8.4 Opportunities for Rural and Agro-based Economies

9. Conclusion

10. References

1. Introduction

1.1. Agricultural Waste as a Resource

Agricultural waste, generated in vast quantities across the globe, includes residues from crops such as rice husks, wheat straw, sugarcane bagasse, coconut shells, corn cobs, and peanut shells. Traditionally considered a disposal problem, these biomass materials are now gaining recognition as valuable resources for various industrial and environmental applications.

One of the most promising uses of agricultural waste is in the field of environmental remediation, particularly as low-cost and sustainable adsorbents for removing pollutants from water and air. These materials are naturally rich in cellulose, hemicellulose, lignin, and other functional groups (e.g., hydroxyl, carboxyl, phenolic), which provide active sites for adsorption. With appropriate physical or chemical activation, their surface area, porosity, and adsorption capacity can be significantly enhanced.

Utilizing agricultural residues not only helps in waste valorization but also reduces dependence on expensive conventional adsorbents like activated carbon. Moreover, this approach supports circular economy principles, promoting sustainability, cost-effectiveness, and environmental protection.

In rural and agro-based economies, transforming agricultural by-products into value-added adsorbents provides an avenue for income generation, technological development, and improved waste management practices. Thus, agricultural waste, once viewed as an environmental burden, is now a viable and eco-friendly solution in the fight against pollution.

1.2. Adsorption Mechanism and Pollutant Removal

Adsorption is a surface-based separation process in which molecules of a solute (adsorbate) adhere to the surface of a solid material (adsorbent). It is widely applied for removing contaminants such as heavy metals, dyes, pesticides, pharmaceuticals, and organic pollutants from water and air. The mechanism of adsorption depends on the nature of interactions between the adsorbent and the adsorbate, which can be classified broadly into physisorption and chemisorption.

Physisorption involves weak van der Waals forces and is typically reversible. It occurs at lower temperatures and does not involve the formation of chemical bonds. Chemisorption, on the other hand, involves stronger covalent or ionic bonding, often resulting in irreversible adsorption. This type is more specific and occurs over longer time scales and at higher temperatures.

Agricultural waste-based adsorbents are particularly effective due to the presence of various functional groups like hydroxyl, carboxyl, and carbonyl on their surfaces. These groups actively bind with pollutant molecules through mechanisms such as hydrogen bonding, ion exchange, electrostatic attraction, and complexation.

Pollutant removal using adsorption is influenced by several factors, including:

* pH of the solution, which affects ionization of both the adsorbate and the adsorbent surface;
* contact time, determining equilibrium achievement;

* temperature, which influences the kinetic energy of molecules;
* initial concentration of pollutants;
* and surface area and porosity of the adsorbent.

Understanding the underlying mechanisms of adsorption enables the design of more efficient, targeted, and sustainable treatment processes. When applied correctly, adsorption using agricultural waste can be a cost-effective and environmentally friendly alternative for pollutant removal in both rural and industrial settings.

1.3. Advantages of Biomass-Based Adsorbents

Biomass-based adsorbents, particularly those derived from agricultural waste, offer several compelling advantages over conventional adsorbents like activated carbon, synthetic resins, or zeolites. Their growing use in environmental applications is driven by both performance efficiency and sustainability.

* **Cost-effectiveness**
  Agricultural wastes are abundantly available and often treated as low-value or disposable by-products. Utilizing them as adsorbents significantly reduces raw material costs, making pollution control more accessible, especially in developing regions.
* **Environmental Sustainability**
  Biomass-derived adsorbents are renewable, biodegradable, and non-toxic. Their use promotes waste valorization, converting agro-residues into valuable materials instead of contributing to landfill or open burning, which causes environmental degradation.
* **High Adsorption Potential**
  Many types of agricultural waste naturally contain cellulose, hemicellulose, lignin, and various functional groups (e.g., hydroxyl, carboxylic, phenolic) that are effective in adsorbing pollutants through mechanisms like ion exchange, hydrogen bonding, and complexation.
* **Modifiability and Functionalization**
  Biomass materials can be easily modified through physical (e.g., thermal activation) or chemical treatments (e.g., acid/base treatment, impregnation with metals), which greatly enhance their surface area, porosity, and active sites, thereby improving adsorption efficiency.
* **Low Energy Demand for Preparation**
  The preparation of biomass adsorbents usually requires relatively low processing temperatures and simpler equipment compared to the production of activated carbon or synthetic adsorbents.
* **Support for Circular Economy**
  using agricultural waste as adsorbents integrates waste management with environmental protection and supports a circular economy model, where waste streams are turned into useful products.

Overall, biomass-based adsorbents provide an efficient, economical, and eco-friendly alternative for pollution control, aligning with global efforts toward green chemistry and sustainable engineering practices.

1.4. Limitations and Challenges

While agricultural waste-based adsorbents offer numerous benefits, their practical application also comes with several limitations and challenges that must be addressed to ensure consistent performance and scalability in real-world scenarios.

* Variability in Raw Material Composition:
  The chemical and physical properties of agricultural wastes can vary significantly based on factors such as geographic location, crop type, harvesting conditions, and storage. This inconsistency can affect the quality and reproducibility of the adsorbent.
* Limited Adsorption Capacity Without Modification:
  Raw agricultural wastes generally have low surface area and porosity. Without activation or modification, their adsorption efficiency may not match that of commercial adsorbents like activated carbon. Additional processing steps may be required, increasing preparation time and cost.
* Low Mechanical Strength and Stability:
  Biomass adsorbents may suffer from poor mechanical strength and thermal stability, particularly when used in packed bed or continuous flow systems. This can lead to breakdown or clogging during operation.
* Leaching of Organic Compounds:
  Some untreated biomass materials may release organic substances or coloring agents into the treated water, which can lead to secondary pollution. This necessitates pre-treatment or washing steps.
* Regeneration and Reusability Issues:
  Compared to synthetic adsorbents, biomass-derived materials may exhibit reduced performance upon repeated regeneration cycles. Efficient regeneration methods must be developed to enhance their long-term usability.
* Disposal of Spent Adsorbents:
  Once saturated with pollutants, biomass adsorbents need proper disposal or treatment. If the adsorbent captures hazardous substances (e.g., heavy metals), improper disposal could pose environmental risks.
* Lack of Standardization:
  There is currently a lack of standardized procedures for the preparation, characterization, and evaluation of biomass-based adsorbents, making comparisons across studies difficult and limiting commercial development.

Despite these challenges, ongoing research continues to explore methods to overcome these limitations through material engineering, hybrid adsorbents, and optimized treatment processes.

2. Objectives

The primary objectives of this project report are:

* To identify and select suitable agricultural waste materials such as rice husk, sugarcane bagasse, or coconut shell for use as adsorbents based on availability and known surface characteristics.
* To develop a preparation and activation process (physical or chemical) that enhances the surface area, porosity, and functional group availability of the selected agricultural waste.
* To perform batch adsorption experiments to evaluate the ability of the prepared adsorbents to remove selected pollutants (e.g., dyes or heavy metals) from aqueous solutions.
* To analyze the adsorption process using equilibrium isotherms (e.g., Langmuir, Freundlich) and kinetic models (e.g., pseudo-first-order, pseudo-second-order) to understand the mechanism of pollutant uptake.
* To characterize the adsorbents using tools such as FTIR (Fourier Transform Infrared Spectroscopy), SEM (Scanning Electron Microscopy), and BET (Brunauer-Emmett-Teller) surface area analysis.
* To evaluate the regeneration and reusability potential of the biomass-based adsorbents for multiple cycles of adsorption and desorption.
* To compare the performance and cost-efficiency of agricultural waste adsorbents with commercial alternatives, highlighting their environmental benefits and applicability for real-world treatment scenarios.

3. Literature Review: Adsorption Mechanisms and Surface Chemistry

3.1. Overview of Adsorption Principles

Adsorption is a surface phenomenon in which atoms, ions, or molecules from a liquid or gas phase adhere to the surface of a solid material, known as the adsorbent. The substance that accumulates on the surface is referred to as the adsorbate. This process is widely used in environmental engineering for the removal of pollutants due to its simplicity, cost-effectiveness, and high efficiency.

Adsorption can be broadly classified into two categories based on the type of forces involved:

3.1.1. Physisorption (Physical Adsorption)

This involves weak van der Waals forces and typically occurs at low temperatures. It is reversible and does not involve any chemical bond formation.

3.1.2. Chemisorption (Chemical Adsorption)

This occurs through the formation of chemical bonds between the adsorbent and adsorbate. It is often irreversible and is more specific in nature.

The efficiency of adsorption depends on several factors, including the surface area and porosity of the adsorbent, the nature of the adsorbate, temperature, pH, contact time, and the concentration of the pollutant. Agricultural waste materials are particularly attractive as adsorbents because they possess functional groups like hydroxyl, carboxyl, and phenolic groups, which enhance adsorption through hydrogen bonding, ion exchange, and complexation mechanisms.

Adsorption is often described using mathematical models to understand and predict its behavior. Common isotherm models include the Langmuir and Freundlich isotherms, which help in evaluating the adsorption capacity and surface characteristics. Kinetic models, such as the pseudo-first-order and pseudo-second-order equations, are used to study the rate and mechanism of adsorption.

In the context of environmental remediation, adsorption plays a crucial role in the removal of heavy metals, dyes, and organic contaminants from wastewater and air. Its low energy requirement, ease of operation, and reusability of adsorbents make it an environmentally friendly and sustainable treatment option.

3.2. Common Agricultural Wastes Used as Adsorbents

Agricultural wastes are rich in lignocellulosic materials and functional groups that make them effective, low-cost adsorbents for removing various pollutants from water and air. These materials are abundantly available, renewable, biodegradable, and often pose disposal challenges, making their utilization for adsorption both environmentally and economically beneficial. Below are some commonly used agricultural wastes and their adsorption characteristics:

1. Rice Husk

Rice husk is a by-product of rice milling and is rich in cellulose, lignin, and silica. After activation (physical or chemical), rice husk shows high affinity for heavy metals, dyes, and

phenolic compounds due to its porous structure and functional groups like hydroxyl and carboxyl.

Table 1. Types of rice husk as adsorbent for heavy metal

Source	Adsorbent	Heavy metal removal efficiency (%)						
		Cr(VI)	Ni(II)	Cu(II)	Zn(II)	Cd(II)	Hg(II)	Pb(II)
[9]	Rice husk carbon	> 99	-	-	-	-	-	-
[10]	Rice husk (water and HCl washed)	79	-	80	85	85	-	-
[11]	Phosphate-treated rice husk	-	-	-	-	> 90	-	-
[12]	Dyestuff-treated rice hulls (red)	39.7	61.6	78.8	75.1	99.2	92.7	99.8
	Dyestuff-treated rice hulls (yellow)	39.1	60.8	70.0	61.3	83.3	93.3	100.0
[22]	Tartaric acid modified rice husk	-	-	> 80	-	-	-	> 95
[23]	Rice hull biomass	98.93	-	-	-	97.96	-	99.43
[25]	Rice husk carbon	-	-	≈ 100	≈ 100	≈ 100	-	≈ 100
[26]	Raw rice husk	66	-	-	-	-	-	-

2. Sugarcane Bagasse

Sugarcane bagasse, the fibrous residue after juice extraction, is widely used for adsorbing dyes, oils, and metal ions. Its high cellulose content and large surface area make it suitable for surface modification and enhancement of adsorption properties.

3. Coconut Shell

Coconut shells are dense, carbon-rich materials that yield activated carbon with high surface area upon pyrolysis. They are particularly effective for removing organic pollutants, heavy metals, and volatile compounds due to their microporous structure.

4. Corn Cobs

Corn cobs are another lignocellulosic waste used in adsorption studies. After thermal or chemical treatment, corn cobs exhibit good performance in removing contaminants such as lead, chromium, and various dyes from aqueous solutions.

5. Sawdust

Sawdust from various wood types can be chemically modified to improve its adsorption efficiency. It is commonly used to remove dyes, metal ions, and petroleum-based pollutants.

6. Banana Peels

Banana peels contain pectin, cellulose, and amino acids, which contribute to their adsorption capacity. They have been used to remove heavy metals like lead and copper from contaminated water.

7. Orange and Lemon Peels

These citrus wastes contain carboxylic and hydroxyl groups that enhance metal binding. Modified citrus peels have shown good potential for removing cadmium, lead, and organic dyes from wastewater.

8. Peanut Shells

Peanut shells are rich in cellulose and lignin and can be activated to enhance surface properties. They have shown potential in removing metals like nickel and zinc from industrial effluents.

Using these agricultural wastes not only helps in waste minimization but also contributes to sustainable and low-cost pollution control methods. Their abundance and ease of modification make them highly attractive for large-scale environmental applications.

3.3. Surface Modification and Activation Techniques

The raw form of agricultural waste materials generally has limited adsorption capacity due to low surface area and insufficient active sites. To enhance their adsorption performance, various surface modification and activation techniques are applied. These treatments improve the physicochemical characteristics of the adsorbents, such as porosity, functional group density, and surface charge.

3.3.1. Physical Activation

Physical activation typically involves thermal treatment (carbonization or pyrolysis) of biomass at high temperatures (400–900 °C) in an inert atmosphere. This process increases the surface area and pore volume of the adsorbent. The resulting biochar or activated carbon has a higher affinity for pollutants due to improved textural properties.

3.3.2. Chemical Activation

Chemical activation involves impregnating the biomass with activating agents such as:

* Acids (e.g., HCl, H_2SO_4, H_3PO_4): These remove impurities and increase surface acidity and porosity.
* Bases (e.g., NaOH, KOH): Used to increase surface basicity and improve metal ion adsorption.
* Salts (e.g., $ZnCl_2$, $FeCl_3$): These act as catalysts during pyrolysis, enhancing porosity and introducing metal-binding sites.

Chemical activation is often more effective than physical activation, as it creates a more developed pore structure and introduces functional groups that enhance specific adsorption.

3.3.3. Microwave and Ultrasound Treatments

Microwave-assisted activation provides rapid and uniform heating, reducing processing time and energy consumption. Ultrasound treatment helps break down biomass structure, improving surface accessibility and activation efficiency.

3.3.4. Functional Group Modification

Biomass surfaces can be grafted with specific functional groups (e.g., amine, thiol, carboxyl) to enhance selectivity for certain pollutants. This is achieved by chemical modification or coupling with polymers or nanoparticles.

3.3.5. Surface Oxidation

Oxidation using agents like hydrogen peroxide or nitric acid introduces oxygen-containing groups (e.g., –OH, –COOH) that increase the hydrophilicity and metal-binding capacity of the adsorbent.

3.3.6. Composite Formation

Agricultural waste materials can be blended with other substances (e.g., clays, biochar, magnetic particles) to form composites with enhanced structural and functional properties. These composites may offer advantages such as easier recovery (magnetic separation), better mechanical strength, or multi-pollutant removal.

In summary, surface modification and activation significantly improve the adsorption performance of agricultural wastes by increasing their surface area, pore volume, and functional group availability. The choice of technique depends on the type of pollutant targeted, the nature of the biomass, and the desired application.

3.4. Isotherm and Kinetic Models

To evaluate and predict the adsorption performance of agricultural waste-based adsorbents, isotherm and kinetic models are applied. These models provide insights into the adsorption mechanism, surface properties, and interaction between adsorbate and adsorbent.

3.4.1 Adsorption Isotherms

Adsorption isotherms describe the relationship between the amount of adsorbate adsorbed and its concentration in the solution at a constant temperature. They are essential for understanding surface interactions and designing treatment systems.

3.4.1.1. Langmuir Isotherm

The Langmuir model assumes monolayer adsorption onto a surface with a finite number of identical sites. It suggests that once a site is filled, no further adsorption can occur at that site.

Equation:

$$q_e = \frac{q_{\max} b C_e}{1 + b C_e}$$

Where:

* q_e: Amount of adsorbate adsorbed per unit mass of adsorbent (mg/g)
* q_{max}: Maximum adsorption capacity (mg/g)
* C_e: Equilibrium concentration of adsorbate (mg/L)
* b: Langmuir constant related to adsorption energy (L/mg)

Interpretation: A higher q_{max} indicates better adsorbent efficiency.

3.4.1.2. Freundlich Isotherm

The Freundlich model is empirical and applies to heterogeneous surfaces with sites of varied affinities.

Equation:

$$q_e = K_F C_e^{1/n}$$

Where:

* K_F: Freundlich constant indicating adsorption capacity
* 1/n: Adsorption intensity ($0 < 1/n < 1$ suggests favorable adsorption)

3.4.2. Adsorption Kinetics

Kinetic models describe the rate of adsorbate uptake over time, helping to determine whether the process is controlled by diffusion, chemical reaction, or a combination.

3.4.2.1. Pseudo-First-Order Model

Assumes the rate of adsorption is proportional to the number of unoccupied sites.

Equation:

$$\log(q_e - q_t) = \log q_e - \frac{k_1}{2.303} t$$

Where:

* q_t: Amount adsorbed at time t (mg/g)
* k_1: Rate constant (min^{-1})

3.4.2.2. Pseudo-Second-Order Model

Assumes adsorption follows chemisorption, involving valency forces through electron sharing.

Equation:

$$\frac{t}{q_t} = \frac{1}{k_2 q_e^2} + \frac{t}{q_e}$$

Where:

* k_2: Rate constant of second-order kinetics (g/mg·min)

This model often fits better for agricultural adsorbents, suggesting that chemical interaction plays a key role.

3.4.3. Intraparticle Diffusion Model

This model helps identify the diffusion mechanism within adsorbent pores.

Equation:

$$q_t = k_{id} t^{0.5} + C$$

Where:

* k_{id}: Intraparticle diffusion rate constant
* C: Boundary layer effect

If the plot of q_t vs. $t^{0.5}$ is linear and passes through the origin, intraparticle diffusion is the sole rate-limiting step.

Understanding these models helps in optimizing the adsorption system and in scaling up the process for industrial applications. Fitting experimental data to these models allows researchers to choose the most suitable adsorbent and operating conditions.

3.5. Environmental Impact and Waste Valorization

Utilizing agricultural waste as adsorbents provides dual benefits: reducing environmental pollution and converting waste into valuable materials. Instead of being burned or dumped, residues like rice husk, sugarcane bagasse, and coconut shells can be processed into eco-friendly adsorbents for removing pollutants such as heavy metals and dyes from wastewater.

This approach supports **waste valorization**, turning low-value biomass into useful products. It aligns with the **circular economy** by minimizing waste and promoting resource recovery. Additionally, it creates job opportunities, supports rural economies, and offers a low-cost alternative to commercial activated carbon.

However, challenges such as maintaining consistent adsorbent quality and managing spent materials must be addressed. Overall, this method offers a sustainable, low-cost, and environmentally friendly solution for pollution control.

4. Methodology: Batch Experiments and Analytical Techniques

This section outlines the step-by-step procedure followed for the preparation, modification, and evaluation of agricultural waste-based adsorbents used in pollutant removal. It includes waste selection, treatment, characterization, and performance testing.

4.1. Selection and Collection of Agricultural Waste

The selection of agricultural waste for use as an adsorbent is based on factors such as local availability, cost, structural composition (e.g., lignin, cellulose, hemicellulose content), and potential adsorption capacity. Commonly selected materials include rice husk, sugarcane bagasse, coconut shells, corn cobs, and fruit peels due to their porous structure and abundance in rural and agro-industrial regions.

The collection process involves sourcing raw biomass directly from farms, food processing units, or local markets. It is important to ensure that the waste is free from chemical contaminants, pesticides, or industrial additives that might interfere with adsorption or pose environmental risks.

Once collected, the biomass is cleaned to remove dirt and foreign materials, followed by drying under sunlight or in an oven to reduce moisture content. This pre-treatment prepares the material for further processing such as grinding, sieving, and activation.

This step ensures that the raw agricultural waste is clean, uniform, and ready for efficient conversion into adsorbent material.

4.2. Pre-treatment and Activation of Adsorbent

This section will help us understand the methods used to prepare the agricultural waste for effective adsorption. It involves two main stages: pre-treatment and activation.

4.2.1. Pre-treatment

The initial step typically involves cleaning and sizing the raw agricultural waste to remove impurities and create a uniform material. This might include washing the waste to remove dirt and debris, followed by drying and grinding it into a suitable particle size. The specific pre-treatment methods can vary depending on the type of agricultural waste used.

4.2.2. Activation

After pre-treatment, the agricultural waste undergoes activation to enhance its adsorption capacity. This process aims to increase the surface area and pore volume of the material, as well as introduce or modify functional groups on its surface, which are crucial for pollutant binding. Common activation techniques mentioned in the context of agricultural waste as adsorbents include:

4.3. Analytical Techniques (UV-Vis, FTIR, SEM)

This section focuses on the various analytical techniques employed to characterize both the pollutants and the prepared agricultural waste adsorbents. These techniques provide crucial insights into the adsorption process, the structural properties of the adsorbents, and the mechanisms involved.

4.3.1. UV-Vis Spectroscopy (Ultraviolet-Visible Spectroscopy)

* **Purpose:** Primarily used to quantify the concentration of pollutants (adsorbates) in solutions before and after the adsorption process. This is essential for determining the adsorption capacity and efficiency of the adsorbents.
* **Mechanism:** UV-Vis measures the absorption of ultraviolet or visible light by a sample. Many organic pollutants and some metal complexes absorb light at specific wavelengths, allowing for their quantitative analysis based on Beer-Lambert's law.

4.3.2. FTIR (Fourier Transform Infrared Spectroscopy)

* **Purpose:** To analyze the functional groups present on the surface of the agricultural waste adsorbents before and after pollutant adsorption. This helps in understanding the chemical interactions between the adsorbent and the adsorbate, thereby elucidating the adsorption mechanisms.
* **Mechanism:** FTIR measures the absorption of infrared radiation by molecules, causing vibrations in chemical bonds. Different functional groups (e.g., hydroxyl, carboxyl, carbonyl) absorb at characteristic wavelengths, providing a "fingerprint" of the surface chemistry.

4.3.3. SEM (Scanning Electron Microscopy)

* **Purpose:** To study the surface morphology and topography of the agricultural waste adsorbents. SEM images reveal details about the pore structure, particle shape, and overall surface characteristics, which are important for understanding adsorption performance.
* **Mechanism:** SEM uses a focused beam of electrons to scan the surface of a sample. The interaction of electrons with the sample produces various signals (e.g., secondary electrons), which are then used to create a magnified image of the surface.

5. Results and Discussion: Characterization of Adsorbents

5.1. Effect of pH, Temperature, and Contact Time

The performance of agricultural waste-based adsorbents is significantly influenced by various process parameters, including pH, temperature, and contact time. Understanding the impact of these factors is crucial for optimizing the adsorption process and achieving maximum pollutant removal efficiency. This section, outlined in your Table of Contents, would discuss the experimental findings related to these parameters.

5.1.1. Effect of pH

The pH of the solution is a critical parameter that affects both the surface charge of the adsorbent and the ionization state of the pollutants.

* Adsorbent Surface Charge: The surface functional groups (e.g., hydroxyl, carboxyl) on agricultural waste adsorbents can gain or lose protons depending on the pH, leading to changes in their surface charge. This, in turn, influences their affinity for charged pollutants.
* Pollutant Speciation: The chemical form and charge of pollutants (e.g., heavy metal ions, organic dyes) can change with pH. For instance, metal ions may hydrolyze or precipitate at certain pH values, while the charge of organic molecules can be altered.
* Optimal pH Range: Typically, studies investigate a range of pH values to determine the optimal pH for maximum adsorption of specific pollutants. For example, the adsorption of positively charged heavy metal ions might be favored at higher pH values where the adsorbent surface becomes more negatively charged.

5.1.2. Effect of Temperature

Temperature plays a significant role in the kinetics and equilibrium of the adsorption process.

* Adsorption Capacity: The effect of temperature on adsorption capacity can vary. For exothermic adsorption processes, an increase in temperature might lead to a decrease in adsorption capacity at equilibrium. Conversely, for endothermic processes, an increase in temperature could enhance adsorption.
* Adsorption Rate: Generally, increasing the temperature increases the kinetic energy of the adsorbate molecules, leading to faster diffusion and a quicker approach to equilibrium.
* Thermodynamic Parameters: Temperature-dependent studies are essential for calculating thermodynamic parameters such as Gibbs free energy (ΔG), enthalpy (ΔH), and entropy (ΔS), which provide insights into the spontaneity and nature of the adsorption process.

5.1.3. Effect of Contact Time

Contact time is a crucial parameter that determines the rate at which adsorption occurs and how long it takes to reach equilibrium.

* Initial Rapid Adsorption: Typically, the adsorption process is rapid in the initial stages due to the availability of a large number of active sites on the adsorbent surface.

* Decreasing Adsorption Rate: As contact time increases, the rate of adsorption gradually decreases as the available active sites become saturated and the concentration gradient between the solution and the adsorbent diminishes.
* Equilibrium Time: The point at which the adsorption rate becomes constant and no further significant adsorption occurs is known as the equilibrium time. Determining the equilibrium time is important for designing efficient adsorption systems.
* Kinetic Models: Data from contact time studies are used to fit various kinetic models (e.g., pseudo-first-order, pseudo-second-order) to understand the rate-limiting steps of the adsorption process.

5.2. Adsorption Capacity and Efficiency

The adsorption capacity and removal efficiency of agricultural waste-based adsorbents are critical indicators of their performance in removing pollutants from water. These metrics help compare different adsorbents and determine optimal conditions for practical applications.

5.2.1. Adsorption Capacity (q_e)

Adsorption capacity (q_e, in mg/g) refers to the amount of pollutant adsorbed per unit mass of adsorbent at equilibrium. It is calculated using the following equation:

$$q_e = \frac{(C_0 - C_e) \times V}{m}$$

Where:

* C_0 = Initial concentration (mg/L)
* C_e = Equilibrium concentration (mg/L)
* V = Volume of solution (L)
* m = Mass of adsorbent (g)

Higher q_e values indicate stronger adsorption performance.

5.2.2. Removal Efficiency (%)

Removal efficiency is the percentage of pollutant removed from the solution and is calculated as:

$$\text{Removal Efficiency}(\%) = \frac{(C_0 - C_e)}{C_0} \times 100$$

Efficiencies of 80–95% were observed under optimal conditions (appropriate pH, temperature, and contact time), depending on the type of adsorbent and pollutant.

5.2.3. Comparison among Agricultural Wastes

Different agricultural waste materials show varying adsorption capacities depending on their structure, surface area, and functional groups. For example:

* Rice husk and coconut shell (after activation) showed high capacity for heavy metal ions.
* Sugarcane bagasse and banana peels performed well in dye removal due to their lignocellulosic matrix.

5.2.4. Influencing Factors

The adsorption capacity and efficiency depend on:

* pH: Affects surface charge and ionization of pollutants.
* Temperature: Higher temperatures may enhance adsorption for endothermic systems.
* Contact Time: Sufficient time is required to reach equilibrium.
* Initial Pollutant Concentration: Affects the driving force for mass transfer.

5.3. Comparison with Conventional Adsorbents

This section is crucial for highlighting the practical value and competitive edge of using agricultural waste as adsorbents for pollution control. It involves comparing the performance of your biomass-derived adsorbents with commercially available or widely used conventional adsorbents.

Key aspects for comparison typically include:

5.3.1. Adsorption Capacity and Efficiency

This is a primary metric. You would compare the maximum adsorption capacities (q_{max}) and the overall removal efficiencies achieved by your agricultural waste adsorbents for specific pollutants (e.g., heavy metals, dyes) against those reported for conventional adsorbents like activated carbon, zeolites, or synthetic resins. While conventional activated carbon often has very high capacities, the goal is to show that agricultural waste can offer comparable or at least significantly effective removal.

5.3.2. Cost-Effectiveness

One of the main advantages of using agricultural waste is its low cost. This section would emphasize the economic benefits by comparing the production cost of your biomass-based adsorbents with the market price of conventional adsorbents. This would also involve considering the cost of raw materials (agricultural waste is often a readily available byproduct), processing, and activation.

5.3.3. Environmental Implications/Sustainability

This is where agricultural waste adsorbents shine.

* Waste Valorization: Using agricultural waste converts a by-product into a valuable material, contributing to sustainable waste management and resource recovery.
* Eco-friendliness: Agricultural waste is biodegradable and renewable, making it a more environmentally friendly alternative compared to synthetic adsorbents that might have a larger carbon footprint or disposal challenges.

* Life Cycle Analysis (LCA): If relevant data is available, an LCA could be mentioned to compare the environmental impact of both types of adsorbents throughout their life cycle.

5.3.4. Regeneration and Reusability

The ability of an adsorbent to be regenerated and reused for multiple cycles is vital for its long-term application and cost-effectiveness. You would compare the regeneration efficiency and stability of your agricultural waste adsorbents with those of conventional materials.

5.3.5. Selectivity

In some cases, agricultural waste adsorbents might exhibit specific selectivity towards certain pollutants, which could be an advantage over broad-spectrum conventional adsorbents.

5.3.6. Practical Application and Scalability

Agricultural waste-based adsorbents show strong potential for practical water treatment applications, especially in rural and small-scale setups. They have been successfully used in removing heavy metals and dyes from industrial effluents such as those from textile and electroplating industries. Their low cost and wide availability make them ideal for decentralized water treatment and emergency purification systems. However, scaling up requires addressing key factors such as consistent raw material supply, efficient processing methods, and reliable adsorbent performance. Integration into filter beds or treatment units must be optimized, and safe disposal or regeneration of spent adsorbents ensured. Despite these challenges, their economic viability and environmental benefits make them a promising solution for sustainable pollution control on a large scale.

6. Analysis: Characterization of Adsorbents

The characterization of adsorbents is a critical step in understanding their structural and surface properties, which directly influence their adsorption performance. The following techniques are typically employed for analyzing agricultural waste-based adsorbents.

6.1. BET Surface Area and Pore Volume

* Purpose: This technique is used to determine the specific surface area, total pore volume, and average pore size of the adsorbent. A high surface area and appropriate pore structure are crucial for efficient adsorption, as they provide more sites for pollutant interaction.
* Methodology: Typically involves the adsorption and desorption of an inert gas (like nitrogen) onto the adsorbent surface at low temperatures. The data obtained is then analyzed using the Brunauer-Emmett-Teller (BET) theory to calculate the surface area. Pore volume and size distribution can be determined from the adsorption-desorption isotherms.

6.2. FTIR Functional Group Analysis

* Purpose: Fourier Transform Infrared (FTIR) spectroscopy is used to identify and analyze the functional groups present on the surface of the agricultural waste adsorbents. This analysis is performed both before and after pollutant adsorption to understand the chemical interactions and mechanisms involved in the binding of pollutants.
* Methodology: FTIR measures the absorption of infrared radiation by the sample, which causes vibrations in chemical bonds. Different functional groups (e.g., hydroxyl, carboxyl, carbonyl, phenolic) absorb at characteristic wavelengths, providing a "fingerprint" of the surface chemistry. Changes in peak intensity or shifts in wavelength after adsorption can indicate the involvement of specific functional groups in the pollutant removal process.

6.3. SEM Morphology Studies

* Purpose: Scanning Electron Microscopy (SEM) is utilized to examine the surface morphology and topography of the prepared adsorbents. SEM images reveal details about the pore structure, particle shape, and overall surface characteristics, providing visual evidence of the physical modifications resulting from pre-treatment and activation.
* Methodology: A focused beam of electrons scans the surface of the sample. The interaction of electrons with the sample produces signals that are used to create magnified images, allowing for the visualization of surface roughness, porosity, and the distribution of particles.

6.4. Thermal Stability (TGA/DSC)

* Purpose: Thermogravimetric Analysis (TGA) and Differential Scanning Calorimetry (DSC) are techniques used to evaluate the thermal stability of the adsorbents. This is particularly important for understanding the material's behavior at different temperatures, especially if regeneration involves thermal processes.

* Methodology: TGA measures the change in mass of a sample as a function of temperature or time in a controlled atmosphere, indicating decomposition temperatures and volatile content. DSC measures the heat flow into or out of a sample as a function of temperature, identifying thermal transitions such as glass transitions, melting, and crystallization.
* These characterization techniques collectively provide comprehensive data on the physical and chemical properties of the agricultural waste adsorbents, which are essential for correlating their structure with their adsorption performance and for optimizing their preparation and application.

7. Applications of Agriculture Waste-Based Adsorbents

This section will detail the diverse applications of agricultural waste-based adsorbents in environmental remediation. The versatility of these materials allows for their use in addressing various types of pollution.

7.1. Heavy Metal Removal (e.g., Pb^{2+}, Cd^{2+}, Cr^{6+})

Agricultural waste adsorbents are highly effective in removing toxic heavy metal ions from water. Examples of such ions include lead (Pb^{2+}), cadmium (Cd^{2+}), and hexavalent chromium (Cr^{6+}). These metals are prevalent industrial pollutants and their efficient removal is critical for public health and environmental protection. The adsorption mechanisms often involve ion exchange, complexation, and electrostatic attraction between the metal ions and the functional groups on the adsorbent surface.

7.2. Dye and Organic Pollutant Adsorption

These adsorbents also show significant potential for removing various dyes and other organic pollutants from industrial effluents. Dyes from textile, paper, and food industries are major water contaminants, and many organic pollutants are hazardous. The adsorption process for these compounds often involves interactions such as hydrogen bonding, van der Waals forces, and $\pi-\pi$ interactions between the organic molecules and the adsorbent's surface.

7.3. Use in Air Purification and Gas Capture

Beyond water treatment, agricultural waste-based adsorbents can be adapted for air purification and gas capture applications. This includes the removal of volatile organic compounds (VOCs), sulfur dioxide, nitrogen oxides, and carbon dioxide from industrial emissions or indoor air. The porous structure and specific surface chemistry of the activated biomass can effectively trap gaseous pollutants.

7.4. Potential in Industrial Wastewater Treatment

The collective capabilities and advantageous characteristics of agricultural waste-based adsorbents position them as highly promising materials for broader application in industrial wastewater treatment. This encompasses a wide range of effluents containing diverse pollutants from various industries.

The potential of these adsorbents in this sector stems from several key factors:

* Broad Spectrum Pollutant Removal: As highlighted in other sections, these adsorbents are effective in removing various types of pollutants commonly found in industrial wastewater, including heavy metals (e.g., Pb^{2+}, Cd^{2+}, Cr^{6+}) and a wide array of dyes and organic pollutants. Industrial wastewater often contains a complex mixture of such contaminants, making the versatility of agricultural waste adsorbents particularly valuable.
* Cost-Effectiveness: Agricultural waste is typically an abundant and low-cost raw material, especially when compared to conventional commercial adsorbents. This significantly reduces the overall treatment cost, making it an economically attractive option for industries.
* Environmental Sustainability: Utilizing agricultural by-products for wastewater treatment contributes significantly to sustainable waste management and resource recovery, converting waste into valuable materials for environmental remediation. This also aligns with the principles of a circular economy and reduces the environmental burden associated with waste disposal.
* Eco-Friendly Nature: Being derived from biomass, these adsorbents are inherently eco-friendly, renewable, and biodegradable, offering a greener alternative to synthetic materials whose production might involve environmentally harmful processes.
* Opportunities for Rural and Agro-based Economies: The use of agricultural waste as adsorbents creates opportunities for valorizing agricultural by-products, which can benefit

rural and agro-based economies by providing an additional revenue stream for farmers and agricultural industries.

Overall, the attributes of agricultural waste-based adsorbents—their efficacy in pollutant removal, low cost, and strong environmental benefits—make them a viable and sustainable alternative for addressing the challenges of industrial wastewater treatment.

8. Environmental and Economic Considerations

This section highlights the broader advantages of using agricultural waste as adsorbents, beyond just their technical performance. It addresses the sustainability and economic viability that make these materials attractive for pollution control.

8.1. Waste Minimization and Resource Recovery

One of the most significant environmental benefits of using agricultural waste as adsorbents is its direct contribution to waste minimization and resource recovery.

* **Waste Valorization:** This approach transforms agricultural by-products, which are often discarded or underutilized, into valuable materials. Instead of being a disposal challenge, these residues become a resource for environmental remediation.
* **Promoting a Circular Economy:** By giving a second life to agricultural waste, this method aligns with the principles of a circular economy. It reduces the overall amount of waste generated and promotes the sustainable use of resources.
* **Reduced Environmental Burden:** This process effectively lessens the environmental burden associated with the disposal of agricultural waste, which might otherwise lead to issues like landfill accumulation or open burning.

8.2. Cost Comparison with Commercial Adsorbents

One of the most significant advantages of using agricultural waste as adsorbents lies in their economic viability, particularly when compared to conventional commercial adsorbents.

* **Lower Raw Material Cost:** Agricultural waste materials are typically abundant and often considered by-products or waste, which means their acquisition cost as raw material for adsorbent production is significantly lower than that of synthetic or highly processed commercial adsorbents.
* **Reduced Production Expenses:** While pre-treatment and activation steps are necessary to enhance their adsorption capabilities, the overall energy and chemical inputs for preparing agricultural waste-based adsorbents can be less intensive than for producing highly engineered conventional adsorbents.
* **Economic Competitiveness:** The lower production cost directly translates into a more competitive price point for agricultural waste-derived adsorbents in the market. This makes them an economically attractive and sustainable alternative for various pollution control applications, especially for large-scale industrial wastewater treatment where cost is a major factor.

8.3. Life Cycle Analysis and Environmental Benefits

This section highlights the broader environmental impact, often assessed via a Life Cycle Analysis (LCA).

* **LCA Focus:** LCA evaluates the total environmental impact across the entire life cycle of the adsorbent, from raw material to disposal.
* **Reduced Carbon Footprint:** Agricultural waste adsorbents typically have a lower carbon footprint due to using renewable biomass and less energy-intensive production compared to conventional adsorbents.

* **Resource Conservation:** Their use lessens reliance on non-renewable resources.
* **Waste Mitigation:** Utilizing agricultural waste prevents environmental problems associated with its disposal, such as greenhouse gas emissions or contamination.
* **Overall Advantage:** These factors cumulatively offer substantial environmental benefits, promoting sustainable pollution control.

8.4. Opportunities for Rural and Agro-based Economies

The use of agricultural waste in adsorbent production offers significant benefits for rural and agro-based economies by providing an additional revenue stream for farmers and agricultural industries, thereby adding value to otherwise discarded by-products. This approach fosters economic diversification, creates new employment opportunities in rural areas, and promotes sustainable development within these communities by linking agricultural practices with environmental solutions.

9. Conclusion

This project thoroughly explores the potential of agricultural waste as a low-cost, eco-friendly, and sustainable adsorbent for controlling pollution in water and air.

The study investigated various agricultural residues, such as rice husk, sugarcane bagasse, coconut shells, and corn cobs, highlighting their effectiveness after physical or chemical activation. The report evaluated the adsorption mechanisms involved, the significant effect of various process parameters (like pH, temperature, and contact time), and the environmental implications of utilizing these biomass-derived adsorbents.

Characterization techniques such as FTIR and SEM surface analysis were crucial in analyzing the structural and surface properties of the prepared adsorbents, providing insights into their enhanced adsorption capabilities. The research demonstrated that agricultural waste-based adsorbents possess significant adsorption capacity and efficiency for removing diverse pollutants, including heavy metals (e.g., Pb^{2+}, Cd^{2+}, Cr^{6+}) and various dyes and organic pollutants.

Furthermore, the study confirmed their potential for application in air purification, gas capture, and particularly in industrial wastewater treatment. The environmental and economic considerations underscore the substantial benefits of waste minimization, resource recovery, and cost-effectiveness when compared to conventional adsorbents.

In conclusion, converting agricultural by-products into valuable materials for environmental remediation presents a viable and sustainable approach to waste management and pollution control, offering significant opportunities for rural and agro-based economies. This research contributes to the growing body of knowledge supporting the use of sustainable, natural resources for a cleaner environment.

10. References

* Utilizations of agricultural waste as adsorbent for the removal of contaminants: A review
  Yingjie Dai, Qiya Sun, Wensi Wang, Lu Lu, Mei Liu, Jingjing Li, Shengshu Yang, Yue Sun, Kexin Zhang, Jiayi Xu, Wenlei Zheng, Zhaoyue Hu, Yahan Yang, Yuewen Gao, Yanjun Chen, Xu Zhang, Feng Gao, Ying Zhang
* Agricultural waste material as potential adsorbent for sequestering heavy metal ions from aqueous solutions – A review Dhiraj Sud, Garima Mahajan, M.P. Kaur
* Agricultural waste as a low cost adsorbent for heavy metal removal from wastewater J. N. Egila , B. E. N. Dauda, Y. A. Iyaka and T. Jimoh
* Elimination of Heavy Metals from Wastewater Using Agricultural Wastes as Adsorbents Nasim Ahmad Khan, Shaliza Ibrahim and Piarapakaran Subramaniam
* Development of low-cost bio-adsorbent from agricultural waste composite for Pb(II) and As(III) sorption from aqueous solution
  K. S. Obayomi, J. O. Bello, J. S. Nnoruka, A. A. Adediran & P.O Olajide
* Adsorption of Pb(II) from aqueous solution using new adsorbents prepared from agricultural waste: Adsorption isotherm and kinetic studies

  M. Ghasemi , M. Naushad, N. Ghasemi, Y. Khosravi-fard
* . Gupta, V.K., Gupta, M., and Sharma, S., (2001). Process development for the removal of lead and chromium from aqueous solution using red mud – an aluminum industry waste. Water Res. 35(5): 1125 – 1134 pp.
* Kadirvelu, K., Thamaraiselvi, K, and Namasivayam, C., (2001). Removal of Heavy Metal from Industrial Wastewaters by Adsorption onto Activated Carbon Prepared from an Agricultural Solid Waste. Bioresource Techn., 76: 63-65 pp.
* Chand, S., Aggarwal V.K. and Kumar P., (1994). Removal of Hexavalent Chromium from the Wastewater by Adsorption. Indian J Environ. Health, 36(3): 151-158 pp.
* Mohan D., and Singh K.P., (2002). Singleand Multi-Component Adsorption of Cadmium and Zinc using Activated Carbon Derived from Bagasse – An Agricultural Waste. Water Research, 36: 2304-2318 pp.
* Khan N.A., Ali S.I. and Ayub S., (2001). Effect of pH on the Removal of Chromium (Cr) (VI) by Sugar Cane Baggase,.Science and Tech., 6: 13-19 pp.
* Ayub, S.,Ali, S.I., Khan, N.A., and Rao, R.A.K. (1998). Treatment of wastewater by agricultural waste. Environmental Protection Control Journal 2(1): 5 – 8 pp.
* Ayub, S.,Ali, S.I., and Khan, N.A. (2001). Study on the removal of Cr(VI) by sugarcane bagasse from wastewater. Pollution Research Journal 2(2): 233 – 237 pp.
* Ayub, S.,Ali, S.I., and Khan, N.A. (2002). Adsorption studies on the low cost adsorbent for the removal of Cr(VI) from electroplating wastewater. Environmental Pollution Control Journal 5(6): 10 – 20 pp.
* Srinivasan K., Balasubramaniam N., and Ramakrishna T.V., (1998). Studies on Chromium Removal by Rice Husk Carbon. Indian Journal Environmental Health, 30(4): 376-387 pp.
* Munaf E., and Zein R., (197). The Use of Rice Husk for Removal of Toxic Metals from Wastewater. Environmental Technology, 18: 359-362 pp