

```

%root_path = fileparts(mfilename("fullpath"));
%root_path = pwd;
scuts_path = 'e:\SHARE\Fe\Data\analysis\07_fit_with_multicut_allJ\sel_cuts';
Cutfitfile = fullfile(scuts_path, 'GP_FFCutsFits.mat');

if ~exist('GP_FFCutsFits', 'var')
    ld = load(Cutfitfile);
    GPFFfitDte200e400 = ld.fit_src_struct;
end


```

```

selectCuts= 'Ei200_off200GPmiff';
cuts_list = GP_FFCutsFits.(selectCuts);
if ~iscell(cuts_list)
    cuts_list = {cuts_list};
end

mi = maps_instrument(200,600,'S');
sample=IX_sample(true,[1,0,0],[0,1,0],'cuboid',[0.04,0.03,0.02]);
for i=1:numel(cuts_list)
    cuts_list{i} = cuts_list{i}.set_instrument(mi);
    cuts_list{i} = cuts_list{i}.set_sample(sample);
    plot(cuts_list{i}); lz 0 1; keep_figure;
end

```



```

dir_name = "GP";

dE_step = 2; %original energy transfer step data were binned to. No point in
going finer
half_dE = 5; % half width of data binning

```

```

en_mm = cuts_list{1}.data.img_range(:,4);
en_mm(1) = max(30,en_mm(1));
%en_mm(1) = 100;
%en_mm(2) = 110;
cut_en = en_mm(1)+half_dE:2*half_dE:(en_mm(2)-half_dE);

cut_dimensions = 1;
GP_FFCutsFits.(selectCuts) = cuts_list;

```

```

GP_FFCutsFits = fit_multicutsFF_along_direction(...
    GP_FFCutsFits,selectCuts,cut_dimensions,cut_en,dE_step,half_dE,true);


```

```

*****
**** En = 35±5 going to 125
*****

```

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.072\pm0.0033$; $J_0=7.1\pm0.063$; $\gamma=1.69139\pm0.0487504$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $30 \leq E \leq$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




```

*****
**** En = 45±5 going to 125
*****


```

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.064\pm0.0018$; $J_0= 6.3\pm0.043$; $\gamma=2.97131\pm0.0650617$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $40 \leq E \leq$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 55±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.051\pm0.0028$; $J_0= 5.8\pm0.035$; $\gamma=3.49443\pm0.77364$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $50 \leq E \leq$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 65±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.054\pm0.0012$; $J_0= 5.4\pm0.023$; $\gamma=6.60185\pm0.125371$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $60 \leq E \leq$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 75±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.05\pm0.0022$; $J_0= 5.1\pm0.033$; $\gamma=8.6508\pm0.454147$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $70 \leq E \leq$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 85±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.033\pm0.001$; $J_0= 4.9\pm0.031$; $\gamma=10.6668\pm0.33485$
 $0.1 \leq \xi \leq 0.1$ in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, $80 \leq E \leq 80$
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 95±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.039\pm0.0024$; $J_0= 4.5\pm0.028$; $\gamma=12.3404\pm1.6022$
 0.1 in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, ξ
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 105±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.049\pm0.0033$; $J_0= 4.4\pm0.024$; $\gamma=11.4448\pm1.66755$
 0.1 in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, 1
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$




 **** En = 115±5 going to 125

Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.053\pm0.0041$; $J_0= 4.3\pm0.03$; $\gamma=18.9691\pm2.60514$
 0.1 in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, 1
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$






 **** En = 125±5 going to 125


Fe_ei200_align_sym3, w2_200off200m.sqw
 $S=0.058\pm0.0021$; $J_0=4.1\pm0.019$; $\gamma=22.8767\pm1.47467$
 0.1 in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, 1
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$



Fe_ei200_align_sym3, w2_200off200m.sqw
 0.1 in $[2-\xi, -\xi, 0]$, $-0.1 \leq \eta \leq 0.1$ in $[2+0.5\eta, -0.5\eta, \eta]$, 1
 $\zeta=-0.005:0.01:0.305$ in $[2-\zeta, \zeta, \zeta]$









```
c1 = GP_FFCutsFits.(selectCuts);
GPFFfitDte200e400.(selectCuts) = [c1{:}];
```

```
beep
beep
beep
```

```
all_fit_par = GP_FFCutsFits.Ei200_off110GPmiff_all_fit_par;
bg_data = extract_bg_par(all_fit_par,[1,2]);
% original slope parameters
pd(bg_data(1));lx(all_fit_par(1).en,all_fit_par(end).en);keep_figure;
```



```
pd(bg_data(2));lx(all_fit_par(1).en,all_fit_par(end).en);keep_figure
```



```
%pd(bg_data(3));lx(fit_res.peak_fit_par(1).en,fit_res.peak_fit_par(end).en);keep_  
figure;  
%pd(bg_data(4));lx(fit_res.peak_fit_par(1).en,fit_res.peak_fit_par(end).en);keep_  
figure
```

```
fit_resEi200 = fit_res_rec;  
save(res_name,"fit_resEi200")
```