Identity — Poly methyl Methacrylate

Source — Indefinite [redacted] A1B, 7, 5/12

Age — Indefinite [redacted]

Notes

C

Identity established by [redacted] as Polymethyl methacrylate with the possibility of a few percent of cross linked esters in addition to polymethylmethacrylate. Identification was made on basis of (1) infra red spectrum (submitted with this report, (2) elemental analysis C 60.53% H 7.93 (3) density 1.19 @ 25C. (4) Softening point ca. 3 and (5) Solubility in sulfuric acid and ethyl acet

H-B13

Source this resin is produced in U.S. Work has been done on it in many foreign Countrie [redacted] has raw materials from other proces (by-products) which make it more economica to manufacture than in [redacted] where work ha also been done on the substance.

The casting resembles products made in [redacted] Several subjective opinions were rendered to the effect that its composition and appearance migh lead one to believe that this was its origin

[redacted]