



tungsten (cubic)
 E : 389 GPa, isotropic



copper (cubic)
 E : 67–192 GPa



zinc (hexagonal)
 E : 35–124 GPa

