photopolymer



over-cure into the layer below

PBF and DED



remelting of the layer below

filament (FFF)



chains interdiffuse, often incompletely

cold spray



plastic deformation at impact

binder jetting



binder bridges, then sinter necks

sheet lamination



a glue line

What joins layer n to layer $n-1$ sets the strength along z: the origin of anisotropy in AM parts.