

# PROSES WINDOW DATA SHEET

Date : 05 Agt 2025

Part Name : Case B Right TL2

Matrial name : PA66 DOMO TECHNYL

MTC : 60

Colling time : 10 sec

Part No : DH02400-C11-0310

Grade : A218V358K BLK

Colling tower : -

Heater mold : -

Mesin : 03/80 t

Dryer : 90 c H°

Chiller : -

Cycle Time : 28.6 sec

| Kondisi | Holding Pressure ( % ) |     |     | Ht1 (Sec) | Chuslon | Wight (grm ) |      |       |       |      |      |      |      | Part App |      |       |
|---------|------------------------|-----|-----|-----------|---------|--------------|------|-------|-------|------|------|------|------|----------|------|-------|
|         | Hp1                    | Hp2 | Hp3 |           |         | Cav1         | Cav2 | Cav3  | Cav4  | Cav5 | Cav6 | Cav7 | Cav8 | S M/Hike | Good | Burry |
| 1       | 80                     | 10  | 5   | 0.5       | 9.05    |              |      |       |       |      |      |      |      |          |      | o     |
| 2       | 80                     | 15  | 10  | 0.8       | 8.56    |              |      |       |       |      |      |      |      |          |      | o     |
| 3       | 80                     | 20  | 15  | 1.0       | 7.95    |              |      |       |       |      |      |      |      |          |      | o     |
| 4       | 80                     | 25  | 20  | 1.2       | 7.15    |              |      |       |       |      |      |      |      |          |      | o     |
| 5       | 80                     | 30  | 25  | 1.5       | 6.98    |              |      |       |       |      |      |      |      |          |      | o     |
| 6       | 80                     | 35  | 30  | 1.5       | 6.85    |              |      |       |       |      |      |      |      |          |      | o     |
| 7       | 80                     | 40  | 30  | 1.5       | 6.75    |              |      | 7.736 | 7.773 |      |      |      |      |          |      | o     |
| 8       | 80                     | 45  | 30  | 1.5       | 6.55    |              |      |       |       |      |      |      |      |          |      | o     |
| 9       | 80                     | 50  | 30  | 1.8       | 6.05    |              |      |       |       |      |      |      |      |          |      | o     |
| 10      | 80                     | 55  | 30  | 2.0       | 5.85    |              |      |       |       |      |      |      |      |          |      | o     |

| Temperatur Barrel | Nozlle | Front | Middle | rear  |
|-------------------|--------|-------|--------|-------|
|                   | 280°C  | 280°C | 275°C  | 270°C |

| Temperatur Hot Runner | Zona 1 | Zona 2 | Zona 3 | Zona 4 |
|-----------------------|--------|--------|--------|--------|
|                       |        |        |        |        |

## Hasil Pengecekan Proses Window

|                      |     | Holding Pressure ( ) |    |    |    |    |    |    |
|----------------------|-----|----------------------|----|----|----|----|----|----|
|                      |     | 25                   | 30 | 35 | 40 | 45 | 50 | 55 |
| Holding time ( sec ) | 0.5 |                      |    |    |    |    |    |    |
|                      | 0.8 |                      |    |    |    |    |    |    |
|                      | 1.0 |                      |    |    |    |    |    |    |
|                      | 1.2 |                      |    |    |    |    |    |    |
|                      | 1.5 |                      |    |    |    |    |    |    |
|                      | 1.8 |                      |    |    |    |    |    |    |
|                      | 2.0 |                      |    |    |    |    |    |    |
|                      | 2.5 |                      |    |    |    |    |    |    |
|                      | 3.0 |                      |    |    |    |    |    |    |

 → Good Kondisi

 → Lower Kondisi

 → Dhanger kondisi

| Approved | Checked | Prepared |
|----------|---------|----------|
|          |         |          |

Kesimpulan : Proses Window adalah untuk menentukan Parameter Standar, sudah di lakukan trial Dan Inspection Dan akan menentukan :

A. Gate Balance ( 30,50,75,85 )% No Holding Press & Holding Time

B. Gate Seal ( Di tentukan saat proses trial dimana part wight sudah tidak berubah )



- Note :
1. Dimensi Ng Wait data sheet pengukuran
  2. App ( Burry All cavity ) Analysa Insert Slider Not Touching