

PT. IMC TEKNO INDONESIA

INJECTION MOLDING CONDITION STANDARD

DATE : 27 JULI 2026

STATUS :

○

 TRIAL

●

 MASS PRO

PART NAME : BUSHING TL.4

PART NO. : DH610-11

CUSTOMER : PT. CABININDO

QUALITY CONTROL	ENGINEERING	PRODUCTION	PREPARED BY
			ENDANG S

INJECTION MACHINE

MC no/Ton.: 12/40T SCREW Ø : 26 mm

MODEL : PS40E5AMC

CONTROLLER : NC 9000

MATERIAL

NAME : PA UBE

GRADE : 1013 NW8

COLOUR : NATURAL

DRY UP TM : 4 H

DRY UP TMP : 120 °C

REGRIND : - %

MASTER BATCH : - %

PART

CAVITY : 8/8

TOTAL WEIGHT : 5,872 g

PART WEIGHT :

●

 0,328 g

●

 0,327 g

●

 0,326 g

●

 0,328 g

RUNNER WEIGHT : 3,259 g

:

●

 0,330 g

●

 0,326 g

●

 0,324 g

●

 0,324 g

ANNEALING STANDARD :

MOLD

MTC SETTING : 55 °C

MTC ACTUAL TEMP. : 55 °C

CHILLER TMP : °C

MOLD ACTUAL TEMPERATURE (± 5) °C

CAVITY SIDE : 56 °C

CORE SIDE : 50 °C

< INJ / MTG >

1. INJ TM : 5 sec

2. COOL TM : 10 sec

3. CYC ST TM : 0,2 sec

4. MTG ST. TM : - sec

5. NOZZLE BWD TM : - sec

6. V5 : 5 %

7. V4 : 12 %

8. V3 : 25 %

9. V2 : - %

10. V1 : - %

11. TP2 : 1 sec

12. S5 : 7 mm

13. S4 : 10 mm

14. S3 : 12 mm

15. S2 : - mm

16. S1 : - mm

17. SM : 14 mm

18. SD : 5 mm

19. P3 : 10 %

20. P2 : 30 %

21. P1 : 50 %

22. VS : 65 %

23. BACK PRESSURE : 10 kgf

BARREL TEMPERATURE (± 10) °C

NOZZLE

Set 230 °C

Act 230 °C

FRONT

Set 235 °C

Act 235 °C

MIDDLE

Set 225 °C

Act 225 °C

REAR

Set 220 °C

Act 225 °C

< OPEN CLOSE >

1. HI MILD CLS V : 35 %

2. CLAMP SLOW V : 20 %

3. LOW MLD CLS P : 10 %

3. HI MLD CLS P : 95 %

5. OPEN SLOW : 12 %

6. HI MLD OPEN V : 15 %

7. PRI OPEN V : 5 %

8 PRI OPEN TM : 0,2 %

< EJECTOR >

1. EJECT PRES : 35 %

2. FWD EV1 : 25 %

3. COUNT : 2 %

4. START TM : 0,2 %

5. MOMENT STOP : 1ST ~~LAST~~

6. BWD EV 4 : 45 %

7. BWD PRES : 45 %

8. STOP TM : 0,2 %

9. REPEAT EJECT EV 3 : 55 %

FEEDER TEMPERATURE (± 10) °C

°C

Limit Switch			Rev.No	Date	Description	Prod	PE	QC
LS 5	Eject forward stop	mm	△					
LS 14	Eject backward stop	mm						
LS 3	High Pressure Selection	mm	△					
LS 2	Low pressure mold clamping	mm						
LS 8	Mold opening slow down	mm	△					
LS 4	Mold opening stop	mm						

INJECTION MOLDING CONDITION STANDARD

*Referensi Pengisian Std. & Act. MCS

* DATA STATISTIC

[illegible]

FLOW COOLING SYSTEM

✓	ROBOT RUNNER SETTING	
✓	RE- TRACK	
	USE ROBOT RUNNER	
	NOT USE ROBOT RUNNER	
	RE- TRACK	
	NO RE-TRACK	
	EJECTOR OPERATING	
	NORMAL	☐ OVERRIDE
	MONITOR	
	COUNTER	
	NOZZLE NOT LEAKING	

[illegible]

LIMIT MATERIAL STAY IN HOPPER

	Kg
--	----