

PT. IMC TEKNO INDONESIA
INJECTION MOLDING CONDITION STANDARD

DATE : 28 JULI 2026

STATUS : ☒ TRIAL ☐ MASSPRO

PART NAME : BOBBIN ARMA TL.3

PART NO. : 1WD-8185X-02

CUSTOMER : PT. YAMAHA MOTOR ELECTRONIC INDONESIA

QUALITY CONTROL

ENGINEERING

PRODUCTION

PREPARED BY

ENDANG S

INJECTION MACHINE

MC no/Ton.: 30/140T SCREW Ø : 50

MODEL : ES3000-36E

CONTROLLER : TACT

MATERIAL

NAME : PA6 AMILAN

GRADE : CM1011 G30

COLOUR : BLACK

DRYUP TM : 4 H

DRYUP TMP : 90 °C

REGRIND : - %

MASTER BATCH : - %

PART

CAVITY : 4/4

TOTAL WEIGHT : 61,472 gr

PART WEIGHT : (A) 4,025 gr (C) 3,955 gr

RUNNER WEIGHT : 45,122 gr

(± 0.15 gr) : (B) 4,090 gr (D) 4,280 gr

ANNEALING STANDARD : -

MOLD

HEATER SET : 60 °C

HEATER ACT TEMP : 60 °C

CHILLER TMP : - °C

MOLD ACTUAL TEMPERATURE (± 5°C)

CAV.SIDE : 65 °C

CORE SIDE : 50 °C

MAIN DATA

INJ TM

INJECT 4 sec

COOL 30 sec

CYC START 0,2 sec

MTG START TM - sec

HI V 25 %

LOW V 20 %

L V L P 50 mm

H P CL 1,67 mm

LOW P 15 %

HI P 98 KN

OPEN

OPEN END V 20 %

HI V1 25 %

OPN ST 15 %

OPN STP 340 mm

SLW DSTNC 50 mm

HI V 25 mm

V6 - %

V5 - %

V4 - %

V3 55 %

V2 65 %

V1 75 %

3 Step

SV5 - mm

SV4 - mm

SV3 - mm

SV2 15 mm

SV1 25 mm

SM 45 mm

HOLD

Pp3 - %

Pp2 25 %

Pp1 35 %

TP2 -

TP1 1 s

2 Step

PRESSURE

PV3 - %

PV2 - %

PV1 75 %

Sp2 -

Sp1 - mm

1 Step

Decomp V 10

Decomp Before MTG -

SD 10 mm

Stroke -

EJECT

PATTERN 1

FWD EV1 20 %

FWD STOP 48 mm

EJT TMG -

STOP TM -

(± 10)°C

TEMP

NOZZLE

Setting 280 °C

Actual 280 °C

* FRONT

* HEAD - °C

* MIDDLE

* FRONT 285 °C

* MIDDLE 285 °C

* REAR1

* REAR 280 °C

* REAR2

* REAR 275 °C

FEED

273 °C

- °C

INJECTION MOLDING CONDITION STANDARD

* DATA STATISTIC

[illegible][illegible]

☒	ROBOT RUNNER SETTING	
☒	RE- TRACK	
☐	USE ROBOT RUNNER	
☐	NOT USE ROBOT RUNNER	
☐	RE- TRACK	
☐	NO RE-TRACK	
☒	EJECTOR OPERATING	
☐	☐	NORMAL ☐ OVERRIDE
☐	MONITOR	
☐	COUNTER	
☐	NOZZLE NOT LEAKING	

0	Kg
---	----