

PT. IMC TEKNO INDONESIA

INJECTION MOLDING CONDITION STANDARD

|                 |             |            |             |
|-----------------|-------------|------------|-------------|
| QUALITY CONTROL | ENGINEERING | PRODUCTION | PREPARED BY |
| ALREADY SIGN    |             |            |             |
| WAHYU J         |             |            | ENDANG S    |

DATE : 25 MEI 2026

STATUS : ☐ TRIAL ☒ MASS PRO

PART NAME : ROD A LOCK PIN

PART NO. : MB83-63101

CUSTOMER : PT. MTAT

INJECTION MACHINE

MC no/Ton.: 31/110T SCREW Ø: 45 mm

MODEL : FN2000-25A

CONTROLLER : NC 9000

MATERIAL

|                    |                     |                |
|--------------------|---------------------|----------------|
| NAME : PA66 AMILAN | GRADE : CM3001 G30  | COLOUR : BLACK |
| DRY UP TM : 4 H    | DRY UP TMP : 120 °C | REGRIND : - %  |
| MASTER BATCH : - % |                     |                |

PART

|                                                                                                                                 |                         |
|---------------------------------------------------------------------------------------------------------------------------------|-------------------------|
| CAVITY : 2/2                                                                                                                    | TOTAL WEIGHT : 43,492 g |
| PART WEIGHT : <input checked="" type="radio"/> 16,755 g <input type="radio"/> g <input type="radio"/> g <input type="radio"/> g | RUNNER WEIGHT : 9,817 g |
| : <input checked="" type="radio"/> 2 16,920 g <input type="radio"/> g <input type="radio"/> g <input type="radio"/> g           | ANNEALING STANDARD :    |

MOLD

|                                  |                          |                   |
|----------------------------------|--------------------------|-------------------|
| MTC SETTING : 50 °C              | MTC ACTUAL TEMP. : 50 °C | CHILLER TMP : °C  |
| MOLD ACTUAL TEMPERATURE (± 5) °C | CAVITY SIDE : 50 °C      | CORE SIDE : 48 °C |

< INJ / MTG >

|           |            |              |               |                  |
|-----------|------------|--------------|---------------|------------------|
| 1. INJ TM | 2. COOL TM | 3. CYC ST TM | 4. MTG ST. TM | 5. NOZZLE BWD TM |
| 5 sec     | 20 sec     | 0,2 sec      | - sec         | - sec            |

|       |       |       |       |        |
|-------|-------|-------|-------|--------|
| 6. V5 | 7. V4 | 8. V3 | 9. V2 | 10. V1 |
| 5 %   | 12 %  | 50 %  | 45 %  | 50 %   |

|         |        |        |        |        |        |        |        |
|---------|--------|--------|--------|--------|--------|--------|--------|
| 11. TP2 | 12. S5 | 13. S4 | 14. S3 | 15. S2 | 16. S1 | 17. SM | 18. SD |
| 1 sec   | 8 mm   | 10 mm  | 15 mm  | 20 mm  | 25 mm  | 35 mm  | 5 mm   |

|        |        |        |        |                   |
|--------|--------|--------|--------|-------------------|
| 19. P3 | 20. P2 | 21. P1 | 22. VS | 23. BACK PRESSURE |
| 20 %   | 26 %   | 65 %   | 70 %   | 17 kgf            |

BARREL TEMPERATURE (± 10) °C

NOZZLE

Set 285 °C

Act 279 °C

FRONT

Set 275 °C

Act 275 °C

MIDDLE

Set 265 °C

Act 265 °C

REAR

Set 250 °C

Act 250 °C

< OPEN CLOSE >

|                  |                  |                  |                 |
|------------------|------------------|------------------|-----------------|
| 1. HI MILD CLS V | 2. CLAMP SLOW V  | 3. LOW MLD CLS P | 3. HI MLD CLS P |
| 25 %             | 20 %             | 17 %             | 85 %            |
| 5. OPEN SLOW     | 6. HI MLD OPEN V | 7. PRI OPEN V    | 8 PRI OPEN TM   |
| 20 %             | 25 %             | 15 %             | 0,2 %           |

< EJECTOR >

|                      |             |             |             |
|----------------------|-------------|-------------|-------------|
| 1. EJECT PRES        | 2. FWD EV1  | 3. COUNT    | 4. START TM |
| 25 %                 | 15 %        | 1 %         | 0,5 %       |
| 5. MOMENT STOP       | 6. BWD EV 4 | 7. BWD PRES | 8. STOP TM  |
| 1ST LAST             | 55 %        | 55 %        | 0,5 %       |
| 9. REPEAT EJECT EV 3 |             |             |             |
| 65 %                 |             |             |             |

FEEDER TEMPERATURE (± 10) °C

°C

| Limit Switch |                            |    | Rev.No | Date | Description | Prod | PE | QC |
|--------------|----------------------------|----|--------|------|-------------|------|----|----|
| LS 5         | Eject forward stop         | mm | △      |      |             |      |    |    |
| LS 14        | Eject backward stop        | mm |        |      |             |      |    |    |
| LS 3         | High Pressure Selection    | mm | △      |      |             |      |    |    |
| LS 2         | Low pressure mold clamping | mm |        |      |             |      |    |    |
| LS 8         | Mold opening slow down     | mm | △      |      |             |      |    |    |
| LS 4         | Mold opening stop          | mm |        |      |             |      |    |    |

## INJECTION MOLDING CONDITION STANDARD

\*Referensi Pengisian Std. & Act. MCS

### \* DATA STATISTIC

[illegible]

## FLOW COOLING SYSTEM

|   |                      |                                   |
|---|----------------------|-----------------------------------|
| ✓ | ROBOT RUNNER SETTING |                                   |
| ✓ | RE- TRACK            |                                   |
|   | USE ROBOT RUNNER     |                                   |
|   | NOT USE ROBOT RUNNER |                                   |
|   | RE- TRACK            |                                   |
|   | NO RE-TRACK          |                                   |
|   | EJECTOR OPERATING    |                                   |
|   | NORMAL               | <input type="checkbox"/> OVERRIDE |
|   | MONITOR              |                                   |
|   | COUNTER              |                                   |
|   | NOZZLE NOT LEAKING   |                                   |

This image shows a single sheet of white paper with horizontal ruling lines. The lines are evenly spaced and run across the width of the page. There are no margins, text, or other markings on the paper.

### LIMIT MATERIAL STAY IN HOPPER

|  |    |
|--|----|
|  | Kg |
|--|----|