

PT. IMC TEKNO INDONESIA

INJECTION MOLDING CONDITION STANDARD

QUALITY CONTROL	ENGINEERING	PRODUCTION	PREPARED BY
ALREADY SIGN			
WAHYU J			ENDANG S

DATE	: 25 MEI 2026
STATUS	: ☐ TRIAL ☒ MASS PRO
PART NAME	: BOBBIN ARMA TL.3
PART NO.	: 1WD-8185X-08
CUSTOMER	: PT. YEID

INJECTION MACHINE

MC no/Ton.: 46/140T SCREW Ø: 56 mm	MODEL : FN3000-36A	CONTROLLER : NC 9000
------------------------------------	--------------------	----------------------

MATERIAL

NAME : PA6 AMILAN	GRADE : CM1011 G30	COLOUR : BLACK
DRY UP TM : 4 H	DRY UP TMP : 120 °C	REGRIND : - %
MASTER BATCH : - %		

PART

CAVITY : 4/4	TOTAL WEIGHT : 62,473 g
PART WEIGHT : ☒ 4,008 g ☒ 4,294 g ☐ g ☐ g	RUNNER WEIGHT : 45,083 g
: ☒ 4,115 g ☒ 4,973 g ☐ g ☐ g	ANNEALING STANDARD :

MOLD

HEATER SET : 60 °C	HEATER ACT TEMP. : 60 °C	CHILLER TMP : °C
MOLD ACTUAL TEMPERATURE (± 5) °C	CAVITY SIDE : 60 °C	CORE SIDE : 57 °C

< INJ / MTG >

1. INJ TM 4 sec	2. COOL TM 35 sec	3. CYC ST TM 0,2 sec	4. MTG ST. TM - sec	5. NOZZLE BWD TM - sec			
6. V5 65 %	7. V4 75 %	8. V3 85 %	9. V2 - %	10. V1 - %			
11. TP2 1 sec	12. S5 8 mm	13. S4 12 mm	14. S3 20 mm	15. S2 - mm	16. S1 - mm	17. SM 28 mm	18. SD 5 mm
	19. P3 25 %	20. P2 30 %	21. P1 65 %	22. VS 65 %	23. BACK PRESSURE 10 kgf		

BARREL TEMPERATURE (± 10) °C

NOZZLE	
Set	265 °C
Act	267 °C

FRONT	
Set	280 °C
Act	280 °C

< OPEN CLOSE >

1. HI MILD CLS V 30 %	2. CLAMP SLOW V 25 %	3. LOW MLD CLS P 20 %	3. HI MLD CLS P 85 %
5. OPEN SLOW 20 %	6. HI MLD OPEN V 45 %	7. PRI OPEN V 15 %	8 PRI OPEN TM 0,2 %

MIDDLE	
Set	275 °C
Act	275 °C

< EJECTOR >

1. EJECT PRES 35 %	2. FWD EV1 25 %	3. COUNT 2 %	4. START TM 0,2 %
5. MOMENT STOP 1ST LAST	6. BWD EV 4 65 %	7. BWD PRES 65 %	8. STOP TM 0,2 %
9. REPEAT EJECT EV 3 65 %			

REAR	
Set	260 °C
Act	260 °C

FEEDER TEMPERATURE (± 10) °C

°C

Limit Switch			Rev.No	Date	Description	Prod	PE	QC
LS 5	Eject forward stop	mm	△					
LS 14	Eject backward stop	mm						
LS 3	High Pressure Selection	mm	△					
LS 2	Low pressure mold clamping	mm						
LS 8	Mold opening slow down	mm	△					
LS 4	Mold opening stop	mm						

INJECTION MOLDING CONDITION STANDARD

*Referensi Pengisian Std. & Act. MCS

* DATA STATISTIC

NO	DESCRIPTION	UNIT	STD	TOLERANSI
	MOLD			
01 a	MTC No.		-	
b	MTC Temp. Oli / Water *	°C	60	±10
02	Chiller Temp.	°C	-	±5
03	Core Temp.	°C	57	±5
04	Cavity Temp.	°C	60	±5
	TIMING			
05	Injection TM	Sec	4	±0
06	Cooling TM	Sec	35	±0
07	TP2	Sec	1	±1
	SPEED			
08	V1	%	-	±10
09	V2	%	-	±10
10	V3	%	85	±10
11	V4	%	75	±5
12	V5	%	65	±5
	PRESSURE			
13	P1 / PV1 *	%	65	±10
14	PV2	%	-	±10
15	PV3	%	-	±10
	HOLD			
16	P2 / Pp1 *	%	30	±10
17	P3 / Pp2 *	%	25	±10
	INJECTION DISTANCE			
18	SD	mm	5	±5
19	SM	mm	28	±5
20	S1 / SV1 *	mm	-	±5
21	S2 / SV2 *	mm	-	±5
22	S3 / SV3 *	mm	20	±5
23	S4 / SV4 *	mm	12	±5
24	S5 / SV5 *	mm	8	±5
25	BACK PRESS	Kgf/cm ²	10	±5
	BAREL TEMP			
26	NOZZLE	°C	265	±10
27	*HEAD *FRONT	°C	-	±10
28	*FRONT *MIDDLE	°C	280	±10
29	*MIDDLE *REAR 1	°C	275	±10
30	*REAR *REAR 2	°C	260	±10
	HOPPER DRYER			
31	TEMPERATURE	°C	120	±10
	PART			
32	Cav.No	Pcs	4/4	
33	Part Weight / Shoot	Gr	17,39	
34	Runner Weight / Shoot	Gr	45,083	
35	Total Weight / Shoot	Gr	62,473	

LIMIT MATERIAL STAY IN HOPPER

	Kg
--	----

[illegible]

FLOW COOLING SYSTEM

✓	ROBOT RUNNER SETTING	
✓	RE- TRACK	
	USE ROBOT RUNNER	
	NOT USE ROBOT RUNNER	
	RE- TRACK	
	NO RE-TRACK	
	EJECTOR OPERATING	
	NORMAL	☐ OVERRIDE
	MONITOR	
	COUNTER	
	NOZZLE NOT LEAKING	