

PT. IMC TEKNO INDONESIA

INJECTION MOLDING CONDITION STANDARD

QUALITY CONTROL	ENGINEERING	PRODUCTION	PREPARED BY
			NURRONI

DATE : 28 MEI 2026

STATUS :

TRIAL

V

 MASS PRO

PART NAME : GEAR DRIVENT TL.2

PART NO. : DA4-E3325-00

CUSTOMER : PT. IHARA

INJECTION MACHINE

MC no/Ton.: 02/80T SCREW Ø: 40 mm

MODEL : FE80S18A

CONTROLLER : NC 9000

MATERIAL

NAME : PA66 AMILAN

GRADE : CM3006 G30

COLOUR : NATURAL

DRY UP TM : 4 H

DRY UP TMP : 90 °C

REGRIND : - %

MASTER BATCH : - %

PART

CAVITY : 2/2

TOTAL WEIGHT : 26,237 g

PART WEIGHT :

3

 6,475 g g g g

RUNNER WEIGHT : 13,280 g

ANNEALING STANDARD :

:

4

 6,482 g g g g

MOLD

MTC SETTING : - °C

MTC ACTUAL TEMP. : - °C

CHILLER TMP : 18 °C

MOLD ACTUAL TEMPERATURE (± 5) °C

CAVITY SIDE : - °C

CORE SIDE : - °C

< INJ / MTG >

1. INJ TM

2. COOL TM

3. CYC ST TM

4. MTG ST. TM

5. NOZZLE BWD TM

4 sec

15 sec

0,2 sec

- sec

- sec

6. V5

7. V4

8. V3

9. V2

10. V1

3 %

5 %

10 %

20 %

30 %

11. TP2

12. S5

13. S4

14. S3

15. S2

16. S1

17. SM

18. SD

1 sec

7 mm

10 mm

12 mm

15 mm

20 mm

25,5 mm

5 mm

19. P3

20. P2

21. P1

22. VS

23. BACK PRESSURE

35 %

K1 30 %

75 %

70 %

10 kgf

K2 32 => dimensi NG , APP Cav 3 (burry), Cav 4 (OK)

K3 35 => dimensi NG, App : NG (Burry)

< OPEN CLOSE >

1. HI MILD CLS V

2. CLAMP SLOW V

3. LOW MLD CLS P

3. HI MLD CLS P

20 %

20 %

20 %

85 %

5. OPEN SLOW

6. HI MLD OPEN V

7. PRI OPEN V

8 PRI OPEN TM

15 %

25 %

15 %

0,2 %

< EJECTOR >

1. EJECT PRES

2. FWD EV1

3. COUNT

4. START TM

- %

15 %

1 %

1 %

5. MOMENT STOP

6. BWD EV 4

7. BWD PRES

8. STOP TM

1ST LAST

- %

15 %

1 %

9. REPEAT EJECT EV 3

- %

BARREL TEMPERATURE (± 10) °C

NOZZLE

Set 280 °C

Act 281 °C

FRONT

Set 275 °C

Act 275 °C

MIDDLE

Set 270 °C

Act 270 °C

REAR

Set 265 °C

Act 265 °C

FEEDER TEMPERATURE (± 10) °C

°C

Limit Switch			Rev.No	Date	Description	Prod	PE	QC
LS 5	Eject forward stop	mm	△					
LS 14	Eject backward stop	mm						
LS 3	High Pressure Selection	mm	△					
LS 2	Low pressure mold clamping	mm						
LS 8	Mold opening slow down	mm	△					
LS 4	Mold opening stop	mm						

INJECTION MOLDING CONDITION STANDARD

*Referensi Pengisian Std. & Act. MCS

✓	ROBOT RUNNER SETTING	
✓	RE- TRACK	
	USE ROBOT RUNNER	
	NOT USE ROBOT RUNNER	
	RE- TRACK	
	NO RE-TRACK	
	EJECTOR OPERATING	
	NORMAL	☐ OVERRIDE
	MONITOR	
	COUNTER	
	NOZZLE NOT LEAKING	

NO	DESCRIPTION	UNIT	STD	TOLERANCE
	MOLD			
01 a	MTC No.		-	
b	MTC Temp. Oil / Water *	°C	-	±10
02	Chiller Temp.	°C	18	±5
03	Core Temp.	°C	-	±5
04	Cavity Temp.	°C	-	±5
	TIMING			
05	Injection TM	Sec	4	±0
06	Cooling TM	Sec	15	±0
07	TP2	Sec	1	±1
	SPEED			
08	V1	%	30	±10
09	V2	%	20	±10
10	V3	%	10	±10
11	V4	%	5	±5
12	V5	%	3	±5
	PRESSURE			
13	P1 / PV1 *	%	75	±10
14	PV2	%	-	±10
15	PV3	%	-	±10
	HOLD			
16	P2 / Pp1 *	%	30	±10
17	P3 / Pp2 *	%	35	±10
	INJECTION DISTANCE			
18	SD	mm	5	±5
19	SM	mm	25,5	±5
20	S1 / SV1 *	mm	20	±5
21	S2 / SV2 *	mm	15	±5
22	S3 / SV3 *	mm	12	±5
23	S4 / SV4 *	mm	10	±5
24	S5 / SV5 *	mm	7	±5
25	BACK PRESS	Kgf/cm ²	10	±5
	BAREL TEMP			
26	NOZZLE	°C	280	±10
27	*HEAD *FRONT	°C	-	±10
28	*FRONT *MIDDLE	°C	275	±10
29	*MIDDLE *REAR 1	°C	270	±10
30	*REAR *REAR 2	°C	265	±10
	HOPPER DRYER			
31	TEMPERATURE	°C	90	±10
	PART			
32	Cav.No	Pcs	2/2	
33	Part Weight / Shoot	Gr	12,957	
34	Runner Weight / Shoot	Gr	13,28	
35	Total Weight / Shoot	Gr	26,237	

LIMIT MATERIAL STAY IN HOPPER

	Kg
--	----

[illegible]

FLOW COOLING SYSTEM

[illegible]