

PT. IMC TEKNO INDONESIA

INJECTION MOLDING CONDITION STANDARD

DATE : 28 MEI 2026

STATUS :

TRIAL

V

 MASS PRO

PART NAME : SEAT B SPRING TL.7

PART NO. : HK0J2-393-02-IN

CUSTOMER : PT. ASTEMO BEKASI Mfg

QUALITY CONTROL	ENGINEERING	PRODUCTION	PREPARED BY
ALREADY SIGN			
WAHYU J			SUDIN K

INJECTION MACHINE

MC no/Ton.: 08/160T SCREW Ø : 50 mm

MODEL : FS160S36ASE

CONTROLLER : NC 8000 ; NC 8300

MATERIAL

NAME : GFPP-30

GRADE : HSBK 018 (PPGF 30%)

COLOUR : BLACK

DRY UP TM : 3 H

DRY UP TMP : 80 °C

REGRIND : - %

MASTER BATCH : - %

PART

CAVITY : 4/4

TOTAL WEIGHT : 261,692 g

PART WEIGHT : (21) ##### g (23) 60,973 g

RUNNER WEIGHT : 17,830 g

(± 0.15 gr) : (22) ##### g (24) 60,877 g

ANNEALING STANDARD : -

MOLD

MTC SETTING : 80 °C

MTC ACTUAL TEMP. : 80 °C

CHILLER TMP : °C

MOLD ACTUAL TEMPERATURE (± 5) °C

CAVITY SIDE : 78 °C

CORE SIDE : 75 °C

CONDITION

TIMER

TM1 INJ TM : 15 sec

TM2 COOL TM : 90 sec

TM3 ST TM : 0,2 sec

V5 : - %

V4 : - %

V3 : 18 %

V2 : 90 %

V1 : 60 %

VS : 75 %

MOLD CLOSE

CV1 : 10 %

CV2 : 15 %

CP2 : 20 %

S4 : - mm

S3 : - mm

S2 : 70 mm

S1 : 150 mm

SM : 155 mm

SD : 5 mm

MOLD OPEN

OV 3 : 10 %

OV 2 : 20 %

OT 2 : 1 sec

EJECTOR

EV 1 : 15 %

ETC : 1

OPTION

HI MILD CLS P : 01 90

PRI OPEN V : 03 0,2

MTG ST TM : 04 5 sec

BARREL TEMPERATURE (± 10) °C

NOZZLE : Set 225 °C Act 225 °C

FRONT : Set 220 °C Act 220 °C

MIDDLE : Set 210 °C Act 210 °C

REAR : Set 195 °C Act 195 °C

BACK PRESSURE Kgf/cm²

Limit Switch			Rev.No	Date	Description	Prod	PE	QC
LS 5	Eject forward stop	mm	△					
LS 14	Eject backward stop	mm						
LS 3	High Pressure Selection	mm	△					
LS 2	Low pressure mold clamping	mm						
LS 8	Mold opening slow down	mm	△					
LS 4	Mold opening stop	mm						

INJECTION MOLDING CONDITION STANDARD

* DATA STATISTIC

[illegible]

This image shows a single sheet of white paper with horizontal blue or grey ruling lines. The lines are evenly spaced and run across the width of the page. There are approximately 20 lines visible. The paper has a slight shadow on its right side, suggesting it's resting on a surface.

LIMIT MATERIAL STAY IN HOPPER

HAL : 2/2