

| Property                                                             | Latex                                                                      |
|----------------------------------------------------------------------|----------------------------------------------------------------------------|
| Thickness (single)                                                   | Middle finger $\geq 0.17$ mm<br>Palm $\geq 0.14$ mm<br>Cuff $\geq 0.11$ mm |
| Length                                                               | 240 mm or above                                                            |
| Tensile Strength                                                     | $\geq 21$ Mpa                                                              |
| Ultimate elongation                                                  | $\geq 700\%$                                                               |
| Tensile Strength after aging                                         | $\geq 16$ Mpa                                                              |
| Ultimate elongation after aging                                      | $\geq 500\%$                                                               |
| Concentration of extractable proteins on latex gloves (Lowry method) | Powder $\leq 100$<br>Powder Free $\leq 30$                                 |

| Property                                                             | Nitrile                                                                    |
|----------------------------------------------------------------------|----------------------------------------------------------------------------|
| Thickness (single)                                                   | Middle finger $\geq 0.15$ mm<br>Palm $\geq 0.13$ mm<br>Cuff $\geq 0.11$ mm |
| Length                                                               | 240 mm or above                                                            |
| Tensile Strength                                                     | $\geq 21$ Mpa                                                              |
| Ultimate elongation                                                  | $\geq 700\%$                                                               |
| Tensile Strength after aging                                         | $\geq 16$ Mpa                                                              |
| Ultimate elongation after aging                                      | $\geq 500\%$                                                               |
| Concentration of extractable proteins on latex gloves (Lowry method) | Not Detectable                                                             |

| Category  | Inspection Level & Sampling Plan | AQL |
|-----------|----------------------------------|-----|
| Critical  | G-1                              | 1.0 |
| Major     | G-1                              | 1.5 |
| Minor     | G-1                              | 2.5 |
| Physicals | S-2                              | 2.5 |