

DESIGN VERIFICATION REPORT

Meridian Neurovascular (fictional) — synthetic fixture for interview use only

Document: NV-200-VR-014
Title: Design Verification Report — NeuroFlow NV-200 Access Guidewire
Revision: 2.0
Verifies protocol: NV-200-TP-014, Version 2.1
Testing performed: 15 to 19 June 2026
Date: 24 July 2026
Test equipment: Instron 5943 (serial 5943-11); calibration due 31 March 2027

1. Summary

Verification testing of the NeuroFlow NV-200 access guidewire was carried out between 15 and 19 June 2026 against the acceptance criteria of NV-200-TP-014 Version 2.1. All five tests defined by that protocol were performed at the sample sizes and under the conditions it specifies. Results are recorded in section 2. A human reviewer determines pass or fail against the protocol criteria.

2. Results

Test ID	Test	Acceptance criterion	n tested	Result and disposition
T1	Tensile bond strength	$\geq 5.0\text{ N}$	30	Min 5.3 N, mean 6.4 N. Tested in 37°C saline bath. Pass.
T2	Coating particulate	≤ 20 particles $\geq 10\text{ }\mu\text{m}$ per unit	30	Max 12 particles. Pass.
T3	Tip flexibility (bend force)	0.20 – 0.40 N	30	Range 0.24 – 0.36 N, mean 0.30 N. Tested at 37°C. Pass.
T4	Corrosion resistance	No visible corrosion at 24 h	10	No visible corrosion at 24 h. Pass.
T5	Cytotoxicity (biocompatibility)	Reactivity grade ≤ 2	3	Reactivity grade 1. Pass.

3. Deviations

No deviation from NV-200-TP-014 Version 2.1 arose during this verification. Sample sizes, test conditions, instrumentation and acceptance criteria were as specified by the protocol. This section is recorded as nil rather than omitted, so that its absence cannot be read as an oversight.

4. Conclusion

Results for all five tests required by NV-200-TP-014 Version 2.1 are recorded above against the acceptance criteria of that protocol version, with the raw data held in the design history file. Disposition of each test, and any decision on release to the next design phase, rests with the reviewer and the design team.