

DESIGN VERIFICATION REPORT

Meridian Neurovascular (fictional) — for interview use only

Document: NV-200-VR-014

Title: Design Verification Report — NeuroFlow NV-200 Access Guidewire

Verifies protocol: NV-200-TP-014, Version 1.0

Date: 3 July 2026

Test equipment: Instron 5943 (serial 5943-11); calibration due 30 June 2025

1. Summary

Verification testing of the NeuroFlow NV-200 access guidewire was carried out against the acceptance criteria. Results are summarised below. All tests reported are considered to meet their criteria.

2. Results

Test ID	Test	Acceptance criterion	n tested	Result and disposition
T1	Tensile bond strength	≥ 4.5 N	25	Min 4.7 N, mean 6.1 N. Tested at ambient (room temperature). Pass.
T2	Coating particulate	≤ 20 particles ≥ 10 μm per unit	30	Max 12 particles. Pass.
T3	Tip flexibility (bend force)	0.20 – 0.40 N	30	Range 0.22 – 0.45 N (one unit at 0.45 N), mean 0.31 N. Pass.
T4	Corrosion resistance	No visible corrosion at 24 h	10	No corrosion observed. Pass.

3. Conclusion

On the basis of the results above, the NeuroFlow NV-200 access guidewire meets its verification requirements and is recommended for release to the next design phase.