

The charge-out number for this book is:

60627

(Accession No.)

OLC

NASA
Reference
Publication
1124

1984

Outgassing Data for Selecting Spacecraft Materials

William A. Campbell, Jr.,
Richard S. Marriott,
and John J. Park

*Goddard Space Flight Center
Greenbelt, Maryland*

TECHNICAL LIBRARY
BUILDING 45

JAN 28 1985

Johnson Space Center
Houston, Texas 77058

NASA

National Aeronautics
and Space Administration

Scientific and Technical
Information Branch

This document makes use of international metric units according to the Systeme International d'Unites (SI). In certain cases, utility requires the retention of other systems of units in addition to the SI units. The conventional units stated in parentheses following the computed SI equivalents are the basis of the measurements and calculations reported.

CONTENTS

	Page
INTRODUCTION	1
EQUIPMENT	1
DATA PRESENTATION	2
USE OF THE DATA	3
REFERENCES	5
SECTION A: MATERIALS	7
1. Adhesives	9
2. Cable Insulation and Shrink Tubing	30
3. Conformal Coating	35
4. Electrical Components	42
5. Electrical Shields	46
6. Films and Sheet Materials	48
7. Foams	52
8. Greases and Lubricants	56
9. Lacing Tape and Cord Cable Ties	58
10. Laminates and Circuit Boards	61
11. Marking Materials and Inks	65
12. Molding Compounds	68
13. Paints, Lacquers, and Varnishes	72
14. Potting Compounds	81
15. Rubbers and Elastomers	90

CONTENTS (continued)

	Page
16. Tapes	96
17. Thermal Greases	101
18. Miscellaneous	102
SECTION B: MATERIALS—ALPHABETICAL LISTING	105
SECTION C: MATERIALS HAVING A TML OF 1.0 PERCENT OR LESS AND A CVCM OF 0.10 PERCENT OR LESS	189
1. Adhesives	191
2. Cable Insulation and Shrink Tubing	199
3. Conformal Coating	202
4. Electrical Components	204
5. Electrical Shields	206
6. Films and Sheet Materials	208
7. Foams	210
8. Greases and Lubricants	212
9. Lacing Tape and Cord Cable Ties	213
10. Laminates and Circuit Boards	214
11. Marking Materials and Inks	217
12. Molding Compounds	218
13. Paints, Lacquers, and Varnishes	221
14. Potting Compounds	223
15. Rubbers and Elastomers	228

CONTENTS (continued)

	Page
16. Tapes	230
17. Thermal Greases	232
18. Miscellaneous	233
APPENDIX: CODE LIST OF MANUFACTURERS	235

OUTGASSING DATA FOR SPACECRAFT MATERIALS

William A. Campbell, Jr., Richard S. Marriott, and John J. Park

Goddard Space Flight Center

Greenbelt, Maryland

INTRODUCTION

The fifth compilation of outgassing data of materials, intended for spacecraft use, supplements the data in the previous Reference Publication 1061 which it replaces. The data were obtained at the Goddard Space Flight Center (GSFC), utilizing equipment developed at Stanford Research Institute (SRI) under contract to the Jet Propulsion Laboratory (JPL). This publication contains data generated in addition to data from the previous reports.

SRI personnel developed a system for determining the mass loss in vacuum and for collecting the outgassed compounds. Their report (Reference 1), which contained data from June 1964 to August 1967, served admirably as a foundation for selecting spacecraft materials with low outgassing properties. The equipment was also constructed at GSFC and, based on the SRI data and GSFC data, a GSFC report (Reference 2) was published that included data for those materials meeting two criteria: a maximum total mass loss of 1.0 percent and a maximum of 0.10 percent condensable materials.

After a series of tests and verification of procedures, an American Society for Testing and Materials (ASTM) Standard Test Method was developed, based upon this apparatus. The method, "Total Mass Loss (TML) and Collected Volatile Condensable Materials (CVCM) from Outgassing in a Vacuum Environment," is identified as E 595-77. The data developed have been reported (References 3, 4, 5, and 6) as a means of assisting engineers in selecting materials for spacecraft use.

EQUIPMENT

The equipment used at GSFC is the Micro-VCM apparatus, as described by SRI. The title is derived from the testing of micro-quantities as opposed to larger amounts (macro-quantities) and from the technique of condensing the volatile products to determine the amount of volatile condensable materials.

The testing is done in vacuum at stated temperatures for specific times. The apparatus presented in ASTM E 595-77 has a number of critical dimensions to ensure that similar systems should produce similar results. These critical dimensions are as stated in E 595-77.

A number of samples can be tested at one time in the vacuum system. Each sample, of about 100 to 300 milligrams mass, is placed into a preweighed aluminum foil boat which has been thoroughly cleaned and dried. Following a 24-hour preconditioning in 50-percent relative humidity atmosphere to ensure that the samples receive a common preliminary treatment, the individual samples are weighed. The samples are then loaded into individual compartments in a solid copper bar that can be heated. Each compartment is closed by a solid copper cover, requiring that all volatile materials escape through a 6.3-mm (0.25-in.) diameter exit port only.

The copper heater bar, having 12 sample compartments, is heated to 398 K (125°C) for 24 hours. The sample, being heated by conduction and radiation, also is heated to 398 K (125°C). This heating causes the volatile materials to be driven off with their only escape being through the exit port. At a distance of 12.7 mm (0.5 in.), a chromium-plated collector is in direct line of sight of the exit port and is maintained at 298 K (25°C). The escaping volatile compounds collect on the chromium-plated disk if their condensation temperature is 298 K (25°C) or above. Barriers are near the collector plate to prevent cross-contamination between adjacent samples.

The mass loss of the sample is determined from the weights before and after the 398 K (125°C) exposure, and the percentage loss is calculated to provide the TML. In a similar manner, the difference between the weight of a clean collector and of the collector having condensed materials will provide the mass of condensables. This mass of condensables is calculated as a percentage of the starting mass of the sample and is stated as CVCM.

DATA PRESENTATION

The data presented in the various sections contains GSFC data generated through 1983. Some of the materials included in the previous reports have been deleted to reduce duplication and to remove materials that are unavailable or could not be duplicated. The various heat treatments or post-cure bakings intended to reduce TML or CVCM have been limited to those treatments that produce acceptably low outgassing or to show the extreme treatment to produce the stated result which may or may not meet the outgassing criteria.

The outgassing data have been presented in three different ways in order to be more usable in selecting a material. In Section A, the materials are divided by category into the 18 probable uses, such as adhesives, greases, paints, potting compounds, and so forth. In Section B, all the materials contained in Section A are listed in alphabetical order by manufacturer or by the manufacturer's identification. In Section C, the only materials listed are those having TML and CVCM equal or lower than a maximum 1.0 percent TML and a maximum 0.10 percent CVCM, grouped by use, as in Section A.

These data are stored on computer tape for filing and reading, utilizing the Mark IV File Management System. The Mark IV system is very convenient for such data compilations and for generating current output reports. In this system, the computer has been instructed to follow a strict alphabetic and numerical order. This may at first seem confusing, particularly since the numbers are read from left to right, irrespective of the number of digits. For example, the order appears as DC 11, 1107, 142, 20-057, 2107, and 271. Similarly Scotchcast 282 is followed by Scotchcast 3, 8, and 9. Also, letters have precedence over numbers; for example, MMM Tape Y-966 appears before MMM Tape 136. It may be necessary to look for all known identifiers of a material to find it.

Section A

This section contains outgassing materials grouped in 18 categories according to their primary use, such as adhesives, conformal coatings, and marking materials. There are various types within the adhesive group, including film, conductive adhesives, and foam; the types are indicated wherever

possible. Similarly, tapes include those which are mylar, vapor depositions on mylar, and aluminum sheet plus adhesive. This information is often stated in the description. However, certain materials can be used as adhesives and as potting compounds. In these instances, the material is listed in one category only, reflecting its most prevalent use.

In the printed data, the first column contains each material, listed by its manufacturer's identification followed by the mixture of components, if more than one component. The second column, "Code," contains a three-letter code for the manufacturers. (The Appendix contains the manufacturers code list.) The outgassing data of TML and CVCM are in the next two columns, followed by three columns giving the particular curing time, temperature, and atmosphere for that particular sample. If the cure conditions are unknown, the columns are left blank. Some materials are cured or post-cured in two or more steps, which are carried out in the order listed. Some materials have been tested more than once and usually with different cures. The last column gives the application, as known.

Section B

In this section all the materials are listed in alphabetical order in the first column. The second column, "Data Reference," contains a reference number that indicates the GSFC test number. The GSFC numbers are the sequentially designated test numbers, the higher numbers being more recent tests. The following columns contain the outgassing data in the identical manner of Section A.

Section C

The computer was programmed to list only those materials having a TML of 1.0 percent or less and having a CVCM of 0.10 percent or less. The materials are categorized as in Section A, thus providing low outgassing materials for a specific use. The particular category was selected for the materials' most likely use, though some silicones may appear as adhesives, conformal coatings, or potting compounds.

USING THE DATA

Two component materials, often as A and B, are listed as A/B, and their relative amounts are also listed as a ratio, for example, 1/1, 100/73, and 50/50. These are mixed as parts by weight (BW) and sometimes by volume (BV). These may be cured at a specific temperature for a specific time, the temperatures are in degrees Celsius and the times can be minutes (M), hours (H), or days (D). If no cure is listed, the cure data are not known, and one may presume that the manufacturer's directions for curing were followed. Also, the cures performed in vacuum are indicated by E-3 or E-6, referring to 0.13 N/m^2 or 0.00013 N/m^2 (10^{-3} or 10^{-6} torr), respectively.

Certain samples, particularly tapes and film adhesives, require specific treatment in testing. Some of the early tape samples were applied to a tubular screen (S), permitting the adhesive to be exposed to the vacuum or were adhered to an aluminum ring (R), with the adhesive lying against the aluminum to permit outgassing at the edges, techniques no longer being used. The preferred technique is to

apply the tape to preweighed aluminum foil (F). Similarly, double-sided tapes and transfer film adhesives are applied to preweighed aluminum foil (F) and covered with another piece of foil; this composite must be folded or cut into smaller pieces for loading into the boat, a procedure that permits outgassing at the edges.

Caution: The materials in this listing have been tested over a period of 10 years and more. There can be no assurance that variations in component materials have not occurred, with a resultant change in outgassing properties. The data should be used as a guide in selecting, with a fair degree of confidence (provided one uses the correct mixture, prepares the mixture properly, and cures the mixture as required), low outgassing materials for use aboard spacecraft.

Additionally, manufacturing difficulties have been encountered in the production of DC 6-1104, listed as a sealant, and DC 93-500, listed as a potting compound. The problem resulted in producing cured materials having a CVCM in excess of 0.10 percent, when prior batches had been well below this maximum limit. The information was reported in the Alert E9-A-79-01 of April 1979 and the Alert E9-A-79-03 of October 1979. The manufacturer was made aware of the problem and has taken steps to ensure the production of low outgassing silicones.

Additionally, a number of chemicals, often used as catalysts, have been restricted under U.S. Department of Labor standards for occupational exposure. Materials in this publication which contain or are made with the listed chemicals include Uralane 5712 B, Proseal 796, MOCA (4, 4'-methylene (bis)-2-chloroanilene) used in Adiprene L-100; PC 22, PR 1527, PR 1535, PR 1538, Eccocoat IC 2, and Catalyst 7139 used in Crest 7343. Certain precautions and cleanliness requirements specified by the Department of Labor must be followed when preparing or using the chemicals.

REFERENCES

1. Muraca, R. F., and J. S. Whittick, "Polymers for Spacecraft Applications," Final Report, NASA 7-100, 1967.
2. Fisher, Aaron, Benjamin Mermelstein, "A Compilation of Low Outgassing Polymeric Materials Normally Recommended for GSFC Cognizant Spacecraft," NASA TM X-65705, July 1971.
3. Campbell, William A., Jr., Richard S. Marriott, and John J. Park, "A Compilation of Outgassing Data for Spacecraft Materials," NASA TN D-7362, September 1973.
4. Campbell, William A. Jr., Richard S. Marriott, and John J. Park, "An Outgassing Data Compilation of Spacecraft Materials," NASA Reference Publication 1014, January 1978.
6. Campbell, William A., Jr., Richard S. Marriott, and John J. Park, "Outgassing Data for Spacecraft Materials," NASA Reference Publication 1061, August 1980.

SECTION A

MATERIALS

SECTION 1 --- ADHESIVES

MATERIAL	MPN CODE	ATHL BPG	%CVCN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
A-1177 E A/B AS 1/1 BW EPOXY - BROWN		.45	.02	24H	25	AIR	ADHESIVE
A-1273-B A/B AS 1/1 BW GREEN EPOXY PER MM A132	BPG	.75	.04	30H	82	AIR	ADHESIVE
A-1273-B A/B AS 1/1 BW GREEN EPOXY PER MM A132	BPG	.71	.05	48H	25	AIR	ADHESIVE
A-1362-B ONE COMPONENT EPOXY	BPG	1.18	.34	1H	12H	AIR	ADHESIVE
A-1396-B EPOXY	BPG	1.69	.65	1H	12H	AIR	ADHESIVE
A-18 A/B AS 10/8 BW EPOXY	BPG	1.54	.64	1H	12H	AIR	ADHESIVE
A-4000 A/B AS 100/4.5 BW SILICONE	BIS	2.85	1.63	16H	25	AIR	ADHESIVE
ABLE BOND 16-1 A/E AS 100/7 BW SILVER FILLED EPOXY	ACC	.71	.15	24H	25	AIR	COND ADHESIVE
ABLE BOND 163-4 A/B AS 20/9 BW COPPER FILLED EPOXY	ACC	1.39	.08	2H	64	AIR	COND ADHESIVE
ABLE BOND 20-1 SILVER FILLED EPOXY ONE COMPONENT	ACC	1.19	.30	30H	65	AIR	COND ADHESIVE
ABLE BOND 224-1 A/B AS 10/1 BW EPOXY	ACC	3.30	.38	1H	15H	AIR	COND ADHESIVE
ABLE BOND 224-3 A/B AS 100/7.3 BW EPOXY	ACC	2.39	.90	4H	52	AIR	ADHESIVE
ABLE BOND 2293-1 A/B AS 25/2 BW FILLED EPOXY	ACC	1.32	.32	4H	74	AIR	ADHESIVE
ABLE BOND 293-1 A/B AS 25/4 BW EPOXY	ACC	1.32	.08	2H	74	AIR	ADHESIVE
ABLE BOND 3422-1 34CC/5% BLACK EPOXY	ACC	1.05	.07	2H	65	AIR	ADHESIVE
ABLE BOND 36-2 SILVER FILLED EPOXY	ACC	.30	.00	30H	15H	AIR	COND ADHESIVE
ABLE BOND 41-5 EPOXY	ACC	.46	.00	30H	15H	AIR	ADHESIVE
ABLE BOND 463-1 A/B AS 10GM/16DPS SILVER FILLED EPOXY	ACC	.34	.01	2H	25	AIR	COND ADHESIVE
ABLE BOND 463-1 A/B AS 10GM/16DPS SILVER FILLED EPOXY	ACC	.62	.01	2H	65	AIR	ADHESIVE
ABLE BOND 57-2R MODIFIED EPOXY DARK RED	ACC	2.59	.16	1H	71	AIR	COND ADHESIVE
ABLE BOND 71-1 SILVER FILLED POLYIMIDE	ACC	.24	.06	10H	15H	AIR	COND ADHESIVE
ABLE BOND 71-1 SILVER FILLED POLYIMIDE	ACC	.25	.00	30H	15H	AIR	COND ADHESIVE
ABLE BOND 826-1 ONE COMPONENT SILVER FILLED ADH	ACC	.58	.03	30H	27H	AIR	COND ADHESIVE
ABLE BOND 872-3 A/B AS 2/3 BW FLEXIBLE PINK EPOXY	ACC	2.76	1.19	8H	75H	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	ACC	4.85	.31	90H	80	AIR	COND ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	ACC	2.41	.04	1H	93	AIR	COND ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	ACC	2.02	.06	1H	12H	AIR	COND ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	ACC	2.04	.01	1H	15H	AIR	COND ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY THIN	ACC	.76	.00	1H	12H	AIR	COND ADHESIVE
ABLE FILM ECF 518 CLOTH SUPPORT/EPOXY FILM ADH GRAY	ACC	.81	.01	24H	12H	E-J	CLOTH SUPPORT/EPOXY FILM ADH GRAY
ABLE FILM ECF 535 CLOTH SUPPORT/SILVER FILLED EPOXY	ACC	.88	.01	3H	12H	AIR	CLOTH SUPPORT/SILVER FILLED EPOXY
ABLE FILM 550-1 GLASS SUPPORT/SILVER FILLED EPOXY	ACC	.42	.16	2H	12H	AIR	CLOTH SUPPORT/SILVER FILLED EPOXY
ABLE FILM 501 A/D GLASS CLOTH SUPPORT/EPOXY ADH	ACC	.37	.10	3H	12H	AIR	CLOTH SUPPORT/EPOXY ADH
ABLE FILM 501T GLASS SUPPORT/MUD EPOXY FILM ADH	ACC	1.62	.08	3H	74	AIR	CLOTH SUPPORT/MUD EPOXY FILM ADH
ABLE FILM 504 CLOTH SUPPORT/EPOXY FILM ADH - WHITE	ACC	.52	.00	45H	14H	AIR	CLOTH SUPPORT/EPOXY FILM ADH - WHITE
ABLE FILM 506 CLOTH SUPPORT/EPOXY FILM ADH - PINK	ACC	.38	.00	1.5H	93	AIR	CLOTH SUPPORT/EPOXY FILM ADH - PINK
ABLE FILM 509 CLOTH SUPPORT/EPOXY FILM ADH/F - WHITE	ACC	1.05	.32	90H	10H	AIR	CLOTH SUPPORT/EPOXY FILM ADH/F - WHITE
ABLE FILM 507 GLASS CLOTH SUPPORT/EPOXY FILM ADH	ACC	.90	.00	1.5H	12H	PSI	CLOTH SUPPORT/EPOXY FILM ADH
ABLE FILM 517 GLASS CLOTH SUPPORT/EPOXY FILM ADH PINK	ACC	.38	.00	1.5H	74	AIR	CLOTH SUPPORT/EPOXY FILM ADH PINK
ABLE FILM 518 CLOTH SUPPORT/EPOXY FILM ADH - GRAY	ACC	.83	.00	3H	93	AIR	CLOTH SUPPORT/EPOXY FILM ADH - GRAY
ABLE FILM 550-1-K CLOTH SUPPORT/EPOXY FILM ADH - WHITE	ACC	.31	.04	3H	19H	AIR	CLOTH SUPPORT/EPOXY FILM ADH - WHITE
ABLE FILM 550-1-004 CLOTH REINFORCED EPOXY FILM IN WHITE	ACC	.42	.13	3H	12H	AIR	CLOTH REINFORCED EPOXY FILM IN WHITE
ABLE FILM 56 K CLOTH SUPPORT/EPOXY FILM THERM COND	ACC	.42	.13	2H	12H	AIR	CLOTH SUPPORT/EPOXY FILM THERM COND

SECTION 1 --- ADHESIVES

MATERIAL	MFR CODE	XTCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
ARMSTRONG A-12 A/E AS 1/1 BN BROWN EPOXY	APC	1.25	.04	8H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 1/1 BN BROWN EPOXY	APC	1.25	.04	20H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 2/3 BN BROWN EPOXY	APC	1.25	.04	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 2/3 BN BROWN EPOXY	APC	1.25	.04	3H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 2/3 BN BROWN EPOXY	APC	1.25	.04	6H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 2/3 BN BROWN EPOXY	APC	1.25	.04	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 3/2 BN BROWN EPOXY	APC	1.25	.04	3H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 3/2 BN BROWN EPOXY	APC	1.25	.04	6H	AIR	ADHESIVE
ARMSTRONG A-12 A/E AS 3/2 BN BROWN EPOXY	APC	1.25	.04	24H	AIR	ADHESIVE
ARMSTRONG A-24 AS 1/2 BN EPOXY	APC	1.45	.02	24H	AIR	ADHESIVE
ARMSTRONG A-24 AS 1/2 BN EPOXY	APC	1.45	.02	4H	AIR	ADHESIVE
ARMSTRONG A-24 AS 1/2 BN EPOXY	APC	1.45	.02	20H	AIR	ADHESIVE
ARMSTRONG A-27 A/E AS 7/3 BN EPOXY	APC	1.49	.02	2H	AIR	ADHESIVE
ARMSTRONG A-3 AS 100/6 BN BLACK EPOXY	APC	1.85	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN BLACK EPOXY	APC	1.72	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN BLACK EPOXY	APC	1.57	.02	4H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN BLACK EPOXY	APC	1.63	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN BLACK EPOXY	APC	1.63	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN BLACK EPOXY	APC	1.63	.02	24H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN TAN EPOXY	APC	1.55	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN TAN EPOXY	APC	1.73	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/3 BN TAN EPOXY	APC	1.73	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY (CHNG IN B COMP)	APC	1.51	.02	3000H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.51	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.51	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.44	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.44	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.44	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/4 BN EPOXY	APC	1.44	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	4H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	7D	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	25H	AIR	ADHESIVE
ARMSTRONG A-3 AS 6/6 BN EPOXY	APC	1.97	.02	7D	AIR	ADHESIVE
ARMSTRONG C-1 ACT AS 25/2 BN EPOXY	APC	1.97	.02	25H	AIR	ADHESIVE
ARMSTRONG C-1 ACT AS 25/2 BN EPOXY	APC	1.97	.02	7D	AIR	ADHESIVE
ARMSTRONG C-1 ACT AS 25/2 BN EPOXY	APC	1.97	.02	25H	AIR	ADHESIVE
ARMSTRONG C-1 ACT AS 25/2 BN EPOXY	APC	1.97	.02	7D	AIR	ADHESIVE
ARMSTRONG C-4 ACT AS 1/1 BN EPOXY	APC	1.33	.02	25H	AIR	ADHESIVE
ARMSTRONG C-4 ACT AS 1/1 BN EPOXY	APC	1.33	.02	7D	AIR	ADHESIVE
ARMSTRONG C-4 ACT AS 1/1 BN EPOXY	APC	1.33	.02	25H	AIR	ADHESIVE
ARMSTRONG C-4 ACT AS 1/1 BN EPOXY	APC	1.33	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 1/1 BN EPOXY	APC	2.69	.02	23H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 1/1 BN EPOXY	APC	2.69	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 2/3 BN EPOXY	APC	2.35	.02	23H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 2/3 BN EPOXY	APC	2.35	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 2/3 BN EPOXY	APC	2.35	.02	23H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 2/3 BN EPOXY	APC	2.35	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	24H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	24H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	25H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	25H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	25H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	7D	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	25H	AIR	ADHESIVE
ARMSTRONG C-7 ACT AS 3/1 BN CLEAR EPOXY	APC	1.79	.02	7D	AIR	ADHESIVE
AVERT MOUNTING TABS - SEN	APP	13.32	6.21	4H	45	ADHESIVE
AVERT MOUNTING TABS - SEN	CIB	6.61	1.05	3H	6.5	AIR
AVERT MOUNTING TABS - SEN	HYS	6.68	.27	30H	45	AIR
BARCO BOND AB-2 A/E AS 2/1 BN EPOXY	AST	1.20	.05	30H	6.21	PSI
BONDMASTER E645 A/E AS 10/3 BN ADH	NSC	.68	.04	1H	6204	AIR
BONDMASTER E645 A/E AS 10/3 BN EPOXY	NSC	.50	.01	4H	1100	E-2
BONDMASTER E645 A/E AS 10/3 BN EPOXY THINNER	NSC	.90	.14	1H	1177	PSI
BONDMASTER E645 A/E AS 10/3 BN THERMOSET EPOXY	NSC	1.52	.15	3H	25	AIR
BONDMASTER #688/CH-16 AS 100/32 BN EPOXY	NSC	4.92	.21	1H	9130	AIR
BONDMASTER #688/CH-16 AS 100/32 BN EPOXY	NSC	2.62	.03	16H	25	AIR
BONDMASTER #688/CH-8 AS 100/13 BN EPOXY	NSC	2.90	.08	8H	1241	AIR
BONDMASTER #773 A/E AS 1/1 BN EPOXY	NSC	3.90	.11	2H	220	AIR
BONDMASTER #773 A/E AS 1/1 BN EPOXY	NSC	2.50	.09	1H	60	AIR
BONDMASTER #773 A/E AS 1/1 BN EPOXY	NSC	3.63	.11	2H	60	AIR
				8H	65	AIR

SECTION 1 -- ADHESIVES

MATERIAL	MPN CODE	XTCI	%VCN	CURE TIME	CURE TEMP	STATUS	APPLICATION
BONDMASTER 3773 A/E AS 1/1 BW EPOXY	NSC	2.37	.10	8H	95	AIR	ADHESIVE
BONDMASTER 3777 A/E AS 1/1 BW EPOXY	NSC	1.82	.09	1H	70	E-2	ADHESIVE
BONDMASTER M777 PLUS A/B AS 1/1 BW EPOXY	NSC	2.41	.13	2H	60	AIR	ADHESIVE
BONDMASTER 4500 PLUS A/B AS 1/1 BW EPOXY	NSC	2.71	.13	8H	65	AIR	ADHESIVE
BONDMASTER 4500 PLUS A/B AS 1/1 BW EPOXY	NSC	.74	.02	2H	93	E-3	ADHESIVE
BONDMASTER 620				1H	150	AIR	ADHESIVE
BOSTIK 7008 ELECTRIC ADHESIVE ONE COMPONENT	FPC	1.75	.21	1H	200	AIR	ADHESIVE
BR 34 EPOXY ADHESIVE	ACC	.05	.00	5H	135	AIR	ADHESIVE
B3 34 EPOXY ADHESIVE	ACC	.34	.00	30M	215	AIR	ADHESIVE
BR 90/BR 862 AS 100/6 BW EPOXY ADHESIVE	ACC	6.80	.04	7D	248	AIR	ADHESIVE
BR 90/BR 802 AS 100/8 BW EPOXY ADHESIVE/F	ACC	1.77	.03	7D	25	AIR	ADHESIVE
B6-0014 PHENOLIC RESIN/F	PLM	3.04	.01	2H	25	AIR	ADHESIVE
BA-125 PRIMER AND NITRILE EPOXY/F	ACC	1.19	.13	30M	120	AIR	ADHESIVE
BR-610 EPOXY/TETRAHYDROFURANE/F	WTB	1.14	.01	1.5H	25	AIR	ADHESIVE
BR-610 EPOXY/TETRAHYDROFURANE/F	WTB	.99	.02	30M	10	AIR	ADHESIVE
BSL 308 BLACK EPOXY UNSUPPORTED ADHESIVE FILM	CIB	.70	.99	1H	60	AIR	ADHESIVE
BUTYL ACRYLATE-BENZYL PEROXIDE FILM	CIB	11.95	.12	1.5H	60	AIR	ADHESIVE
C-68CAT A AS 10/5-3 BW GRAY EPOXY UNSUPPORTED ADHESIVE FILM	RYS	.12	.01	20M	150	AIR	ADHESIVE
CASTALL E A/B AS 10/1 BW GRAY EPOXY 70% SANDFILLED	CAS	.51	.00	12H	170	AIR	ADHESIVE
CASTALL QUICK CURE EPOXY CAST-PAK PRE-MIX	CAS	2.65	.03	30M	100	AIR	ADHESIVE
CASTALL 9520/BAT-7 AS 100/7.5 BW EPOXY	CAS	1.25	.07	24H	65	AIR	ADHESIVE
CASTALL 490/HAT-1 AS 1/1 BW BLUE HI-STRENGTH EPOXY	CAS	1.28	.07	4H	125	AIR	ADHESIVE
CAULK GRIP CEMENT METHACRYLATE FILLED	CAU	1.00	.02	5D	25	AIR	ADHESIVE
CD-772 POLYURETHANE	HCC	1.01	.02	3D	25	AIR	ADHESIVE
CB-100 IODIDE COUPLING COMPOUND BLEND 10/1	HAK	8.50	.55	24H	160	AIR	ADHESIVE
CB-100 IODIDE COUPLING COMPOUND BLEND 10/1	HAK	9.60	.60	30M	25	AIR	ADHESIVE
CEMLOK 205 ADHESIVE PRIMER GREY	HCC	.34	.00	104	160	AIR	ADHESIVE
CEMLOK 216 ON EPOXY	HCC	15.72	.49	24H	25	AIR	ADHESIVE
CEMLOK 220 ADHESIVE BLACK	HCC	.39	.00	30M	25	AIR	ADHESIVE
CHEMLOK 234	HCC	15.54	.10	30M	25	AIR	ADHESIVE
CHEMLOK 234B ELASTOMER BONDING AGENT - BLACK	HCC	51.85	.88	24H	149	AIR	ADHESIVE
CHEMLOK 236A BONDING AGENT FLAT BLACK/F	HCC	30.19	.29	30M	25	AIR	ADHESIVE
CHEMLOK 236A BONDING AGENT FLAT BLACK/F	HCC	27.93	.21	30M	95	AIR	ADHESIVE
CHEMLOK 305 A/B AS 1/1 BW EPOXY	HCC	1.51	.02	3D	25	AIR	ADHESIVE
CHO-BO ND 1024 CONDUCTIVE SILICONE	CHO	.44	.18	5H	177	AIR	CONDUCTIVE SILICONE
CHO-BO ND 1024 CONDUCTIVE SILICONE	CHO	.02	.00	48H	177	AIR	CONDUCTIVE SILICONE

SECTION 1 -- ADHESIVES

MATERIAL	APR CODE	ATHL	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CHO-BOND 1029 CONDUCTIVE SILICONE	CHO	.38	.16	1H	66	AIR	COND ADHESIVE
CHO-BOND 1030 ONE PART SILVER FILLED SILICONE	CHO	.31	.65	7D	25	AIR	COND ADHESIVE
CHO-BOND 1035 ONE PART SILVER FILLED SILICONE	CHO	1.08	.35	1H	25	AIR	COND ADHESIVE
CHO-BOND 1092 ONE PART SILVER FILLED SILICONE	CHO	1.66	.35	1H	25	AIR	COND ADHESIVE
CHO-BOND 260-18 A/E AS 40/1 BH CONDUCTIVE EPOXY	CHO	1.17	.35	24H	113	AIR	COND ADHESIVE
CHO-BOND 260-208 CONDUCTIVE EPOXY ADHESIVE	CHO	.66	.06	24H	25	AIR	COND ADHESIVE
CHO-BOND 404-1-0402 A/B AS 1/1 BW BROWN BOND EPOXY	CHO	.39	.04	24H	100	AIR	COND ADHESIVE
CHO-BOND 584-29 A/E AS 100/6.3 BW BROWN BOND EPOXY	CHO	1.15	.03	24H	100	AIR	COND ADHESIVE
CHO-BOND 586-29 A/E AS 100/4.2 BW SILVER EPOXY	CHO	1.96	.04	24H	65	AIR	COND COATING
CHOMERICS HOT MELT CONDUCTIVE ADHESIVE FILM	CHO	1.96	.34	2H	100	AIR	ADHESIVE FILM
CMC-522 EPOXY LAMINATING FILM	CHO	.31	.39	2H	100	AIR	FAIL ADHESIVE
CMC-10 ADHESIVE FILM	CHO	1.02	.03	2H	100	AIR	FAIL FILM
CONAP K-20 A/B AS 20/9 BW GRAY EPOXY	CON	1.75	.05	2H	165	AIR	ADHESIVE
CONAFA K-26 WHITE EPOXY THERMOSETTING	CON	1.10	.12	2H	85	AIR	ADHESIVE
CONATHANE CE 1170 - FLUORESCENT EQUAL LENGTHS FROM TUBES	CON	1.60	.09	2H	65	AIR	FLUORESCENT
CONATHANE CE 1171 - FLUORESCENT	CON	9.32	.09	2H	140	AIR	FLUORESCENT
CONATHANE DP 9761 A/B AS 100/4.5 BW POLYURETHANE BLEND	CON	.93	.01	30D	25	AIR	ADHESIVE
CONATHANE EN-21 A/B AS 100/4.5 BW POLYURETHANE BLEND	CON	.82	.03	30D	25	AIR	ADHESIVE
CONATHANE EN-21 A/E AS 100/16 BW POLYURETHANE BLEND	CON	.59	.02	30D	25	AIR	ADHESIVE
CONATHANE EN-21 A/E AS 100/16 BW POLYURETHANE BLEND	CON	.72	.02	30D	25	AIR	ADHESIVE
CONATHANE EN-24 A/E AS 100/82 BW POLYURETHANE	CON	.57	.04	24H	25	AIR	ADHESIVE
CONATHANE EN-24 A/E AS 100/82 BW POLYURETHANE	CON	.52	.02	24H	65	AIR	PUTTYING FOAM
CORPIL 615/D/A AS 100/7 BW EPOXY	ACC	.93	.13	3H	65	AIR	ADHESIVE
COTRONICS THERMEEZ CERAMIC PUTTY	COT	.77	.01	14D	25	AIR	ADHESIVE
COTRONICS THERMEEZ CERAMIC PUTTY	COT	.06	.01	24H	25	AIR	ADHESIVE
COTRONICS 360-M ECLIDABLE CERAMIC	COT	3.41	.02	2H	190	AIR	ADHESIVE
COTRONICS 360-D ECLIDABLE CERAMIC	COT	2.67	.01	24H	25	AIR	ADHESIVE
COTRONICS 918 CERAMIC ADHESIVE	COT	4.74	.02	14D	25	AIR	ADHESIVE
COTRONICS 918 CERAMIC ADHESIVE	COT	1.20	.01	24H	25	AIR	ADHESIVE
COTRONICS 919/H2C AS 7-7/1 BW HIGH RES CERAMIC	COT	5.34	.02	14D	25	AIR	ADHESIVE
COTRONICS 919/H2C AS 7-7/1 BW HIGH RES CERAMIC	COT	4.20	.01	24H	200	AIR	ADHESIVE
COTRONICS 940/ACT AS 4/1 BW FAST SET CERAMIC	COT	1.57	.03	2H	100	AIR	ADHESIVE
COTRONICS 940/ACT AS 4/1 BW FAST SET CERAMIC	COT	.79	.01	24H	25	AIR	ADHESIVE
COTRONICS 944/H2C AS 5-5/1 BW HIGH STR CERAMIC	COT	5.30	.03	2H	100	AIR	ADHESIVE
COTRONICS 944/H2C AS 5-5/1 BW HIGH STR CERAMIC	COT	.59	.01	24H	25	AIR	ADHESIVE
COX-28 EPOXY A/B AS 7/1 BW EPOXY	CPC	3.13	.90	20H	100	AIR	ADHESIVE
CREST 315/11 AS 1/1 BW EPOXY	CPC	2.47	.05	24H	25	AIR	ADHESIVE
CREST 3170 A/B AS 1/1 BW MODIFIED WHITE EPOXY	CPC	4.38	.04	3D	25	AIR	ADHESIVE
CREST 3170 A/B AS 50/50 BW EPOXY	CPC	2.19	.04	24H	125	AIR	ADHESIVE
CREST 3170/13 AS 1/1 BW WHITE EPOXY	CPC	3.25	.09	16H	25	AIR	ADHESIVE
CREST 3725/14 AS 1/1 BW EPOXY-URETHANE	CPC	3.47	.39	21D	25	AIR	ADHESIVE
CREST 3725/14 AS 1/1 BW EPOXY-URETHANE	CPC	2.01	.41	3H	66	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	NFR CODE	XMTL	ACVCM	CURE TIME	CURE TEMP	ADTS	APPLICATION
CREST 391 A/B AS 100/60 BW BLACK POLYURETHANE	CPC	26-86	7-58	SD	25	AIR	LOW TEMP ADH
CREST 419 A/B AS 100/60 BW POLYURETHANE	CPC	26-52	7-36	SD	25	AIR	LOW TEMP ADH
CREST 7343 A/B AS 100/11 BW POLYURETHANE ADH	CPC	1-10	-17	SD	25	AIR	ADHESIVE
CREST 7344 A/B AS 100/14 BW BROWN EPOXY/POLYURETHANE	CPC	2-28	-68	72H	25	PSI	LOW TEMP ADH
CREST 7344 A/B AS 100/6 BW BROWN EPOXY/POLYURETHANE	CPC	1-51	-67	SD	25	AIR	ADHESIVE
CREST 7344/7119 AS 50/7 BW EPOXY MODIFIED BROWN EPOXY	CPC	2-78	-66	24H	225	AIR	ADHESIVE
CREST 7360 A/B AS 100/16 BW YELLOW POLYURETHANE	CPC	2-62	-23	SD	25	AIR	LOW TEMP ADH
CREST 7410 A/B AS 100/16 BW YELLOW POLYURETHANE	CPC	7-92	4-80	SD	25	AIR	LOW TEMP ADH
CREST 7410 A/B AS 100/26 BW YELLOW POLYURETHANE	CPC	6-76	4-01	SD	25	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW	CPC	1-45	-10	24H	225	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW	CPC	1-85	-17	7D	225	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW	CPC	1-12	-11	1H	825	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW	CPC	1-34	-14	24H	225	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW	CPC	1-78	-30	7D	225	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW	CPC	1-12	-19	1H	825	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW	CPC	1-21	-30	24H	225	AIR	LOW TEMP ADH
CREST 7450 A/B AS 100/16 BW	AMC	2-35	-01	90H	80	AIR	COND ADHESIVE
CT 4042-1 A/B AS 1/1 B* SILVER FILLED EPOXY	AMC	1-55	-14	30H	93	AIR	COND ADHESIVE
CT 503VA/B-97 AS 17/1 BW SILVER FILLED EPOXY	AMC	1-55	-14	24H	825	AIR	COND ADHESIVE
CT 5047-2 A/B AS 100/6 BW SILVER FILLED EPOXY	AMC	1-39	-00	24H	625	AIR	COND ADHESIVE
CYBOND 4010 A/E AS 3/1 BW	ACC CCC	1-48 3-31	-72 -43	21D 3H	27 135	AIR	ADHESIVE
CYCLE FLD 55-9	CIB	-78	-01	40H	135	AIR	ADHESIVE
CY 209/HT972 CLEAR AMBER EPOXY	DCC	1-97	-04	14D	225	AIR	ADHESIVE
DC 142 OVER A-4054 PRIME	DCC	4-75	-85	24H	225	AIR	ADHESIVE
DC 271 SILICONE	DCC	3-62	-89	4H	69	AIR	ADHESIVE
DC 3110/H AS 10% CAT H	DCC	1-35	-34	4H	95	AIR	ADHESIVE
DC 3110/S AS 15% CAT S	DCC	1-43	-41	7H	525	AIR	ADHESIVE
DC 3144 SILICONE	DCC	1-74	-90	30H	225	AIR	ADH SEALANT
DC 3145 SILICONE	DCC	1-70	-60	24H	225	AIR	ADH SEALANT
DC 3145 CNE COMPONENT GRAY SILICONE	DCC	-54	-27	7D	225	AIR	ADH SEALANT
DC 6-1104 LOT E2134-142	DCC	-29	-03	SD	25	AIR	AUHESIVE-COATING
DC 6-1104 LOT F014384	DCC	-16	-05	SD	225	AIR	ADHESIVE
DC 6-1104 LOT FM109321	DCC	-26	-05	7D	225	AIR	ADHESIVE
DC 6-1104 LOT FM109329	DCC	-21	-03	14D	225	AIR	ADHESIVE
DC 6-1104 LOT FM125370	DCC	-13	-23	7D	225	AIR	ADHESIVE RESIN
DC 63-488 A/B AS 10/1 BW OPTICAL SILICONE RESIN	DCC	-142	-74	4H	26	AIR	SILICONE RESIN

SECTION 1 -- ADHESIVES

MATERIAL	NFR CODE	X-TML	%CVM	CURE TIME	CURE TEMP	CURE ATMOS	APPLICATION
DC 63-488 A/B AS 10/1 BW SILICONE	DCC	.99	.43	16H	2.5	AIR	ADHESIVE
DC 63-489 A/B AS 10/1 BW OPTICAL SILICONE RESIN	DCC	1.42	.57	24H	6.5	AIR	
DC 63-489 A/B AS 10/1 BW SILICONE	DCC	.89	.44	4H	60	AIR	SILICONE RESIN
DC 63-489 SILICONE	DCC	.23	.15	4H	95.0	E-J	ADHESIVE
DC 63-489 SILICONE	DCC	.36	.17	6.9H	13.0	E-O	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT E2467-133 9/76	DCC	.09	.03	17	99H	E-6	
DC 93-500 A/B AS 10/1 BW SILICONE LOT F0420392	DCC	.10	.02	7D	25	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LQT 047611 6/77	DCC	.19	.04	7D	25	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT FM119335R2	DCC	.13	.01	7D	25	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT FM129358	DCC	.10	.02	7D	25	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE	DCC	.09	.01	7D	25	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE	DCC	.04	.00	48H	25	AIR	ADHESIVE
DC 93-500 A/B AS 20/1 BW SILICONE	DCC	.38	.21	24H	40	AIR	PUTTY
DC 93076-1/2 FM 059240	DCC	3.15	.88	16H	25	E-C	ADHESIVE
DC 93076-1/2 GRAY SILICONE	DCC	3.30	.96	4H	99H	AIR	ADHESIVE
DC 96-080 DELTA BOND 152-K-A EPOXY KIT 152/RTA2 AS 20/1.5 BW	DCC WAK	1.48	.11	4H	60	AIR	
DELTA BOND 152-Q-B4 A/B AS 100/3.5 BW BLUE EPOXY	DCC WAK	1.73	.01	8H	25	AIR	AQH-SOLVENT CAND ADHESIVE
DELTA BOND 152-1-A EPOXY KIT PRE-MIX BLUE	DCC WAK	-4.9	.00	1H	22	AIR	ADHESIVE
DELTA BOND 152-1-B EPOXY KIT PRE-MIX BLUE	DCC WAK	1.14	.02	16H	25	AIR	ADHESIVE
DELTA BOND 152/RTA AS 100/7.5 BW	DCC WAK	1.14	.01	2H	60	AIR	ADHESIVE
DELTA BOND 152/RTA AS 100/7.5 BW	DCC WAK	1.59	.05	2H	60	AIR	ADHESIVE
DEN 438/MDA AS 100/27 BW EPOXY - AMBER	DNH	.60	.01	24H	9.3	AIR	ADHESIVE
DENNIS 1169 A/B AS 1/1 BW EPOXY	DMS	5.00	.35	4H	91.5	AIR	ADHESIVE
DENNIS 1169 EPOXY	DMS	8.00	.01	3H	25	AIR	ADHESIVE
DER 324/DEH-20/DER-732 AS 100/12/12 BW	DOW	2.30	.10	4H	25	AIR	ADHESIVE
DER 324/DEH-20/VERSALID 150 AS 100/12/50 BW	DOW	3.02	.41	4H	60	AIR	ADHESIVE
DER 332/DAIDS/LITTAFAK AS 10/3/40 BW EPOXY - CREAM	DOW	.24	.00	24H	6.6	AIR	ADHESIVE
DER 332/TETRA/LITTAFAK AS 100/14/170 BW EPOXY-WHITE	DOW	.39	.00	1H	150	AIR	ADHESIVE
DER 332/TETRA/LITTAFAK/CAB-O-SIL AS 100/14/235/.67BW	DOW	.29	.01	1H	100.5	AIR	ADHESIVE
DER 332/VERSALID 125 AS 1/1 BW EPOXY	DOW	.58	.01	24H	100.5	AIR	ADHESIVE
DER 332/VERSALID 24 AS 9/9/2 BW EPOXY	DOW	1.78	.17	4D	25	AIR	ADHESIVE
DER 332LC/VERSALID 140 AS 9/7 BW EPOXY	DOW	.54	.01	24H	60	AIR	ADHESIVE
DEVCON F-2 A/B AS 9/1 BW ALUMINUM FILLED EPOXY	DEV	.53	.06	12H	40	AIR	ADHESIVE
DEVCON MINI TUBE EPOXY EQUAL PARTS FROM TUBES	DEV	1.53	.09	24H	25	AIR	ADHESIVE
DEVCON 5 MINUTE EPOXY EQUAL PARTS FROM TUBES	DEV	1.53	.08	24H	25	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MPN CODE	XTML	XCVN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
DOLPHON CE-1078 W/F3187/D8585 AS 20/1 BW BLACK DOUBLE BUBBLE EPOXY PATCH KIT PRELATURED GRAY DPPC/N 46971/CAT 8C5 AS 10/1 BW	JCD HIC DUP	1.34 1.27 .05	.01 .01 .00	7D 4H 1H	25 25 195	Air Air Air	ADHESIVE ADHESIVE ADHESIVE
DUPONT 5504A SILVER FILLED EPOXY	DUP	.05	.18	2d	240	Air	None ADHESIVE
E-SOLDER 3021 A/B AS 1/1 BW SILVER FILLED EPOXY	EPO	9.36	.18	3H	95	Air	None ADHESIVE
E-SOLDER 3022/16 AS 10J/8 BW SILVER FILLED EPOXY	EPO	1.27	.02	1.5d	85	Air	None ADHESIVE
E-252/C-46 CAT/STYRENE AS 10/3/1.3 B*	STV	2.55	.02	2H	82	Air	None ADHESIVE
E-2730-13 A/B AS 10/1 BW SILICONE - SPECIAL	DCC	.85	.02	10D	25	Air	None ADHESIVE
EA 8A/B AS 10/6 BW BROWN EPOXY	HYS	.98	.02	90H	93	Air	None ADHESIVE
EA 907 A/B AS 10/11 BW EPOXY MAROON	HYS	.83	.04	5H	116	Air	None ADHESIVE
EA 907 A/B AS 10/8 BW LIGHT BLUE EPOXY	HYS	.60	1.03	3D	25	Air	None ADHESIVE
EA 921 A/B AS 4/1 EM GRAY EPOXY	HYS	2.42	.02	2H	82	Air	None ADHESIVE
EA 9307 A/B AS 100/14 BW BROWN EPOXY	HYS	.48	.00	30M	121	Air	None ADHESIVE
EA 9309 A/B AS 100/23 BW EPOXY	HYS	2.18	.00	2H	82	Air	None ADHESIVE
EA 9309 A/B AS 100/23 BW EPOXY	HYS	1.25	.00	7D	25	Air	None ADHESIVE
EA 9313 A/B AS 100/23 BW EPOXY LOT 25195	HYS	1.20	.02	5H	74	Air	None ADHESIVE
EA 9313 ORANGE EPOXY	HYS	2.08	.15	16H	25	Air	None ADHESIVE
EA 9320 A/B AS 100/19 BW BLUE EPOXY	HYS	1.12	.04	6H	89	Air	None ADHESIVE
EA 9321 GRAY EPOXY	HYS	.94	.04	12M	121	Air	None ADHESIVE
EA 934 A/B AS 100/33 BW GRAY EPOXY (EPOX 94)	HYS	.49	.01	90M	95	Air	None ADHESIVE
EA 934 A/B AS 100/33 BW GRAY EPOXY	HYS	.54	.01	7D	25	Air	None ADHESIVE
EA 9414 1/ONE COFFEE CUP WHITE EPOXY	HYS	.78	.14	14M	PSI	Air	None ADHESIVE
EA 951 SUPPORTED EPOXY ADHESIVE FILM GRAY	HYS	2.15	.19	1H	177	Air	None ADHESIVE
EA 953 EPOXY	HYS	2.28	.06	1H	177	Air	None ADHESIVE
EA 9601 SUPPORTED EPOXY ADHESIVE FILM YELLOW	HYS	.69	.02	1H	177	Air	None ADHESIVE
EA 9653 EPOXY FILM ADHESIVE	HYS	1.54	.04	1H	177	E-1	None ADHESIVE
EASTMAN 910 FABRIC/ACRYLIC FOIL SANDWICH REPAIR KIT A/B AS EQUAL LENGTHS FROM TUBES WHITE	EAC	2.27	.06	5D	25	Air	Film ADHESIVE
EASTMAN 910 CYANOACRYLIC FOIL SANDWICH REPAIR KIT A/B AS EQUAL LENGTHS FROM TUBES WHITE	EAC	6.15	.05	24H	25	Air	Film ADHESIVE
EASYPoxy K-256 A/B AS EQUAL LENGTHS FROM TUBES WHITE	CON	6.60	.04	24H	25	Air	ADHESIVE
EASYPoxy K-26 WHITE EPOXY	CON	1.11	.05	24H	66	Air	ADHESIVE
EASYPoxy K-40 A/B AS EQUAL LENGTHS FROM TUBES GRAY	CON	6.60	.05	24H	25	Air	ADHESIVE
EASYPoxy K-43 A/B AS EQUAL LENGTHS FROM TUBES BLUE	CON	1.87	.08	24H	25	Air	ADHESIVE
EC 1614 A/L AS 1/1 BW EPOXY ADH	MNN	1.90	.12	1H	66	Air	ADHESIVE
EC 2126 BUNA N ADHESIVE	MNN	9.48	1.32	72H	66	Air	ADHESIVE
EC 2258 EPOXY ADH	MNN	1.90	.09	24H	175	Air	ADHESIVE
EC 2290 EPOXY ADH	MNN	.20	.15	30M	92	Air	ADHESIVE
EC 2290 EPOXY ADHESIVE	MNN	.01	.01	30M	177	Air	ADHESIVE
EC 3500 B/A IS 2/3 BW EPOXY ADHESIVE	MNN	1.60	.00	2H	177	Air	ADHESIVE
EC 3500 EPOXY ADHESIVE	MNN	1.19	.06	60M	121	Air	ADHESIVE
ECOBOND 104 A/B AS 100/64 BW GRAY/GREEN EPOXY	EMC	.52	.08	6H	170	Air	ADHESIVE
ECOBOND 24 A/B AS 100/28 BW CLEAR EPOXY	EMC	1.69	.04	24H	25	Air	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MFR CODE	STL	SCVCH	CURE TIME	CURE TEMP	ADHS	APPLICATION
ECCOBOND 276/CAT 17 AS 10/1 BW EPOXY	EMC	.49	.00	2H	80	AIR	ADHESIVE
ECCOBOND 281 ONE PART EPOXY - BLACK	EMC	.35	.06	2H	150	AIR	THERM COND ADH
ECCOBOND 285/11 AS 20/1 BW EPOXY	EMC	.28	.01	5H	200	AIR	ADHESIVE
ECCOBOND 285/24LV AS 25/2 BW EPOXY	EMC	.09	.00	8H	82	AIR	ADHESIVE
ECCOBOND 285/9 AS 25/1 BW EPOXY	EMC	.48	.01	24H	25	AIR	ADHESIVE
ECCOBOND 286/A/B AS 1/1 BW EPOXY	EMC	.58	.07	24H	25	AIR	ADHESIVE
ECCOBOND 45/15 AS 1/2 BW SEMI-RIGID EPOXY CLEAR BLACK	EMC	.58	.07	24H	104	AIR	ADHESIVE
ECCOBOND 45LV/15LV AS 2/1 BW SEMI-RIGID EPOXY BLACK	EMC	.98	.02	30H	104	AIR	ADHESIVE
ECCOBOND 51/9 AS 100/7 BW SEMI-RIGID EPOXY BLACK	EMC	.44	.02	24H	25	AIR	ADHESIVE
ECCOBOND 55/9 AS 5C/6 BW EPOXY	EMC	.46	.02	24H	25	AIR	ADHESIVE
ECCOBOND 56C/9 AS 50/6 BW EPOXY	EMC	.45	.02	30H	65	AIR	ADHESIVE
ECCOBOND 56C/9 AS 40/1 BW SOLDER	EMC	.23	.01	30H	25	AIR	ADHESIVE
ECCOBOND 57C A/B AS 1/1 BW CND EPOXY SILVER	EMC	.52	.04	1H	65	AIR	CND ADHESIVE
ECCOBOND 57C A/B AS 1/1 BW CND EPOXY SILVER	EMC	.36	.03	7D	150	AIR	CND ADHESIVE
ECCOBOND 58C SOLVENT FILLED EPOXY	EMC	.36	.01	2H	149	AIR	CND ADHESIVE
ECCOBOND 60L A/b AS 10/3 BW SILVER FILLED EPOXY	EMC	.54	.07	24H	23	AIR	CND ADHESIVE
ECCOBOND 787 A/B AS 1/1 BW THIKOTROPIC EPOXY	EMC	.29	.03	24H	23	AIR	ADHESIVE
ECCOBOND 83C A/B AS 10/3-5 BW BI-PAK SILVER FILLED	EMC	.64	.02	1H	6149	AIR	CND ADHESIVE
ECCOBOND 83C-1 ONE COMPONENT SILVER FILLED	EMC	.35	.01	1H	149	AIR	CND ADHESIVE
ECSCHOLD L23/24LV AS 100/26.4 BW	EMC	.73	.05	4D	25	AIR	ADHESIVE
ECOSAL W-19/CAT 1 24LV AS 100/26.4 BW EPOXY AMBER	EMC	.17	.08	24H	65	AIR	ADHESIVE
ECOSEAL W-19/CAT 9 AS 100/12 BW EPOXY	EMC	2.68	.03	4D	25	AIR	ADHESIVE
ECOSHIELD RVS ADHESIVE/ECCOSHIELD SYR/BOLI	EMC	.28	.1	24H	65	AIR	CND ADHESIVE
ECOSIL 1043-A/B AS 10/1 BW CLEAR SILICONE	EMC	.18	.04	30H	190	AIR	ADHESIVE
ELECTROBOND 1700 A/B AS 100/5.3 BW	EMC	.19	.1	24H	25	AIR	ADHESIVE
ELECTROBOND 2115 A/B AS 10/1 BW SILVER FILLED EPOXY	EPI	.44	.02	2H	65	AIR	CND ADHESIVE
EMX-116 A/B AS 1/1 BW TAN EPOXY	LUS	.37	.04	3H	25	AIR	ADHESIVE
EPIBOND 1210/9615/CAT 9615 AS 100/65 BW EPOXY	FPI	.75	.01	3H	65	AIR	ADHESIVE
EPIBOND 1210/9861 AS 5/1 BW EPOXY	FPI	.75	.01	7D	25	AIR	ADHESIVE
EPIBOND 122/CAT 952	FPI	.17	.01	16H	65	AIR	ADHESIVE
EPIBOND 123/CAT 9615-10	FPI	.37	.01	7D	25	AIR	ADHESIVE
EPIBOND 8510/A/B AS 10/3 BW	FPI	.85	.03	5D	25	AIR	ADHESIVE
EP IPHEN 825A/NOD T/PILLER/CONVERTER - EPOXY	BCH	.83	.01	16H	25	AIR	ADHESIVE
EPO-TEK H11 A/B AS 15/2-B BW SILVER FILLED EPOXY	EPK	.40	.02	8H	65	AIR	CND ADHESIVE
EPO-TEK H20E A/B AS 2/1 BW SILVER FILLED EPOXY	EPK	.18	.01	2H	190	AIR	CND ADHESIVE
EPO-TEK H20E A/B AS 2/1 BW/S/0 METAL FILLED EPOXY	EPK	.18	.02	15H	150	AIR	ADHESIVE
EPO-TEK H20S A/B AS 1/1 BW SILVER FILLED EPOXY	EPK	.54	.01	2H	100	AIR	CND ADHESIVE
EPO-TEK H21D A/B AS 1/1 BW SILVER FILLED EPOXY	EPK	.19	.03	10H	100	AIR	CND ADHESIVE
EPO-TEK H22 A/B AS 20/0-9 BW SILVER FILLED EPOXY	EPK	.00	.01	30H	50	AIR	ADHESIVE
EPO-TEK H22 A/B AS 10/1 BW SILVER FILLED EPOXY	EPK	.99	.01	20H	100	AIR	ADHESIVE
EPO-TEK H27D A/B AS 10/1 BW SILVER FILLED EPOXY	EPK	.52	.05	1H	150	AIR	CND ADHESIVE
EPO-TEK H31 SILVER FILLED EPOXY	EPK	.59	.05	1H	150	AIR	CND ADHESIVE
EPO-TEK H31D LV SILVER FILLED EPOXY SINGLE COMPONENT	EPK	.47	.02	1H	125	AIR	CND ADHESIVE
EPO-TEK H40 GOLD FILLED EPOXY SINGLE COMPONENT	EPK	.19	.00	1H	120	AIR	CND ADHESIVE
EPO-TEK H41 GOLD FILLED EPOXY	EPK	.14	.00	1H	150	AIR	CND ADHESIVE
EPO-TEK H43 GOLD FILLED EPOXY	EPK	.20	.00	1H	150	AIR	CND ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MRK CODE	XTHM	%CVCN	CURE TIME	CURE TEMP	ADHS	APPLICATION
EPO-TEK H44 GOLD FILLED EPOXY EPO-TEK H70E A/B AS 1/1 BW THERM COND EPOXY EPO-TEK H70E A/B AS 1/1 BW THERM COND EPOXY	EPK EPK EPK	.27 .51 .99	.00 -0.3 -0.3	1H 12H 12H	150 50 60	AIR AIR AIR	COND ADHESIVE THERM COND ADHESIVE
EPO-TEK H72 A/B AS 10/-4 BW DIELECTRIC EPOXY PASTE EPO-TEK H74 A/B AS 10/-3 BW THERM COND EPOXY BROWN EPO-TEK H77 A/B AS 20/3 BW BROWN EPOXY	EPK EPK EPK	.31 .56 .22	.00 -0.0 -0.0	30H 10H 1H	150 125 125	AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE
EPO-TEK H80 SILVER FILLED EPOXY EPO-TEK H81 A/B AS 1/1 BW PLATINUM FILLED EPOXY	EPK EPK	.16 .62	-0.1 -0.3	24H 16H	50 60	AIR AIR	COND ADHESIVE COND ADHESIVE
EPO-TEK H81 A/B AS 10/1 BW GOLD FILLED EPOXY EPO-TEK H81 A/B AS 1/1 BW GOLD FILLED EPOXY EPO-TEK 301 A/B AS 20/3 BW OPTICAL CEMENT EPOXY EPO-TEK 301 A/B AS 20/5 BW OPTICAL CEMENT EPOXY LOT 375049	EPK EPK EPK EPK	.96 .20 1.08 1.29	-0.1 -0.1 -0.1 -0.1	12H 24H 24H 18H	50 190 25 65	AIR AIR AIR AIR	COND ADHESIVE COND ADHESIVE OPT CEMENT OPT CEMENT
EPO-TEK 301 A/B AS 20/5 BW OPTICAL EPOXY LOT 375051	EPK	1.17	-0.2	0H	65	AIR	OPT CEMENT
EPO-TEK 301-2 A/E AS 10/2 BW OPTICAL CEMENT EPOXY EPO-TEK 301 A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY EPO-TEK 305 A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY EPO-TEK 305 A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY	EPK EPK EPK EPK	2.62 3.58 1.54 3.28	1.03 -0.5 -0.4 -1.5	24H 24d 24d 24H	6H 225 225 65	AIR AIR AIR AIR	OPT CEMENT OPT CEMENT OPT CEMENT OPT CEMENT
EPO-TEK 320 A/B AS 5/1 BW BLACK EPOXY EPO-TEK 353ND HIGH TEMP EPOXY PRE-MIX PACK 10/1 BW	EPK EPK	1.49 2.03	-0.2 -0.2	7D 24H	225	AIR	ADHESIVE ADHESIVE
EPO-TEK 353ND HIGH TEMP EPOXY PRE-MIX PACK 10/1 BW	EPK	1.83	-0.1	5H	60	AIR	ADHESIVE
EPO-TEK 353ND HIGH TEMP EPOXY PRE-MIX PACK 10/1 BW	EPK	1.88	-0.4	10H	200	AIR	ADHESIVE
EPO-TEK 390 POLYIMIDE F	EPK	.43	-0.1	24H	150	AIR	ADHESIVE
EPO-TEK 415G A/B AS 1/1 BW SILVER FILLED EPOXY EPO-TEK 417 A/B AS 15/1 B SILVER FILLED EPOXY EPO-TEK 417 A/B AS 15/1 B SILVER FILLED EPOXY	EPK EPK EPK	1.82 2.19 3.13	-2.7 -0.2 -0.1	30H 3D 45M	225 225 80	AIR AIR AIR	COND ADHESIVE COND ADHESIVE COND ADHESIVE
EPO-TEK 920 EPOXY ADHESIVE EPOCAST 930 A/B AS 100/3.7 BW FILLED EPOXY SL-15E EPOCAST 1363/9313 AS 50/7 B EPOXY-FURANE SL-15E EPOCAST 8508 EPOXY ADHESIVE	EPK EPK EPK EPK SL	.82 5.83 4.10 .42	-0.1 -0.1 -2.4 -0.5	45M 3H 24H 15H	80 25 25 60	AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EPON X-24 EPOXY				4H 25 25 25	100 93 93 93	AIR AIR AIR AIR	ADHESIVE ADHESIVE ADH-PORTING ADH-PORTING
EPON 1001-BT-70/VERSAMID 115/TOLUENE THINNER EPON 1001/VERSAMID 115 A/B AS 2/1 BW THINNER EPON 8/CAT A/CYCLOTEXANOL AS 100/12.5/25 BW EPON 8/CAT A/CYCLOTEXANOL AS 100/12.5/25 BW	SHL SHL SHL SHL	9.00 12.02 6.36 4.74	-0.0 -0.2 -0.2 -0.3	10H 14H 3H 24H	100 93 93 12.1	AIR AIR AIR E-4	ADHESIVE ADHESIVE ADH-PORTING ADHESIVE
EPON 315/DEH-20/VERSAMID 150 AS 100/12/12 BW EPOXY EPON 815/DEK 732/VIS SILVER PDR/AEP EPON 815/DEK 10/1 BW EPOXY	SHL SHL SHL	.81 2.56 2.96	-0.3 -0.7 -0.6	24H 4H 7D	60 74 25	AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	NPA CODE	XTL	%CVC	CUBE TIME	CURE TEMP	ATMOS	APPLICATION
EPON 815/T AS 10/1 ⁸ BW EPOXY	SHL	2.41	.03	7D	25	AIR	ADHESIVE
EPON 815/TETA AS 10/1 BW CURE 2	SHL	1.83	.03	6D	25	AIR	ADHESIVE
EPON 815/TETA AS 10/1 BW CURE 4	SHL	-76	.02	16H	63	AIR	ADHESIVE
EPON 815/V AS 3/8 BW EPOXY	GSC	-51	.02	16H	25	AIR	ADHESIVE
EPON 815/V 140/AL2C3/PIGMENT MODIFIED BLACK EPOXY	GSC	-69	.06	7D	25	AIR	CUND ADHESIVE
EPON 815/V 140/DTA AS 100/15/6 BW EPOXY	SHL	2.42	.08	7D	25	AIR	ADHESIVE
EPON 815/V 140/DTA AS 100/6/6 BW EPOXY	SHL	4.68	.44	7D	25	AIR	ADHESIVE
EPON 820/TETA AS 10/1 BW CURE 1	SHL	-43	.04	16H	25	AIR	ADHESIVE
EPON 820/TETA AS 10/1 BW CURE 8	SHL	-36	.04	16H	25	AIR	ADHESIVE
EPON 826/ANNA/BDMA AS 100/88.5/1.5 BW EPOXY	SHL	-41	.00	2H	93	AIR	ADHESIVE
EPON 827/VERSAMID 140 AS 1/1 BW EPOXY	SHL	*9*	.01	3.5H	17	AIR	ADHESIVE
EPON 828/ALUMINA/V-125/ETHANEDIAMINE/ALUMINA	SHL	*2*	.01	3H	60	AIR	ADHESIVE
EPON 828/DER 732/AEP/CARBON BLACK EPOXY ADHESIVE	SHL	1.36	.06	24H	66	AIR	ADHESIVE
EPON 828/DTA AS 100/1 BW EPOXY	SHL	*75	.04	3D	25	AIR	ADHESIVE
EPON 828/EN 308/SILICA FLOUR AS 10/5/1 BW EPOXY	HAC	*29	.00	3D	25	AIR	ADHESIVE
EPON 828/TETA AS 10/1 BW CURE 1	SHL	*50	.01	16H	25	AIR	ADHESIVE
EPON 828/TETA AS 10/1 BW CURE 8	SHL	*38	.00	2D	25	AIR	ADHESIVE
EPON 828/V 140/AL2C3/PIGMENT MODIFIED BLACK EPOXY	GSC	1.46	.02	7D	25	AIR	CUND ADHESIVE
EPON 828/VERSAMID 125 AS 1/1 BW W/3% SiO ₂	SHL	1.06	.02	16H	60	AIR	ADHESIVE
EPON 828/VERSAMID 125 AS 100/75 BW EPOXY	SHL	*99	.03	16H	82	E-6	ADHESIVE
EPON 828/VERSAMID 140 AS 30/70 BW EPOXY	SHL	4.68	.45	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140 AS 40/60 BW EPOXY	SHL	1.63	.17	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	SHL	1.16	.14	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	SHL	*58	.94	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/DATA AS 70/30/1 BW EPOXY	GSC	*18	.03	12H	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/DATA AS 135 AS 5/5/20 BW	SHL	*81	.03	12H	50	AIR	CUND ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 5/5/20 BW	SHL	*30	.04	24H	125	AIR	CUND ADHESIVE
EPON 828/VERSAMID 140/SR 82 AS 70/30/1 BW EPOXY	SHL	*35	.04	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/T-6-1 AS 2/3/16 BW EPOXY	GSC	*88	.05	7D	25	AIR	ADHESIVE
EPON 828/VERSAMID 15/DIA/T-102 AS 25/7/15/40 BW	GSC	1.12	.05	7D	25	AIR	ADHESIVE
EPON 828/ZZL-0803 AS 100/35-5 BW EPOXY DISPERSION	GSC	1.93	.05	7H	221	AIR	ADHESIVE
EPON 828/140/NOVACITE 1250 COATING	SHL	1.49	.16	7D	25	AIR	ADHESIVE
EPON 828/87/AEP/CB-0-SIL AS 15/50 BW EPOXY	SHL	1.71	.33	4H	64	AIR	ADHESIVE
EPON 828/140 AS 50/50 BW EPOXY	SHL	*92	.02	7D	25	AIR	ADHESIVE
EPON 934/A/B AS 100/33 BW EPOXY	SHL	*26	.00	7D	225	AIR	ADHESIVE
EPON 934/A/B AS 100/33 BW EPOXY W/MEK	SHL	2.87	.02	2H	225	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW W/MEK/MOS 2	SHL	2.93	.03	2H	82	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	SHL	2.01	.11	1H	140	AIR	ADHESIVE
EPON 956/A/B AS 100/58 BW CARBOLAC/CABOSIL	SHL	*19	.01	7D	225	AIR	ADHESIVE
EPON 956/A/B AS 100/58 BW MOS2/CARBOLAC/CABOSIL	SHL	*81	.00	11	225	AIR	ADHESIVE
EPoxy-Patch Kit 0151 CLEAR EQUAL LENGTHS FOR TUBES	HYS	*88	.11	7D	25	AIR	ADHESIVE
EPoxy-Patch Kit 0151 EQUAL LENGTHS FOR TUBES	HYS	1.51	.01	24H	625	AIR	ADHESIVE
EPoxy-Patch Kit 1C WHITE EQUAL LENGTHS FOR TUBES	HYS	1.80	.02	24H	25	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	#FR CODE	XMTL	XCVCM	CURE TIME	CURE TEMP	ATMS	APPLICATION
EPOXI-PATCH KIT 1073 EQUAL LENGTHS FR TUBES EPOXI-PATCH KIT 606 CILINDRICAL TUBES EPOXY ADHESIVE FCR REPLICAS GRATINGS - PROPRIETARY	HYS BNL INC HUE HUE NSI	4.77 3.99 5.53 1.60 10.89 2.25	.15 .12 .31 .07 .07 .66	24H 24H 30M 24H 24H 7D	90 80 115 25 25 4H	AIR AIR AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EPOXY 14 EPOXY 220 A/B AS EQUAL PARTS FROM TUBES EPOXY 330 A/B AS EQUAL PARTS FROM TUBES EPOXY 907 A/B AS EQUAL LENGTHS FROM TUBES							
EPOXYLITE P EPOXY EPOXYLITE 9653 TYPE 3	EPC EPC PIC PIC PIC DUP	3.27 15.48 .93 .53 .50 .94	.03 -0.1 -.13 -.13 -.33 .38	24H 24H 16H 45M 45M 3H	25 25 150 150 150 1H	AIR AIR AIR AIR AIR 160	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EPY 150 PRE PACK EPOXY ADH LOT L 101	ACC	1.30	.16	2H	150	AIR	ADHESIVE
ESP 108 GRAY ONE PART EPOXY	ACC	1.43	.27	1H	121	AIR	ADHESIVE
ESP 109 GRAY ONE PART EPOXY	ACC	1.68	.01	1H	121	AIR	ADHESIVE
ESP 110 GRAY ONE PART EPOXY	ACC	1.94	.00	90M	124	PSI	ADHESIVE
EUREPO 710/VERSAMID 140 AS 2/1 SW EPOXY EX 8762 EPOXY DIELECTRIC ADHESIVE	ACC	.81	.00	1H	121	AIR	ADHESIVE
FA-8/DA-5 AS 100/13.5 BW EPOXY	BAC	.74	-.25	2H	240	AIR	ADH. PUTTING
PASSON TAPE 333 WHITE POLYESTER FILM/R FIBERITE E-3938 EPOXY	APF FIB	2.64 .44	-.34 .01	24H 10M	71	AIR	ADHESIVE TAPE
FM 123-2 EPOXY ADH FILM - ORANGE	ACC	1.17	.01	30M	149	AIR	ADHESIVE
FM 123-2 EPOXY ADH FILM - ORANGE	ACC	1.17	.01	30M	150	PSI	ADHESIVE
FM 123-2LC EPOXY ADH FILM PURPLE/F	ACC	1.68	.27	1H	121	AIR	ADHESIVE
FM 123-2LC MODIFIED AS NB4JD-68C EPOXY PURPLE	ACC	1.94	.01	1H	121	PSI	ADHESIVE
FM 123-5 EPOXY ADH FILM BLUE-GREEN	ACC	.81	.02	1H	121	PSI	ADHESIVE
PH 123-5 EPOXY ADH FILM GREEN	ACC	.98	.02	1H	121	PSI	ADHESIVE
PH 150-1 SUPPORTED EPOXY ALUM FILM HONEYCOMB ADH	ACC	4.9	-.04	14H	177	AIR	ADHESIVE
PH 150-2 SUPPORTED EPOXY FILM EP 15 HONEYCOMB ADH	ACC	8.7	-.06	1H	177	AIR	ADHESIVE
PH 150-2U UNSUPPORTED EPOXY FILM ADH	ACC	8.9	-.02	1H	177	AIR	ADHESIVE
PH 24 EPOXY ADH FILM ORANGE	ACC	.86	.21	10H	121	PSI	ADHESIVE
PH 34-18U ADHESIVE FILM POLYIMIDE/Glass	ACC	1.38	-.00	90M	177	AIR	ADHESIVE
PH 35U UNSUPPORTED EPOXY ADHESIVE FILM BLUE	ACC	1.48	-.34	1H	121	PSI	ADHESIVE
PH 36 FILM ADHESIVE POLYIMIDE/Glass	ACC	.82	-.02	2H	288	AIR	ADHESIVE
PH 37 EPOXY FOAM ALH OLIVE GREEN	ACC	1.73	-.04	10H	121	PSI	ADHESIVE
PH 37 EPOXY FOAM ALH PER HMS 20-1591-CL2	ACC	1.11	-.05	3H	177	AIR	ADHESIVE
PH 40 EPOXY FOAM	ACC	1.30	-.05	1H	177	PSI	ADHESIVE
PH 400 SUPPORTED EPOXY FILM ADH GRAY	ACC	1.13	-.05	6H	177	AIR	ADHESIVE
PORTN ECO3103 EPOXY FILM ADH UNSUPPORTED	FIC VEL	4.49 4.48	2.59 1.98	14D 14D	25 25	AIR AIR	ADHESIVE ADHESIVE
PR 127 A/E AS 16/1 BW							
PR 127 A/B AS 16/1 BW							
PR 7035 UNSUPPORTED ADH FILM	FBC	2.31	.94	1H	121	AIR	ADHESIVE
PRALOK X-912 FILM ADH SYSTEM - THERMOSETTING	FRA	2.63	.53	45M	170	AIR	PALE ADHESIVE
PS49 A/B AS 1/1 BW FILLED EPOXY	JIN	3.32	.01	24H	25	AIR	CONC ADHESIVE
PS8CP/P88CPL AS 13/10 BW	TRI	3.00	-.92	24H	25	AIR	ADHESIVE
GA-2 A/B AS 1/1 BW EPOXY CEMENT	AUT	2.48	.18	48H	25	AIR	ADHESIVE

SECTION 1 — ADHESIVES

MATERIAL	MF&A CODE	XTHL	XCVCM	CURE TIME	CUBE TEMP	ADHS	APPLICATION
GAGEKOTE 1 STRAINAGE ADH AND COATING GARLOCK 201 A/B AS 1/1 BW EPOXY GE 4088 ADHESIVE CLEAR	HTB GEL GEC	8.12 4.75 3.52	1.40 24H .00	25 25 30H	AIR AIR AIR	ADH-LOCATING ADHESIVE ADHESIVE	
GELVA MP SOL RA 263/ACRYLIC PRES SENS ADH GELVA MP SOL RA 263/ACRYLIC PRES SENS ADH	MON MON	.79 .62	.08 .03	160 24H	AIR AIR	ADHESIVE ADHESIVE	
GELVA MP SOL RA 657/ACRYLIC PRES SENS ADH GELVA MP SOL RA 657/ACRYLIC PRES SENS ADH	MON MON	.85 .71	.31 .04	24H 24H	AIR AIR	ADHESIVE ADHESIVE	
GELVA MP SOL RA 784/ACRYLIC PRES SENS ADH GELVA MP SOL RA 784/ACRYLIC PRES SENS ADH	MON MON	1.55 1.00	.19 .05	7D 24H	AIR AIR	ADHESIVE ADHESIVE	
GELVA MP SOL RA 858/ACRYLIC PRES SENS ADH GELVA MP SOL RA 858/ACRYLIC PRES SENS ADH	MON MON	1.25 1.02	.38 .02	24H 24H	AIR AIR	ADHESIVE ADHESIVE	
GENEPOXY 185/VERSAMID 115 AS 1/1 BW EPOXY	GMC	.35	.00	24H 16H	95 95	AIR AIR	ADHESIVE
G3 306-4 EPOXY FILM ADHESIVE GLASS ADH 2060 A/B AS 2/1 BW EPOXY	ACC MM	.89 1.07	.01 .01	PSI 21D	66 25	AIR AIR	FILM ADHESIVE ADHESIVE
GT 400 TAPE S/ASSEMBLY POLYESTER/POLYESTER HE 10 OPTICAL CEMENT A/B AS 93/7 BW	GTS EAS	18.69 18.69	.12 .70	24H 48H	160 160	AIR AIR	2-SIDED TAPE OPTICAL CEMENT OPTICAL CEMENT OPTICAL CEMENT FILM ADHESIVE
HE 79 OPTICAL CEMENT A/B AS 100//2.5 BW HE 80 OPTICAL CEMENT A/B AS 100//2.5 BW	EAS EAS	15.11 15.87	1.27 1.26	7D 7D	225 225	AIR AIR	OPTICAL CEMENT OPTICAL CEMENT
HEXABOND 1 EPOXY FILM ADHESIVE HEXABOND 3 A/B AS 100/19.7 BW	HEX HEX	1.40 1.40	.35 .30	1H 1H	12.1 15.4	AIR AIR	HEXABOND FILM ADHESIVE
HEXBOND 3 EPOXY FILM ADHESIVE UNSUPPORTED HS 5400 EPOXY PHENOLIC FILM ADHESIVE	HEX HS2	1.23 1.93	.26 .14	12.7 14H	12.7 14H	AIR AIR	FILM ADHESIVE FILM ADHESIVE
HP 432 EPOXY-PHENOLIC FILM ADHESIVE	ACC ACC	.7	-.02	10D 17.4	10D 17.4	PSI PSI	ADHESIVE FILM ADHESIVE
HP-424 PASTE - OLIVE/GREEN HK-1000 LAMINATING FILM	ACC MM	1.27 1.10	.00 .00	45H 15H	14.3 24.9	AIR AIR	ADHESIVE ADHESIVE
HSOL 11C A/B AS 1/1 BW EPOXY HSOL 2C A/B AS 25/110 BW BROWN EPOXY	HYS HYS	.63 1.85	2.14 -.01	1H 1H	14.9 14.9	AIR AIR	ADHESIVE ADHESIVE
HSOL 4326/3421 AS 100/6 BW HSOL 6C A/B AS 1/1 BW ALUM FILLED EPOXY	HYS HYS	1.42 1.55	-.00 -.00	4H 4H	90 90	AIR AIR	ADHESIVE ADHESIVE
HSOL 6C A/B AS 12/4.6 BW ALUM FILLED EPOXY K-10 ADHESIVE	KCO KCO	1.92 1.92	-.08 -.08	48H 48H	25 25	AIR AIR	ADHESIVE ADHESIVE
K-16 A/B AS 3/1 BW CONDUCTIVE EPOXY K-20 A/B AS 10/7 BW EPOXY	HYS HYS	2.22 2.43	-.01 -.01	7D 7D	25 25	AIR AIR	CONDUCTIVE CONDUCTIVE
KLEEN-STIK DUBL-STIK 2 SIDED TAPE/F K3-7238/H2-3475 AS 25/4 BW EPOXY	CON HYS	1.31.15 1.32	3.49 3.49	24H 24H	25 25	AIR PSI	ADHESIVE ADHESIVE
LAMINATING FILM 2C-200-1/FCIL SANDWICH LCA4/ACT BAS 10C/4-5 BW EPOXY	THE BAC	.61 1.19	-.01 -.03	30H 16H	135 100	AIR AIR	ADHESIVE ADHESIVE
LCA9/ACT BAS 10C/4-5 BW MINERAL FILLED GREEN LEAL CC EPOXY ADH	LEL LEL	1.23 1.45	-.03 -.07	2H 30H	93 25	AIR AIR	ADHESIVE ADHESIVE
LEPKO FLD 109/LH-52 AS 100/74 BW LIGHT GRAY EPOXY LEPKO FLD 109/LH-52 AS 100/74 BW LIGHT GRAY EPOXY	LCC LCC	1.17 1.03	.05 .02	24H 24H	104 104	AIR AIR	ADHESIVE LOW TEMP ADH
LEPKO FLD 109/LH-52 AS 100/74 BW LIGHT GRAY EPOXY	LCC	2.65	.03	24H	25	AIR	ADHESIVE
				1H	93	AIR	

SECTION 1 --- ADHESIVES

MATERIAL	6PA CODE	STML	RCVCH	CURE TIME	CURE TEMP	4THS	APPLICATION
LEFKOW ELD 46/LH-52 AS 100/74 BW YELLOW/GREEN EPOXY	LCC	1.94	.08	3H	68	AIR	ADHESIVE
LEFKOW ELD 49/LH-52 AS 100/74 BW YELLOW/GREEN EPOXY	LCC	2.30	.09	3H	68	AIR	ADHESIVE
LENS BOND C-59 A/B AS 20/1 BV	SUD	2.94	.10	8D	42	AIR	OPT CEMENT
LENS BOND F-62 A/B AS 20/1 BV	SUD	4.83	.16	24H	70	AIR	OPT CEMENT
LENS BOND F-62 A/B AS 20/1 BV	SUD	5.77	.26	24H	70	AIR	OPT CEMENT
LENS BOND UV-9 POLYESTER SUN LAMP CURE	SUD	3.65	.26	44H	70	AIR	OPT CEMENT
LENS BOND UV-9 POLYESTER UV LAMP CURE	SUD	3.68	.44	0.3	24H	25	THERMSEAL
LOCTITE A RED ADHESIVE FROM BOLTS	LTC	2.47	.11	7D	25	PSI	THREAD SEAL
LOCTITE A RED ADHESIVE FROM BOLTS	LTC	2.86	.07	7D	25	PSI	THREAD SEAL
LOCTITE A RED ADHESIVE FROM SHIMS	LTC	1.64	.00	19H	50	PSI	THREAD SEAL
LOCTITE AA OVER PRIMER N	LTC	1.94	.00	72H	25	PSI	WELD SEALANT
LOCTITE AA WELD SEALANT GREEN FROM SHIMS	LTC	1.19	.02	16H	25	PSI	WELD SEALANT
LOCTITE BB BEARING MOUNT YELLOW FROM BOLTS	LTC	14.30	.43	48H	25	PSI	ADH-SEALANT
LOCTITE BB BEARING MOUNT YELLOW FROM BOLTS	LTC	12.63	.30	7D	25	PSI	ADH-SEALANT
LOCTITE CC BLUE ADHESIVE	LTC	13.45	.68	7D	25	PSI	ADH-SEALANT
LOCTITE C BLUE ADHESIVE FROM BOLTS	LTC	2.48	.86	12H	77	PSI	ADH-SEALANT
LOCTITE DEP-33	LTC	2.89	.53	48H	25	PSI	ADH-SEALANT
LOCTITE E-L-277	LTC	3.79	.29	24H	25	PSI	ADH-SEALANT
LOCTITE E-222 MILD STRENGTH ADH PURPLE FROM BOLTS	LTC	17.71	.22	72H	25	PSI	THREAD SEAL
LOCTITE E-222 MILD STRENGTH ADH PURPLE FROM BOLTS	LTC	26.84	.65	72H	25	PSI	THREAD SEAL
LOCTITE E-2442 MEDIUM STRENGTH ADH BLUE FROM BOLTS	LTC	13.74	.78	48H	25	PSI	ADH-SEALANT
LOCTITE E-2442 MEDIUM STRENGTH ADH BLUE FROM BOLTS	LTC	16.43	.43	72H	25	PSI	ADH-SEALANT
LOCTITE E-262 HIGH STRENGTH ADH RED FROM BOLTS	LTC	14.43	.18	16H	50	PSI	ADH-SEALANT
LOCTITE E-262 HIGH STRENGTH ADH RED FROM SHIMS	LTC	6.10	.12	12H	24H	PSI	ADH-SEALANT
LOCTITE E-271 HIGH STRENGTH ADH RED FROM BOLTS	LTC	6.10	.24	47H	48H	PSI	ADH-SEALANT
LOCTITE E-290 MEDIUM STRENGTH ADH GREEN FROM BOLTS	LTC	5.19	.02	48H	25	PSI	ADH-SEALANT
LOCTITE E-290 MEDIUM STRENGTH ADH GREEN FROM BOLTS	LTC	2.97	.97	48H	25	PSI	ADH-SEALANT
LOCTITE E-290 MEDIUM STRENGTH ADH GREEN FROM SHIMS	LTC	2.43	.91	16H	50	PSI	ADH-SEALANT
LOCTITE E-290 MEDIUM STRENGTH ADH GREEN FROM SHIMS	LTC	1.93	.91	7D	25	PSI	ADH-SEALANT
LOCTITE E-317 STRUCTURAL ADHESIVE	LTC	1.02	.46	13H	22	PSI	ADHESIVE
LOCTITE E-324/ACT 707	LTC	5.00	.00	11	15M	12.1	AIR
LOCTITE E-325/ACT 7C7	LTC	2.45	.00	28	15M	12.1	AIR
LOCTITE E-326/PRIMER N	LTC	3.75	.08	14	6H	60	E-2
LOCTITE E-326/L OCQUIC PRIMER N	LTC	1.21	.08	6H	60	E-2	OPICAL CEMENT
LOCTITE E-354 AD ACYLIC UV CONVERTIBLE	LTC	9.61	.33	6H	60	AIR	OPICAL CEMENT
LOCTITE E-354 AD ACYLIC UV CONVERTIBLE	LTC	8.94	.32	6H	60	AIR	OPICAL CEMENT
LOCTITE E-361 HIGH STRENGTH ADH GREEN	LTC	5.21	.32	24H	25	PSI	ADHESIVE
LOCTITE E-93-13 SUFEE BONDER ADHESIVE	LTC	8.92	.32	24H	25	PSI	ADHESIVE
LOCTITE HA-509 CONDUCTIVE A/B AS 1/1 BY YELLO	OME	1.28	.09	25D	25	AIR	ADHESIVE
MACBOND 962b POLYESTER FILM/2 SIDE ACR ADH M1418/F	NOK	1.56	.05	25D	25	AIR	FILM ADHESIVE
MACBOND 95-1b3 SINGLE COMPONENT CU FILLED EPOXY	NOK	1.25	.00	25D	25	AIR	FILM ADHESIVE
HARPOXY 95-1b8 A/B AS 19/1 Bi Cu FILLED EPOXY	KEY	.28	.01	2H	149	AIR	ADHESIVE
HARPOXY 95-202 SINGLE COMPONENT CU FILLED EPOXY	KEY	.45	.04	16H	204	AIR	CUBU ADHESIVE
		.27	.00	2H	204	AIR	ADHESIVE

SECTION 1 — ADHESIVES

MATERIAL	MFR CODE	WTML	ACCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
MARPOXY 95-4 A/B AS 19/1 BW CU FILLED EPOXY	KEY	1.45	-10	24H	25	AIR	COLD ADHESIVE
MARPOXY 95-7 A/B AS 19/1 BW CU FILLED EPOXY	KEY	1.18	-0.8	24H	66	AIR	COLD ADHESIVE
MARPOXY 95-9 ONE COMPONENT CU FILLED EPOXY	KEY	.63	-0.6	1H	160	AIR	LONG ADHESIVE
MASTER BOND GP6 POLYESTER COPOLYMER	MBI	14.73	.01	24H	204	AIR	THEATR SEAL
H-30 A/B AS 95/5 EN ACRYLIC ADH/BENZYL PEROXIDE	ACP	14.01	.04	7D	249	AIR	ADHESIVE
H-30 A/B AS 95/5 EN TOLUENE ACRYLIC ADHESIVE	ACP	1.03	.04	25H	149	AIR	ADHESIVE
METLBOND 1113 EPOXY FILM ADHESIVE	WCN	1.28	.08	1H	127	AIR	ADH FILM
METLBOND 227 EPOXY FILM ADHESIVE	WCN	1.27	.01	1H	177	2-1	ADH FILM
METLBOND 329 CLOTH SUPPORTED EPOXY FILM	WCN	.49	.00	2H	93	AIR	ADHESIVE
METRE-GRIP 3446/19 AS 1% CAT BW	HEP						
MICROOC CIRCUIT TYPE A SILVER FILLED EPOXY	TNC	6.14	-2	16d	204	AIR	COLD ADHESIVE
MHN TAPE X-1140 THERMOSET RUBBER ADH FILM/R	MHN	6.00	-0.07	30M	121	AIR	2-SIDED TAPE
MHN TAPE X-1255 KAFTON THERMOSET ACRYLIC ADH/2 SIDE	MHN	1.00	.00				2-SIDED TAPE
MHN TAPE X-1255 KAFTON THERMOSET ACRYLIC ADH/2 SIDE	MHN	.93	.02				2-SIDED TAPE
MHN TAPE 4016 FOAM/2 SIDE ACRYLIC ADH/FOIL SANDWICH	MHN	2.64	.02				FOAM TAPE 2 SIDE
MHN TAPE 464 TISSUE FILM/RUBBER ADH/R	MHN	6.17	.08				2-SIDED TAPE
MHN TAPE 465 TRANSFER FILM/SYN ACRYLIC ADH/R	MHN	.84	.00				TRANSFER TAPE
MHN TAPE 666 PVC FILM/2 SIDE ACRYLIC ADH/R	MHN	2.11	.15				2-SIDED TAPE
MHN TAPE 666 PVC FILM/2 SIDE ACRYLIC ADH/R	MHN	4.53	1.4	30M	25	AIR	ADHESIVE
MHN TAPE 2704 SILICONE ALH	MHN						
NARMCO 3135/7111 AS 1/1 BW EPOXY	WCN	.59	.01	30d	40	AIR	ADHESIVE
NARMCO 328 SHEET ADHESIVE	WCN	1.00	.01	30d	165	AIR	ADH FILM
NARMCO 329 SHEET ADHESIVE	WCN	1.21	.05	90d	165	AIR	ADH FILM
NE 581 A/B AS 4/1 EPOXY OPTICAL CEMENT - EPOXY	NEI	10.66	.002	7D	25	AIR	OPT CEMENT
NOA 60 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	2.22	.002	1H	125	AIR	OPT CEMENT
NOA 60 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	.90	.01				OPT CEMENT
NOA 61 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	2.24	.01				OPT CEMENT
NOA 61 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	1.65	.01				OPT CEMENT
NOA 63 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	2.27	.04				OPT CEMENT
NOA 65 OPTICAL ADHESIVE F 5 MIN UV EXP	NOR	2.89	.14				OPT CEMENT
NODE BOND BAR-10176 LX-125 THERMOSET ADH/F	ACC	.61	.00	30M	25	AIR	ADHESIVE
NODE BOND GG-288-8 BATCH 108	ACC	.57	.04	30M	177	AIR	ADHESIVE
OPTICAL COUPLING CIND - SILICONE (PROPRIETARY)	BPN	2.98	1.12	1H	25	AIR	ADHESIVE
P-400/CAT 515 AS 1/1 BW EPOXY	APP	.30	.01	14D	25	AIR	ADHESIVE
P-460 A/B AS 100/7 BW EPOXY	APP	3.18	.17	24H	25	AIR	ADHESIVE
P-61 SILICA FILLED EPOXY	REC	.31	.04	8H	135	AIR	ADHESIVE
PALMER CEMENT 0014	PLM	4.02	.01	17H	80	AIR	ADHESIVE
PERMA-LOK HH120 FRCH SHIMS	PIC	3.29	.37	48H	120	PSI	ADH-SEALANT
PERMA-LOK HL126 FRCH SHIMS	PIC	3.76	.02	48H	225	PSI	ADH-SEALANT
PERMA-LOK HL133 FRCH SHIMS	PIC	4.16	.03	48H	225	PSI	ADH-SEALANT
PERMA-LOK HH09 FRCH SHIMS	PIC	4.41	.04	48H	225	PSI	ADH-SEALANT
PERMA-LOK HL09 FRCH SHIMS	PIC	4.57	.03	48H	225	PSI	ADH-SEALANT
PERMA-LOK LM012 FRCH SHIMS	PIC	28.57	.6-10	48H	225	PSI	ADH-SEALANT
PERMA-LOK LM113 FRCH SHIMS	PIC	14.67	.02-3	48H	225	PSI	ADH-SEALANT
PERMA-LOK LM115 FRCH SHIMS	PIC	10.84	.4-56	48H	225	PSI	ADH-SEALANT
PERMA-LOK TM124 TMYLAR/2 SIDE NATURAL RUBBER/R	PER	3.58	.58				2-SIDED TAPE

SECTION 1 --- ADHESIVES

MATERIAL	NFR CODE	%TAL	ACVCM	CURE TIME	CURE TEMP	ADHS	APPLICATION
PETEON CHEM EPCY A/B AS 1/1	PCB	1.06	.46	24H	125	AIR	ADHESIVE
PITEL CA A/B AS 1 TROP A/B GH B CONDUCTIVE ADHESIVE	DUP	2.58	.38	3D	1.5	AIR	COAT ADHESIVE
PLASTI LOCK 717 B NYLON/EPOXY ADHESIVE	BFG	1.77	.76	1H	12.1	AIR	FLAT ADHESIVE
PLAOUND 30 FLUON TUBE/FOIL SANDWICH	GAC	1.55	.73	4H	25	AIR	ADHESIVE
PLV 2000 VITON ADHESIVE	PEL	1.77	.63	3D	25	AIR	ADHESIVE
POLY CAST EC EPOXY LCT 173-4416-4	PLA	.83	.27	3H	171	AIR	ADHESIVE
POLYGUIDE LAMINATING FILM	ECC	1.48	.33	5H	163	AIR	FLAT ADHESIVE
POLYSET EPC 68 BLUE EPOXY POWDER	MNC	.25	.03	24H	125	PSI	ADHESIVE
PR 156 4 A/B AS 7.7/100 BN/BV POLYURETHANE CASTING	PRC	1.12	.01	20H	160	AIR	ADHESIVE
PR 412 1 A/B AS 1/1 BN EPOXY	PTI	7.3	.03	16H	85	AIR	ADHESIVE
PYRALUX WA CLOTH SUPPORT/ACRYLIC FILM ADH - AMBER	DUP	.24	.01	1H	190	B-2	FLAT ADHESIVE
PYRALUX 3249-87 CLCH SUPPORTED FILM ADHESIVE	DUP	.31	.02	2H	100	AIR	FLAT ADHESIVE
Q1-2557 SILICONE AS 1/4 BN	DCC	2.59	.07	1H	95	AIR	FLAT ADHESIVE
Q3-6552 7 A/B AS 1/1 BN OPTICAL COUPLING CPND	DCC	1.73	.78	1H	25	AIR	OPTICAL COUPLE
R-1500 ONE COMPONENT ELEC COND SILICONE LOT U13-058	HCG	.31	.04	7D	90	AIR	ADH-SEALANT
R-1500 ONE COMPONENT ELEC COND SILICONE LOT U13-087	HCG	.45	.06	7D	204	AIR	ADH-SEALANT
R-1500 ONE COMPONENT ELEC COND SILICONE LOT U13-087	HCG	.39	.06	7D	204	AIR	ADH-SEALANT
R-2500 A/B AS 10/1 BN CLEAR SILICONE LOT U14-034	HCG	.27	.04	7D	95	AIR	ADH-PUTTING
R-2500 A/B AS 10/1 BN CLEAR SILICONE LOT U14-034	HCG	.25	.05	7D	25	AIR	ADH-PUTTING
R-2500 A/B AS 10/1 BN CLEAR SILICONE LOT 298	HCG	.25	.05	7D	25	AIR	ADH-PUTTING
R-2510 0.5% BN CAT WHITE SILICONE LOT 295	HCG	.29	.03	7D	25	AIR	ADHESIVE
R-2510 0.5% BN CAT WHITE SILICONE LOT 295	HCG	.37	.03	7D	25	AIR	ADHESIVE
R-2520 0.5% BN CAT WHITE SILICONE LOT 297	HCG	.59	.03	7D	25	AIR	ADHESIVE
R-2520 0.5% BN CAT WHITE SILICONE LOT 297	HCG	.28	.05	7D	25	AIR	ADHESIVE
R-2566 0.5% BN CAT RED COUNTERTOP VOLATILE SILICONE	HCG	.42	.07	7D	25	AIR	ADHESIVE
R-2566 0.5% BN CAT RED SILICONE LOT 281	HCG	.44	.07	7D	25	AIR	ADHESIVE
R-2566 0.5% BN CAT RED SILICONE LOT 281	HCG	.35	.03	7D	25	AIR	ADHESIVE
R-2566 0.5% BN CAT RED SILICONE LOT 282	HCG	.31	.03	7D	25	AIR	ADHESIVE
R-2567 0.5% BN CAT CLEAR SILICONE LOT 282	HCG	.35	.03	7D	25	AIR	ADHESIVE
R-2567 0.5% BN CAT CLEAR SILICONE LOT 300	HCG	.63	.05	7D	25	AIR	ADHESIVE
R-2567 0.5% BN CAT CLEAR SILICONE LOT 300	HCG	.62	.05	7D	25	AIR	ADHESIVE
R-2568 0.5% BN CAT CLEAR SILICONE LOT 300	HCG	.41	.04	7D	25	AIR	ADHESIVE
R-2568 0.5% BN CAT RED SILICONE LOT 301	HCG	.31	.03	7D	25	AIR	ADHESIVE
R-2568 0.5% BN CAT RED SILICONE LOT 301 (KEKUN 120888)	HCG	.38	.07	7D	25	AIR	ADHESIVE
R-313 A/B AS 100/8 BN EPOXY	GG	1.71	.19	12H	125	AIR	ADHESIVE
RD 3327-6/ACCEL 4/F RELIGAL PAPER MKCC11069 POLYIMIDE FILM	HCC	7.93	.37	24H	66	AIR	ADHESIVE
RELIGAL CND 398 FILM ADHESIVE GRAY	ERG	3.35	.31	20M	25	AIR	ADHESIVE
	MNC	1.17	.01	1H	130	PSI	FLAT ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MFR CODE	MFR ATML	ACVCH	CURE TIME	CURE TEMP	ATMOS	APPLICATION
RELIABOND 7115 CLOTH SUPPORT EPOXY FILM KESDEL EPoxy LIte IIRON FILLING RESIN 6005/RESDEL 41 AS 5/1 BW EPOXY KESDEL 01-02-01 CLEA 6005/T-12 AS 1/1 BW KESDEL 7004 EPOXY ADH A/B AS 1/1 BW RESYN 30-1215 PRESSURE SENSITIVE ACRYLIC ADHESIVE	RHC RES FUL NSC	.96 .82 1.67 .63	.06 .03 .12 .04	1H 160 24H 25	121 160 25 25	PSI AIR AIR AIR	FILM ADHESIVE ADHESIVE ADHESIVE ADHESIVE
RHOPLEX N-619 FRE SENS ACRYLIC ADH/FOIL SANDWICH	ROH	.51	.00	30d	95	AIR	ADHESIVE
RIGIDAMP 1900-1 VISCOELASTIC FILM/3M TAPE 467 RTV 118 ONE COMPONENT TRANSLUCENT SILICONE RTV 11/T-12 SILVER FLAKE 0-5% T-12/70% SILVER FLAKE RTV 11/T-12 SILVER FLAKE 0-5% T-12/70% SILVER FLAKE	BAR GEC GEC GEC	2.01 3.46 4.32 4.81	.04 .50 1.10 .22	1H 1D 4D 7D	25 25 25 25	AIR AIR AIR AIR	ADHESIVE ADHESIVE CUND ADHESIVE CUND ADHESIVE
RTV 118 ONE COMPONENT TRANSLUCENT SILICONE RTV 118 SILICONE CEND RTV 1142 ONE COMPONENT WHITE SILICONE RTV 1142 ONE COMPONENT WHITE SILICONE RTV 1142 ONE COMPONENT WHITE SILICONE LOT JM 107 RTV 1154 ADHESIVE SEALANT RTV 1162 ONE COMPONENT WHITE SILICONE RTV 1168 SILICONE RTV 511 .007-.009 IN THICK	GEC GEC GEC GEC GEC GEC GEC GEC	1.96 2.21 .24 .24 .22 1.59 1.72 .62	1.01 1.07 .01 .00 .00 4.42 3.79 .55	24H 24H 6D 7D 7D 7D 7D 48H	25 25 25 25 25 25 25 25	AIR AIR AIR AIR AIR AIR AIR AIR	ADHESIVE ADH-SEAL-ENCAPS ADH-SEALANT ADHESIVE ADHESIVE ADH-SEALANT ADHESIVE ADHESIVE
RTV 511 .007-.009 IN THICK	GEC	.78	.39	48H	150	E-O	ADHESIVE
RTV 511 0-5% B CAT DEVOL AT 100C LOT JN 170 RTV 511 0-5% B CAT DEVOL AT 125C LOT JN 170 RTV 511 0-5% B CAT DEVOL AT 150C LOT JN 170 RTV 511 0-5% B CAT VIGGIN RESIN LOT KH 181 RTV 511/577/T-12 AS 40 GR/10 DROPS SILICONE RTV 511/577/T-12 AS 1/4% BW	GSC GSC GSC GSC GSC GSC	1.82 .78 .49 .49 .69 .65	.49 .7D .21 .7D .76 .35	7D 225 7D 225 7D 72H	125 125 125 125 25 25	AIR AIR AIR AIR AIR E-O	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
RTV 560/T-12 AS 0-1% T-12 RTV 560/T-12 AS 0-1% T-12	GEC	2.22	.49	150D	25	AIR	ADHESIVE
RTV 560/T-12 AS 0-5% T-12 RTV 560/T-12 AS 1/1/0.5% BW SILICONE	GEC	2.52	.15	24H	125	E-O	ADH-SEAL-ENCAPS
RTV 560/577/T-12 AS 1/9/0.5% BW SILICONE RTV 560/577/T-12 AS 1/9/0.5% BW SILICONE	GEC GEC	3.39 .45	.57 .08	30D 14D	25 25	E-O AIR	ADHESIVE ADHESIVE
RTV 560/580/T-12 AS 1/2 BW 6/0.5% T-12	GEC	2.20	.71	1D	225	AIR	ADHESIVE
RTV 560/580/T-12 ECA ADHESIVE	GEC	.46	.21	4D	75	E-O	ADH-SEAL-ENCAPS
RTV 566 0-075% BW CAT SILICONE	GEC	2.82	.46	36H	25	AIR	ADHESIVE
RTV 566 0-085% BW CAT SILICONE	GEC	1.11	.09	7D	225	AIR	ADHESIVE
RTV 566 0-09% BW CAT SILICONE	GEC	1.10	.01	7D	225	AIR	ADHESIVE
RTV 566 0-1% BW CAT SILICONE LOT BH 164/AH102	GEC	.10	.02	7D	25	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MEP CODE	#ML	%CVC	CURE TIME	CURE TEMP	ATMOS	APPLICATION
RTV 566 0-16 BK CAT SILICONE LOT J2 133	GBC	.24	.00	7D	25	AIR	ADHESIVE
RTV 566 0-16 BK CAT SILICONE LOT KA 136	GBC	.13	.00	7D	25	AIR	ADHESIVE
RTV 566 0-16 BK CAT SILICONE LOT KA 137	GBC	.12	.01	4H	80	AIR	ADHESIVE
RTV 566 0-16 BK CAT SILICONE LOC 1200 PAKHER/SANDWICH	GBC	.13	.01	4H	80	AIR	ADHESIVE
RTV 566 0-16 BK CAT SILICONE/GE SS4 155 PAKHER/SANDWICH	GBC	.34	.03	24H	25	AIR	PULLING-ADH
RTV 566 0-3% BK CAT SILICONE	GBC	.36	.02	5D	25	AIR	PULLING-ADH
RTV 566 0-5% BK CAT SILICONE	GBC	.10	.01	4H	25	AIR	ADHESIVE
RTV 566 0-13% BK CAT SILICONE	GBC	.99	.04	7D	25	AIR	ADH-SEALANT
RTV 577/T-12 SILICONE	GBC	.10	.04	7D	25	AIR	ADHESIVE
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 3	GBC	.73	.46	24H	120	AIR	ADHESIVE
RTV 630 5% BW CAT GRAY SILICONE	GBC	.73	.41	1H	120	E-3	ADH-POULTING
RTV 8111/CAT 9851 AS 97/3 BN	GBC	.36	.31	1H	25	AIR	ADH-POULTING
RTV 8112/CAT 9858 AS 94/6 BN	GBC	.21	.21	1H	25	AIR	ADH-POULTING
RTV 8223/CAT 9858 AS 96/4 BN	GBC	.23	.21	1H	25	AIR	ADH-POULTING
RTV 8243/CAT 9858 AS 96/4 BN	GBC	.38	.22	1H	25	AIR	ADH-POULTING
RTV 8262/CAT 9858 AS 97/3 BN	GBC	.68	.22	1H	25	AIR	ADH-POULTING
RTV 8263/CAT 9858 AS 94/6 BN	GBC	.79	.25	1H	25	AIR	ADH-POULTING
RTV 8312/CAT 9858 AS 95/5 BN	GBC	.90	.21	1H	25	AIR	ADH-POULTING
RTV 8373/CAT 9858 AS 97/3 BN	GBC	.41	.22	1H	25	AIR	ADH-POULTING
RTV 8382/CAT 9858 AS 95/3 BN	GBC	.31	.22	1H	25	AIR	ADH-POULTING
RTV 8383/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8384/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8385/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8386/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8387/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8388/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8389/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8390/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
RTV 8391/CAT 9858 AS 97/3 BN	GBC	.10	.04	7D	25	AIR	ADH-POULTING
SCOTCHBOND 4170 STUD LOCKING BLUE FROM BOLTS	MMD	.41	.02	7H	22	PSI	ADH-SEALANT
SCOTCHBOND 4171 STUD LOCKING PURPLE FROM BOLTS	MMD	.69	.04	7H	22	PSI	ADH-SEALANT
SCOTCHBOND 4172 SCREW LOCKING PURPLE FROM BOLTS	MMD	.69	.04	7H	22	PSI	ADH-SEALANT
SCOTCHBOND 4173 BUSHING ASSY GREEN FROM BOLTS	MMD	.13	.04	7H	22	PSI	ADH-SEALANT
SCOTCHBOND 4174 BUSHING ASSY GREEN FROM SHIMS	MMD	.04	.04	7H	22	PSI	ADH-SEALANT
SCOTCHBOND 4175 HYDRAULIC SEALANT AMBER FROM BOLTS	MMD	.01	.02	7H	22	PSI	ADH-SEALANT
SCOTCHCAST 10 (XR-5241) A/B AS 1/1 BW RUST RED EPOXY	MMD	.96	.52	7D	22.5	AIR	ADHESIVE
SCOTCHGRIP EC 1357 CONTACT CEMENT RUBBER BASE	MMD	.09	.81	24H	22.5	AIR	ADHESIVE
SCOTCHGRIP 2353 BELLEFON BOLTS	MMD	.48	.90	24H	22.5	AIR	ADHESIVE
SCOTCHGRIP 2451 CRANGE FROM BOLTS	MMD	.19	.48	24H	22.5	PSI	ADHESIVE
SCOTCHWELD 1838 E/A AS 2/1 BW 2-PHENYL GLYCIDYL ETH	MMD	.88	.10	24H	22.5	PSI	ADHESIVE
SCOTCHWELD 1838 E/A AS 1/1 BW EPOXY	MMD	.65	.06	24H	22.5	AIR	ADHESIVE
SCOTCHWELD 2214 ED ALUM FILLED EPOXY	MMD	.48	.05	24H	22.5	AIR	ADHESIVE
SCOTCHWELD 2214 HIGH TEMP ALUM FILLED EPOXY	MMD	.45	.05	40H	22.5	AIR	ADHESIVE
SCOTCHWELD 2214 NMF UNFILLED EPOXY	MMD	.77	.00	1H	12.1	AIR	ADHESIVE
SCOTCHWELD 2214 E/A AS 5/7 BW FLEXIBLE GRAY EPOXY	MMD	.25	.02	48H	49	AIR	ADHESIVE
SCOTCHWELD 2216 E/A AS 5/7 BW FLEXIBLE GRAY EPOXY	MMD	.21	.03	24H	22.5	AIR	ADHESIVE
SCOTCHWELD 2216 E/A AS 5/7 BW 4% N-5 CAB-O-SIL	MMD	.16	.01	2H	65	AIR	ADHESIVE
SCOTCHWELD 2216 E/A AS 5/7 BW 4% N-5 CAB-O-SIL	MMD	.76	.03	16H	22.5	AIR	ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER U/A AS 1/1 BW EPOXY	MMD	.60	.32	180	25	AIR	ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER B/A AS 1/1 BW EPOXY	MMD	.60	.35	2.5H	68	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MFR CODE	XTRM	%VCVM	CURE TIME	CURE TEMP	ATMS	APPLICATION
SCOTCHWELD 2216 CLEAR AMBER B/A AS 5/7 BW EPOXY	MMH HHH	1.75 1.09	.31 .04	7D 24H	65 25	AIR AIR	ADHESIVE ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER B/A AS 5/7 BW EPOXY	MMH HHH	1.13	.02	7D 24H	65 25	E-C	ADHESIVE ADHESIVE
SCOTCHWELD 2216 SANDWICHED BETWEEN ALUMINUM AS 1/1 BY MOUL EPOXY	MMH HHH	1.51	.07	4H	25	AIR	ADHESIVE
SCOTCHWELD 3532 E/A AS 1/1 BW POLYURETHANE BROWN	MMH HHH	1.66	.07	4H	25	PSI	ADHESIVE
SCOTCHWELD 588 SEMIKOTE SF653K825AS EPOXY FSN 804-0-0-916-9847	MMH HHH	4.50	.41	1H	149	AIR	ADHESIVE
SILASTIC 140 WHITE SILICONE	PRC DCC TCA	4.20 1.38 2.08	.53 .01 .22	1H 24H	154 225	PSI	ADHESIVE
SILCOSET 152 WHITE SILICONE	SOA WSL	7.69 16.25	.07 .07	3H 1H	60 25	AIR	AIR-SEALANT ADHESIVE
SMOOTH ON INSTANT EPOXY SMP 62/63 AS 1/1 BW EPOXY	WSL	4.27	.04	10H	25	AIR	ADHESIVE
SMP 62/63 AS 1/1 BW EPOXY	WSL	1.40	.14	2H	60	AIR	ADHESIVE
							FIELD DIELECTRIC
SO LITHANE 113/300/TIPA AS 100/51/4.5 BW FORMULA 10 SR 529 SILGRIP SILICONE PSA	TCC GEC	3.6 2.48	.02 .02	8H 2H	65 25	AIR	ADHESIVE ADHESIVE
SR 585 SILVER FILLED SILICONE	GEC	22.99	1.00	1H	25	AIR	ADHESIVE
SR 585 SILVER FILLED SILICONE ON SILVERED TEFILON	GEC	.60	.00	1H	25	AIR	ADHESIVE
SR 585 SILVER FILLED SILICONE ON SILVERED TEFILON	GEC	10.37	.14	1.5H	38	AIR	ADHESIVE
SS 415 TOLUENE PRIMER BASE	GEC	15.52	.09	24H	95	AIR	ADHESIVE
SPARKING CPND BLUE SOLVENTE 113/300 BASE	IDC	4.43	.00	1H	25	AIR	ADHESIVE TAPE
STYCAST CPC 18A/B AS 100/12.5 BW POLYURETHANE	EBC	.96	.06	7D	25	AIR	ADHESIVE PRIMER
STYCAST 1263/3 A/B AS 100/3 BW EPOXY	EBC	.33	.06	16H	65	AIR	STAKING CEND
STYCAST 1263/3 A/B AS 100/30 BW CLEAR EPOXY	EBC	1.06	.07	16H	107	AIR	ADHESIVE
STYCAST 2651/CAT 11 AS 100/8 BW BLACK EPOXY	EBC	.63	.01	24H	66	AIR	ADHESIVE
STYCAST 2651/MX/CAT 11 AS 100/8 BW BLACK EPOXY	EBC	.84	.03	18D	140	AIR	ADHESIVE
STYCAST 2850 FT/24LY AS 100/4.5 BW EPOXY	EBC	.38	.01	7D	25	AIR	ADHESIVE
STYCAST 2850 FT/24LY AS 100/7 BW EPOXY	EBC	.39	.00	12H	85	AIR	ADHESIVE
STYCAST 2850 GT/9 AS 100/3 BW EPOXY	EBC	.33	.00	24H	25	AIR	ADHESIVE
STYCAST 2850 NT/1 AS 100/2.7 BW BLUE EPOXY	EBC	.52	.03	7D	74	AIR	ADHESIVE
STYCAST 2850 NT/9 AS 100/2.1 BW BLUE EPOXY	EBC	.52	.02	24H	24H	AIR	ADHESIVE
STYCAST 3050/9 AS 100/6 BW DARK RED EPOXY	EBC	.09	.01	7D	25	AIR	ADHESIVE
SYLGARD 170 A/B AS 10/1 BW DARK GRAY SILICONE	EBC	1.19	.01	7D	25	AIR	ADHESIVE
SYLGARD 184 A/B AS 10/1 BW DEVOLLOT GDU 533274 BATCH 1	GSC	.19	.01	7D	25	AIR	ADHESIVE
SYLGARD 186 A/B AS 100/4.5 BW SILICONE COND	DCC AMC	2.19	.01	24H	60	AIR	ADHESIVE
T-661 A/B AS 100/.5 BW BLUE EPOXY THERM COND	AMC	1.24	.03	25H	25	AIR	ADHESIVE
TAME 200 A/B AS 1/25 BW ACRYLIC BASE ADH	BFG	2.28	.03	24H	65	AIR	CUND ADHESIVE
TECKNIT 72-0002 SILVER FILLED SILICONE	TFC	.60	.01	24H	25	AIR	CUND ADHESIVE
TECKNIT 72-0002 SILVER FILLED SILICONE	TFC	.02	.00	30H	99	AIR	CUND ADHESIVE
TECKNIT 72-09110 CND EPOXIA/B AS 1/1 BW	TFC	1.61	.02	48H	121	E-C	2 SLICE TAPE
TERMA BOND THREE TON ADHESIVE AS 1/1 BW	CHR THE	1.44	.04	7D	25	AIR	ADHESIVE
TILE COTE 1202 A/B AS 1/1 BW BLACK EPOXY	DIV STA	1.80 5.78	.06 .08	1H 2H	25	AIR	STAKING CEND

SECTION 1 — ADHESIVES

MATERIAL	MFR CODE	WTML	%CVC	CURE TIME	CURE TEMP	ADHESIVE	APPLICATION
TRA-BOND 2101 EPOXY BIPAX KIT	TRA	1.71	.01	2H	60	AIR	ADHESIVE
TRA-BOND 2101T EPOXY BIPAX KIT THIXOTROPIC	TRA	1.35	.03	2H	25	AIR	ADHESIVE
TRA-BOND 2111 STAKING CPND EPOXY BIPAX KIT	TRA	2.95	.08	72H	22	AIR	STAKING CEND
TRA-BOND 21112 STAKING CPND EPOXY BIPAX KIT	TRA	1.45	.01	7D	25	AIR	STAKING CEND
TRA-BOND 2113 EPOXY BIPAX KIT	TRA	3.49	.15	24H	25	AIR	ADHESIVE
TRA-BOND 2114 CLEAR EPOXY BIPAX KIT/FULL SANDWICH	TRA	3.16	.62	72H	22	AIR	SANDING CPND
TRA-BOND 2115 EPOXY BIPAX KIT	TRA	1.31	.05	24H	25	AIR	ADHESIVE
TRA-BOND 2116 ALUM FILLED EPOXY BIPAX KIT	TRA	1.12	.05	72H	25	AIR	ADHESIVE
TRA-BOND 2122 BLACK EPOXY BIPAX KIT	TRA	1.12	.05	72H	25	AIR	ADHESIVE
TRA-BOND 2135D EPOXY BIPAX KIT	TRA	2.06	.10	3D	22	AIR	ADHESIVE
TRA-BOND 2143D POLYAMID-EPOXY BIPAX KIT	TRA	1.95	.09	72H	22	AIR	ADHESIVE
TRA-BOND 2151 THREE COMPOUND EPOXY BIPAX KIT	TRA	.95	.02	72H	22	AIR	ADHESIVE
TRA-BOND 2248 THIXOTROPIC HI-TEMP EPOXY BIPAX KIT	TRA	.72	.01	16H	25	AIR	ADHESIVE
TRA-CON ER12795/2193 EPOXY KIT	TRA	1.43	.04	24H	90	AIR	ADHESIVE
TRA-CON J1158/E-6 AS 50/6.25 BW EPOXY	TRA	16.34	1.13	16H	25	AIR	ADHESIVE
TRA-DUCT BA 2902 EPOXY KIT - SILVER FILLED	TRA	1.06	.03	2H	60	AIR	COND ADHESIVE
UNISET C-110 ONE COMPONENT SILVER FILLED EPOXY	AMC	1.31	.95	1H	150	AIR	COND ADHESIVE
UNISET C-429-2 SILVER FILLED THIXOTROPIC EPOXY	AMC	.44	.15	14	189	AIR	COND ADHESIVE
UNISET C-840 SILVER FILLED EPOXY ONE COMPONENT	AMC	.19	.01	90H	125	AIR	COND ADHESIVE
UNISET C-840 SILVER FILLED EPOXY ONE COMPONENT	AMC	.32	.00	1H	125	AIR	COND ADHESIVE
UNISET C-850 SILVER FILLED EPOXY ONE PART	AMC	.91	.00	1H	150	AIR	COND ADHESIVE
UNISET C-850-4 SILVER FILLED EPOXY ONE PART	AMC	.14	.00	1H	150	AIR	COND ADHESIVE
UNISET C-850-6 ONE COMPONENT SILVER FILLED EPOXY	AMC	.43	.01	1H	125	AIR	COND ADHESIVE
UNISET C-929-49 SILVER FILLED EPOXY	AMC	.60	.01	1H	145	AIR	COND ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	AMC	.31	.00	30M	150	AIR	COND ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	AMC	.06	.00	10M	170	AIR	COND ADHESIVE
UNISET C-940-4 ONE COMPONENT SILVER FILLED POLYIMIDE	AMC	.02	.00	1H	170	AIR	COND ADHESIVE
UNISET ME-845 THERMAL COND ADHESIVE OLIVE-GREEN	AMC	.08	.00	10M	270	AIR	COND ADHESIVE
UNISET ME-945 ONE COMPONENT POLYIMIDE/F	AMC	.30	.01	1H	125	AIR	THERMAL COND ADH
UNISET 906-25 SEMI-RIGID EPOXY	AMC	.26	.52	1H	170	AIR	LIQUID COND ADH
UNISET 909-60 ONE COMPONENT FILLED EPOXY	AMC	1.31	.31	30M	270	AIR	ADH-PUTTING
URALANE 5753 A/B AS 1/5 BW	FPI	1.31	.04	2H	93	AIR	LIQUID COND ADH
URALANE 5753 A/B/ALUMINA AS 1/5/ 3 BW	FPI	1.01	.02	14H	125	AIR	ADHESIVE
URALANE 8260 UV 66 SUMMERS LAES - DATA INCLUDES GLASS SUBSTRATE	FPI	.73	.03	14H	38	AIR	ADHESIVE
UV 69 OPTICAL CEMENT POLYMERIZED WITH SUN LAMP	SUM	1.74	.03	24H	55	AIR	OPT CEMENT
UVE 1003 EPOXY OPTICAL ADHESIVE/F 5 MIN UV EXP	SUM	3.03	.04	1H	150	AIR	OPT CEMENT
UVE 1003 EPOXY OPTICAL ADHESIVE/F 5 MIN UV EXP	GEC	1.09	.54	1H	150	AIR	OPT CEMENT
VC-3 NYLOCK SEALING CPND	GEC	1.91	.10	1H	150	AIR	NYLOCK SEALANT
VC-3 NYLOCK SEALING CPND	NYL	3.99	.62	1H	74	AIR	NYLOCK SEALANT
VERSILOK 101/ACCEL 11/P	HCC	7.47	.63	1H	121	AIR	ADHESIVE
VIBRA-TITE FASTENER F SET LIGGY 2 PART KIT	OAK	2.37	.14	24H	25	AIR	ADHESIVE
WILCO FAST SET LIGGY 2 PART KIT	WAI	1.80	.02	24H	25	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MRK CODE	XTHL	%CVCM	CURE TIME	CURE TEMP	AIDS	APPLICATION
X 3878-15-1 SILICONE PSA	CHO	2.35	1.01	304	25	AIR	ADHESIVE
X 7902 A/E AS 4/1 EW BLACK FLEXIBLE EPOXY	WSA	.48	.12	4H	125	AIR	ADHESIVE
X 7902 A/E AS 4/1 EW BLACK FLEXIBLE EPOXY	SA	.47	.11	4H	125	AIR	ADHESIVE
XA-3476 ONE COMPONENT GRAY EPOXY XC9-G710/H2 3561 AS 10/0/26 BW EPOXY	MM HYS	.28 .96	.04 .02	18H 24H	125 25	AIR	ADHESIVE
XB-4-3099 ONE PART SILICONE	DCC	1.39	.25	8H	69	AIR	ADHESIVE
AR-4-3138 ONE PART SILICONE	DCC	1.60	.24	7D	25	AIR	ADHESIVE
X1-2561 A/B AS 10/C-2 BW CLEAR SILICONE COATING	DCC	.19	.00	14D	25	AIR	COAT COAT
X3-6022/CAT 6060 AS 10/1 BW SILICONE/PRIMER DC92-02.3	DCC	.35	.00	1H	25	AIR	ADHESIVE
X3-6092 1/2B-1125 CNE PAINT WHITE SILICONE	DCC	.17	.01	24H	25	E-2	ADHESIVE
X3-6572 1/2B AS 10/1 B* CNE PAINT GRAY SILICONE	DCC	.31	.54	7D	80	AIR	ADHESIVE
Y-663 THERMOPOXY ALH ONE COMPONENT	STV	.40	.08	1H	177	AIR	ADHESIVE

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	MFN CODE	AMP	ACVCA	CURE TIME	CURE TEMP	ATMOS	APPLICATION
ALPHA WIRE 9853 BLACK TEFLON INSULATION	AWC	0.1	0.0	0.0	0.0	AIR	WIRE INSUL
ALPHA WIRE 5853 WHITE TEFLON INSULATION	AWC	0.1	0.0	0.0	0.0	AIR	WIRE INSUL
AMP HV SILICONE CABLE WITHOUT METAL	AMP	1.39	3.5	10.93	10.93	AIR	CABLE
AMP HV WIRE HV-1 SILICONE INSUL MIDDLE	AMP	1.44	3.5	10.93	10.93	AIR	CABLE
AMP HV WIRE SILASTIC 1410 SHRINK TUBING ONLY	AMP	1.39	3.5	10.93	10.93	AIR	CABLE
B 123 PHENOLIC CCIL VARNISH	WEC	2.23	3.7	8H	135	AIR	VARNISH
B 142-1 PHENOLIC CCIL VARNISH	WEC	0.34	0.4	8H	135	AIR	VARNISH
BC 500T SUEFLEX-SLIVERFLEX SLEEVING	BC1	0.95	0.95	0.2	0.2	AIR	INSUL
BELDEN BLUE ISOLATED 36-1 MAGNET WIRE BLUE/GREEN	BLD	0.90	0.90	0.2	0.2	AIR	WIRE COATING
BELDEN MAGNET WIRE 8082 MIL 583 C POLYTHENE/MALEZE INS	BLD	0.02	0.02	15.49	10.93	AIR	WIRE COATING
BELDEN PVC THERMOCOELASTIC WIRE INSULATION	BLD	0.05	0.05	24.03	8.72	AIR	WIRE WINDING
BELDEN 3524-1000 VINYL INSULATION INCLIMENT OF FIRE	BLD	0.03	0.03	BLD	BLD	AIR	CABLE INSUL
BELDEN 36T-1 MAGNET WIRE GREEN	BLD	0.24	0.24	BLD	BLD	AIR	LINE COATING
BEN-HAB PYRO-SLEEVE SUR COATED GLASS FIBER	BHM	0.92	0.92	BLD	BLD	AIR	SLEEVE
BLD PYRE 5636-L-G20 WHITE SILICONE WIRE INSULATION	BLW	1.28	1.28	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 BLACK PART	BLW	0.93	0.93	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 BLACK PART	BLW	0.77	0.77	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 ENTIRE CABLE	BLW	0.51	0.51	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 ENTIRE CABLE	BLW	0.93	0.93	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.42	0.42	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.56	0.56	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.04	0.04	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.94	0.94	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.74	0.74	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.11	0.11	BLW	BLW	AIR	WIRE INSUL
BLD PYR 5639-L-G22 OUTER JACKET	BLW	0.97	0.97	BLD	BLD	AIR	WIRE INSUL
CABLE BELDEN RG-58 C/U 8262 3000 HR VAC EXPOSURE	BLD	1.93	1.93	BLD	BLD	AIR	CABLE INSUL
CABLE BELDEN 8404 - 3000 HR VAC EXPOSURE	BLD	9.47	9.47	BLD	BLD	AIR	CABLE INSUL
CABLE COAX WHITE OUTERS INSUL MICRORODOT	MIR	0.00	0.00	MIR	MIR	AIR	CABLE INSUL
CABLE COCOU 2955 COAX WHITE OUTERS INSUL	MIS	0.02	0.02	MIS	MIS	AIR	CABLE INSUL
CABLE HI-VOLTAGE WHITE OUTERS SHEATH	DIS	0.41	0.41	DIS	DIS	AIR	CABLE INSUL
CABLE RG-316/J COAX TAN OUTERS INSUL	DUP	0.12	0.12	DUP	DUP	AIR	CABLE INSUL
CABLE 1/2" 0.61 BYCKONITE DUPONT HYPAOLON	DIS	4.52	4.52	DIS	DIS	AIR	CABLE INSUL
CABLE 2024 INSULATION BLACK/WHITE SILICONE	MIS	1.69	1.69	MIS	MIS	AIR	CABLE INSUL
CABLE 2219930J CR ALTON BLACK/WHITE TEFLON INSULATION	MIS	0.93	0.93	MIS	MIS	AIR	CABLE INSUL
CABLE 24799408 KALTON SHIELDED POLYIMIDE	CTD	0.44	0.44	CTD	CTD	AIR	CABLE INSUL
CABLE 2619620 CRESJ COAX RED OUTER INSUL	MIS	0.00	0.00	MIS	MIS	AIR	CABLE INSUL
CHEMELDUR TEFONITE SHRINK TUBING	CHE	0.69	0.69	CHE	CHE	AIR	SLEEVING
CHO-SHREINK THERMO SILEX CONDIN/SUR HEAT GUN SHRINK	CHO	0.70	0.70	CHO	CHO	AIR	SLEEVING
DK-15-02 DIA-ROUTE EPOXY	CIC	0.24	0.24	CIC	CIC	AIR	SLEEVING
DURADY/TPE LINE INSULATION RED/BLK NPC	HYS	0.49	0.49	HYS	HYS	AIR	SLEEVING
DURADY/TPE LINE INSULATION YELLOW SPC	HYS	0.96	0.96	HYS	HYS	AIR	SLEEVING
END CAP D100-16 SHRINKABLE IRRAD BLACK POLYOLEFIN	RCC	0.92	0.92	RCC	RCC	AIR	SLEEVING
EXPANDO SLEEVING HE RED HALAR	BHM	0.29	0.29	BHM	BHM	AIR	SLEEVING
EXPANDO SLEEVING BL WHITE HALAR	BHM	0.27	0.27	BHM	BHM	AIR	SLEEVING
EXPANDO SLEEVING PT BLACK POLYESTER	BHM	0.00	0.00	BHM	BHM	AIR	SLEEVING
FEP TEFION 30KV LINE INSULATION POLYESTER FILM/NO ADH	MIS	0.21	0.21	MIS	MIS	AIR	SLEEVING
FIBERMAT 1 TYPE 2540 POLYESTER FILM/NO ADH	MIS	0.15	0.15	MIS	MIS	AIR	SLEEVING
FIBERMAT 1 TYPE 2540 POLYESTER FILM/NO ADH	MIS	0.14	0.14	MIS	MIS	AIR	SLEEVING

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	FR CODE	#ML	ACVCA	CURE TIME	CURE ATMOS	APPLICATION
FIBERFAT 1V						INSULATION
FIT 221 IRRADIATED POLYOLEFIN SHRINK TUBING NEUTRAL - HEAT GUN	AEN	1-68	.04			SURFACE TUBING
FIT 350 KYNAR SHRINK TUBING BLACK POLYOLEFIN SHRINK TUBING	AEN	1-42	.68			SURFACE TUBING
FLEXITE PO 135 CLEAR POLYOLEFIN SHEATH TUBING	NAJ	1-59	.99	5H	121	SURFACE TUBING
FLEXITITE TGL SILICONE RUBBER TAPE NO ADH	MAX	7-73	.96	.31	121	TAPE
FLEXITITE TGL SILICONE TAPE NO ADHESIVE	EAR	9-95	.34	20H	150	TAPE
FLUOROCARBON WIRE INSULATION BLACK	BAV	1-31	.12	20H	149	TABLE
PP 301 SHRINK TUBING NEUTRAL	ECC	1-99	.03			WIRE INSUL
GORE-TEX MICROWAVE CABLE INNER INSULATION WHITE	LLG	1-53	.24			SURFACE TUBING
GORE-TEX MICROWAVE CABLE OUTER INSULATION PURPLE	LLG	1-02	.20			CABLE INSUL
GORE-TEX PTFE/CN CABLE INSULATION 3 PLY	LLG	1-04	.09			CABLE INSUL
HAVEG FR-1 STYLE 3239 WHITE SILICONE WIRE INSUL	DAY	1-36	.38			SILICONE INSUL
HAVEG FR-1 STYLE 3239 WHITE SILICONE WIRE INSUL	DAY	1-86	.43	22H	100	ALK
HELLI-TUBE HT 1/8-N	NEW	3-51	.02			CABLE WRAP
HIGH TEMP HT 221 MAGNET WIRE COATING	ETR	3-53	.41			WIRE COATING
HOSE SAE 100R5 BLACK RUBBER	PT	3-13	.41			HOSE
HT SHRINK ST 9100 PVC/OLEFIN SHRINK PEES SHRUNK	ST	2-50	.84			SHRINK TUBING
ISONEL 200 MAGNET WIRE COATING BROWN 180C USE 12MIL	SAC	1-61	.00			SHRINK TUBING
KAPTON T400-1/20 BEAN-REX	BEA	1-35	.00			WIRE COATING
KAPTON T-TEFLON FEE COATED 1473-1/24 BRAND-REX	BRY	1-18	.00			WIRE COATING
KY NAR SHRINK TUBING 123053/8 HEAT GUN SHRINK	BRY	1-51	.10			WIRE INSUL
KY NAR SHRINKABLE SLEEVING SLEEVE BLUE /WHITE INSERTS	RCC	1-52	.09			SURFACE TUBING
KY NAR SOLDER SLEEVE WITH POLYETHYLENE RINGS	RCC	1-66	.04			SURFACE TUBING
KY NAR SOLDER SLEEVE WITH POLYETHYLENE SLEEVES	RCC	1-37	.07			SURFACE TUBING
KY NAR WIRE INSULATION - RED	ECC	1-44	.07			SURFACE TUBING
MAGNET WIRE COATING TFE TEFLON/DURAD	EIC	1-07	.00			WIRE INSUL
MAGNET WIRE HEAVY AL POLYIMIDE	HAY	1-29	.00			WIRE COATING
MAGNET WIRE HEAVY AL POLYIMIDE	HAY	1-53	.00			WIRE COATING
MICRODOT CONNECTOR RUBBER BOOT 7502 BLACK	PDC	1-89	.08			WIRE COATING
MICROTHIN TEFLON SLEEVING 20 GAUGE	MWS	1-78	.01			WIRE COATING
MIL-ENE C WIRE INSULATION - YELLOW {COATING ONLY}	SHA	1-62	.00			WIRE COATING
MIL-ENE C WIRE INSULATION - YELLOW {COATING ONLY}	LLG	1-92	.00			WIRE COATING
MULTIFILLAR MAGNET WIRE PYRE ML B-4-30-28-0-5 CALC %	LLG	1-78	.13	4H	150	ALK
NORFLEX N221 POLYOLEFIN SHRINK TUBING PRE-SHRUNK	MWS	1-98	.03			SURFACE TUBING
NYLAFLOW 413 HOSE SLEEVING OUTER SHEATH ONLY	EPC	1-78	.13			SURFACE TUBING
NYLZE MAGNET WIRE COATING RED (COATING ONLY)	PDC	1-43	.00			WIRE COATING
NYLZE MAGNET WIRE INSULATION GREEN (COATING ONLY)	PDC	1-34	.23			WIRE COATING
PENNNTUBE II SO 3-7104AX/CTEFON TUBING	PDC	1-17	.13			WIRE COATING
PENNNTUBE V POLYOLEFIN SHRINK TUBE CLEAR	FPC	1-01	.00			WIRE COATING
PENNNTUBE VILB NEGCFENE SHRINK TUBING BLACK	FPC	4-45	.00			SURFACE TUBING
POLY-FLO TUBING OFF - POLYETHYLENE	IMP	8-42	.13			SURFACE TUBING
POLYURETHANE TUBING 8030-0060	STE	4-46	.15			TUBING
RAYCHEM COAX 2026A-1211-9 ORANGE INNER INSUL	RCC	1-77	.22			WIRE INSUL
RAYCHEM COAX 2026A-1211-9 WHITE OUTER INSUL	RCC	1-72	.16			WIRE INSUL
RAYCHEM KYNAR PRE-SHRUNK	RCC	1-28	.04			SURFACE TUBING
RAYCHEM KYNAR PRE-SHRUNK	RCC	1-24	.13			SURFACE TUBING

SECTION 2 — CABLE INSULATION SHRINK TUBING

MATERIAL	IFER CODE	ATM	ACVCM	CURE TIME	CURE TEMP	ATMA	4/P APPLICATION
RAYCHEM POLYALKENE WIRE INSULATION TYPE 44	RCC	1.73	.01				WHITE INSUL
RAYCHEM POLYALKENE WIRE RADIATION CROSSLINKED	RCC	.75	.03				WHITE INSUL
RAYCHEM POLYALKENE WIRE 88B011-20-Y WHITE	RCC	.34	.07				WHITE INSUL
RAYCHEM POLYALKENE WIRE 88B011-20-Y GRAY	RCC	.15	.01				WHITE INSUL
RAYCHEM POLYOLEFIN MT 13-4 SHRINK TUBING PRESHRUNK	RCC	.14	.00				SURFACE TUBING
RAYCHEM SPEC 44 WIRE INSUL LOT JU20197902	RCC	.82	.21	104	71	AIR	
RAYCHEM SPEC 44 WIRE INSUL LOT JU408297704 INNER	RCC	.46	.03				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT JU4084297704 OUTER	RCC	.71	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT JU604077905 INNER	RCC	.18	.02				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT JU604077905 OUTER	RCC	.64	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1102067911 INNER	RCC	.15	.02				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1102067911 OUTER	RCC	.66	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1105187913 INNER	RCC	.68	.03				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1105187913 OUTER	RCC	.22	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT PJ0401127801	RCC	.67	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT PJ051107814	RCC	.65	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT PJ0602278014	RCC	.26	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL WHITE LOT PJU0503157909	RCC	.29	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL WHITE LOT PJU0503157909	RCC	1.49	.08				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL WHITE LOT PJ61212915	RCC	.19	.05				WHITE INSUL
RAYCHEM SPEC 44/0411-3 SPACE GR WHITE LOT PJ61212915	RCC	.77	.03				WHITE INSUL
RAYCHEM SPEC 44/0411-3 SPACE GR OUTER INS WHITE	RCC	.26	.02				WHITE INSUL
RAYCHEM SPEC 44/041-20X SP GR LINS W/O BENZOPHENONE	RCC	.95	.03				WHITE INSUL
RAYCHEM SPEC 44/041-24-9 WHITE WIRE INSUL	RCC	.13	.01				WHITE INSUL
RAYCHEM SPEC 44/041-24-9 WHITE OUTER INS WHITE	RCC	.73	.05				WHITE INSUL
RAYCHEM SPEC 44/0411 GEN PURP GRADE WIRE LNS WHITE	RCC	.46	.02				WHITE INSUL
RAYCHEM SPEC 44/0411-3 SPACE GR WHITE LOT PJ61212915	RCC	.15	.04				WHITE INSUL
RAYCHEM SPEC 44/0411-3 SPACE GR OUTER INS WHITE	RCC	.22	.00				WHITE INSUL
RAYCHEM SPEC 44/041-20X SP GR LINS W/O BENZOPHENONE	RCC	.38	.00				WHITE INSUL
RAYCHEM SPEC 44/041-24-9 WHITE WIRE INSUL	RCC	.80	.00				WHITE INSUL
RAYCHEM SPEC 44/041-24-9 COLOR CODE INSUL	RCC	.95	.00				SURFACE TUBING
RAYCHEM SPEC 44/0411-3 SPACE GR WHITE OUTER SHEATH	RCC	.73	.00				WHITE INSUL
RAYCHEM SPEC 44/0411-3 SPACE GR WHITE OUTER INSUL	RCC	.49	.00				SHRINK TUBING
RAYCHEM SPEC 25/040811-24-9 PJ04032682 02 BLUE/WHITE	RCC	.37	.00				CABLE INSUL
RAYCHEM SPEC 88 FOIL X INSULATION	RCC	.95	.00				INDIVIDUAL LN
RAYCIN P CABLE 41262 1332 INSULATION GRAY	RCC	.73	.00				WHITE INSUL
RAYCIN GLO 125 WHITE POLYOLEFIN SHRINK TUBING	RCC	.49	.00				WHITE INSUL
RAYCIN GLO 125 WHITE POLYOLEFIN SHRINK TUBING ONLY	TIN	.01	.00				WHITE INSUL
RT 1146 BLACK VITON SLEEVES - NYLON	RCC	.37	.06				SHRINK TUBING
SE 9025 SILICONE WIRE INSULATION BLACK	GEC	3.32	.06				SURFACE TUBING
SE 9025 SILICONE WIRE INSULATION BLACK	GEC	3.38	.58				SURFACE TUBING
SE 9025 SILICONE WIRE INSULATION BLACK	GEC	3.42	.03				SURFACE TUBING
SE 9045 SILICONE WIRE INSULATION - OUTER	GEC	1.37	.01				SHRINK TUBING
SE 9045 SILICONE WIRE INSULATION	HAY	4.12	.01				SURFACE TUBING
SHRINK TUBING BLACK FROM CABLE BRAND REX	BRY	2.62	.22				SURFACE TUBING
SHRINK TUBING GREEN MAX SHRINK-HEAT GUN	AMI	1.98	.29				SURFACE TUBING
SHRINK TUBING WHITE FROM CABLE PIKELLI	FIM	1.70	.34				SURFACE TUBING
SILASTIC 1410 SHRINKABLE TUBING - PRESHRUNK	DCC	1.56	.15				SURFACE TUBING
SILICONE WIRE INSULATION	TDI	1.25	.28				SURFACE TUBING
SOLDERFREE MAGNET WIRE RED	PDC	1.75	.14				SURFACE TUBING
SPACE POLYOLEFIN TYPE 702 BLACK	RCC	.53	.05				CABLE WRAP
SPIRAL NYLON CABLE W/4 P50013	AMP	2.03	.05				CABLE WRAP
SR 290 SILICONE WIRE 18/2 AND SR 98)	GEC	6.00	.26				COATING
STW 0474 WHITE SILICONE WIRE INSUL	STC	4.16	.76				COATING
							INSULATION

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	MFN CODE	STL CODE	%CVCH	CURE TIME	CURE TEMP	ATMOS	APPLICATION
SURLYN A WHITE SILICONE WIRE INSUL	STW 0474	DUP	.28	.03	AIR	INSULATION	
SURLYN A WIRE INSULATION IN SHEET FORM	SURLYN A	DUP	.55	.08	AIR	WIRE INSUL.	
SYNTHITE BC 307 VANISHING FIT 4 JO	SYNTHITE BC	JCD	3.70	.69	110	AIR	INSULATION
TEFLON FEP SHINK TUBING FIT 4 JO	TEFLON INSUL	AWC	.00	.00	AIR	SHRINK COATING	
TEFLON PFA WIRE SLEEVING TE-9704 SODIUM ETCHED	TEFLON PFA	BRX	.00	.00	AIR	SHRINK TUBING	
TEFLON PFA WIRE SLEEVING TE-9704 UNFICHED	TEFLON PFA	DUP	.00	.00	AIR	SHRINK TUBING	
TEKFIT GPO 135 BLACK POLYOLEFIN SHRINK TUBING	TEKFIT GPO	RTC	.58	.05	AIR	SHRINK TUBING	
TEKSILITE 4318L-1 HIGH VOLTAGE WIRE INSUL MCD TFE	TEKSILITE	CTD	1.13	.28	AIR	SHRINK TUBING	
TFE WIRE INSULATION	TFE WIRE INSULATION	MSY	.04	.00	AIR	WIRE INSUL.	
TERMATICS 145-20-1922 WHITE WIRE INSUL	TERMATICS	THI	.04	.00	AIR	WIRE INSUL.	
TERMATICS 145-20-1922 BLACK WIRE INSUL	TERMATICS	THI	.00	.00	AIR	WIRE INSUL.	
TERMATICS 63574AA OUTER WHITE LACQUER IMPREG NYLON	TERMATICS	TWC	1.46	.27	AIR	WIRE INSUL.	
TERMAX TEFILON IMPREG FIBERGLASS WIRE INSULATION	TERMAX TEFILON	TWC	1.27	.01	AIR	WIRE INSUL.	
TERMAX TEFILON WIRE INSULATION TYPE E	TERMAX TEFILON	BAL	.02	.02	AIR	WIRE INSUL.	
TERMELEC G 2735 CCIL COATING	TERMELEC				AIR	COIL COATING	
TERMOPHIT CONNECTION BOOT 214A332-3 HEAT GUN SHRINK	TERMOPHIT	RCC	.91	.32	AIR	SHRINK TUBING	
TERMOPHIT CRN CLEAR	TERMOPHIT	RCC	1.60	.54	225	AIR	SHRINK TUBING
TERMOPHIT CRN WHITE	TERMOPHIT	RCC	1.66	.88	225	AIR	SHRINK TUBING
TERMOPHIT KYNAR CLEAR	TERMOPHIT	RCC	1.14	.05	AIR	SHRINK TUBING	
TERMOPHIT KYNAR VITON - BLACK HEAT GUN SHRINK	TERMOPHIT	RCC	1.31	.07	AIR	SHRINK TUBING	
TERMOPHIT RNP 100 CLEAR - SURFACE ETCHED	TERMOPHIT	RCC	1.02	.20	AIR	SHRINK TUBING	
TERMOPHIT RNP 100 TY1 BLACK SHRINK TUBING LOT 17595	TERMOPHIT	RCC	1.59	.30	AIR	SHRINK TUBING	
TERMOPHIT RT 102 BLACK POLYOLEFIN HEAT GUN SHRINK	TERMOPHIT	RCC	1.72	.29	AIR	SHRINK TUBING	
TERMOPHIT RT 216 BLACK KYNAR/VITON HEAT GUN SHRINK	TERMOPHIT	RCC	1.24	.24	AIR	SHRINK TUBING	
TERMOPHIT RT 301 BLACK KYNAR SHRINK TUBING NATURAL	TERMOPHIT	RCC	1.68	.28	AIR	SHRINK TUBING	
TERMOPHIT RT 879 PCLYOLEFIN CLEAR PRESSHUNK	TERMOPHIT	RCC	1.15	.15	AIR	SHRINK TUBING	
TERMOPHIT RT 879 PCLYOLEFIN RED PRESSHUNK	TERMOPHIT	RCC	1.16	.19	AIR	SHRINK TUBING	
TERMOPHIT RT 876 PCLYOLEFIN WHITE HEAT GUN SHRINK	TERMOPHIT	RCC	1.77	.30	AIR	SHRINK TUBING	
TERMOPHIT RT 876 FRESHUNK	TERMOPHIT	RCC	.67	.10	AIR	SHRINK TUBING	
TERMOPHIT SCL - ACT SHRUNK	TERMOPHIT	RCC	.68	.19	AIR	SHRINK TUBING	
TERMOPHIT SCL - PHISHRUNK	TERMOPHIT	RCC	.61	.14	AIR	SHRINK TUBING	
TERMOPHIT SCL - SPECIAL AS-8SCL-NO2-CL3512	TERMOPHIT	RCC	.47	.20	AIR	SHRINK TUBING	
TERMOPHIT SCL BLACK - HEAT GUN SHRINK	TERMOPHIT	RCC	.69	.25	AIR	SHRINK TUBING	
TERMOPHIT SCL BRCKN	TERMOPHIT	RCC	.76	.54	AIR	SHRINK TUBING	
TERMOPHIT SCL WHITE	TERMOPHIT	RCC	.63	.26	AIR	SHRINK TUBING	
TERMOPHIT SCL GRAY	TERMOPHIT	RCC	.83	.54	AIR	SHRINK TUBING	
TERMOPHIT SCL GRAY SHRINK TUBING LOT 11491	TERMOPHIT	RCC	.74	.28	AIR	SHRINK TUBING	
TERMOPHIT SCL WHITE	TERMOPHIT	RCC	.82	.51	AIR	SHRINK TUBING	
TERMOPHIT SCL WHITE	TERMOPHIT	RCC	.63	.25	AIR	SHRINK TUBING	
TERMOPHIT TFE & TEFLON PRE-SHRUNK SLEEVE	TERMOPHIT	RCC	.52	.24	AIR	SHRINK TUBING	
TERMOPHLEX HYGRADE 1200 FIBERGLASS SLEEVE	TERMOPHLEX	RCC	.06	.01	AIR	SHRINK SLEEVE	
TUFCON 50 MIL-ENE POLYESTER RIBBON CABLE	TUFCON	WLG	.36	.21	AIR	PLEXI-WIRING	
TUFCON 50 MIL-ENE POLYESTER RIBBON CABLE	TUFCON	WLG	.36	.24	90	E-J	

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	MFR CODE	#TML	%CVM	CURE TIME	CURE TIME	ATMOS	APPLICATION
TYGON TUBING FOR POLYURETHANE COATING	NPC	32.91	14.96				TUBE AS COATING
T-4 MAGNET WIRE GLASS TAPE/VOLAN A FINISH/NO ADH	MWS	.66	.08				WIRE COATING
UNIGLASS 1542 FIBERGLASS TAPE/VOLAN A FINISH/NO ADH	UNI	.03	.01				INSULATION
VARGLAS NO. 1601 FRAY SLEEVING TYPE HO	VFA	.53	.11				INSUL SLEEVE
VARGLAS S-1601 TYPE H FIBERGLAS SLEEVE	VFA	.01	.00				INSUL SLEEVE
VARGLAS SPEC A307 CLASS/SILICONE WIRE INSUL TA N	VFX	.69	.07				WIRE INSUL
VITON TUBING C-641-47	DOU	.13	.00				TUBING
WIRE INSULATION YELLOW/BROWN	LDD	.68	.00				WIRE INSUL
WIRE INSULATION GREEN COATED KAPTON MIL-W-81381/7	GEC	1.97	.00				WIRE INSUL
WIRE INSULATION GREEN FLUOROCARBON POLYIMIDE/TFE	MIS	.24	.03				WIRE INSUL
WIRE INSULATION ORANGE MIL-W-22759/18-20	ICO	.07	.01				WIRE INSUL
WIRE INSULATION RED FLUOROCARBON POLYIMIDE/TFE	MIG	.19	.01				WIRE INSUL
WIRE INSULATION WHITE COATED KAPTON MIL-W-81381/7	GEC	1.02	.05				WIRE INSUL
WIRE INSULATION WHITE FLUOROCARBON FUJAO 80	MIS	.03	.00				WIRE INSUL
WIRE INSULATION WHITE MIL-W-22759/18-20	ICO	.10	.01				WIRE INSUL
Y-210 VARNISH INSULATION	STV	3.60	.22				VARNISH

SECTION 3 -- CONFORMAL COATING

MATERIAL	MFR CODE	#ML	ACVCM	CURE TIME	ATMOS	APPLICATION
ACRYLOID AU608/DESNOUD L2219A/T-12 CLEAR COATING AMLGUARD CORROSION PROTECTIVE COATING/P APCO 1260 A/B AS 1/1 BW	BOH NDC APP	12.70 14.01 6.46	.03 .12 .02	14D 24H 24H	AIR AIR AIR	COATING COATING COAT
APCO 1266 A/B AS 1/1 BN POLYURETHANE CYCLED APCO 1266 A/B AS 1/1 BW POLYURETHANE CYCLED	APP APP	18.35 17.06	.02 .04	90M 80M	AIR AIR	CONF COAT PAINT
ARALDITE 502/951/PC-1244 EPOXY	CIB	2.00	.01	24H	E-0	COAT
ARMSTRONG C-7/ACT 1/CA BOSIL 1/CA BOSIL/NAZ-LAR ER ENAMEL BETACOTE 91-18 A/B AS 3/1 BW	APC APC ESA	1.68 2.13 7.10	.01 .01 .00	6H 3H 16H	AIR AIR AIR	COATING COATING COAT
BLUE COATING LI 001057REVA FLEXIBLE MOD EPOXY	NCR	.41	.04	1H	12.5	COATING
CARE #2 ANTI STICK/MOLD RELEASE AEROSOL/F CHEMGLAZE Z001 CLEAR POLYURETHANE FLEXIBLE CHEMGLAZE Z201 CLEAR POLYURETHANE FLEXIBLE CHEMGLAZE Z301 CLEAR POLYURETHANE FLEXIBLE LOT TBA CHEMGLAZE Z304 CLEAR POLYURETHANE HIGH FLEX LOT TAA CHEMGLAZE Z304 CLEAR POLYURETHANE HIGH FLEX LOT TAA CHEMGLAZE Z2004 CLEAR POLYURETHANE HIGHLY FLEXIBLE CHEMGLAZE Z2053 CLEAR POLYURETHANE HIGHLY FLEXIBLE	CRE HCC HCC HCC HCC HCC HCC HCC	16.78 1.42 1.18 1.50 1.51 1.50 1.20 1.22	.98 .01 .02 .01 .01 .01 .01 .01	3H 14D 14D 14D 14D 14D 14D 14D	AIR AIR AIR AIR AIR AIR AIR AIR	RELEASE COAT COAT COAT COAT COAT COAT COAT
CONATHANE CE 1155 A/B AS 10/7 BW	CON	1.60	.04	30M	AIR	COAT
CONATHANE CE 1155/CELLOSOLVE ACETATE MULTICURE	CON	.81	.05	3H	AIR	COAT
CONATHANE CE 1164 MIL 1 46058C TYPE UR 2 COATS/FOIL CONATHANE CE 1164 MIL 1 46058C TYPE UR 2 COATS/FOIL	CON CON	7.95 CON	.09 .07	15H 3H	AIR AIR	COAT COAT
CONATHANE BN 1510/CONACURE AH18 AS 5/2 BW CRANOLIN PLASTIK SPRAY DRY 10M/COAT/ROCK TEMP CRANOLIN PLASTIK SPRAY DRY 10M/COAT/ROCK TEMP	CON CON CLI	1.09 1.84 13.93	.09 .09 .09	14D 14D 16H	AIR AIR AIR	COAT COAT COAT
C15-067 A/B AS 100/120 BW	HYS	1.94	.01	12H	AIR	COATING
DC 0-6-005 ONE PART SILICONE DC QCP-3-6500 ONE PART SILICONE STRIPPED IN VAC	DCC DCC DCC DCC DCC DCC DCC DCC DCC DCC	1.43 1.84 13.96 13.67 6.13 1.52 1.34 1.54 1.54	.56 .58 2.35 2.65 5.54 6.1 2.4H 6.3	7D 7D 18H 7D 25H 25H 24H 25H 25H	AIR AIR AIR AIR AIR AIR AIR AIR AIR	CONF COAT CONF COAT CONF COAT RELEASE AGENT RELEASE AGENT CONF COAT CONF COAT COATING
DC 1107/T-12 AS 10GM/5 DROPS SILICONE FLUID DC 3-6550 KTV DISPERSION ONE PART CLEAR	DCC DCC DCC DCC DCC DCC	1.02 1.02 1.02 1.02 1.02 1.02	.06 .06 .06 .06 .06 .06	24H 24H 24H 24H 24H 24H	AIR AIR AIR AIR AIR AIR	COATING COATING COATING COATING COATING COATING
DC 31440 DC 31440	DCC DCC	.16 .16	.06 .06	24H 7D	E-0 AIR	COATING COATING
DC 6-1104 UNFILLED W/LUMINESCER 174 DC 6-1104/HEK/XYLENE DC 6-1109 - UNFILLED SILICONE DC 806A SILICONE IN XYLENE/TOLUENE/F	GSC GSC GSC GSC	.30 .28 .19 .90	.07 .04 .01 .11	7D 25 25 1H	AIR AIR AIR AIR	CONF COAT CONF COAT CONF COAT COATING

SECTION 3 -- CONFORMAL COATING

MATERIAL	MFR CODE	%ML	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
DE 806 A SILICONE IN XYLENE/TOLUENE/F DE 92-024 SILICONE OVER PRIMER DC 1240 DENFLEX 162 A/B AS 1/1 BW FLEXIBLE EPOXY DER 332LC/VERSAMID 140 AS 35/30 BW EPOXY COATING DK-4 DRI-KOTE SPECIA POWDER COATING DURAFILM 300 SERIES ENAMEL	DCC DCC DNB DNB HYS ADP	2.14 2.13 4.91 4.91 HYS .33	.14 .84 .95 .95 .01 .01	7D SD 3H 3H 20H 20H	25 66 71 24H 149 149	AIR COAT COAT COAT COATING COATING	COATING COAT COAT COATING COATING COATING
EA 934 A/E AS 100/33 BW GRAY EPOXY EA 934 A/E AS 100/33 BW GRAY EPOXY EC 1981 FLEXIBLE COATING - CLEAR ECOCOAT CC-2 CONDUCTIVE SILVER COATING/F ECOCOAT CC-4 SILVER FILLED ELASTOMER ECOCOAT EP-3 A/E AS 2/1 BW EPOXY COATING	HYS MM EMC EMC EMC EMC	.79 1.07 1.37 2.15 2.15 .03	.01 .01 .08 .08 2.1 2.1	7D SD 30M 30M 7D 24H	60 25 48H 150 75 95	AIR COAT COAT COATING COATING COAT	COATING COAT COAT COATING COATING COAT
ECOCOAT TF-11 A/B AS 1/1 BW AMBER COATING ECOCOAT 582 A/B AS 100/7 BW THERMAL COATING EP 2200 BLACK SCALAR ABSORBENT COATING/F EP 120N 123/CAT 952 AS 10/0.3 BW EPOXY EPOT-TEK H73 A/B AS 10/0.3 BW EPOXY EPOCAST 26-11 EPOXY UNDER COATING EPON 815/V 140 AS 50/50 BW EPOXY EPON 815/V-140 AS 50/50 BW EPOXY	EMC EMC PP1 PP1 PPK PP1 SUL SHL	1.01 3.56 1.99 1.63 1.43 1.09 1.07 1.84	.01 .02 .74 .93 .01 .01 .10 .08	30M 24H 24H 24H 20H 1H 1H 16H	25 25 25 25 109 177 25 25	AIR COAT THERM CONTROL ADHESIVE COATING COATING COAT COAT	COATING COAT THERM CONTROL ADHESIVE COATING COATING COAT COAT
EPON 815/VERSAMID 150 AS 60/40 BW EPOXY EPON 828/CAT 951 AS 10/1 BW EPOXY EPON 828/VERSAMID 140 AS 50/50 BW EPOXY EPON 828/VERSAMIC 140 AS 50/50 BW EPOXY EPON 828/VERSAMID 140 AS 70/30 BW EPOXY EPON 828/VERSAMID 140 AS 70/30 BW EPOXY EPON 828/VERSAMIC 140/SR 8/2/DETA/MEK EPON 828/VERSAMIC 140/SR 8/2/DTA/TOLUENE EPON 828/VERSAMIC 140/SR 8/2/DTA/TOLUENE EPON 828/VERSAMIC 140/SR 8/2/DTA/TOLUENE EPOXY ANTI-TRACK COATING EPOXYLITE 9653 POLYURETHANE E-194-8 CQATS EP 73/DACRON KNIT/ER 127 PRIMER CN FOIL	SHL SHL SHL SHL SHL SHL SHL SHL SHL SHL WEC WEC	1.29 1.27 1.91 1.01 2.24 2.32 4.69 1.35 1.87 .13 2.01	.06 24H 24H 30D 24H 0.0 1H 0.0 8H 1H .01 .61	24H 24H 24H 30D 24H 0.0 25 25 25 25 25 25	25 25 25 25 25 25 25 25 25 25 100 100	AIR COATING COATING COAT COATING COAT COAT COAT COAT COAT AIR COAT	COATING COATING COATING COATING COATING COATING COATING COATING COATING COATING COAT COAT
PPC 461 FLUOROCARBON/VINYL COPOLYMER FILM PPC 461 FLUOROCARBON/VINYL COPOLYMER FILM HL 155-55-1/2 AS 4€/1 BW ACRYLIC COATING	FPL FPL HYD	.38 .24 6.32	.01 .01 .00	24H 24H 48H	25 60 25	AIR COATING COAT	COATING COATING COAT

SECTION 3 -- CONFORMAL COATING

MATERIAL	MR CODE	STD.	XCVCA	CURE TIME	CURE TEMP	ATMOS	APPLICATION
HL-34-237 A/E/B/C AS 100/5/1 FLEXIBLE ACRYLIC COATING	HYD	6.79	.06	7D	25	AIR	COAT COAT
HUMISEAL X-381V A/E AS 1/1 BW POLYURETHANE	CTC	21.66	.89	2H	75	AIR	COAT COAT
HUMISEAL 1A20 POLYURETHANE	CTC	2.58	.02	1H	25	AIR	COAT COAT
HUMISEAL 1A27 AEROSOL/F	CTC	8.66	.24	7D	25	AIR	COAT COAT
HUMISEAL 1A33 POLYURETHANE	CTC	8.54	.24	10D	25	AIR	COAT COAT
HUMISEAL 1A33 POLYURETHANE	CTC	4.98	.00	24H	65	AIR	COAT COAT
HUMISEAL 1B12 ACRYLIC	CTC	1.78	.00	24H	80	AIR	COAT COAT
HUMISEAL 1B12 ON SCREEN	CTC	6.89	.18	30M	77	AIR	COAT COAT
HUMISEAL 1B15 ACRYLIC	CTC	9.38	.02	24H	25	AIR	COAT COAT
HUMISEAL 1B20 ACRYLIC	CTC	14.04	.06	4H	75	AIR	COAT COAT
HUMISEAL 1B31 ACRYLIC FREE FILM	CTC	3.80	.02	24H	66	AIR	COAT COAT
HUMISEAL 1B31 ACRYLIC ON FOIL	CTC	9.74	.02	10H	66	AIR	COAT COAT
HUMISEAL 1B31/AYLENE AS 3/2 BV ACRYLIC 1 HR 25C/COAT	CTC	11.81	.07	30M	80	AIR	COAT COAT
HUMISEAL 2A52LU A/E AS 1/1 BV EPOXY	CTC	3.27	.14	30M	25	AIR	COAT COAT
HUMISEAL 2A53 A/E AS 1/1 BV MOD EPOXY COATING	CTC	1.94	.03	24H	71	AIR	COAT COAT
HUMISEAL 2A56 A/E AS 1/1 BV POLYURETHANE	CTC	12.73	.16	16H	85	AIR	COAT COAT
HJMISEAL 2A72 A/E AS 1/1 BV FLUORESCENT POLYURETHANE	CTC	8.63	.02	40D	25	AIR	COAT COAT
HJMISEAL 2A72 A/E AS 1/1 BV FLUORESCENT POLYURETHANE	CTC	9.38	.02	8H	66	E-9	COAT COAT
HJMISEAL 2B13LU 2B13 AS 100/2 BW EPOXY	CTC	14.80	.47	24H	66	E-9	COAT COAT
IC-2 POLYURETHANE COATING	EMC	.59	.08	16H	60	AIR	COAT COAT
ISOCHEMREZ 1251LV/22H AS 25/2 BW THERM COND EPOXY	IBC	2.42	.09	48H	50	E-5	COATING
ISOCHEM R-65 ACRYLIC COATING SYSTEM/F	BEB	5.52	.02	24H	50	AIR	COATING
ISOCHEM ED 129/ED 100 AS 1/1 BW	ELB	5.82	.02	16H	55	AIR	COAT COAT
ISOCHEM POLYESTER/PCLINIMIDE COATING	SCH	4.44	.03	2H	40	AIR	COAT COAT
KOIKI PYROFILS PVC/7C KED RESISTOR COATING #11-129092	WEI	1.14	.16	16H	75	AIR	COATING
LACQUER TYPE LIQUID ACRYLIC FS N 8010-00-552487	AMA	4.35	.23	10H	25	AIR	LACQUER
LEXCOTE G-3183/G3174 AS 100/5.7 BW CLEAR COATING	BAL	17.65	.39	10H	25	AIR	COAT COAT
ME 5146A/B-97 AS 100/1-6 BW CLEAR BLUE EPOXY/F	AMC	9.33	.15	30M	60	AIR	COATING
MOBIL 173 COATED VITRIFIED KAPTON	KST	1.85	.02	2H	80	AIR	THEMAL BLANKET
MOBIL 173 COATED VITRIFIED KAPTON	KST	1.05	.04	24H	50	AIR	THEMAL BLANKET
MT 114 POLYACRIC CATING	NFI	3.69	.07	1H	75	AIR	COAT COAT
OF 100 GLASS RESIN 40% BW IN ETHANOL/F	OII	.25	.07	1H	175	AIR	COAT COAT
OF 650 GLASS RESIN 40% BW IN ETHANOL/F	OII	.15	.03	1H	175	AIR	COAT COAT
PC 17 A/E AS 2/1 BW FLEXIBLE EPOXY COATING	HYS	13.85	.07	7D	25	AIR	COAT COAT
PC 17 A/E AS 2/1 BW FLEXIBLE EPOXY COATING	HYS	12.21	.06	30M	65	AIR	COAT COAT
PC 17 A/E AS 2/1 BW FLEXIBLE EPOXY COATING	HYS	7.01	.06	5H	25	AIR	COAT COAT
PC 18 POLYURETHANE COATING	HYS	4.51	.20	1H	71	AIR	COATING

SECTION 3 -- CONFORMAL COATING

MATERIAL	APK CODE	XPMI	ACVCM	CURE TIME	CURE TEMP	AIDS	APPLICATION
PC 18M ONE PART EPIURETHANE COATING/F	HYS	2.06	.09	24H	25	AIR	COATING COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	HYS	3.10	.05	7D	60	AIR	COAT COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	HYS	1.04	.05	16H	50	AIR	COAT COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	HYS	.86	.03	24H	80	AIR	COAT COAT
PC 20M ONE PART ACRYLIC COATING/F	HYS	4.00	.05	24H	80	AIR	E-2 COAT COAT
PC 29 A/B AS 5/3 B ₁ URETHANE	HYS	7.42	.10	7D	25	AIR	COAT COAT
PC 401/T AS 10/17 B ₁ SILK SCREEN EPOXY GREEN	PCK	1.59	.18	30M	60	AIR	COATING DASK
PC 401/T AS 10/17 B ₁ SILK SCREEN EPOXY GREEN	PCK	.72	.01	3.5H	160	AIR	COATING DASK
PD 147 (RTV 511)	GEV	.11	.00	10H	190	AIR	COATING
PHOTOPOLYMER 6011G MED VISCOSITY POLYTHIOETHER	WRG	2.5b	.04	48H	E-6	AIR	COAT COAT = ADH
PHOTOPOLYMER 9111L RIGID POLYTHIOETHER	WRG	1.97	.09	30H	82	AIR	COAT COAT = ADH
POLYBECAST V-356-TEF	USP	2.18	.09	30H	82	AIR	COAT COAT
POLYURETHANE COATING 22H ONE COMPONENT/FOIL	ELS	.91	.01	2H	82	AIR	COATING
POLYURETHANE COATING 22H ONE COMPONENT/FOIL	ELS	1.98	.03	12H	120	AIR	COATING
PR 153 OVER PR 1531 A/B AS 32/10 BW	PRC	1.94	.59	7D	25	AIR	COAT COAT
PR 154L A/B AS 40/100 BW POLYURETHANE TUBE FILM	PRC	.63	.06	3H	82	AIR	COAT COAT
PR 154L A/B AS 40/100 BW POLYURETHANE TUBE FILM	PRC	.78	.06	60H	82	AIR	COAT COAT
PR 156.8 AEROSOL URETHANE COATING/F	PRC	1.57	.05	1H	82	AIR	COAT COAT
PR 156.8 AEROSOL URETHANE COATING/F	PRC	3.25	.02	12H	50	AIR	COAT COAT
PR 156.8 AEROSOL URETHANE COATING/F	PRC	1.92	.02	24H	75	AIR	COAT COAT
PR 156.8 AEROSOL URETHANE COATING/F	PRC	3.00	.02	1H	82	AIR	COAT COAT
PR 156.8 AEROSOL URETHANE COATING/F	PRC	1.69	.08	48H	82	AIR	COAT COAT
PR 156.8 DIP COATING/F	PRC	2.29	.05	7D	25	AIR	COAT COAT
PR 156.8 DIP COATING/F	PRC	.97	.04	1H	82	AIR	COAT COAT
PR 166OL A/B 45 1/4 BW W/HEK - POLYURETHANE	PRC	.86	.01	16H	62.5	AIR	COAT COAT
PRINT-KOTE GC 14-2 ON FOIL	GCE	3.45	.79	16H	25.0	AIR	COAT COAT
PRINT-KOTE GC 14-2 ON FOIL	GCE	1.47	.98	24H	100	AIR	COAT COAT
PT 201 THERMOSETTING YELLOW GOLD EPOXY COATING/P	PTI	.96	.37	1H	16.3	AIR	COATING
PT 207 POLYVINYL FLUORIDE COATING/F	PTI	.88	.21	48H	16.3	AIR	COATING
PT 4121 A/B AS 100/73 3W EPOXY	PTI	8.31	.03	5H	54	AIR	COAT COAT
PT 750 A/B AS 3/1 EV diAKOON	PTI	1.74	.13	24H	52	AIR	COATING
PT 750 A/E AS 3/1 EV POLYURETHANE 15 MIN FLASH/COAT	PTI	10.95	.01	40M	71	AIR	COAT COAT
PYRE-ML RK 692 POLYIMIDE 15 MIN FLASH/COAT	DUP	.96	.00	24H	249	AIR	COATING
PYRE-ML RK 692 POLYIMIDE 15 MIN FLASH/COAT	DUP	.86	.00	15M	204	AIR	COATING
					24H	249	AIR

SECTION 3 -- CONFORMAL COATING

MATERIAL	HFR CODE	#ML	%VCM	CURE TIME	ATMOS	APPLICATION
QB - 4-3117 ONE PART SILICONE QB - 4-3117 ONE PART SILICONE	DCC DCC	1.49 1.07	.19 .25	7D 25	AIR AIR	CONF COAT CONF COAT
QB - 6-3112 CLEAR RTV COATING/F QB - 6-3112 CLEAR RTV COATING/F	DCC DCC	3-.33 2-.33	.01 .01	24H 10D	AIR AIR	COATING COATING
RS - 9384 COATED VULCANIZED KAPTON RS - 9384 COATED VULCANIZED KAPTON	KST KST	.773 .715	.003 .01	2H 24H	AIR AIR	IDEAL BLANKET IDEAL BLANKET
R-1152 ONE COMPONENT SILICONE - CLEAR LOT 013-166 RCC-15D UV POLYMER	ECG HAG	2.34 1.48	.028 .03	7D 24H	50 25	E-6 E-6
RCC-15D UV POLYMER RD 1875-3 POLYURETHANE	HCC HCC	1.60 1.35	.18 .18	24H 24H	AIR AIR	CONF COAT CONF COAT
RESISTOR COATING TYPE 100 PLAT BLACK/F	TNC	1.18	.75	20H 20H	71 75	E-3 E-3
RESISTOR COATING TYPE 150 PLAT BLACK/F	TNC	.26	.13	3H 3H	65 65	AIR AIR
RESISTOR COATING TYPE 200 PLAT BLACK/F	TNC	.32	.08	30H 30H	125 125	AIR AIR
RESISTOR COATING TYPE 250 PLAT BLACK/F	TNC	.86	.44	20H 20H	25 25	AIR AIR
RESINFIELD 7200 A/E AS 2/1 BY EPOXY COATING RESINFIELD 7200 A/E/SOL AS 2/1/2 BW EPOXY COATING	FHB FHB	4-0.3 11.01	.01 .03	3H 1H	154 164	AIR AIR
EMBC 18 A/B AS 4/1 BW CLEAR EPOXY	BYd	6.85	.01	1H 1H	66 69	AIR AIR
RTV 511/T-12 AS 0.5% T-12 BW SILICONE	GEC	-0.9	-0.0	30H 1H	13.2 13.2	AIR AIR
RTV 615 A/B AS 10/1 BW DEVOL AT 125C	GSC	3.19	1.07	7D 7D	177 177	E-3 E-3
R101 PROTECTANT COATING	UGC	3.10	1.06	16H 16H	25 25	AIR AII
R4-3117 ONE PART SILICONE - FREE FILM - CLEAR	DCC	-6.1	-2.3	124 124	121 121	AIR AII
R4-3117 ONE PART SILICONE/F SARAN F310 PONDER LOT C301508	DCC DCC	1.43 2.71	.24 .24	24D 14D	25 25	AIR AII
SCOTCHCAST 281/282 EPOXY FORMULATION	AND AND	4.37 4.25	.95 .95	4H 4H	120 120	AIR AII
SOLITHANE 113/PPG-425/EH-310 FOR FORMULA 20 SOLITHANE 113/ACICINOLEYL ALCOHOL FOR FORMULA 25	TCC TCC	.59 1.38	.01 .01	7D 7D	25 25	AIR AII
SOLITHANE 113/T-440/TMP FORMULA 27 SOLITHANE 113/300 AS 100/100 BW FORMULA 4	TCC TCC	.87 1.30	.02 .03	7D 7D	25 25	AIR AII
SOLITHANE 113/300 AS 100/73 BW FORMULA 1 SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC TCC	.32 .28	.04 .04	24H 24H	79 79	AIR AII
SOLITHANE 113/300/CALCAFLUOR WHITE/T-12/MIBK SOLITHANE 113/300/EHMISSEAL THINNER 521	TCC TCC	.57 .56	.04 .05	54 54	54 54	AIR AII
SOLITHANE 113/300/EHMISSEAL THINNER 521 SOLITHANE 113/300/N-METHYL MORPHOLINE FORMULA 23	TCC TCC	.42 .42	.02 .02	2H 2H	93 93	AIR AII
SOLITHANE 113/300/QUADROL FORMULA 24 SOLITHANE 113/300/QUADROL FORMULA 26	TCC TCC	.88 .29	.00 .00	7D 7D	25 25	AIR AII
SOLITHANE 113/300/1-12/CALCAFLOU RAW/DB CASTOR OIL SOLITHANE 113/300/1-12/SILFLAKE 135/HEXANE	SLK TCC	.31 .62	.02 .02	7D 7D	60 60	AIR AII

SECTION 3 -- CONFORMAL COATING

MATERIAL	NFR CODE	XFM	%CVC	CURE TIME	CURE TEMP	STATUS	APPLICATION
SOLITHANE 113/300 TOLUENE AS 100/73 BW/173 BV	TCC	.50	.03	24H	55	AIR	COAT
SOLITHANE 113/300 1/4 TRIETHYLAMINE FOKMULA 22	TCC	.43	.03	24H	70	AIR	COAT
SOLITHANE 113/300 AS 100/14-328 AS 100/14-5 BW FORMULA 15	TCC	.79	.04	24H	70	AIR	COAT
SOLITHANE 113/300 AS 100/14-5 BW FORMULA 15	TCC	.19	.08	3H	66	AIR	COAT
SOLITHANE 113/300 AS 100/6-5-5/1 FORMULA 29	TCC	.60	.03	24H	70	AIR	COAT
SOLITHANE 113/300 AS 100/6-5-5/1 FORMULA 29	TCC	.60	.03	24H	70	AIR	COAT
SPACE GARD 4-C-25 CLEAR COATING	DEX	.44	.03	24H	70	AIR	COAT
SPENKEL 486-50CX POLYURETHANE	SPK	.84	.02	24H	70	AIR	COAT
SPRAY-LAT 1071B STRIPPEABLE COATING	SPX	.30	.03	12H	300	AIR	COATING
S3 165/1 CALCIUM OXIDE/ALUM SILICATE COATING	GRU	.31	.07	24H	70	AIR	PROTECTIVE COAT
STRIPPEABLE VINYL COATING	EBC	.31	.07	24H	70	AIR	COATING/ETCHING
STYCAST CPC 18 A/B AS 100/12-5 BW POLYURETHANE	EBC	.37	.15	7D	25	AIR	COATING/POTTING
STYCAST CPC 18 A/B AS 100/12-5 BW POLYURETHANE	EMC	.37	.12-16	48H	70	AIR	COATING/POTTING
STYCAST CPC 19 A/B AS 100/38 BW POLYURETHANE	EMC	.20	.16	16H	52	AIR	COATING/POTTING
STYCAST 1217/9 AS 100/13 BW EPOXY	EMC	.20	.16	24H	150	AIR	COATING
STYCAST 2850KA/24LV AS 100/1 BW BLUE EPOXY	EMC	.65	.09	7D	25	AIR	COATING
TRIFLON TYPE Y960 ALUM KAPTON/Y966 COMPQSILE TAPE	GTS	.44	.01	24H	125	AIR	THERMAL CONTROL
UCAR SIL Y-4310 SILICONE	UCC	.64	.01	6H	125	AIR	COAT
UCAR SIL Y-4486	UCC	.64	.07	24H	70	AIR	COAT
UNICOAT 2081-31A ONE COMPONENT EPOXY/F	AMC	.95	.73	2H	25	AIR	COAT
UNICOAT 2081-31A ONE PART FLUORESCENT EPOXY/F	AMC	.31	.11	1H	125	AIR	COAT
UNICOAT 2081-31A ONE PART FLUORESCENT EPOXY/F	AMC	.26	.25	12H	180	AIR	COAT
URALANE 22H POLYURETHANE	FPI	.60	.06	24H	75	AIR	COAT
URALANE 22H POLYURETHANE FILM	FPI	.44	.05	16H	75	AIR	COAT
URALANE 22H POLYURETHANE FILM	FPI	.44	.05	7D	25	AIR	COAT
URALANE 22H POLYURETHANE 2 COAT SAMPLE	FPI	.65	.01	20M	25	AIR	COAT
URALANE 22H/MDAC FLUORESCENT TRACER	FPI	.43	.08	24H	85	AIR	COAT
URALANE 5738 A/B AS 100/55 BW	FPI	.71	.11	24H	75	AIR	COAT
URALANE 5750 A/B AS 18/100 BW	FPI	.41	.03	24H	93	AIR	COAT
URALANE 5750 A/B AS 18/100 BW	FPI	.41	.03	24H	93	AIR	COAT
URALANE 5750 A/B AS 4/25 BW ULET HANE	FPI	.45	.01	2H	93	AIR	COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	FPI	.62	.01	2H	93	AIR	COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	FPI	.60	.01	24H	93	AIR	COAT
URALANE 8267 TRANSEALANT POLYURETHANE	FPI	.00	.17	24H	25	AIR	COATING
US 0009 A/B AS 100/35 BW POLYURETHANE	HYS	.69	.03	1H	25	AIR	COAT
VINYL DISPERSION PLASTISOL 77X-3720 BLACK	STA	.89	.01	2H	60	AIR	COAT
VORITE 63 POLYURETHANE COATING	WDP	.66	.01	24H	100	AIR	COAT
WORNOV 1000 MASK FILM GREEN	WDP	.07	.43	1H	135	AIR	MASK
XR-6-2205 ONE PART SILICONE	DCC	.95	.39	7D	25	AIR	COATING
XR40-110/CAT 23A/DYE 7GA AS 454/1.3/0-1 PBW SILICONE	DCC	.28	.22	1d	74	AIR	COATING
XR40-110/CAT 23A/DYE 7GA AS 454/1.3/0-1 PBW SILICONE	DCC	.28	.22	1d	74	AIR	COATING
					6H		

SECTION 3 -- CONFORMAL COATING

MATERIAL	MFR CODE	%TML	%CVCN	CURE TIME	CURE TEMP	AIRLOS	APPLICATION
XU-2118 HP POLYIMIDE BULK MATERIAL X1-2561 A/B AS 1C/1 BW CLEAR SILICONE COATING	CIB DCC	2.32 .19	.00 .03	7D	25	AIR	CONF COAT CONF COAT
X1-2561 A/B AS 1W/1 BW CLEAR SILICONE COATING X1-2577 CLEAR POLYDIMETHYL SILOXANE - ONE PART ZITTEL 61 IN ACCCHCI	DCC DCC DUP	.06 .20 2.32	.93 .52 .22	1H 21D 7D 30M	100 25 25 90	AIR AIR AIR AIR	CONF COAT CONF COAT CONF COAT COATING

SECTION 4 -- ELECTRICAL COMPONENTS

MATERIAL	MFR CODE	#TEL	%CICA	CURE TIME	ATMOS	APPLICATION
ADOLET PEM-2 ELECTRICAL FEED THRU NEMA X-A GRADE 550 ALBORN N CONNECTOR KGE2P/B7Y BLACK GLASS FILL/NYLON	TCC	2.97	.00	FED THRU CONNECTION		
ALPHA LUX 490 POXYDENOL OXIDE	ABI	.77	.05	INSULATION		
ALPHA WIRE 221-25-64 INSULATION	WPC	.08	.04	CONNECTOR		
AMP CONNECTOR 2052-207-1 NYLON/GLASS FIBER	AMP	1.30	.00	INSULATOR		
AMP CONNECTOR 945850-1 BLACK GLASS FILLED POLYESTER	AMP	1.62	.00	CONNECTOR		
AMP FEED THRU TERMINAL BLOCK 2043U7-6-70-39 EPOXY	AMP	.26	.00	CONNECTOR		
AMP FEED THRU TERMINAL BLOCK 2043U7-6-70-39 SILICONE	AMP	.28	.00	FEED THRU		
AMP 228 (1-2) SOLID INSULATION - RELEASER	AMP	.66	.00	INSULATION		
AMPHENOL CONNECTOR MIL-C88999 BLUE INSERT 418 SERIES	ABR	.55	.00	Conn. & SUL		
AMPHENOL CONNECTOR MIL-C88999 CLEAR SEAL 418 SERIES	ABR	.59	.00	Conn. & SUL		
AMPHENOL CONNECTOR SERIES 118 BLUE FLUOROSILICONE	ABR	.56	.10	Conn. & SUL		
AMPHENOL CONNECTOR SERIES 118 TA THERMOPLASTIC ONLY	ABR	.93	.00	Conn. & SUL		
AMPHENOL 481 CONNECTOR PHENOLIC/SILASIC 35U	ABR	.59	.01	Conn. & SUL		
AMPHENOL 481 CONNECTOR RED SILICONE 35U ONLY	ABR	.17	.08	Conn. & SUL		
APPLETON CONNECTOR RED BLACK PHE NO LIC FI BERGLASS	AEL	.56	.00	Conn. & SUL		
APPLETON CONNECTOR WHITE FLUOROSILICONE INSERT	AEL	.24	.00	Conn. & SUL		
ARMORED POLYETHER MA 52-200 MAGNET WIRE BROWN	PDC	.85	.11	PIPE COATING		
AUGAT CONNECTOR 14005-9-483 GRAY POLYESTER	AUG	.44	.00	CONNECTOR		
BENDIX CONNECTOR ECD 9-6500 SILICONE	BEN	.12	.00	Conn. & SUL		
BENDIX CONNECTOR J1906RE-22-355 OLIVE GREEN POLYMER	BEN	.04	.02	Conn. & SUL		
BENDIX CONNECTOR J1906RE-22-355 RED SILICONE	BEN	.95	.00	Conn. & SUL		
BENDIX CONNECTOR J1907RE-24-35P DARK BLUE POLYMER	BEN	.29	.02	Conn. & SUL		
BENDIX CONNECTOR J1907RE-24-35P PINK SILICONE	BEN	.17	.00	Conn. & SUL		
BENDIX CONNECTOR PT07H-14-19P BLACK ORING	BEN	.14	.04	Conn. & SUL		
BENDIX CONNECTOR PT07H-14-19P GREEN GLASS INSEKT	BEN	.00	.00	Conn. & SUL		
BENDIX CONNECTOR T-CLLON 4204 POLYAMID-IMID	AOC	.23	.00	Conn. & SUL		
BENDIX CONNECTOR 9-5400 RED RUBBER INSERT MATERIAL	BEN	.11	.04	Conn. & SUL		
BENDIX CONNECTOR 9-5500 RED RUBBER INSERT MATERIAL	BEN	.07	.03	Conn. & SUL		
CANNON CONNECTOR ECUSING DE 5094-1 NYLON	CAN	.24	.02	Conn. & SUL		
CANNON CONNECTOR MIX POLYMING INTERFACIAL SEAL	CAN	.44	.00	Conn. & SUL		
CANNON CONNECTOR MIL-C88999 PINK INSUL GREEN	CAN	.44	.00	Conn. & SUL		
CANNON CONNECTOR NS3479 BLACK PHENOLIC INSERT	CAN	.54	.01	Conn. & SUL		
CANNON CONNECTOR NS3479 PINK SILICONE	CAN	.07	.01	Conn. & SUL		
CANNON CONNECTOR PW6G24B11SWC 16 ASFC 40M 3.95 6.9	CAN	.14	.00	CONNECTOR		
CANNON CONNECTOR PW6G24B11SWC 16 BLACK PLASTIC	CAN	.61	.00	CONNECTOR		
CANNON CONNECTOR PW6G24B11SWC 16 RED SILICONE	CAN	.19	.00	CONNECTOR		
CANNON CONNECTOR SM 3204-55 PINK SILICONE	CAN	.08	.00	Conn. & SUL		
CANNON CONNECTOR SM 3500-79 PINK SILICONE	CAN	.34	.02	Conn. & SUL		
CANNON CONNECTOR 7624-200 BLACK NYLON/GLASS	CAN	.49	.04	Conn. & SUL		
CANNON FILTER PIN CONN DDJ-5UPNM-A106 BLUE SILICONE	CAN	.64	.06	Conn. & SUL		
CANNON FILTER PIN CONN DDJ-5UPNM-A106 BLUE SILICONE	CAN	.31	.06	Conn. & SUL		
CANNON WA 202 CONNECTOR	CAN	.24	.00	Conn. & SUL		
CERTAINIUM 61 SOLDER - OXIDIZED S/N/P/B/15% CD	ARC	.00	.00	SOLDER		
CERTAINIUM 61 SOLDER SH/2B/15% CD	CM	.00	.06	CONN. FORM		

SECTION 4 -- ELECTRICAL COMPONENTS

MATERIAL	NFR CODE	HTM	%VCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
COIL FORM BASE - WHITE	CNT	4.52	0.0	0.88	1.30	AIR	BASE
COIL FORM PHENOLIC	CAN	4.76	1.34	24H	175	AIR	COIL FORM
CONNECTOR INSERT BLUE SILICONE	CAN	4.87	1.14	24H	175	AIR	CONNECTOR INSUL.
CONNECTOR INSERT TAN RUBBER PER MIL C38999	PNC	4.42	0.23	24H	175	AIR	CONNECTOR INSUL.
CONNECTOR INSERT TAN RUBBER PER MIL C38999	PNC	2.20	0.04	24H	175	AIR	CONNECTOR INSUL.
CONNECTOR INSERT 44-11-96-093 RED FLUOROSILICONE	CIN	4.62	0.11	24H	175	AIR	CONNECTOR INSUL.
CONNECTOR MIL C38999 RED INSERT	GHT	4.62	0.11	24H	175	AIR	CONNECTOR INSUL.
CONNECTOR PLUG JP1S1PB GRAY	HIN	5.52	0.91	24H	175	AIR	CONNECTOR
CONNECTOR 3612261-01 BLACK NYLON/GLASS	HUP	1.25	0.55	24H	175	AIR	CONNECTOR
CONNECTOR-THERMO COUPLE BLUE COPPER/CON	TEL	4.44	0.91	24H	175	AIR	CONNECTOR
CONNECTOR D-8150 POLYAMIDE-IEHDE/ADH/COPPER	ROG	1.15	0.02	24H	175	AIR	HEAT CORE
D-8970 EPOXY FILM/ADH/COPPER	ROG	4.42	0.00	24H	175	AIR	CAST CORD
DA P - MESA PLASTICS		3.4	0.00	24H	175	AIR	
DAP CONNECTOR A1 GO4202	HAC	6.61	0.01	24H	175	AIR	CONNECTOR
DAP CONNECTOR 3-2-520 GLASS FILLED/FLAME RESISTANT	ACR	6.67	0.04	24H	175	AIR	CONNECTOR
DAP INSERT/CANNON CONNECTOR DDM 24W7P	CAN	4.44	0.00	24H	175	AIR	CONNECTOR
DAP SDG-P MIL H-14 AMP CONNECTOR	AMP	4.44	0.00	24H	175	AIR	CONNECTOR
DAP/FLAME RETARDANT-GLASS FILLED CANNON CON PS-80	CAN	4.44	0.00	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR A81210F16-1451 BROWN SILICONE	DEU	3.1	0.02	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR A81511-46FF0151 BROWN SILICONE	DEU	2.22	0.07	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR A81511/46FF0151 GREEN MOLD INSERT	DEU	2.21	0.00	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR ETK06-16-615 GREEN HOLD INSERT	DEU	1.50	0.00	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR F11-10350 BOLDED INSERT	DEU	0.99	0.06	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR F11-10350 BOLDED INSERT	DEU	1.23	0.01	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR 6825 RHO4-4425 SILICONE INSERPT	DEU	1.29	0.05	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR 6825 RHO4-4425 SILICONE INSERPT	DEU	1.25	0.00	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR 72201 UAS64-212P SILICONE INSERPT	DEU	2.22	0.01	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR 75033 RTK00-14-44P SILICONE INSERPT	DEU	1.16	0.05	24H	175	AIR	CONNECTOR
DEUTSCH CONNECTOR 7544E RE64-12P SILICONE INSERPT	DEU	2.44	0.02	24H	175	AIR	CONNECTOR
DEUTSCH CTY SERIES TERMINAL BLOCK K RED SILICONE ONLY	DEU	2.44	0.03	24H	175	AIR	TERMINAL BLOCK
DEUTSCH TERMINAL BLOCK T11E06-01 SILICONE INSERPT	DEU	2.19	0.01	24H	175	AIR	TERMINAL BLOCK
DEUTSCH T-10-70 SHORT GLASS FIBER/DAP	DEU	1.43	0.00	24H	175	AIR	CONNECTOR
EC-COCOAT 200 A/B AS 10/1 BW EPOXY	EMC	9.90	0.04	24H	175	AIR	COIL COATING
ECOSORB AN 74 ETHANOL WASH - 3	EMC	7.70	0.07	24H	175	AIR	ABSORBANT
ECOSORB AN 79 MICROWAVE ABSORBANT	EMC	4.37	0.45	24H	100	AIR	ABSORBANT
ECOSORB AN 79 MICROWAVE ABSORBANT 16H METOH WASH	EMC	1.03	-15	24H	25	AIR	ABSORBANT
ECOSORB CR-S 124 A/B AS 100/1 BW SILICONE BASE	EMC	2.29	0.09	24H	80	AIR	ABSORBANT
ECOSORB CR-124 X/Y AS 50/1 BW EPOXY	EMC	1.11	0.00	24H	140	AIR	ABSORBANT
ECOSORB GDS IRON FILLED SILICONE REINFORCED	EMC	3.89	0.98	24H	53	AIR	ABSORBANT
ECOSORB OCP 9 FLAME RETARDED MICROWAVE ABSORBER	EMC	3.83	0.53	24H	53	AIR	ABSORBER
EHP-3 HR POLYIMIDE IMPREG NOMEK PAPER HONEYCOMB	DUP	1.97	-0.2	24H	50	AIR	ABSORBER
EHP-8 MICROWAVE ABSORBING FOAM	EMC	5.07	-0.29	24H	50	AIR	ABSORBER
ELECTROLUMINESCENT LAND GRIMES-YELLOW	NRG	4.1	-0.01	24H	50	AIR	LAMP
EMA 7037 IRON	SBI	3.4	-0.01	24H	50	AIR	DIE-EL-ETRIC
EMA 7085 IRON	SBI	2.3	-0.00	24H	50	AIR	DIE-EL-ETRIC
EMI GASKET AMP RF-SMA CONNECTOR RED SILICONE	AMP	2.1	-0.00	24H	50	AIR	GASKET
GASKET AMP RF-SMA CONNECTOR WHITE SILICONE	AMP	1.4	-0.02	24H	50	AIR	GASKET

SECTION 4 — ELECTRICAL COMPONENTS

MATERIAL	HFB CODE	XMTL TIME	ACVCH	CURE TIME	ADHS	APPLICATION
GORE-TEX P GTS 810 F/FEE RIBBON CABLE C/PND S 1817	WLG	.01	.009	.009	Air	PLATE MARKING
GROMMET PR JOSHUA RUBBER SILICONE C/PND S 1116	GRC	.034	.005	.009	Air	GRINDING
GROMMET 1042 60 EUROMERIT SBR CUMM GRADE RUBBER	JAS	.13-.51	.005	.009	Air	GRINDING
HEATER - COLUMN MAIL COX SPEC 4500 BLASTER	GCC	11-.92	.005	.009	Air	GRINDING
HEATING TAPE CLAYBCRN LABS A-16 DC 282 SILICONE	COA	.019	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS A-16-2 DC 282 SILICONE/F	TSI	.021	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS D-16-2 DC 282 SILICONE	CLY	.010	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS D-16-2 DC 282 SILICONE	CLY	.014	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS D-16-2 DC 282 SILICONE	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS D-16-2 DC 282 SILICONE	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS H-16-2X DC 282 SILICONE	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS H-16-2X DC 282 SILICONE	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE COAL RTV 6-1104	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE CLAYBCRN LABS 2 COATS RTV 6-1104	CLY	.015	.001	.24H	Air	HEAT TAPE
HEATING TAPE -CLAYBCRN LABS DC 282 OA ADH	CLY	.015	.001	.24H	Air	HEAT TAPE
INSUL-X POLY CELLULOSE NITRATE AND SOLVENT	JINX	.018	.001	.24H	Air	COATING
INSULATOR NOLDED MIL #20693	BEN	.024	.001	.025	Air	INSULATION
INSULATOR 10230-LAF POLYURETHANE COATING	ROS	.024	.001	.025	Air	INSULATION
INSULATOR 445 URETHANE DIELECTRIC	IER	.038	.001	.1H	Air	DIELECTRIC
INT CONNECTOR 7929 DBN-258 BLUE/GREEN MOLD INSERT	ITT	.055	.001	.10D	Air	CONN INSUL
MELAMINE G-5 PEE MIL P-15037B FUSE INSULATOR	NVF	.021	.001	.003	Air	INSULATOR
MELAMINE G-5 PEE MIL P-15037B FUSE INSULATOR	NVF	.026	.001	.003	Air	SWITCH
MICRO SWITCH 311 SX4-T GLASS FILLED PHENOLIC W/ADH	NSD	.044	.001	.003	Air	CONN INSUL
MICRODOD CONNECATOR RED SILICONE INSERT	MIR	.054	.001	.003	Air	INSULATION
MICRODOD CONNECATOR RED SILICONE INSERT	MIR	.054	.001	.003	Air	CONNECTOR
MICAOI 750 AEG GRAILE LEAD BORATE/MICA MIL	MEL	.067	.001	.003	Air	CONNECTOR
NYLAFIL GLASS AS 7/30 CONNECTOR INSERT - CANNON	FBA	.091	.001	.003	Air	CONNECTOR
PA 61 CERAMIC PART MOTECIA CMOS 14011 DTD 7720	CAN	.091	.001	.003	Air	CONNECTOR
PLASTIC PART MOTECIA CMOS 14044 DTD 7731	ELK	.091	.001	.003	Air	CONNECTOR
PLASTIC PART MOTECIA 74LS00 DTD 7732	HOT	.092	.001	.003	Air	CONNECTOR
PLASTIC PART MOTECIA 74LS174 DT D 7733	HOT	.092	.001	.003	Air	CONNECTOR
PLASTIC PART NATL SEMICONDUCTOR CHOS 4011 DTD 7233	NSE	.094	.001	.003	Air	CONNECTOR
PLASTIC PART NATL SEMICONDUCTOR CHOS 4044 DTD 727	NSE	.094	.001	.003	Air	CONNECTOR
PLASTIC PART SCA CMOS 4011 DTD 723	HCA	.097	.001	.003	Air	CONNECTOR
PLASTIC PART ACA CMOS 4044 DTD 701	ACA	.097	.001	.003	Air	CONNECTOR
PLASTIC PART SIGNETICS 74LS00 DTD 7733	SIG	.098	.001	.003	Air	CONNECTOR
PLASTIC PART SIGNETICS 74LS174 DTD 7723	SIG	.098	.001	.003	Air	CONNECTOR
PLASTIC PART TEXAS INST 74LS00 DTD 7710	TII	.098	.001	.003	Air	CONNECTOR
PLASTIC PART TEXAS INST 74LS174 DTD 7718	TII	.098	.001	.003	Air	CONNECTOR
POLYDOP POLYSYRINGE COIL COATING	POL	.096	.001	.003	Air	COATING
RATE GYRO 142 STYRENE INSULATION MATERIAL	GCE	.072	.001	.24H	Air	INSULATION
REXOLITE 142 STYRENE MOLDED TERMINAL	ACA	.092	.001	.24H	Air	INSULATION
RTV 70 RED SILICONE MOLDED TERMINAL	BHA	.092	.001	.24H	Air	INSULATION
AV 401 SPOOL FOIL /FIBERGLASS	GBC	.051	.001	.32H	Air	COIL FORM
SCOTCHFLEX SOCKET CONNECTOR GLASS REINF POLYESTER	SPI	.032	.001	.19H	Air	CONNECTOR
SH 2X2-5 HEATER - RED SILICONE	AMM	.08	.001	.04H	Air	HEAT
SH 3/4X5 HEATER - RED SILICONE	EFH	.12	.001	.03H	Air	HEAT
SILICONE INSULATOR SO-1050-8913 RED	LCR	.30	.001	.18	Air	INSULATION
SPICAST HI K 500 DIELECTRIC	EMC	.47	.001	.04	Air	INSULATOR

SECTION 4 -- ELECTRICAL COMPONENTS

MATERIAL	MFR CODE	%TML	%CVCM	CURE TIME	CURE TEMP	ATLAS	AIR PLACEMENT
TEFLON PTFE CONDUCTOR RIBBON CABLE INSULATION	WLG	.00	.00				
TERMINAL T-2 SS CLAYBON LABS DC 282 - GE 102 - VIBRO FLO E 8530-2 FLUIDIZED BED COATING	CLY	.89	.65				
VIBRO FLO E-301 EPOXY POWDER COATING	APC	.57	.32	54	204	AIR	TERMINAL PAD COATING
VISHAY MOLLED COMECNLT 3118 & BLACK EXTRUDED RODS	APC	.87	.08	304	180	AIR	PADS COATING
ZITTEL 101 BLACK EXTRUDED RODS	VIS	2.09	.09				HOLD GND
	DUP	1.19	.00				CONN GND

SECTION 5 -- ELECTRICAL SHIELDS

MATERIAL	MFR CODE	%TML	%CVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
CHO-BOND 4041-0402 A/B AS 1.5/5.5 BW BROWN	CHO	.32	.11	3H	200	AIR	HF SHIELD
CHO-BOND 4041-0402 A/B AS 1.5/5.5 BW BROWN	CHO	.31	.11	6H	200	AIR	HF SHIELD
CHO-SEAL 1212 SILVER FILLED SILICONE 125 GRADE	CHO	.44	.15	15H	171	AIR	SILICON
CHO-SEAL 1212 SILVER FILLED SILICONE 125 GRADE	CHO	.08	.02	15H	177	AIR	SILICON
CHO-SEAL 1214 SILVER FILLED SILICONE 125 GRADE	CHO	.26	.05	24H	177	AIR	GASKET
CHO-SEAL 1214 SILVER FILLED SILICONE 125 GRADE	CHO	.04	.02	15H	177	AIR	GASKET
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	CHO	.06	.02	15H	177	AIR	SILICON
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	CHO	.46	.07	24H	177	AIR	SILICON
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	CHO	.29	.01	15H	171	AIR	SILICON
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	CHO	.03	.00	15H	177	AIR	SILICON
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	CHO	.34	.08	24H	177	AIR	SILICON
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	CHO	.05	.02	15H	177	AIR	SILICON
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	CHO	.30	.00	15H	177	AIR	SILICON
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	CHO	.05	.00	15H	177	AIR	SILICON
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	CHO	.36	.12	24H	177	AIR	SEAL
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	CHO	.43	.06	15H	171	AIR	SILICON
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	CHO	.04	.02	15H	177	AIR	SILICON
CHO-SEAL 1250 SILVER FILLED SILICONE COND INNLA SURF	CHO	.71	.16	24H	177	AIR	SEAL
CHO-SHRINK BOOT 71-04-7004-100 AG COND INNER SURFACE	CHO	.98	.22	15H	121	AIR	SILICON TUBING
CHO-SHRINK TUBING SILVER COND INNER SURFACE	CHO	.61	.06	0.5M	121	AIR	SILICON TUBING
CHO-SIL 1401 SILVER FILLED SILICONE COND INNER SURFACE	CHO	.65	.11	0.5M	121	AIR	SILICON TUBING
CHO-SIL 1401 SILVER FILLED SILICONE	CHO	.16	.02	24H	177	AIR	SILICON
CHO-SIL 1405 SILVER FILLED SILICONE	CHO	.05	.02	24H	177	AIR	SILICON
CONSIL G SILICON FILLED SILICONE	TBC	.93	.02	24H	115	E-3	SILICON
CONSIL MEDIUM HARD SILVER FILLED SILICONE	TBC	.06	.01	24H	115	E-3	SILICON
CONSIL MEDIUM HARD SILVER FILLED SILICONE	TBC	.22	.01	24H	177	AIR	SILICON
CONSIL R SILVER FILLED SILICONE	TBC	.05	.01	24H	115	E-3	SILICON
CONSIL SILVER FILLED SILICONE SHEET	TBC	.20	.10	24H	115	E-3	SILICON
CUSTCW LOAD 410-50 EPOXY	TBC	.44	.12	24H	177	AIR	KP ABSORBER
ECCOSHIELD PST-C ALUM FOIL/SILVER FILLED PLASTIC ADH	CUM	.11	.01	24H	177	AIR	TAPE
ECCOSHIELD SV-SILVER FILLED SILICONE	EMC	.26	.09	24H	177	AIR	SILICON
ECCOSHIELD SV-R SILVER FILLED SILICONE	EMC	.16	.08	24H	177	AIR	SILICON
ECCOSHIELD SV-S SILVER FILLED SILICONE	EMC	.03	.06	24H	177	AIR	SILICON
ECCOSHIELD VY CONDUCTIVE SEALER	EMC	.15	.06	24H	177	AIR	SILICON
ECCOSHIELD VY CONDUCTIVE SEALER	EMC	.58	.32	24H	177	AIR	SILICON

SECTION 5 -- ELECTRICAL SHIELDS

MATERIAL	MPR CODE	XTHL	%CVCM	CURE TIME	ATMOS	APPLICATION
ECCOSORB FDS						
ECCOSORB FDS						
ECCOSORB LS FOAM						
ECCOSORB MF 110	IBCN FILLED EPOXY	EBC	.29	.12	AIR	ABSORBANT
ECCOSORB MF 112	IBCN FILLED EPOXY	EBC	.05	.44		ABSORBANT
ECCOSORB MF 114	IBCN FILLED EPOXY	EBC	.51	.01		ABSORBANT
ECCOSORB MF 114	IBCN FILLED EPOXY	EBC	.24	.01		SHELD
ECCOSORB MF 124	IBCN FILLED EPOXY	EBC	.22	.00		SHELD
ECCOSORB SF 9-5	RESONANT ABSORBER-SILICONE FILLED	EBC	.08	.00		ABSORBANT
ECCOSORB SF 9-5	RESONANT ABSORBER-SILICONE FILLED	EBC	.31	.15		ABSORBER
ECCOSORB SFU 2-5		EBC	.19	.06		ABSORBER
ECCOSORB SFU-9	POLYURETHANE	EBC	.14	.06		ABSORBANT
ECCOSORB ELASTOMET	WIRE EMBEDDED SILICONE SHIELDING	EBC	.46	.05		ABSORBANT
EML SILVER FILLED	SILICONE ME 51-08-U201	TEC	.05	.03	E-J	EEL SHIELDING
KAPTON FILM W/ MGE	ACRYLIC ADH ON B SIDE	NET	1.06	.35		GASKET
METALSTATIC SILICONE FILLED ALUM MESH		SHI	.55	.09	1H	DIELECTRIC
METALSTATIC SILICONE FILLED ALUM MESH		SHI	.03	.16	190	SHIELDING
PORCUPINE METALASTIC SILICONE FILLED MONEL MESH		SHI	.65	.02	24H	SHIELDING
PORCUPINE METALASTIC SILICONE FILLED MONEL MESH		SHI	.09	.25	177	SHIELDING
SIC 9030/GREEN		GSD	.24	.05	24H	SHIELDING
STYCAST HHIK FILLED EPOXY		EAC	.38	.01		DIELECTRIC
TECKNIT 7-09-76 SILVER COATED NYLON		TBC	1.02	.02		SHIELDING
TECKSPAN P/N 48-C9866	WIRE EMBEDDED SILICONE	TBC	.92	.20		EEL SHIELDING
XECON CS-14	12% SILVER FILLED SILICONE	NET	.45	.20	100	EEL SHIELDING
			.11	.17H	177	COLD GASKET

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	AFR CODE	#MIL	ACVCM	CURE TIME	TEMP	STATUS	APPLICATION
ACETATE BUTYRATE - CLEAR		4-.73	.00			LENS	
ACLEAR 22A CLEAR FILM POLYCHLOROTRIFLUOROETHYLENE	ACM	.13	.01			GELA	
ACLEAR 33C CLEAR FILM POLYCHLOROTRIFLUOROETHYLENE	ACC	.11	.01			GELA	
ACRYLIC STERF	ACC	.51	.05			STRUCTURAL	
ANTI STATIC FILM 219						FILM	
ARMALON FILM TG403C BLACK TFE ON GLASS FABRIC	MM	.32	.05			DEAD BARRIER	
ARMALON FILM TG403C NEUTRAL TEFON ON GLASS FABRIC	DUP	.05	.01			DEAD BARRIER	
BAVICK LI METHYL METHACRYLATE - MODIFIED	DUP	.05	.00			INSULATION	
BETA MARQUISSETTE MCVEN FIBERGLASS STYLE 2530	CRY	.29	.00			INSULATION	
BZT-92 NATURAL SCREW NOMEX THREAD	STE	.93	.00			INSULATION	
CAPRON 512 NYLON 611 STATIC FILM PURPLE	EDP	3-.95	.08			INSULATION	
CELLULOSE ACETATE EUTRADE 200 MICRON FILM BLUE	FAB	4-.93	.12			INSULATION	
CELLULOSE ACETATE FILM SHIM STOCK	FAB	1-.79	.01			INSULATION	
CHO-THERM 1661 TEEREN COND SHEET WHITE SILICONE	ART	1-.28	.08			INSULATION	
CHO-THERM 1661 TEEREN COND SHEET WHITE SILICONE	CHO	.76	.06			INSULATION	
CHO-THERM 1663 TEEREN COND SHEET WHITE SILICONE	CHO	1-.53	.14			INSULATION	
CHO-THERM 1664 TEEREN COND SHEET - BLUE 7.5 MIL THICK	CHO	.26	.05			INSULATION	
CHO-THERM 1664 TEEREN COND SHEET WHITE SILICONE	CHO	.45	.13			INSULATION	
CHO-THERM 1667 TEEREN COND SHEET WHITE SILICONE	CHO	.76	.07			INSULATION	
CHO-THERM 1671 TEEREN COND SHEET WHITE SILICONE	CHO	.10	.05			INSULATION	
CHO-THERM 1673 TEEREN COND SHEET GREEN SILICONE	CHO	1-.18	.10			INSULATION	
CHO-THERM 1673 TEEREN COND SHEET GREEN SILICONE	CHO	.11	.04			INSULATION	
CHO-THERM 1674 TEEREN COND SHEET BLUE SILICONE	CHO	.45	.01			INSULATION	
CHO-THERM 1677 TEEREN COND SHEET BLUE SILICONE	CHO	.12	.01			INSULATION	
CLOTH TFE COATED FIBERGLAS STYLE 16781 TYPE S	STE	.48	.27			INSULATION	
CONDULON ANTI STATIC FILM 4 MIL BLACK	PVL	.88	.03			INSULATION	
CONDULON ANTI STATIC FILM 4 MIL BLACK #9436	PVL	1-.76	.02			INSULATION	
CONDULON 89-7 ANTI STATIC FILM BLACK	PVL	.92	.02			INSULATION	
COVERLITE H FABRIC 55-6181-XX HYPALON COATED NYLON	EE	7.84	.92			INSULATION	
COVERLITE H FABRIC 55-6181-XX HYPALON COATED NYLON	EE	1.11	.55			INSULATION	
COVERLITE H FABRIC 55-6181-XX HYPALON COATED NYLON	EE	.98	.00			INSULATION	
CROMAFLEX FILM - FROSTY	DUP	.75	.01			INSULATION	
CYCOM MCG FIBER - NICKEL COATED GRAPHITE	ACC	.37	.01			INSULATION	
DACRON CLOTH 3 OZ CABRILLON	HOB	.02	.04			INSULATION	
DACRON DAYBOND Y-46-8X	HOB	.45	.09			INSULATION	
DACRON MESH D2A	APA	.19	.03			INSULATION	
DACRON MESH B2A FLYESTER NETTING	APA	.15	.00			INSULATION	
DACRON NETTING 7C886-10	BEP	.19	.06			INSULATION	
DACRON POLYESTER CLOTH	SST	.33	.04			INSULATION	
DACRON POLYESTER CLOTH MESH STYLE 15320	DUN	.12	.00			INSULATION	
DUN-CHBONE 500C VDATEFLON	DAS	.01	.00			INSULATION	
EA-7 POLYESTER FILM INSULATOR - FROSTY	ACH	.46	.01			INSULATION	
ECTFE EXTRUDED SHEET HI-TEMP APPLICATION	ACH	.38	.01			INSULATION	
ECTFE 0.5 MIL FILM	ACH	.17	.05			INSULATION	
ECTFE 1.0 MIL FILM	ACH	.19	.02			INSULATION	
ECTFE 10.8 OZ/YD FABRIC UNCALENDERED UNWASHED	ACA	.62	.09			INSULATION	
ECTFE 10.8 OZ/YD FABRIC UNCALENDERED UNWASHED	ACA	.28	.03			INSULATION	
ECTFE 7.3 OZ/YD FABRIC UNCALENDERED UNWASHED	ACA	.33	.01			INSULATION	
ECTFE 7.3 OZ/YD FABRIC UNCALENDERED WASHED	ACA	.21	.01			INSULATION	
EPC-01 KAPTON FILM/HERMOSET ADH	PLA	1.26	.25			INSULATION	
		75M	.171	AIR		INSULATION	

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	MPN CODE	XTPL CODE	%CVC CH	CURE TIME	ATDS TEMP	APPLICATION
ESTAR PHOTOGRAPHIC FILM	EAS	1.26	.00			FILM
FAIRBANE VSO060 BLACK VITON A SHEET	DUP	*32	*05			GASKET-SEAL
FAIRBANE FELT TYPE I	DUP	3.61	*01	24H	125	GASKET-SEAL
FELT NO. 1000X ROCK FELT TYPE I	DUP	2.82	*01	18H	60	FELT
PEP TEFILON SILVERED/PERMACEL 223 TAPE/F	GTS	*77	*35		E-1	FILM
PIBERGLASS WOVEN NETTING STYLE 1562	STE	*23	*03			INSULATION
PLEXAUST S.D. COATED FABRIC DUCT HOSE	PLA	*51	*47			HOSE
PLUGOQUELL DE-1200 TEFILON FILM-ACRYLIC ADH	DIN	*19	*01			PASS-SENS FILM
FLUOROCLAS 329-7 BETACLOTH/PIPE COATED	DIN	*03	*01			INSULATION
G 143700 THERMAL CONTROL FILM LAMINATE	GTS	*16	*07			INSULATION
G 401500 SILVERED TEFILON FILM	GTS	*28	*16			IDEAL CONTROL
G 401500 TAPE PTFE FILM/AG METALIZED ACRYLIC ADH/R	GTS	*30	*00			IDEAL CONTROL
GENOTHERM D10B UNPLASTICIZED PVC FILM CLEAR	GTS	*33	*00			FILM
GENOTHERM HT UNPLASTICIZED PVC FILM CLEAR	AMH	*12	*00			TAPE
GENOTHERM NTLS UNPLASTICIZED PVC FILM CLEAR	AMH	*23	*01			TAPE
GENOTHERM NTLS UNPLASTICIZED PVC FILM WHITE	AMH	*33	*05			FILM
GENOTHERM US 1004 UNPLASTICIZED PVC FILM CLEAR	AMH	*38	*05			FILM
GENOTHERM US 3003 UNPLASTICIZED PVC FILM CLEAR	AMH	*21	*02			FILM
GLASS CLOTH TAPE 134	AMH	*50	*06			FILM
GLASS CLOTH 1626 - SMALL WEAVE	PTC	*18	*03			CLOTH TAPE
GLASS FABRIC 195450/857 SQUARE MESH COATED WHITE	STE	*13	*03			CLOTH
KAPTON FEP FILM 40CF02	DUP	*23	*05			INSULATION
KAPTON FEP FILM 40CF022	DUP	*31	*18			FILM
KAPTON H FILM FIBERGLASS REINFORCED	DUP	*25	*01	90M	302	ATM
KAPTON H FILM REINFORCED GLASS CLOTH 104	DUP	*46	*05			INSULATION
KAPTON H FILM SILK LINING	RCA	*42	*02			IDEAL CONTROL
KAPTON H FILM SILK LINING/WEAVE BETA MARQUISITE GLASS CLOTH	DUP	*77	*02			FILM
KAPTON ALUMINIZED/CHENGGLAZE H322 FILM	DUP	*13	*03	24H	150	ATM
KAPTON/DACRON KEVLAR BONDED PROPRIETARY ADHESIVE	APL	*31	*03	15H	150	AIR
KEVLAK 29 YELLOW FIBERS	APL	*43	*17	4H	176	AIR
KEVLAK 49 COMPOSITE KEVLAR 5143 RES	NAC	*30	*13			IDEAL BLANKET
KIHFOL 8 GAUGE POLYCARBONATE	DUP	*13	*00			FILMS
KODALITH CRTHO FILE TYPE 3	GCC	*16	*00			ADDS/BLK
LECTROLIQUE CONDUCTIVE FABRIC - BLUE/BLACK VINYL	EAS	*98	*00			INSULATION
LENS TISSUE E8	PLA	*31	*00			FILM
LEXAN 9034-112 POLYCARBONATE CUSHION FILM - BLACK	GEC	*82	*03			STATIC CCNTROL
LE86-13 STATIC DISSIPATIVE CUSHION FILM ON FABRIC	GEC	*19	*01			WIRE
MA 385-3 FILM BLACK TEFLON ON FABRIC	DIN	*68	*01			LEADS
MAXOEB SOLAR FOIL BLACK NICKEL W/ADHESIVE	HPP	*55	*01			BAGGING
MAXOEB SOLAR FOIL BLACK NICKEL W/ADHESIVE	HPP	*44	*03			HEAT BARRIER
MP 1485 POLYURETHANE FILM	HOP	*92	*00			IDEAL CONTROL
MP 1885 POLYURETHANE FILM	HOP	*67	*00			IDEAL CONTROL
MYLAR IMAGING FILM/CIRCUITRY	SCS	*70	*04			FILM
NYLAR LA 616 - MIL FILM	DUP	*70	*04			FILM
NYLAR NYLAR PHOTOSENSITIVE FILM TYPE A	DUP	*15	*00			FILM INSERT
NORYL N-44 WHITE TEREAD NATURAL 5977B	DUP	*59	*00			FILM/SHEET
NORYL GPN-3-801 MCD PPO	SAC	3.93	*29			IDEAL
NORYL MODIFIED PEC	GEC	*10	*02			INSULATION
NYLON FILM-ANTISTATIC DF	GEC	*10	*00			MOULD
NYLON ORANGE MIL-C-702 OF TYPE I SUNSHADE MATL	SCE	*42	*06			FILM
ORCOFLA KN-10 KAPTON/NOMEX THREAD/POLYESTER BINDER	PUR	*92	*02	48H	125	E-2
						LAKE MUL. BLANKET

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	NPA CODE	SYML	SCVCM	CURE TIME	CURE ATMOS	APPLICATION
ORCOPILM KN-10 KAPTON/NOMEX THREAD/POLYESTER BINDER	ORC	1.19	-08			THERMAL BLANKET
ORCOPILM KN-11 KAPTON/NOMEX THREAD/POLYESTER BINDER	GTB	1.41	-05			THERMAL BLANKET
P-62 POLYETHER URETHANE FOAM WHITE	GTB	1.47	-11	24H	AIR	FUAN
P-62 POLYETHER URETHANE FOAM WHITE	GTB	1.49	-04	24H	AIR	FUAN
P-65 POLYETHER URETHANE FOAM WHITE H2O WASH	GTB	1.12	-10	24H	AIR	FUAN
P-65 POLYETHER URETHANE FOAM WHITE ISO-OCTANE WASH	GTB	1.12	-02	24H	AIR	FUAN
P-65 POLYETHER URETHANE FOAM WHITE NEUTOH WASH	GTB	1.14	-05	24H	AIR	FUAN
P-65 POLYETHER URETHANE FOAM WHITE NEUTOH/H2O WASH	GTB	1.14	-05	24H	AIR	FUAN
PARASOL GT-76 LAMINATE NYLON/ALUM	JSC	10.93	-08			THERMAL CONTROL
PBI THREAD - POLYBENZIMIDAZOLE	PTL	31.57	-09			THREAD
PEE VEL 38056 CLEAR ANTISTATIC FILM	PVL	6.22				FILM
PHENOLIC/NATURAL LINEN STANDOFF	ATP	3.92	-00			STRUCTURAL
PLEXIGLAS VS-100 OPTICAL	ATP	1.89	-00	24H	AIR	STRUCTURAL
PLEXIGLAS 11 UV	ROH	1.00	-01			LENS
POLASHET GRAY SILICONE SHEET/EMBEDDED MONEL WIRE	MEI	1.57	-00			LENS
POLASHET GRAY SILICONE SHEET/EMBEDDED MONEL WIRE	MEI	1.56	-46			SHIELD
POLYCARBONATE CIRCUIT CARD GUIDE	CAL	1.20	-11			GUIDE
POLYCHROME FILM 8 MIL	PCR	1.12	-02			FILM
POLYETHYLENE FILM ANTISTATIC DF CLEAR	SCE	1.64	-01			FILM
POLYETHYLENE FILM ANTISTATIC DALTON PINK-BRANCHED	DUP	1.41	-16			FILM
POLYETHYLENE FILM 2 MILS DALTON BRANCHED	DUP	1.14	-06			FILM
POLYETHYLENE FILM ULTRA HIGH MOLECULAR WEIGHT	PHI	1.42	-02			STRUCTURAL
POLYETHYLENE VAPC FILM .6 MIL	EXX	1.20	-10			FILM
POLYFENIC POLYSTYRENE	MMB	1.09	-00			STRUCTURAL
POLYURETHANE FILM E560 W/BUTTER ADH/F	DUP	1.49	-40			FILM
POLYVINYL CHLORIDE FILM - BUTYL THICK	DUP	3.31	5			FILM
PIRALUX FILM POLYLIIDE 2 MILS THICK	DUP	1.34	-00			FILM
RAYBESTOS R500 FRICTION MATERIAL	RMI	1.13	-00	1H	AIR	FRICTION PAD
RC-AS-1200 PR ANTISTATIC POLYETHYLENE FILM	RCI	.29	-04	16H	E-5	FILM
RC-AS-2400 ANTI STATIC NYLON FILM DINKO BANG	RCI	.34	-15			FILM
RC-AS-2400 A120 NYLON FILM W/O ANTI STATIC COMP/CLEAR	RCI	.75	-24			FILM
SAIL CLOTH ALUMINIZED NYLON/ALUM FOIL	ADL	.43	-18			FILM
SAIL COMPOSITE NYLON/NYLON/WHITE PAINT	MSF	.97	-22			FILM
SIL-PADS 400 SILICONE/WHITE GLASS SHEET GRAY	BEM	.40	-21			FILM
SILK NETTING SILVIE 5517	JMC	2.53	-07			NETTING
SILK NETTING SILVIE 5517	JMC	2.34	-12	24H	25	E-6
SILTEMP 64CH WOVEN GLASS CLOTH - BROWN	AME	5H	25			E-6
SILTEMP 64CH WOVEN GLASS CLOTH - LIGHT AQUA/WHITE VINYL	HEU	11.18	17			THEM CONTROL
SUBLIN 3810 NOMEX FILM	PIE	4.49	-05			PACKAGING
SURLYN 1652 2 MIL EATING FILM	DUP	1.39	-05			FILM
TEDLAR 150 BL 30 CC BLACK FILM	RPC	1.14	-05			COATING
TEPLON FEP INSULATION TAPE 72-731	HTW	.02	-00			ISULATION
TEPLON FEP TAPE 4 MIL FILM	DUP	.01	-00			FILM/SHEET
TEPLON FEP FILM SILVER-9705	DUE	.00	-00			FILM
TEPLON FILM 201/SILVER/ALUM FOIL COMPOSITE	GSC	.34	-13			BLANKET
TEFLON FILM 2 MIL	DUP	.22	-07			FILM
TEMP-PLATE 240/ROD	DUP	.90	-27			BLANKET
TEMP-PLATE 240/SCREEN	DUP	4.14	-30			FILM
TI ADDON FILM POLYPARABANIC ACID (H)	EXX	1.26	-00			FILM INSUL

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	MFR CODE	STML	%CURE	CURE TIME	STATUS	APPLICATION
TROYFELT S4-19-070-17P POLYESTER	TRO	.10	.04			THERMAL BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE	TRO	.33	.12			THERMAL BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE	TRO	.25	.08			THERMAL BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE	TRO	.04	.03	6.7H	E-5	THERMAL BLANKET
TROYTUF 1-9-0-195 AOM WOVEN DACRN FELT WHITE WASHED	TRO	.25	.04	115	AIR	THERMAL BLANKET
VELOSTAT CONDUCTIVE PLASTIC	CUM	.67	.21			FIELD
XR SODIUM PERFLUOROSULFONATE FILM	DUP	2.41	.00			FIELD

SECTION 7 - FOAMS

MATERIAL	MFR CODE	#TML	%CVM	CURE TIME	CUBE TENS	ATMOS	APPLICATION	
AAP-SI-H RF ABSORBER METALLIC/GRAPHITE/FOAM	AAP	.85	.04	2H	93	Air	PUT FOAM	
ABLESTIK 861-2/ECCOSPHERES SI AS 35/45 BM - WHITE	AAC	.78	.30	2H	93	Air	PUT FOAM	
ABLESTIK 861-2/ECCOSPHERES SI AS 55/45 BM - WHITE	ACC	.80	.30	2H	93	Air	PUT FOAM	
ABLESTIK F1200/20 FOAM/Z04 GLASS FIBERS	FBR	.93	.12	16d	121	Air	FOAM	
AF 3001/EPOXY FOAM	ACM	.94	.12	16d	177	Air	FOAM ADH	
AF 3001/EPOXY FOAM	AUC	.88	.10	2H	10	Air	FOAD PIPE	
AF 3001/EPOXY FOAM	AUC	1.15	.01	16H	100	Air	FOAD PIPE	
ANGEL FOAM 6818 CLEAN ROOM WIPE 6 HR METCH WASH	AUC	1.15	.01	16H	100	Air	FOAD INSULATION	
ARMAPLEX TUBULAR INSULATING SLEEVE BLACK FOAM	ACT	.81	.05	72H	96	Air	FOAD	
CHEN-POL 30156 1/2023 AS 1/1 BW POLYURETHANE FOAM	FRE	7.07	.03	24H	100	Air	FOAM	
CLARK FOAM 1234 FOLIUMETHANE - WHITE ALCOHOL WASH	BLA	.85	.03	8H	100	Air	FOAM INSULATION	
CONAFLEX EA-50 POLYURETHANE FOAM	UJC	.87	.10	1H	120	Air	FOAM	
CPR 17-2C POLYURETHANE FOAM	UJC	1.24	.19	6H	80	Air	FOAM	
CPR 17-2C POLYURETHANE FOAM	UJC	1.31	.33	16H	90	E-O	FOAM	
CPR 17-2C POLYURETHANE FOAM	UJC	1.97	.39	16H	75	Air	FOAM	
CPR 17-2C POLYURETHANE FOAM	UJC	1.26	.34	6H	85	Air	FOAM	
CPR 17-2C POLYURETHANE FOAM LOT N280	UJC	1.13	.96	24H	65	Air	FOAM	
CPR 9002-3 POLYURETHANE FOAM BLUE/GREEN	UJC	3.81	.12	1H	100	Air	FOAD	
CPR 9005-2 POLYURETHANE FOAM GREEN	UJC	4.34	.06	1H	125	Air	FOAD	
CPR 9005-2 POLYURETHANE FOAM GREEN	UJC	2.19	.26	0.93	72H	100	E-1	FOAD
CPR 9005-2 POLYURETHANE FOAM GREEN	UJC	7.24	.43	24H	66	E-4	FOAD	
CPR 9800-60 POLYESTER URETHANE FOAM 6#/CU FT	UJC	1.23	.12	16H	204	AIR	DAMPER	
DC 5370 SILICONE FCAN	DCC	.59	.09	72H	150	AIR	FOAM	
DER 661/2-PHENYLIMIDAZOLE WHITE SYNTACTIC FOAM	HIS	.72	.03	2H	100	AIR	FOAM	
DK 18-05/ECCOSPHERES SI AS 55/45 BM - BLUE	HIS	.77	.20	24H	93	AIR	FOAM	
EC COBOND SF 40 SYNTACTIC FOAM EPOXY RESIN	EMC	.23	.34	16H	80	AIR	PUT FOAM	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	1.96	.34	16H	80	AIR	PUT FOAM	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	1.88	.28	7D	80	E-4	PUT FOAM	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	.91	.27	16H	80	AIR	PUT FOAM	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	1.23	.35	16H	80	AIR	PUT FOAM	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	.93	.36	4D	80	E-4	FOAM DAMPER	
ECCOFAM EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	.40	.09	24H	100	AIR	FOAM DAMPER	
ECCOFAM EFF-14F SYNTACTIC FOAM	EMC	2.32	.99	5H	110	AIR	PUT FOAM	
ECCOFAM EFF-14F SYNTACTIC FOAM	EMC	.72	.30	8H	135	E-6	FOAD	
ECCOFAM EFF-14F SYNTACTIC FOAM - ORANGE EPOXY	EMC	.67	.29	24H	125	AIR	FOAD	
ECCOFAM EFF-14F SYNTACTIC FOAM - ORANGE EPOXY	EMC	.73	.23	2H	125	E-0	FOAM DAMPER	
ECCOFAM EFF-14F SYNTACTIC FOAM - ORANGE LOT 318	EMC	1.05	.56	114H	100	AIR	PUT FOAM	
ECCOFAM EFF-14F SYNTACTIC FOAM - ORANGE LOT 521	EMC	1.04	.52	24H	100	E-C	PUT FOAM	
ECCOFAM FS POLYURETHANE FOAM	EMC	4.98	.79	1H	100	AIR	STRUCTURAL FOAM	
ECCOFAM FS POLYURETHANE FOAM ETOH WASH X2	EMC	.72	.19	24H	100	AIR	STRUCTURAL FOAM	
ECCOFAM PP-14F WHITE	EMC	.81	.18	24H	100	AIR	STRUCTURAL FOAM	
ECCOFAM PP-14F WHITE	EMC	2.44	.24	24H	100	AIR	STRUCTURAL FOAM	
ECCOFAM PP-2	EMC	2.77	.39					

SECTION 7 -- FOAMS

MATERIAL	MR CODE	%ML	%CVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
ECOFOAM SH 14#/CU FT POLYURETHANE FOAM	EMC	1-0.4	.02	Foam			
ECOFOAM SH 2#/CU FT POLYURETHANE FOAM	EMC	1-0.59	.02	Foam			
ECONOORB 179 MICROWAVE ABSORBANT 4H	EMC	2-2.0	.14	Foam			
EHP-1 POLYURETHANE FOAM - BLACK	CAF	3-7.3	.27	AIR			
EHP-1 POLYURETHANE FOAM/BLUE NYLON PAINT	CAR	1-7.3	.83	AIR			
EDDM SILVER STARLE CLOSERD CELL FOAM/ADH FILM/FOIL	DAC	1-3.63	.73	AIR			
EARL 2795 HN 951 SYNTACTIC FOAM	HAC	.50	.02	24H	25	AIR	
ETHAFOAM 220 POLYETHYLENE FOAM 2#-2#/CU FT	FEI	.47	.03	Foam			
ETHAFOAM 400 POLYETHYLENE FOAM 6#/CU FT	FIW	.39	.08	Foam			
ETHAFOAM 600 POLYETHYLENE FOAM 6#/CU FT	FIW	.26	.04	Foam			
FLUOREEL 1062 FOAM	FIW	.24	.04	Foam			
FLUOROSILICONE CLOSED CELL EXTRUDED FOAM - BROWN	FIW	.38	.03	Foam			
PX 41 EPOXY FOAM SILVER-GRAY	FIW	.12	.03	16H	204	AIR	
FOAM CLOSED CELL POLYURETHANE MIL P26514 ETOH WASH	ACC	.76	.00	1H	100	AIR	
FOAM GRAY POLYESTER 2#/CU FT	EOF	.84	.00	24H	100	AIR	
FOAM 4E-10-34-1 FOLYIMIDE	EOF	.40	.02	Foam			
FOAM 4E-2-17-52-3 FOLYIMIDE	INT	.49	.05	DAMPER			
FOAM POLYURETHANE COPENCELL ROGERS 263	INT	.53	.05	TEARD LOUVER			
FOAM POLYURETHANE MILSHIRE CHEN	WIL	1-3.4	.42	8H	125	AIR	
FOAM POLYURETHANE EH1-00530	INT	.00	.00	Foam			
FOAM WIPES POLYURETHANE CLEAN ROOM WIPE	ACN	4-80	1-86	Foam			
FOAM WIPES POLYURETHANE CLEAN ROOM WIPE ALCOHOL EXTRACTION	TEX	3-5.5	.33	Foam			
FOAM/FILL RIGID POLYURETHANE FOAM FROM AEROSOL	TEX	2-1.53	.41	Foam			
INST-A-FOAM 2#/CU FT POLYURETHANE HONEYCOMB FILL	TON	1-1.84	.01	24H	120	AIR	
MICROFOAM FOAM FIBRICANT RESERVOIR FREON TA WASH	GPM	1-0.19	.05	Foam			
MICROFOAM B-302 CROSSLINKED POLYPROPYLENE FOAM WHITE	HIF	0-1.14	.41	Foam			
MONSANTO 1835 POLYETHER-URETHANE FOAM	HAV	2-8.2	.59	DAMPER			
MONSANTO 1835 POLYETHER-URETHANE FOAM	DON	3-1.3	.60	Foam			
MONSANTO 1835 POLYETHER-URETHANE FOAM	MON	1-2.5	.48	72H	120	AIR	
MONSANTO 1835 POLYETHER-URETHANE ISOPROP WASH	MON	.29	.08	Foam			
MONSANTO 1835 POLYETHER-URETHANE FOAM MELOH WASH	MON	.27	.04	24H	100	AIR	
MONSANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	MON	.42	.13	30H	100	AIR	
MONSANTO 3865-F POLYETHER-URETHANE FOAM	MON	3-0.5	.71	21H	100	AIR	
MONSANTO 3865-F POLYETHER-URETHANE FOAM	MON	.94	.90	Foam			
MONSANTO A206-1	MON	2-0.0	.97	14H	14H	AIR	
NO PCO G302 POLYURETHANE FOAM - WHITE	MON	3-3.0	.07	25H	65	AIR	
NO PCO H-402N WITH EVA COVER	MON	1-1.19	.01	14H	92	AIR	
NO PCO H-402N WITHOUT PVA COVER	MON	2-1.40	1-0.3	14H	92	AIR	
NO PCO J106 POLYURETHANE	MON	2-1.12	1-0.3	14H	92	AIR	
NO PCO J106 POLYURETHANE	MON	1-1.19	.02	4H	32	CO	
NYLAFILE P3/15 NYLON FOAM/15% GLASS FIBER	FBR	1-7.6	.03	16H	60	CO	
P-17 POLYURETHANE FOAM - OPEN CELL	GTR	.60	.13	Foam			
P-17 POLYURETHANE FOAM 0-.062 THICK WHITE	GTR	.77	.08	Foam DAMPER			
P-17 POLYURETHANE FOAM 0-.062 THICK WHITE	GTR	.49	.08	16H	100	AIR	

SECTION 7 --- FOAMS

MATERIAL	AFCR CODE	XTM	XCCM	CURE TIME	CURE TEMP	ADMS	APPLICATION
P-17 POLYURETHANE FOAM 0.186 THICK WHITE	SIR	1.11	.11	.07			
P-22 POLYURETHANE FOAM OPEN CELL	GTR	1.28	.07				
P-25 POLYURETHANE FOAM OPEN CELL	GTR	1.92	.04				
PBI FOAM 4#/CU FT SAMPLE 925-50 POLYBENZIMIDAZOLE	WCN	4.99	.01				
PERVEL ANLISTATIC EAT BLUE	PVL	5.37	.01				
PERVEL CONDUCTIVE FOAM BLACK HIGH DENSITY	PVL	1.77	.11				
PERVEL CONDUCTIVE FOAM BLACK LOW DENSITY	PVL	2.39	.11				
PERVEL 1H30A STATIC DISSIPATIVE CAT MAROON COLOR	PVL	10.25	.45				
POLYURETHANE FOAM BY DISSTOCKWELL RUBBER	SRC	1.53	.15				
POAON URETHANE FOAM 4#-0-12.5-16.33	ROG	1.99	.02				
PORON URETHANE FOAM 4701-0-20.25-16.33	ROG	1.35	.01				
PORON URETHANE FOAM 4701-0-1-20.25-16.33	ROG	4.35	.05				
PROFIL FOU/20 POLYPROPYLENE FOAM 20% GLASS FIBER	PBR	1.16	.04				
PROOF BOARD CLOSED CELL POLYURETHANE FOAM	GOL	1.14	.04				
REICHOLD POLYURETHANE FOAM	GOL	1.36	.30				
RFL 263 POLYURETHANE FOAM GRAY	REL	5.80	.17				
RFF 263 POLYURETHANE FOAM GRAY	RPC	1.79	.22				
ROGERS POLYURETHANE FOAM	ROG	1.53	.25				
RTV 760 SILICONE FOAM	GEC	8.51	.51				
SCOTT CHCASTAR-30-68 EPOXY FOAM	HED	1.55	.44				
SCOTT INDUSTRIAL FCAM POLYESTER URETHANE	SCT	1.91	.32				
SCOTT POLYESTER-URETHANE FOAM - TAN	SCT	4.46	.63				
SCOTT POLYESTER-URETHANE FOAM - TAN	SCT	4.63	.63				
SCOTT POLYESTER-URETHANE FOAM - TAN	SCT	4.81	.84				
SCOTT POLYESTER-URETHANE FOAM - TAN	SCT	4.88	.05				
SCOTT POLYESTER-URETHANE FOAM 100 PPI	SCT	3.96	.05				
SCOTT POLYESTER-URETHANE FOAM 100 PPI	SCT	3.69	.00				
SCOTT POLYESTER-URETHANE FOAM 100 PPI	SCT	3.22	.42				
SCOTT POLYESTER-URETHANE FOAM 60 PPI	SCT	1.81	.62				
SCOTT POLYESTER-URETHANE FOAM 60 PPI	SCT	2.53	.39				
SCOTT POLYESTER-URETHANE FOAM 60 PPI	SCT	2.33	.24				
SCOTT POLYESTER-URETHANE FOAM 60 PPI	SCT	4.48	.42				
SCOTT POLYETHER-URETHANE FOAM GRAY 2#/CU FT WASHED	SCT	1.59	.24				
SCOTT POLYETHER-URETHANE FOAM GRAY 2#/CU FT WASHED	SCT	1.69	.24				
SCOTT POLYURETHANE FOAM BLACK 41 PPI	SCT	1.55	.48				
SCOTT POLYURETHANE FOAM GREEN 100 PPI	SCT	2.14	.24				
SCOTT POLYURETHANE FOAM GREEN 100 PPI	SCT	2.81	.44				
SCOTT POLYURETHANE FOAM WHITE 100 PPI	SCT	2.57	.43				
SCOTT POLYURETHANE FOAM WHITE 100 PPI	SCT	2.83	.31				
SCOTT POLYURETHANE FOAM WHITE 100 PPI	SCT	2.02	.43				
SCOTT PYRELL FOAM POLYURETHANE GRAY FLAME RETARD	SCT	1.18	.37				
SCOTT PYRELL FOAM POLYURETHANE GRAY FLAME RETARD	SCT	1.72	.34				
SHUR-LOK SLE 3010 SYNTACTIC FOAM GREEN	SLK	1.13	.19				
		8H	12H				
		8H	25				
		8H	65				
		8H	65				
		8H	121				

SECTION 7 -- FOAMS

MATERIAL	MFR CODE	XTEL	XCVN	CURE TIME	CURE ATOMS	APPLICATION
SKYBOND R1 7271-01 FLEXIBLE POLYIMIDE FOAM	NON	.86	.52			FOAM
SKYBOND R1 7271-06 RIGID POLYIMIDE FOAM	MON	.31	.04			FOAM
SKYBOND R1 7271-12 RIGID POLYIMIDE FOAM	MON	.42	.01			FOAM
SOLINIDE R1 7271-18 RIGID POLYIMIDE FOAM	MON	.45	.01			FOAM
SOLINIDE TA-301 FLEXIBLE POLYIMIDE FOAM MIL F8709Q	IMI	.48	.01			DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	ELM	1.40	4-9.2	E-7		DAMPER
SPONGE AUEBER SILICONE MIL ZZ-R-65 LED	ELM	2.74	1-6.0	24H	12.5	DAMPER
STANTHANE 817C-2 FORMERLY CPR 17-2C	GRC	.83	.40			FOAM
STANTHANE 817C-2 FORMERLY CPR 17-2C	ERP	1.78	.00	12H	66	AIR
STANTHANE 817C-2 FORMERLY CPR 17-2C	ERP	1.32	.00	4H	10.5	AIR
STATIC CONTROL TABLE MAT 8210 BROWN VINYL/FOAM	HAN	1.37	.01	2H	12.0	AIR
SEPAANOFOAM G-306 6.4/CU FT WHITE	SSC	.87	.06	23-6.6	2.5	STATIC CONTROL
STYCAST 1090-SI/24IV AS 100/23 BW EPOXY FOAM	EBC	3.44	.10	4H	6.5	AIR
STYCAST 1095/1 AS 100/12 BW EPOXY FOAM	EBC	.36	.02	16H	6.5	AIR
STYROFOAM F30/20 ECYSTYRENE FOAM/20% GLASS FIBER	FBR	.26	.02	24H	12.5	AIR
SYNTACTIC FOAM WHITE EPOXY/ECCOSPHERES AS 40/60 BW	DOV	.62	.02			SUN SHEL
TENNECO PO 502 URETHANE FOAM WHITE 1.8#/CU FT	HOT	.54	.02			FOAM
TE NNECO 1194 URETHANE FOAM GREEN 3.9#/CU FT	TEN	5.66	2-0.2			FOAM
TJ - 1000 SYNTACTIC FOAM WHITE	HYS	2.14	.14	90M	12.6	PUFFING FOAM
TJ - 1000 SYNTACTIC FOAM WHITE	HYS	1.40	.14	24H	6.5	PUFFING FOAM
UNITED FOAM 5010 MIL P26514 GRAY TYPE I ALCOHOL WASH	UNF	1.17	.09	10H	1.0	AIR
UNITED FOAM 5010 MIL P26514 GRAY TYPE I CLASS II GA	UNF	4.33	.51	6H	12.1	AIR
US ALANE E 1723 A/B AS 100/85 BT/LITHIUM FLUORIDE	UNP	2.44	.24	24H	9.0	E-6
VELOFOAM 1901 BLACK	MAN	5.45	.24	24H	25	AIR
VITON 05-2154 CLOSED CELL EXTRUDED FOAM - GRAY	INR	3.91	.29	16H	20.4	CLOUD FOAM
VOLARA FOAM 16L204 RIGID POLYURETHANE FOAM 4#/CU FT	VOL	3.80	.26			SUN SHEL
VULTA 16L204 RIGID POLYURETHANE FOAM 4# ETOH WASH	GLC	1.77	.02	25H	10.0	FOAM
XN 3529/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM PINK	AMC	2.51	.01	2H	12.5	AIR DAMPER
XN 3529/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM PINK	AMC	.80	.00	8H	6.6	E-3
XN 3529/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM PINK	AMC	.82	.01	8H	10.0	AIR DAMPER
ZEREFIL F700/20 VINYL FOAM/20% GLASS FIBERS	FBR	.88	.02	8H	6.6	E-3
ZEREFIL F700/20 VINYL FOAM/20% GLASS FIBERS	FBR	.21	.00	2H	10.0	AIR DAMPER

SECTION 8 -- GREASES LUBRICANTS

MATERIAL	MR CODE	%TML	%CVCM	CURE TIME	ATMUS	APPLICATION
AERODAG G COLLOIDAL GRAPHITE ISOPROPYL ALCOHOL	ACAH	1.78	.14	24H	AIR	LUBRICANT
AERODAG G COLLOIDAL GRAPHITE ISOPROPYL ALCOHOL	ACAH	2.05	.04	24H	AIR	LUBRICANT
AERODAG M COLLOIDAL MOS2/ISOPROPYL ALCOHOL	ACAH	4.97	.19	47.4H	AIR	LUBRICANT
APIEZON C OIL VACUUM DEGassed	BID	81.19	47	1d	E-2	GAS/SL
APIEZON H HYDROCARBON DEGassed	BID	.25	.02			GAS/SL
APIEZON L GREASE VACUUM DEGassed	BID	.34	.01			GAS/SL
APIEZON M GREASE	BID	.08	.02			GAS/SL
APIEZON N GREASE	BID	.76	.02	24H	AIR	LUBRICANT
APIEZON T GREASE	SPI	.27	.02			GAS/SL
BLACK MAGIC MOLY SPRAY/FOIL - AEROSOL MQS2	BOC	.03	.02			LUBRICANT
BRAYCO 813 CLEAR OIL BATCH DLM3	BOC	.07	.02			LUBRICANT
BRAYCO 815Z CLEAR OIL BATCH DLD1 WHITE	BOC	.07	.02			LUBRICANT
BRAYCOTE 3L-38 GREASE WHITE	BOC	.04	.01	24H	AIR	LUBRICANT
BRAYCOTE 3L-38-MS GREASE WHITE	BOC	.09	.04			GAS/SL
BRAYCOTE 3L-38-RP GREASE WHITE	BOC	.02	.01			LUBRICANT
BRAYCOTE 3L-38-ZN GREASE WHITE	BOC	.24	.13			GAS/SL
BRAYCOTE 803 GREASE WHITE	BOC	.52	.09	20H	AIR	LUBRICANT
BRAYCOTE 8065 GREEN TIE AEROSOL COATING/E	CIP	.17	.07			GAS/SL
C6-1103 SILICONE GREASE OPTICAL COUPLING COMPOUND	DCC	.86	.02			GAS/SL
DR-I-SLIP POWDERED LUBRICANT - AEROSOL	MM	10.73	4.69			LUBRICANT
DAI-LIP E 82 FLUOROSILICONE LUBRICATING GREASE	MM	6.53	2.41			LUBRICANT
E-COSLIP TH-24 LCW FRICTION EPOXY	EMC	.40	.00	1H	60	SEAL LUBE
EKKCEL WB-25 AROMATIC POLYESTER/TPE BLEND TAN	CRB	.01	.00			SOLID LUBE
ENVEX 1000	ROG	1.94	.01			BEARING/HATL
ENVEX 1000	ROG	1.74	.01	24H	AIR	BEARING/HATL
ENVEX 1000X POLYIMIDE	ROG	1.83	.01	24H	AIR	BEARING/HATL
ENVEX 1115	ROG	1.67	.01	24H	AIR	BEARING/HATL
ENVEX 1228	ROG	1.29	.01	24H	AIR	BEARING/HATL
ENVEX 1228	ROG	1.29	.00	24H	AIR	BEARING/HATL
ENVEX 1315	ROG	1.25	.00	24H	AIR	BEARING/HATL
ENVEX 1315	ROG	2.03	.00	24H	AIR	BEARING/HATL
FLUOKONG DAY FILM LUBRICANT AEROSOL	TBT	15.36	.92	24H	AIR	LUBRICANT
FLUOKONG DAY FILM LUBRICANT AEROSOL DRY FILM LUBRICANT/F	TBT	15.36	.7D	25	AIR	LUBRICANT
FLUOKONG 500 MICA FILLED TFE SILICONE LUBE OIL	CHE	9.49	3.09	7D	AIR	BEARING/HATL
GE 1147 METHYL ALKYL SILICONE LUBE OIL	PPC	0.05	.00			UL
HI-VAC GREASE	GBC	4.28	2.41			LUBRICANT/GREASE
HI-VAC GREASE 970V SILICONE	DCC	1.52	.34			LUBRICANT/GREASE
JOINT COMPOUND SOCCNY MOBIL TEMP 1 GREASE	DCC	7.73	.22			GAS/SL
KRYTOX 143 AB LUBRICATING OIL DE VOL 143C	DUP	3.82	1.74			OIL
KRYTOX 143 AX FLUOROALKYL POLYETHER LUBRICATING OIL	DUP	28.54	5.71			LUBRICANT
KRYTOX 240 AC FLUOROCARBON GREASE (143AC OIL/TEFLON)	DUP	21.72	3.99			LUBRICANT FILM
LUBRI-BONE K SOLID FILM LUBRICANT MOS2/F	EPI	1.38	.12	24H	AIR	LUBRICANT FILM
LUBRI-FILM N 630A PASTE GRAY	EPI	2.90	1.19	25	AIR	LUBRICANT
LUBRI-KOTE G-N PASTE GRAY	FIS	31.00	4.59	20	AIR	LUBRICANT
	DCC	51.76	4.82			LUBRICANT/GREASE

SECTION 8 -- GREASES LUBRICANTS

MATERIAL	AFR CODE	XMTL	XCVN	CURE TIME	CURE ATMS	TEMP	APPLICATION
HOLYKOTE GREASE HS-122 FLUOROCARBON DRY LUBRICANT - AEROSOL	DCC	3.20		1.25			LUBRICANT
NYE 182 SPECIAL OIL FOR BEARING LUBRICATION	HSI	13.19		6.76			LUBRICANT
92-3067 OPTICAL COUPLING COMPOUND	NYE	17.07		11.46			OIL
RO YCO 43 GREASE FEF MIL G4343B	DCC	17.07		11.46			RELEASE
AT DUR-OIL 4300 REINFORCED TEFILON PTFE	HLC	85.13		15.34			LUBRICANT
RJLON A TEFILON FILLED BEARING MATERIAL	ROG	*01		*00			BEARING MTL
RJLON B TEFILON FILLED BEARING MATERIAL	DIX	*00		*00			BEARING MTL
RJLON C TEFILON FILLED BEARING MATERIAL	DIX	*00		*00			BEARING MTL
AU LON J D TEFILON FILLED BEARING MATERIAL	DIX	*10		*91			BEARING MTL
RJLON LD TEFILON FILLED BEARING MATERIAL	DIX	*00		*00			BEARING MTL
SILVER 123 TEFILON FILLED BEARING MATERIAL	DIA	*00		*00			BEARING MTL
TEXACO RB PREMIUM IMP GREASE	CFC	2.48		*62			BEARING MTL
TRANSLUBE 20204 LUBRICANT FILM	TXI	37.82		22.77			LUBRICANT
TRANSLUBE 20204 LUBRICANT FILM	JSP	9.13		25.88			LUBRICANT FILM
VE SP EEL SP-21-D-1 POLYIMIDE RESIN X	JSP	5.29		2.27			SOLID LUBE
VE SP EEL SP-21-D-1 POLYIMIDE RESIN X	DUP	*48		*00			SOLID LUBE
VE SP EEL SP-21-D-1 POLYIMIDE 15% GRAPHITE AS 60/40 BN	DUP	*58		*01			SOLID LUBE
VE SP EEL SP-22-D-1 POLYIMIDE 15% GRAPHITE AS 60/40 BN	DUP	*57		*01			SOLID LUBE
VE SP EEL SP-3 POLYIMIDE 15% 402 FORMERLY SP-3 1-D-1	DUP	*54		*01			SOLID LUBE
WDAK 1000 FLUOROTELMERA	DUP	*67		*08			LUBRICANT

SECTION 9 -- LACING TAPE & CORD CABLE TIES

MATERIAL	MPN CODE	XTML XCVCM	CURE TIME	CURE ATmos	TEMP	APPLICATION
BAR LCK CABLE TIE NYLON 66	DNN	2.69	.01			CABLE FILE
BEN-HAR HT-30 LOC E SERIES LACING TAPE	BHH	2.98	.30			LACING TAPE
CABLE CLAEP TAU 4105HU-07HB RED RUBBER SLEEVE	TAN	2.48	.23			CABLE CLAMP
CLAMP WIRE BUNDLE TA 11C62 D710 FIBERGLASS/SILICON	TAN	.16	.21	AIR		CLAMP
CLAMP WIRE BUNDLE TA 11C62 WD10 FIBERGLASS/SILICON	TAN	.14	.29	AIR		CLAMP
DIAL CORD STUR-D-DIAL DACKN 164 WHITE	GBE	.48	.05			DIAL CORD
FASTRAPS SERIES 60 NYLON CABLE TIE	DIN	.98	.03			CABLE TIE
LACING CORD DACKN 50D-TOP17CW - WHITE	HMB	.3-2.4	.76			CORD
LACING CORD GUDELACE 20 BLACK NYLON - WAXED	WFC	1.1-3.27	.54			CORD
LACING CORD LC-136 BLACK	ANC	8.3-9	.95			CORD
LACING TAPE A-60-E NYLON	HMB	2.27	.38			CORD
LACING TAPE A-60-E POLYESTER	HMB	3.83	.42			CORD
LACING TAPE DA-BURN 2047 DACKN - COATED	DAD	.11-1.5	.64			CORD
LACING TAPE DA-BURN 20D-TGX - WHITE	WFC	.11-1.3	.04			CORD
LACING TAPE DA-BURN 2077-476 TEFLOON GLASS METOH WASH	DIN	.19	.04			CORD
LACING TAPE E 77-9-1075 TEFLOON GLASS	DIN	.07	.02			CORD
LACING TAPE E 779-1075 TEFLOON GLASS	DIN	.70				CORD
LACING TAPE E 779-122 TEFLOON GLASS	DIN	.42	.46			CORD
LACING TAPE E 779-303 TEFLOON GLASS	DIN	.46	.57			CORD
LACING TAPE E 779-680 TEFLOON GLASS	DIN	.99	.26			CORD
LACING TAPE E 779-680 TEFLOON GLASS	WFC	1.02	.12			CORD
LACING TAPE FIR-LACE-R 21DR DACKN/VINYL IMPREG	GBE	13.27	.6			CORD
LACING TAPE GE NYLON	HMB	7.29	.21			CORD
LACING TAPE GE POLYESTER	HMB	1.00	.02			CORD
LACING TAPE GUDE-NYLACE 18B NYLON/NYLON WHITE	GBE	2.425	.19			CORD
LACING TAPE GUDE-NYLACE 18B NYLON/NYLON WHITE	GBE	2.425	.19			CORD
LACING TAPE GUDE-NYLACE 18D96 DACKN/SILICONE BLACK	GBE	.52	.15			CORD
LACING TAPE GUDE-NYLACE 18D96 DACKN/SILICONE BLACK	GBE	.52	.15			CORD
LACING TAPE GUDE-SPACE 18D96 DACKN/SYN RUBBER BLACK	GBE	.40	.18			CORD
LACING TAPE GUDE-SPACE 18D96 DACKN/SYN RUBBER WHITE	GBE	.40	.18			CORD
LACING TAPE GUDE-SPACE 18D96 DACKN/SYN RUBBER WHITE	GBE	.72	.21			CORD
LACING TAPE GUDE-SPACE 18D96 DACKN/SYN RUBBER WHITE	GBE	.72	.15			CORD
LACING TAPE GUDE-SPACE 21D96 DACKN/SYN RUBBER WHITE	GBE	.73				CORD
LACING TAPE GUDE-TEMP 18P NOMEK POLYCARBONATE COAT	GBE	2.78	.04			CORD
LACING TAPE GUDE-TEMP 723 NOMEK WITHOUT FINISH	GBE	2.39	.05			CORD
LACING TAPE GUDE-TEMP 723H NOMEK RUBBER FINISH	GBE	2.19	.12			CORD
LACING TAPE GUDE-TEMP 723S NOMEK/SILICONE FINISH	GBE	2.19	.12			CORD
LACING TAPE GUDE-LACE 18 NYLON BRAID-WAXED - NATURAL	GBE	7.72	.95			CORD
LACING TAPE GUDE-LACE 21H NYLON BRAID-SYN RUBBER	GBE	2.216	.23			CORD
LACING TAPE GUDE-LACE 22H NYLON BRAID-NATURAL	GBE	1.53	.19			CORD
LACING TAPE HT30VR NOMEK/TEFLON COAT/SIN RUBBER SAT	BHN	4.64	.06			CORD
LACING TAPE HT3-38 POLYESTER	HMB	1.89	.18			CORD
LACING TAPE NYLON POLYESTER	HMB	6.60	.178			CORD
LACING TAPE NOMEK EGED 1342VC VITON COATED	GBE	3.92	.17			CORD
LACING TAPE NOMEK SCOURRED LOT 13278	GBE	2.94	.09			CORD
LACING TAPE NOMEK SCOURRED LOT 13278	GBE	3.13	.14			CORD
LACING TAPE NOMEK SCOURRED LOT 13278	GBE	2.61	.03			CORD
LACING TAPE NOMEK SCOURRED LOT 13278	GBE	1.77	.18			CORD

SECTION 9 --- LACING TAPE & CORD CABLE TIES

MATERIAL	MR CODE	XTHL	%CVC	CURE TIME	CURE TEMP	STATUS	APPLICATION
LACING TAPE PBI STYLE 1330 UNCOATED	GDE	9.08	.02			LACING TAPE	
LACING TAPE PBI STYLE 1330 VC VITON COATED	GDE	6.98	.02			LACING TAPE	
LACING TAPE SR POLYESTER	HMB	1.21	.18			LACING TAPE	
LACING TAPE STUR-D-LACE 18DB DACHON/NYLON WHITE	GDE	1.42	.18			LACING TAPE	
LACING TAPE STUR-D-LACE 18DH SCOURED LOT 30378	GDE	.28	.03	15H	149	AIR	
LACING TAPE STUR-D-LACE 18DH SCOURED LOT 30378	GDE	.51	.01			LACING TAPE	
LACING TAPE STUR-D-LACE 18DP DACHON/POLYCARBONATE	GDE	2.17	.27			LACING TAPE	
LACING TAPE STUR-D-LACE 18DP DACHON SCOURED PROD SAMPLE	GDE	1.14	.27			LACING TAPE	
LACING TAPE STUR-D-LACE 18DU DACHON LEACHED GDE	GDE	1.13	.02			LACING TAPE	
LACING TAPE SUPER-GUDE SPACE DET-H SCQURED DACRON	GDE	.41	.02			LACING TAPE	
LACING TAPE SUPER-GUDE-SPACE DET-H SCQURED DACRON	GDE	.38	.04			LACING TAPE	
LACING TAPE TEFLON 90103A FIBERGLAS/TEFLON WHITE	GDE	.43	.04			LACING TAPE	
LACING TAPE TEMP-LACE H231H TEFLON BRAID/SYN RUBBER	GDE	.36	.05			LACING TAPE	
LACING TAPE TEMP-LACE H256H TEFLON BRAID/SYN RUBBER	GDE	.24	.05			LACING TAPE	
LACING TAPE TEMP-LACE H256H TEFLON OIL BRAID/NO FIN	GDE	.24	.05			LACING TAPE	
LAVING TAPE FG-40 FIBERGLAS/TEFLON COAT	BHE	.50	.02			LACING TAPE	
NYLON 6 BLACK CABLE CLAMP - WECKER	WCK	.84	.00	24H	125	AIR	
PAN-TY CABLE MOUNT	PAN	.63	.94			CABLE CLAMP	
PAN-TY CABLE TIE	PAN	.44	.94			CABLE TIE	
PAN-TY CABLE TIE LIGHT BROWN	PAN	.21	.94			CABLE TIE	
PAN-TY CABLE TIE HALAR MARCON	PAN	1.73	.92			CABLE TIE	
PAN-TY CABLE TIE NYLON NATURAL	PAN	.08	.02			CABLE TIE	
SECUR-A-TIE CABLE TIE NYLON	DIN	.93	.01			CABLE TIE	
STA-STRAP ST CABLE TIE NYLON	DIN	.25	.00			SUPPLY RETAINER	
TU-101 NYLON WIRE SUPPORT	TEST	1.59	.00			CABLE CLAMP	
TU-102 TY-RAP NYLON CABLE RETAINER	TEST	1.38	.02			CABLE CLAMP	
TU-105 A WIRE CLIP ADHESIVE CLAMP	TEST	6.66	.01			ADHESIVE CLAMP	
TU-106 NYLON CABLE CLAMP	TEST	1.05	.01			CABLE CLAMP	
TU-1112 TY-RAP NYLON CABLE CLAMP	TEST	1.61	.02			CABLE CLAMP	
TU-1112 TY-RAP NYLON CABLE CLAMP	TEST	1.02	.00			CABLE CLAMP	
TU-818 TY-RAP NYLON CABLE CLAMP	TEST	1.35	.02			CABLE CLAMP	
TU-828 TY-RAP NYLON MOUNTING PLATE	TEST	2.15	.02			CABLE CLAMP	
TU-92 TY-RAP NYLON CABLE CLAMP	TEST	1.30	.01			DOUBT CLAMP	
TIE CORD E 761-1330 TFE TEFLON/GLASS	DIN	1.18	.00			DOUBT CLAMP	
TIE CORD E 761-688 TFE TEFLON/GLASS	DIN	1.15	.00			DOUBT CLAMP	
TP-2 PANDUIT NYLON SUPPORT	DIN	.37	.01			DOUBT CLAMP	
TY LINE-2 LINING NYLON DIAH 3 PLY	DUD	.09	.02			DOUBT CLAMP	
TY 254 TY-RAP NYLON CABLE TIE	TBT	2.94	.04			DOUBT CLAMP	
TY 254 TY-RAP NYLON CABLE TIE	TBT	1.74	.05			DOUBT CLAMP	
TY 307 TY-RAP NYLON CABLE TIE	TBT	.10	.00			DOUBT CLAMP	
TY 34N TY-RAP NYLON CABLE TIE	TBT	.03	.00			DOUBT CLAMP	
TY 46N TY-RAP NYLON CABLE TIE	TBT	2.49	.02			DOUBT CLAMP	
TY 46N TY-RAP NYLON CABLE TIE	TBT	2.33	.02			DOUBT CLAMP	
TY 46A TY-RAP NYLON CABLE TIE	TBT	1.90	.00			DOUBT CLAMP	
TY 5 TY-RAP ZYTEL 103 CABLE TIE	TBT	1.24	.01			DOUBT CLAMP	
TY 523M KYNAR CABLE TIE	TBT	2.49	.02			DOUBT CLAMP	
TY-RAP AS 33-7 NYLON LACING TAPE	TBT	1.85	.02			DOUBT CLAMP	
TY-RAP AS 33-7 NYLON LACING TAPE	TBT	1.83	.03			DOUBT CLAMP	
		2.60	.03			DOUBT CLAMP	

SECTION 9 -- LACING TAPE & CORD CABLE TIES

MATERIAL	MFG CODE	%MIL	KVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
TYB 23M TY-RAP NYLON CABLE TIE	TBT	1.81	.05	16d	100	AIR	CABLE TIE
TYB 23M TY-RAP NYLON CABLE TIE	TBT	1.85	.06	24H	125	AIR	CABLE TIE
TYB 24M TY-RAP NYLON CABLE TIE	TBT	2.06	.04	24H	125	AIR	CABLE TIE
TYD 25M TY-RAP NYLON CABLE TIE	TBT	1.98	.04	24H	125	AIR	CABLE TIE
TY TON T18R-9 CABLE TIE	TYT	3.43	.03				CABLE TIE

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	MPN CODE	%TML	%CVCM	CURE TIME	CURE TEMP	ATDS	APPLICATION
ABALDITE MY750/HY219/DE219/TEXYO GLASS 460 BALL BEARING CAGE PHENOLIC - RETRACTED	CIB	.55	.01	30H	25	AIR	LADINATE SUBJECT CIRCUIT BOARD
CIRCUIT BOARD COMPOSITE NEMA G10 MICA/CE 115 _o	SYA	.85	.01				
COAST EPOXY PREPREG F161-83-1PU8/20	GDC	.48	.01	2H	163	AIR	AIR FILM
COAST EPOXY PREFREG F161-83-108-B	CMS	.66	.01	1H	149	AIR	AIR FILM
COAST EPOXY/GLASS FIBERGLASS LAMINATE - POTTING FORMS	CMS	.46	.01	2H	204	AIR	LADINATE
EPOXY/FIBERGLASS ECON C/LINDE CONVAIR GRAPHITE/EPOXY/SI203/ALUMINUM CYCCH 950-S2 EPOXY/GLASS	GDC	.29	.01	165 _o	163	AIR	COMPOSITE SUBJECT
GYCOM 985-T300 GRAPHITE/EPOXY	ACC	.49	.01	1H	66	B-2	SUBJURAL
F-720 EPOXY/FIBERGLASS LAMINATE - POTTING FORMS	ACC	.49	.01	1H-5H	138	ET-2	STRUCTURAL
EPOXY/FIBERGLASS ECON C/LINDE CONVAIR GRAPHITE/EPOXY/SI203/ALUMINUM CYCCH 950-S2 EPOXY/GLASS	SP1	.57	.01	2H	121	PSI	STRUCTURAL
GYCOM 985-T300 GRAPHITE/EPOXY	PLI	.54	.04		177	PSI	STRUCTURAL
FIBERGLASS CLUTCH PRE-PREG A10-104-75	PLC	.20	.05				LADINATE
FIBERGLASS HY-E-10761 EPOXY GRAPHITE LAMINATE	PLC	.88	.03	90 _o	121	AIR	LADINATE
FIBERGLASS HY-E-1334A EPOXY/GRAFITE LAYUP	FIB	.50	.00	2H	177	E-3	LADINATE
FIREBAK 600 EPOXY/FIBERGLASS	FIB	.81	.01	2H	177	E-3	LADINATE
PLEXASALP FLEXAFLAME/FIBERGLASS	FAS	.64	.03	90 _o			LADINATE
PLEXASALP FLEXAFLAME/FIBERGLASS	FAS	.42	.01				LADINATE
GOODYEAR GRAPHITE FIBER EPOXY COMPOSITE/EM 1000	GAC	.55	.04				STRUCTURAL
GRAPHITE FIBER REINFORCED POLYMER HONEYCOMB	GAC	.82	.05	24H	121	E-3	STRUCTURAL
GT-5500 COPPER FOIL/ULVAN LAMINATE ONE SIDE	HER	.48	.04	6H	149	E-4	STRUCTURAL
GY-70/4-30 GRAPHITE EPOXY COMPOSITE	GTS	.05	.04				STRUCTURAL
GY-70/508 GRAPHITE EPOXY COMPOSITE	GDC	.46	.01	2H	177	AIR	STRUCTURAL
GY-70/5209 GRAPHITE EPOXY COMPOSITE	WCN	.53	.01	2H	177	AIR	STRUCTURAL
HEXCEL F153 EPOXY GLASS PREPREG	WCN	.49	.01	2H	177	PSI	STRUCTURAL
HEXCEL F174-120 GLASS CLOTH/POLYIMIDE PRE-PREG	HEX	.18	.00	7H	177	PSI	STRUCTURAL
HNL 7 LINEAR POLYACRYLICATE LAMINATE	FOC	.40	.00				LADINATE
HONEYCMB HMF 76/34 EPOXY/GRAPHITE %/FN73M ADH	FIB	.90	.01				LADINATE
HONEYCMB SPECIAL COMPOSITE EPON 828/FIBERGLASS/PLUS	KAD	1.62	.01				STRUCTURAL
HR-H-10 NYLON/PHENYLIC HONEYCOMB CORE	1D	1.27	.01				HONEYCMB
JF-1006 CHLORONATE 19/70/30	HEX	2.74	.01				MOLD COMB
KEVLAR 120/NARMAXC 85197 STRUCTURAL COMPOSITE	IN	1.64	.01				LADINATE
KEVLAR 49/FR 8601 FESTIN PRE-PREG	TRW	1.33	.00	45 _o	121	PSI	LADINATE
KFL 4036 ACETAL/30% GLASS/15% TPE	FBC	5.1	.20	2H-5d	121	PSI	LADINATE
KL 4536 ACETAL/30% GLASS/15% TPE/SILICONE	LNP	.26	.02				P&E, PREG
KL 4540 ACETAL/20% TPE/SILICONE	LNP	.35	.02				STRUCTURAL
LAMINATE AL-30-G3 POLYIMID/Glass - BROWN	LNP	.53	.02				STRUCTURAL
LAMINATE AL-3137 FR TYPE FL-GP W/O COPPER	ATL	.63	.01				LADINATE
LAMINATE AL-3247 FR THIN W/O COPPER	ATL	.29	.00	1H	177	AIR	LADINATE
LAMINATE AS-4/19C8 EPOXY/GRAFITE	UR	.11	.01	6H	135	PSI	LADINATE
LAMINATE AS-4/19C8 EPOXY/GRAFITE	HER	.19	.01	2H	121	PSI	LADINATE
LAMINATE BL-2 EPOXY/FIBERGLASS W/O COPPER	GEC	.25	.01	149	PSI	LADINATE	
LAMINATE E33 NATURAL TYPE GF CURIKAR 5104/Glass/FR4	PLC	.62	.00	1H	177	PSI	LADINATE
LAMINATE GE339 HES EPOXY/GRAFITE TUBE	PLC	.54	.03	6H	177	PSI	SUBJURAL
LAMINATE GNC 608-1-3-1 KAPTON COOPER FOIL/KAPTON	GNC	.19	.02				LADINATE
LAMINATE GNC 608-1-3-1 KAPTON COOPER FOIL/KAPTON	SYN	.11	.04				STRUCTURAL
LAMINATE GNC 608-1-3-1 KAPTON COOPER FOIL/KAPTON	SYN	.19	.01	8H	100	AIR	STRUCTURAL

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	FR4 CODE	RTM CODE	SCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
LAMINATE CP-109A CM CHOPPED MOLDED CARBON PHENOLIC	HAV	4-.75	.00	4H	149	AIR	LADINATE
LAMINATE CP-109A 2L TAPER TRAPPED CARBON PHENOLIC	EMM	.3-.6	.00	4H	149	AIR	LADINATE
LAMINATE CUCLAU TEFILON/GLASS W/FORTIN ECO31PU3 ADH	EMM	.0-.6	.00	4H	177	AIR	LADINATE
LAMINATE CUSTOM LAY CO.	EMM	.0-.2	.00	4H	177	AIR	LADINATE
LAMINATE CUSTOM EPOXY FIBERGLASS	CUA	.0-.2	.00	4H	177	AIR	LADINATE
LAMINATE EPOXY FIBERGLASS ASSY	KOL	.0-.4	.02	2H	49	PSI	PC BOARD
LAMINATE EPOXY FIBERGLASS LOT 79-4309 (MT)	KER	1.04	.023	6H	74	PSI	BONDED
LAMINATE EPOXY/FIBERGLASS LOT 79-4835 (MT)	FEA	.94	.17	24	74	PSI	NON FLAMM
LAMINATE EPOXY/FIBERGLASS TYPE I, CLASS E GRADE 2	USA	.28	.01				LADINATE
LAMINATE EPOXY/FIBERGLASS UVE 749/DY 19/1272	USA	.93	.00				LADINATE
LAMINATE EPOXY/GLASS UVE MIL-P-13949/44 MULTILAYER	NUP	.33	.01				PC BOARD
LAMINATE EPOXY/GLASS UNIGLASS STYLE 181	UNI	.30	.00	2H	131	AIR	LADINATE
LAMINATE EPSILAN 10 NICKEL WIRE SUBSTRATE W/O COPPER	DMN	.04	.00				LADINATE
LAMINATE FRG 65m 26-11 EPOXY/FIBERGLASS/FIRE RETARD	MMF	.13	.00				LADINATE
LAMINATE FRG/PK 4 FC BOARD	MMF	.19	.00				LADINATE
LAMINATE FRG/PK 39C2/1B3B EPOXY/GLASS MULTILAYER	MMF	.32	.01				LADINATE
LAMINATE FRG/PK 250C2/2A1B EPOXY/FIBERGLASS 2 SIDE	MMF	.51	.01				LADINATE
LAMINATE FR-4 G-11 EPOXY/FIBERGLASS	ATL	.31	.01				LADINATE
LAMINATE FR-16-1-63-11E6/20 EPOXY/FIBERGLASS	MCA	.31	.01				LADINATE
LAMINATE FR-10 BLACK EPOXY FIBERGLASS	HEX	.27	.01				LADINATE
LAMINATE G-10 EPOXY GLASS	ATL	.34	.01				LADINATE
LAMINATE G-10 TC MIL P13949 - NORPLATE	NCA	.48	.01				LADINATE
LAMINATE G-10 TFC MIL P13949 - WESTINGHOUSE	DOE	.93	.01				LADINATE
LAMINATE G-10 405 EPOXY/FIBERGLASS	WEC	.42	.00				LADINATE
LAMINATE G-11 GEC-11 EPOXY/GILFGLASS	SYN	.47	.03				LADINATE
LAMINATE GEE MIL P18117 EPOXY/FIBERGLASS	GEC	.59	.00				LADINATE
LAMINATE GEE MIL P18117 BLUE EPOXY/FIBERGLASS	GEC	.43	.00				LADINATE
LAMINATE GEE-MACO ASGIN EPOXY/FIBERGLASS - BLACK	GEC	.52	.02				PURGING CUP
LAMINATE GEE-SILICONE GLASS CIC1H/SILICONE WHITE	GEC	.61	.01				LADINATE
LAMINATE G10 WESTINGHOUSE 65625 FR-4 FLAME RETARDANT	NEC	.14					LADINATE
LAMINATE HONEYCOMB KEVLAR/EPOXY/FM 123-2	PARK	.34	.00	1H	121	PSI	STRUCTURAL
LAMINATE GDC	.88	.10		1H	121	PSI	LADINATE
LAMINATE GDC	.29	.00	85s	177	PSI	PSI	LADINATE
LAMINATE HME	.01	.00	2H	177	AIR	LADINATE	
LAMINATE HMM	.05	.01	90d	166	PSI	LADINATE	
LAMINATE DUP	.39	.01					LADINATE
LAMINATE GEV	.33	.02					LADINATE
LAMINATE GEV	.79	.02					LADINATE
LAMINATE GEV	.94	.06					LADINATE
LAMINATE GDC	2.10	.01	85s	121	PSI	PSI	LADINATE
LAMINATE K-6098 TEFILON/FIBERGLASS/3M	MM	.01	.00	2H	177	AIR	LADINATE
LAMINATE K-6098 1/AF 46 FILM ADHESIVE	MM	.05	.00	2H	177	AIR	LADINATE
LAMINATE KAPTON ENCAPSULATED COPPER	DUP	.39	.01	90d	166	PSI	LADINATE
LAMINATE KEVLAR/EPOXY	GEV	.33	.02				LADINATE
LAMINATE KEVLAR/EPOXY	GEV	.79	.02				LADINATE
LAMINATE KEVLAR/EPOXY	GEV	.94	.06				LADINATE
LAMINATE KEVLAR/EPOXY	GDC	2.10	.01	85s	121	PSI	LADINATE
LAMINATE LIB501 FLEXIBLE W/COPPER	MM	.43	.01	17	23	AIR	LADINATE
LAMINATE MICAPLY EG 802 UNCLAD	NCA	.41	.02	90d	171	PSI	LADINATE
LAMINATE MICAPLY EG 402 UNCLAD	NCA	.91	.01				PC BOARD
LAMINATE MICAPLY PC 418T POLYIMIDE/FIBERGLASS PRE-PREG 8 LAYER	NCA	.62	.00				LADINATE
LAMINATE MICAPLY 162-11 EPOXY/GLASS PRE-PREG	NCA	.38	.03				LADINATE
LAMINATE MICAPLY 162-11/G-10 EPOXY/GLASS PRE-PREG	NCA	.44	.00	80M	163	PSI	LADINATE
LAMINATE MICAPLY 1C2-28M PR-4 EPOXY/GLASS PRE-PREG	NCA	.39	.02	1H	188	PSI	LADINATE

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	MPN	XTL	ACVCM	CURE TIME	CURE TEMP	ATDS	APPLICATION
	CODE						
LAMINATE MICAPLY 102-69-B STAGE PRE-PREG	NCA	2.1		1-39			LADDAE
LAMINATE MICAPLY 818T W/O COPPER GREEN	NCA	.36		00			LAMINATE
LAMINATE MICARTA 6550-22 LIGHT GREEN	WEC	.28		00			LAMINATE
LAMINATE MULTI-LAYER PER MIL P55 617 P 13 94 9	TCI	.32		00			LAMINATE
LAMINATE MUL-TIWIRE PC BOARD	KOL	.93		01			PC BOARD
LAMINATE N-105 EPOXY/GLASS PL-GP FR-4 W/O COPPER	NCO	.25		00			LADDAE
LAMINATE N-205 EPOXY/GLASS PL-GP FR-4 W/O COPPER	NCO	.24		01			LADDAE
LAMINATE N-3105 RESIN RICH FR-EPOXY/GLASS W/O COPPER	NCO	.39		00			LADDAE
LAMINATE N-4105 EPOXY/Glass FLEXIBLE GLASS W/O COPPER	NCO	.33		01			LADDAE
LAMINATE NARICO 32C3-120 EPOXY/GLASS	WCN	.32		00			LADDAE
LAMINATE NARICO 32C3-1581 EPOXY/GLASS	WCN	.47		00			LADDAE
LAMINATE NARICO 8517 EPOXY/GLASS	WCN	.23		00			LADDAE
LAMINATE NEMA FR-4C BY GE W/O COPPER GEC	SYN	.38		00			LADDAE
LAMINATE NEMA G-10 SEC 500E EPOXY/FIBER GLASS	SYN	.11		00			LADDAE
LAMINATE NEMA G10 WESTINGHOUSE 65M27-S-12 NO COPPER	WEC	.06		01			LADDAE
LAMINATE NEMA G10 WESTINGHOUSE 65M27-S-12 W/COPPER	WEC	.09		02			LADDAE
LAMINATE NEMA G7 GLASS FABRIC/SILICONE SYN	SYN	.12		02			LADDAE/RESIST
LAMINATE NEMA FR-4 W/SR1000 SOLDER RESIST FLA	AUG	.14		02			LADDAE/RESIST
LAMINATE NEMA FR-4 W/SR1000 SOLDER RESIST/IR CURE	NVP	.38		03			LADDAE
LAMINATE NEMA FR-4 W/PFLATE RETARDANT RED MARKING	NVP	.49		00			LADDAE
LAMINATE NEMA G-10 GREEN MARKING	NVF	.47		00			LADDAE
LAMINATE NEMA G10 FABRIC/PHENOLIC RESIN	SYN	2.77		00			LADDAE
LAMINATE NEMA G10 IRADIATED POLYOLEFIN	WCA	.68		01			PC BOARD
LAMINATE PC BOARD IRADIATED POLYOLEFIN	WAC	.68		01			LADDAE
LAMINATE PHENOLIC/FIBERGLASS PREPREG	USP	.48		01			LADDAE
LAMINATE PHB-15/HMG EPOXY GRAPHITE BY AMQCO	AOC	.77		00			LADDAE
LAMINATE POLYIMIDE/GLASS FABRIC BY AMQCO	AOT	.55		00			LADDAE
LAMINATE SHIN AL-KAPTON/7366 TAPE/AG-TEFLON-CTR	GSC	.52		00			SOLID
LAMINATE SUN SHADE AL-KAPTON/7366 TAPE/AG-TEFLON-EDG	HOT	1.12		00			SOLID
LAMINATE TELGE MULTILAYER	TUP	2.33		00			LADDAE
LAMINATE TUFNOL GRADE 0/45 FABRIC/EPOXY COLOR	FPC	.58		00			LADDAE
LAMINATE T300/934 GRAPHITE/EPOXY	FPC	.59		01			LADDAE
LAMINATE V-378A/HMG EPOXY/BRAHYTE	USP	.45		01			LADDAE
LAMINATE VECTORBOARD 63G24WE GLASS/EPOXY	FER	.17		01			LADDAE
LAMINATE WBC 3201C ON 112 GLASS CLOTH EPOXY RESIN	WEC	.23		02			LADDAE
LAMINATE WESTINGHOUSE EPOXY/FIBERGLASS	YLI	.43		00			PIPE
LAMINATE YLI 55589E028 SILICONE/FIBERGLASS	KCF	1.69		00			ADDAE SUBSTRATE
LAMINATE 602 TEFLON/SILICONE/EPOXY	ATL	.01		00			PC BOARD
LARC 160 GRAPHITE/FOLYIMIDE LAMINATE 5 STEP POSTCURE	LRC	.83		00			LADDAE
LOUVER 550/120 BCNYCOMB	HTC	1.43		01			LOUVER
LOUVER 550/1581 EPOXY PRE-PREG	WCN	.69		06			LADDAE
NARICO 550/120 EPOXY/Glass PRE-PREG	NCO	.29		00			LADDAE FABRIC
NELCO 11-4205-2 F-GLASS FR4 FABRIC/EPOXY COATED	FLA	1.91		04			ADDAE
NO-FLO A 11-108-65 FIRE PREV LAMINATE	ATP	3.30		02			LAMINATE
PHENOLIC AGD PER MIL-79C GRADE NA TYPE FBE	DBP	.62		01			STRUCTURAL
POTTING CUP				4H			LADDAE

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	MFR CODE	%TML	%CVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
PYRALIN 12 POLYIMIDE PREPREG	DUP	.52	.0.0	30M	177	PSI	LAD BLADE
PYRALIN 3 POLYIMIDE PREPREG	DUP	.47	.07	2H	290	PSI	LAD BLADE
PYRALIN COPPER CLAD 2 SIDES 5.5 MILS THICK	DUP	.14	.09	1H	177	PSI	LAD BLADE
REFL4536 NYLON 6/6 W/10% GLASS/15% TFE/SILICONE	LMP	1.17	.17			AIR	SAND-OFF
REFL4536 NYLON 6/6 W/10% GLASS/15% TFE/SILICONE ONLY	LMP	1.57	.03			AIR	SAND-OFF
RL 454 NYLON 6/6 W/20% TFE/SILICONE	LMP	1.40	.07			AIR	SAND-OFF
RT DUROID 5870 - LAMINATE	ROG	.05	.00			AIR	LAD BLADE
RT DUROID 5880 - LAMINATE	ROG	.03	.00			AIR	LAD BLADE
RT DUROID 6015 - LAMINATE	ROG	.03	.00			AIR	LAD BLADE
SCI REZ 80/S GLASS FIBER/RESIN WOUND COMPOSITE	SCI	.22	.03	4H	79	AIR	BAND
SCOTT POLYURETHANE FOAM/ALUM KAPTON SANDWICH LOUVER	SCI	2.84	.13	4H	107	AIR	
SCOTT POLYURETHANE FOAM/ALUM MYLAR SANDWICH	SCI	1.28	.09	3H	149	AIR	
SCOTT POLYURETHANE FOAM/ALUM MYLAR SANDWICH	SCI	1.20	.04	3H	177	AIR	LAD BLADE
SKYBOND 703 GRAPHITE/POLYIMIDE LAMINATE 3 STEP PCURE	SCI	.81	.04	48H	120	AIR	LAD BLADE
STAND-OFF G-10 EPOXY/Glass COMPOSITION	MON	.36	.01	1H	177	E-2	LAD BLADE
V 378 GRAPHITE/PCLYIMIDE LAMINATE 2 STEP POSTCURE	BFS	.10	.00			PSI	SAND-OFF
XP1-MC-154 POLYIMIDE	USP	.60	.01	30M	82	PSI	THERM CONTROL
	ACC	1.14	.01	4H	177	PSI	SAND-OFF

SECTION 11 -- MARKING MATERIALS & INKS

MATERIAL	HPN CODE	XTRNL CODE	ZCVCN TIME	CURE TIME	CURE TEMP	STATUS	APPLICATION
BRADY FILM L363-61A/SILICONE ADHESIVE/F	WHB	1.17	.47	.38	24H	150	AIR
BRADY FILM L363-61A/SILICONE ADHESIVE/F	WHB	1.84	.48	.48	24H	150	AIR
BRADY FILM 436-81E/SILICONE ADHESIVE/F	WHB	1.82	.34	.34	24H	150	AIR
BRADY FILM 921 CLEAF ACRYLIC ADH/F	WHB	1.86	.90	.90	24H	150	AIR
BRADY HI-TEMP LAEFLIS ON L-363-81B TAPE/P	WHB	6.50	1.07	1.07	24H	150	AIR
BRADY LABEL B-637 YELLOW/BLACK/TEFLON/ACRYLIC ADH/F	WHB	2.59	1.19	1.19	24H	150	AIR
BRADY LABEL B-927 WHITE/BLACK/WHITE/POLYESTER ADH	WHB	2.59	1.05	1.05	24H	150	AIR
BRADY MARKERS AF-4-2-CAP TDSP-400-1	WHB	1.91	.08	.08	24H	150	AIR
BRADY MARKERS B-40C TDSP-400-1	WHB	1.20	.02	.02	24H	150	AIR
BRADY MARKERS B-70C VEN 0-49	WHB	1.63	.41	.41	24H	150	AIR
BRADY MARKERS B-70C VEN 1-33	WHB	1.72	.45	.45	24H	150	AIR
BRADY MARKERS B-70C/F	WHB	1.74	.29	.29	24H	150	AIR
BRADY MARKERS B-931 HI-200	WHB	1.66	.23	.23	24H	150	AIR
BRADY MARKERS B-933 HI-200/F	WHB	1.81	.02	.02	24H	150	AIR
BRADY PERMA CODE LABELS SPECIAL	WHB	5.52	.02	.02	24H	150	AIR
BRADY WRITE ON LABELS NO-19	WHB	4.03	.56	.56	24H	150	AIR
C-1589-3 BLACK INK/F	CIK	1.09	3.36	7D	25	AIR	LABEL
C-917 MS BLACK INK/F	CIK	1.09	3.29	7D	25	AIR	LABEL
C-917 MS BLACK INK/F	CIK	1.12	.38	.38	24H	60	AIR
CHEMGLAZE 2004 W/10% P-82 RED COLOR PASTE	CIK	9.76	.15	.15	7D	25	AIR
CHEMGLAZE 2004 W/5% CHROMIC OXIDE PIGMENT	HCC	6.17	.20	.20	24H	225	AIR
CHEMGLAZE 2004 W/5% CHROMIC OXIDE PIGMENT	HCC	6.20	.33	.33	24H	225	AIR
CHEMGLAZE 2652 TILI GREEN GLOSS POLYURETHANE	HCC	.83	.03	.03	24H	25	AIR
CHEMGLAZE 2853 EID YELLOW GLOSS POLYURETHANE	HCC	2.79	.02	.02	14D	60	AIR
DC 92-007 WHITE SILICONE INK/F	HCC	2.57	.02	.02	14D	25	AIR
DECA-DRY DECAL CARBON SHEET	DCI	4.45	.14	.14	1H	93	AIR
DECA-DEY LETTER DECALS	CPI	8.39	1.51	1.51	4H	149	AIR
DEON 315/140/PMS 175-ED AS 50/50/5 BN WHITE EPOXY	CPI	11.26	1.96	1.96	3H	65	AIR
FASCON 710 CIRCEPLATED POLYESTER/ACRYLIC ADH/R	SHL	1.64	.08	.08	24H	150	AIR
FASCON 313 SAILIN FINISH LABEL - WHITE	APP	1.20	.08	.08	24H	150	AIR
FEELT MARKER BLACK/F	APP	5.42	.01	.01	24H	150	AIR
HANCO 1355 RAVEN BLACK OPAQUE COATING/F	FED	15.75	.87	.87	24H	150	AIR
LABEL MARKING PRESSURE SENSITIVE FOIL/F	HAN	16.85	.01	.01	24H	150	AIR
MARKEN 7224 BLACK INK	APP	5.36	.12	.12	24H	150	AIR
MARKEN 7224 BLACK INK	TMC	3.93	.11	.11	24H	150	AIR
MARKEN 7224 GREEN INK 497-F	MIN	3.12	.08	.08	24H	150	AIR
MARKEN 7224 WHITE INK SLOW SOLVENT	MIN	4.45	.02	.02	24H	121	AIR
MARKEN 7224 WHITE INK FAST SOLVENT	MIN	1.88	.01	.01	24H	121	AIR
MARKEN 72251 GREEN INK 497-F	MIN	1.22	.12	.12	24H	107	AIR
MARKEN 72251 WHITE INK SLOW SOLVENT	MIN	9.64	.64	.64	24H	107	AIR
MARKEN 72252 WHITE INK FAST SOLVENT	MIN	5.34	.01	.01	24H	107	AIR
MARKEN 7254 BLACK INK - PHENOLIC	MIN	4.05	.05	.05	24H	125	AIR
MARKEN 7902 WHITE INK A/B AS 2/1 BN	MIN	4.27	.03	.03	24H	125	AIR
MARKEN 7905 WHITE INK A/B AS 2/1 BN	MIN	8.01	.02	.02	24H	88	AIR

SECTION 11 -- MARKING MATERIALS & INKS

MATERIAL	MFR CODE	STYL	WCVCM	CUBE TIME	CURE TEMP	ATMOS	APPLICATION
MARKER 7906 WHITE INK A/B AS 8.18/1 BW	MIN	48	.01	2H	121	AIR	INK
MARKER 8829 WHITE INK	MIN	11	.33	13	AIR	INK	MARKER
MARKERS 881A L-124/BLACK INK	LIN	2	.33	.88	25	AIR	MARKER
NAMEPLATE ANODIZED ALUMINUM W/ADH ON FOIL	BEN	63	.50				NAMEPLATE
NAMEPLATE PHOTO ALUMINUM W/ADH ON FOIL	HEL	10	.01				NAMEPLATE
NAMEPLATE PHOTO SENSITIVE ALUM/VANGDIZED/SEALED	HPC	10	.01				NAMEPLATE
NAMEPLATE PHOTO SENSITIVE ALUM/VANGDIZED/SEALED BLACK	NPC	11	.01				NAMEPLATE
NAMEPLATE 3655 BLACK/ALUM PVC W/ADH/F	MHE	65	.38				NAMEPLATE
PYRCHARKER H104 DTEMP WHITE MARKER/F	TEM	83	.42				dark ink
REDIMARK FELT MARKER BLACK/F	DAN	40	.62	7D	25	AIR	dark ink
REDIMARK 139-101 FELT MARKER BLUE/F	DAN	25	.35	39	25	AIR	dark ink
SANFORD ER SKETCH 2000 FELT TIP MARKER	SAN	24	.14	91	25	AIR	dark ink
SCOTCHCAL 8001 RED ALUM LABEL UNCOATED	HIN	99	.31				FULL LABEL
SCOTCHCAL 8001 RED ALUM LABEL COATING 3900	HIN	17	.01				FULL LABEL
SCOTCHCAL 8001 RED ALUM LABEL COATING 7700	HIN	12	.01				DECAL/MARKER
SCOTCHCAL 8005 BLACK PHOTO SENSE FILM/ALUM/ADH/FOIL	HIN	12	.01				DECAL/MARKER
SCOTCHCAL 8005 PHOTOSENS FILM/ALUM/ARYLIC ADH	HIN	19	.00				DECAL/MARKER
SCOTCHCAL 8005 PHOTOSENS FILM/ALUM/INYLCOAT/ACR ADD	HIN	19	.01				DECAL/MARKER
SCOTCHCAL 8009 BLUE ALUM LABEL UNCOATED	HIN	08					FULL LABEL
SCOTCHCAL 8009 BLUE ALUM LABEL COATING 3900	HIN	15	.01				FULL LABEL
SCOTCHCAL 8009 BLUE ALUM LABEL FILM 7700	HIN	14	.01				FULL LABEL
SCOTCHCAL 8011 RED PHOTO SENSE FILM/ADH/FOIL	HIN	56	.03				DECAL/MARKER
SCOTCHCAL 8015 PHOTOSENS FILM/MYLAR/ARYLIC ADH	HIN	14	.03				DECAL/MARKER
SCOTCHCAL 8015 PHOTOSENS FILM/MYLAR/INYLCOAT/ACRADH	INK	33	.76	7D	25	AIR	dark ink
SENTRY SEAL RED MARKING INK	GMB	72	.01	24H	25	AIR	darkens fluid
SPEED-O-SEAL RED COPAYEING LIQUID	SIN	99	1-8	2D	25	AIR	darkens
SUPER LAMINATE MARKERS WED POLYESTER ADH	SAN	100	1-24	24H	25	AIR	darkens
TECH-MARK INK BLACK LOT 105/F	HTC	81	1-24				dark
TELAOPEN GREEN INK FROM TUBE	HTC	55					TELE-TUBE
TERMOTEMP MODEL 110 TEMP RECORDER TAPE/F	RCC	92	.05				dark ink sleeve
TERMOTEMP AT 1800/1 HT TMS WHITE HEAT GUN SHRINK	RCC	72					dark ink tubing
UNIGLAZE C-1752 GAFF EPOXY INK	UIC	21					dark ink
UNIGLAZE 2010/9120 AS 3/1 BW YELLOW EPOXY INK	UIC	12					dark ink
UNIGLAZE 3005/9120 AS 3/1 BW RED EPOXY INK	UIC	12					dark ink
WORNOW CAT-L-INK 5C-10/10/CAT 9/50-900 THINNER WHITE/F	WPP	62	.01	30H	25	AIR	dark ink
WORNOW CAT-L-INK 5C-121869/CAT 28 AS 20/1 BW ALUD	WPP	94	-0.5	30N	149	AIR	dark ink
WORNOW CAT-L-INK 50-300/CAT 20 AS 100/6-4 BW GREEN	WPP	76	-18	30H	25	AIR	dark ink
WORNOW CAT-L-INK 5C-407/CAT 20 AS 100/7-5 BW BLUE	WPP	1175	-0.9	5D	25	AIR	dark ink
WORNOW CAT-L-INK 5C-700/CAT 20 AS 100/7 BW	WPP	486	-0.1	72H	93	AIR	dark ink
WORNOW H-2-N BED/CAT 45/T-1 THINNER/F	WPP	40	-0.2	14H	45	AIR	dark ink
WORNOW H-5-N GREEN/CAT 45/T-1 THINNER/F	WPP	44	-0.2	15H	49	AIR	dark ink

SECTION 11 -- MARKING MATERIALS & INKS

MATERIAL	NFR CODE	%ML	XCVCM	CURE TIME	TEMP	AIRUS	APPLICATION
HORNOW SERIES H KEL INK H-2-N 0.5% CAT A	HPP	2.94	-0.5	5D	25	Air	Link
HORNOW SERIES H WHITE INK H-9-N 5.0% CAT A	HPP	4.63	-0.4	3H	66	Air	Link
HORNOWINK H-0-N/CAT A AS 100/4 BW BLACK PRE-MIX INK	HYS	7.95	-1.3	7D	51	E-o	
HORNOWINK H-0-N/CAT B3 AS 100/4 BW BLACK PRE-MIX INK	HYS	6.08	-0.9	3H	25	Air	Link
HORNOWINK H-2-N/CAT A AS 100/4 BW RED EPOXY INK	HYS	6.97	-1.6	7D	54	Air	Link
HORNOWINK H-2-N/CAT B3 AS 100/4 BW RED EPOXY INK	HYS	4.20	-1.1	3H	25	Air	Link
HORNOWINK H-4-N/CAT 45 AS 20/1 BW YELLOW EPOXY	HYS	.84	-1.9	1H	54	Air	Link
HORNOWINK H-9-N/CAT A AS 100/4.9 BW WHITE PREMIX INK	DYS	6.10	-1.1	4H	25	Air	Link
HORNOWINK H-9-N/CAT B3 AS 100/4.9 BW WHITE PREMIX INK	HYS	4.27	-1.1	7D	25	Air	Link
HORNOWINK HONC/CAT B AS 1/1 BW BLACK	HPP	4.53	-0.5	3H	54	Air	Link
				6H	60	Air	Link

SECTION 12 -- MOLDING COMPOUNDS

MATERIAL	DPK CODE	ATL	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
ABS VACUUM MOLDED CASING ACRYLIC GLASS 7/20 SILICONE/ACRYLONITRILE/FIB GLA AS 80/20	SHE FBR FBR DUP DUP	1.13 2.2 7.1 .34	.16 .03 .03 .03	6M 2H 2H 100	204 120 120 E-O	E-Z	ADOL CEND
ACRYLIC GLASS 540/20 STIRRED ACRYLONITRILE/FIBER GLASS							ADOL CEND
ADIPRENE L83/CAVITUR 21 AS 100/16 BW POLYURETHANE							ADOL CEND
ADIPRENE L83/CAVITUR 21 AS 100/16 BW POLYURETHANE							ADOL CEND
AP 1006 ACRYLIC BUTYLENE STYRENE	LMP	.20	.01	72H			ADOL CEND
AP 1006 ACRYLIC BUTYLENE STYRENE	AMP	.51	.01				ADOL CEND
AP 3005 FAST CURE EPOXY ACU-PAK PRE MIX	ALK	.90	.01	24H	25	AIR	ADOL CEND
ARYLON T POLYARYL ETHER EPOXY MOLDED AT 260C	UNC	.36	.03				ADOL CEND
ASTREL 360 POLYARYL SULFONE TAN	MM	.94	.02				ADOL CEND
BP 1006 SILKENE ACRYLONITRILE	GRB	1.60	.00				ADOL CEND
BUSHING TYPE MPE MIL-N-14 MICA FILLED PHENOLIC	LNP	.24	.01				ADOL CEND
CAPRON 512B NYLON ANTI STATIC FILM	GHP	.98					BU/SILIC
CELCON M-90-04 ACETAL COPOLYMER UNMOLDED PELLETS	CPN	.94	.03				BU/SILIC
CPN 1006 SILKENE FIBER GLASS AS 70/30	LNP	.10	.01				BU/SILIC
CJ-4215/B2-3561 AS 20/3 BW GLASS FILLED	JAC	.26	.04				BU/SILIC
DAP C2580-11B FOR FMC - DAPON M	HYS	.68	.00	2.5H	105	AIR	ADOL CEND
DAP SHORT GLASS FIBER FILLED BLACK	FMC	.30	.00				ADOL CEND
DE 307 MOLDING CINE - VISITOR RS-1A-XX (E7741).	ROG	.44					ADOL CEND
DELTRIN 107 BLACK ROD - WHITE	DCC	.62	.02	24H	177	AIR	ADOL CEND
DEXSIL 5001 - BORON/SILICATE/POLYCARBONATE/FIBER GLASS AS 70/30	DUP	.39	.02				ADOL CEND
DUR-O-LITE DF 1006 POLYCARBONATE/FIBER GLASS AS 70/30	CLL	.07	.00				ADOL CEND
DUR-O-LITE ECCOMOLD L-28	CBC	.14	.01				ADOL CEND
ECCOMOLD L-28	EMC	.87	.01				ADOL CEND
ECCOMOLD L-28	EMC	.59	.03	30M	127	AIR	ADOL CEND
ECCOMOLD L-28	EMC	.18	.01	2H	.70	AIR	ADOL CEND
ECCOMOLD L-28	EMC	.59	.07				ADOL CEND
ECCOMOLD CR-117X AS 100/12 BW	EMC	.32	.01	12H	74	AIR	ADOL CEND
ECCOMOLD CR-110 X/Y AS 100/12 BW	EMC	.26	.00	12H	74	AIR	ADOL CEND
EKKCEL C-1000 Aromatic Copolyester BROWN HIGH TEMP	CRB	.26	.00				ADOL CEND
EKKCEL C-2000 Aromatic Copolyester TAN HIGH TEMP	CRB	.65	.01	30M	316	AIR	ADOL CEND
ELTEK POLYETHERIMIDE	GEC	.48	.00	15M	PSI		ADOL CEND
EM 7302 GLASS FILLED EPOXY	GSP	.48	.04	12H	143	PSI	ADOL CEND
EMC 115-B-1 GLASS/EPOXY	PAC	.29					ADOL CEND
EPICL 1914 EPOXY/GLASS - BLACK	ACP	.47					ADOL CEND
EPOCAST 403-S-3	FPI	.32					ADOL CEND
EPOCAST 461-008 MINERAL FILLED FIBERGLASS SQUARE STRUCTURAL TUBE	FPI	.48					ADOL CEND
EPT 1006 HI-DENSITY POLYETHYLENE/GLASS REINFORCED PHENOLIC	LNP	.12					ADOL CEND
FIBERITE FM 4005 GLASS REINFORCED PHENOLIC	FIB	1.60	.00	5M	163	PSI	ADOL CEND
FM 4008 GLASS FIBER/PHENOLIC BLACK	FIB	.97	.01	18H	140	AIR	ADOL CEND
FORDAFT G80-20 ACETYL/FIBER GLASS AS 80/20 BW	FBR	1.49	.02	5M	166	PSI	ADOL CEND
FORDAFT G83-40 GLASS REINFORCED PHENOLIC	FPI	.44		30	149	AIR	ADOL CEND
GAR-DUR CLEAR	GAR	.32		6M	149	AIR	ADOL CEND
GAR-DUR YELLOW	GAR	.97		30	149	AIR	ADOL CEND

SECTION 12 -- HOLDING COMPOUNDS

MATERIAL	MR CODE	STL CODE	%CVCN	CURE TIME	CURE TEMP	ATENS	APPLICATION
GE 4524U SILICONE	GEC	.52	.18	25M 8H	163 121	AIR AIR AIR	ADLD CPND
GEMON 3010 THERMOSET POLYIMIDE	GEC	.34	.02	24H 24H	121 60	E-0	ADLD CPND
GP 1006 POLYSULFONE/PIDER GLASS AS 70/30	LNP	.14	.02	24H	121	E-0	ADLD CPND
HATHANE 1602-60D A/B AS 2/1 BV URETHANE	HPC	.72	.01	24H	25	AIR	ADLD CPND
HATHANE 1602-60D A/B AS 2/1 BV URETHANE	HPC	.72	.01	24H	25	AIR	ADLD CPND
HF 1006 NYLON 11 GLASS AS 70/30	LNP	.37	.02	24H	121	AIR	ADLD CPND
HOSTALEN GUR HIGH MOLECULAR WT POLYETHYLENE	ANH	.14	.02	24H	121	AIR	ADLD CPND
INPAK 5M W/UNW FCIYMER - NATURAL	IP1	.22	.03	24H	121	AIR	STRUCTURAL
JP 1004 POLYETHERSULFONE/GLASS AS 60/20 BW	IP1	.59	.03	24H	121	AIR	ADLD CPND
JF 1008 POLYETHERSULFONE/GLASS AS 60/40 BW BLACK	IP1	.49	.03	24H	121	AIR	ADLD CPND
KF 1006 ACETAL/GLASS AS 70/30	LNP	.27	.03	24H	121	AIR	ADLD CPND
KJB CYCOLAC BLUE 5500 SERIES W/FIRE RETARDANT	BVC	1.06	.03	24H	121	AIR	ADLD CPND
KJB CYCOLAC PINK F5500 EPCAY/CELIION 3000 GRAPLITE COMPOSITE	BVC	.42	.03	24H	121	PSI	CABO GUIDE
LAMINATE 500 POLYCARBONATE	HEX	.42	.03	24H	121	PSI	LADLE GUIDE
LEXAN 940 BLACK LILAL PLATE	GEC	.16	.03	24H	121	PSI	DIAL CPND
MAI-60 MOLDING CENE - GRAY	ACD	.73	.04	24H	121	PSI	ADLD CPND
MAI-60 MOLDING CENE - GRAY	ACD	.73	.04	24H	121	PSI	ADLD CPND
MP 1006 POLYPROPYLENE/GLASS AS 70/30	LNP	.13	.03	24H	121	PSI	ADLD CPND
MG 8/10 134 HOLDING CF-2 BLACK	HIS	.22	.01	24H	121	PSI	ADLD CPND
MH 11 BLACK HOLDING COMPOUND	HYS	.18	.01	24H	121	PSI	ADLD CPND
MH 6F HOLDING CPNL - BLACK	HYS	.41	.01	24H	121	PSI	ADLD CPND
NP 1006 PEQFIBER GLASS AS 70/30	LNP	.11	.03	24H	121	PSI	ADLD CPND
NORYL EN 265	WPC	.17	.03	24H	121	PSI	ADLD CPND
NYLASINT 64 HV SINTERED NYLON OIL RESERVOIR	PPC	.25	.02	24H	121	PSI	OIL RESERVOIR
NYLON CARD GUIDE RED FLAME RETARANT	PPC	.73	.02	24H	121	PSI	ADLD CPND
NYLON HD-LP-410A 6/6 HOUSING IMPACT	PEP	2.43	.03	24H	121	PSI	SARJURAL
NYLON 6/6 PC HDLED INSERTS NEUTRAL COLOR	PEP	2.36	.03	24H	121	PSI	ADLD CPND
NYLON 6/6 PC BD CHANNEL BLACK GLASS FILLED FLAME RET	TEK	1.09	.03	24H	121	PSI	ADLD CPND
PENTON - CHLORONATED POLYETHER	TER	1.42	.03	24H	121	PSI	ADLD CPND
PF 1006 NYLON 6	LNP	.50	.03	24H	121	PSI	ADLD CPND
PHENAL 6000 PHENYLIC	ACM	1.18	.03	24H	121	PSI	ADLD CPND
PHENOLIC MOLD CPND PER MIL MIL 14-CF1-10 BLACK	ACM	1.34	.03	24H	121	PSI	ADLD CPND
PHENOLIC MOLD CPND PER MIL MIL 14-CF1-10 BLACK	FIB	4.82	.04	24H	121	PSI	ADLD CPND
PHENOLIC 76.00/1-0-E/EPoxy ANHYDRIDE 76-0001-10	FIB	3.29	.04	24H	121	PSI	ADLD CPND
POLYCARBONATE 350/2C POLYCARBONATE & FIBER GLA AS 80/20	SPZ	.33	.07	24H	121	PSI	ADLD CPND
POLYESTHERSULFONE 2COP THERMOPLASTIC	FBR	1.04	.00	24H	121	PSI	ADLD CPND
POLYSET 521 BLACK	ICI	1.04	.00	24H	121	PSI	ADLD CPND
POLYSTYRENE CO EXTRUDED BLUE BOX	MNC	.30	.00	24H	121	PSI	ADLD CPND
POLYSTYRENE CO - EXTRUDED WHITE INSERT	SHC	.50	.00	24H	121	PSI	ADLD CPND
POLYSULFONE	SHC	.28	.00	24H	121	PSI	ADLD CPND
POLYURETHANE 9250 FROM HIGH WEIGHT POLYETHYLENE HEAT PIPE WICK	UCC	.33	.00	24H	121	PSI	ADLD CPND
POREX ULTRA HIGH WEIGHT POLYISOPROPYLIC	DIC	1.83	.00	24H	121	PSI	ADLD CPND
PR 1201-Q AS 1/10 BW POLYURETHANE	POR	1.11	.01	24H	121	PSI	ADLD CPND
PR 1535 4/E AS 3/100 BW POLYURETHANE	PRC	.32	.01	24H	121	PSI	ADLD CPND
PR 1538 4/B AS 3/100 BW POLYURETHANE	PRC	.98	.05	24H	121	PSI	ADLD CPND
	PRC	.52	.05	24H	121	PSI	ADLD CPND
	PRC	.52	.05	24H	121	PSI	ADLD CPND

SECTION 12 --- MOLDING COMPOUNDS

MATERIAL	DPA CODE	XTHL	ACTH	CURE TIME	CURE TEMP	AIR	APPLICATION
PR 1547 A/B AS 32/100 BW POLYURETHANE PYRACNE 6/10 30% FIBER GLASS	PRC FLX LNP LDV	3.65 3.49 0.95 1.38	0.3 0.3 0.4 0.4	7H 1H	450	AIR AIR	BOLD CEND BOLD CEND BOLD CEND BOLD CEND
RADITE 75 NYLON 0/6 AF 106 NYLON 0/6 RICOHENE 371 THERMOSET THERMOPLASTIC HYDROCARBON ROGERS RX 611	LMP RIC ROG	1.81 1.59 1.53	0.9 0.9 0.8	10M 30M 30M	149	AIR AIR AIR	BOLD CEND BOLD CEND BOLD CEND
RRY 615 A/B AS 10/1 BW DEVOL AT 140°C LOT KA210 BTCHS	GSC	0.9	0.5	25	204	AIR	PORING
RYTON R-4 POLYPHENYLENE SULFIDE 50/50 GLASS SECTOCAST 225A/B AS 5/8 BW BAROON FOLIUM ETHANE	GSC HHA	0.53 1.15	0.3 0.3	10M 7H	166 210	E-1 E-1	BOLD CEND BOLD CEND
SE 4401 SILICONE ELASTOMER GRAY SHORE A40	GEC	0.6	0.0	24H	249	AIR	BOLD CEND
SE 4401 U GENERAL PURPOSE SILICONE SE 4504U GENERAL PURPOSE SILICONE SE 4524U CLEAR SILICONE	GEC GEC GEC	0.10 0.10 0.07	0.0 0.0 0.0	24H 25M 7H	163 163 200	AIR AIR WFB	BOLD CEND BOLD CEND BOLD CEND
SE 5204 SILICONE FOOD GRADE FF SE 5554U SILICONE FOOD GRADE GG	GEC GEC	0.7 0.6	0.0 0.0	8H 15H	216 200	AIR PSI	E-6 E-6
SE 565/VAROX AS 10C/0.6 BW EXTREME LOW TEMP SILICONE SE 565/VAROX AS 100/0.6 BW EXTREME LOW TEMP SILICONE	GEC GEC	0.25 0.12	-12 -0.3	15H 2H	121 177	AIR AIR	BOLD CEND BOLD CEND
SF 1006 NYLON 12/Glass AS 70/30 SILASTIC 6508/TS-50 CADOX AS 99/1 BW SILICONE SILASTIC 6508/TS-5G CADOK AS 99/1 BW SILICONE	LNP DCC DCC	1.65 1.27 0.80	-0.1 -34 -18	48H 5H 5H	177 116 116	AIR AIR AIR	BOLD CEND BOLD CEND BOLD CEND
STYCAST 0005 POLYSTYRENE/BLACK POLYSTYRENE/FIBER GLASS SULFIL 1500/20 POLYSULFONE/FIBER GLASS AS 80/20 SUPRANICA 30/SYNTETIC ALICA/ORGANIC BINDER SWITCH CASE ES-4 BLACK PHENOLIC TEFLON PFA MOLDED SPECIMEN TE-9704	EMC FBR MYC CAN DUP	0.29 0.20 0.33 0.33 0.01	-0.1 -0.0 -0.0 -0.0 -0.0	24H	121 163 121 121 121	E-3 E-6 E-6 E-6 E-3	BOLD CEND BOLD CEND BOLD CEND BOLD CEND BOLD CEND
TEPEZEL POLYHENE/TETRAFLUOROETHYLENE COPOLYMER TF 1004 POLYURETHANE/FIBER GLASS AS 80/20 TF 1008 PVC/URIDATE/GLASS AS 60/40 TORLON 4203 MOLD POLYAMIDE/LIMIDE TULIEN D6202 GREY FROM MOLD CND UNREINFORCED TULIEN 1090 CLEAR ANDER MOLD CND VALOX 420 THERMOPLASTIC POLYESTER/30% GLASS FIBER VALOX 420 THERMOPLASTIC POLYESTER/30% GLASS FIBER VESPEL KS-105 AKAMID	DUP LNP LNP AOC GEC GEC GEC GEC DUP	-0.0 -0.0 -0.0 -0.0 -0.0 -0.0 -0.0 -0.0 -0.0	-0.1 -0.1 -0.1 -0.0 -0.0 -0.0 -0.0 -0.0 -0.0	17 56 37 85 37 40 20 16 35	117 108 100 100 100 100 100 100 100	STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL STRUCTURAL	

SECTION 12 -- MOLDING COMPOUNDS

MATERIAL	MFR CODE	ATHL	%CVCN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
VESPEL SP-5 POLYIMIDE/30% SHORT GLASS FIBERS	DUP	.49	.05				BULD CPND
VP 1607 PVC 35% FIBER GLASS	LNP	.30	.05				BULD CPND
WF 1006 THERMOPLASTIC POLYESTER/FIB GLASS AS 80/20	LNP	.19	.05				BULD CPND
XP 1004 POLYIMIDE/GLASS AS 80/20	LNP	.06	.01				BULD CPND
XP 1006 POLYARYLIC ETHER/GLASS AS 70/30	LNP	.29	.01				BULD CPND
XP 1006 NYLON/GLASS AS 70/30	LNP	.04	.01				BULD CPND
ZYTEL 1011 BLACK CONNECTOR INSERT	DUP	.31	.03				CBK CPND
ZYTEL 7010-33 NYLCA RESIN	DUP	.09	.01				BULD CPND
ZYTEL 7110-13 NYLCA RESIN	DUP	.28	.01				BULD CPND

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	NRK CODE	SPNL	ACVCM	CURE TIME	CURE TEMP	AIRUS	APPLICATION
ANDREW BROWN BLACK EPOXY PRIMER A-136 ANDREW BROWN BLACK EPOXY PAINT/PRIMER A-136	AEC AEC	9.48 2.77	.21 .16	5D 10H	25 2.5	AIR AIR	PAINT PAINT
BC 337 HI-THICK VARNISH	JCD	2.74	.30	30H	14.9	AIR	VARNISH
BC 340 VARNISH POLYESTER/XYLENE	JCD	6.01	.40	1H	13.8	AIR	VARNISH
BS 346-B PHENOLIC VARNISH 4-3/4 AS 3/1 BV	JCD	3.31	1.02	9H	13.5	AIR	VARNISH
BSSTIK FINCH 4-3/4 AS 3/1 BV WHITE EPOXY PAINT	FPC	7.95	.15	7D	2.5	AIR	PAINT
BSSTIK FINCH 4-3/4 AS 3/1 BV POLYURETHANE 3/1 BW	FPC	4.67	.02	9H	12.7	AIR	PAINT
BR-127 PRIMER/F EPOXY PRIMER FR 463-12-8 A/B AS 3/1 BW	FPC	4.29	.04	9H	12.7	AIR	PAINT
CAT-A-LAC FLAT BLACK EPOXY COATING	FPC	3.48	.06	72H	2.5	AIR	PAINT
CAT-A-LAC WHITE EPOXY A/B AS 3/1 BV	FPC	3.03	.06	72H	5.1	E-O	PAINT
CAT-A-LAC WHITE EPOXY A/B AS 3/1 BW	FPC	3.94	.13	7D	2.5	AIR	PAINT
CAT-A-LAC 463-3-10C A/B AS 3/1 BW WHITE EPOXY PAINT	FPC	12.09	.14	7D	9.3	AIR	PAINT
CAT-A-LAC 463-3-10C A/B AS 3/1 BW WHITE EPOXY PAINT	FPC	6.75	.23	24H	2.5	AIR	PAINT
CAT-A-LAC 463-3-10C A/B AS 3/1 BW WHITE EPOXY PAINT	FPC	4.13	.04	16H	6.6	AIR	PAINT
CAT-A-LAC 463-3-10C/CA-118 AS 3/1 BV WHITE PAINT	FPC	4.16	.02	16H	2.5	AIR	PAINT
CAT-A-LAC 463-3-10C/CA-118 AS 3/1 BV/PRIMER 463-6-5	FPC	4.11	.02	16H	7.0	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	FPC	.35	.17	24H	7.0	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	FPC	4.50	.12	47H	6.6	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	FPC	1.18	.21	72H	2.5	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	FPC	.55	.22	48H	12.1	AIR	PAINT
CAT-A-LAC 463-3-8 BLACK OVER PRIMER 463-12-1A	FPC	.70	.03	24H	2.5	AIR	PAINT COMPOSITE
CAT-A-LAC 463-3-8 BLACK OVER PRIMER 463-6-2 GREEN/F	FPC	2.14	.03	1H	4.8H	12.1	AIR
CAT-A-LAC 463-3-8 FLAT BLACK EPOXY PAINT	FPC	1.33	.00	30H	6.6	AIR	PAINT
CAT-A-LAC 463-3-8 FLAT BLACK EPOXY PAINT	FPC	1.02	.05	4H	12.0	AIR	PAINT
CAT-A-LAC 463-3-8/CA-118 AS 3/1 BV BLACK EPOXY PAINT	FPC	4.05	.03	30H	13.5	AIR	PAINT
CAT-A-LAC 463-3-8/CA-118 AS 3/1 BV FLAT BLACK EPOXY	FPC	3.42	.03	1d	12.5	E-O	PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV BATCH - GSFC	FPC	2.91	.25	2H	6.0	AIR	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV BATCH - THW	FPC	3.96	.17	2H	6.6	AIR	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	FPC	8.16	.33	6.5H	10.4	AIR	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	FPC	6.98	.35	24H	2.5	AIR	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	FPC	2.17	.35	24H	6.6	AIR	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	FPC	1.47	.34	6H	10.4	AIR	COND PAINT

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	PPR CODE	STML CODE	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION	
CAT-A-LAC 473-3-1 A/B AS 3/1 BY CLEA EPOXY	FPC	9.02	.43	1H	25	AIR	COATING	
CAT-A-LAC 643-1-1 ALUMINUM PAINT 3/1 BN CLEAR EPOXY	FPC	4-.36	.24	1H	60	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE	HCC	2-.35	.19	1H	70	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE	HCC	1-.67	.15	10H	45	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE LOT TJD	HCC	2-.25	.02	1D	25	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE LOT TJD	HCC	2-.37	.10	1D	25	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE/F	HCC	1-.46	.10	1D	25	AIR	PAINT	
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE/F	HCC	1-.89	.14	28H	225	AIR	PAINT	
CHEMGLAZE H322 BLACK CONDUCTIVE PAINT POLYURETHANE	HCC	1-.92	.07	48H	20H	E-6	COND PAINT	
CHEMGLAZE H322 BLACK CONDUCTIVE PAINT POLYURETHANE	HCC	1-.86	.09	30H	121	AIR	COND PAINT	
CHEMGLAZE H323 BLACK CONDUCTIVE PAINT POLYURETHANE	HCC	1-.57	.06	14D	225	AIR	COND PAINT	
CHEMGLAZE TS 3692-51 FLAT BLACK POLYURETHANE LOT YEA	HCC	1-.18	.01	14D	225	AIR	PAINT	
CHEMGLAZE TS 3692-74 FLAT BLACK POLYURETHANE LOT DAC	HCC	1-.07	.02	14D	225	AIR	PAINT	
CHEMGLAZE TS 2881-7 UV RESIST WHITE POLYURETHANE	HCC	8-.67	.10	1D	25	AIR	PAINT	
CHEMGLAZE TS 2881-7 UV RESIST WHITE POLYURETHANE	HCC	4-.30	.22	30D	225	AIR	PAINT	
CHEMGLAZE TS 3107-13 FLAT BLACK POLYURETHANE LOT SIA	HCC	1-.30	.02	14D	225	AIR	PAINT	
CHEMGLAZE TS 3107-13 FLAT BLACK POLYURETHANE LOT SIA	HCC	1-.35	.02	14D	225	AIR	PAINT	
CHEMGLAZE TS 3692-51 FLAT BLACK POLYURETHANE	HCC	2-.15	.02	14D	225	AIR	PAINT	
CHEMGLAZE TS 3692-74 FLAT BLACK POLYURETHANE	HCC	1-.23	.02	14D	225	AIR	PAINT	
CHEMGLAZE V200 GLOSS WHITE POLYURETHANE PAINT	HCC	1-.73	.17	1D	25	AIR	PAINT SYSTEM	
CHEMGLAZE V200/9924 GLOSS WHITE POLYURETHANE PAINT/F	HCC	.72	.07	30D	225	AIR	PAINT SYSTEM	
CHEMGLAZE V200/9924 GLOSS WHITE POLYURETHANE PAINT/F	HCC	.72	.03	11D	225	AIR	PAINT SYSTEM	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT	HCC	10-.03	.47	72H	290	E-O	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT	HCC	10-.19	.47	1D	225	AIR	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT	HCC	9-.97	.96	30D	225	AIR	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT	HCC	8-.46	.51	4D	225	AIR	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT LOT BHA	HCC	1-.07	.04	24H	60	E-O	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT LOT BHA	HCC	5-.48	.23	48H	190	E-O	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT MOD POLYURETHANE	HCC	1-.35	.01	24H	190	E-O	PAINT	
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT MOD POLYURETHANE	HCC	.90	.04	7D	225	AIR	COND PAINT	
CHEMGLAZE Z004 CLEAR POLYURETHANE LOT XGB	HCC	1-.72	.91	24H	70	AIR	COND PAINT	
CHEMGLAZE Z004/XC-72R/9924 PRIMER BLACK COND PAINT	HCC	1-.46	.91	14D	225	AIR	COND PAINT	
CHEMGLAZE Z004/9924 PRIMER COMPOSITE BLACK COND MOD	HCC	2-.99	.01	7D	225	AIR	COND PAINT	
CHEMGLAZE Z004/9924 PRIMER COMPOSITE BLACK COND MOD	HCC	1-.94	.04	7D	225	AIR	COND PAINT	
CHEMGLAZE 42002 POLYURETHANE FURNITURE COATING TS 1603-16	HCC	2-.60	.92	24H	70	AIR	PAINT	
CHEMGLAZE 42002 POLYURETHANE FURNITURE COATING TS 1603-16	HCC	2-.93	.90	10D	225	AIR	PAINT	
CHEMGLAZE 2306 GLOSSY BLACK POLYURETHANE	HCC	1-.39	.00	14D	225	AIR	PAINT	
CHEMGLAZE 2306 GLOSSY BLACK POLYURETHANE	HCC	1-.12	.03	21D	225	AIR	PAINT	
CHEMGLAZE Z306 BATCH L11247	HCC	.49	.02	24H	190	E-J	PAINT	
					24H	100	E-O	

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MPK CODE	%VNL	XCVN	CURE TIME	TEMP	ATMOS.	APPLICATION
CHEMGLAZE 2306 LCT LBC	HCC	.47	.04	2H	25	AIR	PAINT
CHEMGLAZE 2306 LCT LBC	HCC	1.32	.01	16H	66	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.91	.28	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.42	.27	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.42	.27	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.01	.51	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.90	.50	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.13	.06	7YR	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	1.13	.06	7YR	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	.87	.04	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT MA	HCC	.76	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT OAB	HCC	1.64	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT OAB	HCC	1.04	.31	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT OAB	HCC	1.10	.00	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT OAB	HCC	1.91	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT R/A	HCC	.83	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT TDA	HCC	1.16	.00	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	HCC	1.92	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	HCC	1.09	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	HCC	1.83	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306/B401 MICROBALLOONS/TOLUENE	HCC	1.83	.03	15D	25	AIR	PAINT
CHEMGLAZE 2306/CAT 996 AS 100/1 BW/FREE FILM	HCC	1.08	.25	25D	200	AIR	PAINT
CHEMGLAZE 2306/CAT 998 AS 100/1 TWO COATS	HCC	1.81	.36	15A	25	AIR	PAINT
CHEMGLAZE 2306/CHEMGLAZE 9924 PRIMER COMPOSITE	HCC	1.18	.05	30H	71	AIR	PAINT
CHEMGLAZE 2306/CHEMGLAZE 9924 PRIMER COMPOSITE/F	HCC	1.85	.06	24H	23D	AIR	PAINT
CHEMGLAZE 2306/CHEMGLAZE 9924 PRIMER COMPOSITE/F	HCC	1.45	.13	30H	225	AIR	PAINT
CHEMGLAZE 2306/CHEMLOCK AP131 PRIMER/F	HCC	1.76	.05	30H	225	AIR	PAINT
CHEMGLAZE 2306/KAPTON H REINFORCED	HCC	1.00	.08	42D	225	AIR	PAINT
CHEMGLAZE 2306/KAPTON H REINFORCED	HCC	.94	.09	42D	225	AIR	PAINT
CHEMGLAZE 2306/KAPTON H REINFORCED	HCC	.88	.09	42D	225	AIR	PAINT
CHEMGLAZE 2306/PAINTER DESOTO 513-102/F	GSC	1.75	.12	41D	25	AIR	PAINT
CHEMGLAZE 2306/RANOLPH EPOXY/POLYAMIDE PRIMER/F	RAN	1.67	.08	14D	225	AIR	PAINT
CHEMGLAZE 2306/SUPER KOROPON PRIMER/F	GSC	2.80	.03	14D	225	AIR	PAINT
CHEMGLAZE 2402 ALUM FILLED POLYURETHANE LOT MEB	HCC	6.68	.07	30H	74	AIR	PAINT
CHEMGLAZE 2651 GREEN GLOSS POLYURETHANE F	HCC	2.35	.03	7D	25	AIR	PAINT
CHEMGLAZE 9421 ALUM FILLED P-URETHANE PRIMER LOT XIB	HCC	1.84	.03	14D	25	AIR	PAINT
CHEMGLAZE 9922 EPOXY PRIMER FOR SEAL	HCC	1.58	.13	1H	60	AIR	PAINT
CHEMGLAZE 9924 AND AS 1/1 BY WASH PRIMER/F	HCC	6.88	.29	7D	25	AIR	PAINT
COATING 5459 OVER PRIMER 6362	HSD	6.91	.20	7D	25	AIR	PAINT
COATING 5459/CAT 6201 AS 1/1 BY FLAT BLACK EPOXY	HSD	7.51	.32	7D	25	AIR	PAINT
CPL-15 A/E AS 3/1 EW BLACK EPOXY PAINT	CPL	2.11	.19	24H	225	AIR	PAINT
CPL-15 A/E AS 3/1 EW BLACK EPOXY PAINT	CPL	3.93	.03	24H	225	AIR	PAINT

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	NFK CODE	HTM	%CVCM	CURE TIME	CURE TEMP	AIR DROS	APPLICATION
CTL-15 GLOSSY BLACK PAINT	CTL	2.16	.06	30M	25	AIR	Paint
CTL-15 GLOSSY BLACK PAINT THREE COATS	CTL	1.80	.04	24H	94.1	AIR	Paint
CUVERT 1652 BLACK POLYURETHANE COATING	CTL	2.90	.10	12H	125	AIR	Paint
DAG BC 1652 BLACK PAINT	HAC	.69	.02	14D	100	AIR	Paint
DAN PO X ENAMEL 160F AS 1/1 BY BLACK/F	ACH	.79	.02	14D	100	AIR	Paint
D- 92-007 WHITE SILICONE PAINT	DCL	2.54	.26	7D	25	AIR	Paint
D- 92-007 WHITE SILICONE PAINT	DCC	.91	.36	24H	25	AIR	Paint
DC 92-019 SILICONE PRIMER	DCC	.63	.20	24H	25	AIR	Paint
DC 94-003 DISPERSSION COATING	DCC	1.12	.07	8H	60	AIR	Paint
DC 991 VARNISH - CLEAR SILICONE/P	DCC	5.37	.18	24H	25	AIR	Coating
DC 991 VARNISH - CLEAR SILICONE/F	DCC	2.47	.93	24H	25	AIR	Coat
DENNIS 1162 A/B AS 1/1 BW LIQUID N/4600 THINNER	DNS	.88	.50	24H	125	AIR	Lacquer
DUPONT BLUE LACQUER 43907-1HXP/DETZLER PRIMER DZL-32	DUP	4.57	.66	6H	730	AIR	Paint System
DUPONT 4817 CONDUCTIVE SILVER PAINT	DUP	3.84	.04	24H	25	AIR	Condu Paint
DUPONT 4922 A/B AS 1/1 BW COND SILVER PAINT	DUP	.61	.00	15H	66	AIR	Condu Paint
DURALAC BLACK ENAMEL-LUSTERLESS	NLC	2.70	.21	1H	25	AIR	Paint
DUTCH BOY RED ENAMEL 756	MAC	1.94	.33	12.5	125	AIR	Condu Paint
D4 D CONDUCTIVE PAINT	GEV	1.88	.39	48H	66	AIR	Condu Paint
D4 D CONDUCTIVE PAINT	GEV	1.57	.34	48H	66	AIR	Condu Paint
D4 D LEAFING ALUMINUM	GEC	8.91	.78	48H	190	AIR	Paint
D4 D LEAFING ALUMINUM	GEC	7.72	.10	48D	25	AIR	Paint
E-KOTE 3030 CONDUCTIVE ACRYLIC PAINT	EPO	.76	.05	1H	25	AIR	Condu Paint
E-KOTE 40 COND SILVER PAINT/ACRYLIC	EPO	3.32	.10	24H	25	AIR	Condu Paint
EA 9203 ONE COMPONENT PRIMER FOR EPOXY	HYS	19.65	1.96	1H	60	AIR	Primer
ECP 2200 BLACK SCLAR ABSORBER COATING/F	HYS	.08	.00	24H	25	AIR	Thermal Control
ECP 2200 BLACK SCLAR ABSORBER COATING/F	HYS	.61	.07	4H	24.1	AIR	Thermal Coating
ENAMEL PLATE BLACK ABSORBER COATING/F	HYS	.85	.14	72H	100	AIR	Paint
ENAMEL PLATE BLACK ABSORBER COATING/F	HYS	.95	.09	7D	25	AIR	Paint
ENAMEL 453-4-5/CA-112 AS 1/1 BV BLUE EPQXY/F	FPC	1.67	.12	16H	25	AIR	Paint
EPON 828/VERSAMID 140/CARBOLAC/SYLOID 620	SHL	1.66	.07	16H	25	AIR	Paint
EPON 956 A/B AS 10G/58 BW/CARBOLAC/NOVACITE 1250	SHL	1.96	.12	2H	66	AIR	Paint
EPON 956 A/B AS 10G/58 BW/CARBOLAC/SYLOID 620	EPP	1.02	.00	7D	25	AIR	Paint
EPPELEY PARSONS BLACK FINCH ELACK PAINT 663-3-2 POLYURETHANE A/B AS 4/1 BW	FPC	13.33	3.95	24H	25	AIR	Paint
FINCH BLACK PAINT 663-3-2 POLYURETHANE A/B AS 4/1 BW	FPC	4.62	.10	16H	66	AIR	Paint
FINCH PRIMER 463-4-4 A/B AS 3/1 BW	FPC	4.42	.00	24H	25	AIR	Paint
FINCH PRIMER 463-4-4 A/B AS 3/1 BW	FPC	7.21	.00	7D	25	AIR	Primer

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MRK CODE	WTML	%CVCN	CURE TIME	CURE TEMP	ATMOS TEMP	APPLICATION
FISHER BLACK COATING 113/113-300 /CARBOLAC/MEK/T-12	GSC FLO SHW	.51 3.85 .05	.02 .28 .01	7D 7D 15M	25 25 93.0	AIR AIR AIR	PALM PALM PALM
FLUOCOIL BLACK PAINT V78VP21							
FLUOROCAL WHITE G794P37	SHW	.67	.05	30H	26.0	AIR	PALM
FSS BLUE PAINT/F	GSC	2.53	.22	10D	22	AIR	PALM
FSS BLUE PAINT/F	GSC	.71	.05	72H	96	AIR	PALM
G 3113 BLACK COATING BALL CHEM ALKYD-SILICONE	BAL	.03	.02	14H	232	AIR	PALM
G-1897 HT ALUMINUM COATING	BAL	.09	.04	1H	232	AIR	PALM
G-3230 ALKYD WHITE PAINT	BAL	.13	.07	24H	225	AIR	Varnish
GE 7031 INSULATING VARNISH - PHENOLIC	GEC	.75	.85	45M	1H	120	AIR
GE 7031 INSULATING VARNISH - PHENOLIC	GEC	6.87	.71	45M	250	AIR	VARNISH
G3FC 657-38 SILICONE WHITE PAINT	GSC	.13	.13	72H	89	E-O	PALM
G3FC 657-41 SILICONE WHITE PAINT	GSC	.17	.13	7D	25	AIR	PALM
G5FC 657-41 SILICONE WHITE PAINT	GSC	.14	.09	3.5D	25	AIR	PALM
G5PC 657-42 SILICONE WHITE PAINT	GSC	.21	.08	4D	66	AIR	PALM
G5PC 657-44 SILICONE WHITE PAINT	GSC	.15	.07	3D	25	AIR	PALM
K-1 URETHANE PRIMER/S FURANE PLASTICS	FPI	9.10	.98	14H	250	AIR	PALM
KAPTON/ALUM/H322/9586 FILM COMPOSITE	APL	3.08	.03	15M	125	AIR	INTERNAL CONTROL
KAPTON/ALUM/H322/9586 FILM COMPOSITE	APL	2.15	.22	24H	125	AIR	INTERNAL CONTROL
KAPTON/ALUM/H322/9588 FILM COMPOSITE	APL	2.33	.25	24H	125	E-J	INTERNAL CONTROL
KOLORANE U-1-6002/9500 PRIMER - GLOSS WHITE ENAMEL	KEE	2.01	.01	24H	225	AIR	PALM SYSTEM
KRYLON 1302 CLEAR COATING MULTICOAT FILM	BCE	7.23	.02	24H	225	AIR	PALM
KRYLON 1602 ULTRA FLAT BLACK PAINT	BCE	5.23	.45	7D	25	AIR	PALM
LAMINATE ASHMAN G40 GRADE EPOXY/FIBERGLASS	ANS	1.39	.01				LADY NATE
LEACH 009 SEMI-GLOSS BLACK LACQUER AEROSOL/F	LCR	1.74	.28	7D	25	AIR	PALM
LEACH 010 FLAT LACQUER AEROSOL/F	LCR	10.82	.54	7D	25	AIR	PALM
LEACH 013 AS 4/1 BV BLUE EPOXY ENAMEL	LGR	4.84	.57	7D	25	AIR	PALM
LEACH 014 AS 4/1 BV GLOSS BLACK EPOXY ENAMEL	BEE	8.48	.52	1H	66	AIR	PALM
LOGO 1709/508 LACQUER/THINNER AS 3/1 BV	BEE	1.65	.23	1H	16.3	AIR	LACQUER
M-152 LACQUER BASECOAT W/ VAC DEP ALUMINUM	BEE	4.82	1.03				LACQUER W/ALUM
M-152 LACQUER BASECOAT W/ THINNERS - SHAYED 2 COATS	BEE	2.43	.19	1H	66	AIR	LACQUER
M-152 LACQUER BASECOAT	BEE	4.04	.03	2H	12.1	AIR	LACQUER
MC469/MC470 AS 4/1 BW BROWN WASH PRIMER	BCL	9.81	.01	30M	25	AIR	MAIN PRIMER
METALAST PRIMER 919/920 AS 1/4 BM	MMI	8.99	.23	1H	60	AIR	PRIMER
METALAST 920 PRIMER/DILUENT AS 4/1 BM	MMI	11.35	.00	1H	225	AIR	PRIMER
MW 101-C10 VELVET BLACK ALKYD	MMI	4.95	.24	1H	25	AIR	PAINT
MW 101-C10 VELVET BLACK ALKYD	MMI	5.02	.02	7D	25	E-4	PAINT

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MFR CODE	#IDL	%CVCM	CURE TIME	CUBE TEMP	ATMOS	APPLICATION
MM 101-C10 VELVET BLACK PAINT ALKYD	MM	6-0.2	-14	96H	210	AIR	PAINT
MM 301-C10 VELVET BLACK	MM	5-17	.02	1H	121	E-6	PAINT
MM 301-C10 VELVET BLACK	MM	5-0.0	.02	1H	25	AIR	PAINT
MM 401 BLACK OVER ZINC CHROMATE	MM	4-82	-12	5D	25	AIR	PAINT COMPOSITE
MM 401-A10 A/B AS 3/1 BV WHITE PAINT	MM	2-88	-02	7D	95	AIR	PAINT
MM 401-A10 A/B AS 3/1 BV WHITE PAINT	MM	2-85	-03	7D	95	E-3	PAINT
MM 401-A10 A/B AS 3/1 BV VELVET WHITE	MM	3-0.9	-0.8	7D	25	AIR	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	MM	2-91	.01	30H	121	AIR	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	MM	3-33	.02	30H	121	E-6	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	MM	3-18	.00	30H	95	E-5	PAINT
MM 401-C10 VELVET BLACK OVER E-SOLDER 3022 LAYUP	MM	2-76	.01	34H	120	AIR	PAINT COMPOSITE
MM 403-C10 A/B AS 3-5/1 BV VELVET BLACK	MM	3-11	.01	14H	24H	E-2	COAT COAT
MM 403-C10 A/B AS 3/1 BV VELVET BLACK	MM	3-0.0	.07	10H	71	AIR	PAINT
MS 125 WHITE COATING BASO4/PVA/KRYLON	GSC	1-70	.10	14D	25	AIR	OPTICAL PAINT
MS 242 BEING 2K/FACTING K2S103/T102/ZNO/A1203	GSC	1-66	.33	24H	25	AIR	PAINT
MS 74 WHITE COATING K2S103/T102/ZNO/A1203	GSC	6-27	-0.3	48H	100	AIR	PAINT
MS 74 SILANE 6020 ERIMIN COMPOSITIVE/F	GSC	4-54	-0.0	7D	195	AIR	PAINT COMPOSITE
MSA 101E GREEN PAINT OIL 650/CHROMIC OXIDE	GSC	4-36	-0.0	7D	95	AIR	PAINT
MSA 101E GREEN PAINT OIL 650/CHROMIC OXIDE	GSC	1-04	-47	6H	66	AIR	PAINT
MSA 102 BLACK PAINT CARBON BLACK	GSC	1-11	-0.1	39H	150	AIR	PAINT
MSA 103 BLACK PAINT OIL 650/CARBON BLACK	GSC	0-95	-35	6H	150	AIR	PAINT
MSA 5 BLACK COATING	GSC	1-3-14	-0.2	39H	95	AIR	PAINT
MSA 82 WHITE PAINT OIL 650/NA TREATED ZNO	GSC	2-24	-0.4	48H	100	AIR	PAINT
MSA 82 WHITE PAINT OIL 650/ZINC OXIDE	GSC	1-67	-2.58	6H	150	AIR	PAINT
MSA 90 WHITE PAINT OIL 650/POTASSIUM TREATED ZNO	GSC	1-58	-56	6H	95	AIR	PAINT
MSA 94E BLACK PAINT	GSC	3-66	-0.0	16H	25	AIR	PAINT
MSA 95E WHITE PAINT	GSC	4-30	-2.3	24H	50	AIR	PAINT
MSA 96A GREEN PAINT	GSC	2-75	-95	24H	50	AIR	PAINT
NE 560 WATER BASE LATEX S102 PAINT	NBL	2-96	-0.3	21D	55	AIR	PAINT
NEXTEL 3101-1 COATING 8/1 BLACK SUEDE PAINT	MM	2-21	-37	7D	25	AIR	PAINT
NS 43C WHITE PAINT K2S103/ZNO/A1203/T102	GSC	3-40	-0.0	14D	25	AIR	PAINT
NS 59A GREEN REGULATED PAINT K2S103/ZNO AS 1/3 BL W/1% COBALT	GSC	2-16	-90	24H	25	AIR	PAINT
OI 650 RESIN WHITE PAINT GSPC SHAI	ITR	2-59	-32	1H	121	AIR	PAINT BASE
OI 650 RESIN WHITE PAINT GSPC TRIOL	GSC	2-51	-0.02	10H	100	AIR	PAINT
OI 650G - GIORI MOL /ZAO GSFC	ITR	2-87	-51	1H	16.3	AIR	PAINT BASE

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MFR CODE	STYL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
P 764 EPOXY PRIMER EPON 828 BASE P 764-1A WHITE SILICONE PAINT PAINT WHITE EPOXY FER MIL C 2275C/F	GSC GSC ROP CAC	2.66 1.59 1.50 2.04	.00 .03 .07 .23	72H 7D 14D 6H	25 60 25 71	AIR PAINT PAINT PAINT	PAINT PAINT PAINT PAINT
PAINT 2019 OVER PRIMER 2012	CAC	2.92	.07	16H	25	AIR	PAINT
PALADIN BLACK SATIN LACQUER	WJR	.27	.13	24H	93	E-O	LACQUER
PALADIN BLACK SATIN LACQUER PC-5 BLACK COATING PITT-GLAZE 16-40-2/120 BASE ACRYLIC/EPOXY WHITE PAINT PITT-GLAZE 16-90-1/16-80-2 BASE ACRYLIC/EPOXY WHITE PAINT PKT WHITE PAINT OIL 650/POTASSIUM TITANATE AS 1/1 BN PLASTIKOTE PAINTER VARNISH POTASSIUM TITANATE WHITE PAINT 150 GSFCSHAI PR 1506 CLEAR PRIMER	WJR GCE PPG PPG GSC BLK GSC PPC PRC PRC PRC PRC PRC DUP DES RAN RAN	6.42 4.31 2.80 4.23 1.95 1.75 1.84 3.97 5.97 5.41 12.49 3.43 2.50 3.23 2.32	1.69 1.12 0.97 1.13 1.44 1.44 1.44 0.5 2.29 1.30 0.1 0.1 0.9 0.9 -0.2 -0.2	16H 24H 14D 10D 10H 18H 18H 16H 24H 24H 16H 24H 24H 24H 24H 24H	100 25 25 25 30 22.2 22.2 82 82 82 25 25 25 25 25 25	E-4 AIR PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT	LACQUER PAINT PAINT PAINT PAINT VARNISH PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT
PR 420 ORANGE PRIMER PR 420 PRIMER/ACRITONE PREPARAKOTE PRIMER DE SOTO 513-102-1/1 PRIMER RANDOLPH GREEN ZINC CHROMATE PRIMER RANDOLPH GREEN ZINC CHROMATE	SH HSD ABC GRO ETI ETI ETI ETI ETI	3.23 7.06 5.24 4.01 9.24 3.00 3.00 3.00 3.00	22 19 19 0.2 -0.2 1.00 30H 10H 15H	24H 24H 24H 24H 24H 24H 24H 24H 24H	25 25 25 25 25 25 25 25 25	AIR PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT	PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT
PRIMER ZINC CHROMATE 3-1W-24/3-1E-6 AS 3/1 BW EPOXY URETHANE WHITE PRIMER 6362/CAT 6341 AS 1/1 BW EPOXY PROLITE P-527-66/P-863-66 AS 1/1 BW YELLOW EPOXY/F PROFOAR 4000 BLACK EPOXY PAINT/545 RED PRIMER	SH HSD ABC GRO ETI ETI ETI ETI ETI	3.23 7.06 5.24 4.01 9.24 3.00 3.00 3.00 3.00	22 19 19 0.2 -0.2 1.00 30H 10H 15H	24H 24H 24H 24H 24H 24H 24H 24H 24H	25 25 25 25 25 25 25 25 25	AIR PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT	PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT
PR 401 WHITE PAINT PT 401/H-11 AS 16/1 BW WHITE PAINT	PTI	1.87	.07	15H	25	AIR	PAINT
PT 401/H-11 AS 16/1 BW GLOSSY WHITE EPOXY	PTI	1.05	.10	15H	25	AIR	PAINT
PT 426 A/E AS 1/1 EV TUP/FILM GLOSSY WHITE EPOXY PT 426 A/E AS 1/1 EV TUP/FILM GLOSSY WHITE EPOXY PT 100 SILICONE WHITE PAINT PYROMARK STANDARD WHITE SILICONE ON ALUMINUM PYROMARK STANDARD WHITE SILICONE ON EPOXY P4 15A EPOXY PRIMER	PTI PTI WEP TEA WEP	1.89 1.28 2.86 -0.6 3.97	.14 15 0.2 -0.2 .10	90H 7D 2H 6	12.1 25 6.6 12.1 25	AIR PAINT PAINT PAINT PAINT	PAINT PAINT PAINT PAINT PAINT

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MPN CODE	%THI	%VOC	CURE TIME	CURE TEMP	AIR TIME	AIR TEMP	APPLICATION
P527 PRIMER EPOXY/FOLYAMIDE	ABC	2.16	.04	15H	75	AIR	PRIMER	
S1-2577 CLEAR SILICONE	DCC	2.77	.85	25D	25	AIR	PAINT	BASE
S1-12 MICRO SHIELD PAINT	GSC	1.70	.47	21D	25	AIR	PAINT	
BS-12 MICRO SHIELD PAINT ON FOIL	GSC	6.54	2.36	21D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT BM242 BATCH 9	HCC	5.58	4.01	7D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT BM252 BATCH 5	GSC	4.44	.05	7D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT CN258 BATCH 3	GEC	4.46	.05	7D	25	AIR	PAINT	BASE
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT CN258 BATCH 3	GEC	6.55	.03	7D	25	AIR	PAINT	BASE
RTV 602/SRC 05 AS 0-25% CAT FOLAC 1/TOLUENE BLACK PAINT	GEC	4.41	.03	7D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT FOLAC 1/TOLUENE BLACK PAINT	GSC	1.19	.18	7D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT FOLAC 1/TOLUENE BLACK PAINT	GSC	6.59	.09	7D	25	AIR	PAINT	
RTV 602/SRC 05 AS 0-25% CAT FOLAC 1/TOLUENE BLACK PAINT	GSC	3.33	.09	7D	25	AIR	PAINT	
S-13-G SILICONE NO/TOLUENE DEVOL BATCH 4	GSC	4.42	.09	48H	25	AIR	PAINT	
S-13-G WHITE PAINT STANDARD D236C	ITR	8.2	.16	16H	12	AIR	E-O	
S-13-G-LO WHITE PAINT	ITR	.56	.13	48H	25	AIR	PAINT	
S-13-G-LO WHITE PAINT A/B AS 100/1 BN W/TOLUENE	ITR	.54	.10	24H	25	AIR	PAINT	
S-13-G-LO WHITE PAINT E-127 NO PRIMER	ITR	.50	.12	7D	25	AIR	PAINT	
S-13-G-LO WHITE PAINT E-389 NO PRIMER	ITR	.37	.04	24H	25	AIR	PAINT	
S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-406	ITR	.44	.02	24H	25	AIR	PAINT	
S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-497	ITR	.49	.03	24H	25	AIR	PAINT	
S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-555	ITR	.47	.03	24H	25	AIR	PAINT	
SCHENECTADY VANISHE 1700	SCH	1.19	.23	24H	25	AIR	PAINT	
SCOTCHCAST PRIMER XR-5137 A/B AS 5/1 BN THIN COAT	SCH	16.62	.19	24H	25	AIR	PAINT	
SICON BLACK 7X9055 SILICONE	MM	8.58	.36	24H	25	AIR	PAINT	
SICON BLACK 7X9055 SILICONE	DEX	6.94	.04	24H	25	AIR	PAINT	
SICON BLACK 7X933/S4 AS 4/1 BN	MM	1.98	.62	30H	24	AIR	PAINT	
SICON B-8A929 BLACK PAINT	MM	1.39	.62	30H	24	AIR	PAINT	
SICON 3X258 LEAFING ALUMINUM	MM	4.05	.05	3H	10	AIR	PAINT	
SICON 3X258 LEAFING ALUMINUM	MM	4.02	.05	3H	10	AIR	PAINT	
SICON 3X258 LEAFING ALUMINUM	MM	.72	.17	48H	25	AIR	PAINT	
SICON 3X258 LEAFING ALUMINUM	MM	.70	.11	48H	25	AIR	PAINT	
SICON 3X258 LEAFING ALUMINUM	MM	.79	.09	48H	25	AIR	E-J	
SILCOSET 152 PRIMER/F	ICA	3.30	.09	8D	25	AIR	PAINT	
SOLITHANE 113/300/T-12/FERRIC OXIDE/CABOSIL	GSC	.38	.06	7D	25	AIR	PAINT	
SPACE GARD 4-B-33 FLAT BLACK COATING	DEX	8.95	.05	24H	25	AIR	PAINT	
SPACE GARD 4-B-33 CVER RANDOLPH PRIMER T54/F	DEX	1.78	.02	24H	25	AIR	PAINT	COMPOSITE
SPEREX SP-101 VHT HIGH TEMP COATING-WHITE SILICONE	DEX	7.9	.03	24H	69	AIR	PAINT	COMPOSITE
SPEREX SP-101 VHT HIGH TEMP COATING-WHITE SILICONE	SPX	7.44	.03	7D	25	AIR	E-2	
SR 240 SILICONE LEAFING ALUMINUM	GEC	.29	.01	15H	25	AIR	PAINT	
SR 240 SILICONE LEAFING ALUMINUM	GEC	.58	.19	48H	25	AIR	PAINT	
SR 240 SILICONE LEAFING ALUMINUM	GEC	.74	.24	48H	25	AIR	E-J	

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	MFN CODE	WT/L	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
SILICONE LEAPING ALUMINUM	GEC	.72	.18	48H	25	AIR	PAINT
STAG SOLITE 20678 CVER STAG PREVOX 1766 PRIMER/P	HAB	4.27	.39	8D	71	E-J	PAINT SYSTEM
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/F	DES	3.97	.13	7D	25	AIR	PAINT
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/F	DES	1.55	.15	48H	75	E-O	PAINT
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/F	DES	1.51	.19	72H	100	AIR	PAINT
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/F	DES	5.03	.21	7D	25	AIR	PAINT
THERMELIC G 3334 BLACK ANTI-TRACK COATING	BAL	8.55	.36	304	74	AIR	PAINT
TALON AB-894 URETHANE PRIMER - BLUE	DAY	.75	.36	5H	93	AIR	PAINT
TITON Q-317 URETHANE PRIMER - BROWN	DAY	.75	.12	1H	125	AIR	PAINT
TILE COPE 1201A/B AS 1/1 BY WHITE EPOXY PAINT	STA	5.96	.79	1H	60	AIR	PAINT
TOESE SEAL FLUORESCENT LACQUER	CPC	10.16	1.08	2H	60	AIR	PAINT
VARNISH STERLING THERMOPOXY T-653-LBH	STV	1.82	.31	7D	25	AIR	PAINT
VARNISH STERLING THERMOPOXY T-653-LBH	STV	.70	.02	8H	135	AIR	PAINT
VINSYNITE AU-1/BT 215 AS 1/2 LV	SPC	6.86	.01	4H	180	AIR	PAINT
Y-210 VARNISH - THERMODUR	STV	1.27	.24	24H	25	E-J	PAINT
Y-210 VARNISH - THERMODUR	STV	.56	.07	20H	149	AIR	PAINT
Z-93 POTASSIUM SILICATE ZNO2 WATER BASE	GRU	2.54	.00	24H	125	E-O	PAINT
Z-6040 SILANE PRIMER	DCC	2.97	1.46	24H	25	AIR	PAINT

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	MFR CODE	XTEL	ZCVCM	CURE TIME	AIRUS	APPLICATION	
ABLEBOND 731-1 A/B AS 100/47 BW YELLOW EPOXY	AAC	1.92	-11	3H	AIR	POTTING	
ABLESTIK 857-1 A/B AS 100/47 EPOXY	AAC	1.98	-10	4H	AIR	POTTING	
ABLETHERM 7-2 FILLED SILICONE	AAC	2.29	-10	4H	AIR	POTTING	
ABLETHERM 7-5 A/E AS 100GM/7 DRIPS FILLED SILICONE	AAC	.68	-19	4H	AIR	POTTING	
ABLETHERM 7-5 A/E AS 100GM/7 DRIPS FILLED SILICONE	AAC	.51	-28	24H	65	E-O	
ABLETHERM 7-5 OXIDE FILLED SILICONE	AAC	.31	-14	8H	80	AIR	POTTING
ABLETHERM 708-3 CERAMIC FILLED SOUTHLANE 113/300/T12	AAC	.16	-09	4H	AIR	POTTING	
ACTON EPOXY - CLEAR	ACT	1.32	-09	4H	AIR	POTTING	
ADIPRENE 100/40 SOLITHANE C-300/C8BN BLK AS 100/40/1.4	DUP	1.74	-07	24H	50	AIR	POTTING
ALLCAST 1776 POTTING CPND FOR OPTICAL COMPONENTS	BAC	1.25	-01	24H	25	AIR	POTTING
ARALDITE AW100/HV994 AS 1/1 BW EPOXY	CIB	.57	-15	3H	60	AIR	AUD POTTING
ARALDITE AW134B/HV994 AS 1/100 BW EPOXY	CIB	1.59	-01	24H	25	AIR	POTTING
ARALDITE CY179/606/606/AS-XL EPOXY	CIB	1.16	-04	16H	93	AIR	POTTING
ARALDITE CY236/HV968 AS 10/3 BW SPURAY	CIB	1.14	-07	3H	70	AIR	POTTING
ARALDITE HY750/HV972/MARBLE FLOUR AS 100/27/100 BW	CIB	.26	-01	3H	80	AIR	POTTING
ARALDITE HY750/HV974 AS 20/4 BW EPOXY	CIB	.27	-03	4H	190	AIR	AUD POTTING
ARALDITE D004/506/CALESSIL/DP-138/HV951/PC-1244 EPOXY	CIB	3.74	-07	4H	60	AIR	POTTING
A3-4219/HD-3404 AS 100/9 BW EPOXY	HYS	2.96	-06	2H	25	AIR	POTTING
BACON IND IMPREGNANT NO 2	BAC	.27	-01	4H	71	AIR	POTTING
BAKER POLYURETHANE SYSTEM 65	BAK	.28	-03	4H	190	AIR	CURE COAT-POT
BAKER POLYURETHANE SYSTEM 65 BR-620 ONE COMPONENT HEAT CURING EPOXY	BAK	.26	-01	16H	80	AIR	CURE COAT-POT
BSL 201 A/B AS 11/1 BW	ACC	2.6	-01	16H	69	AIR	POTTING
BSL 201 A/E AS 11/1 BW	CIB	2.52	-03	16H	121	AIR	POTTING
BSL 206 BLACK EPOXY	CIB	1.46	-05	3H	25	AIR	POTTING
BSL 206 BLACK EPOXY	CIB	1.42	-15	2H	120	AIR	POTTING
BSL 208 EPOXY	CIB	.82	-11	1H	120	AIR	POTTING
C-18FA/B AS 4/5 BW 1/1% H-3441 BLACK EPOXY	CIB	.49	-10	1H	194	AIR	POTTING
CASTALL CX2303B CLEAR SILICONE	HYS	.74	-06	4H	130	AIR	POTTING
CEBDA 60 POLYURETHANE	CAS	1.61	-57	4H	130	AIR	POTTING
CEBLA 70 POLYURETHANE	CEL	1.98	-24	4H	130	AIR	POTTING
CF 3003 EPOXY FE HUGHES CONNECTOR 1380320 HO1	CCL	1.07	-36	4H	130	AIR	POTTING
CHEMICK 205/CHEMICK 220 AS 1/1 BW AS FREE FILM	HAC	.43	-04	4H	130	AIR	POTTING
CHEMICK 205/CHEMICK 220 AS 1/1 BW ON SOIL	HCC	.95	-03	30M	25	AIR	POTTING PRIMER
COLAD 984 A/B AS 3/1 BW WHITE QUICK SET EPOXY	HCC	6.89	-01	30M	93	AIR	POTTING PRIMER
COLAD 984 A/B AS 3/1 BW WHITE QUICK SET EPOXY	CCD	1.19	-02	30M	60	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CCD	.84	-01	16H	190	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.23	-02	24H	60	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.27	-02	10H	60	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.43	-02	24H	60	E-J	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.38	-01	24H	55	AIR	POTTING
CONATHANE EN-12 A/E AS 100/55 BW POLYURETHANE	CON	.43	-01	24H	55	AIR	POTTING
CONATHANE EN-12 A/E AS 11-3/15 BW BUTADIENE URETHANE	CON	.44	-02	12H	38	AIR	POTTING
CONATHANE EN-4 A/E AS 100/17.5 BW CARBON BLACK	CON	1.15	-49	24H	80	AIR	POTTING
CONATHANE EN-5 A/B AS 100/17.5 BW POLYURETHANE	CON	.78	-02	7D	25	AIR	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	MFKA CODE	XMTL	ACYCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CONATHANE EN-7 A/B AS 100/17.5 BW POLYURETHANE	CON	.32	.01	20H	2J	AIR	POTTING
CONATHANE EN-9 POLYURETHANE	CON	.39	.00	24H	6J	AIR	POTTING
CONOPIC EN-30 A/B AS 50/22.75 BW CLEAR URETDANE	CON	.74	.01	16H	9J	AIR	POTTING
CORFL 65/50 DTA AS 100/7 BW EPOXY	ACC	.83	.01	24H	6J	AIR	POTTING FOAM
CPR 23-2A/2B AS 23.4/9.9 BW	UJC	1.04	.00	18H	25	AIR	POTTING
CREST 7340/7109/7120 EPOXY	CPC	.35	.04	2d	9J	AIR	POTTING
L15-015 EPOXY	HYS	5.69	.00	2H	204	AIR	POTTING
C2-4259/3401	HYS	.55	.00	20	25	AIR	POTTING
C9-F700 EPOXY	HYS	.16	.00	4H	77	AIR	POTTING
C9-F183/H2-3561/P-1244 EPOXY	HYS	.50	.00	24H	125	AIR	POTTING
C9-4190/H8-3553 AS 10/13 BV RED FLEXIBLE EPOXY	HIS	.43	.03	25H	145	AIR	POTTING
C9-4198/H2-1561 AS 100/15 BW EPOXY	HYS	.38	.09	8H	65	AIR	POTTING
C9-4218/H2-3561 AS 20/3 BW BLACK EPOXY	HYS	.46	.05	8H	25	AIR	POTTING
C9-5349/H2-3420 AS 100/8.3 BW EPOXY	HYS	.98	.05	8H	149	AIR	INSECTANT
DAPCN 35 SEALANT / IMPREGNANT	HMC	13.98	.05	6H	124	E-2	POTTING FOAM
DC 3101 LOH DENSITY SYNTACTIC FOAM A/B AS 10/1 BW	DCC	1.25	.30	2H	25	AIR	ENCAPS
DC 3110/E AS 10% CAT F	DCC	1.96	.30	30D	25	AIR	ENCAPS
DC 3110/5 AS 10% CAT S	DCC	1.13	.34	30D	25	AIR	ENCAPS
DC 3116/CAT S/1-12 AS 10/1 BW - 10% T-12	DCC	1.46	.48	4H	66	AIR	ENCAPS
DC 3118/DIETHYL SILOXANE	DCC	.92	.32	20	32	AIR	POTTING - ENCAPS
DC 93-500 A/B AS 10/1 BW SILICONE	DCC	.20	.00	7D	25	AIR	POTTING - ENCAPS
DC 93-500 A/B AS 10/1 BW SILICONE	DCC	.16	.00	7D	25	AIR	POTTING - ENCAPS
DC 93-500 A/B AS 10/1 BW SILICONE	DCC	.29	.00	7D	25	AIR	POTTING - ENCAPS
DC 93-500 A/B AS 10/1 BW SILICONE LQ1 E2 134-16	DCC	.17	.02	7D	25	AIR	POTTING - ENCAPS
DC 93-500 FM 029/5 AS 10/1 BW	DCC	.17	.02	7D	25	AIR	POTTING - ENCAPS
DC 93-500 FM 029/5 AS 10/1 BW	DCC	.39	.12	7D	25	AIR	POTTING - ENCAPS
DC 93-500 FM 029/5 AS 10/1 BW	DCC	.28	.12	7D	25	AIR	POTTING - ENCAPS
DC 93-500 FM 028/5 AS 10/1 BW	DCC	.24	.12	7D	25	AIR	POTTING - ENCAPS
DC 96-052 A/Y3 AS 10/1 BW	DCC	.72	.24	8H	25	AIR	POTTING
DELTA CAST 153-K-A EPOXY KIT 15.3/RTA2 AS 20/1.5 BW	WAK	.62	.01	8H	85	AIR	POTTING
DER 332/MDA/LITHIAFLAX/P-200 MODIFIED GRAY	DOM	.50	.00	4D	25	AIR	POTTING
DER 332/MDA/LITHIAFLAX/P-200 CARBON BLACK MODIFIED	DOM	.48	.00	18H	65	PSL	POTTING
DER 332/TETA AS 10/1 BW EPOXY	DOM	.54	.00	18H	65	PSL	POTTING
DER 332/732/AEP/SR-82 AS 60/40/15/4 DROPS SR-82	DOM	.34	.03	2H	60	AIR	POTTING
DER 332/732/AEP/SR-82 AS 60/40/16/4 DROPS SR-82	DOM	.32	.07	12H	60	AIR	POTTING
DER 332LC/HV AS 10.5/18 BW EPOXY	DOM	.33	.01	1H	60	AIR	POTTING
DOLPHON CB-1078/EE-2000 AS 20/1 BW BLACK EPOXY	JCD	2.09	.01	12H	25	AIR	POTTING
DOLPHON CR-1050/EE-2010 AS 20/7 BW	JCD	2.80	.01	24H	90	AIR	POTTING
E 788 POTTING RESIN	USP	1.25	.01	3D	25	AIR	POTTING
E 876 EPOXY EA 9309 A/E AS 104/23 BW EPOXY LOT FAAS 90551	USP	.88	.02	4H	177	AIR	POTTING
EA 9309 A/E AS 104/23 BW EPOXY LOT FAAS 90551	HYS	3.27	.02	24H	121	AIR	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL		HFR CODE	XTHL	XCVN	CURE TIME	ATMOS	APPLICATION	
EA 9309-3 A/B AS 160/22/0.5% POLYPROPYLENE BEADS BW		HYS HYS	.95 .99	.03 .02	24H 24H	AIR AIR	POTTING POTTING	
EA 9309-3 A/B AS 160/22/0.5% POLYPROPYLENE BEADS BW		HYS HYS	.95 .99	.03 .02	24H 24H	AIR AIR	POTTING POTTING	
EA 9559 BROWN EPOXY		HYS HYS	.80 .92	.00 .19	4H 7D	7.7 2.5	AIR AIR	POTTING POTTING
ECCOBOND 1663 A/B AS 1/10 BW SILICONE SEALANT		HYS HYS	1.02	.00	4H	7.7	AIR	POTTING
ECCOBOND 1663 A/B AS 1/10 BW SILICONE SEALANT		HYS HYS	1.02	.00	4H	7.7	AIR	POTTING
ECCOBOND 24 A/B AS 100/28 BW 4/4-7% BW BLUE PIGMENT		EMC EMC	1.94	.22	30D	2.5	AIR	POTTING
ECCOBOND 24 A/B AS 30/8 BW CLEAR EPOXY		EMC EMC	1.69	.43	7D	2.5	AIR	POTTING
ECCOBOND 45LV/15LV AS 4/1 BW EPOXY		EMC EMC	1.31	.13	7D	2.5	AIR	POTTING
ECCOBOND 582/CAT 9 AS 100/7 BW EPOXY		EMC EMC	2.24	.73	24H	5.9	AIR	POTTING
ECCOFoAM FP 12-10 A/L AS 100/12 BW POLYURETHANE FOAM		EMC EMC	3.58	.02	16H	2.5	AIR	POTTING
ECCOFoAM FP 12-10 A/L AS 100/12 BW POLYURETHANE FOAM		EMC EMC	3.54	.06	24H	4.0	AIR	POTTING
ECCOFoAM FPH 12-10 F A/B AS 4/3 BW POLYURETHANE FOAM		EMC EMC	3.45	.06	24H	4.0	AIR	POTTING
ECCOFoAM FPH/12-2H POLYURETHANE FOAM		EMC EMC	2.10	.03	24H	4.0	AIR	POTTING
ECCOFoAM FPH/12-2H POLYURETHANE FOAM		EMC EMC	.99	.07	24H	6.0	AIR	POTTING
ECCOFoAM FPH/12-4H POLYURETHANE FOAM		EMC EMC	1.08	.10	12H	6.0	AIR	POTTING
ECCOFoAM FPH/12-4H POLYURETHANE FOAM		EMC EMC	1.08	.12	6.0H	6.0	AIR	POTTING
ECCOFoAM SH 8# CU FT POLYURETHANE FOAM		EMC EMC	.98	.08	48H	100	AIR	POTTING
ECCOFoAM SH 8# CU FT POLYURETHANE FOAM		EMC EMC	.78	.08	48H	100	AIR	POTTING
ECCOSEAL #19/CAT 11 AS 100/16 BW EPOXY - AMBER		EMC EMC	1.33	.08	48H	100	AIR	POTTING
ECCOSEAL #19/CAT 20 AS 100/15 BW BLACK EPOXY		EMC EMC	7.38	.34	16H	7.7	AIR	POTTING
ECCOSEAL 1218 A/E AS 10/7 BW EPOXY		EMC EMC	.27	.04	4H	7.7	AIR	POTTING
ECCOSIL 4640/CAT 25 AS 0/3% CAT SYNTACTIC FOAM		EMC EMC	1.03	.35	12H	1.77	AIR	POTTING
ECCOSIL 4640/CAT 5G AS 0/3% CAT SYNTACTIC FOAM		EMC EMC	.91	.24	16H	2.5	AIR	POTTING
ECCOSIL 4850/CAT 25 AS 100/0.5 BW SILICONE		EMC EMC	1.28	.35	16H	6.6	AIR	POTTING
ECCOSIL 4850/CAT 25 AS 100/0.5 BW SILICONE		EMC EMC	1.21	.34	2H	6.6	AIR	POTTING
EMC 90 - BLACK		PAC PAC	.69	.01	1H	1.1	AIR	POTTING
EPOCAST N4E-053/CAT 9816		PPI PPI	.07	.02	24H	1.50	AIR	POTTING
EPOCAST 202-100		PPI PPI	5.24	.01	2H	9.3	AIR	POTTING
EPOCAST 202-60		PPI PPI	5.54	.01	5H	6.6	AIR	POTTING
EPOCAST 202-9615 AS 10/8 BW SYNTACTIC EPOXY FOAM		PPI PPI	5.69	.02	48H	2.5	AIR	POTTING
EPOCAST 8219 A/B AS 5/1 BW SYNTACTIC EPOXY FOAM		PPI PPI	2.94	.10	48H	8.0	AIR	POTTING
EPON 815/U AS 4/1 EW EPOXY		SHL SHL	1.14	.01	4H	9.3	AIR	POTTING
EPON 815/V AS 50/50 BW EPOXY		SHL SHL	.73	.06	30D	2.5	AIR	POTTING
EPON 815/V 140 AS 65/35 BW EPOXY		SHL SHL	.40	.02	24H	2.5	AIR	POTTING
EPON 815/V 140/SILFLAKE 135 AS 5/5/38 BW		GSC GSC	.65	.03	7D	1.0	AIR	SILICONE ROTTING
EPON 825/V 140 AS 166 BW EPOXY		SHL SHL	.32	.02	24H	7.5	AIR	POTTING
EPON 826/871/2 AS 166 BW EPOXY		IFT IFT	.64	.01	24H	8.0	AIR	POTTING
EPON 828/DER 732/CAB-O-SIL/AEP		SHL SHL	1.46	.06	4H	13.0	AIR	POTTING
EPON 828/EM 308 AS 2/1 BW EPOXY		SHL SHL	.34	.06	2H	7.4	AIR	POTTING
EPON 828/LINDENIDE 6/DMP 30 AS 100/90/1 BW EPOXY		SHL SHL	.34	.06	1H	10.0	AIR	POTTING

SECTION 14 --- POTTING COMPOUNDS

MATERIAL	NFS CODE	#ML	%CVC/M	CURE TIME	CURE TEMP	AMBI.	APPLICATION
EPON 828/LINOLIDE 8/DMP 3J AS 10/0/90/1 BN EPOXY/SAND	SHL	.04	.00	1d 48H	100	AIR	POTTING
EPON 828/VERSAMID 125 AS 50/50 BN EPOXY	SHL	1.93	.26	2H	50	AIR	POTTING
EPON 828/VERSAMID 125 AS 65/35 BN EPOXY	SHL	.79	.31	7D	25	AIR	POTTING
EPON 828/VERSAMID 125 AS 69/33 BN EPOXY	SHL	.49	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 125 AS 79/33 BN EPOXY	SHL	.55	.05	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 45/55 BN EPOXY	SHL	.74	.19	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 50/50 BN EPOXY	SHL	1.28	.23	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 55/50 BN EPOXY	SHL	.86	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 60/40 BN EPOXY	SHL	.43	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 65/35 BN EPOXY	SHL	.30	.00	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 66/33 BN EPOXY	SHL	.26	.00	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 70/30 BN EPOXY	GSC	.19	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 140/B40 MICROBALLOONS	GSC	.61	.03	48H	25	AIR	POTTING
EPON 828/VERSAMID 140/CARBOLAC/B-22A BUBBLES	SHL	1.74	.19	16H	25	AIR	POTTING
EPON 828/VERSAMID 140/CARBOLAC/GLASS BEADS	SHL	1.80	.39	2H	60	AIR	POTTING PRIMER
EPON 828/VERSAMID 140/XYLENE/NIBK	SHL	6.05	.04	7D	25	AIR	POTTING PRIMER
EPON 828/871/AEP AS 35/65/15.5 BN	SHL	1.01	.05	42H	37	AIR	POTTING
EPON 828/871/AEP AS 40/60/15.5 BN	SHL	1.46	.02	4D	25	AIR	POTTING
EPON 828/871/AEP AS 40/60/15.5 BN	SHL	1.34	.02	7D	25	AIR	POTTING
EPOXI-71B PRE-MEASURED MIX PKG	HYS	.34	.02	9H	25	AIR	POTTING
EPOXYLATED ACRYLATE	EPIC	.45	.03	30d	81	AIR	POTTING
FLUORINATED EPOXYLATED ACRYLATE	NRL	.12	.00	4H	121	AIR	POTTING
FORMULATION E EPOXY	NAL	.59	.00	7D	25	AIR	POTTING
FR-8136-W A/B AS 2/1 BN LOW DENSITY EPOXY - CREAM	GEV	2.43	.02	1H	65	AIR	POTTING
FULTON 404 ACETYL FEEFOLN 80/20	PBC	6.35	.02	24H	25	AIR	POTTING
GENEOXY 190/VERSAMID 140 AS 3/2 BN AMBER EPOXY	LNP	.52	.01	12H	25	AIR	POTTING
HUMISEAL 2B74 A/E AS 100/85 BN POLYURETHANE	CTC	1.12	.05	24H	60	AIR	POTTING
HY-MAT 7534 MOLDED GRAPHITE EPOXY	FIB	1.47	.00	3H	177	AIR	POTTING
HYDANTOIN TC-1-149-1 LIGHT GRAY EPOXY	WEI	.36	.00	16H	135	AIR	POTTING
HYSOL 0025 A/B AS 1/1 BN INSULBOND 810/INSULCURE 24 AS 4/3 BN BLACK EPOXY	HYS	1.97	.03	72H	150	AIR	POTTING
INSULBOND 810/INSULCURE 24 AS 4/3 BN BLACK EPOXY	PSL	1.52	.06	24H	25	AIR	POTTING
INSTRUCR P5003-FK22 GLASS FILLED THERMOSET POLYESTER	CCL	.50	.02	7D	25	AIR	ENCAPSULANT
LC4/ACT EAS A/B AS 100/6 BN EPOXY ENCAPSULANT	BAC	.12	.00	48H	56	AIR	POTTING
LOCTITE PMS-10 IMPREG RESIN CLEAR	LTC	3.40	.11	3D	190	AIR	IMPERMEANT
LOCTITE PMS-10 PMDA METAL SEALANT	LTC	3.24	.03	1H	25	AIR	IMPERMEANT
LOCTITE PMS-10 E PWIR METAL SEALANT	LTC	3.80	.20	31	20	AIR	IMPERMEANT
LOCTITE PMS-50 E PWIR METAL SEALANT	LTC	3.97	.31	56	20	AIR	IMPERMEANT
LOCTITE PMS-90 E PWIR METAL SEALANT	LTC	9.93	.56	4.06	24H	AIR	IMPERMEANT
HERECO 4501 A/B AS 1/1 BN CLEAR FLEXIBLE EPOXY	HEP	6.59	.03	7H	125	AIR	POTTING
PC 12-007 A/B AS 5/4 BN	HYC	6.17	.01	8H	80	AIR	POTTING

SECTION 14 - POTTING COMPOUNDS

MATERIAL	NFR CODE	XTM	%CVCM	CURE TIME	CURE TEMP	ATDS	APPLICATION
PC 12-007 A/B AS 5/4 BW	HYS	4.97	.00	12H	121	AIR	POTTING
PC 22 A/B AS 3/1 E	HYS	1.75	.49	8H	66	AIR	POTTING
PD 200-16 FOAMED RTV 560	GEC	1.12	.49	10H	177	AIR	POTTING
PD 200-16 FOAMED RTV 560	GEC	.03	.02	10H	93	AIR	POTTING
POLYETHYLENE POTTING CARTRIDGE	USE	1.10	.35	24H	177	E-O	POTTING
PR 1524 A/B AS 26/100 BW POLYURETHANE	PRC	.82	.09	10H	82	AIR	POTTING
PR 1525 A/B AS 8/25 BW POLYURETHANE	PRC	.64	.11	16H	82	AIR	POTTING
PR 1527 A/B AS 26/100 BW POLYURETHANE	PRC	.92	.10	2D	251	AIR	POTTING
PR 1538 A/B AS 32/100 BW POLYURETHANE	PRC	1.06	.09	24H	92	AIR	POTTING
PR 1538 A/B AS 32/100 BW POLYURETHANE	PRC	.67	.06	24H	92	AIR	POTTING
PR 1546 A/B AS 40/100 BW POLYURETHANE THICK BLOCK	PRC	.72	.01	7D	25	AIR	POTTING
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	PRC	.74	.02	72H	25	AIR	POTTING
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	PRC	.86	.03	24H	100	E-C	POTTING
PR 1570 A/B AS 7.7/100 BW POLYURETHANE	PRC	.35	.03	24H	25	AIR	POTTING
PR 1570 A/B AS 1/4 BW POLYURETHANE	PRC	.34	.06	16H	82	AIR	POTTING
PR 1574 A/B AS 18/100 BW POLYURETHANE	PRC	1.49	.30	72H	60	AIR	POTTING
PR 1574 A/E AS 18/100 BW POLYURETHANE	PRC	.40	.04	24H	25	AIR	POTTING
PR 1592 A/B AS 53/100 BW POLYURETHANE	PRC	.54	.02	23H	74	AIR	POTTING
PR 1592 A/B AS 53/100 BW POLYURETHANE	PRC	1.01	.06	5D	25	AIR	POTTING
PR 1930-2 A/B AS 10/1 BW SILICONE	PRC	1.02	.27	17H	65	AIR	POTTING
PROSEAL 799 A/B AS 100/41 BW PURPLE POLYURETHANE	CPI	9.97	.71	14D	25	AIR	POTTING
Q3-6567 A/B AS 1/1 BW BLACK SILICONE POLYURETHANE	CDC	9.95	.41	12H	82	AIR	POTTING
R-1779 CYCLOALIPHATIC EPOXY UNFILLED	CIB	.31	.03	30H	160	AIR	EPOXY RESIN
R-1779 CYCLOALIPHATIC EPOXY/FILLED	CIB	1.17	.05	30H	160	AIR	POTTING
R-2566 0.5% BWCATRED SILICONE LOT 274	ACG	1.34	.05	7D	25	AIR	POTTING
R3 10-51 A/B AS 2/3 BW FLEXIBLE EPOXY	ALL	1.97	.38	24H	25	AIR	POTTING
R3 10-51 A/B AS 2/3 BW FLEXIBLE EPOXY	ALL	1.98	.42	8H	22	AIR	POTTING
R3 8-1338 A/B AS 100/65 BW POLYURETHANE	ALL	.51	.04	8H	60	E-2	POTTING
R3 8-1338 A/B AS 50/34 BW POLYURETHANE	ALL	.75	.04	24H	60	E-2	POTTING
RF 1730 A/B AS 1/1 BW POLYURETHANE (NO MOCA OR TDI)	REF	.85	.00	7D	25	AIR	POTTING
RTV 11/T-12 AS 0.6% T-12 WHITE SILICONE	GEC	.67	.25	40H	65	AIR	POTTING
RTV 11/T-12 AS 100/2 BW SILICONE	GEC	1.08	.37	24H	150	AIR	POTTING
RTV 511 0.5% CAT DEVOLAT 160°C LOI JN 170	GSC	.39	.05	24H	130	AIR	ADHESIVE
RTV 511 0.5% CAT 9811 AS 6.0% BW CAT GREEN SILICONE	GEC	3.59	.64	30D	25	AIR	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	API CODE	#TML	%CVCN	CURE TIME	CURE TEMP	ADHES	APPLICATION
RTV 566 0-15% CAT SILICONE LOT GJ 124	GEC	-13	.01	7D	25	AIR	POTTING
RTV 566 0-17.5% B-Ca SILICONE-U-SIL	GEC	-12	.02			AIR	POTTING
RTV 566 0-2% B-Ca SILICONE	GEC	-23	.03	24H	25	AIR	POTTING-ADH
RTV 566 0-.5% B-Ca SILICONE	GEC	-41	.04	24H	25	AIR	POTTING-ADH
RTV 567 0-3% B-Ca SILICONE	GEC	-18	.05	12D	25	AIR	POTTING-ADH
RTV 601/PRIMER 1200/DC2000 FLUID	GEC	3.43	1.54	1.5H	45	AIR	POTTING
RTV 602/SRC 04 AS 100/1 BW	GSC	2.23	.56	1H	50	AIR	POTTING
RTV 602/SRC 05 AS C-14 CAT LOT DK 263 VIAGIN RESIN	GSC	1.96	.98	2H	60	AIR	POTTING
RTV 602/SRC 05 AS C-25% CAT LOT DK 263 VIRGIN RESIN	GEC	.59	.89	5D	60	AIR	POTTING
RTV 602/SRC 03 AS C-44% CAT/CAPSIOL LOT BM242 BATCH 5	GSC	2.97	.89	7D	65	AIR	POTTING
RTV 31 A/E AS 10/1 BW CLEAR SILICONE	GBC	.91	.37	4H	65	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 125C LOT HD183	GSC	.15	.97	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 125C LOT KA210	GSC	.13	.97	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 125C LOT BTCH 4	GSC	.19	.97	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BC226	GSC	.17	.002	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BC226	GSC	.15	.002	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BTCH 2	GSC	.16	.004	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BTCH 3	GSC	.11	.004	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BTCH 6	GSC	.16	.004	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT BTCH 7	GSC	.20	.008	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 140C LOT KA210	GSC	.16	.008	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 1	GEC	.21	.017	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 4	GSC	.18	.017	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 5	GSC	.71	.041	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 9	GSC	.11	.005	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 15	GSC	.15	.005	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 23	GSC	.15	.005	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 9	GSC	.12	.005	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT JG202 VACUUM	GSC	.14	.001	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT JG202 VACUUM	GSC	.14	.001	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL LOT KA202 VIRGIN RESIN	GEC	1.33	.62	7D	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN DEVOL AT 150C	GSC	.72	.41	7D	25	AIR	POTTING
RTV 615 A/B AS 9/1 BN DEVOL AT 150C	GSC	.16	.03	7D	25	AIR	POTTING
RTV 615 SILICONE	GSC	1.82	.96	1H	100	AIR	POTTING-ENCAPS
RTV 615 A/B AS 10/1 BN BLACK SILICONE	GEC	1.41	.50	24H	25	AIR	POTTING
RTV 615 A/B AS 10/1 BN SILICONE	GEC	1.30	.50	24H	25	AIR	POTTING
RTV 625 A/B AS 10/1 BN DEVOL AT 125C LOT KF084	GSC	1.39	.05	7D	25	AIR	POTTING
RTV 625 A/B AS 10/1 BN DISTILL # 177C # VAC # C82-1	GEY	.96	.31	4H	822	AIR	POTTING
RTV 625 A/B AS 10/1 BN DISTILL # 177C # VAC # C82-2	GZY	.63	.19	4H	25	AIR	POTTING
RTV 625 A/B AS 10/1 BN CLEAR SILICONE	GEC	.95	.19	4H	65	AIR	POTTING
RTV 625 A/B AS 10/1 BN CLEAR SILICONE	GEC	1.42	.65	7D	60	AIR	POTTING
RTV 670 A/D AS 10/1 BN CLEAR SILICONE	GEC	1.37	.65	1H	125	AIR	POTTING
RTV 670 A/B AS 10/1 BN CLEAR SILICONE	GEC	1.25	.23	16H	65	AIR	POTTING
RTV 670 A/B AS 10/1 BN CLEAR SILICONE	GEC	1.02	.23	16H	65	AIR	POTTING
RTV 670 A/B AS 10/1 BN CLEAR SILICONE	GEC	1.12	.28	16H	65	AIR	POTTING
RTV 670 A/B AS 10/1 BN CLEAR SILICONE	GEC	1.16	.24	16H	65	AIR	POTTING
RTV 6243/CAT 9856 AS 9/6/6 BW	GBC	1.16	.87	7D	65	AIR	AIR-ENCAPS
RTV 6243/CAT 9856 AS 9/6/4 BW	GBC	1.16	.87	7D	65	AIR	AIR-ENCAPS
RTV 6263/CAT 9858 AS 9/6/6 BW	GBC	1.16	.87	7D	65	AIR	AIR-ENCAPS
RTV 6372/CAT 9858 AS 9/5/5 BW	GBC	1.32	.21	24H	65	AIR	SILICONE

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	NFR CODE	WTML	%CVCN	CUBE TIME	CUBE TEMP	AEMOS	APPLICATION
RTV 8373/CAT 9858 AS 97/3 BW	GEC	1-19	.20	16H	65	AIR	SILICONE
RTV 8382/CAT 9858 AS 95/3 BW	GEC	1-22	.38	16H	65	AIR	ADHESIVE
RTV 8383/CAT 9858 AS 97/3 BW	GEC	1-66	.23	24H	65	AIR	SILICONE
R3 - 2038/H2-3404 AS 100/11 BW BLACK EPOXY	GYS	1-76	.02	1H	25	AIR	MOULD CURE
R3 - 2038/H2-3404 AS 100/11 BW CLEAR	HYS	2-01	.12	7D	93	AIR	PURGING
R3 - 2039/H2-3404 AS 9/1 BW EPOXY	HYS	2-64	.03	1H	90	AIR	POTTING
SCOTCHCAST XB-5088 A/B AS 2/5 BW EPOXY	MM	38-03	.20	10H	150	AIR	POTTING
SCOTCHCAST XB-5088 A/B AS 2/5 BW EPOXY	MM	37-66	.20	20H	25	AIR	POTTING
SCOTCHCAST XB-5133 EPOXY CASTING POWDER	MM	4-42	.40	30H	65	AIR	POTTING
SCOTCHCAST XB-5240 RUSTY BROWN EPOXY	MM	4-29	1-06	3H	149	AIR	POTTING
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	MM	.55	.01	16H	65	AIR	POTTING
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	MM	.25	.02	24H	69	AIR	POTTING
SCOTCHCAST 226 A/B AS 2/5 BW POLYURETHANE	MM	1-05	.05	72H	50	AIR	POTTING
SCOTCHCAST 255 A/B AS 2/3 BW EPOXY BROWN	MM	.65	.16	16H	25	AIR	POTTING
SCOTCHCAST 255 A/B AS 2/3 BW EPOXY	MM	.98	.12	24H	75	AIR	ADHESIVE
SCOTCHCAST 280 A/B AS 2/3 BW EPOXY	MM	.52	.05	4H	82	AIR	POTTING
SCOTCHCAST 281 A/B AS 2/3 BW BLACK EPOXY	MM	.48	.14	4H	120	AIR	POTTING
SCOTCHCAST 281 A/B AS 2/3 BW GRAY EPOXY	MM	.56	.08	24H	155	AIR	POTTING
SCOTCHCAST 282 A/B AS 2/3 BW SEMI RIGID BLACK EPOXY	MM	.35	.02	12H	130	AIR	POTTING
SCOTCHCAST 282 A/B AS 2/3 BW SEMI RIGID BLACK EPOXY	MM	.49	.10	72H	150	AIR	POTTING
SHUR-LOK SLE 3007 EPOXY - GRAY	SLK	3-60	.04	8H	65	AIR	POTTING
SHUR-LOK SLE 3009 EPOXY - GREEN	SLK	1-20	.18	12H	121	AIR	POTTING
SHUR-LOCK SLE 3010 EPOXY POTTING CPND	SLK	1-22	.04	8H	65	AIR	POTTING
SILASTIC E A/B AS 10/1 BW WHITE SILICONE	DCC	2-08	.71	72H	125	AIR	POTTING
SILASTIC E A/B AS 10/1 BW WHITE SILICONE DEVOL 10QC	GSC	1-22	.39	7D	25	AIR	POTTING
SILASTIC 6-220 A/E/610 DILUENT AS 25/1/1.3 LI	DCC	1-38	.40	24H	60	AIR	POTTING
SILASTIC 736 ONE PART RED SILICONE	DCC	2-93	.45	7D	25	AIR	ADHESIVE
SILASTIC 736 ONE PART RED SILICONE	EML	1-58	.24	6D	25	AIR	POTTING
SNRD 432 90A WHITE	GEV	1-14	.17	48H	100	E-2	POTTING
SOLITHANE 113/300 AS 100/120 BW FORMULA 6	TCC	1-40	.09	16H	65	AIR	POTTING
SOLITHANE 113/300 AS 100/150 BW FORMULA 7	TCC	1-37	.08	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	1-31	.04	16H	50	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW 33% ALUM PIGMENT	TCC	1-31	.04	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/80 BW FORMULA 2	TCC	1-69	.09	7D	25	AIR	POTTING
SOLITHANE 113/300 FORMULA 6 OVER PRIMER 919/920	TCC	1-72	.03	24H	25	AIR	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	MFR CODE	STL	XCVN	CURE TIME	CURE TEMP	AIR DRY	APPLICATION
SOLITHANE 113/300/CABOSIL MSS/RO DABINE B/T-12	TCC	.47	.00	7D	25	Air	POTTING
SOLITHANE 113/300/CABOSIL MSS/T-12/FLUORESCENT DYE	TCC	.42	.00	7D	25	Air	POTTING
SOLITHANE 113/300/CABOSIL MSS/T-12/FLUORESCENT DYE	TCC	.46	.04	7D	25	Air	POTTING
SOLITHANE 113/300/ETDL AS 100/80/5/B	TCC	.66	.09	15H	25H	Air	POTTING
SOLITHANE 113/300/ETDL AS 25/18/25/1 DROB BW	TCC	.12	.01	7D	25	Air	POTTING
SOLITHANE 113/300/TIPA/ALQUINA T-61	TCC	.14	.01	4H	60	Air	ADHESIVE
SOLITHANE 113/300/TRACER-TECH T-704/80	SLA	.36	.02	7D	25	Air	POTTING
SOLITHANE 113/300/2NC AS 100/44/6 BW FORMULA 11	TCC	.44	.04	20H	60	Air	POTTING
SOLITHANE 113/300/2NC AS 100/44/6 BW FORMULA 11	TCC	.34	.00	16H	70	Air	POTTING
SOLITHANE 113/300/328 AS 100/51/4.5 BW FORMULA 10	TCC	.34	.00	16H	70	Air	POTTING
SOLITHANE 113/300/328 AS 100/51/4.5 BW FORMULA 10	TCC	.21	.00	21D	25	Air	POTTING
SOLITHANE 113/300/328/35A GLASS BUBBLES	TCC	.53	.00	16H	70	Air	POTTING
SOLITHANE 113/300/328/ECCOSPHERE'S STI	TCC	.39	.04	7D	25	Air	POTTING
STYCAST CPC-41/A/B AS 5/B BW POLYURETHANE FOAM	EMC	.74	.09	16H	60	Air	Foam
STYCAST 1090-S1/44V AS 100/23 BW EPOXY FOAM	EMC	.49	.06	24H	120	Air	Foam
STYCAST 1095/11 AS 100/12 BW EPOXY FOAM	EMC	.38	.04	3H	95	Air	Foam
STYCAST 1095/9 AS 100/9 BW BLACK EPOXY FOAM	EMC	.72	.07	16H	150	Air	Foam-POTTING
STYCAST 1467/CAT 9 AS 100/7 BW EPOXY FOAM	EMC	.14	.00	16H	25	Air	POTTING
STYCAST 2057/CAT 9 AS 100/6 BW EPOXY	EMC	.72	.01	24H	77	Air	POTTING
STYCAST 2651/CAT 9 EPOXY	EMC	.14	.00	16H	25	Air	POTTING
STYCAST 2651/CAT 9 AS 4/1 BW BLACK EPOXY	EMC	.37	.03	8H	25	Air	POTTING
STYCAST 2762/CAT 14 AS 4/1 BW BLACK EPOXY	EMC	.93	.00	2H	120	Air	POTTING
STYCAST 2762/CAT 14 AS 25/2 BW BLACK EPOXY	EMC	.27	.00	3d	149	Air	POTTING
STYCAST 2850 FT/9 AS 100/3 BW EPOXY	EMC	.25	.01	20H	25	Air	POTTING
STYCAST 2850 FT/11 AS 100/3 BW BLACK EPOXY	EMC	.49	.01	20H	70	Air	POTTING
STYCAST 2850 FT/11 AS 20/1 BW BLACK EPOXY	EMC	.47	.01	20H	60	Air	POTTING
STYCAST 2850 FT/11 AS 25/1 BW BLUE EPOXY	EMC	.30	.04	30H	120	Air	POTTING
STYCAST 2850 FT/24LV AS 25/1 BW BLUE EPOXY	EMC	.00	.00	2H	200	Air	POTTING
STYCAST 2850 FT/24LV AS 25/1 BW BLUE EPOXY	EMC	.02	.04	24H	25	Air	POTTING
STYCAST 2850 FT/24LV AS 25/1 BW DARK RED EPOXY	EMC	.34	.01	16H	65	Air	POTTING
STYCAST 2850 FT/24LV AS 25/1 BW DARK RED EPOXY	EMC	.29	.04	16H	70	Air	POTTING
STYCAST 3050/11 ONE COMP CEM. SILICONE WHITE	SWS	.04	.01	16H	105	Air	POTTING
STYCAST 3050/11 ONE COMP CEM. SILICONE WHITE	DCC	.04	.01	16H	70	Air	POTTING
STYCAST 3050/11 ONE COMP CEM. SILICONE WHITE	GSC	.75	.01	90H	226	Air	POTTING
STYCAST 3050/18 AS 10/3 BW DARK RED EPOXY	EMC	.47	.07	7D	25	Air	POTTING
STYCAST 3050/19 AS 100/8 BW EPOXY	EMC	.10	.01	8H	60	Air	POTTING
STYCAST 3050/19 AS 100/8 BW EPOXY	EMC	.64	.01	21H	225	Air	POTTING
SWS 934 ONE COMP CEM. SILICONE WHITE	SWS	.43	.01	110	190	Air	SILICONE
SYLGARD 182 A/B AS 10/1 BW	DCC	.09	.03	24H	25	Air	POTTING
SYLGARD 182 A/B AS 10/1 BW	DCC	.01	.03	7D	25	Air	SILICONE
SYLGARD 184 A/B AS 10/1 BW	DCC	.01	.03	1H	100	Air	SILICONE
SYLGARD 185 A/B AS 10/1 BW	DCC	.54	.04	24H	121	Air	SILICONE
SYLGARD 187 A/B AS 10/1 BW SILICONE	DCC	1.25	.04	4H	66	Air	HOLD UP TIME
SYLGARD 187 A/B AS 10/1 BW SILICONE	DCC	2.45	.03	8H	82	Air	SILICONE
THALCO 331/732/AEP/BLACK DYE	THI	1.54	.04	30H	82	Air	POTTING
TRUCAST 111M/THUCURE 901 EPOXY	FEN	1.36	.01	24H	66	Air	POTTING
TRUCAST 111M/THUCURE 901 EPOXY	FEN	.00	.01	3H	66	Air	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	MFR CODE	%ML	%CVCM	CURE TIME	CURE TEMP	ATDS	APPLICATION
TJ-0590/XHD-0158 AS 1/1 BW GREEN POLYURETHANE	HYS	.85	.02	4H	25	AIR	POTTING
URALANE 1723 A/B AS 2/1 BW POLYURETHANE FOAM	FPI	2.06	.08	6H	50	AIR	POTTING FOAM
URALANE 5712 A/B AS 1/5 BW POLYURETHANE	FPI	16.28	1.18	16H	82	AIR	POTTING
URALANE 5753 LV A/B AS 1/2 BW POLYURETHANE/PRIMER PR 1	FPI	.87	.01	7D	25	AIR	POTTING
URALANE 5753 LV A/B AS 1/2 BW POLYURETHANE	FPI	.87	.02	14D	25	AIR	POTTING
V 357-80 A/B AS 1/1 BW BLACK POLYURETHANE	USP	2.19	.14	2H	92	AIR	POTTING
VARY-FLEX EPOXY EC1YANIDE	SIP	.64	.01	24H	25	AIR	POTTING
XCU-M179 A/B AS 10/4 BW POLYURETHANE	HYS	15.72	1.06	40H	121	AIR	POTTING
XCU-M179 A/B AS 10/4 BW POLYURETHANE	HYS	17.61	1.51	16H	85	AIR	POTTING
XR-5140 A/B AS 2/3 BW BROWN SEMI-RIGID EPOXY	MM	1.29	.52	7D	25	AIR	POTTING
XR-5140 A/B AS 2/3 BW BROWN SEMI-RIGID EPOXY	MM	1.39	.59	16H	90	AIR	POTTING
XR-5166 A/B AS 2/3 BW FLEXIBLE BLACK EPOXY	MM	.51	.88	8H	66	E-C	POTTING
XRU-0021/XHD-0165 AS 1/1 BW BLACK POLYURETHANE	HYS	.87	.07	6H	79	AIR	POTTING
XUS-0050 A/B AS 10C/36 BW	HYS	.83	.01	4H	25	AIR	POTTING
YARSLEY L100/6/2 POLYURETHANE FORMULATION CLEAR	YAR	1.93	.29	24H	50	AIR	POTTING
YARSLEY L100/6/2 POLYURETHANE FORMULATION CLEAR	YAR	1.77	.12	48H	25	AIR	POTTING

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	MPN CODE	#TM	%CYC	CURE TIME	CURE TEMP	ADDS	APPLICATION
ABLETHERM 7-5 A/E AS 100GM/4 DROPS FILLED SILICONE AF-E-332-11 ERYTHYLENE DERIVATIVE	AAC TRW AMS MET LOR LOR	:38 :60 :11 :42 :32 :39 :28	:12 :08 :04 :11 :09 :5.2 :5.2	6H 48H 4H 16H 16H 24H 24H	6.7 12.1 2.4 25.0 25.0 164 164	A/E A/E A/E A/E A/E A/E	RFI GASKET DAD DEA CUSHION GASKET GRIPSET DAD DEA DAD DEA DAD DEA DAD DEA DAD DEA DAD DEA
AMS 3325 SILICON RUBBER							
AMMEX XECON SILICONE FILLED SILICONE							
BTR LI SILICONE GASKET CB 1077-40 BROWN							
BTR RUBBER HD22-31							
BTR RUBBER HD22-31	LOR ENJ	1.39 2.28	:13 :28	1.39 :28	1.3 1.3	A/E A/E	DAD DEA DAD DEA
BTR RUBBER HD22-22-2 IN ALUMINUM SANDWICH	LOR	1.41	:20	1.41	2.0	A/E	DAD DEA
BTR RUBBER HTD (J-9330-5-1)/21	LOR	1.34	:45	1.34	4.5	A/E	DAD DEA
BTR RUBBER VIBRATION ISOLATOR HT 2-100	ENJ	3.52	1.07	3.52	1.07	A/E	KUBIK KUBIK
BUTYL 218-N CURED	ENJ	2.09	1.36	2.09	1.36	A/E	KUBIK KUBIK
BUTYL 218-N UNCURED	ENJ	3.17	1.36	3.17	1.36	A/E	DAD DEA DAD DEA
CB 4012 FLUOROSILICONE COATED DACRON FABRIC	CHR	3.29	1.39	3.29	1.39	A/E	KUBIK KUBIK
CHO - SEAL 1239 A/E INFORCED SILICONE GASKET SEAL RED	CHO	4.41	1.12	4.41	1.12	A/E	GASKET GASKET
CHO - SEAL 1285 ELEC COND SILICONE BLUE	CHO	4.12	1.12	4.12	1.12	A/E	GASKET GASKET
CHO - SEAL 1285 ELEC COND SILICONE BLUE	CHO	4.40	1.13	4.40	1.13	A/E	TULIP CONTROL TULIP CONTROL
CHO - THERE 1642 A/B AS 100/3 BW FILLED BLUE SILICONE	CHO	3.94	1.07	3.94	1.07	A/E	ELAPSOID CONTROL
CHO - THERE 1671 T/FIRM CUND SHEET - WHITE SILICONE	CHO	3.97	1.07	3.97	1.07	A/E	ELAPSOID CONTROL
CHB 1809 GRAY CLEAR SUPPORTED SILICONE FILM/SHEET	CHR	4.64	1.14	4.64	1.14	AIR	RFI GASKET RFI GASKET
CHORLASTIC RFI GASKET 8016 ALUM CLOTH/NEOPRENE	CHR	3.73	1.24	3.73	1.24	A/E	RFI GASKET RFI GASKET
CHORLASTIC RFI GASKET 8020 ALUM CLOTH/NEOPRENE	CHR	3.52	1.14	3.52	1.14	A/E	RFI GASKET RFI GASKET
CHORLASTIC RFI GASKET 8518 ALUM CLOTH/SILICONE	CHR	4.42	1.13	4.42	1.13	A/E	FUJIA RUBBER
CHORLASTIC RUBBER K10470 #1	CHR	6.7	2.4	6H	2.4	AIR	FUJIA RUBBER
CHORLASTIC RUBBER K10470 SILICONE SPONGE BROWN	CHR	1.10	0.3	24H	24H	E-0	DAD DEA
CHORLASTIC R10450 GLASS REINE DARK GRAY SILICONE	CHR	1.12	0.5	24H	24H	AIR	DAD DEA
CHORLASTIC R10460 DARK BLUE SILICONE SPONGE SHEET	CHR	4.49	1.18	4.49	1.18	AIR	DAD DEA
CHORLASTIC R10480 ERWIN SILICONE SPONGE - MEDIUM	CHR	4.45	1.18	4.45	1.18	AIR	DAD DEA
CHORLASTIC R10480 ERWIN SILICONE SPONGE - MEDIUM	CHR	6.61	3.1	6.61	3.1	AIR	DAD DEA
CHORLASTIC R10480 FED SILICONE SPONGE - SOFT	CHR	6.94	3.38	6.94	3.38	AIR	DAD DEA
CHORLASTIC R10480 FED SILICONE SPONGE - SOFT	CHR	6.67	3.38	6.67	3.38	AIR	DAD DEA
CHORLASTIC R10480 FED SILICONE SPONGE - SOFT	CHR	1.16	5.6	1.16	5.6	AIR	GASKET GASKET
CHORLASTIC R10480 FED SILICONE SPONGE - SOFT	CHR	1.21	5.6	1.21	5.6	AIR	GASKET GASKET
CHORLASTIC 3109 SILICONE RUBBER SHEET GEN PURPOSE	CHR	1.93	2.7	1.93	2.7	AIR	SPACER SPACER
CHORLASTIC 3320 SILICONE RUBBER SHEET GEN PURPOSE	CHR	1.97	4.3	1.97	4.3	AIR	SPACER SPACER
CHORLASTIC 4003 SILICONE RUBBER SHEET GEN PURPOSE	CHR	2.26	4.8H	2.26	4.8H	AIR	SPACER SPACER
CHORLASTIC 5003 SILICONE RUBBER SHEET GEN PURPOSE	CHR	1.90	5.9	1.90	5.9	AIR	SPACER SPACER
CHORLASTIC 6003 SILICONE RUBBER SHEET GEN PURPOSE	CHR	1.81	3.4	1.81	3.4	AIR	SPACER SPACER
CHORLASTIC 7003 SILICONE RUBBER SHEET GEN PURPOSE	CHR	4.45	1.15	4.45	1.15	A/E	GASKET GASKET
CHORLASTIC 9235 SILICONE RUBBER SHEET HIGH PERFOR	CHR	4.93	4.3	4.93	4.3	A/E	GASKET GASKET
CHORLASTIC 9275 SILICONE RUBBER SHEET HIGH PERFOR	CHR	7.7	2.9	7.7	2.9	A/E	GASKET GASKET
CHORLASTIC 9355 SILICONE RUBBER SHEET HIGH PERFOR	CHR	6.7	1.8	6.7	1.8	A/E	GASKET GASKET
CORK/DC100 SHEET	ACI	5.55	1.16	5.55	1.16	A/E	DAD DEA
CORK/DC100 SHEET	ACI	5.05	1.16	5.05	1.16	A/E	DAD DEA
CP 1006 NATURAL RUBBER	BAR	1.16	1.16	1.16	1.16	A/E	DAD DEA
CP 6002 SILICONE RUBBER	BAR	4.35	1.16	4.35	1.16	A/E	DAD DEA

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	MPA CODE	XTEL BAR	XCVN	CURE TIME	CURE TEMP	AIROS	APPLICATION
CP 6002 SILICONE RUBBER							
CP 6007 SILICONE RUBBER	BAR	3.08	.58	15H	177	AIR	DADPER
CP 6007 SILICONE RUBBER	BAR	1.15	.35	15H	177	AIR	DADPER
CYANOPRENE 1880 CLEAR THERMOPLASTIC POLYURETHANE	ACC	1.16	.18	4H	143	AIR	GASKET
DC 6-1104 LOT FMG95313	DCC	*1.19	-34	7D	25	AIR	SEALANT
DC 6-1104 LOT GA003347	DCC	*2.0	-0.3	7D	25	AIR	SEALANT
DC 6-1104 LOT GAC8348	DCC	*1.16	-0.3	7D	25	AIR	SEALANT
DC 6-1104 LOT GA091568	DCC	*1.14	-0.3	7D	25	AIR	SEALANT
DC 6-1104 SAMPLE A LOT FM108-046	DCC	*7.5	-0.39	40D	25	AIR	SEALANT
DC 6-1104 SAMPLE B LOT FM108-061	DCC	*7.5	-4.3	40D	25	AIR	SEALANT
DC 6-1104 SAMPLE C LOT FM108-087	DCC	*4.2	-2.4	40D	25	AIR	SEALANT
DC 6-1104 SAMPLE D LOT FM108-088	DCC	*4.3	-2.4	40D	25	AIR	SEALANT
DC 6-1104 SAMPLE E LOT FM128-102	DCC	*4.9	-2.6	28D	25	AIR	SEALANT
DC 6-1104 SAMPLE F LOT FM128-103	DCC	*4.7	-2.6	28D	25	AIR	SEALANT
DC 6-1104 SAMPLE G LOT FM128-104	DCC	*4.6	-2.6	28D	25	AIR	SEALANT
DC 6-1104 SAMPLE H LOT FM128-104	DCC	*4.9	-2.7	26D	25	AIR	SEALANT
DC 6-1104 SAMPLE I LOT FM128-104	DCC	*4.7	-2.4	30D	25	AIR	SEALANT
DC 6-1104 SAMPLE J LOT FM128-102	DCC	*4.8	-2.6	30D	25	AIR	SEALANT
DC 6-1104 SAMPLE K LOT FM128-102	DCC	*4.0	-2.6	30D	25	AIR	SEALANT
DC 6-1104 V-1232 BLUE FERRO DYE	DCC	*3.3	-0.3	24H	25	AIR	SEALANT
DC 6-1104 V-1236 YELLOW FERRO DYE	DCC	*2.9	-0.3	24H	25	AIR	SEALANT
DC 6-1104 V-1244 BLACK FERRO DYE	DCC	*2.1	-0.3	24H	25	AIR	SEALANT
DC 6-1104 V-1247 BLACK FERRO DYE	DCC	*4.2	-0.7	24H	25	AIR	SEALANT
DC 6-1104 V-1250 V-1936 V-1936	DCC	*1.3	-0.2	45D	25	AIR	SEALANT
DC 6-1104 V-1251 V-1936 V-1936	DCC	*0.9	-0.1	7D	25	AIR	SEALANT
DC 6-1106 A/B AS 10/1 BW SILICONE	DCC	*1.23	-3.7	24H	E-3	SILICONE	ELASTOMER
DC 90-006 A/B AS 10/1 BW HT SILICONE SEALANT	DCC	*1.23	-3.7	24H	E-3	SILICONE	ELASTOMER
DC 90-031 A/B AS 1C/1 BW ABLATIVE SILICONE SEALANT	DCC	*1.23	-3.7	24H	E-3	SILICONE	ELASTOMER
DC 90-031 SILICONE SEALANT	DCC	*0.98	-1.8	24H	E-3	SILICONE	ELASTOMER
DC 90-092 SILICONE SEALANT	DCC	*.54	-1.5	4H	150	AIR	SEALANT
DC 92-018 SILICONE SEALANT	DCC	*2.03	-2.7	3D	150	AIR	SEALANT
DC 93-006 A/B AS 10/1 BW DARK GRAY SILICONE	DCC	*2.09	-8.2	5D	225	AIR	SEALANT
DC 93-072 A/B AS 10/1 BW SILICONE SEALANT	DCC	*1.95	-2.8	24H	225	AIR	SEALANT
DC 93-072 A/B AS 10/1 BW AEROSPACE SILICONE	DCC	*1.67	-6.0	24H	225	AIR	SEALANT
DC 955 SILICONE ELASTOMER PEROXIDE CAT DI CUP 40C	DCC	*2.12	-4.6	7D	160	AIR	POTTING
DC 96-079 A/B AS 1/1 BW PEROXIDE CAT DI CUP 40C	DCC	*.15	-0.0	6H	177	AIR	ELASTOMER
DE 100 SILICONE RUEBER GE SE 505 BASE	DCC	*.76	-1.9	24H	175	AIR	SILICONE
DE 100 SILICONE RUEBER GE SE 505 BASE	DEC	*.05	-0.2	4H	177	AIR	SILICONE
DUX SEAL EC 1675 A/B AS 1/1 BW POLYSULFIDE SEALANT	JON	2.75	*4.3	30H	232	AIR	SEALANT
EC 3439 EPOXY FOAM WHITE ONE PART SYSTEM	JMM	7.14	*4.8	1H	25	AIR	SEALANT
EC 3524/EC 3624 AS 100/94 BW EPOXY FOAM BLUE	JMM	2.53	*2.8	1H	125	AIR	FOAM SEALANT
	JMM	3.84	*5.1	16H	25	AIR	FOAM SEALANT

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	MFN CODE	RTM	ACVCM	CURE TIME	CURE TEMP	ADDS	APPLICATION
ECCUSIBLE SILVER FILLED SILICONE PASTE AS 100/9 BW	EMC	1.05	.23	7D	25	AIR	W/ SHIELD
ECCOSIL TP-50 A/E AS 100/0-02 BW FILLED SILICONE	EMC	1.07	.14	7D	25	AIR	SEALANT
ECCOSIL 4952/CATE 5C AS 100/0-01 BW FILLED SILICONE	EMC	.24	.10	7D	25	AIR	IDEAL CONTROL
ECCOSIL 4954/CATE 5C AS 100/0-01 BW FILLED SILICONE	DUP	.14	.09				IDEAL CONTROL
ECD 006 PERFLUOROELASTOMER	DUP	.14	.09				SEAL - GASKET
ED-487-50 PERFLUOROELASTOMER	DUP	.51	.93				SEAL
FAIRPRENE M5550 CURED	DUP	.53	.79				ROBUST SEALANT
FAIRPRENE SR5520	BEN	.41	.17				SILICONE
FLUOBOSILICONE GASKET WHITE THREE PART SYSTEM	BEN	.41	.03				SILICONE
FLURAN F5000 BLACK FLUOROELASTOMER TUBING	NPC	.16	.03				TUBING
GEVAC VAC SEALANT 1	NPC	.53	.41				TUBING
GEVAC VAC SEALANT 2	GEC	12.08	1.41	24H	65	AIR	SEALANT
GORE-TEX CARBON LOFTED EXPANDED TEFLON - GRAY	GCR	.05	.00				SEALANT
GORE-TEX DURET TIO ₂ /CARBON AS 9/11W - GRAY/WHITE	GCR	.18	.03				DAMPING
GORE-TEX MODIFIED LIQUID WITH CARBON - BLACK	GCA	.19	.03				DAMPING
GROMMET BLACK RUBBER ADDITIVE G3036	AIR	10.85	4.92				GRADIENT
HS 50/VARIOX/RUBBER ADDITIVES BLUE CONNECTOR INSUL.	DCC	.79	.00				CONN INSUL
HS 50/VARIOX/RUBBER ADDITIVES BLUE CONNECTOR INSUL.	DCC	.13	.01				CONN INSUL
HS 50/VARIOX/RUBBER ADDITIVES BLUE CONNECTOR INSUL.	DCC	.13	.01				CONN INSUL
HYDRIN RUBBER EPICHLOROHYDRIN-ETHYLENE OXIDE HYDRAEL 4055 POLYESTER/ANTIOXIDANT IMPALENE TUBING STABILIZED PCV/POLYPROPYLENE	BFG	1.22	.18				ELASTOMER
INTERFACIAL SEAL SILICONE UC-K-1314	DUP	.22	.08				ELASTOMER
INTERFACIAL SEAL SILICONE UC-K-1314	UCC	.29	.04				TUBING
KALREZ 1050 PERFLUOROELASTOMER	UCC	.49	.13				SEAL
KALREZ 3018 PERFLUOROELASTOMER	DUP	.44	.06				SEAL
KIRKHILL SILICONE SPONGE RUBBER	DUP	.40	.00				SEAL
KIRKHILL SILICONE SPONGE RUBBER	KRC	1.23	.10				SEAL
KIRKHILL SILICONE SPONGE RUBBER	KRC	1.50	.71				GASKET
LATEX SURGICAL TUBING	HDM	6.44					TUBE
LD 400 VIBRATION DAMPER	LDR	6.18	.35				DALE
LST 350 EMI SUPPRESSANT TUBING	LES	3.37	.14	26H	125	AIR	SEAL
ML 6-55 URETHANE HIGH FRICTION ELASTOMER BLUE	NEK	2.22					SEAL
ML 6-55 URETHANE HIGH FRICTION ELASTOMER CLEAR	NEK	1.19	.39				SEAL
MHM 601 A/B AS 10/1 BW SEALANT	HEA	1.20	.36				SEAL
MHM 601 A/B AS 10/1 BW SEALANT	HEA	4.0	.78	24H	25	AIR	SEAL
MOSITES 1028 BLACK FLUOREL SPONGE RUBBER	MOS	.81	.20				SEAL
MOSITES 1028 BLACK FLUOREL SPONGE RUBBER	MOS	.30	.08				SEAL
MOSITES 1028 SPONGE	MOS	.21	.00				SEAL
MOSITES 1059 FLUOROCARBON ELASTOMER BLUE	MOS	.05					ELASTOMER
MOSITES 1071 FLUOREL FLUOROCARBON ELASTOMER CLEAR	MOS	.64	.35				ELASTOMER
MOSITES 1079K FLUOREL FLUOROCARBON ELASTOMER CLEAR	MOS	.24					ELASTOMER
MS-30108 NEOPHANE W GASKET SEAL	NOX	.04					ELASTOMER
O RING - SILICONE	NBR	.07					SEAL
O RING - VITON A	NBR	.04	.85				O-RING
O RINGS FLEXCO 4069 RED SILICONE	AM1	1.12	.29				O-RINGS
O RING 1109 BLACK NITRILE RUBBER	FYC	2.21	.93				O-RINGS
O RING 5560 BLACK NITRILE RUBBER	DSL	1.16	.33				O-RINGS
PARKER O-LUBE BARIUM BASE GREASE	DSL	8.35	.35				O-RINGS
PARKER O-RING B 612-70	PSC	5.78	.61				O-RINGS
PARKER O-RING B 612-70	PSC	4.70	.03				O-RINGS

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	NPN CODE	%THI	ACVCA	CURE TIME	CURE TEMP	ATMOS	APPLICATION
PARKER O-RING E-515-8 VISTALON 404	PSC	1.21		.18			
PARKER O-RING E-572-8 BLACK EPR	PSC	2.22		.47			O-RING
PARKER O-RING E-677-7 RED FLUOROSILICONE	PSC	.32		.03		AIR	O-RING
PARKER O-RING E-606-BU BLUE FLUOROSILICONE	PSC	1.89		.03		AIR	O-RING
PARKER O-RING E-646-BU BLUE FLUOROSILICONE	PSC	4.49		.27		AIR	O-RING
PARKER O-RING E-219-7 BUNA N	PSC	14.74		.25		AIR	O-RING
PARKER O-RING E-299-5 BUNA N	PSC	2.58		.22		AIR	O-RING
PARKER O-RING E-674-70 BUNA N	PSC	4.99		.40		AIR	O-RING
PARKER O-RING S-383-70 RED SILICONE	PSC	*17		.01		AIR	O-RING
PARKER O-RING S-455-70 RED SILICONE	PSC	*18		.02		AIR	O-RING
PARKER O-RING S-604-7 SILICONE	PSC	1.18		.36		AIR	O-RING
PARKER O-RING S-641-5 SILICONE	PSC	2.29		.09		AIR	O-RING
PARKER O-RING V-747-75 VITON DUP 260C FLUOROCARBON	PSC	.19		.09		AIR	O-RING
PARKER O-RING 2-023 NEOPRENE	PSC	.35		.37		AIR	O-RING
PARKER O-RING 77-545 VITON A	PSC	.11		.02		AIR	O-RING
PARKER SEAL S 18C8-50 GREEN SILICONE	PSC					AIR	SEAL
PITTEL CP CONDUCTIVE PUTTY RUBBER A/B AS PAL-MIX	DUP	5.88	2.18	24H	24H	AIR	ELASTIC
PA 1221 A/B AS 10/1 EW POLYSULFIDE	DUP	57.92	2.89	48H	25	AIR	PUTTY
PA 1710 POLYSULFIDE SEALANT	PRC	.38		.04	16H	AIR	GASKET
PR 1710 POLYSULFIDE SEALANT	PRC	.66			25	AIR	SEALANT
PR 165 BLACK POLYURETHANE RUBBER	PRC	1.35		.97	7D	AIR	GASKET
PROSEAL 790-80 A/B AS 10/3 BW	CPA	1.41		.02	24D	AIR	URIDANE
PROSEAL 790-80 A/B AS 10/3 BW	CPT	1.21		.02	24H	AIR	URIDANE
PR2 11165 SILICONE O-RING	PRP	*30		.04	80	AIR	O-RING
PUTTY VACUUM SEALING	PRD	1.87		.48		AIR	SEALANT
PED HIGH VAC SEALANT SILICONE IN XYLENE	PRD	3.55		2-28	2H	AIR	SEALANT
KEDAKE SI 503 REINFORCED SILICON HOSE	RED	1.96		.31		AIR	HOSE
RELIEF CAP - SILICONE RUBBER	HIC	1.20		.28		AIR	CAP
BS 423 SILICONE RUBBER	HIC	5.59		1-37		AIR	SEAL
BS 423 SILICONE RUBBER	HIC	.11		.02	24H	AIR	SEAL
WHITE DANLATEX RUBBER SHEET	GEC	1.25		.03	24H	AIR	SEAL
SBR RUBBER STANDARD UNCURED	DRC	1.76		.52		AIR	GASKET
SE 456/TS-50 SILICONE - TAN	MON	7.23		.34		AIR	RUBBER
SE 456/TS-50 SILICONE - TAN	MON	8.90		.10		AIR	RUBBER
SE 511/U LOW TEMP SILICONE	GEC	1.00		.01	16H	AIR	RUBBER
SE 557/VARUX AS 100/0.3 BW GRAY SILICONE	GEC	.22		.07	4H	AIR	RUBBER
SE 557/VARUX AS 100/0.3 BW GRAY SILICONE	GEC	.17		.02	4H	AIR	RUBBER
SFR 60-60W WHITE SILICONE	SFR	1.91		.39	16H	AIR	RUBBER
SFR 60-60W WHITE SILICONE	SFR	1.43		.11	6H	204	AIR
SFR 60-694W WHITE SILICONE	SFR	3.94		.85			CUSHION
SILASTIC S-508U/T-50 AS 100/1-4 BW SILICONE	SFR	*64		.13	6H	204	CUSHION
SILASTIC 35 SILICONE	DCC	*35		.14	06	24H	ELASTOMER
SILASTIC 675 SILICONE	DCC	*41		.04	5M	249	SILICONE
						116	SEAL-GASKET
						250	AIR

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	MFR CODE	STYL#	%CVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
SILASTIC 68-110 A/E AS 25//1 BW	DCC	1-15	26	24H	25	AIR	SILICONE
SILASTIC 68-120 A/E AS 25//1 BW	DCC	*84	*35	150H	25	AIR	SILICONE
SILASTIC 68-120 A/E AS 25//1 BW	DCC	*88	*25	24H	25	AIR	SILICONE
SILASTIC 68-210 A/E AS 25//1 BW	DCC	1-22	*24	150H	25	AIR	SILICONE
SILASTIC 68-210 A/E AS 25//1 BW	DCC	1-24	*38	24H	25	AIR	SILICONE
SILASTIC 68-210 A/E AS 25//1 BW	DCC	1-91	*16	24H	25	AIR	SILICONE
SILASTIC 68-210 A/E AS 25//1 BW	DCC	1-03	*18	150H	25	AIR	SILICONE
SILASTIC 68-210 A/E AS 25//1 BW	DCC	1-50	*25	24H	25	AIR	SILICONE
SILASTIC 68-310 A/E AS 25//1 BW	DCC	1-24	*33	150H	25	AIR	SILICONE
SILASTIC 68-320 A/E AS 25//1 BW	DCC	1-64	*32	24H	25	AIR	SILICONE
SILASTIC 68-330 A/E AS 25//1 BW	DCC	1-29	*28	24H	25	AIR	SILICONE
SILASTIC 69-210 A/E AS 10//1 BW	DCC	1-02	*24	24H	25	AIR	SILICONE
SILASTIC 69-210 A/E AS 10//1 BW	DCC	1-04	*26	150H	25	AIR	SILICONE
SILASTIC 69-210 IOT EU 103007	DCC	*80	*27	16H	25	AIR	COATING
SILASTIC 69-210 IOT EU 103007	DCC	*92	*08	24H	25	AIR	COATING
SILASTIC 69-220 A/E AS 25//1 BW	DCC	1-16	*02	24H	25	AIR	SILICONE
SILASTIC 69-220 A/E AS 25//1 BW	DCC	1-31	*25	150H	25	AIR	SILICONE
SILASTIC 731 KIV SEALANT PART NON-CORROSIVE SILICONE	DCC	1-39	*38	24H	25	AIR	SEALANT
SILASTIC 738 ONE PART NON-CORROSIVE SILICONE	DCC	1-63	*51	24H	25	AIR	ADH-SEALANT
SILASTIC 75 SILICONE	DCC	1-16	*22	24H	25	AIR	VALVE SEAT
SILASTIC 861/CAT AS 14-2//.55 BW SILICONE	DCC	1-29	*09	3H	204	AIR	SILICONE
SILASTIC 910 GASKET	DCC	1-63	*43	90M	38	AIR	SILICONE
SILICONE RUBBER - VIBRATION DAMPER	DCC	1-49	*03	24H	24.9	AIR	GASKET
SILICONE RUBBER - VIBRATION DAMPER	BAI	*89	*30	24H	24.9	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 CLASS 11B GRADE 55-75 RED	BAI	*57	*81	24H	204	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 CLASS 11B GRADE 55-75 RED	GRB	*60	*20	24H	204	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 CLASS 2 GRADE 55 - GRAY	FCC	1-51	*53	16H	200	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 GRADE 40 RED	FCC	1-51	*53	24H	160	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 GRADE 40 RED	CHP	*36	*21	24H	160	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 GRADE 40 RED	HGP	2-82	*32	24H	175	AIR	GASKET
SILICONE RUBBER FEAM AMS 3332 RED	HGP	1-31	*35	24H	23.2	AIR	SILICONE
SILICONE RUBBER UNION CARBIDE	UCC	*10	*39	24H	204	AIR	CUSHION
SILICONE RUBBER 16254 GRAY SWEET TAN	FCC	1-14	*73	3H	3.9	AIR	DOOR LND
SILICONE RUBBER FAIRING SPKLENE FILL R3065 TYPE HB	TAN	*73	*35	7D	25	AIR	GASKET
SILSS-06R/F SHIELDING SPKLENE GASKET	SAC	*71	*64	7D	25	AIR	SEALANT
SILSS-06R/F SHIELDING SPKLENE GASKET	GEV	*49	*13	11H	135	AIR	SEALANT
SILSS-06R/F SHIELDING SPKLENE GASKET	GEV	1-11	*13	11H	135	AIR	SEALANT
SILRD 100F90 (43-3) FILLED HYDROCARBON RUBBER	GEV	2-46	*27	110H	100	AIR	DAMPER
SILRD 100F90	GEV	1-52	*19	16H	100	AIR	DAMPER
SILRD 100F90 CYCLICHEXANE WASH - INTERNAL PORTION	GEV	1-56	*22	24H	25	AIR	DAMPER
SILRD 100F90 CYCLICHEXANE WASH - SURFACE PORTION	GEV	2-28	*27	24H	25	AIR	DAMPER
SILRD 100F90 FLEXIBLE EPOXY FOAM	GEV	1-10	*11	96H	130	E-O	DAMPER
SILRD 100F90 FLEXIBLE EPOXY FOAM	GEV	1-03	*11	168H	130	E-O	DAMPER
SILRD 100F90 NEW RESIN REPLACEMENT	GEV	1-23	*11	96H	130	E-O	DAMPER
SOLITHANE 113/300 AS 100/80 5% CARBOLAC 2	TCC	1-39	*17	8H	100	E-3	DAMPER
SOLITHANE 113/300/CABOSIL NS/CARBOLAC 1	TCC	*43	*31	7D	25	AIR	SEALANT
SOLITHANE 291	TCC	1-36	*51	7D	25	AIR	SEALANT

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	NBR CODE	#TML	%CVC	CURE TIME	CURE TEMP	ATMOS	APPLICATION
SOLITHANE 29 1/27 1/TIPA AS 100/48.5/1.9 BN	TCC	1.45	.57	1H 16H	60 100	E-3 Air	CUSHION
SPONGE RUBBER SILICONE AMS 3192 0.031#/CU IN	SAC	.91	.40	24H	138	AIR	DAMPER
SPONGE RUBBER SILICONE AMS 3195 0.031#/CU IN	SBC	.71	.40	24H	177	AIR	DAMPER
SPONGE RUBBER SILICONE AMS 1/1 BN SILICONE	SCR	.07	.05	24H	177	AIR	DAMPER
SPONGE RUBBER SWS269/SER546 AS 1/1 BN SILICONE	CWR	.53	.23	42H	177	AIR	DAMPER
SPONGE RUBBER SWS269/SER546 AS 1/1 BN SILICONE	CIR	.48	.23	42H	177	AIR	DAMPER
SR 2702-75 VITON PER MIL R83248 TYPE 2 CLASS 1	STI	.16	.00	24H	260	AIR	SEAL
SR 2724-75 VITON E-60	STI	.46	.00	24H	260	AIR	SEAL
SI 634-70 BUTYL C KING STILLMAN RUBBER	SIS	.93	.10	10H	175	AIR	O RING
TECKNIT 86-10005 BLACK RUBBER GASKET/O RING	TEC	.35	.04	24H	175	AIR	GASKET/O RING
TECKNIT 86-10005 BLACK RUBBER GASKET/O RING	TEC	.99	.04	10H	149	AIR	GASKET/O RING
TH 1006 SILICONE	LMP	.71	.15	2H 4H	204	AIR	SEAT
THERMACOTE 250 THERMAL JOINT CND							
TOAR SEAL A/B AS 1/1 BV	THC	.99	.02	16H	246	AIR	SEALANT
TUBING-SILICONE-BEL GRADE 60 CL2 SPEC ZZR765	VAB	.84	.00	24H	25	AIR	INSULATION
TUBING-SILICONE-BEL GRADE 60 CL2 SPEC ZZR765	NET	.75	.06	24H	166	AIR	ADJ. SEALANT
TYGOTHANE POLYURETHANE TUBING	NET	.09	.04	24H	166	AIR	TUBING
V-700U75/BENZOYL PEROXIDE AS 100/1 BN	MEC	.44	.19	24H	166	AIR	TUBING
VACSEAL SILICONE LEAK SEALER	RES	.47	.01	10H	93	AIR	PIPE
VACSEAL SILICONE LEAK SEALER	SEL	.52	.01	7D	25	AIR	SEALANT
VALCOR O RING - ETV 75	SEL	1.48	.45	24H	100	AIR	SEALANT
VITON A O KING NAS 1593-012	DCC	.25	.09	24H	100	AIR	O KING
VITON B DUPOINT B DUPONT	DUP	.21	.02	24H	100	AIR	WASHED
VITON B-525 FOAM RUBBER BLACK CLOSED CELL	AG1	.89	.00	24H	100	AIR	SEAL
VITON C BOSE IMPREGNATE LACRON DUPONT 84-001	DUP	.86	.04	16H	204	AIR	FOAM DAMPER
WASHER BROWN SPONGE RUBBER SILICONE AMS 3195	DUP	.33	.03	16H	204	AIR	TUBING
WASHER POLYPHENYLENE SULFIDE 40% GLASS FILLED	CHR	.85	.09	19	19	AIR	DAMPER
	THE	.08	.01				WASHED

SECTION 16 -- TAPE

ATERIAL	MFR CODE	XMTL	ACVCM	CURE TIME	CURE TEMP	ATMS	APPLICATION
C-725 TAPE POLYESTER FILM/2 SIDE ACRYLIC ADH/F	AT	1.54	.14				2 SIDED TAPE
C-727 TAPE PVC FILE/2 SIDED ACRYLIC ADH/F	AT	1.24	.21				2 SIDED TAPE
CIRCLE K705 TAPE PVC PROPYLENE FILM/2 SIDE ACB ADH/F	KAS	10.50	4.72				2 SIDED TAPE
DABURIN TAPE ST 275-3/4 SILICONE ADHESIVE TRANSFER FILM/F	DAD	3.78	2.73				TAPE
DENSIL 2403 SEAL TAPE SILICONE ADHESIVE TRANSFER FILM/F	DNN	1.94	.66				TRANSPARENT FILM
DEV SEAL 7580A TAPE POLYESTER FILM/2 SIDE ACE ADH/F	DTC	1.61	.04				TRANSPARENT FILM
DODGE IND TAPE 2045-3 PTFE FILM SILICONE ADH/R	DIN	1.57	.17	24H	60	AIR	2 SIDED TAPE
DODGE IND TAPE 234-2K KAPTON FILM/ACRYLIC ADH/F	DIN	1.20	.24	24H	90	AIR	TAPE
DODGE IND TAPE 234-2K KAPTON FILM/ACRYLIC ADH/F	DIN	1.20	.33	16H	65	AIR	TAPE
PASCAL 715 CHROME REALIZED MYLAR/ACRYLIC ADH/R	APP	.19					TAPE - TAPE
PASSON ALU/ENR FOIL/ACRYLIC ADH/VINYL COAT/R	APP	1.36	.42	16H	65	AIR	TAPE
PASSON TAPE 1 ALUM FOIL/ACRYLIC ADH/A	APP	1.43	.09				2 SIDED TAPE
PASSON TAPE 220 TISSUE PAPER/2 SIDED ACRYLIC ADH/F	APP	2.39	.33				TAPE
PASSON TAPE 431 BLACK POLYETHYLENE/POLYESTER ADH/F	PIB	1.82	.33				ROLLING TAPE
FLBERT TAPE MAC-13 CARBON FIBER MOLDING TAPE	PIB						TAPE
FLUORGAS TAPE 234-2-1K KAPTON/ACRYLIC ADH/F	CHG	83	.03				TAPE
FLUORGAS TAPE 234-2-1K KAPTON/SILICONE ADH/F	OMG	65	.16				TAPE
FLUORGAS TAPE 234-2 SIDE SILICONE ADH/F	OMG	76	.11				2 SIDED TAPE
G 1003 TAPE ALUM KAPTON/SILICONE ADH/R	GTS	1.48	.32				TAPE
G 400201 TAPE ALUMINIZED TEFLON/Y966 ADH/F	GTS	1.48	.32				TAPE
G 405900 TAPE VDA 4 SIDES KAPTON FILM/SR FILM 585 ADH/F	GTS	98	.48	4.8H	125	E-2	2 SIDED TAPE
G 406400 TAPE ALUMINATED KAPTON/ACRYLIC ADH/F	GTS	75	.01				TAPE
G 406403-020 TAPE ALUMINATED KAPTON/ACRYLIC ADH/F	GTS	1.03	.02				TAPE
G 40710 TAPE ALUMINATED KAPTON/SILICONE ADH/F	GTS	1.93	.38				TAPE
G 410310 TAPE ALUM KAPTON 2 SIDE SILICONE ADH/F	GTS	4.45	.57				2 SIDED TAPE
G 410310 TAPE ALUMINATED KAPTON/SILICONE ADH/F	GTS	2.44	.53				TAPE
G-400/100 TAPE/S	GTS	2.94	.08				TAPE
GT 100 TAPE NYLON COMPOSITE AS NYLAB/GT 100 NYLAB	GTS	2.46	.15				TAPE - NYLON
GT 300 TAPE ONE SIDE HEAT SEALING POLYSTER FILM	GTS	2.46	.16				TAPE
IR-9 BLACK PVC TAPE NO ADH	GTS	4.69	1.07	4H	216	AIR	TAPE
KAPTON TAPE H FILM - ALUMINIZED W/MN 467 ADH/F	GMC	4.69	1.04	24H	100	E-2	TAPE
KAPTON TAPE 603-1 SILICONE ADHESIVE/F	MHM	1.50	.61				TAPE
KAPTON TAPE 603A KAPTON/ACRYLIC ADH/A	MHM	80					TAPE
KENDEL TAPE 293 FIBERGLASS/SILICONE ADH/S	TP2	2.92					TAPE
KENDEL TAPE 294 FIBERGLASS/ACRYLIC ADH/S	KEN	2.79	.30				TAPE
LAMANT TAPE 892 ALUM FOIL CONDENSER RUBBER/R	KEN	2.08	.01				TAPE
MM TAPE 7800 ALUMINUM/ACRYLIC ADH/R	MNM	4.60					FOL
MM TAPE X-1170 ALUM FOIL/CONDENSER RUBBER/R	MNM	6.20					TAPE
MM TAPE X-1181 COPPER FOIL/ACRYLIC ADH/F (ECC 4868P)	MNM	.51	.27				TAPE
MM TAPE X-1205 KAPTON/ACRYLIC ADH/F	MNM	.38	.04	1H	125	AIR	TAPE
MM TAPE X-1205 KAPTON/ACRYLIC ADH/R	MNM	1.30	.02				TAPE
MM TAPE X-1237 NYLON PAPER/ACRYLIC ADH/R	MNM	2.16	.35				TAPE
MM TAPE X-1242 ECYESTER/THERMOSET RUBBER ADH/R	MNM	1.19	.42	3H	121	AIR	TAPE
MM TAPE X-1244 NYLON/ACRYLIC ADH/R	MNM	2.90	1.04	16H	120	AIR	TAPE
MM TAPE X-1244 NYLON/ACRYLIC ADH/R	MNM	2.88	1.25	16H	120	E-2	TAPE
MM TAPE X-1267 ENEOS AL/ACRYLIC ADH/F BAKE ON SCABEN	MNM	2.05	1.05	16H	120	E-2	TAPE
MM TAPE X-1267 ENEOS AL/ACRYLIC ADH/F BAKE AS ROLL	MNM	4.44	.21	16H	120	E-2	TAPE
MM TAPE Y-582 TISSUE FILM/2 SIDED ADH/F (Y-9169)	MNM	4.42	.41	2H	121	AIR	2 SIDED TAPE

SECTION 16 - TAPES

MATERIAL	MFR CODE	MML	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
TAPE Y-8437 ALUM/ELYLAK/ACRYLIC ADH/F (FORMER Y-9360)	MM	.68		.02			
TAPE Y-9040 2 MIL ALUM FOIL/SILICONE ADH/F (433)	MM	.47		.21			
TAPE Y-9050 ALUM FOIL/GLOSS CLOTH/SILICONE ADH/R	MM	.91		.38			
TAPE Y-9133 GREEN POLYESTER FILM/SILICONE ADH/F	MM	.75		.34			
TAPE Y-9184A GCLD LEAF ACRYLIC ADH/R	MM	1.42		.41			
TAPE Y-9184S GCLD LEAF SILICONE ADH/R	MM	2.42		.41			
TAPE Y-9224 TEFILON FOIL ACRYLIC ADH/R	MM	1.18		.03			
TAPE Y-9339 ALUM FOIL ACRYLIC ADH/R TYPE 2-2-UAL	MM	1.93		.003			
TAPE Y-9340 ALUM FOIL ACRYLIC ADH/R	MM	.54		.001			
TAPE Y-9400 ISCTAL ACRYLIC TRANSFER FILM 2 MIL/F	MM	.85		.00			
TAPE Y-9469 ISCTAL ACRYLIC TRANSFER FILM 5 MIL/F	MM	1.29		.02			
TAPE Y-9473 ISCTAL ACRYLIC TRANSFER FILM 10 MIL/F	MM	1.27		.03			
TAPE Y-9567 (467)BAL TRANSFER FILM ACRYLIC/F SANDWICH	MM	1.02		.01			
TAPE Y-966 TRANSFER FILM ACRYLIC/FOIL SANDWICH	MM	1.81					
TAPE Y-9364 EXPERIMENTAL ALUM GLASS CLOTH/F	MM	1.44		.04			
TAPE Y-1194 COPPER FOIL/NON COND ACRYLIC ADH/P	MM	2.28		.12			
TAPE Y-1245 EMBOSSED COPPER FOIL/ACRYLIC ADH/P	MM	2.26		.12			
TAPE Y-131 POLY ESTER FILM/ACRYLIC ADH/P	MM	1.48		.12			
TAPE Y-363 ALUM GLASS CLOTH/SILICONE ADH (MOD) /P	MM	1.28		.13			
TAPE Y-365 GLASS CLOTH/SILICONE ADH/F	MM	1.39		.07			
TAPE 4032 SCOTCHMOUNT FOAM/2 SIDE ACRYLIC ADH/R	MM	2.46					
TAPE 4032 SCOTCHMOUNT FOAM/2 SIDE ACRYLIC ADH/F	MM	2.09		.10			
TAPE 415 SCOTCHMOUNT FOAM/2 SIDE ACRYLIC ADH/F	MM	2.29		.15			
TAPE 420 SUBEEL BASE ADHESIVE ONLY/F	MM	1.91		.14			
TAPE 420 5 MIL LEAD FOIL/RUBBER BASE ADH/P	MM	1.85		.13			
TAPE 422 5 MIL LEAD FOIL/RUBBER BASE ADH/P	MM	1.99		.04			
TAPE 425 LEAD FOIL/SYNTHETIC ADH/F	MM	1.03					
TAPE 425 3 MIL ALUM FOIL/SYNTHETIC ADH/F	MM	.95		.03			
TAPE 428B 4 MIL ALUM FOIL/SYNTHETIC ADH/F	MM	2.44					
TAPE 433 2 MIL ALUM FOIL/SILICONE ADH/F (Y-9040)	MM	2.70		.01			
TAPE 465 2 MIL ALUM FOIL/SILICONE ADH/F	MM	1.53		.25			
TAPE 467 TRANSFER FILM ACRYLIC/FULL SANDWICH	MM	1.20		.07			
TAPE 467 VINYL/SYNTHETIC RUBBER ADH/R	MM	.88		.04			
TAPE 471 VINYL/SYNTHETIC RUBBER ADH/R	MM	.83		.04			
TAPE 4945 SCOTCHMOUNT ACRYLIC FOAM/2 SIDE ACH ADH/F	MM	1.24		.01			
TAPE 4962 SCOTCHMOUNT NEOP FOAM/2 SIDE ACR ADH/P	MM	2.94		.01			
TAPE 5 POLYESTER/ACRYLIC ADH/R	MM	1.56					
TAPE 53 POLYESTER/THERMOSET RUBBER ADH/R	MM	1.92					
TAPE 541 KAPTON/SILICONE ADH/P	MM	.58					
TAPE 5413 KAPTON/SILICONE ADH/F	MM	.87					
TAPE 5490 TEFLON/THERMOSET RUBBER ADH/R	MM	.77					
TAPE 56 POLYESTER/THERMOSET RUBBER ADH/R	MM	2.67					
TAPE 56 POLYESTER/THERMOSET RUBBER ADH/R	MM	1.22					
TAPE 61 TEFLON/THERMOSET SILICONE ADH/R	MM	1.14					
TAPE 61 TEFLON/THERMOSET SILICONE ADH/R	MM	.33					
TAPE 63 TEFLON/THERMOSET ACRYLIC ADH/R	MM	.39					
TAPE 65 TEFLON/THERMOSET ACRYLIC ADH/R	MM	.39					
TAPE 67 EPOXY FIBERGLASS CLOTH/THERMOSET RUBBER	MM	2.76		.71			
TAPE 69 EPOXY FIBERGLASS CLOTH/THERMOSET SILICONE ADH/S	MM	2.92		1.09			
TAPE 69 EPOXY FIBERGLASS CLOTH/THERMOSET SILICONE ADH/S	MM	2.25		1.18			

SECTION 16 -- TAPES

MATERIAL	MPA CODE	XTEL	ACVCM	CURE TIME	CURE TEMP	ADHES.	APPLICATION
HISTIK TAPE 70 SILICONE RUBBER TAPE/SILICONE ADH/R	MM	1.92	.73	24H	121	E-3	TAPE
HISTIK TAPE 70 SILICONE RUBBER TAPE/THERMOSET RUBBER ADH/P CYCLE	MM	2.20	.60	24H	-40	E-2	TAPE
HISTIK TAPE 75 POLYESTER FILM/THERMOSET RUBBER ADH/R	MM	3.12	.72	24H	65	E-0	TAPE
HISTIK TAPE 75 GLASS CLOTH/ACRYLIC ADH/F (Y-9064)	MM	5.26	.75				TAPE
HISTIK TAPE 840 2 POLYESTER FILM/SILICONE ADH/F	MM	5.54	.31				TAPE
HISTIK TAPE 840 2 POLYESTER FILM/THERMOSET RUBBER ADH/P CYCLE	MM	1.73	.02				TAPE
HISTIK TAPE 848 VAP DEP AU/KAPTON/ACR ADH/F LOT 9	MM	1.79	.92				TAPE
HISTIK TAPE 848 VAP DEP AU/KAPTON/ACR ADH/F	MM	1.99	.71				TAPE
HISTIK TAPE 849 AP DEP AU/KAPTON/SILICONE ADH/F	MM	1.99	.09				TAPE
HISTIK TAPE 850 ALUMINIZED POLYESTER/E/ACRYLIC ADH/R	MM	6.87	.02				TAPE
HISTIK TAPE 850 BLACK MYLAR/ACRYLIC ADH/R	MM	6.77	.02				TAPE
HISTIK TAPE 850 TRANSPARENT POLYESTER/ACRYLIC ADH/F	MM	6.71	.08				TAPE
HISTIK TAPE 851 POLYESTER FILM/GREEN SPEC BLEND ADH/P	MM	3.33	.93				TAPE
HISTIK TAPE 852 ALUMINIZED POLYESTER FILM/ACRYLIC ADH/F	MM	2.79	.22				TAPE
HISTIK TAPE 854 TRANSPARENT POLYESTER/WHITE SYN RUB ADH/P	MM	2.22	.14				TAPE
HISTIK TAPE 92 KAPTON/THERMOSET SILICONE ADH	MM	7.8	1.25				Shear Available TAPE
HISTIK TAPE 92 KAPTON/THERMOSET SILICONE ADH SHRINK	MM	4.15	1.22				TAPE
HISTIK TAPE 4053 GOLD/KAPTON/ACRYLIC ADH/R	BCM	4.49	1.42				TAPE
HISTIK TAPE 4053 GOLD/KAPTON/ACRYLIC ADH/R	BCM	4.41	0.66				TAPE
HISTIK TAPE 646 2 POLYPROPYLENE/LATEX ADH/F	BCM	3.73	.93				TAPE
HISTIK TAPE 646 2 POLYESTER FILM/2 SIDE'S RUBBER/FLS	BCG	5.99	2.01				2 SIDED TAPE
HISTIK TAPE 9466 TRANSFER FILM/ACRYLIC ADH/R	BCG	1.51	1.42				2 SIDED TAPE
HISTIK TAPE 9466 FIBERGLASS/SILICONE ADH/S	BCG	2.49	1.20				TAPE
HISTIK TAPE 7021 GLASS CLOTH/ACRYLIC ADH/F	BCN	1.41	.65				TAPE
HISTIK TAPE 7021 GLASS CLOTH/2 SIDE'S SILICONE ADH/R	BCN	3.22	.25				2 SIDED TAPE
HISTIK TAPE 7321 POLYESTER FILM/THERMOSET RBBR ADH/F	BCN	1.45	.49				TAPE
HISTIK TAPE 7341 POLYESTER FILM/ACRYLIC ADH/R	BCN	2.23	.34				TAPE
HISTIK TAPE 7341 KAPTON/SILICONE ADH/F	BCN	2.25	.93				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.19	.27				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.92	1.54				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.92	1.50				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.92	2.5				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.92	2.4				TAPE
HISTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCN	1.92	1.50				TAPE
HISTIK TAPE 7362 KAPTON/SILICONE ADH/F	BCN	4.65	1.23				TAPE
HISTIK TAPE 7362 KAPTON/SILICONE SAN DWLCH/2 SIDE SIL	BCN	4.06	1.10				2 SIDED TAPE
HISTIK TAPE 7366 KAPTON/CLOTH LINENE/2 SIDE SIL/F	BCN	2.19	1.43				2 SIDED TAPE
HISTIK TAPE 7366 KAPTON/CLOTH LINMER/2 SIDE SIL/F SAN	BCN	2.97	1.32				2 SIDED TAPE
HISTIK TAPE 7366 KAPTON/SILICONE ADH/FOIL SANDWICH	BCN	4.92	1.49				2 SIDED TAPE
HISTIK TAPE 7366 KAPTON/SILICONE ADH/FOIL SANDWICH	BCN	2.99	1.79				2 SIDED TAPE
HISTIK TAPE 7367 KAPTON/ACRYLIC ADH	BCN	6.63	.04				TAPE
HISTIK TAPE 7367 KAPTON/ACRYLIC ADH/R	BCN	6.69	.02				TAPE
HISTIK TAPE 7397 KAPTON/ACRYLIC ADH/F	BCN	1.95	2.4				TAPE
HISTIK TAPE 7397 KEDAR/ACRYLIC ADH/R GLAY	BCN	1.45	2.36				TAPE
HISTIK TAPE 7375 TIDLAR/ACRYLIC ADH/R WHITE	BCN	1.34	2.00				TAPE
HISTIK TAPE 7402 ALUM FOIL/SILICONE ADH/FOIL COMP	BCN	1.69	.35				TAPE - COMPOSITE
HISTIK TAPE 7420 COPPER FOIL/RUBBER BASE ADHESIVL ONLY/F	BCN	1.33	.20				TAPE
HISTIK TAPE 7430 4.5 MIL LEAD FOIL/RUBBER ADH/F	BCN	5.60	1.43				TAPE
HISTIK TAPE 7432 ALUM FOIL/ACRYLIC ADH/R	BCN	2.24	.93				TAPE
HISTIK TAPE 7433 ALUM FOIL/ACRYLIC ADH/R	BCN	2.09	.09				TAPE

SECTION 16 -- TAPES

MATERIAL	MPN CODE	#ML	%VCH	CURE TIME	CURE TEMP	ATMOS	APPLICATION
MYSTIK TAPE 7503 TEFLON/SILICONE ADH/F LOT ALM4A11K	ECM	.30	-13				TAPE
MYSTIK TAPE OT-6/F	GBC	.21	.08				TAPE
ORCOTAPE	PER	1.2-.26	7-.39				TAPE
PERMACEL TAPE EE-6379 KAPTON H/SILICONE ADH	PER	8-.50	.88				TAPE
PERMACEL TAPE EE-6300 ALUM/POLYESTER RUBBER ADH	PER	2.74	.90				TAPE
PERMACEL TAPE EE-6396 KAPTON/SILICONE ADH/S	PER	1.94	.97				TAPE
PERMACEL TAPE EE-6562 KAPTON/2 SIDE SILICONE ADH/F	PER	.75	.03				2-SIDED TAPE
PERMACEL TAPE EE-7240 GLASS CLOTH/ACRYLIC ADH/R	PER	.75	.03				TAPE
PERMACEL TAPE EE-7390 MYLAR FILM/ACRYLIC ADH/R	PER	.75	.03				TAPE
PERMACEL TAPE PE-0512 SIDE ACRYLIC ADH/F	PER	.36	.03				2-SIDED TAPE
PERMACEL TAPE PE-100 2 SIDE AL FOIL/GLASS FABRIC/SIL ADH	PER	.08	.03				TAPE
PERMACEL TAPE 212 HI TEMP GLASS CLOTH/SILICONE ADH/R	PER	1.35	.74	1H	149	AIR	TAPE
PERMACEL TAPE 213 GLASS CLOTH/ACRYLIC ADH/F	PER	1.79	.70				TAPE
PERMACEL TAPE 221 KAPTON/SILICONE ADH/F	PER	.47	.02				TAPE
PERMACEL TAPE 222 KAPTON/SILICONE ADH/F	PER	.25	.02				TAPE
PERMACEL TAPE 223 KAPTON/ACRYLIC ADH/F	PER	1.80	.63				TAPE
PERMACEL TAPE 252 NYLAR/THERMOSET RUBBER ADH/R	PER	.60	.03				2-SIDED TAPE
PERMACEL TAPE 264 NYLON PAPER/TS ACR ADH	PER	1.50	.37				TAPE
PERMACEL TAPE 2650 RED SILICONE TAPE WRAP	PER	7.96	.58	2H	149	AIR	TAPE
PERMACEL TAPE 4220 TEFLON/SILICONE ADH/R	PER	.97	.47				TAPE
PERMACEL TAPE 423 TEFLON/SILICONE ADH/F	PER	.25	.09				TAPE
PERMACEL TAPE 423 TEFLON/SILICONE ADH/S	PER	.65	.33				TAPE
PERMACEL TAPE 621 FIBERGLASS/SILICONE ADH/S	PER	1.39	.75				TAPE
POLYCOHRTAPE 921 WHITE MYLAR FILM SPLICING TAPE	PER	12.69	.95				TAPE
PP 87 TAPE POLYOLEFIN FILM/PVDF RUBBER ADH/P	PER	9.91	.24				TAPE
SB TAPE POLYPROPYLENE FILM/PSYN LATEX ADH/F	NOI	4.58	1.37				TAPE
SB 1020 GLASS REINFORCED SILICONE RUBBER TAPE	BIS	2.29	.64				TAPE
STRIP-N-STICK 4000 ED SILICONE RUBBER TAPE	BOX	.90	.36				TAPE
STRIP-N-STICK 4004 ED SILICONE SPONGE/ACRYLIC ADH/F	BOX	.25	.05				TAPE
TAPE-TEFLON 03441 TFE FILM/SILICONE ADH/F	CHR	3.05	.91				TAPE
TEMP-R-TAPE A2005 FIBERGLASS/TEFLON TPE/SILICONE ADH	CHR	3.4	.11				TAPE
TEMP-R-TAPE A-471 FIBERGLASS/PIBERGLAS/ACRYLIC ADH	CHR	.47	.17				TAPE
TEMP-R-TAPE C-4000 TEFILON PE/SILICONE ADH/F	CHR	.67	.33				TAPE
TEMP-R-TAPE G-550 FIBERGLASS/ACRYLIC ADH/R	CHR	.27	.09				TAPE
TEMP-R-TAPE G-5557 SILICONE COAT FIBERGLASS/SIL ADH/F	CHR	1.39	.46				TAPE
TEMP-R-TAPE G-565 FIBERGLASS/SILICONE ADH/F PLANE R	CHR	.14	.02	4d	205	AIR	TAPE
TEMP-R-TAPE G-565 FIBERGLASS/SILICONE ADH/F	CHR	2.72	.46				TAPE
TEMP-R-TAPE HH-225 TEFILON TPE/SILICONE ADH/F PRIMER/F	CHR	1.62	.95				TAPE
TEMP-R-TAPE HH-325 TEFILON TPE/SILICONE ADH/F PRIMER/F	CHR	1.42	.93				TAPE
TEMP-R-TAPE HH-430 TEFILON TPE/SILICONE ADH/F	CHR	1.10	.67				TAPE
TEMP-R-TAPE HH-650 TEFILON TPE/SILICONE ADH/F	CHR	.28	.15				TAPE
TEMP-R-TAPE K-100 KAPTON/2 SIDE SILICONE ADH/KAPTON	CHR	.19	.07	24d	66	E-4	Tape
	CHR	1.74	.08				COMPOSITE

SECTION 16 -- TAPES

MATERIAL	MPR CODE	STL	ACVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
TECHP-R-TAPE K-102 KAPTON/ACRYLIC ADH/F	CHR	.65	.01				TAPE
TECHP-R-TAPE K-102 KAPTON/ACRYLIC ADH/F	CHR	.78	.01				TAPE
TECHP-R-TAPE K-104 KAPTON/SILICONE ADH/F	CHR	1.42	.76				TAPE
TECHP-R-TAPE K-105 KAPTON/SILICONE ADH/F	CHR	.64	.15				TAPE
TECHP-R-TAPE K-250 KAPTON/SILICONE ADH/F	CHR	.88	.32				TAPE
TECHP-R-TAPE K-250 KAPTON/SILICONE ADH/F	CHR	.81	.25	24h	66	E-4	COMPOSITE
TECHP-R-TAPE K-350 KAPTON/SILICONE ADH/F	CHR	.93	.47				TAPE
TECHP-R-TAPE K-350 MYLAR/SILICONE ADH/F TRANSPARENT	CHR	.48	.34				TAPE
TECHP-R-TAPE K-69 MYLAR/SILICONE ADH/F TRANSPARENT POLYESTER/FR ACRYLIC ADH/F	CHR	.63	.02				2-SIDED TAPE
TECHP-R-TAPE K-706 MYLAR/ACRYLIC ADH/YELLOW/F	CHR	.41	.04				TAPE
TECHP-R-TAPE K-797 MYLAR/ACRYLIC ADH/YELLOW/F	CHR	.52	.07				TAPE
TECHP-R-TAPE K-99 MYLAR/ACRYLIC ADH/YELLOW	CHR	.37	.05				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	.44	.20				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	1.07	.41				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	.50	.27				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	.71	.41				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	.52	.31	24h	100	AIR	TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	CHR	.50	.33				TAPE
TECHP-R-TAPE K-102 TEFON/Teflon/SILICONE ADH/F	VAL	.35	.14				TAPE
VALCA TAPE 7910 PTIE FILM/SILICONE ADH/F							

SECTION 17 -- THERMAL GREASES

MATERIAL	HPK CODE	X-TML	ACVCM	CURE TIME	CURE ATMOS	APPLICATION
CASTALL 832-N HEAT SINK GREASE - PINK	CAS	9-58	3-33			THERMAL GREASE
CASTALL 832-MJ HEAT SINK GREASE - WHITE	CAS	7-79	3-47			THERMAL GREASE
CHOMERICS 4220 SILVER FILLED SILICONE GREASE	CHO	-57	-10			COND. GREASE
CS-1102 SILICONE GREASE	DCC	-95	-02			THERMAL GREASE
DC-340 HEAT SINK GREASE	DCC	-35	-11			HEAT SINK
DC-340 SILICON/E/ALUMINUM PIGMENT AS 25/1 BN	DCC	-50	-12			HEAT SINK
ECOSHIELD CO. G4/WHITE FILLED SILICONE GREASE	EMC	36-89	22-29			COND. GREASE
ECOCOTHERM LN 80142 FILLED HEAT SINK GREASE	EMC	-33	-16			THERMAL GREASE
ECOCOTHERM TC-4 FILLED HEAT SINK GREASE	EMC	-54	-05			THERMAL GREASE
ECOCOTHERM TC-4 FILLED HEAT SINK GREASE	EMC	-52	-07			THERMAL GREASE
ECOCOTHERM TC-5 FILLED HEAT SINK GREASE	EMC	-54	-19			THERMAL GREASE
ECOCOTHERM TC-9 FILLED HEAT SINK GREASE	EMC	-49	-10			THERMAL GREASE
ECOCOTHERM TC-9 FILLED HEAT SINK GREASE	EMC	-49	-13			THERMAL GREASE
G-640 INSULGREASE FEAT TRANSFER	GEC	-37	-15			GREASE
G-641 INSULGREASE	GEC	-71	-12			THERMAL GREASE
G-642 THERMAL GREASE	GEC	-16	-07			THERMAL GREASE
G-9042 THERMAL GREASE - WHITE SILICONE	GCG	-55	-38			THERMAL GREASE
G-9052 ELEC CONDUCTIVE GREASE - BLACK SILICONE	GCG	-05	-30			COND. GREASE
WAKEFIELD THERMAL GREASE 120	WAK	-41	-01			GREASE

SECTION 18 -- DISCELLANEOUS

MATERIAL	MPR CODE	ATML TIME	SCVN TIME	CUBE TIME	CUBE TEMP	ADHS	APPLICATION
AAP-HC HC NYLON MICROWAVE ABSORBER ADIPIRENE L100/MOCA AS 100/10 BW	AAP DUP STC 224 APC APC APC APC APC APC APC APC CON JOH JOH CCC WOP	1-75 1-13 -49 -56 2-39 1-59 1-21 -07 20-36 11-12 11-07	-04 -01 -09 -03 -19 -13 -01 -01 -00 -00	7D 2H 2H 2H 1H	25 60 74 74 4-82	AIR AIR AIR AIR AIR	ADSORBER Coat Coat Coat Epoxy Coat Film ADHESIVE Coat Coat Coat Coat Coat Coat INSULATION Coat WASHED PAINT
ALUMINIZED MYLAR 1CON42 ALUMINIZED NYLAR/EACTION DOWNTON ADH 4696U ARASTRONG A-31 4/EPOXY AS 9/4 BW ARASTRONG A-81 EPOXY X-81/A AS 10/1 BW ARASTRONG A-81 EPOXY X-81/A AS 10/1 BW/2FLEX RESIN B-010 UNBONDED B FIBER B-010 UNBONDED B FIBER BALSAW RESIN BORON NITRIDE 5 FEAT SINK WASHER C-99/DETA AS 25/1 EW EPOXY FILM	CAC BLA BLA CON CON DUR DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP EPCL EPCL	3-50 8-86 1-93 1-30	3-39 3-17 -34 -38	12H 5D -01 3H	225 25 25	AIR AIR AIR	ADHESIVE INSULATION INSULATION Coat Coat
CARICL 1019 EPOXY A/B AS 1/1 BW CONAFLEX EA-50 PCLIURETHANE FOAM W/ADH BACKING CONAFLEX EA-50 PCLIURETHANE FOAM W/O ADH BACKING CONATHANE CE 1155 A/b/CELLSOLVE ACETATE AS 10/7/3	DUR DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP DUP EPCL EPCL	-37 -23 -26 -29 -27 -23 -23 -23 -23 -23 -23 -23 -23 -23 -00	-08 -05 -08 -06 -06 -06 -02 -14	3H -01 -01 -01 -01 -01 -01 -01 -01 -01 -01 -01 -01 -01 -01	60	AIR	FIBER OPTIC FIBER OPTIC PAINT
CROFON LIGHT CONE CLEAR NO JACKET CROFON 1 COND/JACKET YELLOW CODE CROFON 1 YELLOW CCLED JACKET ONLY CROFON 3 COND/JACKET GREEN CODE CROFON 4 COND/JACKET PURPLE CODE CROFON 5 COND/JACKET BLUE CODE CSB-49 STAR NYLON IONIZED FANSH FATCH 1541 HUGHES ACFT CTL-15 BLACK EPOXY FAINT FATCH 1541 HUGHES ACFT	EPCL EPCL	4-91 5-36	-0.0	15H	25	AIR AIR	PAINT PAINT
CPL-15 WHITE EPOXY PAINT BATCH 1694 HUGHES ACFT	CTL	3-85	-0.0	15H	25	AIR AIR	PAINT
D-24-F3 SILICONE RESIN D-2106 SILICONE RESIN D-325 A/EIAS 100/EEN ABLATIVE SILICONE DC-510 SILICONE FLUID 30,000 CPS DEVOLATILIZED DC-510 SILICONE FLUID 30,000 CPS DEVOLATILIZED DC-510 SILICONE FLUID 30,000 CPS DEVOLATILIZED	HSP DCC DCC DCC DCC DCC DCC DCC DCC DCC DCC DCC DCC DCC EPD EPD	1-02 1-46 2-11 -98 -16	-02 -39 -43 -13	4H 3H 3H 24H 24H	25 149 80 80 125	AIR AIR E-2 E-2 AIR	PAINT BASE SLICONE ADHESIVE FLUID DADDA FLUID DADDA FLUID DADDA FLUID
DC 93-500 UNCURED ECONOMER LOT E2467-133 DYNA-FLEX REFRACTORY FIBER FELT - ETOH WASH DYNA-FLEX REFRACTORY FIBER FELT E-SOLDER 3022/HARLENER 18	JOH JOH JOH EPD	-0.6 -0.9 -1.13 -1.25	-0.2 -0.5 -0.5 -1.0	24H 24H 24H 3H	65 65 65 65H	AIR AIR AIR AIR	PAINT PAINT PAINT Coat &ADHESIVE
ECCOFoam FPH 12-10f 4/B AS 4/3 BW POLYURETHANE FOAM	EMC	1-93	-0.1	1-5H	85	AIR	ROAD
ECCOMOLD 66A EPOXY - MOLD AT 135C AND 420 PSI ECCOSORB AN 74 METEANOL WASH - 3 ECCOSORB AN 79 MICROWAVE AESOBANT/3M ADH 44	EMC EMC EMC SHL	-49 -51 -1.16 2.70	-0.6 -0.5 -3.9 -0.1	4.8H 1H 2H 4H	40 118 100 250 71	AIR AIR AIR AIR AIR	E-5 STRUCTURAL ADHESIVE ADHESIVE ADHESIVE COAT
EPON 828/VERSAMIL 125/MD AS 100/21/13 BW EPOXY	SHL	2.91	-0.0	1H 4H	25 60	AIR AIR	E-6

SECTION 18 -- MISCELLANEOUS

MATERIAL	MFN CODE	RTM TIME	%CVM	CURE TIME	CURE TEMP	ADHESIVE	APPLICATION
EPON 828/815/140/CARBOLAC/NOVACITE 1250	SHL	1.72	.10	16H	25	AIR	ADHESIVE
EPON 828/871/EP/CAB-O-SIL AS 40/60/15.5/3 B-6 EPOXY	SHL	1.24	.91	8H	66	AIR	ADHESIVE
EPON 929 EPOXY	SHL	.60	.00	14H	54.9	AIR	ADHESIVE
EPOXYLITE EP-100	EPIC	5.84	.02	72H	50	B-6	ADHESIVE
EPOXYLITE 8712 VARNISH	EPIC	8.41	.03	24H	52	AIR	ADHESIVE
EPOXYLITE 9653 POLYURETHANE E-160 8 COATS	EPIC	9.15	.01	1H	71	AIR	COAT COAT
FASTENER 06077 INJECTION MOLDED POLYURETHANE	DNN	.76	.12				PASLEK
FIBER GRADE 5-600 1/8 POLYURETHANE	SCT	2.95	.32				FIBER PAD
FIBER OPTIC CABLE CC-100	BX	.27	.07				FIBER OPTIC
FIBER OPTIC CABLE 5030ST	PIA	.33	.13				FIBER OPTIC
FIBER OPTIC CABLE 5030ST - NO SILICONE	PIA	.28	.07				FIBER OPTIC
F4 123-2 EPOXY ADH FILM PURPLE	ACC	1.23	.14	1H	121	AIR	ADD FILM
F4 123-2 EPOXY ADH FILM PURPLE	ACC	1.92	.24	10H	PSI		ADD FILM
FMD 60-FURE PIPE GLASS BATTING	OII	.89	.04				INSULATION
F3RMVA RAGNIER WIRE COATING 105 DEG C USE	ZZ2	4.23	.00				WIRE COATING
FSP43 CONDUCTIVE COATING	JHM	4.32	.00				PAINT
FULLER 171-A 152 ALUMINUM SILICONE PAINT	FHB	3.20	.07	34H	25	AIR	COAT PAINT
F3-1100 CONTROLLED VOLATILITY FLUID	DCC	.05	.03				SILICONE FLUID
F3-1100 CONTROLLED VOLATILITY FLUID	DCC	.07	.03				SILICONE FLUID
F3-1101 CONTROLLED VOLATILITY FLUID	DCC	.11	.07				SILICONE FLUID
F3-1105 CONTROLLED VOLATILITY FLUID	ZZ2	.68	.02				STRUCTURAL
GFRP TUBE GLASS/POLYESTER TUFF	PSI	.54	.00				STRUCTURAL
HEATER KAFTON TS Q-9485	STS	.58	.01				HEATER
HIGH K 707-L-9 INSULATION BLANKET MULTILAYER	AMC	.07	.00				INSULATION
LAMINATE HAS-G-10-4	AMC	.01	.00				INSULATION
LAMINATE REYOLITE 2200 LIQUID CRYSTALS INCAPSULATED IN PLASTIC/ADHESIVE	ZZ2	.37	.00				LAMINATE
LIQUID CRYSTALS INCAPSULATED IN PLASTIC/ADHESIVE	HLR	.88	.00				LAMINATE
MAGIC WULC N20 PAINE EPOXYLITE EPOXYLITE	HLR	5.99	.03	1H	12.5	E-4	DEAL SENSOR
MAGNET FLEXIBLE STRIP MAG-1016	NAG	2.12	.01				COUPLER
METASEAL 19V5 THERMOSET POLYESTER/STYRENE COPOLYMER	NED	.34	.07				DAE HOLD DOWN
METHYLENTETENE POLYMER	AMS	9.38	.49	3H	14.9	AIR	ADHESIVE
HICROLITE FELT AA C.6# /CU FT W/SILICONE BIND-CENTER	TBN	.67	.49				WAVESGUARD
MIN-K TYPE SS HT INSULATION	JOB	.29	.09	1H	29.0	AIR	INSULATION
MIN-K 1301 HT INSULATION	JOB	.20	.00				INSULATION
MIN TAPE ALUMINUM/ACRYLIC ADH/B (Y-930Q)	JOB	.31	.06				TAPE
MIN TAPE 29 POLYESTER/ACRYLIC ADH/B	JOB	1.25	.00				TAPE
KOBAY-TEXIN 35SD POLYURETHANE FASTENER	ASB	1.93	.03				FASTENER
AS 224 HS5 MOLD RELEASE ON FOIL	ASI	1.37	.08				FASTENER
MS-136 FLUOROCARBON MOLD RELEASE	MSI	10.42	.47				FASTENER
MS1023D3 FASTENER REUSABLE INSERT	DEL	2.26	.03				FASTENER
NICKEL BLACK/ELACO HOLES PLATED ALUMINUM	GSC	3.24	.04				COATING
NICKEL DULL PLATED ALUMINUM	GSC	1.12	.05				COATING
NICKLE BLACK/COPPER PLATED ALUMINUM	GSC	1.28	.05				COATING
NORTON EAR VIBRATION DAMPING FOAM	ZZ2	15.49	.9				FOAM
MLCN NETTING	222	11.41	.03				NETTING
NYLON ROD PER MIL F-17091	DNN	2.13	.05	72H	5.1	AIR	ADD FASTENER
NYLON 6 FASTENER - WHITE	DNN	2.71	.05				FASTENER

SECTION 18 -- MISCELLANEOUS

MATERIAL	MPN CODE	KURE	%CVCN	CURE TIME	ATMOS	APPLICATION
ORTEC EPOXY ALUMINUM COVER GOLD CCVER	ORT ORT	2.0 ^b 8.87	.00 .05	104 104	AIR AIR	DEFLECTOR DEFLECTOR
P-49 POLYESTER W/2% BENZOYL PEROXYDE AS C. 25% CAT DEVOL BATCH 10	ROH GSC	1.04 .339	.05 .02	7D 7D	AIR AIR	TUBING TUBING
RIV 602/SRC 05 AS C. 25% CAT DEVOL BATCH 15	GSC	.39	.02	7D	AIR	TUBING
RIV 602/SRC 05 AS C. 25% CAT DEVOL BATCH 20	GSC	.39	.02	7D	AIR	TUBING
RIV 602/SAL 05 AS C. 25% CAT DEVOL BATCH 25	GSC	.57	.02	7D	AIR	TUBING
R90-709 SILICONE JUNCTION COATING	DCC	.88	.37	1H	70	SILICON E
SAM SILICONE RESIN RIGIDIZER W/SILICA FIBERS	GEV	.29	.02	16H	150	AIR
SCOTCHMATE POLYESTER FASTENER HOOK/NAP	HMD	.39	.02		AIR	ADhesive
SCOTCHMATE SJ3401 NYLON HOOK AND LOOP	HMD	1.41	.01		AIR	FASTENER
SCOTCHMATE SJ3402 NYLON HOOK AND LOOP BLACK	HMD	1.79	.03		AIR	FASTENER
SCOTCHMATE SJ3526/SJ3527 ADH BACKED HOOK & LOOP	HMD	5.60	.22	3H	204	AIR
SE 5403 U 10-10 FASTENER GRAY ANODIZE	GBC	.02	.01		AIR	FASTENER
TBS 757 FLAME RETARDANT SILICONE BARRIER NAP	DEL	2.90	.02		AIR	FASTENER
TECKFELT 45-09802 SILICONE IMPREG SINT STAINLESS	GEC	2.90	.02		AIR	FASTENER
TECKFELT 45-09810 UNIFLEX SINT STAINLESS	TIP	1.41	.02		AIR	FASTENER
TECKFELT 82-124571 SILICONE SPONGE W/SCREEN	TEC	4.37	.01		AIR	FASTENER
TECKFELT 82-124571 SILICONE SPONGE W/SCREEN	TEC	4.12	.02		AIR	FASTENER
TECKFELT 82-124571/72-124571 COMPOSITE	TEC	4.12	.02		AIR	FASTENER
TECHMA-PPA 43-03-4 INSULATOR	THE	.98	.05		AIR	INSULATOR
VELCRO ASTRO H 6L POLYESTER-BETA GLASS-TEFLON-FLUOREL	VEL	.78	.02		AIR	FASTENER
VELCRO HI-AIR FASTENER NOMEX/FLAME RETARD/ETOH WASH	VEL	5.33	.04		AIR	FASTENER
VELCRO HI-AIR FASTENER NOMEX/FLAME RETARD/ETOH WASH	VEL	2.39	.01	16H	100	AIR
VELCRO HI-AIR FASTENER NOMEX/FLAME RETARD/EXTRACTED	VEL	2.97	.01		AIR	FASTENER
VELCRO HI-AIR HOOK/LOOP FLAME RETARD 0399 BACKING	VEL	5.82	.03		AIR	FASTENER
VELCRO HI-AIR HOOK/LOOP FLAME RETARD 062-C66-017-0399 BACKING	VEL	3.74	.05		AIR	FASTENER
VELCRO HI-GARD HOOKS STAINLESS STEEL	VEL	.92	.01		AIR	FASTENER
VELCRO HI-TEMP FASTENER NOMEX/POLYIMIDE	VEL	.52	.00		AIR	FASTENER
VELCRO HI-TEMP FASTENER NOMEX/POLYIMIDE/EXTRACTED	VEL	.55	.00		AIR	FASTENER
VELCRO NYLON HOOK AND LOOP	VEL	1.08	.05		AIR	FASTENER
VELCRO NYLON HOOK/LOOP 1999 BACKING	VEL	1.59	.04		AIR	FASTENER
VELCRO P537 FLBERGLASS/FLUOREL/TEFLON LOOPS	VEL	.37	.01		AIR	FASTENER
VELCRO V330-165) 63/330-2-63 BLACK NYLON HEL	VEL	1.77	.03		AIR	FASTENER
VELCRO 100% POLYESTER HOOK AND LOOP	VEL	.54	.02		AIR	FASTENER
VELCRO 100-003-017-032 TAB NOMEX HOOK LOOP W/ADH	VEL	.13	.02	1-70	25	AIR
VELCRO 100-005-012-0199AB HEL	VEL	.79	.02		AIR	FASTENER
VELCRO 100-006-015-1299AP STAINLESS LOOP	VEL	1.30	.03		AIR	FASTENER
VELCRO 100-006-015-1299AP STAINLESS LOOP	VEL	1.30	.03		AIR	FASTENER
VELCRO 1000-081-012-0199 WHITE HOOK	VEL	1.41	.05		AIR	FASTENER
VELCRO 1000-081-106-0199/1000-009-106-0199 OL/GREEN	VEL	1.10	.05		AIR	FASTENER
VELCRO 1000-061-33C-0199/1000-009-330-0199 BLACK	VEL	1.98	.06		AIR	FASTENER
X-850 FILM LAMINATE ALUM MYLAR/DACKON SCHIM/AL MYLAR	GTS	1.51	.14		AIR	COVER
XR PERFLUOROSULFONIC ACID MEMBRANE ACID PRECURSOR TUBING	DUP	4.77	.02		AIR	Handmade
		.73				TUBING

SECTION B

MATERIALS - ALPHABETICAL LISTING

MATERIAL	DATA	XTEL	XCYCA	CURE TIME	CURE TIME	ATMOS	APPLICATION
A-1177 E/A/E AS 1/1 BW EPOXY - BROWN	GSPC7166	.45	.02	24H	2.5	AIR	ADHESIVE
A-1273-B A/B AS 1/1 BW GREEN EPOXY PER MIL A132	GSPC9536	.75	.04	48H	2.5	AIR	ADHESIVE
A/B AS 100/4.5 BW SILICONE	GSPC9560	.75	.05	15d	12.1	AIR	ADHESIVE
A-1362-B ONE COMPONENT EPOXY	GSPC9298	1-18	.34	1H	12.1	AIR	ADHESIVE
A-1396-B EPOXY	GSPC8300	11-69	.65	1H	12.1	AIR	ADHESIVE
A-18 A/B AS 100/4.5 BW SILICONE	GSPC9451	1-54	.04	7D	2.5	AIR	ADHESIVE
A-4000 A/B AS 100/4.5 BW SILICONE	GSPC5479	2.85	1-63	1H	2.5	AIR	ADHESIVE
AAP-HC HC/HY COMB MICROWAVE ABSORBER	GSC13006	1-75	.04	20H	9.3	AIR	ADHESIVE
ABLE BOND 16-1 SILVER FILLED METALLIC/GRAPHITE/FOAM	GSPC8938	.85	.04	24H	2.5	AIR	FILM COMPOSITE
ABLE BOND 16-1 A/E AS 100/7 BW SILVER FILLED EPOXY	GSPC9392	.71	.15	16H	7.7	AIR	FILM ADHESIVE
ABLE BOND 163-4 A/E AS 20/9 BW COPPER FILLED EPOXY	GSPC1978	1-39	.08	20H	6.5	AIR	FILM ADHESIVE
ABLE BOND 20-1 SILVER FILLED ONE COMPONENT	GSPC5531	0-09	.38	15d	15.0	AIR	FILM ADHESIVE
ABLE BOND 224-1 A/E AS 10/1 BW EPOXY	GSPC5250	3-30	.00	1H	5.2	AIR	ADHESIVE
ABLE BOND 2293-1 A/B AS 100/7 BW EPOXY	GSPC3293	2-39	.02	4H	7.4	AIR	ADHESIVE
ABLE BOND 293-1 A/E AS 25/2 BW FILLED EPOXY	GSPC13325	1-32	.08	4H	7.4	AIR	ADHESIVE
ABLE BOND 34-1 A/B AS 25/4 BW EPOXY	GSPC5272	1-35	.07	2H	6.5	AIR	ADHESIVE
ABLE BOND 36-2 SILVER FILLED EPOXY	GSPC10886	1-30	.00	30H	6.50	AIR	ADHESIVE
ABLE BOND 41-5 SILVER FILLED EPOXY	GSPC5693	1-46	.00	30H	15.0	AIR	ADHESIVE
ABLE BOND 41-6 EPOXY	GSPC5635	1-44	.00	30H	15.0	AIR	ADHESIVE
ABLE BOND 463-1 A/E AS 10GM/16DPS SILVER FILLED EPOXY	GSPC5637	.62	.01	30H	15.0	AIR	ADHESIVE
ABLE BOND 57-1 SILVER FILLED POLYIMIDE	GSPC9395	.62	.01	2H	2.5	AIR	ADHESIVE
ABLE BOND 57-2R BODIFIED EPOXY DARK RED	GSC12148	2-59	.16	2H	6.5	AIR	ADHESIVE
ABLE BOND 71-1 SILVER FILLED POLYIMIDE	GSC10814	.24	.06	10d	15.0	AIR	ADHESIVE
ABLE BOND 731-1 A/E AS 100/47 BW YELLOW EPOXY	GSC11651	.25	.00	30H	10H	AIR	ADHESIVE
ABLE BOND 826-1 ONE COMPONENT SILVER FILLED ADH	GSPC7220	.92	.11	3H	2.75	AIR	ADHESIVE
ABLE BOND 872-3 A/B AS 2/3 BW FLEXIBLE PINK EPQXY	GSPC7892	.58	.03	30H	15.0	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSPC8324	2.76	1-19	8H	1.19	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11696	4-85	.31	90H	12.5	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11699	2-41	.00	1H	8.0	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11824	2-92	.09	1H	12.5	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11827	2-07	.00	1H	15.0	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11887	.76	.00	1H	15.0	AIR	ADHESIVE
ABLE BOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY THIN	GSC11932	.81	.01	14	12.5	E-3	ADHESIVE
ABLE FILM ECF 518 CLOTH SUPPORT/EPOXY FILM ADH GRAY	GSPC9372	.88	.01	1H	14.0	AIR	FILM ADHESIVE
ABLE FILM ECF 535 CLOTH SUPPORT/SILVER FILLED EPOXY	GSPC7763	.42	.01	3H	7.4	AIR	FILM ADHESIVE
ABLE FILM ECF 550-1 GLASS SUPPORT/SILVER FILLED EPOXY	GSC124490	1-37	.16	3H	12.5	AIR	FILM ADHESIVE
ABLE FILM 501 ADH GLASS SUPPORT/EPoxy ADH	GSPC23312	1-52	.08	3H	7.4	AIR	FILM ADHESIVE
ABLE FILM 504 CLOTH SUPPORT/EPOXY FILM ADH - WHITE	GSPC69792	1-38	.00	45d	14.9	AIR	FILM ADHESIVE
ABLE FILM 506 CLOTH SUPPORT/EPOXY FILM ADH - WHITE	GSPC8792	1-05	.37	3H	9.3	AIR	FILM ADHESIVE
A3 LEFIELD 509 CLOTH SUPPORT/EPOXY FILM ADH/F - WHITE	GSPC8795	1-90	.32	90H	12.5	AIR	FILM ADHESIVE
ABLE FILM 507 GLASS CLOTH/B-STAGGED EPOXY FILM ADH	GSPC50491	1-38	.02	1.5H	16.3	AIR	FILM ADHESIVE
ABLE FILM 517 GLASS CLOTH SUPPORT/EPOXY FILM ADH PINK	GSPC2272	0-07	.01	3H	7.4	AIR	FILM ADHESIVE
ABLE FILM 518 CLOTH SUPPORT/EPOXY FILM ADH - GRAY	GSC13413	-83	.00	3H	9.3	AIR	FILM ADHESIVE
ABLE FILM 550-A CLOTH SUPPORT/EPOXY FILM ADH - WHITE	GSPC8717	-31	.04	2H	12.5	AIR	FILM ADHESIVE
ABLE FILM 550-1-004 CLOTH REINFORCED EPOXY FILM WHITE	GSPC7523	-32	.12	3H	-	AIR	FILM ADHESIVE

MATERIAL	DATA REFERENCE	XTLA	RCVCM	CURE TIME	CURE TEMP	AIDS	APPLICATION
ABLESTIK 561K CLEAR SUPPORT/EPOXY FILM-THERM COND	GSC12910 GSCF1943 GSFC510b GSFC6832	.42 .44 .42 .34	.13 .07 .04 .32	2H 1H 1H 1H	125 74 100 175	AIR AIR AIR AIR	FILM ADHESIVE ADHESIVE CONF COAT-ADH FILM ADHESIVE
ABLESTIK 240-2 POLYURETHANE							
ABLESTIK 257-1 A/B AS 100/179-2 BW POLYURETHANE							
ABLESTIK 681-12 BLUE/GREEN							
ABLESTIK 681-12 KOD EPOXY FILM A							
ABLESTIK 681-12 VLT EPOXY FILM ADHESIVE GREEN	GSPCo89b	.98	.04	16H	100	AIR	FILM ADHESIVE
ABLESTIK 724-14C SINGLE COMPONENT POLYURETHANE	GSFC6872 GSE7598 GSFC7775 GSFC7694	1-11 1-36 1-36 1-78	.12 .09 .09 .09	1H 1H 2H 2H	150 71 93 71	AIR AIR AIR AIR	FILM ADHESIVE ADHESIVE CONF COAT-ADH FILM ADHESIVE
ABLESTIK 761-6 A/D VLT AG AS 100/5/223 EW							
ABLESTIK 857-1 E/CCC SPHERES SI AS 55/45 BW - WHITE	GSFC7697	.80	.01	2H	93	AIR	FILM ADHESIVE
ABLESTIK 861-2 E/CCC SPHERES SI AS 55/45 BW - WHITE	GSFC2605 GSFC5603	.96 .93	.36 .35	8H 8H	71 71	AIR AIR	FILM ADHESIVE FILM ADHESIVE
ABLESTIK 7-2 AS 100GM/14 DROPS FILLED SILICONE	GSFC13332	1-29	.10	4H	74	AIR	FILM ADHESIVE
ABLESTIK 7-2 AS 100GM/7 DROPS FILLED SILICONE	GSFC5609	1-03	.31	8H	71	AIR	FILM ADHESIVE
ABLESTIK 7-2 FILLED SILICONE/16 DROPS FILLED SILICONE	GSFC5607	.89	.15	8H	71	AIR	FILM ADHESIVE
ABLESTIK 7-3 AS 100GM/6 DROPS FILLED SILICONE	GSFC13346	.68	.19	4H	74	AIR	FILM ADHESIVE
ABLESTIK 7-3 AS 100GM/14 DROPS FILLED SILICONE	GSFC13428	.39	.12	6H	67	AIR	FILM ADHESIVE
ABLESTIK 7-3 AS 100GM/4 DROPS FILLED SILICONE	GSFC2224	.51	.28	6H	65	E-6	FILM GASKET
ABLESTIK 7-5 AS 100GM/7 DROPS FILLED SILICONE	GSFC7253	.49	.23	8H	74	AIR	FILM ADHESIVE
ABLESTIK 7-5 AS 100GM/7 DROPS FILLED SILICONE	GSFC2829	.31	.14	8H	89	AIR	FILM ADHESIVE
ABLESTIK 8-2 A/V AS 10/1 BW EPOXY	GSPCo5443	.41	.30	90H	93	AIR	THEM ADHESIVE
ABLESTIK 908-3 CERAMIC FILLED SOLITHANE 113/300/T12	GSC13329	1-16	.01	4H	74	AIR	FILM ADHESIVE
ABS VACUUM GOLD C CASING FILLED SOLITHANE 113/300/T12	GSC11493	1-13	.01	6H	204	E-2	FILM CPND
ABSA/FIL F1200/20 GLASS BUBBS	GSE4927	1-33	.01	6H	60	AIR	FILM CPND
AC-1 A/V AS 10/1 E/ CONDUCTIVE EPOXY SOLVER	GSFC4504	2-54	.42	16H	40	AIR	FILM CPND
ACETATE BUTYRATE - CLEAR	GSCFC0457	4-73	.00				LENS
ACLEAR 22A CLEAR FILM POLYCHLOROTRIEPIJORETHYLENE	GSCFC2847	-11	.01				FILM
ACLEAR 33C CLEAR FILM POLYCHLOROTRIEPIJORETHYLENE	GSCFC3850	-11	.01				FILM
ACRYLAFIL G4/7/20 STYR ACRYLONITRILE/FIB GLA AS 80/20	GSCFC969	-23	.03				FILM CPND
ACRYLAGLAS S40/35 STYRENE-ACRYLONITRILE/FIBER GLASS	GSCFC0941	-22	.03				FILM CPND
ACRYLITE ACRYLIC SHEET	GSCFC0945	-21	.05				STRUCTURAL
ACRYLOID AUL 08/DESODUR 12219A/T-12 CLEAR COATING	GSCFC1320	12-70	.03				COATING
ACTONE EPCX-1 CLEAR	GSCFC1495	1-32	.03				PUTTING
ADIPIRENE L100/1 MOCA AS 100/10 BW	GSCFC1825	1-74	.15				COMP COAT
ADIPIRENE L100/1 MOCA AS 100/10 BW	GSCFC7601	1-74	.15				PUTTING
ADIPIENE 183/CAYTUE 21 AS 100/16 BW POLYURETHANE	GSCFC8696	7-64	.47				PUTTING
ADIPIENE 183/CAYTUE 21 AS 100/16 BW POLYURETHANE	GSCFC8678	7-34	.03				PUTTING
ADDLET PEN-2 ELECTRICAL FIELD THRU NEBA X GRADE 550	GSCFC3775	2-97	.00				FEED THRU
ADDLET PEN-2 ELECTRICAL FIELD THRU NEBA X GRADE 550	GSCFC3021	1-40	.09				FILM ADHESIVE
AEROBOND AE 3041-1C EPOXY HONEYCOMB ADH	GSCFC2639	1-72	.73				AIR-FILM
AEROBOND 3030 EPOXY HONEYCOMB ADH - GRAY	GSCFC5204	1-26	.00				AIR-FILM
AERODAG G COLLOIDAL GRAPHITE ISO PROPYL ALCOHOL	GSCFC6294	1-78	.01				SUBRICANT
AERODAG G COLLOIDAL GRAPHITE ISO PROPYL ALCOHOL	GSCFC6488	2-05	.04				SUBRICANT
AERODAG H COLLOIDAL POSSUM ISOPROPYL ALCOHOL	GSCFC0930	4-97	.19				SUBRICANT
AF 100/6 ACRYLIC BUTA LINE SYRENE	GSCFC0689	1-20	.01				BUILD CPND
AF 110 PILM ADHESIVE	GSCFC3676	1-94	.43				FILM ADHESIVE
AF 3309-2 EPOXY FLAH	GSC12844	1-09	.12				FILM ADHESIVE
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED	GSC13012	-95	.25				FILM ADHESIVE
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED		-25					
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED		1H					
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED		168H					
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED		74					
AF 3309-2U FILM ADHESIVE CREAM UNSUPPORTED		1-3					

MATERIAL	DATA REFERENCE	X-TML	XCVN	CURE TIME	CURE TEMP	AIRUS	APPLICATION
AF 3109-2U FILM ADHESIVE CREAM UNSUPPORTED	GSC13078	1.72	.72	1H	127	AIR	FILM ADHESIVE
AF 31094 EPOXY FILM ADHESIVE	GSC12305	1.26	.09	90M	107	AIR	FILM ADHESIVE
AF 3109U FILM ADHESIVE BLUE GREEN UNSUPPORTED	GSC13009	1.54	.28	1H	127	AIR	FILM ADHESIVE
AF 42 FILM ADHESIVE EPOXY UNSUPPORTED THERMOSETTING	GSFPC5445	3.91	.37	1H	177	AIR	FILM ADHESIVE
AF 45 SUPPORTED FILM ADHESIVE FILM JAROON	GSC12306	2.11	.31	90M	196	AIR	FILM ADHESIVE
AF 55 FILM ADHESIVE EPOXY DERIVATIVE	GSC12755	.81	.17	1H	177	AIR	FILM ADHESIVE
AF-E-3/C125690-1 HARD FOAMED EPOXY	GSC13000	.60	.08	2H	177	AIR	SLADDER
AG-1/HARDENER 22 AS 16/1 EW SILVER FILLED EPOXY	GSC13023	.89	.00	3H	99	AIR	FOAMED ADHESIVE
AIR BORN CONNECTOR AGE9-2PRGY BLACK GLASS FILL/NYLON	GSC1324	.37	.00	2H	127	E-3	COND ADHESIVE
ALLACAST 1776 POTLING CPND FOR OPTICAL COMPONENTS	GSPC8516	.71	.09	2H	127	E-3	CONNECTOR
ALPHA LUX 400 POLYBENZYL OXIDE	GSPC9313	.25	.01	24H	25	AIR	POTTING
ALPHA WIRE 221-3-64 INSULATION	GSPC9313	.08	.01	24H	25	AIR	INSULATION
ALPHA WIRE 5853 BLACK TEFLON INSULATION	GSC12601	1.30	.34	24H	25	AIR	WIRE INSUL
ALUMINIZED NYLAR 100M42	GSC12604	.01	.00	24H	25	AIR	WIRE INSUL
AMGUARD CORROSION PROTECTIVE COATING/P	GSPC81258	.46	.01	24H	25	AIR	REFLECTOR
AMP CONNECTOR 205-289-1 NYLON GLASS FIBER	GSPC9316	.62	.01	24H	25	AIR	COATING FILM
AMP CONNECTOR 645650-1 PHENOLIC/GLASS FIBER	GSC13059	.30	.00	24H	25	AIR	CONNECTOR
AMP FEED THRU TERMINAL BLOCK 20430-6-70-39 EPOXY	GSPC93045	.28	.00	24H	25	AIR	CONNECTOR
AMP HV SILICONE CAFFLE INSUL PEP	GSPC93047	.66	.00	24H	25	AIR	FEED THRU
AMP HV WIRE ENTIRE CAFFLE WITHOUT METAL	GSPC92290	.39	.00	24H	25	AIR	INSULATION
AMP HV WIRE HA/HV-1 SILICONE INSUL MIDDLE	GSPC91339	.39	.00	24H	25	AIR	CAFFLE
AMP HV WIRE SILASTIC 14100 SHRINK TUBING ONLY	GSPC91336	1.44	.34	24H	25	AIR	CAFFLE
AMP HOLDING COUPLED AMBER INSULATION - LED	GSPC12877	.39	.00	24H	25	AIR	CAFFLE
AMP 221841-2 SCREWLESS INSULATION - LED	GSPC93816	.54	.02	24H	25	AIR	CAFFLE
AMPHENOL CONNECTOR MIL C38999 CILAR SEAL 418 SERIES	GSC130422	.35	.00	24H	25	AIR	CONN INSUL
AMPHENOL CONNECTOR MIL C38999 CILAR SEAL 418 SERIES	GSC130434	.50	.00	24H	25	AIR	CONN INSUL
AMPHENOL CONNECTOR SERVICES 118 BLUE FLUOROSILICONE	GSPC93033	.59	.00	24H	25	AIR	CONN INSUL
AMPHENOL CONNECTOR SERVICES 118 TAN THEMOPLASTIC	GSPC93036	.03	.00	24H	25	AIR	CONN INSUL
AMPHENOL 481 CONNECTOR PHENOLIC ONLY 350	GSPC93036	.59	.01	24H	25	AIR	CONNECTOR
AMPHENOL 481 CONNECTOR PHENOLIC/SILASTIC 350 ONLY	GSPC93044	.56	.02	24H	25	AIR	CONNECTOR
AMR 1036 GREEN EPOXY	GSC12855	.36	.00	24H	25	AIR	ADHESIVE
AMS 3345 ORANGE EPOXY	GSPC9359	2.66	.00	24H	25	AIR	ADHESIVE
ANDREW BROWN BLACK EPOXY PAINT/PIMER A-136	GSPC9496	.11	.04	48d	121	E-4	PAINT
ANDREW BROWN BLACK EPOXY PAINT/PIMER A-136	GSPC1444	9.48	.21	5D	25	AIR	PAINT
ANGEL FOAM 6818 CLEAN ROOM WIPE	GSPC6509	1.24	.10	10M	149	AIR	FOAM WIPE
ANGEL FOAM 6818 CLEAN ROOM WIPE 6 HR MATCH WASH	GSPC6677	1.15	.01	16d	100	AIR	FOAM WIPE
ANTI STATIC FILM 2100	GSC11845	.32	.05	24H	71	AIR	FILM
A3 805 OPTICAL CEMENT BUTYL METHACRYLATE	GSPC9366	.45	.05	24H	71	AIR	OPT CEMENT
A3 805 OPTICAL CEMENT BUTYL METHACRYLATE	GSPC9369	.04	.02	24H	71	AIR	OPT CEMENT
APCO 1260 A/B AS 1/1 BW	GSPC2677	6.46	.02	24H	71	AIR	CONF COAT
APCO 1266 A/B AS 1/1 BW POLYURETHANE CYCLED	GSPC1207	18.35	.02	90d	89	AIR	CONF COAT
APCO 1266 A/B AS 1/1 BW POLYURETHANE CYCLED	GSPC1420	17.06	.04	24H	65	E-5	PAINT

MATERIAL	DATA REFERENCE	ATRL	%CVCM	CURE TIME	CURE TEMP	AIR H2S	APPLICATION
APCO 5313 A/B AS 100/8 BW GREEN EPOXY	GSC10553 GSC11800	1.80 81.19	0.5 47.47	1H 1H	66 65	AIR 5-2	ADHESIVE LUBRICANT
APIEZO N OIL VACUUM DEGassed	GSCFC4696	0.25	0.02				GEASE
APIEZO N HYDROCARBON GREASE	GSCFC9320	0.24					GEASE
APIEZO N GREASE VACUUM DEGassed	GSC11803	0.34	0.01				GEASE
APIEZO N GREASE	GSCFC6380	0.08	0.02				GEASE
APPLETECN CONNECTOR RED SILICONE INSERT	GSC11222	0.34					CONN INSUL
APPLETECN CONNECTOR WHITE FLUOROSILICONE FIBREGLASS	GSC11216	0.24					CONN INSUL
APPLETECN CONNECTOR WHITE FLUOROSILICONE INSERT	GSCFC7079	3.91	0.91	22	24H	AIR	ADHESIVE
APP8005 FAST CUBE EPOXY ACU-PAK PRE-MIX	GSCFC7130	3.90	0.90			AIR	ADHESIVE
ARALDITE AV 100 HY100 AS 1/1 BW EPOXY	GSCFC1123	0.57	0.57		1.5H	AIR	AIR POTTING
ARALDITE AV 100 HY100 AS 1/1 BW EPOXY	GSCFC1126	0.78	0.78		1.0H	AIR	AIR POTTING
ARALDITE AV 124 HY948 AS 1/1 BW EPOXY	GSCFC4432	0.01	0.01		20	AIR	ADHESIVE
ARALDITE AV 138 HY998 AS 100/40 BW EPOXY	GSCFC6899	1.97	1.59	0.35	7.0H	AIR	ADHESIVE
ARALDITE AV 349 HY994 AS 100/40 BW EPOXY	GSCFC7130	1.59	0.94	0.24H	2.5H	AIR	ADHESIVE
ARALDITE CY79 HY60605/MS-XL EPOXY	GSCFC4552	1.16	0.02	16H	25	AIR	POTTING
ARALDITE CY79/HY60605/MS-XL EPOXY	GSCFC9539	1.14	0.02	9.0H	24H	AIR	POTTING
ARALDITE CY79/HY998 AS 10/3 BW EPOXY	GSCFC9050	1.26	0.02	3H	2.5H	AIR	ADHESIVE
ARALDITE HY750/HY752/HARBLE FLOUR AS 100/27/100 BW	GSCFC7226	7.55	0.01	30H	80	AIR	CURING
ARALDITE HY750/HY919/DY219/TEXOGLASS 480J AS 20/4.6 BW EPOXY	GSCFC1133	7.19	0.01	30H	25	AIR	CURING
ARALDITE HY750/HY974 AS 20/4.6 BW EPOXY	GSCFC1138	1.27	0.03	24H	60	AIR	CURING
ARALDITE HY950/HY974 AS 20/4.6 BW EPOXY	GSCFC6578	5.18	0.02	24H	190	AIR	CURING
ARALDITE HY950/HY974 AS 20/4.6 BW EPOXY	GSCFC3943	1.88	0.03	24H	25	AIR	CURING
ARALDITE HY951/HY951/BW EPOXY	GSCFC4778	2.00	0.01	1H	2.5H	AIR	CURING
ARALDITE 508/EPOX 628/ARALDITE 951/PC-1244 EPOXY	GSCFC4768	2.31	0.42	0H	49	AIR	ADHESIVE
ARALDITE 6004/508/CABOSIL/DP-138/951/PC-1244 EPOXY	GSCFC4770	3.74	0.07	16H	25	AIR	COTTING
AREMCO-BOND 517 THERMAL CONDUCTIVE SLEEVE BLACK	GSCFC8912	1.91	0.04			AIR	ADHESIVE
AREMCO-BOND 556 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11531	1.54	0.08	3H	66	AIR	CONF COAL
AREMCO-BOND 556 A/E AS 1/1 BW SILVER FILLED EPOXY	GSC11533	0.73	0.05	4H	96	AIR	CONF COAL
ARMAPLEX TUBULAR INSULATION SLEEVE BLACK	GSC11519	0.59	0.41	2.4H	125	2-3	ADHESIVE
ARMALON FILM TIG435C BLACK TFE ON GLASS FABRIC	GSCFC5569	0.5	0.01				HEAT BARRIER
ARMORED FOLIATE POLYTHENE 2000 MAGNET WIRE BROWN	GSCFC49909	0.93	0.02				HEAT COATING
ARMORED FOCON SILICA FILLED SILICON EPOXY	GSCFC6739	1.42	0.01				GASKET
ARMSTRONG A-12 A/B AS 1/1 BW BROWN EPOXY	GSCFC6739	1.1	0.01	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 1/1 BW BROWN EPOXY	GSCFC6762	1.25	0.04	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 2/3 BW BROWN EPOXY	GSCFC4764	1.24	0.04	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 2/3 BW BROWN EPOXY	GSCFC6766	1.94	0.06	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 2/3 BW BROWN EPOXY	GSCFC6766	1.94	0.06	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 2/3 BW BROWN EPOXY	GSCFC6766	1.87	0.07	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 3/2 BW BROWN EPOXY	GSCFC6712	0.87	0.09	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 3/2 BW BROWN EPOXY	GSCFC6736	0.65	0.09	31	24H	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 3/2 BW BROWN EPOXY	GSCFC34439	1.46	0.06	31	25	AIR	ADHESIVE
ARMSTRONG A-12 A/B AS 3/2 BW BROWN EPOXY	GSCFC4918	1.73	0.02	31	25	AIR	ADHESIVE
ARMSTRONG A-21 A/E AS 1/1 BW EPOXY	GSCFC4920	0.49	0.05	31	93	AIR	ADHESIVE
ARMSTRONG A-21 A/E AS 1/1 BW EPOXY	GSCFC12151	0.85	0.05	30H	93	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 100/6 BW BLACK EPOXY	GSCFC12151	0.85	0.04	1H	22	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/3-4 BW TAN EPOXY	GSCFC11397	0.72	0.04	7D	25	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/3-6 BW EPOXY	GSCFC9930	0.53	0.04	7D	25	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/3-8 BW TAN EPOXY	GSCFC11399	0.55	0.05	7D	25	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/3-11 BW TAN EPOXY	GSCFC11401	-	-	-	-	-	ADHESIVE

MATERIAL	DATA REFERENCE	#TEL	%CVC	CURE TIME	CURE TIME	AIR	APPLICATION
ARMSTRONG A-31 A/B AS 6/4 BN EPOXY	GSPC1117	-56	.03	2H	60	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/4 BN EPOXY (CHNG IN B COMP)	GSPC8768	-74	.01	7D	25	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/4 BN TAN EPOXY	GSC11403	-57	.03	7D	25	AIR	ADHESIVE
ARMSTRONG A-31 A/B AS 6/4 BN TAN EPOXY	GSC12799	-54	.03	7D	25	AIR	ADHESIVE
ARMSTRONG A-32 ACT 4 AS 10/6 BN EPOXY	GSPC4944	-49	.00	4H	65	AIR	ADHESIVE
ARMSTRONG C-1/ACT 4 AS 25/2 BN EPOXY	GSPC10649	-97	.04	24H	65	AIR	ADHESIVE
ARMSTRONG C-1/ACT 4 AS 25/2 BN EPOXY	GSPC8492	-1	.01	2H	65	AIR	ADHESIVE
ARMSTRONG C-4/ACT 1 AS 1/1 BN EPOXY	GSPC12802	-1	.01	3H	65	AIR	ADHESIVE
ARMSTRONG C-4/ACT 1 AS 1/1 BN EPOXY	GSPC8843	-1	.01	3H	65	AIR	ADHESIVE
ARMSTRONG C-4/ACT 1 AS 1/2 BN EPOXY	GSPC3001	-83	.28	7D	25	AIR	ADHESIVE
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC3391	-81	.02	21D	25	AIR	ADHESIVE
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC4480	-81	.01	3H	66	AIR	COATING
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC12859	-79	.05	24H	66	AIR	COATING
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC0089	-2	.39	13	74	AIR	ADHESIVE
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC0095	-1	.59	13	74	AIR	COAT
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC6834	-8	.21	5D	25	AIR	COAT
ARMSTRONG C-7/ACT 1 AS 2/3 BN EPOXY	GSPC1873	-36	.03	3H	66	AIR	ADHESIVE
ARMSTRONG C-7/H-20 AS 3/1 BN CLEAR EPOXY	GSPC4536	-6	.27	30M	44	AIR	ADPREG ADHESIVE
ARMSTRONG X-81 EPOXY X-81/A AS 10/1 BN 2/FLEX RESIN	GSPC1924	-94	.02	4H	150	AIR	ADLD CPND
ARMSTRONG X-81 EPOXY X-81/A AS 10/1 BN 2/FLEX RESIN	GSC10236	-90	.02	4H	150	AIR	ADLD CPND
ARMSTRONG X-81 EPOXY X-81/A AS 10/1 BN 2/FLEX RESIN	GSC13210	-24	.07	4H	150	AIR	CONNECTOR
ARMSTRONG X-81 EPOXY X-81/A AS 10/1 BN 2/FLEX RESIN	GSC12913	-32	.07	4H	150	AIR	CONNECTOR
ARYLON ALPHA 201 POLYARYL ETHER INCLED AT 260C AS-4318/H-3486 AS 10/3 BN IMPEAD NO 2	GSPC6269	-61	.05	3H	65	AIR	ADHESIVE
ARYLON ALPHA 201 POLYARYL ETHER INCLED AT 260C AS-4318/H-3486 AS 10/3 BN IMPEAD NO 2	GSPC934	-61	.05	3H	65	AIR	ADHESIVE
ASTREL 360 POLYARYL SULFONE	GSPC2641	-96	.05	3H	121	AIR	POTTING FILM
ASTREL 360 POLYARYL SULFONE TAN GRAY POLYESTER AUGAT CONNECTOR 14C05-64N3 SEMI ROLLING 1 AB ₂ -SEMI	GSPC4966	-2	.39	1H	121	AIR	ADHESIVE
ASTREL 360 POLYARYL SULFONE TAN GRAY POLYESTER AUGAT CONNECTOR 14C05-64N3 SEMI ROLLING 1 AB ₂ -SEMI	GSPC4073	-54	.04	8H	135	AIR	VARNISH
BARCO BOND AD-2/A/FAS 2/1 BN EPOXY	GSPC6784	-07	.01	1H	482	AIR	INSULATION
BAVICK LI-METHYL METHACRYLATE -MODIFIED BC 337 HI-THERM VARNISH	GSPC6786	-07	.01	4H	71	AIR	POTTING
BAVICK LI-METHYL METHACRYLATE -MODIFIED BC 337 HI-THERM VARNISH	GSPC4624	-07	.01	8H	100	AIR	CONF COAT-POT
BAKER POLYURETHANE SYSTEM 65	GSPC4720	-28	.03	4H	25	AIR	STRUCTURAL
BALL BEARING CAGE LINEN/PHENOLIC - EXTRACTED	GSPC4722	-26	.01	16H	80	AIR	RESIN
BLACK CABLE TIE NYLON 66	GSC11603	-35	.00	4H	60	AIR	CABLE TIE
BARCO BOND AD-2/A/FAS 2/1 BN EPOXY	GSPC6049	-20	.00	30M	66	AIR	ADHESIVE
BAVICK LI-METHYL METHACRYLATE -MODIFIED BC 337 HI-THERM VARNISH	GSPC5837	-69	.05	30M	66	AIR	LEADS
BC 340 VARNISH PVCYL ESTER/XYLENE	GSPC3986	-21	.00	30M	25	AIR	VARNISH
BC 346-B PHENOLIC VAENISH	GSPC0454	-59	.00	30M	25	AIR	VARNISH
BC 500T SUFFLEX-SILVERFLEX SLEEVING	GSC12589	-74	.00	30M	25	AIR	VARNISH
BELDEN BIGUE ISOMID 36T-1 MAGNET WIRE BLUE/GREEN	GSPC1306	-31	.49	1H	135	AIR	WIRE COATING
BELDEN MAGNET WIRE 3002 MIL 583C POLYBHENZALEE INS	GSPC10781	-05	.02	7D	75	AIR	WIRE COATING
BELDEN PVC THREAPLASTIC PLASTIC WIRE INSULATION	GSPC4442	-05	.02	15-049	10-33	AIR	WIRE INSUL
BELDEN SMC WIRE VALUES INCLUDE WT OF WIRE	GSPC2803	-02	.02	15-049	10-33	AIR	MOTOR WINDING
BELDEN 8524-1000 VINYL INSULATION	GSPC2149	-05	.02	24-03	8-72	AIR	CABLE INSUL
BELDEN GREEN 36T-1 MAGNET WIRE GREEN BE-N-HAR PIRO-SLEEVING TAPE	GSPC3181	-24	.02	24-03	8-72	AIR	LACING TAPE
BELDEN GREEN 36T-1 MAGNET WIRE GREEN BE-N-HAR PIRO-SLEEVING TAPE ST COATED GLASS FIBER	GSPC0659	-24	.02	24H	300	AIR	SLEEVING
BELDEN GREEN 36T-1 MAGNET WIRE GREEN BE-N-HAR PIRO-SLEEVING TAPE ST COATED GLASS FIBER	GSPC4446	-24	.02	24H	300	AIR	
BELDEN GREEN 36T-1 MAGNET WIRE GREEN BE-N-HAR PIRO-SLEEVING TAPE ST COATED GLASS FIBER	GSPC1066	-24	.02	24H	300	AIR	
BELDEN GREEN 36T-1 MAGNET WIRE GREEN BE-N-HAR PIRO-SLEEVING TAPE ST COATED GLASS FIBER	GSC10931	-24	.02	24H	300	AIR	

MATERIAL	REFERENCE	DATA	STL.	ICVCA	CURE TIME	CURE TEMP	ADHESIVE	APPLICATION
BENDIX CONNECTOR FCD 2-6500 RED SILICONE GREEN POLYMER	GSC11264 GSC11165 GSC11169 GSC11174 GSC11171	-10 -10 -16 -16 -29	.04 .04 .04 .04 .04	.03 .04 .05 .05 .05	CURE INSUL CURE INSUL CURE INSUL CURE INSUL CURE INSUL	CURE INSUL		
BENDIX CONNECTOR JIGGERS 22-355 RED SILICONE POLYMER	GSC11165	-10	.04	.03	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR JIGGERS 24-355 DARK SILICONE POLYMER	GSC11169	-10	.04	.04	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR JIGPOZER 24-35P PINK SILICONE	GSC11174	-16	.04	.04	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR JPT024-14-19P RED SILICONE	GSC11171	-29	.05	.05	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR PT074-14-19P BLACK U RING	GSC11177	-17	.04	.04	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR PT074-14-19P GREEN GLASS INSERT	GSC11189	-14	.03	.03	CURE SEAL	CURE SEAL		
BENDIX CONNECTOR PT074-14-19P RED SILICONE O RING	GSC11225	-23	.03	.03	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR TCRUN 4204 POLYAMID-IMID	GSPC8309	-71	.03	.03	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR 9-5500 RED RUBBER INSERT MATERIAL	GSPC8347	-19	.03	.03	CURE INSUL	CURE INSUL		
BENDIX CONNECTOR 9-5500 RED RUBBER INSERT MATERIAL	GSPC8347	-37	.03	.03	CURE INSUL	CURE INSUL		
BETACONAR QUISETTE NOVEN FIBERGLASS STYLE 2530	GSPC7094	-03	.03	.03	CURE COAT	CURE COAT		
BETACONAR QUISETTE NOVEN FIBERGLASS STYLE 2530 A/B AS 3/1 EW	GSPC7030	-10	.03	.03	CURE COAT	CURE COAT		
BF 1006 STYRENE ACRYLONITRILE 240 WHITE SILICONE WIRE INSULATION	GSPC0933	-24	.01	.01	BUILD CEND	BUILD CEND		
BLW P/E 5639-L-G20 WHITE SILICONE WIRE INSULATION	GSPC0538	-28	.29	.29	WIRE INSUL	WIRE INSUL		
BLW P/E 5639-L-G20 BLACK PART	GSPC0530	-03	.32	.32	WIRE INSUL	WIRE INSUL		
BLW P/N F5639-L-G22 BLACK PART	GSPC0649	-72	.32	.32	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G22 ENTIRE CABLE	GSPC0649	-35	.33	.33	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G22 ENTIRE CABLE	GSPC0704	-51	.10	.10	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G23 INNER CABLE INSUL	GSPC0704	-93	.09	.09	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G24 OUTER JACKET	GSPC0637	-42	.13	.13	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G24 OUTER JACKET	GSPC0631	-04	.04	.04	CABLE INSUL	CABLE INSUL		
BLW P/N F5639-L-G22 WHITE MIDDLE CORE	GSPC0692	-04	.04	.04	CABLE INSUL	CABLE INSUL		
BLW 5639-L-G22 UNSHELLED CABLE WHITE SILICONE INSUL	GSPC0688	-74	.24	.24	CABLE INSUL	CABLE INSUL		
BLW 5639-L-G22 UNSHELLED CABLE WHITE SILICONE INSUL	GSPC0681	-11	.02	.02	CABLE INSUL	CABLE INSUL		
BLACK MAGNETIC MOLY SEPARATE FOIL - AEROSOL NO. 32	GSPC9534	-27	.04	.04	LUBRICANT	LUBRICANT		
BLUE COATING 11001057/KEA FLEXIBLE AND EPOXY	GSPC0495	-41	.04	.04	LOCATING	LOCATING		
BONDMASTER E645 A/E AS 10/3 BW ADH	GSPC7529	-68	.04	.04	ADHESIVE	ADHESIVE		
BONDMASTER E645 A/E AS 10/3 BW EPOXY	GSPC4554	-50	.01	.01	ADHESIVE	ADHESIVE		
BONDMASTER E645 A/E AS 10/3 BW EPOXY W/MEK THINNER	GSPC4672	-90	.15	.15	ADHESIVE	ADHESIVE		
BONDMASTER E645 A/E AS 10/3 BW THERMOSET EPOXY	GSPC3441	-52	.03	.03	ADHESIVE	ADHESIVE		
BONDMASTER M688/CH-16 AS 100/32 BW EPOXY	GSPC0155	-04	.04	.04	AIR	AIR		
BONDMASTER M688/CH-16 AS 100/32 BW EPOXY	GSPC4412	-62	.03	.03	AIR	AIR		
BONDMASTER M688/CH-8 AS 100/13 BW EPOXY	GSPC1390	-290	.08	.08	AIR	AIR		
BONDMASTER M688/CH-8 AS 100/13 BW EPOXY	GSPC3363	-390	.11	.11	AIR	AIR		
BONDMASTER M773 A/E AS 1/1 BW EPOXY	GSPC3959	-50	.09	.09	AIR	AIR		
BONDMASTER M773 A/E AS 1/1 BW EPOXY	GSPC5180	-63	.11	.11	AIR	AIR		
BONDMASTER M773 A/E AS 1/1 BW EPOXY	GSPC5248	-37	.10	.10	AIR	AIR		
BONDMASTER M777 A/E AS 1/1 BW EPOXY	GSPC3961	-82	.09	.09	AIR	AIR		
BONDMASTER M777 A/E AS 1/1 BW EPOXY	GSPC5182	-41	.13	.13	AIR	AIR		
BONDMASTER M777 A/E AS 1/1 BW EPOXY	GSC12592	-72	.13	.13	AIR	AIR		
BONDMASTER 4500 PLUS A/B AS 1/1 EV FAST CURE EPOXY	GSPC12592	-71	.6	.6	E-3	E-3		
BONDMASTER 4500 PLUS A/B AS 1/1 EV FAST CURE EPOXY	GSC12592	-71	.93	.93				

MATERIAL	DATA REFERENCE	XTHL	XCVCM	CURE TIME	CURE ALMOS	APPLICATION
BONDMASTER 620	GSPC3936	.74		.02 2H	80 1H	AIR ADHESIVE
BORON NITRIDE - HEAT SINK WASHER BOSTIK PINCH 4-43-3/4-304 AS 3/4" BY WHITE EPOXY PAINT BOSTIK PINCH 6-43-2-20-7/1 BW WHITE POLYURETHANE ADHESIVE ONE COMPONENT BOSTIK PINCH ELECTRONIC ADHESIVE ONE COMPONENT	GSPC6788 GSPC8396 GSPC8468 GSC12703	7-.05 4-.67 1-.75	.06 .13 .21	7D 7D 5H	25 25 65 135	WASHER PAINT PAINT ADHESIVE
BOSTIK PINCH EPOXY PRIMER PR 463-12-8 A/B AS 3/4 BW B3 34 EPOXY ADHESIVE	GSPC8036 GSPC3700	4-.29 .65	.02 .06	2H 30H	25 194 177	AIR PRIMER ADHESIVE
B3 34 EPOXY ADHESIVE	GSPC3702	-.34	.00	30H	25 30M	AIR ADHESIVE
BR 90/BR 802 AS 100/8 BW EPOXY ADHESIVE	GSC12358	6-.80	.04	90H	288	AIR ADHESIVE
BR 90/BR 802 AS 100/8 BW EPOXY ADHESIVE/F	GSC12361	1-.77	.03	7D	25	AIR ADHESIVE
BR-0014 PHENOLIC RESIN/EPOXY/F BR-125 PRIMER/MOD NITRILE EPOXY/F	GSC12727	3-.04	.01	24H	250	AIR ADHESIVE
BR-127 PRIMER/F B3-610 EPOXY/TETRAHYDROFURANE/F BR-610 EPOXY/TETRAHYDROFURANE/F	GSC12268	1-.19	.13	30H	25	AIR ADHESIVE
BR-626 ONE COMPONENT HEAT CURING EPOXY BRADY FILM L363-81A/SILICONE ADHESIVE/F BRADY FILM L363-81A/SILICONE ADHESIVE/F BRADY FILM L363-81E/SILICONE ADHESIVE/F BRADY FILM 939 CLEAR ACRYLIC ADH/F BRADY HI-TEMP LABELS ON L-363-81B TAPE/F BRADY LABEL B-637 VELLION/BLACK TEDLAR/ACRYLIC ADH/F	GSC10164 GSPC7988 GSPC7991	1-.48 1-.14 -.99	.31 .02	1.5H 90N 30H	1110 1127 60	AIR PRIMER ADHESIVE
BRADY MARKERS B-4-2-CAP POLYESTER ADH	GSPC8564 GSPC8566 GSPC8598 GSPC8570	1-.84 1-.82 1-.86 1-.50	.01 30H	1H	25 121	AIR LABEL FILM LABEL FILM LABEL FILM
BRADY MARKERS B-400 TD-400-1	GSPC31923 GSPC1926 GSPC3864 GSPC3161	2-.59 1-.86 1-.01 1-.01	.05 28			LABEL LABEL MARKER
BRADY MARKERS B-600	GSPC6688 GSPC5661	1-.80 1-.63				DARKER
BRADY MARKERS B-700 YM 0-49	GSPC4894 GSPC11788	2-.21 1-.74				DARKER
BRADY MARKERS B-7002/F	GSPC5631 GSPC11863	1-.34 1-.74				DARKER
BRADY MARKERS B-7053 LT-200/F	GSPC3542 GSPC9915	1-.66 1-.81				DARKER
BRADY MARKERS B-7053 HT-200/F	GSPC5252 GSPC3639	1-.52 4-.03				DARKER
BRADY PERMA CODE LABELS NO-19 SPECIAL	GSPC9632 GSPC9633	1-.75 1-.74				LABEL
BRADY WHITE ON LABELS NO-19	GSPC9632 GSPC9633	1-.42 1-.03				LUBRICANT
BRAYCO 813 CLEAR OIL BATCH EIA3	GSPC9632 GSPC9633	1-.34 1-.03				LUBRICANT
BRAYCO TE 8152 CLEAF CIL BATCH DLM 3	GSPC9396 GSPC9397 GSPC9321	1-.03 1-.07 1-.07				RELEASE
BRAYCO TE 3L-38 GREASE BATCH DLD1 WHITE	GSPC9488	1-.04				LUBRICANT
BRAYCO TE 3L-38 GREASE BATCH DLD1 WHITE	GSPC9512	1-.09				RELEASE
BRAYCO TE 3L-38-NS GREASE BATCH CLT7 YELLOW	GSPC9587 GSPC9491	1-.04 2-.39				RELEASE
BRAYCO TE 3L-38-ZN GREASE BATCH ELM4 BLACK	GSPC9491	1-.01 1-.03				LUBRICANT
BSL 201 A/B AS 11/1 BW	GSPC1141	1-.03 1d				RELEASE
		25				PUTTING

MATERIAL	DATA REFERENCE	STYL	%CVCM	CURE TIME	CURE TEMP	AIRHOJ	APPLICATION
B5L 201 A/B AS 11/1 BW	G5FC1144	1.46	.05	30H	100	A/A	PUTTING
B5L 206 BLACK EPCKY	G5FC8726	1.42	.15	1H	25	A/A	PUTTING
B5L 308 BLACK EPOXY UNSUPPORTED ADHESIVE FILM	G5FC81108	.82	.11	1H	164	A/A	PUTTING
B5L 308 EPOXY	G5FC1129	.70	.09	1H	174	A/A	ADH FILM
B5L 312 GRAY EPOXY UNSUPPORTED ADHESIVE FILM	G5FC8135	.49	.10	1H	175	A/A	PUTTING
BTR II SILICONE GRAYMET CB 1077-40 BROWN	G5FC12694	.62	.07	30H	120	A/A	ADH FILM
BTR RUBBER HD22-31	G5FC4896	.32	.11	1H	164	A/A	COMMET
BTR RUBBER HD22-31	G5FC1132	.39	.09	1H	164	A/A	DAMPER
BTR RUBBER HD22-22-2 IN ALUMINUM SANDWICH	G5FC2785	1-39	.13	1H	164	A/A	DAMPER
BTR RUBBER HTG (J-63330-5-1)/21	G5FC7352	.28	.20	1H	174	A/A	DAMPER
BTR RUBBER VIBRATION ISOLATOR HT-100	G5FC8513	.41	.20	1H	175	A/A	DAMPER
BTR SHING TYPE BEETLE HILL D-14 MICA FILLED PHENOLIC	G5FC8572	1-34	.45	1H	164	A/A	SUSING
BUTYL METACRYLATE-BENZYL PEROXIDE	G5FC0612	1-38	.01	1H	164	A/A	SUSING
BUTYL 218 CURED	G5FC0143	3-52	.01	1.5H	100	A/A	SUSING
BUTYL 218-A CURED	G5FC0140	2-00	.07	1-07	100	A/A	SUSING
BUTYL 218-A UNCURD	G5FC0146	3-17	.57	1-07	100	A/A	SUSING
BUTYL 218-A UNCURD	G5FC0122	3-20	.01	1-15	160	A/A	SUSING
BUTYL 92 NATURAL SCALDED NOMEX THREAD	G5FC8474	1-95	.95	2H	160	A/A	SUSING
C-1589-3 BLACK INK/P AS 4/5 B/A 4/16 H4-3441 BLACK EPOXY	G5C11794	11-68	.06	3-06	7D	A/A	LINK
C-18F/A/B AS 4/5 B/A 4/16 H4-3441 BLACK EPOXY/70% SANDBILLED	G5FC9182	74	.06	4H	130	A/A	ROTTING
C-68/C/AS 100% 3.6W GRAY EPOXY/70% SANDBILLED	G5FC7517	1-12	.06	20H	82	A/A	ADHESIVE
C-725 TAPE POLYESTER FILM/2 SIDE ACRYLIC ADH/F	G5FC5058	1-54	.04	1-14	20H	A/A	2 SIDED TAPE
C-727 TAPE PVC FILM/2 SIDED ACRYLIC ADH/F	G5FC5061	1-24	.04	1-24	20H	A/A	2 SIDED TAPE
C-917 MS BLACK INK/P	G5C11791	8-97	.29	1-29	7D	A/A	LINK
C-917 MS BLACK INK/P	G5C1201U	8-12	.08	24H	60	A/A	LINK
C-917 MS BLACK INK/P HEAT GUN DRY	G5C12007	9-76	.15	7D	25	A/A	LINK
C-99/DETA AS 25/1 EM EPOXY FILM	G5FC4456	11-07	.04	12H	60	A/A	LINK
CABLE BELDEN BG-58 C/U 8262 3000 Hh VAC EXPOSURE	G5PC3760	1-97	.36	1-36	13-93	A/A	CABLE INSUL
CABLE BELDEN BG-58 C/U 8262 3000 Hh VAC EXPOSURE	G5FC3608	13-92	.93	1-36	13-93	A/A	CABLE INSUL
CABLE CLAMP TAO 21-07 H0-07UB RED BUBBER SLEEVE	G5FC13439	-00	.47	1-03	1-03	A/A	CABLE CLAMP
CABLE COAX WHITE OUTER INSUL MICRORODOT	G5C11075	-00	.00	1-00	1-00	A/A	CABLE INSUL
CABLE CO6CU2 9551 COAX WHITE OUTER INSUL	G5FC8084	02	.00	1-01	1-01	A/A	CABLE INSUL
CABLE HI-VOLTAGE WHITE OUTERSHEATH	G5C12271	-09	.41	1-01	1-01	A/A	CABLE INSUL
CABLE HI-VOLTAGE WHITE OUTERSHEATH	G5FC8204	-07	.01	1-01	1-01	A/A	CABLE INSUL
CABLE AG-316/0 CCAX TAN OUTER INSUL	G5FC3604	9-13	.53	4-52	4-52	A/A	CABLE INSUL
CABLE 17/C 6-61 BY KONONITE DUONT HYPALEX	G5FC8543	1-69	.03	1-03	1-03	A/A	CABLE INSUL
CABLE 22193000 BLACK/WHITE TEPLOIN INSULATION	G5FC9515	-03	.03	1-01	1-01	A/A	CABLE INSUL
CABLE 247399408 KAFTON SHIELDED POLYIMIDE	G5FC2721	-44	.00	1-00	1-00	A/A	CABLE INSUL
CABLE 2619K2-0 CRESJO COAX BED OUTER INSUL	G5FC8138	-09	.01	1-01	1-01	A/A	CABLE INSUL
CANNON CONNECTOR ACUSATOR MIK U RING INTERFACIAL SEAL	G5FC715	4-24	.02	1-02	1-02	A/A	CANNON HOUSING
CANNON CONNECTOR MIL POLYCARBONATE INSUL GREEN	G5C11421	2-43	.15	1-03	1-03	A/A	CANNON INSUL
CANNON CONNECTOR MIL C38999 PINK INSERT	G5C10438	-44	.01	1-01	1-01	A/A	CANNON INSUL
CANNON CONNECTOR MS3476 BLACK PHENOLIC INSERT	G5FC8279	-54	.01	1-01	1-01	A/A	CANNON INSUL
CANNON CONNECTOR PINK SILICONE INSERT SILICONE C-16 MSFC 40N 39569	G5FC8276	-49	.01	1-01	1-01	A/A	CANNON INSUL
	G5FC5573	-07	.01	1-01	1-01	A/A	CANNON INSUL

MATERIAL	DATA	#THL	ACVCH	CURE TIME	CURE TEMP	STATUS	APPLICATION
CANNON CONNECTOR PW66GB372 PINK SILICONE ONLY	GSPC4144	.14	.02				CONNECTOR
CANNON CONNECTOR PW6G24B31SWC 16 BLACK PLASTIC	GSPC3344	.61	.00				CONNECTOR
CANNON CONNECTOR PW6G24B31SWC 16 RED SILICONE	GSPC3343	.19	.00				CONNECTOR
CANNON CONNECTOR 463-3-6 ASSFC40H 39569	GSPC5575	.08	.03				CUNN INSUL
CANNON CONNECTOR 463-3-6 C-16 PINK SILICONE	GSC11423	.06	.02				CUNN SEAL
CANNON CONNECTOR 463-3-6 PINK SILICONE	GSC11425	.34	.13				CUNN INSUL
CANNON CONNECTOR 7824-2DD-100P BLACK NYLON/GLASS	GSC12448	1.49	.04				CUNN INSUL
CANNON FILTER PIN CONN DDJ-50UPN-A106 BLUE SILICONE	GSPC6979	.64	.23				CUNN INSUL
CANNON FILTER PIN CONN DDJ-50UPN-A106 BLUE SILICONE	GSPC6718	.31	.06				CONNECTOR
CANNON FILTER PIN CONN DDJ-50UPN-A106 BLUE SILICONE	GSPC2334	.24	.00				CONNECTOR
CANNON FILTER PIN CONN DDJ-50UPN-A106 BLUE SILICONE	GSC13030	4.93	.12				CONNECTOR
CAPRAN 512H NYLON ANTI STATIC FILM	GSC13362	6.01	.12				BAGGING
CARE #2 ANTI STATIC FILM	GSC1274	16.78	.93				BAGGING
CARE #2 ANTI STATIC FILM	GSC12934	1.61	.57				BOLD RELEASE
CAREOL 1019 EPOXY A/B AS 1/4 B _n	GSC12934	1.51	.55				BOTTING
CASTALL CX230B CLEAR SILICONE	GSPC7934	2.55	.00	12H	65	AIR	ADHESIVE
CASTALL E/A/B CUBE 1/4 BW GRAY EPOXY	GSPC6605	1.25	.47	24H	25	AIR	ADHESIVE
CASTALL QUICK CUBE EPOXY CAST-PAK PRE-MIX	GSPC10044	0.28	.31	4H	65	AIR	ADHESIVE
CASTALL 450/HF7 AS 100/7.5 BW EPOXY	GSC10536	9.58	3.47	4H	125	AIR	ADHESIVE
CASTALL 450/HF7 AS 100/7.5 BW EPOXY	GSC10559	7.79	3.47	4H	125	AIR	ADHESIVE
CASTALL 832-H HEAT SINK GREASE - PINK	GSPC2527	3.03	.06	72H	25	AIR	HEAT GREASE
CASTALL 832-H HEAT SINK GREASE - WHITE	GSPC2527	3.03	.06	72H	25	AIR	HEAT GREASE
CAT-A-LAC FLAT BLACK EPOXY COATING	GSPC2041	3.94	.13	7D	51	E-D	PAINT
CAT-A-LAC WHITE EPOXY A/B AS 3/1 BV	GSPC2041	3.94	.13	7D	25	AIR	PAINT
CAT-A-LAC WHITE EPOXY A/B AS 3/1 B _n	GSPC2038	12.09	.14	7D	25	AIR	PAINT
CAT-A-LAC 463-3-100 A/B AS 3/1 B _n	GSPC076	6.75	.23	24H	66	AIR	PAINT
CAT-A-LAC 463-3-100 A/B AS 3/1 B _n	GSPC0791	4.13	.14	16H	66	AIR	PAINT
CAT-A-LAC 463-3-100 A/B AS 3/1 B _n	GSPC8918	4.16	.02	24H	25	AIR	PAINT
CAT-A-LAC 463-3-100/CA-118 AS 3/1 BV WHITE PAINT	GSPC8921	4.11	.02	16H	25	AIR	PAINT
CAT-A-LAC 463-3-100/CA-118 AS 3/1 BV/PRIMER 463-6-5	GSPC1147	.35	.17	24H	25	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	GSPC1150	4.50	.12	47H	17	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	GSPC1165	1.18	.21	72H	66	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-12-1A	GSPC1168	.55	.22	48H	121	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK OVER PRIMER 463-6-2 GREEN/P	GSPC8156	.70	.03	24H	25	AIR	PAINT COMPOSITE
CAT-A-LAC 463-3-6 BLACK EPOXY PAINT	GSC10937	2.14	.03	1H	66	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK EPOXY PAINT	GSPC2164	1.33	.00	24H	140	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK EPOXY PAINT	GSPC4240	1.02	.05	4H	25	AIR	PAINT
CAT-A-LAC 463-3-6 BLACK EPOXY PAINT	GSPC4198	4.05	.03	30H	135	AIR	PAINT
CAT-A-LAC 463-3-6/CA-118 AS 3/1 BV BLACK EPOXY PAINT	GSC12622	3.42	.07	1H	25	AIR	PAINT
CAT-A-LAC 463-3-6/CA-97 AS 3/1 BV BLACK EPOXY PAINT	GSPC9464	2.91	.25	2H	60	AIR	COND PAINT
CAT-A-LAC 463-3-6/CA-97 AS 3/1 BV BLACK EPOXY PAINT	GSPC4240	6.5H	104				COND PAINT

MATERIAL	DATA REFERENCE	STL	UVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV BATCH - TKN	GSPC9405	3.96	.17	2H-5H	66-104	A/A	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	GSPC8741	8-16	.33	14D	25	A/A	PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	GSPC9176	6-98	.36	24H	65	A/A	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	GSPC9179	2-17	.35	24h	25	A/A	COND PAINT
CAT-A-LAC 463-6-14/CA-97 AS 3/1 BV COND BLK PAINT/F	GSPC9275	1-47	.34	24H	25	A/A	COND PAINT
CAT-A-LAC 473-3-1 A/E AS 3/1 bV CLEAR EPOXY	GSPC7178	9-02	.43	16H	104	A/A	COATING
CAT-A-LAC 473-3-1 A/X-304 AS 3/1 bW CLEAR EPOXY	GSPC12625	4-36	.24	1H	95	A/A	PAINT
CAT-A-LAC 473-3-1 A/X-304 AS 3/1 bW CLEAR EPOXY	GSPC3580	2-35	.19	100H	45	A/A	PAINT
CAULK GROUT CEMENT LIQUID METHACRYLATE FILLED	GSPC5557	1-06	.02	SD	25	A/A	ADHESIVE
CD-772-2 POLYURETHANE	GSPC1085	1-01	.01	3D	25	A/A	ADHESIVE
CEBDA 60 POLYURETHANE	GSPC2068	1-08	.24				POTTING
CEBDA 70 POLYURETHANE	GSPC9224	-64	.04				POTTING
CELLCON H-90-04 ACETAL COPOLYMER INJECTION MOLDED	GSPC9494	-57	.03				DUOD CPND
CELLULOSE ACETATE UNGELDED PELLETS	GSPC9494	-50	.01				DUOD CPND
CELLULOSE ACETATE FILM 200 MICRON FILM PURPLE	GSPC6080	10-79	1-19				FILM
CELLULOSE ACETATE FILM SHIM STOCK	GSPC4774	-00	.00				FILM
CELLULOSE TRIACETATE 200 MICRON FILM BLUE	GSPC9497	1-28	.00				FILM
CERTAINIUM 61 SOLDER - OXIDIZED SN/PB/5% CD	GSPC6080	1-05	.05				SOLDER
CERTAINIUM 61 SOLDER SN/PB/15% CD	GSPC4774	-00	.00				OPT ADHESIVE
CELLULOSE IODIDE COUPLING COMPOUND BLEND 10/1	GSPC8039	8-50	5-51				OPT ADHESIVE
CESIUM IODIDE COUPLING COMPOUND BLEND 12/1	GSPC8039	9-06	6-33				OPT ADHESIVE
CERIUM 1006 STRANE/EFILE GLASS AS 70/30	GSPC942	-10	-04				DUOD CPND
CF 3003 EPOXY FOR HUGHES CONNECTOR 13°C320 HO1	GSPC7385	-43	-04				POTTING
CFB 4012 FLUOBOSILICONE COATED DACHRON FABRIC	GSPC13054	-45	-09				GASKET
CHEM-PCL 30-1961/2023 AS 1/1 bW POLYURETHANE FOAM	GSPC8111	7-07	72H				ARM
CHEMFLUOK TEFLON LIFE SHRINK TUBING	GSPC4693	7-00	.05				SHANK TUBING
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE	GSPC8801	1-67	14D				PAINT
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE	GSPC9542	2-25	.02				PAINT
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE LOT TJD	GSPC9984	2-37	.10				PAINT
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE LOT TJD	GSPC9987	1-46	.10				PAINT
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE/F	GSPC12244	1-87	.14				PAINT
CHEMGLAZE A276 HIGH GLOSS WHITE POLYURETHANE/F	GSC12247	.99	.08				PAINT
CHEMGLAZE H322 BLACK CONDUCTIVE PAINT POLYURETHANE	GSPC8066	1-92	.07				COND PAINT
CHEMGLAZE H322 BLACK CONDUCTIVE PAINT POLYURETHANE	GSPC8069	1-86	.09				COND PAINT
CHEMGLAZE L301 BLACK CONDUCTIVE PAINT POLYURETHANE	GSPC9467	1-57	.06				COND PAINT
CHEMGLAZE MC 3692-74 FLAT BLACK POLYURETHANE LCT YEA	GSC11890	1-18	.01				PAINT
CHEMGLAZE TC 3692-74 FLAT BLACK POLYURETHANE LCT YEA	GSC12598	1-17	.01				PAINT
CHEMGLAZE TS 2881-7 UV RESIST WHITE POLYURETHANE	GSPC7256	8-57	.02				PAINT
CHEMGLAZE TS 2881-7 UV RESIST WHITE POLYURETHANE	GSPC7328	4-50	.22				PAINT
CHEMGLAZE TS 3107-13 FLAT BLACK POLYURETHANE LOT SHD	GSPC9008	1-30	.02				PAINT
CHEMGLAZE TS 3107-13 FLAT BLACK POLYURETHANE LOT SKA	GSPC9083	1-35	.02				PAINT
CHEMGLAZE TS 31092-51 FLAT BLACK POLYURETHANE LOT SKA	GSPC10694	2-15	.26				PAINT
CHEMGLAZE TS 3492-74 FLAT BLACK POLYURETHANE	GSC10790	1-23	.22				PAINT
CHEMGLAZE V200 GLOSSY WHITE POLYURETHANE PAINT/F	GSC10583	2-73	.17				PAINT SYSTEM
CHEMGLAZE V200/9924 GLOSS WHITE POLYURETHANE PAINT/F	GSC12286	2-52	.07				PAINT SYSTEM

MATERIAL	DATA REFERENCE	XIVNL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CHEMGLAZE V200/9924 GLOSS WHITE POLYURETHANE PAINT/F	GSC12288	.72	.03	11D	25	AIR	PAINT SYSTEM
CHEMGLAZE V200/9985 AS 50/1-3 BW GLOSSY WHITE PAINT	GSC10586	6-03	.47	72H	25	AIR	PAINT
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT LOTBHA	GSC13398	10-19	.76	7D	25	AIR	PAINT
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT LOTBHA	GSC13460	9-97	.56	30D	25	AIR	PAINT
CHEMGLAZE V209 GLOSS WHITE POLYURETHANE PAINT LOTBHA	GSC13463	8-46	.51	4D	25	AIR	PAINT
CHEMGLAZE V209 GLC55 WHITE POLYURETHANE PAINT LOTBHA	GSC13478	1-07	.04	24H	65	B-9	PAINT
CHEMGLAZE V700/9995 AS 25/1 BW BLUE PAINT	GSC13526	5-48	.23	24H	100	B-0	PAINT
CHEMGLAZE 2001 CLEAR POLYURETHANE FLEXIBLE	GSFPC3756	1-42	.01	24H	120	AIR	CONF COAT
CHEMGLAZE 2001 CLEAR POLYURETHANE FLEXIBLE	GSFPC3798	1-18	.02	14D	25	AIR	CONF COAT
CHEMGLAZE 2001 CLEAR POLYURETHANE FLEXIBLE LOT TBA	GSFPC9608	1-50	.01	14D	25	AIR	CONF COAT
CHEMGLAZE 2004 BLACK CND PAINT MOD POLYURETHANE	GSFPC8072	1-35	.01	7D	25	AIR	CONF PAINT
CHEMGLAZE 2004 BLACK CND PAINT MOD POLYURETHANE	GSFPC8282	.90	.04	24H	25	AIR	CONF PAINT
CHEMGLAZE 2004 CLEAR POLYURETHANE HIGH FLEX LOT SHA	GSFPC9611	1-51	.01	24H	70	AIR	CONF COAT
CHEMGLAZE 2004 CLEAR POLYURETHANE HIGH FLEX LOT TAA	GSFPC9614	1-50	.01	14D	25	AIR	CONF COAT
CHEMGLAZE 2004 CLEAR POLYURETHANE HIGHLY FLEXIBLE	GSFPC3758	1-20	.01	14D	25	AIR	CONF COAT
CHEMGLAZE 2004 BLACK CND PAINT MOD POLYURETHANE	GSFCC11893	1-72	.01	14D	25	AIR	CONF COAT
CHEMGLAZE 2004 BLACK CND PAINT MOD POLYURETHANE	GSFCE6161	6-17	.01	20	25	AIR	DARKING LINK
CHEMGLAZE 2004 CLEAR POLYURETHANE LOT XGB	GSFCE6162	2-29	.03	2H	25	AIR	DARKING INK
CHEMGLAZE 2004 W/10% P-82 RED COLORANT	GSFCE7754	-83	.03	2H	25	AIR	DARKING INK
CHEMGLAZE 2004 W/5% CHROMIC OXIDE PIGMENT	GSFCE7755	-2.9	.03	2H	25	AIR	DARKING INK
CHEMGLAZE 2004 PRIMER BLACK CND PAINT	GSFCC8849	1-40	.01	18H	60	AIR	CONF PAINT
CHEMGLAZE 2004 XC-72R/9924 PRIMER BLACK CND MOD	GSFCC8075	2-09	.01	7D	25	AIR	CONF PAINT
CHEMGLAZE 2004 XC-72R/9924 PRIMER COMPOSITE BLACK CND MOD	GSFCE8285	1-24	.04	24H	70	AIR	CONF PAINT
CHEMGLAZE 2053 CLEAR POLYURETHANE COATING	GSFPC6950	2-22	.01	14D	25	AIR	CONF COAT
CHEMGLAZE 2202 POLYURETHANE FOAM ERL TSN 1603-16	GSFPC24613	-60	.02	14D	25	AIR	PAINT
CHEMGLAZE 2202 WHITE POLYURETHANE COATING	GSFPC3109	2-63	.00	30D	25	AIR	PAINT
CHEMGLAZE 2202 GLOSSY BLACK POLYURETHANE	GSFCC3345	1-39	.00	14D	25	AIR	PAINT
CHEMGLAZE 2306 PRIMER L11247	GSC11427	1-12	.04	21D	25	AIR	PAINT
CHEMGLAZE 2306 BATCH L11247	GSC11318	-49	.02	24H	100	B-3	PAINT
CHEMGLAZE 2306 LOT LBC	GSFCC3827	.47	.04	24H	100	B-0	PAINT
CHEMGLAZE 2306 LCT LBC	GSFPC3841	1-32	.01	16H	65	AIR	PAINT
CHEMGLAZE 2306 LOT HAA	GSFPC4316	1-42	.02	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT HAA	GSFPC4314	1-92	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LOT MJC	GSFPC4626	1-91	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT NBA	GSFPC4946	1-90	.00	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT NBA SPRAYED	GSFCC1300	1-13	.06	7H	25	AIR	PAINT
CHEMGLAZE 2306 LCT NDA	GSFCC5228	1-87	.04	14D	25	AIR	PAINT
CHEMGLAZE 2306 LOT OAB SPRAYED	GSFPC5109	1-76	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT QGB SPRAYED	GSFPC6020	1-64	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LOT RLA SPRAYED	GSFPC6629	1-04	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LOT RLA	GSFPC9440	1-10	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT TDA	GSFPC9617	1-91	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	GSFCC10721	1-16	.01	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	GSC11525	1-92	.03	14D	25	AIR	PAINT
CHEMGLAZE 2306 LCT YBA	GSC11896	1-09	.03	14D	25	AIR	PAINT

MATERIAL	DATA REFERENCE	XCVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
CHEMGLAZE Z306/B40L MICROBALLOON STOOL CHEMGLAZE Z306/CAT 9986 AS 100/1 BV/FREE FILM	GSPC2891 GSPC3754	1.83 1.08	.01 .25	24D 15D 24	AIR AIR AIR	PAINT COMPOSITE PAINT COMPOSITE PAINT COMPOSITE
CHEMGLAZE Z306/CAT 9986 AS 100/1 TWO COATS	GSPC3582	1.81	.36	15H 15H 25	AIR AIR AIR	PAINT
CHEMGLAZE Z306/CHEMGLAZE 9924 PRIMER COMPOSITE	GSC11429	1.18	.05	21D 24H 30H	AIR AIR AIR	PAINT COMPOSITE
CHEMGLAZE Z306/CHEMGLAZE 9924 PRIMER COMPOSITE	GSC4124	1.85	.06	10D 13	AIR AIR	PAINT COMPOSITE PAINT COMPOSITE
CHEMGLAZE Z306/CHEMLOCK AP131 PRIMER/F	GSPC7841	1.45	.13	28H 30D	AIR AIR	PAINT COMPOSITE
CHEMGLAZE Z306/CHEMLOCK AP131 PRIMER/F	GSPC3777	1.76	.05	30D 42D	AIR AIR	PAINT COMPOSITE PAINT COMPOSITE
CHEMGLAZE Z306/KAPTON H REINF	GSPC3777	1.00	.08	25	AIR	PAINT COMPOSITE
CHEMGLAZE Z306/KAPTON H REINF	GSPC3781	.94 .88	.09 .09	42H 41D 1H 14D	AIR AIR AIR AIR	PAINT COMPOSITE PAINT COMPOSITE PAINT COMPOSITE PAINT COMPOSITE
CHEMGLAZE Z306/PRIMER DESOTO 513-102/F	GSC10002	1.75	.12	25	AIR	PAINT COMPOSITE
CHEMGLAZE Z306/RANOLPH EPOXY/POLYAMIDE PRIMER/F	GSPC9056	1.67	.08	24H 14D	AIR AIR	PAINT COMPOSITE PAINT COMPOSITE
CHEMGLAZE Z306/SUPER KOROPON PRIMER/F	GSPC9680	2.80	.03	7D 30H	AIR AIR	PAINT COMPOSITE PAINT
CHEMGLAZE 2402 ALUM FILLED POLYURETHANE LOI MED	GSPC4797	.68	.07	14D 7D 93	AIR AIR AIR	PAINT PAINT PAINT
CHEMGLAZE 2651 GREEN GLOSS POLYURETHANE F	GSPC7188	2.79	.02	14D 14D	AIR AIR	DARKING INK DARKING INK
CHEMGLAZE 2652 TIE LINE GREEN GLOSS POLYURETHANE	GSPC6191	0.00	.00	14D	AIR	DARKING INK
CHEMGLAZE 2853 MID YELLOW GLOSS POLYURETHANE	GSC11899	1.84	.03	14D	AIR	PRIMER
CHEMGLAZE 9421 ALUM FILLED P-URETHANE PRIMER LOT XIB	GSPC7979	1.58	.13	1H	AIR	PRIMER
CHEMGLAZE 9922 EPOXY PRIMER FOR METAL	GSPC7979	6.38	.29	7D 30H	AIR AIR	PRIMER PRIMER
CHEMGLAZE 9924 A/E AS 1/1 BV FLASH PRIMER/F	GSPC4093	.34	.00	25	AIR	FLASH PRIMER
CHEMLOCK 205 ADHESIVE PRIMER GREY	GSPC4836	5.95	.03	10H 30H	AIR AIR	POTTING PRIMER POTTING PRIMER
CHEMLOCK 205/CHEMLOCK 220 AS 1/1 BV AS FREE FILM	GSPC7040	6.89	.01	30H	AIR	POTTING PRIMER
CHEMLOCK 205/CHEMLOCK 220 AS 1/1 BV ON FOIL	GSPC7043	15.72	.49	24H 30H	AIR AIR	ADHESIVE ADHESIVE
CHEMLOCK 218 ON FOIL	GSPC6902	.39	.00	25	AIR	ADHESIVE
CHEMLOCK 220 ADHESIVE BLACK	GSPC4838	15.54	.10	10H 30H	AIR AIR	ADHESIVE ADHESIVE
CHEMLOCK 234	GSPC3061	51.85	.88	24H 30H	AIR AIR	ADHESIVE ADHESIVE
CHEMLOCK 234B ELASTICMER BONDING AGENT - BLACK	GSPC6673	30.19	.29	25	AIR	ADHESIVE
CHEMLOCK 236A BONDING AGENT FLAT BLACK/F	GSC13150	27.93	.02	3D 30H	AIR AIR	ADHESIVE ADHESIVE
CHEMLOCK 305 A/B AS 1/1 BV EPOXY	GSPC4811	21.51	.18	18	AIR	COND ADHESIVE
CHO-BOND 1024 CONDUCTIVE SILICONE	GSC10571	.44	.40	1H	AIR	COND ADHESIVE
CHO-BOND 1029 CONDUCTIVE SILICONE	GSPC4384	.02	.02	16	AIR	COND ADHESIVE
CHO-BOND 1030/PRIMER 1030 SILVER FILLED SILICONE	GSPC4776	.38	.31	7D	AIR	COND ADHESIVE
CHO-BOND 1035 ONE PART SILVER FILLED SILICONE	GSPC6299	1.08	.65	25	AIR	COND ADHESIVE
CHO-BOND 1092	GSPC7928	1.67	.35	113	AIR	COND ADHESIVE
CHO-BOND 260-18 A/E AS 40/1 BV COND EPOXY	GSPC5210	1.67	.25H	25	AIR	COND ADHESIVE
CHO-BOND 360-208 CONDUCTIVE EPOXY ADHESIVE	GSPC9683	.66	.04	24H	AIR	COND ADHESIVE
CHO-BOND 4041-0402 A/B AS 1.5/5.5 BV BROWN	GSPC950Q	.39	.10	2H	100	ADHESIVE

MATERIAL	DATA REFERENCE	X-TAL	X-CYAN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CHO-BOND 4041-0402 A/B AS 1-5/5.5 BW BROWN	GSCC9569	.32	.11	3H	200	AIR	AF SHIELD
CHO-BOND 4041-0402 A/B AS 1-5/5.5 BW BROWN	GSCC9593	.31	.11	6H	200	AIR	AF SHIELD
CHO-BOND 584-29 A/E AS 100/6.3 BW COND EPOXY	GSCC4212	1-1.5	.03	45M	100	AIR	COND ADHESIVE
CHO-BOND 584-29 CONDUCTIVE EPOXY	GSCC4584	1-1.2	.04	24H	66	AIR	COND ADHESIVE
CHO-BOND 586-29 A/E AS 100/4.2 BW SILVER EPOXY	GSCC4628	1-9.6	.10	24H	25	AIR	COND COATING
CHO-SEAL 1212 SILVER FILLED SILICONE 125 GRADE	GSFPC3023	.44	.15	2H	100	AIR	FALLER SHIELD
CHO-SEAL 1212 SILVER FILLED SILICONE 125 GRADE	GSFPC3245	.08	.02	15M	171	AIR	FALLER SHIELD
CHO-SEAL 1214 SILVER FILLED SILICONE	GSFPC4602	.26	.05	24H	177	AIR	GASKET
CHO-SEAL 1214 SILVER FILLED SILICONE	GSFPC4604	.04	.02	15M	171	AIR	GASKET
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	GSFPC3201	.06	.02	24H	177	AIR	GASKET
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	GSFPC3203	.46	.07	24H	177	AIR	GASKET
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	GSFPC3163	.29	.01	15M	171	AIR	SHIELD
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	GSFPC3165	.03	.00	15M	171	AIR	SHIELD
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	GSFPC3143	.34	.08	15M	171	AIR	SHIELD
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	GSFPC3145	.05	.02	15M	171	AIR	SHIELD
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	GSFPC3101	.30	.00	24H	177	AIR	SHIELD
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	GSFPC3103	.05	.00	15M	171	AIR	SHIELD
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	GSFPC2203	.36	.12	24H	177	AIR	SHIELD
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	GSFPC3105	.43	.06	15M	171	AIR	SHIELD
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	GSFPC3107	.04	.02	15M	171	AIR	SHIELD
CHO-SEAL 1236 REINFORCED SILICONE GASKET SEAL RED	GSCC11459	.7	.16	24H	177	AIR	GASKET
CHO-SEAL 1250 SILVER FILLED SILICONE	GSCC2140	.71	.12	24H	177	AIR	GASKET
CHO-SEAL 1285 ELEC COND SILICONE BLUE	GSCC12553	.41	.05	24H	177	AIR	GASKET SEAL
CHO-SHINK TUBING SILVER COND IN/OUT INNER SURF	GSCC4746	.98	.21	24H	177	AIR	SHRINK TUBING
CHO-SHINK TUBING SILVER COND IN/OUT INNER SURFACE	GSCC4700	.70	.10	24H	177	AIR	SHRINK TUBING
CHO-SHINK TUBING SILVER COND INNER SURFACE	GSCC4606	.61	.09	5M	121	AIR	SHRINK TUBING
CHO-SIL 1401 SILVER FILLED SILICONE	GSCC4968	.65	.21	0.5M	121	AIR	SHRINK TUBING
CHO-SIL 1401 SILVER FILLED SILICONE	GSCC3704	1-1.6	.22	24H	177	AIR	SHIELD
CHO-SIL 1405 SILVER FILLED SILICONE	GSCC3706	1-0.5	.22	24H	177	AIR	SHIELD
CHO-SIL 1405 SILVER FILLED SILICONE	GSCC32981	1-0.3	.27	24H	177	AIR	SHIELD
CHO-THERM 1642 A/B AS 100/3 BW FILLED BLUE SILICONE	GSCC3708	.06	.02	24H	177	AIR	IN TERM CONTROL
CHO-THERM 1661 THERM COND SHEET WHITE SILICONE	GSCC1761	.40	.18	7D	25	AIR	IN TERM CONTROL
CHO-THERM 1661 THERM COND SHEET WHITE SILICONE	GSCC1093	.7	.08	24H	175	AIR	IN TERM CONTROL
CHO-THERM 1663 THERM COND SHEET WHITE SILICONE	GSCC1240	.10	.06	24H	175	AIR	IN TERM CONTROL
CHO-THERM 1664 THERM COND SHEET - BLUE 7.5 MIL THICK	GSCC1096	1-5.3	.14	24H	175	AIR	IN TERM CONTROL
CHO-THERM 1664 THERM COND SHEET - BLUE 7.5 MIL THICK	GSCC1243	1-2.6	.05	24H	175	AIR	DI ELECTRIC

MATERIAL	DATA REFERENCE	STAB.	RCVCH	CURE TIME	CURE TEMP	AIR HRS	APPLICATION
CHO-THERM 1671 TEEBM COND SHEET - WHITE SILICONE	GSPC9656 GSC11099	.04	.01	24H	175	AIR	BLASTCER
CHO-THERM 1671 TEEBM COND SHEET - WHITE SILICONE	GSC11246	.76	.97	24H	175	AIR	BLASTCER
CHO-THERM 1671 TEEBM COND SHEET - GREEN SILICONE	GSC11247	.18	.03	24H	175	AIR	BLASTCER
CHO-THERM 1673 TEEBM COND SHEET - GREEN SILICONE	GSC11339	.45	.04	24H	175	AIR	BLASTCER
CHO-THERM 1674 TEEBM COND SHEET - BLUE SILICONE	GSC11372	.57	.01	24H	175	AIR	BLASTCER
CHO-THERM 1674 TEEBM COND SHEET - WHITE FLUOROSILICONE	GSC11405	.57	.04	24H	175	AIR	BLASTCER
CHOMERICS 4220 HOT MELT CONDUCTIVE ADHESIVE FILM	GSC11954	1.36	-	13	-	-	ADHESIVE FILM
CHOMERICS 4220 SILVER FILLED SILICONE GREASE FILM/SHEET	GSC13057	.37	.14	24	100	AIR	COND GREASE
CICOIL SILICONE CABLE INSULATED SILICONE FILM/2 SIDE ACR ADH/P	GSPC1345	10.59	4	3H	172	AIR	CABLE INSUL
CIRCLE K 706 TAPE PVC/POLYPROPYLENE FILM/2 SIDE ACR ADH/P	GSPC53932	10.58	4	3H	172	AIR	2 SIDED TAPE
CIRCUIT BOARD COMPOSITES NEMA 310 MICA/C/E 1155	GSPC53978	.48	.31	3H	172	AIR	CIRCUIT BOARD
CL-522 EPOXY LAMINATING FILM	GSC13401	.41	.31	3H	172	AIR	FILM ADHESIVE
CLAMP WIRE BUNDLE TA 11C62 WD10 FIBERGLASS/SILICONE	GSPC8574	.48	.36	21	177	AIR	CLAMP
CLAMP WIRE BUNDLE TA 11C62 WD10 FIBERGLASS/SILICONE	GSPC8576	.36	.21	21	177	AIR	CLAMP
CLAMP WIRE BUNDLE TA 11C62 WD10 FIBERGLASS/SILICONE	GSPC8618	.14	.09	24H	100	AIR	CLAMP
CLARK FOAM 1234 POLYURETHANE STYLITE 16781 TYPE S	GSPC88994	.65	.07	24H	100	AIR	FLOTH
CVC 10 ADHESIVE FILM THERMOSETTING	GSPC2943	1.02	.03	30M	165	AIR	ADH FILM
COAST EPOXY PREPREG 161-83-1PO8/20	GSPC3191	.66	.01	2H	163	AIR	ADH FILM
COAST EPOXY PREPREG 161-83-108-B	GSPC3189	.46	.01	2H	149	AIR	ADH FILM
COAST EPOXY/GLASS FIBREPREG F161-83-1PO8/20	GSPC3323	.29	.01	165M	204	AIR	LAMINATE
COATING 5459 CAT 601 AS 1/1 BV FLAT BLACK EPOXY	GSPC1204	7.51	.29	7D	25	AIR	PAINT COMPOSITE
COATING 5459 CAT 601 AS 1/1 BV REFLECTIVE COATING	GSPC1291	2.1	.19	24H	25	AIR	PAINT
COHRLASTIC R-216 RFI GASKET 8016 ALUM CLOTH/NEOPRENE	GSPC2717	4.64	.21	24H	25	AIR	RFI GASKET
COHRLASTIC R-216 RFI GASKET 8020 ALUM CLOTH/NEOPRENE	GSC13093	3.73	.24	24H	25	AIR	RFI GASKET
COHRLASTIC R-216 RFI GASKET 8516 ALUM CLOTH/SILICONE	GSC13096	.52	.14	24H	25	AIR	RFI GASKET
COHRLASTIC R-216 RFI GASKET 8520 ALUM CLOTH/SILICONE	GSC13102	.67	.24	6H	249	AIR	FLOAM RUBBER
COHRLASTIC RUBBER K10470 SILICONE SPONGE BROWN	GSPC4774	.10	.03	24H	204	AIR	DAMPER
COHRLASTIC R10450 GLASS REINFORCED DARK GRAY SILICONE	GSC13730	.12	.05	24H	182	AIR	DAMPER
COHRLASTIC R10460 LARKEE SILICON SPONGE SHEET	GSC13915	.49	.24	24H	182	AIR	DAMPER
COHRLASTIC R10480 ERON SILICONE SPONGE - MEDIUM	GSC13918	.45	.20	24H	182	AIR	DAMPER
COHRLASTIC R10480 RED SILICONE SPONGE - MEDIUM	GSC13958	.81	.33	24H	182	AIR	DAMPER
COHRLASTIC R10480 RED SILICONE SPONGE - SOFT	GSC13490	.94	.38	24H	182	AIR	DAMPER
COHRLASTIC 300 SILICONE RUBBER SHEET GEN PURPOSE	GSC13284	.16	.08	100H	100	E-O	GASKET
COHRLASTIC 320 SILICONE RUBBER SHEET GEN PURPOSE	GSC132985	1.21	.58	24H	182	AIR	GASKET
COHRLASTIC 400 SILICONE RUBBER SHEET GEN PURPOSE	GSC12988	1.63	.77	24H	182	AIR	GASKET
COHRLASTIC 500 SILICONE RUBBER SHEET GEN PURPOSE	GSC13060	1.37	.73	24H	182	AIR	SPACER
COHRLASTIC 600 SILICONE RUBBER SHEET GEN PURPOSE	GSC13005	1.26	.59	24H	182	AIR	SPACER
COHRLASTIC 700 SILICONE RUBBER SHEET GEN PURPOSE	GSC13021	1.81	.34	24H	182	AIR	SPACER
COHRLASTIC 700 SILICONE RUBBER SHEET GEN PURPOSE	GSC13063	1.45	.33	24H	182	AIR	SPACER
COHRLASTIC 700 SILICONE RUBBER SHEET HIGH PERFORMANCE	GSC12991	.93	.33	24H	182	AIR	SPACER
COHRLASTIC 700 SILICONE RUBBER SHEET HIGH PERFORMANCE	GSC13066	1.77	.43	24H	182	AIR	SPACER
COHRLASTIC 925 SILICONE RUBBER SHEET HIGH PERFORMANCE	GSC13024	.67	.23	24H	182	AIR	SPACER
COHRLASTIC 985 SILICONE RUBBER SHEET HIGH PERFORMANCE	GSC13033	.25	.18	24H	182	AIR	SPACER
COIL FORM - CLEAR BASE - WHITE	GSPC5817	.63	.05	24H	182	AIR	COIL FORM

MATERIAL	REFERENCE	XTRAL	XCVCA	CURE TIME	CURE TEMP	ATMOS	APPLICATION
COIL FORM PHENOLIC COLAD 984 A/B AS 3/1 BY WHITE QUICK SET EPOXY COLAD 984 A/B AS 3/1 BY WHITE QUICK SET EPOXY CONAFLEX EA-50 PVC/URETHANE FOAM ALCOHOL WASH CONAFLEX EA-50 PVC/URETHANE FOAM W/O ADH BACKING CONAP K-20 A/R AS 20/9 BY GRAY EPOXY	GSPC5791 GSPC8519 GSPC8522 GSPC5996 GSPC5951 GSPC5344 GSPC5349	4-76 1-19 -84 -65 -86 1-93 -75	-88 -02 -01 -03 3-17 -05 -05	16H 8H 3H 12H 3H 2H 2H	100 100 85 50 85 30M 6.5	AIR AIR AIR AIR AIR AIR AIR	COIL FORM PUTTING POTTING INSULATION INSULATION ADHESIVE ADHESIVE CONF COAT
CONAP K-26 WHITE EPOXY EQUAL LENGTHS FROM TUBES CO NATHANE CE 1153 A/B AS 10/7 BW CO NATHANE CE 1155 A/B/CELLOSOLVE ACETATE AS 10/7/3 CO NATHANE CE 1155/CELLOSOLVE ACETATE MULTICURE	GSPC12916 GSPC1448 GSPC3889 GSPC3891 GSPC2681	1-10 11-73 1-60 1-30 .81	-12 -12 -04 -08 -.05	30M 3H 30M 3H 10d	25 6.6 25 6.6 25	AIR AIR AIR AIR AIR	CONF COAT CONF COAT CONF COAT
CO NATHANE CE 1164 MIL 1 4605BC TYPE UR 2 COATS/FOIL CO NATHANE CE 1164 MIL 1 4605BC TYPE UR 2 COATS/FOIL	GSPC7133 GSPC7132	7-26 7-95	-00 -07	24H 3H	69 69	AIR AIR	CONF COAT CONF COAT
CO NATHANE CE 1170 - FLUORESCENT CO NATHANE CE 1171 - FLUORESCENT CO NATHANE DP 761 A/B AS 100/46.5 BW POLYURETHANE BLEND CO NATHANE EN 211/DPS761/DP9802 POLYURETHANE BLEND CO NATHANE EN-11 A/E AS 100/55 BW POLYURETHANE CO NATHANE EN-11 A/F AS 100/55 BW POLYURETHANE	GSC12679 GSC12682 GSC11036 GSC11120 GSC11539 GSC11303	9-60 9-30 -93 -92 -33 -27	-09 -01 -02 -01 -02 -01	14D 14D 14D 14D 30D 24H	25 25 6.6 6.6 6.6 10H	AIR AIR AIR AIR AIR AIR	INEREN ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE PUTTING
CO NATHANE EN-11 A/E AS 100/55 BW POLYURETHANE CO NATHANE EN-11 A/E AS 100/55 BW POLYURETHANE CO NATHANE EN-12 A/E AS 100/55 BW POLYURETHANE CO NATHANE EN-12 A/F AS 71-375 BW BUTADIENE URETHANE	GSPC7971 GSPC7993 GSPC7994 GSPC7947	-38 -43 -43 -44	-02 -01 -01 -02	24H 24H 24H 12H	55 50 50 38	AIR AIR AIR AIR	PUTTING PUTTING PUTTING PUTTING
CO NATHANE EN-2 1 A/E AS 100/116 BW POLYURETHANE BLEND CO NATHANE EN-2 1 A/E AS 100/116 BW POLYURETHANE BLEND CO NATHANE EN-24 A/E AS 100/82 BW POLYURETHANE CO NATHANE EN-24 A/E AS 100/82 BW POLYURETHANE CO NATHANE EN-4 A/B AS 100/17.5 BW CARBON BLACK CO NATHANE EN-5 A/B AS 100/17.5 BW POLYURETHANE CO NATHANE EN-7 A/B AS 100/17.5 BW POLYURETHANE	GSC12055 GSC11407 GSC10838 GSC10841 GSPC5322 GSPC3247 GSPC844	-50 -50 -52 -52 -15 -78 -32	-03 -03 -04 -04 -49 -02 -01	14D 14D 7D 7D 24H 7D 20H	55 45 25 25 60 25 60	AIR AIR AIR AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE PUTTING PUTTING
CO NATHANE EN-9 PVC/URETHANE CONAUCARE AH18 AS 5/2 BN02 CONAUCARE 1B-1145 CONCURE COMPONENT LOT BN02 CONDULON ANTISTATIC FILM 2 MIL BLACK CONDULON ANTISTATIC FILM 4 MIL BLACK #9436 CONDULON 89-74 ANTISTATIC FILM BLACK #9437 CONNECTOR INSERT BLUE SILICONE CONNECTOR INSERT PTDGE-24-612 BROWN SILICONE CONNECTOR INSERT TAN RUBBER PER MIL C38999 CONNECTOR INSERT TAN RUBBER PER MIL C38999 CONNECTOR MILL C36959 RED INSERT CONNECTOR PLUG JF151PB GRAILEY 20% GLASS FILLED CONNECTOR TUBING FCLIPROPILENE	GSPC8729 GSPC1729 GSPC11962 GSC11938 GSC11941 GSC11944 GSC11947 GSPC5793 GSPC1087 GSPC1535 GSC11627 GSC12409 GSPC0445 GSPC0961 GSPC6083	-39 -109 -1-84 -88 -76 -03 -02 -02 -02 -02 -02 -02 -02 -02 -02 -02 -02	00 109 16H 03 02 02 02 02 02 02 02 02 02 02 02 02 02	20M 14.9 16H 16H 16H 16H 16H 16H 16H 16H 16H 16H 16H 16H 16H 16H	25 155 AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA	AIR AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA AIA	CONF COAT CONF COAT

MATERIAL	DATA REFERENCE	STAB	XCYC	CURE TIME	CORE TIME	ADHS	APPLICATION
CONNECTOR 18.1/261-61 BLACK NYLON/GLASS	GSPC5683	1.25	.01				
CONNECTOR 3612-A/B COUPLE B/UP COPPER/CON	GSPC12450	1.25	.05				
CONNECTOR-TUBE A/B COUPLE 30/22-75 BW CLEAR URETHANE	GSPC5913	1.44	.01	16H	6H	A-J	CONNECTOR CUTTING SHIELD
CONNECTOR-EN-30 A/B COUPLE 30/22-75 BW CLEAR URETHANE	GSPC12919	1.74	.01	24H	115	E-J	CONNECTOR CUTTING SHIELD
CONNECTOR-TUBE A/B COUPLE 30/22-75 BW CLEAR URETHANE	GSPC1712	.96	.01	12H			SHIELD
CONSIL 6 SILVER FILLED SILICONE	GSPC3866	.96	.01	12H			SHIELD
CONSIL MEDIUM HARD SILVER FILLED SILICONE	GSPC3868	.35	.01	24H	177	A-J	SHIELD
CONSIL MEDIUM HARD SILVER FILLED SILICONE	GSPC3710	.20	.01	12H	115	E-J	SHIELD
CONSIL 8 SILVER FILLED SILICONE SHEET	GSPC3556	.44	.02	12H			COMPOSITE
CONSIL SILVER FILLED SILICONE SHEET	GSPC2963	.63	.03				COMPOSITE
CONVAIR GRAPHITE/EPOXY/SI203/ALUMINUM	GSPC2994	.54	.01	24H	25	A-J	PUTTING FOAM
CORFIL 615/DIA AS 100/7 BW EPOXY	GSPC1375	2.83	.10	3H	66	A-J	PUTTING FOAM
CORFIL 615/DIA AS 100/7 BW EPOXY	GSPC8168	2.03	.13				DAMPER
CORK/DC100 SHEET	GSPC2670	5.05	.08	1.58	25	A-J	ADHESIVE
COTRONICS THERMELZ CERAMIC PUTTY	GSPC1461	3.07	.02	14D	25	A-J	ADHESIVE
COTRONICS THERMELZ CERAMIC PUTTY	GSPC1507	3.06	.01	24H	25	A-J	ADHESIVE
COTRONICS 360-M MOLDABLE CERAMIC	GSPC1463	3.41	.02	14D	100	A-J	ADHESIVE
COTRONICS 360-M MOLDABLE CERAMIC	GSPC1509	2.67	.01	24H	25	A-J	ADHESIVE
COTRONICS 918 CERAMIC ADHESIVE	GSPC1467	2.74	.02	14D	25	A-J	ADHESIVE
COTRONICS 918 CERAMIC ADHESIVE	GSPC1511	1.20	.01	24H	100	A-J	ADHESIVE
COTRONICS 919/H2O AS 7.7/1 BW HIGH RES CERAMIC	GSPC1469	5.34	.02	14D	25	A-J	ADHESIVE
COTRONICS 919/H2O AS 7.7/1 BW HIGH RES CERAMIC	GSPC1513	4.20	.01	24H	25	A-J	ADHESIVE
COTRONICS 940/ACT AS 4/1 BW FAST SET CERAMIC	GSPC1465	1.57	.03	2H	100	A-J	ADHESIVE
COTRONICS 940/ACT AS 4/1 BW FAST SET CERAMIC	GSPC1515	.79	.01	24H	25	A-J	ADHESIVE
COTRONICS 944/H2O AS 5.5/1 BW HIGH STR CERAMIC	GSPC1471	5.30	.03	14D	100	A-J	ADHESIVE
COTRONICS 944/H2O AS 5.5/1 BW HIGH STR CERAMIC	GSPC1517	3.09	.01	24H	25	A-J	ADHESIVE
COVERLITE H FABRIC 55-61811-XX HYPALON COATED NYLON	GSPC8252	7.84	.78	2H	100	A-J	CLOTH
COVERLITE H FABRIC 55-61811-XX HYPALON COATED NYLON	GSPC8372	1.11	.05	24H	125	A-J	CLOTH
COVERLITE H FABRIC 55-61811-XX HYPALON COATED NYLON	GSPC8399	.98	.02	24H	125	A-J	CLOTH
CDX 28 EPOXY A/B AS 7/1 BW	GSPC1900	3.13	.90	20H	74	A-J	ADHESIVE
CP 1006 NATURAL RUBBER	GSPC4808	10.09	3.14	20H	100	A-J	DAMPER
CP 6002 SILICONE RUBBER	GSPC4810	4.35	1.16	15H	146	A-J	DAMPER
CP 6002 SILICONE RUBBER	GSPC4868	1.01	.36	4H	177	A-J	DAMPER
CP 6007 SILICONE RUBBER	GSPC4812	3.08	.58	24H	166	A-J	DAMPER
CP 6007 SILICONE RUBBER	GSPC4870	1.15	.35	4H	143	A-J	DAMPER
CP 6007 SILICONE RUBBER	GSPC4870	1.15	.35	4H	177	A-J	DAMPER
CPR 17-2C POLYURETHANE FOAM	GSPC3951	.87	.10	1H	120	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM	GSPC3954	.24	.01	12H	80	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM	GSPC4053	1.31	.03	16H	60	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM	GSPC4057	.27	.03	16H	75	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM	GSPC4096	1.26	.04	6H	85	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM	GSPC4120	1.13	.06	24H	65	A-J	FOAM
CPR 17-2C POLYURETHANE FOAM LOT #2280	GSPC4122	1.04	.00	18H	93	A-J	CUTTING
CPR 23-2A/2B AS 23.4/9.9 BW	GSPC2625	1.04	.00	18H	93	A-J	CUTTING
CPR 9002-3 POLYURETHANE FOAM BLUE/GREEN	GSPC3461	3.81	.21				FOAM

MATERIAL		DATA REFERENCE	XTHL	%CVCN	CURE TIME	CURE TEMP	ADHS	APPLICATION
C2R 9005-2 POLYURETHANE FOAM GREEN		GSPC4386	4-34	1-06	96H	125	AIR	FOAM
C2A 9005-2 POLYURETHANE FOAM GREEN		GSPC4434	2-26	.03	72H	100	AIR	FOAM
CPR 9800-60 POLYESTER URETHANE FOAM 0#CU FT	24H METOH WASH	GSPC5037	7-24	.40				FOAM DAMPER
CPR 9800-60 POLYESTER URETHANE FOAM 6#CU FT		GSPC5577	1-23	.46	24H	66	B-4	FOAM DAMPER
CRA/MCLIN PLASTIK SPRAY DRY 10M/COAT/ROOM TEMP	10M/COAT/ROOM TEMP	GSPC5579	1-63	.09				COAT COAT
CRA/MCLIN PLASTIK SPRAY DRY 10M/COAT/ROOM TEMP		GSPC5230	11-93	.11	24H	25	AIR	COAT COAT
CREST 3135/T111 AS 1/1 BW EPOXY		GSPC5184	2-47	.01	24H	60	AIR	ADHESIVE ADH
CREST 3170 A/B AS 1/1 BW MODIFIED WHITE EPOXY		GSPC8594	2-41	.95	SD	225	AIR	LOW TEMP ADH
CREST 3170 A/B AS 50/50 BW EPOXY		GSPC9089	1-38	.04	SD	244	AIR	ADHESIVE
C3 CREST 3170/T133 AS 1/1 BW EPOXY		GSPC4948	2-19	.04	210	25	AIR	ADHESIVE
C3 CREST 3170/T133 AS 1/1 BW WHITE EPOXY		GSPC8348	3-25	.09	16H	25	AIR	ADHESIVE
CREST 3725/T148 AS 1/1 BW EPOXY		GSPC4950	2-47	.39	21D	25	AIR	ADHESIVE
CREST 3725/T148 AS 1/1 BW EPOXY - URETHANE		GSPC4780	2-47	.41	3H	66	AIR	ADHESIVE
CREST 391 A/B AS 100/60 BW BLACK POLYURETHANE		GSPC8588	26-52	.58	SD	225	AIR	LOW TEMP ADH
CREST 419 A/B AS 100/60 BW BLACK POLYURETHANE		GSPC8591	-35	.04	2H	100	AIR	LOW TEMP ADH POTTING
CREST 7344 A/B AS 100/14 BW POLYURETHANE ADH		GSPC3610	1-10	.17	3D	204	AIR	ADHESIVE
CREST 7344 A/B AS 100/16 BW BROWN EPOXY/POLYURETHANE		GSPC8621	2-28	.68	72H	225	AIR	LOW TEMP ADH
CREST 7344 A/B AS 100/16 BW BROWN EPOXY/POLYURETHANE		GSPC9092	1-51	.07	SD	225	AIR	ADHESIVE
CREST 7344/T119 AS 50/7 BW EPOXY		GSPC4952	2-78	.63	21D	225	AIR	ADHESIVE
CREST 7380 A/B AS 100/16 BW MODIFIED BROWN EPOXY		GSPC8597	2-62	.23	SD	225	AIR	LOW TEMP ADH
CREST 7410 A/B AS 100/26 BW YELLOW POLYURETHANE		GSPC8600	7-92	.89	SD	225	AIR	LOW TEMP ADH
CREST 7410 A/B AS 100/26 BW YELLOW POLYURETHANE		GSPC9095	6-76	.01	3D	225	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW		GSPC5981	1-45	.19	4D	125	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW		GSPC8819	1-85	.17	7D	225	AIR	ADHESIVE
CREST 7425 A/B AS 100/24 BW		GSPC9059	1-12	.11	16H	25	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW		GSPC5984	1-34	.14	24H	125	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW		GSPC8822	1-78	.30	7D	225	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW		GSPC9098	1-12	.19	3D	80	AIR	ADHESIVE
CREST 7450 A/B AS 100/16 BW BROWN EPOXY/POLYURETHANE		GSPC8624	1-21	.39	SD	125	AIR	LOW TEMP ADH
CROFON LIGHT CONIC CLEAR NO JACKET		GSPC3890	1-37	.08				FIBER OPTIC
CROFON 1 COND/JACKET YELLOW CODE		GSPC3823	2-33	.05				FIBER OPTIC
CROFON 1 COND/JACKET YELLOW CODE		GSPC3821	2-36	.08				FIBER OPTIC
CROFON 3 COND/JACKET GREEN CODE		GSPC3804	2-26	.04				FIBER OPTIC
CROFON 4 COND/JACKET PURPLE CODE		GSPC3802	2-27	.02				FIBER OPTIC
CROFON 5 COND/JACKET BLUE CODE		GSPC3825	2-33	.02				FIBER OPTIC
CROWN APPLIX FILM - FROSTY TRANSPARENCY		GSPC4264	2-75	.00				TRANSPARENCY
CROWN APPLIX FILM - FROSTY TRANSPARENCY		GSPC4246	2-52	.01				TRANSPARENCY
CROWN 6065 GREEN TFE AEROSOL COATING/E		GSC12994	-54	.09	24H	177	AIR	LUBRICANT
CSB-446 STAB NYLON BONDED FINISH		GSPC2759	4-61	.14	90H	121	E-3	TO READ
CT 404-2-1 a/b AS 1/1 BW SILVER FILLED EPOXY		GSC12196	2-35	.01	15H	80	AIR	COND ADHESIVE
					5K	150	AIR	

MATERIAL	DATA REFERENCE	WT. %	%VCM	CURE TIME	CURE TEMP	AIR HOS	APPLICATION
CF 4091 A/B AS 17/1 B SILVER FILLED EPOXY CF 5030/B-97 AS 100/1.5 BW AG FILLED EPOXY/F CF 5047-2 A/B AS 100/6 BW SILVER FILLED EPOXY	GSC12198 GSC13564 GSC12172	1.55 1.55 1.39	.14 .14 .00	30M 2H 2H	93 80 65	AIR AIR AIR	COND ADHESIVE COND ADHESIVE COND ADHESIVE
CTL-15 A/B AS 3/1 F BLACK EPOXY PAINT CTL-15 BLACK EPOXY PAINT BATCH 1541 HUGHES ACFT	GSCFC6790 GSCFC2649	3.93 5.36	.03 .00	1H 15M	66 66	AIR AIR	PAINT PAINT
CTL-15 GLOSSY BLACK PAINT	GSC10940	2.16	.06	30M	96	AIR	PAINT
CTL-15 GLOSSY BLACK PAINT ONE COAT CTL-15 GLOSSY BLACK PAINT THREE COATS	GSC11285 GSC11288	1.80 1.81	.04 .06	24H 1H	125 103	AIR AIR	PAINT PAINT
CTL-15 WHITE EPOXY PAINT BATCH 1094 HUGHES ACFT	GSCFC2651	3.85	.00	15M	25	AIR	PAINT
CTL-15 WHITE EPOXY PAINT HUGHES ACFT CUSTOM LOAD 4101-190 EPOXY CUTTERIN 306 BLACK POLYURETHANE COATING CYANOPRENE 1857 BLUE THERMOPLASTIC POLYURETHANE CYANOPRENE 1880 CLEAR THERMOPLASTIC POLYURETHANE CYACND 4019 A/B AS 3/1 BW	GSPFC9104 GSPFC5352 GSPFC4782 GSPC6194 GSPC6197 GSPC4576 GSPC3558	2.60 -1.1 -6.9 -1.16 -1.38 -1.48 -3.31	.10 -31 -02 -18 -34 -72 -43	12H 1H 1D 1H 24H 1H 30M	125 103 25	AIR AIR AIR	PAINT PAINT PAINT
CYCCM HGS FIBER - NICKEL COATED GRAPHITE CYCOK 950-S2 EPOXY/GLASS	GSC12871 GSC12222	-02 -49	.01 .01	1.5U	66	E-2	FIBERS
CYCCM 985-T300 GRAPHITE/EPOXY	GSC12224	-57	.01	1H	121	E-2	STRUCTURAL
CY209/HF972 CLEAR AMBER EPOXY	GSPFC8327	-78	.01	40H	25	AIR	ADHESIVE
C15-015 EPOXY C2-4259/A/B AS 100/120 BW	GSPCO884 GSPCO539 GSPC3515 GSPC1981	5.69 1.94 1.95 -05	.01 -31 -31 -02	5H	13.5	AIR	ADHESIVE
C3-1102 SILICONE GREASE C3-1103 SILICONE GREASE	GSPC4488 GSPC4790 GSPC12406	-16 -16 -16	-03 -03 -03	4H 3H 25H	77 125 125	AIR AIR AIR	POTTING POTTING POTTING
C3-4183/H2-3561 AS 100/15 BW EPOXY C3-4190/H8-3503 AS 10/13 BV RED FLEXIBLE EPOXY	GSPC4980 GSC11672 GSPC4958 GSPC1732 GSPC5010 GSPC2296	-38 -68 -49 -69 -1.32 -1.15	.09 -09 -09 -09 -02 -02	8H 8H 8H 8H 14D 14D	60 60 25 25 25 25	AIR AIR AIR AIR AIR AIR	POTTING POTTING POTTING POTTING PAINT BASE PAINT BASE
C3-4198/H2-3561 AS 100/15 BW EPOXY C3-4215/H2-3561 AS 20/3 BW BLACK EPOXY C3-4215/H2-3561 AS 20/3 BW BLACK EPOXY C3-5340/H2-3561 AS 100/8.3 BW EPOXY D-241-F3 SILICONE POLYAMIDE-IPDI/ADH/COPPER D-8150 POLYAMIDE-IPDI/ADH/COPPER D-8970 EPOXY FILM ADH/COPPER DACHON TAPE ST 275 J/4 DACHON CLOTH 302 CARROLLON	GSPC4980 GSC11672 GSPC4958 GSPC1732 GSPC5010 GSPC2296 GSPC8696 GSPC2499	-38 -68 -49 -69 -1.32 -1.15 -42 -73	.09 -09 -09 -09 -02 -02 -03 -03	8H 8H 8H 8H 14D 14D 2.73 2.73	105 60 25 25 25 25 25 25	AIR AIR AIR AIR AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
DACRON DAYBOND Y-4-BX DACRON MESH B2A EGYLYESTER NETTING DACRON MESH B2A EGYLYESTER NETTING DACRON NETTING 708E-10	GSPC2521 GSPC5591 GSC10652 GSPC2501	-19 -19 -19 -19	.04 .03 .03 .03	45 45 45 45	2.04 2.04 2.04 2.04	AIR AIR AIR AIR	THREAD DESH THERM BLANKET SETTING

MATERIAL	DATA REFERENCE	#TML	%CVM	CURE TIME	CURE ATMOS	APPLICATION
DACRON POLYESTER CLOTH FISH STYLE 15320	GSCFC5192	1.3	.04			
DACRON POLYESTER BLACK FAINT 1/1 BV BLACK/z	GSCFC2983	.79	.01			
DAN POX ENAMEL 160°F AS 1/1 BV BLACK/z	GSCFC4299	2.54	.26	7D	AIR	CLOTH FABRIC MESH
DAN PLASTICS CONNECTOR A104202	GSCFC0447	.34	.03			PAINT PAINT
DAP CONNECTOR 3-2-520 GLASS FILLED/FLAME RESISTANT	GSCFC0179	.61	.01			PAINT CEND
DAP C2580-11B FR FEC - DAPON A	GSCFC0970	.97	.04			CONNECTOR CONNECTOR
DAP INSECT/CANNON CONNECTOR DDM 24W72	GSCFC1456	.30	.09			WLD CPND
DAP SDG-P MIL H-14 AMP CONNECTOR DDM 24W72	GSCFC3870	.44	.00			CONNECTOR CONNECTOR
DAP SHORT GLASS FIBER FILLED BLACK	GSCFC2079	.44	.00			WLD CPND
DAP/FLAME RETARDANT-GLASS FILLED CANNON CON PS-80	GSCFC0869	.44	.00			CONNECTOR CONNECTOR
DAP/FLAME SEALANT/IEPREGANI	GSCFC4748	13.98	.05	1H	149	IEPREGNANT
DC 0-96-005 ONE PART SILICONE	GSCFC6653	1.43	.56	6H	121	
DC QCP-3-6500 ONE PART SILICONE	GSCFC6691	1.84	.58	7D	25	AIR
DC QCP-3-6500 ONE PART SILICONE STRIPPED IN VAC	GSCFC6792	1.96	.34	7D	25	AIR
DC 1107 SILICONE FLUID UNCATALYZED	GSC10547	13.6	.02	1H	150	AIR
DC 1107/1-12 AS 10GB/5 DROPS SILICONE FLUID	GSC10550	6.13	.95	18H	25	AIR
DC 142 OVER A-4094 PRIMER	GSCFC2455	1.67	.04	14D	25	AIR
DC 20-057 SILICONE OPTICAL COUPLING COMPOUND	GSCFC7430	.86	.27			ADHESIVE
DC 2106 SILICONE RESIN	GSCFC1917	.06	.02			SILICONE
DC 221 SILICONE	GSCFC3965	4.7	.82			
DC 3-6550 RTV DISPERSION ONE PART CLEAR	GSCFC3988	3.69	.89	4H	25	AIR
DC 3071 MOLDING CENSE - FUSISTOR RS-1A-XX(B7741) BW	GSCFC1935	1.52	.34	7D	25	AIR
DC 3101 LOW DENSITY SYNTACTIC FOAM A/B AS 10/1	GSCFC4608	1.12	.02	24H	177	AIR
DC 3110/X AS 10% CAT H	GSCFC4629	1.23	.30	3H	79	AIR
DC 3110/H AS 10% CAT P	GSCFC4954	1.35	.34	3D	25	AIR
DC 3110/S AS 10% CAT S	GSCFC3131	1.13	.34	4H	65	AIR
DC 3110/S AS 10% CAT S/12 AS 10/1 BW/.163 T-12	GSCFC3896	1.43	.47	30D	25	AIR
DC 3116/S AS 15% CAT S/12 AS 10/1 BW/.163 T-12	GSCFC8351	1.43	.41	1H	65	AIR
DC 3118 DIMETHYL SILLOXANE	GSCFC1282	1.92	.32	7H	50	AIR
DC 3140	GSCFC1156	1.34	.61	24H	25	AIR
DC 3140	GSCFC2263	1.54	.63	7D	25	AIR
DC 3140	GSCFC5308	.16	.06	24H	150	AIR
DC 3144 SILICONE	GSCFC7646	1.75	.66	3D	25	AIR
DC 3145	GSCFC0191	1.74	.90	3D	25	AIR
DC 3145	GSCFC1153	1.70	.60	24H	25	AIR
DC 3145 ONE COMPONENT GRAY SILICONE	GSC10047	.54	.27	7D	25	AIR
DC 3225 A/B AS 100/8 BN ABLATIVE SILICONE	GSCFC0290	1.46	.36	3H	150	AIR
DC 340 HEAT SINK GEASE	GSCFC0419	.35	.11			ABLATIVE
DC 340 SILICONE/ALUM PIGMENT AS 25/1 BW	GSCFC1297	2.11	.12			HEAT SINK
DC 5110 SILICONE FLUID 30,000 CPS DEVOLATILIZED	GSCFC8909	.98	.43	24H	80	WAD
DC 5110 SILICONE FLUID 30,000 CPS DEVOLATILIZED	GSCFC9200	.16	.13	24H	125	WAD
DC 5370 SILICONE FCAM	GSCFC2575	.31	.12	16H	204	WAD
DC 5370 SILICONE FCAM	GSCFC3990	.59	.39	72H	150	WAD
DC 6-1104	GSCFC2017	.19	.01	7D	25	WAD
DC 6-1104 LOT E2134-142	GSCFC6650	.20	.03	5D	25	WAD

MATERIAL	REFERENCE	DATA	ADL	ACVCH	CURE TIME	CURE TEMP	ADJS	APPLICATION
DC 6-1104 LOT FM010380	GSC10820	.16	.05	7D	25	AIR	ADHESIVE	
DC 6-1104 LOT FM010381	GSC10529	.20	.03	7D	25	AIR	SEALANT	
DC 6-1104 LOT FM109321	GSC10769	.21	.03	14D	25	AIR	ADHESIVE	
DC 6-1104 LOT FM109329	GSC10697	.13	.03	7D	25	AIR	ADHESIVE	
DC 6-1104 LOT FM1293370	GSC10823	.16	.03	7D	25	AIR	ADHESIVE	
DC 6-1104 LOT GAC83347	GSC13365	.15	.03	7D	25	AIR	SEALANT	
DC 6-1104 LOT GAC83348	GSC13398	.14	.03	7D	25	AIR	SEALANT	
DC 6-1104 SAMPLE A LOT FM108-046	GSC10143	.73	.39	40D	25	AIR	SEALANT	
DC 6-1104 SAMPLE B LOT FM118-061	GSC10105	.42	.43	40D	25	AIR	SEALANT	
DC 6-1104 SAMPLE C LOT FM118-088	GSC10113	.43	.44	40D	25	AIR	SEALANT	
DC 6-1104 SAMPLE D LOT FM118-102	GSC10101	.49	.47	27	25	AIR	SEALANT	
DC 6-1104 SAMPLE 1C LOT FM128-103	GSC10091	.47	.46	28D	25	AIR	SEALANT	
DC 6-1104 SAMPLE 12 LOT FM128-104	GSC10089	.46	.27	26D	25	AIR	SEALANT	
DC 6-1104 SAMPLE 2 LOT FM128-103	GSC10099	.47	.27	26D	25	AIR	SEALANT	
DC 6-1104 SAMPLE 3 LOT FM128-104	GSC10097	.47	.27	26D	25	AIR	SEALANT	
DC 6-1104 SAMPLE 4 LOT FM128-102	GSC10095	.48	.24	26D	25	AIR	SEALANT	
DC 6-1104 SAMPLE 8 LOT FM128-102	GSC10093	.44	.26	28D	25	AIR	SEALANT	
DC 6-1104 UNFILLED V-1232 BLUE FERRO DYE	GSPCB012	.30	.07	7D	25	AIR	COAT	
DC 6-1104 W/V-1232 BLUE FERRO DYE	GSPCB012	.33	.03	24H	25	AIR	COAT	
DC 6-1104 W/V-1536 YELLOW FERRO DYE	GSPCB012	.29	.01	24H	25	AIR	COAT	
DC 6-1104 W/V-1536 YELLOW FERRO DYE	GSPCB012	.29	.01	24H	25	AIR	COAT	
DC 6-1104 W/V-1747 BLACK FERRO DYE	GSPCB012	.42	.03	24H	25	AIR	COAT	
DC 6-1104/V-NBK/XYLENE	GSPC4650	.28	.04	7D	25	AIR	COAT	
DC 6-1104/V-L015 FM119336 SILICONE	GSC10700	.13	.02	45D	25	AIR	SEALANT	
DC 6-1106 A/B AS 10/1 UNFILLED SILICONE	GSPC3732	.09	.01	7D	25	AIR	SEALANT	
DC 6-1109 - UNFILLED SILICONE	GSPC4676	.19	.01	7D	25	AIR	COAT	
DC 63-488 A/B AS 10/1 OPTICAL SILICONE RESIN	GSPC1624	1.4	.74	4H	60	AIR	SILICONE RESIN	
DC 63-488 A/B AS 10/1 SILICONE	GSPC1780	.99	.43	16H	25	AIR	ADH-SEALANT	
DC 63-489 A/B AS 10/1 BW OPTICAL SILICONE RESIN	GSPC1642	1.42	.57	24H	60	AIR	SILICONE RESIN	
DC 63-489 A/B AS 10/1 BW SILICONE	GSPC1789	.89	.44	4H	60	AIR	ADHESIVE	
DC 63-489 SILICONE	GSPC3762	.23	.15	4H	60	AIR	AIR	
DC 63-489 SILICONE IN XYLYENE/TOLUENE/F	GSPC3843	.36	.17	69H	130	E-3	ADHESIVE	
DC 806A SILICONE IN XYLYENE/TOLUENE/F	GSC10197	.90	.11	69H	85	AIR	COATING	
DC 90-006 A/B AS 10/1 BW HT SILICONE SEALANT	GSPC10212	2.14	.14	7D	25	AIR	COATING	
DC 90-031 A/B AS 10/1 BW ABLEATIVE SILICONE SEALANT	GSPC1063	1.23	.32	24H	70	E-3	SEALANT	
DC 90-031 SILICONE SEALANT	GSPC1050	1.09	.27	24H	70	AIR	SEALANT	
DC 90-092 SILICONE SEALANT	GSPC1072	.98	.18	24H	70	E-3	SEALANT	
DC 92-007 WHITE SILICONE INK/F	GSPC0194	2.03	.15	4H	150	AIR	ADH-SEALANT	
DC 92-007 WHITE SILICONE PAINT	GSPC2044	.91	.36	7D	25	AIR	PAINT	
DC 92-007 WHITE SILICONE PAINT	GSPC4678	.63	.20	24H	60	AIR	PAINT	
DC 92-018 SILICONE SEALANT	GSPC2741	2.30	.82	5D	25	AIR	SEALANT	
DC 92-019 SILICONE PRIMER DC 1200	GSPC2945	4.12	.07	84	25	AIR	PRIMER	
DC 92-024 SILICONE OVER PRIMER DC 1200	GSPC1177	2.07	.84	5D	25	AIR	SILICONE COAT	
DC 93-006 A/B AS 10/1 BW DARK GRAY SILICONE	GSPC8258	1.95	.28	72H	25	AIR	SEALANT	
DC 93-072 A/B AS 10/1 BW SILICONE SEALANT	GSPC6347	1.67	.60	24H	25	AIR	SEALANT	

MATERIAL	DATA REFERENCE	#TML	%CVCN	CURE TIME	TENSILE STRENGTH	ADHESIVE APPLICATION
DC 93-076-2 A/B AS 10/1 BW AEROSPACE SILICONE	GSPC4922 GSC10158	2-12 -20	.46 .02	7D 24H	25 25	AIR AIR SEALANT-POTTING PUTTING-ENCAPS
DC 93-500 A/B AS 1C/1 BW SILICONE	GSPC0371 GSPC0400	-16 -29	.00 .09	7D 7D	25 25	AIR AIR PUTTING-ENCAPS
DC 93-500 A/B AS 10//1 BW SILICONE	GSPC5421	-12	.02	7D	25	AIR PUTTING-ENCAPS
DC 93-500 A/B AS 1C//1 BW SILICONE	GSPC8636	-09	.03	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSC1J844	-10	.02	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 10//1 BW SILICONE	GSPC8639	-19	.04	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSC10670	-13	.04	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 10//1 BW SILICONE	GSPC49611	-02	.02	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSPC119334K2	-10	.02	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSPC19793	-09	.02	7D	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSPC7136	-04	.00	48H	25	AIR ADHESIVE
DC 93-500 A/B AS 1C//1 BW SILICONE	GSPC7181	-04	.00	24H	40	AIR ADHESIVE
DC 93-500 FM 029155 FEB 79	GSC10398	-17	.02	5D	74	E-5 PUTTING
DC 93-500 FM 059240	GSC10979	-38	.02	5D	74	E-5 PUTTING
DC 93-500 FM 059240 MAY 79	GSC10401	-39	.02	5D	74	E-5 PUTTING
DC 93-500 FM 068545 JUN 78	GSC10404	-28	.12	18	118	AIR PUTTING
DC 93-500 FM 128101 DEC 78	GSC10407	-24	.10	18	118	AIR PUTTING
DC 93-500 UNCURED MONOMER LOT E2467-133	GSPC7952	-06	.02	48H	25	AIR ADHESIVE FLUID
DC 93076-1/2 GRAY SILICONE	GSPC8207	-15	.08	16H	25	AIR ADHESIVE
DC 93076-1/2 GRAY SILICONE	GSPC8210	3-30	.96	4H	93	AIR ADHESIVE
DC 94-003 DISPERSION COATING PEROXIDE CAT DI CUP 40C	GSPC1288 GSPC5615	5-37 -76	.18 .26	4H 24H	149	AIR COATING
DC 955 SILICONE ELASTOMER PEROXIDE CAT DI CUP 40C	GSPC5719	.15	.00	6H	160	AIR ELASTOMER
DC 96-052 A/B AS 1C/1 BW	GSPC2346	1-72	.24	24H	177	AIR PUTTING
DC 96-079 A/B AS 1C/1 BW	GSPC3365	-76	.19	100H	85	AIR DETERGENT
DC 96-080 A/B AS 1C/1 BW	GSPC3485	-48	.11	7D	25	AIR BLASTOMER
DC 991 VARNISH - CLEAR SILICONE/F	GSPC7847	-47	.93	7D	25	AIR COAT
DE 991 VARNISH - CLEAR SILICONE/F	GSPC7880	-88	.50	24H	125	AIR SILICONE
DE 100 SILICONE RUBBER GE SE 565 BASE	GSPC3945	-05	.02	4H	204	AIR SILICONE
DECA-DRY DECAL CARRIER SHEET	GSPC1035	8-39	1-5.1	30H	232	AIR DECAL CARRIER
DECA-DRY LETTER DECALS	GSPC1032	11-26	1-5.1	30H	232	AIR DECAL CARRIER
DELGIN 107 BLACK	GSPC13360	-62	.06	4D	25	AIR Welding Capnd
DELGIN 107 WHITE	GSPC6953	-39	.02	4D	25	AIR Welded GEND
DELTA BOND 152-K-A EPOXY KIT 152/RTA2 AS 20/1.5 BW	GSPC2921	1-73	.01	8H	25	AIR JOINT ADHESIVE
DELTA BOND 152-L-B4 A/B AS 100/3-5 BW BLUE EPQXXI	GSPC8375	-49	.00	1H	25	AIR ADHESIVE
DELTA BOND 152-1-A EPOXY KIT PRE-MIX BLUE	GSPC9853	1-14	.02	16H	60	AIR ADHESIVE
DELTA BOND 152-1-B EPOXY KIT PRE-MIX BLUE	GSPC9856	1-14	.01	16H	25	AIR ADHESIVE
DELTA BOND 152/RTA AS 100/7.5 BW	GSPC3205	1-59	.05	8H	60	AIR ADHESIVE
DELTA CAST 153-K-A EPOXY KIT 153/RTA2 AS 20/1.5 BW	GSPC2923	1-62	.01	8H	25	AIR PUTTING

MATERIAL	REFERENCE	DATA	STL	ACVD	CURE TIME	CURE TEMP	ADHESIVE	APPLICATION
DEN 438/MDA AS 100/27 BW EPOXY - AMBER	GSPC7211	.60	.01	2H	90	44H	ADHESIVE	
DENFLEX 1162 A/B AS 1/1 BW YELLOW FLEXIBLE EPOXY	GSPC8719	4-13	.06	105N	150	ALK	WHITE COAT	
DENNIS 1162 A/B AS 1/1 BW LACQUER W/4600 THINNER	GSPC1384	4-29	.10	24H	66	ALK	LACQUER	
DENNIS 1169 A/B AS 1/1 BW EPOXY	GSPC1322N	5-00	.15	1H	65	ALK	ADHESIVE	
DENNIS 1169 EPOXY	GSPC1797	8-00	.35	7D	25	ALK	ADHESIVE	
DENSIL 2078 SILICONE ADHESIVE TRANSFER FILM/F	GSPC1914	2-78	.79	3H	93	ALK	ADHESIVE FILM	
DENSIL 2403 SILICONE ADHESIVE TRANSFER FILM/F	GSPC12226	1-94	.66	4D	25	ALK	ADHESIVE FILM	
DER 324/DEH-20/DER-732 AS 100/12/12 BW	GSPC12228	2-30	.10	4D	25	ALK	ADHESIVE	
DER 324/LEB-20/VERSABID 150 AS 100/12/50 BW	GSPC1202	3-02	.41	4D	25	ALK	ADHESIVE	
DER 332/DADS/LITHAFRAK AS 10/3/40 BW EPOXY - CREAM	GSPC12082	-24	.00	8H	120	ALK	ADHESIVE	
DER 332/MDA/LITHAFRAK/P-200 MODIFIED GRAY	GSPC12085	-50	.00	4H	150	ALK	PUTTING	
DER 332/MDA/LITHAFRAK/P-200/CARBON BLACK MODIFIED	GSPC14042	-48	.00	18H	65	PSI	PUTTING	
DER 332/TEIA AS 10/1 BW GSPCX	GSPC1705	-54	.00	1H	105	ALK	ADHESIVE	
DER 332/TEIA/LITTAFAKA AS 109/14/170 BW EPOXY-WHITE	GSPC1208	-29	.01	1H	105	ALK	ADHESIVE	
DER 332/TEIA/LITTAFAKA/CAB-O-SIL AS 100/14/235/-67B*	GSPC8334	-29	.01	2H	60	ALK	PUTTING	
DER 332/VERSAMID 125 AS 1/1 BW EPOXY	GSPC3114	1-34	.08	12H	35	ALK	PUTTING	
DER 332/VERSAMID/SR-82 AS 60/40/15/4 DROPS SR-82	GSPC3787	1-32	.07	12H	60	ALK	PUTTING	
DER 332/VERSAMID 732/SR-82 AS 60/40/15/4 DROPS SR-82	GSPC9416	4H	.85	4H	85	ALK	ADHESIVE	
DER 332/VERSAMID 732/SR-82 AS 9/9/2 BW EPOXY	GSPC2853	-33	.01	1H	60	ALK	ADHESIVE	
DER 332LC/HV AS 100/18 BW EPOXY	GSPC2809	-78	.17	60H	60	ALK	PUTTING	
DEF 332LC/VERSAMID 140 AS 42/30 BW EPOXY COATING	GSPC5721	-54	.05	24H	70	ALK	WHITE COAT	
DEF 332LC/VERSAMID 140 AS 6/7 BW EPOXY	GSPC0162	-72	.05	12H	40	ALK	PUTTING	
DEUTSCH CONNECTOR 40/2-PHENYLIMIDAZOLE WHITE SINTACTIC FOAM	GSPC5781	-95	.05	12H	40	ALK	CONNECTOR	
DEUTSCH CONNECTOR 481510F-16-145 BAO-N SILICONE	GSPC7778	-31	.05	10	10	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 481511/46FFU151 BROWN SILICONE MOLD INSERT	GSPC1795	2-21	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 481511/4OFFEU151 GREEN HOLD INSERT	GSPC1795	1-50	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 5KU6-16-615 GREEN RUBBER	GSPC0223	0-09	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 41-010320 KED SILICONE	GSPC784	1-23	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 41-010350 KED SILICONE	GSPC7187	1-29	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTION 6825 KHO-4-425 PHENOLIC INSERT	GSPC1249	1-23	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTION 6825 KHO-4-425 SILICONE INSERT	GSPC1249	1-23	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTION 7221 UR804-212P SILICONE INSERT	GSPC4684	1-22	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CONNECTOR 7503 KTK00-14-44P SILICONE INSERT	GSPC10703	-16	.00	22	37	CONNECTOR	CONNECTOR	
DEUTSCH CTJ SERIES TERMINAL BLOCK RED SILICONE ONLY	GSPC3634	-24	.00	22	37	TERMINAL BLOCK	TERMINAL BLOCK	
DEUTSCH TERMINAL BLOCK 116-01 SILICONE INSERT	GSPC2895	1-61	.00	22	37	TERMINAL BLOCK	TERMINAL BLOCK	
DEVSEA 7580A TAPE POLYESTER FILM/2 SIDE ACR ADH/F	GSPC6902	1-53	.00	22	37	2-SIDED TAPE	2-SIDED TAPE	
DEVCON MIX TUBE EPOXY	GSPC1879	1-57	.00	24H	25	ALK	ADHESIVE	
DEVCON 5 MINUTE EPOXY EQUAL PARTS FROM TUBES	GSPC5196	1-53	.00	24H	25	ALK	ADHESIVE	
DBXSL 201-BOAC/SILICA	GSPC0925	-07	.00	24H	25	ALK	BUILD CEND	
DF 1006 POLYCARBONATE/FLIERK GLASS AS 70/30	GSPC0945	-14	.00	24H	25	ALK	BUILD CEND	
DIAL CORD STUR-D-DIAL DACKON 164 WHILE	GSPC5515	-48	.00	24H	25	ALK	DIAL CORD	

MATERIAL	DATA REFERENCE	XMTL.	XCYC	CURE TIME	CURE TEMP	ARMS	APPLICATION
DIAL CORD 75-3-24 TEE COATED GLASS FIBER	GSPC8288	.08	.05	2H	138	AIR	DIAL CORD CONNECTOR
DIALL 52-70-70 SHORT GLASS FIBER/DAP AS 55/45 BW - BLUE	GSPC7232	.43	.20	2H	93	AIR	PUTTY
DK 18-05 / ECOOSPHERES SILICONE D55/45 BW	GSPC7230	.49	.27	3H	204	AIR	SILICONE
DK - 15-02 DRI-KOTE EPOXY	GSPC8867	.37	.17	24H	60	AIR	PUTTING-COATING
DK - 4 DRI-KOTE EPCX-1 POWDER COATING	GSPC4244	.23	.17	24H	60	AIR	TAPE
DODGE IND TAPE 2045-3 PTFE FILM SILICONE ADH/R	GSPC7437	1.57	.17	24H	60	AIR	TAPE
DODGE IND TAPE 2342-2R KAPTON FILM/ACRYLIC ADH/P	GSPC7019	1.24	.24	24H	60	AIR	ADHESIVE
DODGE IND TAPE 2342-2N KAPTON FILM/ACRYLIC ADH/P	GSPC7118	1.34	.24	24H	60	AIR	ADHESIVE
DOLPHON CCE-1078 W/1318 7/8585 AS 20/1 BW BLACK EPOXY	GSPC9443	2.09	.01	30D	25	AIR	POTTING
DOLPHON CR-1050/RE-2000 AS 20/7 BW	GSPC4820	2.89	.01	30D	25	AIR	ADHESIVE
DOUBLE BUBBLE EPOXY PATCH KIT PREMEASURED GRAY	GSPC5641	1.07	.73	24H	60	AIR	LUBRICANT
DRI-SLIP POWDER LUBRICANT - AEROSOL	GSPC8774	6.51	4.47	2.4H	25	AIR	LUBRICANT
DRI-LUBE 822 FLUOROSILICONE LUBRICATING GREASE	GSPC19272	4.42	.39	6H	70	AIR	INTERNAL BLANKET
DUN-CHROME 500C VLA TEFLON	GSPC13383	4.42	.39	6H	70	AIR	PAINT SYSTEM
DUPONT BLUE LACQUER 8571-1HxDIZLER PRIMER DLL-32	GSPC13386	4.27	.27	6H	70	AIR	ADHESIVE
DUPONT 46971/CAT 865 AS 10/1 BW	GSPC2209	3.29	.51	1H	235	AIR	ADHESIVE
DUPONT 4817 CONDUCTIVE SILVER PAINT	GSPC3183	3.84	.04	24H	65	AIR	COND PAINT
DUPONT 4922 A/E AS 1/1 BW COND SILVER PAINT	GSPC2043	.61	.00	15H	65	AIR	COND PAINT
DUPONT 5504A SILVER FILLED EPOXY	GSPC4532	.05	.00	48H	99	AIR	COND ADHESIVE
DUR-O-LITE WIRE INSULATION RED/BLK NPC	GSPC10910	2.87	.17	1H	160	AIR	COND ADHESIVE
DURAD TEE WIRE INSULATION YELLOW SPC	GSPC9248	.06	.00	2H	240	AIR	COND CPND
DURAFILM 300 SERIES ENAMEL	GSPC10191	.02	.00	20D	149	AIR	WIRE INSUL.
DURALAC BLACK ENAMEL-756	GSPC2200	2.70	.21	20H	260	AIR	WIRE INSUL.
DUX SEAL	GSPC3628	.94	.33	1H	125	AIR	PAINT
DYNA-FLEX REFRACTORY FIBER FELT - ETOH WASH	GSPC2098	2.75	.43	1H	125	AIR	SEALANT
D4 D CONDUCTIVE PAINT	GSPC7724	.09	.01	48H	66	AIR	COND PAINT
D4 D CONDUCTIVE PAINT	GSPC11054	1.88	.35	48H	66	AIR	PAINT
D4 D LEAFING ALUMINUM	GSPC11213	1.57	.34	48H	100	AIR	COND PAINT
D4 D LEAPING ALUMINUM	GSPC1507	8.91	.78	140	25	AIR	PAINT
E 788 POTTING EPOXY	GSPC2348	.72	.10	48H	25	AIR	COND PAINT
E 876 EPOXY	GSPC8420	1.25	.01	48H	177	AIR	POTTING
E-KOTE 3030 CONDUCTIVE ACRYLIC PAINT	GSPC8873	.88	.00	2H	121	AIR	COND PAINT
E-KOTE 40 COND SILVER PAINT/ACRYLIC	GSPC2827	.76	.05	1H	96	AIR	COND PAINT
E-SOLDER 3021 A/E AS 1/1 BW SILVER FILLED EPOXY	GSPC3808	3.32	.10	24H	25	AIR	COND PAINT
E-SOLDER 3022/HARDENER 18	GSPC2905	9.56	.18	24H	60	AIR	COND ADHESIVE
E-SOLDER 3022/AS 100/8 BW SILVER FILLED EPOXY	GSPC2056	1.25	.10	24H	25	AIR	COND ADHESIVE
E-SOLDER 3022/AS 10/3/1.3 BW SILICONE - SPECIAL	GSPC3207	1.27	.02	1.5H	35	AIR	COND ADHESIVE
E-2522/C-46 CAT/STYRENE AS 10/3/1.3 BW SILICONE - SPECIAL	GSPC13466	2.55	.29	2H	35	AIR	COND ADHESIVE
E-2794-13 A/B AS 1C/1 BW SILICONE - SPECIAL	GSPC7937	.85	.29	10D	25	AIR	COND ADHESIVE

MATERIAL	DATA REFERENCE	STAB.	RCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
E-720 EPOXY/FIBERGLASS LAMINATE - POTING FOAMS EA 8 2 POLYESTER FILM INSULATOR - FROSTY EA 8 4/B AS 100/6 BW BROWN EPOXY MAROON EA 901 A/B AS 100/11 BW EPOXY MAROON EA 907 A/B AS 10/8 BW LIGHT BLUE EPOXY	GSEFC7007 GSEFC7010 GSEFC86227 GSEFC9954 GSEFC12028	.54 .46 .98 .83 .60	.04 .02 .04 .03 1.03	204 5D 3D 2H 2H	93 110 25 62 25	AIR AIR AIR AIR AIR	LAMINATE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EA 920 3 ONE COMPONENT PRIMER FOR EPOXY EA 921 A/B AS 4/1 BW GRAY EPOXY EA 930 7 A/B AS 100/14 BW BROWN EPOXY EA 930 9 A/B AS 100/23 BW EPOXY EA 930 9 A/B AS 100/23 BW EPOXY LUT F9AS 90551 EA 930 9 A/B AS 100/23 BW EPOXY LCI 29195 EA 930 9 A/B AS 100/22/0.5% POLYPROPYLENE BEADS BN EA 930 9 A/B AS 100/22/0.5% POLYPROPYLENE BEADS BN	GSEFC4998 GSEFC5094 GSEFC10026 GSEFC6794 GSEFC96220	19.65 2.42 .48 2.18 1.25	1.96 .02 .00 .00 .02	2H 2H 3D 2H .02	71 71 121 25 25	AIR AIR AIR AIR AIR	LAMINATE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EA 931 3 ORANGE EPOXY EA 932 0 A/B AS 100/19 BW BLUE EPOXY EA 932 1 GRAY EPOXY EA 934 A/B AS 100/33 BW GRAY EPOXY	GSC10029 GSC10029 GSC10592	1.12 .94 .79	.04 .04 .04	15H 90M 90M	121 66 66	AIR AIR AIR	ADHESIVE ADHESIVE COATING
EA 934 A/B AS 100/33 BW GRAY EPOXY EA 934 NA A/B AS 10C/33 BW GRAY EPOXY (EPCN 934) EA 9414.1 ONE COMPONANT EPOXY WHITE EA 951 SUPPORTED EPOXY ADHESIVE FILM GRAY EA 953 EPOXY EA 956 EPOXY	GSC10601 GSEFC4745 GSC11057 GSC10032 GSEFC5803 GSEFC2847 GSEFC8721 GSEFC2849 GSEFC5805 GSEFC5414 GSEFC4794 GSEFC6836 GSEFC4738 GSEFC6287 GSC12712 GSEFC6281 GSEFC284 GSEFC2607	1.07 .49 .54 .15 2.48 .80 1.54 1.54 1.34 1.34 6.15 .65 .60 1.01 1.01 1.01 1.01 1.01 1.01	.01 .01 .01 .01 .02 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H	30D 7D 7D 30M 1H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H 24H	121 25 25 121 17	AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR	LOCATING ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
EA 960 1 SUPPORTED EPOXY ADHESIVE FILM YELLOW EA 965 3 EPOXY FILM ADHESIVE EASTMAN FA FILM 04C10 EASTMAN 910 CYANACRYLIC FOIL SANDWICH EASYPoxy K-20 REPAIR KIT A/B AS EQUAL BEADS FB TUBES EASYPoxy K-256 A/B AS EQUAL LENGTHS FROM TUBES WHITE EASYPoxy K-26 A/B AS EQUAL LENGTHS FROM TUBES GRAY EASYPoxy K-40 A/E AS EQUAL LENGTHS FROM TUBES BLUE E-1614 A/B AS 1/1 BW EPOXY ADH	GSEFC4192 GSEFC4340 GSEFC4294 GSEFC9933 GSEFC3284 GSEFC3371 GSEFC3495	1.02 .94 7.14 4.45 1.38 1.32 1.20	.02 .02 .04 .04 1H 1H 1H	7D 30D 48H 48H 72H 72H 30M	121 177 82 82 177 177 92	AIR AIR AIR AIR AIR AIR AIR	PUTTING PUTTING SEALANT COAT ADHESIVE ADHESIVE ADHESIVE
EC 166 3 A/B AS 1/10 BW SILICONE SEALANT EC 166 3 A/B AS 1/10 BW SILICONE SEALANT EC 166 5 A/B AS 1/16 BW POLYSULFIDE SEALANT EC 1981 FLEXIBLE CCATING - CLEAR EC 2126 BUNA N ADHESIVE EC 2258 EPOXY ADH EC 2290 EPOXY ADH	GSEFC4192 GSEFC4340 GSEFC4294 GSEFC9933 GSEFC3284 GSEFC3371 GSEFC3495	1.02 .94 7.14 4.45 1.38 1.32 1.20	.02 .02 .04 .04 1H 1H 1H	7D 30D 48H 48H 72H 72H 30M	121 177 82 82 177 177 92	AIR AIR AIR AIR AIR AIR AIR	PUTTING PUTTING SEALANT COAT ADHESIVE ADHESIVE ADHESIVE
EC 2290 EPOXY ADHESIVE EC 2290 EPOXY FCAN WHITE ONE PART SYSTEM EC 3439 EPOXY FCAN WHITE ONE PART SYSTEM EC 3500 E/A AS 2/3 BW EPOXY ADHESIVE	GSEFC3560 GSEFC8735 GSEFC4258 GSEFC3664	-0.1 1.60 2.14 -0.06	.01 -0.08 -0.08 -0.06	30M 30M 2H 1H	121 121 121 121	AIR AIR AIR AIR	ADHESIVE ADHESIVE FLUID SEALANT ADHESIVE

MATERIAL	DATA REFERENCE	XTHL	XCVN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
EC 3500 EPOXY ADHESIVE AS 100/94 BW EPOXY FOAM BLUE	GSPC3618	.40	.00	60M	170	P-1	ADHESIVE
EC 3524/EC 3624 AS 100/94 BW EPOXY FOAM GREEN EPOXY	GSPC3660	.84	.51	16H	255	AIR	FOAM SEALANT
ECCOBOND SF 40 SYNTACTIC FOAM EPOXY/GREEN EPOXY	GSPC2734	.23	.04	48H	2420	AIR	ADHESIVE
ECCOBOND 104 A/B AS 100/64 BW CLEAR EPOXY	GSPC3318	.52	.08	6H	25	AIR	ADHESIVE
ECCOBOND 24 A/B AS 100/28 BW CLEAR EPOXY	GSPC3662	.62	.69	43	25	AIR	ADHESIVE
ECCOBOND 24 A/B AS 100/28 BW 4-5% BN BLUE PIGMENT	GSPC3924	.62	.69	43	25	AIR	POTTING
ECCOBOND 24 A/B AS 30/3 BW CLEAR EPOXY	GSPC5957	.31	.13	7D	25	AIR	POTTING
ECCOBOND 276/CAT 17 AS 10/1 BW EPOXY	GSPC3939	.49	.00	2H	93	AIR	ADHESIVE
ECCOBOND 281 ONE PART EPOXY - BLACK	GSPC9694	.35	.00	2H	200	AIR	THERM COND ADH
ECCOBOND 285/24LV AS 20/1 BW EPOXY	GSPC3221	.28	.01	8H	82	AIR	ADHESIVE
ECCOBOND 285/24LV AS 25/2 BW EPOXY	GSPC3347	.00	.00	24H	25	AIR	ADHESIVE
ECCOBOND 285/9 AS 25/1 BW EPOXY	GSPC3219	.46	.91	24H	25	AIR	ADHESIVE
ECCOBOND 286 A/B AS 1/1 BW EPOXY	GSPC3245	.58	.71	24H	25	AIR	ADHESIVE
ECCOBOND 45/15 AS 1/2 BW SEMI-RIGID EPOXY CLEAR BLACK	GSPC3447	.92	.07	30H	104	AIR	ADHESIVE
ECCOBOND 45LV/15LV AS 2/1 BW EPOXY CLEAR BLACK	GSPC9449	.98	.92	30H	104	AIR	ADHESIVE
ECCOBOND 45LV/15LV AS 4/1 BW EPOXY	GSPC3848	.44	.73	24H	50	AIR	PUTTING
ECCOBOND 51/9 AS 10/0/7 BW EPOXY	GSPC5945	.46	.02	24H	25	AIR	ADHESIVE
ECCOBOND 55/9 AS 50/6 BW EPOXY	GSPC8786	.46	.02	30H	65	AIR	ADHESIVE
ECCOBOND 56C/9 AS 40/1 BW SOLDER	GSPC8789	.45	.02	30H	65	AIR	ADHESIVE
ECCOBOND 56C/9 AS 33/4 BW SOLDER	GSPC8334	.23	.01	30H	25	AIR	ADHESIVE
ECCOBOND 57C A/B AS 1/1 BW COND EPOXY SILVER	GSPF8087	.52	.04	1H	250	AIR	COND ADHESIVE
ECCOBOND 58C A/B AS 1/1 BW COND EPOXY SILVER	GSPC8141	.36	.03	30H	149	AIR	COND ADHESIVE
ECCOBOND 582/CAT 9 AS 100/7 BW EPOXY	GSPC470	.39	.07	16H	25	AIR	COND ADHESIVE
ECCOBOND 60L A/E AS 10/3 BW SILVER FILLED EPOXY	GSPC3216	.39	.02	24H	25	AIR	PUTTING
ECCOBOND 787 A/B AS 1/1 BW TRIZOTROPIC EPOXY	GSPC2396	.54	.54	24H	25	AIR	ADHESIVE
ECCOBOND 83C/A/B AS 10/3.5 BW BI-PAK SILVER FILLED	GSPC2709	.29	.03	1H	66	AIR	COND ADHESIVE
ECCOBOND 83C-1 ONE CONDUCTIVE SILVER FILLED	GSPC2230	.64	.01	1H	149	AIR	COND ADHESIVE
ECCOCOAT CC-2 CONDUCTIVE SILVER COATING/F	GSPC8447	.37	.03	30H	150	AIR	COATING
ECCOCOAT CC-4 SILVER FILLED ELASTOMER	GSPC6440	.44	.10	7D	25	AIR	COND COATING
ECCOCOAT EP-3 SILVER AS 2/1 BW EPOXY COATING	GSPC4286	.15	.03	2H	70	AIR	COND COATING
ECCOCOAT Tr-11 A/B AS 1/1 BW AMBER COATING	GSPC7676	1.01	.01	3H	95	AIR	COATING
ECCOCOAT 200 A/B AS 10/1 BW EPOXY	GSPC2531	.90	.04	8H	25	AIR	COATING
ECCOCOAT 582 A/B AS 100/7 BW THERMAL COATING	GSC11806	.56	.02	72H	25	AIR	WARM COATING
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSC0517	.66	.34	24H	80	AIR	PUT FOAM
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSC10520	.88	.28	16H	80	AIR	PUT FOAM
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSC10526	.91	.27	16H	80	AIR	PUT FOAM
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSC10532	1.23	.35	16H	80	AIR	PUT FOAM
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSPC7355	.93	.40	4D	80	AIR	FOAM DAMPER
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	GSPC7541	.40	.09	2H	125	AIR	FOAM DAMPER
ECCOFoam EFF-14FR SYNTACTIC FOAM	GSPC6371	.32	.99	24H	125	AIR	FOAM DAMPER
ECCOFoam EFF-14FR SYNTACTIC FOAM	GSPC6437	.72	.30	2H	135	AIR	PUT FOAM
ECCOFoam EFF-14FR SYNTACTIC FOAM - ORANGE EPOXY	GSPC7340	.67	.29	2H	125	AIR	FOAM DAMPER

MATERIAL	DATA REFERENCE	RTM TIME	ACVCA CURE TIME	CURE AIR/OS	APPLICATION
ECCOFoAM EFF-14FR SYNTACTIC FOAM - ORANGE EPOXY	GSFEC764	.73	.23	AIR	FOAM DAMPER
ECCOFoAM EFF-14FR SYNTACTIC FOAM - ORANGE LOT 518	GSFEC7457	1.05	.56	2H	FOAM
ECCOFoAM EFF-14FR SYNTACTIC FOAM - ORANGE LOT 521	GSFEC7460	1.04	.52	114H	FOAM
ECCOFoAM FP 12-16 A/B AS 100/12 BW POLYURETHANE FOAM	GSFEC4414	3.54	.05	24H	FOAM
ECCOFoAM FP 12-16 A/B AS 100/12 BW POLYURETHANE FOAM	GSFEC4436	3.45	.06	24H	FOAM
ECCOFoAM FP 12-16 E A/B AS 4/3 BW POLYURETHANE FOAM	GSFEC4416	2.10	.03	24H	FOAM
ECCOFoAM FP 12-16 E A/B AS 4/3 BW POLYURETHANE FOAM	GSFEC4438	1.93	.04	24H	FOAM
ECCOFoAM F-2H/12-2H POLYURETHANE FOAM	GSFEC5906	.99	.07	8H	FOAM
ECCOFoAM FPH/12-2H POLYURETHANE FOAM	GSFEC5912	1.08	.10	8H	FOAM
ECCOFoAM FP/12-4H POLYURETHANE FOAM	GSFEC3654	.61	.12	72H	FOAM
ECCOFoAM FS POLYURETHANE FOAM	GSFEC4786	.68	.93	48H	FOAM
ECCOFoAM FS POLYURETHANE FOAM	GSFEC10490	4.08	.79	48H	FOAM
ECCOFoAM ET OH WASHI X2	GSC10493	.72	.12	90	FOAM
ECCOFoAM ET OH WASHI X2	GSC10496	.81	.12	90	FOAM
ECCOFoAM PP-HI-3 WHITE	GSC11378	2.44	.18	24H	STRUCTURAL FOAM
ECCOFoAM SH 14*/CU FT POLYURETHANE FOAM	GSC11144	1.04	.00	AIR	FOAM
ECCOFoAM SH 24*/CU FT POLYURETHANE FOAM	GSC12757	1.59	.02	AIR	FOAM
ECCOFoAM SH 4*/CU FT POLYURETHANE FOAM	GSC12754	1.79	.00	AIR	FOAM
ECCOFoAM SH 84*/CU FT POLYURETHANE FOAM	GSEC12759	1.33	.08	AIR	STRUCTURAL
ECCMOLD L-28 L28/24LV AS 100/26.4 BW	GSC12262	.73	.05	4D	GOLD CPND
ECCMOLD L28/24LV AS 100/12 BW	GSC11390	.59	.03	30H	GOLD CPND
ECCMOLD 60A EPOXY - MOLD 10M AT 163C W/PSI	GSFEC4392	.49	.06	1H	AIR
ECCMOLD 77A EPOXY - MOLD 10M AT 163C W/PSI	GSFEC7451	.32	.07	16H	AIR
EC COSEAL W-19/CA1 11 AS 100/16 BW EPOXY AMBER	GSFEC4578	7.38	.34	4D	POTTING TAPE
EC COSEAL W-19/CA1 24L AS 100/26.4 BW EPOXY AMBER	GSC12214	4.17	.08	24H	ADHESIVE TAPE
EC COSEAL W-19/CA1 9 AS 100/12 BW EPOXY	GSC12234	2.68	.03	24H	ADHESIVE TAPE
EC COSEAL 1207/CA1 20 AS 100/1.5 BW BLACK EPOXY	GSFEC2278	.27	.01	4H	POTTING TAPE
EC COSEAL 1218 A/E AS 10/7 BW EPOXY	GSFEC2248	2.04	.35	12H	ADHESIVE TAPE
EC COSHIELD COT GRAPHTONE FILLED SILICONE GREASE	GSFEC4788	36.08	22.35	12H	POTTING TAPE
EC COSHIELD PST-C-A ALUM FOIL/SILVER FILLED ACRYLIC ADH	GSFEC2221	.26	.39	12H	ADHESIVE TAPE
EC COSHIELD SV-S ADHESIVE ECO-SHIELD SV-R/FOIL	GSFEC8849	.26	.11	7D	ADHESIVE TAPE
EC COSHIELD SV-S SILVER FILLED PLASTIC SILICONE	GSFEC4975	14.06	.58	8-16H	SILVER SHIELD
EC COSHIELD SV-S SILVER FILLED SILICONE	GSFEC3875	.16	.06	24H	SILVER SHIELD
EC COSHIELD SV-S SILVER FILLED SILICONE	GSFEC8852	.33	.06	24H	SILVER SHIELD
EC COSHIELD SV-S SILVER FILLED SILICONE	GSFEC10077	1.05	.32	25	SILVER SHIELD
EC COSHIELD SX CONDUCTIVE SEALER	GSFEC1942	.58	.04	30M	SILVER SEALANT
EC COSHIELD LN1049-97 A/E AS 10/1 BW CLEAR SILICONE	GSC12526	.19	.07	33	AIR
EC COSIL TP-50 A/E AS 100/9 BW SILICONE PASTE	GSC10913	.19	.27	16H	AIR
EC COSIL 4640/CA1 25 AS 0.3% CAT SYNTACTIC FOAM	GSFEC4216	1.33	.24	8H	AIR
EC COSIL 4640/CA1 50 AS 0.3% CAT SYNTACTIC FOAM	GSFEC4652	.91	.35	25	2-6H
EC COSIL 4850/CA1 25 AS 100/0.5 BW SILICONE	GSFEC1606	1.28	.35	16H	AIR

MATERIAL	DATA REFERENCE	ATMOS	%CVCH	CURE TIME	CURE TEMP	AIR	APPLICATION
ECCOSIL 4850/CAT 25 AS 100/0.5 BH SILICONE	GSPC1609	1.21	.34	2H	66	AIR	POFFING
ECCOSIL 4952/CAT 50 AS 100/0.02 BH FILLED SILICONE	GSC10544	.29	.14	1H	121	AIR	INHERM CONTROL
ECCOSIL 4954/CAT 50 AS 100/0.02 BH FILLED SILICONE	GSC10541	.24	.10	7D	225	AIR	INHERM CONTROL
ECCOSIL TH-24 LOW FRICTION EPOXY	GSPC4011	.40	.00	1H	66	AIR	EOXY LUBE
ECCOSORB AN 74 ETHANOL WASH - 3	GSPC5405	.70	.07	24H	116	AIR	ABSORBANT
ECCOSORB AN 74 METHANOL WASH - 3	GSPC3407	.51	.05	21H	100	AIR	ABSORBANT
ECCOSORB AN 79 MICROWAVE ABSORBANT	GSPC4025	4-37	.45	21H	100	AIR	ABSORBANT
ECCOSORB AN 79 MICROWAVE ABSORBANT 16H METOH WASH	GSPC4842	1-03	.15	3H	25	AIR	ABSORBANT
ECCOSORB AN 79 MICROWAVE ABSORBANT 4H ETOH WASH	GSC11409	2-10	.14	25H	100	AIR	ABSORBANT
ECCOSORB AN 79 MICROWAVE ABSORBANT 4H ADH 44	GSPC1926	1-16	.39	3H	25	AIR	ABSORBANT
ECCOSORB CR-S 124 A/B AS 100/1 BH SILICONE BASE	GSPC5447	.29	.09	2H	80	AIR	ABSORBANT
ECCOSORB CR-117 X/Y AS 100/2.3 BH DARK GRAY EPOXY	GSC12088	.26	.01	12H	74	AIR	OLD CPND
ECCOSORB CR-117 X/Y AS 50/1 BH EPOXY	GSPC3924	.11	.01	140	25	AIR	ABSORBANT
ECCOSORB FDS GDS IRON FILLED SILICONE	GSPC9396	.29	.12	6H	200	AIR	ABSORBANT
ECCOSORB GDS IRON FILLED SILICONE	GSPC9397	.20	.08	24H	100	AIR	ABSORBANT
ECCOSORB LS FOAM	GSPC5248	4-38	.44	24H	100	AIR	ABSORBANT
ECCOSORB MF 110 IRCN FILLED EPOXY	GSPC3965	.51	.51	24H	100	AIR	ABSORBANT
ECCOSORB MF 112 IRCN FILLED EPOXY	GSPC2436	.26	.01	24H	100	AIR	SHIELD
ECCOSORB MF 114 IRCN FILLED EPOXY	GSPC2418	.22	.00	24H	100	AIR	ABSORBANT
ECCOSORB OCP 9 FLAME RETARD MICROWAVE ABSORBER	GSPC3993	.08	.03	24H	100	AIR	ABSORBANT
ECCOSORB SF 9-5 RESONANT ABSORBER-SILICONE FILLED	GSC13105	.31	.15	16H	177	AIR	ABSORBER
ECCOSORB SF 9-2.5	GSPC8261	.14	.06	16H	177	AIR	ABSORBANT
ECCOSORB SFU-9 PCLYURETHANE	GSC11809	.52	.00	16H	25	AIR	ABSORBANT
ECCOSORB SFU-9 PCLYURETHANE	GSC12929	.52	.00	12H	74	AIR	OLD CPND
ECCOTHERM LN 80142 FILLED HEAT SINK GREASE	GSC11333	.33	.16	16H	100	AIR	INHERM GREASE
ECCOTHERM TC 4 FILLED HEAT SINK GREASE	GSPC11522	.54	.05	16H	100	AIR	INHERM GREASE
ECCOTHERM TC 4 FILLED HEAT SINK GREASE	GSPC93245	.52	.05	16H	100	AIR	INHERM GREASE
ECCOTHERM TC-4 FILLED HEAT SINK GREASE BTCH 10803014	GSPC95919	.56	.19	16H	100	AIR	INHERM GREASE
ECCOTHERM TC-5 FILLED HEAT SINK GREASE	GSPC95902	.50	.13	16H	100	AIR	INHERM GREASE
ECCOTHERM TC-6 FILLED HEAT SINK GREASE	GSPC06225	.49	.13	16H	100	AIR	INHERM GREASE
ECCOTHERM TC-7 FILLED HEAT SINK GREASE	GSPC0718	.37	.15	16H	100	AIR	INHERM GREASE
ECD 006 PERFLUOROCESTOMER	GSPC17151	.14	.00	16H	100	AIR	SEAL-GASKET
EFD 49-90 PLASTICLASSTOMER	GSPC1420	.51	.00	16H	100	AIR	SEAL
ECP 2200 BLACK SCALAR ABSORBER COATING/F	GSPC4174	1-99	.74	24H	204	AIR	INHERD CONTROL
ECP 2200 BLACK SCALAR ABSORBER COATING/F	GSPC32649	.08	.00	4H	121	AIR	INHERD CONTROL
ECP 2200 EXTRUDED SHEET HI-TEMP APPLICATION	GSPC3287	.61	.27	4H	121	AIR	INHERD COATING
ECPF 0-5 MIL FILM	GSPC40980	.09	.01	16H	100	AIR	INSULATION
ECPF 1-0 MIL FILM	GSPC4082	.19	.02	16H	100	AIR	OPTICAL FILM
ECTFE 10-8 32/32 YD FABRIC UNCALENDERED UNWASHED ETOH/ACE	GSPC4108	.62	.09	24H	204	AIR	BLANKET
ECTFE 7-3 32/32 YD FABRIC UNCALENDERED UNWASHED ETOH/ACE	GSPC4089	.28	.03	24H	204	AIR	BLANKET
ECTFE 7-3 32/32 YD FABRIC UNCALENDERED WASHED ETOH/ACE	GSPC4190	.33	.03	24H	204	AIR	BLANKET
EHP-1 POLYURETHANE FOAM - BLACK	GSPC5355	.21	.07	24H	204	AIR	FUAM ABSORBER
EHP-3 HR POLYIMIDE IMPREG NOXER PAPER HONEYCOMB	GSPC5358	.20	.07	24H	204	AIR	FUAM ABSORBER
EHP-8 MICROWAVE ABSORBING FOAM	GSPC5361	.97	.02	24H	204	AIR	FUAM ABSORBER
EHP-8 MICROWAVE ABSORBING FOAM	GSPC5363	.50	.07	24H	204	AIR	FUAM ABSORBER

MATERIAL	DATA REFERENCE	RTML	RCVCA	CURE TIME	CURE TEMP	ADHES S	APPLICATION
EKKCEL C-1000 AROMATIC COPOLYESTER BROWN HIGH TEMP	GSPC9242	-26	-00	-00	-00	AIR	BUILD CPND
EKKCEL I-125 AROMATIC POLYESTER/TPE BLEND TAN	GSPC9254	-05	-00	-00	-00	AIR	BUILD CPND
EKKCEL WR-25 AROMATIC POLYESTER/TPE BLEND TAN	GSPC9177	-05	-00	-00	-00	AIR	SOLID GLUE
ELASTONET WE 1700 A/B AS 100/53 E	GSPC3185	-1.19	1.32	36H	160	AIR	SOLID SHIELDING
ELECTROBOND 2015 A/B AS 10/1 BW SILVER FILLED EPOXY	GSPC2967	-0.44	-0.01	24H	25	AIR	ADHESIVE
ELECTROLUMINESCENT LAMP-GRIMES-YELLOW	GSPC13299	-0.41	-0.01	2H	65	AIR	COND ADHESIVE
ELTEK FOLIETHINABLE EN 7302 GLASS FILLED EPOXY	GSC10889	-0.5	-0.01	30H	45A	AIR	BUILD CPND
EN 7302 GLASS FILLED EPOXY	GSC12175	-0.8	-0.01	15M	45A	AIR	BUILD CPND
EMA 7037 IRON	GSPC5741	-24	-0.01	12H	143	ESD	DELECTRIC
EMA 9190 IRON	GSPC5745	-23	-0.00	39	-	-	DELECTRIC
EMC 90 - BLACK	GSPC2260	-29	-0.01	5H	150	AIR	BUILD CPND
EMI SILVER FILLED SILICONE ME 51-U8-0201	GSPC7214	-60	-0.01	5H	-	-	BOTTING
EMX-116 A/E AS 1/1 BW TAN EPOXY	GSPC30905	-1.06	-0.35	14	48H	AIR	SASKTIVE
ENAMEL FLAT BLACK AEROSOL BROWN DUGAN 100	GSC11770	-1.37	-0.85	72H	25	AIR	PAINT
ENAMEL 453-4-5/CA-212 AS 1/1 BW BLUE EPOXY/POLYOLEFIN	GSPC13992	-3.95	-0.01	1H	25	AIR	END CAP
END CAP D300-18 SHEINKABLE IRRAD BLACK POLYOLEFIN	GSPC08578	-9.92	-0.01	7D	260	AIR	DEARING MATT
ENVEX 1000	GSPC0709	-1.94	-0.01	1H	-	-	DEARING MATT
ENVEX 1000X	GSPC0892	-1.87	-0.01	24H	204	AIR	DEARING MATT
ENVEX 1000X POLYIMIDE	GSPC0895	-1.83	-0.01	24H	204	AIR	DEARING MATT
ENVEX 1115	GSPC0712	-1.67	-0.03	3H	-	-	DEARING MATT
ENVEX 1228	GSPC0724	-1.29	-0.03	24H	204	AIR	DEARING MATT
ENVEX 1315	GSPC0917	-1.29	-0.03	24H	204	AIR	DEARING MATT
EP-C-011 KAPTON FILM/HERMOSET ADH STRIP CLOSED CELL FOAM/ADH FILM/FOIL	GSPC0919	-1.25	-0.02	24H	204	AIR	DEARING MATT
EPDM SILVER FILLED EPOXY/GLASS - BLACK	GSPC0934	-2.03	-0.02	24H	204	AIR	DEARING MATT
EPITALL 1914 EPOXY/GLASS - BLACK	GSPC0942	-1.26	-0.02	24H	204	AIR	DEARING MATT
EPIBOND 1210/CAT 9615 AS 100/65 BW EPOXY	GSPC3450	-4.7	-0.03	3H	25	AIR	BUILD CPND
EPIBOND 1210/CAT 9861 AS 5/1 BW EPOXY	GSPC3065	-9.5	-0.03	3H	65	AIR	ADHESIVE
EPIBOND 122/CAT 9311	GSE66798	-7.7	-0.03	7D	25	AIR	ADHESIVE
EPIBOND 122/CAT 952 AS 20/3 BW EPOXY	GSPC3630	-3.17	-0.03	16H	65	AIR	ADHESIVE
EPIBOND 123/CAT 952 AS 20/3 BW EPOXY	GSPC3632	-4.37	-0.03	7D	25	AIR	ADHESIVE
EPIBOND 123/CAT 9615 AS 100/65 BW EPOXY	GSPC6221	-6.3	-0.03	24H	25	AIR	ADHESIVE
EPIBOND 1923/HOD T/FILLER/CONVERTER - EPOXY	GSPC3454	-8.5	-0.03	7D	25	AIR	ADHESIVE
EPIBOND 8510 A/B AS 10/3 BW	GSPC312	-0.5	-0.00	5D	25	AIR	ADHESIVE
EPIPHEN 825A/HOD T/FILLER/CONVERTER - EPOXY	GSPC150	-83	-0.01	1H	150	AIR	ADHESIVE
EPO-TEK H11 A/B AS 15/2-6 BW SILVER FILLED EPOXY	GSPC4930	3.40	-0.02	9H	80	AIR	COND ADHESIVE
EPO-TEK H20E A/B AS 1/1 BW SILVER FILLED EPOXY	GSPC9101	1.18	-0.02	2H	100	AIR	COND ADHESIVE
EPO-TEK H20E A/B AS 1/1 BW SILVER FILLED EPOXY	GSPC7388	8.16	-0.02	15M	150	AIR	COND ADHESIVE
EPO-TEK H20S A/B AS 1/1 BW SILVER FILLED EPOXY	GSPC9107	1.54	-0.01	2H	100	AIR	COND ADHESIVE
EPO-TEK H21D A/B AS 10/1 BW SILVER FILLED EPOXY	GSPC0118	1.00	-0.01	30M	100	AIR	COND ADHESIVE
EPO-TEK H22 A/B AS 20/0.9 BW SILVER FILLED EPOXY	GSPC4446	1.00	-0.01	3.5H	50	AIR	ADHESIVE
EPO-TEK H22 A/B AS 20/0.9 BW SILVER FILLED EPOXY	GSPC9449	1.00	-0.01	20H	100	AIR	ADHESIVE
EPO-TEK H22 D A/B AS 10/1 BW SILVER FILLED EPOXY	GSC19574	5.52	-0.01	1H	150	AIR	COND ADHESIVE
EPO-TEK H31 SILVER FILLED EPOXY	GSPC512	-5.9	-0.02	1H	125	AIR	COND ADHESIVE
EPO-TEK H31DLY SILVER FILLED EPOXY SINGLE COMPONENT	GSPC7112	-4.7	-0.02	1H	120	AIR	COND ADHESIVE
EPO-TEK H40 GOLD FILLED EPOXY SINGLE COMPONENT	GSPC5234	-1.9	-0.02	1H	150	AIR	COND ADHESIVE
EPO-TEK H41 GOLD FILLED EPOXY	GSPC5236	-1.4	-0.02	1H	150	AIR	COND ADHESIVE
EPO-TEK H43 GOLD FILLED EPOXY	GSPC5238	-2.0	-0.02	1H	150	AIR	COND ADHESIVE
EPO-TEK H44 GOLD FILLED EPOXY	GSPC5238	-2.7	-0.02	1H	150	AIR	COND ADHESIVE

MATERIAL	DATA REFERENCE	STAB.	RCVN	CURE TIME	CURE TEMP	AIR	APPLICATION
EPO-TEK H70E A/B AS 1/1 BW THERM COND EPOXY	GSC12127	1.51	.03	12H	50	AIR	THERM COND ADH
EPO-TEK H70E A/B AS 1/1 BW THERM COND EPOXY	GSC12127	.99	.03	12H	60	AIR	ADHESIVE
EPO-TEK H72 A/B AS 10/4 BW DIELECTRIC EPOXY PASTE	GSFC9877	.31	.00	18D	25	AIR	ADHESIVE
EPO-TEK H73 A/B AS 10/0.3 BW EPOXY BROWN	GSC12236	.43	.01	30H	100	AIR	COATING
EPO-TEK H74 A/B AS 10/3 BW THERM COND EPOXY BROWN	GSFC5881	.56	.01	20H	100	AIR	ADHESIVE
EPO-TEK H77 A/B AS 20/3 BW BROWN EPOXY	GSFC9452	.22	.00	1H	150	AIR	ADHESIVE
EPO-TEK H80 SILVER FILLED EPOXY	GSFC3081	.16	.01	24H	50	AIR	COND ADHESIVE
EPO-TEK H81 A/B AS 1/1 BW PLATINUM FILLED EPOXY	GSFC7586	.62	.00	16H	60	AIR	COND ADHESIVE
EPO-TEK H81 A/B AS 10/1 BW GOLD FILLED EPOXY	GSFC4932	.06	.01	12H	95	AIR	B-6
EPO-TEK H81E A/B AS 1/1 BW GOLD FILLED EPOXY	GSFC9590	.20	.01	24H	100	AIR	COND ADHESIVE
EPO-TEK 301 A/B AS 20/5 BW OPTICAL CEMENT EPOXY	GSFC9605	1.08	.00	24H	25	AIR	OPT CEMENT
EPO-TEK 301 A/B AS 20/5 BW OPTICAL EPOXY LOT 375049	GSFC9578	1.09	.01	18H	25	AIR	OPT CEMENT
EPO-TEK 301 A/B AS 20/5 BW OPTICAL EPOXY LOT 375051	GSFC9981	1.17	.02	6H	65	AIR	OPT CEMENT
EPO-TEK 301-2 A/B AS 20/5 BW OPTICAL CEMENT EPOXY	GSFC9724	2.62	1.03	24H	25	AIR	OPT CEMENT
EPO-TEK 301J A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY	GSCF3716	3.58	.15	24H	25	AIR	OPT CEMENT
EPO-TEK 305 A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY	GSFC2689	1.54	.04	24H	25	AIR	OPT CEMENT
EPO-TEK 305 A/B AS 10/2.8 BW OPTICAL CEMENT EPOXY	GSFC9554	3.28	.15	24H	25	AIR	OPT CEMENT
EPO-TEK 320 A/B AS 5/1 BW BLACK EPOXY	GSC12427	1.49	.02	6H	25	AIR	ADHESIVE
EPO-TEK 353ND HIGH TEMP EPOXY PRE-MIX PACK 10/1 BW	GSC12064	2.03	.02	24H	25	AIR	ADHESIVE
EPO-TEK 353ND HIGH TEMP EPOXY PRE-MIX PACK 10/1 BW	GSC12067	1.83	.01	24H	60	AIR	ADHESIVE
EPO-TEK 390 POLYIMIDE/F	GSC12070	1.88	.04	10H	100	AIR	ADHESIVE
EPO-TEK 415G A/B AS 1/1 BW SILVER FILLED EPOXY	GSC13389	.43	.01	24H	25	AIR	ADHESIVE
EPO-TEK 417 A/B AS 15/1 BW SILVER FILLED EPOXY	GSFC9377	1.85	.27	1H	200	AIR	COND ADHESIVE
EPO-TEK 417 A/B AS 15/1 BW SILVER FILLED EPOXY	GSCF4928	2.19	.02	3D	25	AIR	COND ADHESIVE
EPO-TEK 920 A/B AS 100/3.3 BW FILLED EPOXY	GSFC5423	3.13	.01	1H	130	AIR	LUND ADHESIVE
EPO-TEK 930 A/B AS 100/3.3 BW FILLED EPOXY	GSCF4960	.46	.00	45H	80	AIR	ADHESIVE
EPOCAST N4E-053/CA1	GSFC9787	.49	.00	45H	80	AIR	THERM COND ADH
EPOCAST N4E-053/CA1	GSCF2110	.07	.02	24H	93	AIR	POTTING
EPOCAST 1368/9313 AS 50/17 BW EPOXY-FURANE SL-15E	GSFC4128	5.83	.01	8H	25	AIR	ADHESIVE
EPOCAST 202-100	GSFC4990	5.24	.01	5H	66	AIR	POTTING
EPOCAST 202-60	GSFC4898	3.54	.00	5H	66	AIR	POTTING
EPOCAST 202/9615 AS 10/8 BW	GSCC3251	5.69	.02	48H	22	AIR	FLUTTING
EPOCAST 26-1/1 EPOXY POWDER COATING	GSFC4910	1.09	.36	1H	177	AIR	FLUTTING
EPOCAST 403-5-3	GSFC2322	.32	.01	4H	163	AIR	MOLD CEND
EPOCAST 461-008 MINERAL FILLED EPOXY	GSFC12532	.48	.00	48H	25	AIR	MOLD CEND
EPOCAST 8219 A/B AS 5/1 BW SYNTACTIC EPOXY FOAM	GSFC6608	2.94	.10	48H	25	AIR	POTTING FOAM
EPOCAST 8508 EPOXY ADHESIVE	GSFC3489	.10	.24	3H	93	AIR	ADHESIVE
EPON 4-24 EPOXY	GSFC1633	.42	.05	2.5H	95	AIR	ADHESIVE
				10H	60	PSI	
					25	AIR	
					100	AIR	

MATERIAL	DATA REFERENCE	XTHL	ACVCH	CURE TIME	CURE TEMP	AIDS	APPLICATION
EPON 1001-ET-70/VERSAMID 115/MEK/TOLUENE 2/1 BW THINNERS A/B AS 100/12-5/25 BW	GSEFC5220 GSEFC4612 GSCCO355 GSEFC0356	9.00 12.0 6.0 4.74	.00 .02 .01 .00	150M 1H 3H 24H	25 99 93 121	AIR AIR AIR AIR	ADHESIVE ADHESIVE ADH-POTTING ADH-POTTING
EPON 801/VERSAMID 115/MEK/TOLUENE 2/1 BW THINNERS A/CAT A/CYCLOHEXANOL AS 100/12-5/25 BW	GSEFC12218	.81	.03	4D	25	AIR	ADHESIVE
EPON 815/DER 732/V9 SILVER PDR/AER	GSEFC2837 GSC12133 GSC12130	.56 2.90 2.41	.07 .03 .03	4H 7D 25	66 74 25	AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE
EPON 815/DTA AS 10/1 BW EPOXY	GSEFC2542	1.93	.03	6D	25	AIR	ADHESIVE
EPON 815/TETA AS 10/1 BW EPOXY	GSEFC8423	1.14	.01	4H	66	AIR	ADHESIVE
EPON 815/TETA AS 10/1 BW EPOXY	GSCU9936	.21	.02	7D	25	AIR	CUTTING
EPON 815/U AS 4/1 EW EPOXY	GSEPC3810	.70	.06	3D	25	AIR	ADHESIVE
EPON 815/V 140 AS 3/1.8 BW EPOXY	GSEPC9152	1.07	.10	24H	10	AIR	POTTING
EPON 815/V 140 AS 3/1.8 BW EPOXY	GSEPC3812	.40	.02	4H	60	AIR	CUMP COAT
EPON 815/V 140 AS 5/50 BW EPOXY	GSC11630 GSC12136 GSC12139	.60 2.42 4.68	.06 .08 .41	24H 7D 41	25 25 25	AIR AIR AIR	CUND ADHESIVE
EPON 815/V 140/DTA AS 100/6/6 BW EPOXY	GSC17502	.64	.07	3H	65	AIR	ADHESIVE
EPON 815/V 140/PMS 175-ED AS 50/50/5 BW EPOXY	GSEPC9348	1.65	.03	7D	25	AIR	CARKING LNK
EPON 815/V 140/SILFLAKE 135 AS 5/5/38 BW	GSCU2595	1.84	.08	16H	70	AIR	CUND POTTING
EPON 815/V 140/SILFLAKE 135 AS 5/5/38 BW	GSEPC3811	.43	.06	24H	25	AIR	CUMP COAT
EPON 815/VERSAMID 150 AS 60/40 BW EPOXY	GSEPC3807	1.29	.06	3D	25	AIR	ADHESIVE
EPON 820/TETA AS 10/1 BW CURE 1	GSEPC2541	.36	.04	16H	63	AIR	ADHESIVE
EPON 820/TETA AS 10/1 BW CURE 8	GSEPC2339	.36	.04	48H	25	AIR	ADHESIVE
EPON 825/V 140 AS 7/6 BW EPOXY	GSEFC254	.32	.02	2H	75	AIR	CUTTING
EPON 826/NMA/BDMA AS 100/88.5/1.5 BW EPOXY	GSC10302	.42	.00	2H	93	AIR	ADHESIVE
EPON 826/871/Z AS 100/60/25.4 BW EPOXY	GSCU10535	.64	.01	8H	77	AIR	CUTTING
EPON 827/VERSAMID 140 AS 1/1 BW EPOXY	GSEFC6587	.96	.01	3.5H	60	AIR	ADHESIVE
EPON 828/ALUMINA/V-125/NEHTENDIMINE/ALUMINA	GSEFC4606	.21	.01	3H	71	AIR	ADHESIVE
EPON 828/CAT 951 AS 10/1 BW EPOXY	GSC10215	2.31	.127	24H	25	AIR	COATING
EPON 828/DER 732/AEP/CARBON BLACK EPOXY ADHESIVE	GSEFC1387	1.56	.06	24H	66	AIR	ADHESIVE
EPON 828/DER 732/CAB-O-SIL/AEP	GSEFC2855 GSEFC4002 GSEPC6183	1.46 .75 .77	.06 .04 .06	2H 3D 25	74 41H 65	AIR AIR AIR	CUTTING
EPON 828/EM 308 AS 10/1 BW EPOXY	GSEFC4609 GSEFC4872	10/5/1 10/5/1	.00 .00	1H-5H 1H	100 700	AIR AIR	ADHESIVE CUTTING
EPON 828/LIN DRIE 6/DMP 30 AS 100/50/1 BW EPOXY	GSEFC4902	.04	.00	48H	100	AIR	CUTTING
EPON 828/LIN DRIE 8/DMP 30 AS 100/90/1 BW EPOXY/SAND	GSEFC2397	.50	.01	48H	70	AIR	CUMP COAT
EPON 828/TETA AS 10/1 BW CURE 1	GSEFC2397	.50	.01	3D	63	AIR	ADHESIVE
EPON 828/V AS 10/1 CLEAR EPOXY	GSEFC7046 GSC11633	.38	.00	2D	25	AIR	CUTTING
EPON 828/V 140/AL2C3/PIGMENT MODIFIED BLACK EPOXY	GSEFC7046 GSC11633	1.46	.02	7D	25	AIR	CUND ADHESIVE

MATERIAL	DATA REFERENCE	STYL	ACYM	CURE TIME	CURE TEMP	ADHESIVE APPLICATION
EPON 828/VERSAMID 125 AS 1/1 BW W/3% SI02	GSCF7331	1.06	.02	3H	60	AIR ADHESIVE
EPON 828/VERSAMID 125 AS 100/75 BW EPOXY	GSC10326	.99	.33	16H	82	S-O AIR ADHESIVE
EPON 828/VERSAMID 125 AS 50/50 BW EPOXY	GSC6742	.49	.03	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 125 AS 60/40 BW EPOXY	GSC6745	.46	.03	7D	25	AIR PUTTING
EPON 828/VERSAMID 125 AS 65/35 BW EPOXY	GSC6748	.55	.03	7D	25	AIR PUTTING
EPON 828/VERSAMID 125 AS 66/33 BW EPOXY	GSC6751	.59	.03	7D	25	AIR PUTTING
EPON 828/VERSAMID 125 AS 70/30 BW EPOXY	GSC6754	.74	.19	7D	25	AIR PUTTING
EPON 828/VERSAMID 125 AS 100/20 BW EPOXY	GSC6758	.70	.19	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 30/70 BW EPOXY	GSC6763	.48	.05	4H	71	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 40/60 BW EPOXY	GSC10985	1.63	.16	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 45/55 BW EPOXY	GSCF9518	1.28	.15	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSC10389	.86	.03	7D	25	AIR PUTTING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSC10607	.91	.01	30D	25	AIR COATING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSC10610	1.01	.01	24H	60	AIR COATING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSC10799	1.16	.04	24H	60	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSC11557	.58	.04	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 140 AS 60/40 BW EPOXY	GSEFC6721	.86	.01	7D	25	AIR PUTTING
EPON 828/VERSAMID 140 AS 65/35 BW EPOXY	GSEFC6724	.43	.01	7D	25	AIR PUTTING
EPON 828/VERSAMID 140 AS 66/33 BW EPOXY	GSEFC6727	.30	.00	7D	25	AIR PUTTING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	GSC10392	.19	.00	7D	25	AIR PUTTING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	GSC10613	.24	.00	30D	25	AIR COATING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	GSC10616	.32	.00	7D	25	AIR COATING
EPON 828/VERSAMID 140/B40A MICROMALLIQUINS	GSC1U173	.61	.03	24H	60	AIR PUTTING
EPON 828/VERSAMID 140/CARBOLAC/B-22A BUBBLES	GSEFC1882	1.74	.19	90M	125	AIR PUTTING
EPON 828/VERSAMID 140/CARBOLAC/GLASS BEADS	GSEYC1876	1.80	.49	16H	66	AIR PUTTING
EPON 828/VERSAMID 140/CARBOLAC/SYLOID 620	GSEFC1846	1.67	.12	7D	25	AIR PAINT
EPON 828/VERSAMID 140/CARBOLAC/SYLOID 620	GSEFC1855	1.66	.07	16H	25	AIR PAINT
EPON 828/VERSAMID 140/DTA AS 70/30/1 BW EPOXY	GSC10218	.18	.00	7D	60	AIR COND ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 5/5/20 BW	GSC11138	.81	.03	12H	50	AIR COND ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 5/5/20 BW	GSEFC4880	.50	.04	24H	125	AIR COND ADHESIVE
EPON 828/VERSAMID 140/SR 82 AS 70/30/1 BW EPOXY	GSC10221	.36	.01	7D	25	AIR COND ADHESIVE
EPON 828/VERSAMID 140/SR 82/DETA/MEK	GSEFC4654	4.69	.00	16H	25	AIR COND COAT
EPON 828/VERSAMID 140/SR 82/DIA/TOLUNE	GSCF5927	1.35	.00	1H	60	AIR CONP COAT
EPON 828/VERSAMID 140/SR-82/DETA/TOLUNE	GSPC5839	2.91	.00	8H	60	AIR CONP COAT
EPON 828/VERSAMID 140/T-61 AS 2/3/16 BW MOD EPOXY	GSC11959	.88	.05	4H	60	AIR E-O ADHESIVE
EPON 828/VERSAMID 140/T102 R-90 AS 5/5/0.8 BW	GSEFC8237	.87	.05	7D	25	AIR COATING PRIMER
EPON 828/VERSAMID 140/XYLENE/SIBK	GSEFC6920	.05	.04	7D	25	AIR PUTTING PRIMER
EPON 828/VERSAMID 15/DTA/TIO2 AS 25/27/1.5/40 BW	GSC10224	1.12	.04	7D	25	AIR ADHESIVE
EPON 828/VERSAMID 15/T-80/CAD-O-SIL/RED D SPERSON	GSC11773	.93	.05	7D	25	AIR ADHESIVE
EPON 828/24L-0803 AS 100/35.5 BW EPOXY COATING	GSEFC3217	1.09	.04	1H	25	AIR ADHESIVE
EPON 828/815/140/CARBOLAC/NOVACITE 1250	GSEFC1813	1.72	.10	2H	66	AIR ADHESIVE
EPON 828/815/140/CARBOLAC/NOVACITE 1250	GSEFC1852	1.71	.16	7D	25	AIR ADHESIVE

MATERIAL	DATA REFERENCE	XTCM	NCVCM	CURE TIME	CURE TEMP	ADHS	APPLICATION
EPON 328/871/AEP AS 35/65/15.5 BW	GSPC1014	1.01	.05	2H	42	AIR	POTTING
EPON 828/871/AEP AS 40/60/15.5 BW	GSPC0251	.46	.02	4D	AIR	AIR	POTTING
EPON 828/871/AEP/CAB-U-SIL AS 40/60/15.5/3 BW EPOXY	GSPC0249	1.16	.09	7D	AIR	AIR	KINETIC
EPON 828/871/AEP/CAB-U-SIL AS 40/60/15.5/3 BW EPOXY	GSPC0243	1.24	.01	8H	AIR	AIR	ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	GSPC1393	1.35	.03	4H	64	AIR	ADHESIVE
EPON 929 EPOXY	GSPC177	.92	.02	7D	25	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	GSPC0249	.60	.00	1H	149	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	GSPC0249	.95	.01	7D	25	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	GSPC1417	.29	.01	7D	25	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY w/MEK	GSPC1255	2.87	.02	2H	82	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW w/MEK/MDS2	GSPC1255	2.93	.04	1H	82	AIR	ADHESIVE
EPON 956 A/B AS 100/33 BW w/MEK/HDS2	GSPC1447	2.01	.11	1H	164	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW CARBOLAC/CABOSIL	GSPC1774	.81	.01	7D	25	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW CARBOLAC/NOVACATE 1250	GSPC1817	1.96	.03	7D	25	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW CARBOLAC/SYLOID 620	GSPC1817	1.32	.00	12	160	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW CARBOLAC/CABOSIL	GSPC1759	.88	.01	7D	25	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW MOSS/CARBOLAC/CABOSIL	GSPC13555	.13	.01	4H	175	AIR	COATING
EPOTHERM 180 A/B AS 100/4.5 BW BLACK EPOXY	GSPC1209	1.51	.01	24H	25	AIR	ADHESIVE
EPoxy-Patch Kit 0151 CLEAR EQUAL LENGTHS FR TUBES	GSPC1209	1.96	.02	2H	65	AIR	ADHESIVE
EPoxy-Patch Kit 1051 WHITE EQUAL LENGTHS FR TUBES	GSPC12787	4.81	.02	24H	25	AIR	AIR-SEALANT
EPoxy-Patch Kit 1073 EQUAL LENGTHS FR TUBES	GSPC12388	4.78	.02	24H	95	AIR	AIR
EPoxy-Patch Kit 5051 WHITE EQUAL LENGTHS FR TUBES	GSPC7278	3.34	.02	6H	95	AIR	POTTING
EPoxy-Patch Kit 6068 CLEAR EQUAL LENGTHS FR TUBES	GSPC57099	3.07	.01	24H	25	AIR	AIR-SEALANT
EPoxy Adhesive FCR GROUTINGS - PROPRIETARY	GSPC13098	5.99	.12	24H	25	AIR	ADHESIVE
EPoxy Adhesive FCR REPLICAS GRATINGS - PROPRIETARY	GSPC13108	5.53	.01	24H	80	AIR	ADHESIVE
EPoxy Anti-track Coating	GSPC12775	2.01	.01	24H	25	AIR	COATING
EPOXY FIBERGLASS ECOM CYLINDER	GSPC8681	.20	.05	16H	150	AIR	ADHESIVE
EPOXY 144 A/B AS EQUAL PARTS FROM TUBES	GSPC11039	1.60	.09	30M	11b	AIR	ADHESIVE
EPOXY 220 A/B AS EQUAL PARTS FROM TUBES	GSPC4976	.89	.07	24H	25	AIR	ADHESIVE
EPOXY 730 A/B AS EQUAL PARTS FROM TUBES	GSPC4978	10.42	.07	24H	95	AIR	POTTING
EPOXY 719 PRE-MEASURED MIX PKG	GSPC5256	.97	.02	30H	81	AIR	ADHESIVE
EPOXY 907 A/B AS EQUAL LENGTHS FROM TUBES	GSPC4362	2.25	.06	7D	45	AIR	ADHESIVE
EPoxylite P EPOXY	GSPC2987	3.57	.03	8H	65	AIR	ADHESIVE
EPoxylite P EPOXY	GSPC3045	5.84	.02	72H	25	AIR	ADHESIVE
EPoxylite 6203 A/E AS 2/1 BW EPOXY	GSPC2006	4.45	.03	4H	121	AIR	POTTING
EPoxylite 8712 VAENISH PCLYURETHANE E-160 8 COATS	GSPC4680	8.41	.01	24d	52	AIR	IMPREGNANT
EPoxylite 9653 PCLYURETHANE E-160 8 COATS	GSPC3169	9.15	.01	2H	71	AIR	CURE COAT
EPoxylite 9653 PARSONS BLACK TYPE 3	GSPC3167	4.87	.00	1H	90	AIR	CURE COAT
EPoxylite 9653 PRE PACK EPOXY ADH LOT L101	GSPC1960	12.48	.01	2H	70	AIR	ADHESIVE
EPoxylite 9653 PRE PACK EPOXY ADH LOT L101	GSPC5581	.99	.03	10H	25	AIR	ADHESIVE
EPoxylite 9653 PRE PACK EPOXY ADH LOT L101	GSPC2890	.99	.02	24H	150	AIR	ADHESIVE
ESP 108 GRAY ONE PART EPOXY	GSPC12922	.23	.13	42H	150	AIR	ADHESIVE
ESP 109 GRAY ONE PART EPOXY	GSPC12925	.50	.13	45H	150	AIR	ADHESIVE
ESTAR PHOTOGRAFIC FILM	GSPC12928	.60	.13	45H	150	AIR	ADHESIVE
	GSPC9799	1.26	.00				

MATERIAL	DATA REFERENCE	XTHL	XCVCH	CURE TIME	CURE TEMP	APPLICATION	
ETHAFOAM 220 POLYETHYLENE FOAM 2.2#/CU FT	GSPC6089	.47	.03			PUAM PAD	
ETHAFOAM 400 POLYETHYLENE FOAM 4#/CU FT	GSC0460	.36	.04			INSULATION	
ETHAFOAM 600 POLYETHYLENE FOAM 6#/CU FT	GSC0463	.26	.04			INSULATION	
EUREPOX 710/VERSAMID 140 AS 2/1 BM EPOXY EX 8762 EPOXY DIELECTRIC ADHESIVE	GSPC9401	.24	.04			ADHESIVE	
EXPANDO SLEEVING HE RED HALAN	GSPC9534	.08	.00	1H	160	AIR	
EXPANDO SLEEVING HE WHITE HALAN	GSPC9110	.29	.02			SLEEVING	
EXPANDO SLEEVING PT BLACK POLYESTER	GSPC9113	.19	.06			SLEEVING	
EXPANDO SLEEVING PT WHITE POLYESTER	GSPC9119	.21	.00			SLEEVING	
EXPANDO SLEEVING PT FIBERGLASS SQUARE STRUCTURAL TUBE PA-8/B-5 AS 100/13.5 BM EPOXY	GSPC3081	.85	.04	1H	60	AIR	
GSPC33975	.74	.2		24H	71	AIR	STRUCTURAL ADH POTTLING
FAIRBRENE M5550 CURED	GSPC1334	.90	.79			RUBBER SEALANT	
FAIRBRENE SR5520	GSPC1483	.53	.17			SILICONE	
FAIRBRENE VS0060 BLACK VITON A SHEET	GSPC9802	.35	.01			GASKET-SEAL	
FAIRBRENE VS0060 BLACK VITON A SHEET	GSPC9805	.22	.01			GASKET-SEAL	
FASCAL MARKING PLATES POLYESTER ACRYLIC ADH/R	GSPC3850	1.20	.03			NAMEPLATE	
FASCAL 710 CHROMIZED POLYESTER ACRYLIC ADH/R	GSPC3967	.42	.03			NAMEPLATE	
FASCAL 715 CHROME ETCHIALIZED NYLON/VINYLC ADH/R	GSPC3636	.36	.03			TAPE-FILLED	
PASSON ALUMINUM FOIL/ACRYLIC ADH/VINYL COAT/R	GSPC3297	.93	.03			TAPE	
PASSON TAPE 1 ALUM FOIL/ACRYLIC ADH/R	GSPC3682	1.36	.42	1H	65	AIR	
PASSON TAPE 220 TISSUE PAPER/2 SIDED ACRYLIC ADH/F	GSPC9993	1.43	.01			2 SIDED TAPE	
PASSON TAPE 333 WHITE POLYESTER FILM/R	GSPC3083	2.64	.34			2 SIDE TAPE	
PASSON TAPE 431 BLACK POLYETHYLENE/POLYESTER ADH/F	GSPC9347	2.30	.39			TAPE	
PASSON TAPE 513 SATIN FINISH LABEL WHITE	GSPC2775	5.13	.87			LABEL	
FASTRAPS SERIES 6071 INJECTION MOLDED POLYURETHANE	GSPC5088	2.29	.02			FASTENER	
FASTRAPS SERIES 60560-118 NYLON CABLE TIE	GSPC2969	2.29	.03			CABLE TIE	
FEELT MARKER BLACK 1/4	GSPC9993	2.95	.03			FEELT PAD	
FEELT NICKEL ROCKWELL TYPE 1	GSC0176	15.75	.52	7D	25	AIR	
FEELT NICKEL ROCKWELL TYPE 1	GSC0161	13.61	.04			DARKER	
FEELT TEFLON 30KV WIRE SILVERWELL/PERRACEL 223 TAPE/F	GSPC6782	2.82	.01			FEELT	
FFP 1006 HI-DENSITY POLYETHYLENE GLASS AS 70/30	GSPC6784	2.77	.01			FEELT	
FFP 1006 HI-DENSITY POLYETHYLENE GLASS AS 70/30	GSPC62927	1.12	.03			FEELT INSUL	
FIGEAR OPTIC CABLE CC-100	GSPC2454	.27	.07			FIGEAR OPTIC	
FIGEAR OPTIC CABLE EO30ST - NO SILICONE	GSPC2456	.33	.07			FIGEAR OPTIC	
FIGEBRASS CLOTH PEEL-PWEG A10-10475	GSPC7273	.28	.07			LAMINATE	
FIGEBRASS CLOTH PEEL-PWEG A10-10475	GSPC4726	1.38	.07			LAMINATE	
FIGERITE E-3938 EPOXY	GSPC7139	.23	.03			INSULATION	
FIGERITE E-3938 EPOXY	GSPC2322	.44	.01	10H	149	AIR	
FIGERITE FM 4005 GLASS REINFORCED PHENOLIC	GSC10451	1.60	.00			ADHESIVE	
FIGERITE FM-4005 GLASS REINFORCED PHENOLIC	GSPC4728	2.07	.01			ADHESIVE	
FIGERITE HY-E 1076E EPOXY GRAPHITE LAMINATE	GSPC12379	.50	.00	2H	177	ADHESIVE	
FIGERITE HY-E 11334A EPOXY GRAPHITE LAYUP	GSPC6770	.31	.00			ADHESIVE	
FIGERMAT 1 TYPE 2538 POLYESTER FILM/AQ ADH	GSPC4094	.15	.02			ADHESIVE	
FIGERMAT 1 TYPE 2540 POLYESTER FILM/AQ ADH	GSPC4934	.14	.02			ADHESIVE	
FIGERMAT 1V	GSPC3509	.68	.04			INSULATION	
FIGERTAPE MXC-113 CARBON FIBER MOLDING TAPE	GSPC34458	1.82	.03			BUILDING TAPE	
FINCH BLACK PAINT 663-3-2 POLYURETHANE A/B AS 4/1 BV	GSPC1429	4.62	.10	24H	25	AIR	
FINCH BLACK PAINT 663-3-2 POLYURETHANE A/B AS 4/1 BV	GSPC1432	4.42	.00	16H	66	AIR	

MATERIAL	DATA REFERENCE	ATM KCVCH	CURE TIME	CURE TEMP	ADHES APPLICATION
PINCH PRIMER 463-4-4 A/B AS 3/1 BW	GSEFC8042	7-21	.09	7D	AIR
PLATED N 600 EPOXY/ FIBERGLASS	GSEFC0237	-6.4	.03		PLUMER LAMINATE
PLISHED BLACK COATING 1/3-300 CARBOLAC/MENET 12	GSEFC1198	-5.1	.02	7D	AIR
PLIERS 1 IRRA迪E POLYOLEIN SHRINK TUBING-HEAT GUN	GSEFC7052	1-4.2	.68		SHRINK TUBING
PLIERS 1 KYNAR SHRINK TUBING NEUTRAL - HEAT GUN	GSEFC13269	1-30	.47		SHRINK TUBING
PLEXI-PSD COATED POLYOLEIN SHRINK TUBING	GSC10505	1-51	.69	5H	AIR
PLEXI-PSD COATED POLYOLEIN DUCT HOSE	GSC10200	1-50	.69	5H	AIR
PLEXI-PO 135 BLACK POLYOLEIN SHRINK TUBING	GSC10203	1-73	.22	.01	SHRINK TUBING
PLEXI-PO 135 CLEAR POLYOLEIN SHRINK TUBING	GSEFC4486	1-22	.22		SHRINK TUBING
PLEXASTRIIP FLEXIBLE MIRRING LAMINATE	GSC12316	1-96	.31		LAMINATE
PLEXITAPE TIGL SILICONE RUBBER TAPE NO ADH	GSC11282	1-95	.34	20H	TAPE
PLEXITAPE TIGL SILICONE TAPE NO ADH	GSEFC2841	1-35	.12	20H	TAPE
PLEXITAPE BLACK TAPE NO ADH	GSEFC3942	1-35	.28	25	TAPE
PLEXITAPE 4 OZ ALUM FOIL	GSC12391	15-.38	.11	.51	RAIN
PLEXITAPE 4 OZ ALUM FOIL	GSEFC1936	15-.38	.15	.59	TAPE
PLEXITAPE 4 OZ ALUM FOIL	GSC11962	1-38	.12	.03	FOAM
PLEXITAPE 4 OZ ALUM FOIL	GSC11965	1-65	.16		TAPE
PLEXITAPAS TAPE 2345-1E KAPTON ACRYLIC ADH/F	GSC11983	1-76	.10		2 SIDED TAPE
PLEXITAPAS TAPE 2345-1R KAPTON SILICONE ADH/F	GSEFC0673	1-12	.09		PUTTING
PLEXITAPAS TAPE 2345-1R KAPTON/SILICONE ADH/F	GSC10676	1-59	.09		PUTTING
PLEXITAPAS TAPE 2345-1R KAPTON/SILICONE ADH/F	GSEFC0670	1-59	.09		PUTTING
PLEXOCARBON WIRE INSULATION BLACK	GSEFC1130	1-05	.09		PAINT
PLEXOCOCLAD CLEAR V78VP21	GSEFC0875	1-05	.07	30H	AIR
PLEXOCOCLAD CLEAR V78VP21	GSEFC0878	1-67	.05	30H	AIR
PLEXOCOCLAD WHITE G79WP37	GSEFC1562	1-19	.01	.01	PAINT
PLEXOFILM DF-1200 TEFLON FILA-ACRYLIC ADH	GSEFC1939	1-03	.01		PRESS SENS FILM
PLEXOFILM 389-7 DETA CLOTH/PIPE COATED	GSEFC10691	1-49	.3	.03	INSULATION
PLEXOFILM 389-7 DETA CLOTH/PIPE COATED	GSEFC10692	1-12	.32	.03	OIL
PLEXOFILM 389-7 DETA CLOTH/PIPE COATED	GSEFC10693	1-41	.05	.05	FOAM
PLEXOFILM 389-7 DETA CLOTH/PIPE COATED	GSEFC10694	1-39	.05	.05	PAINT
PLEXOFILM 500 MICA FILM	GSCC10137	1-16	.03		GASKET
PLEXOFILM 500 MICA FILM	GSEFC61227	1-39	.03		TUBING MAT
PLEXOFILM 500 MICA FILM	GSEFC4582	1-53	.16		TUBING
PLEXOFILM 500 MICA FILM	GSC10393	1-43	.27		FILM
PLEXOFILM 500 MICA FILM	GSC10394	1-43	.27		FILM
PLEXOFILM 500 MICA FILM	GSEFC4464	1-92	.22	10H	FILM
PLEXOFILM 500 MICA FILM	GSEFC10745	1-98	.08	.01	FILM
PLEXOFILM 500 MICA FILM	GSEFC3253	1-94	.08	90M	FILM
PLEXOFILM 500 MICA FILM	GSEFC3259	1-81	.03	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3269	1-99	.04	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3369	1-17	.04	30H	FILM
PLEXOFILM 500 MICA FILM	GSC13126	1-82	.02	2H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3491	1-49	.04	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3493	1-87	.06	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3463	1-89	.02	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC4460	1-86	.21	10H	FILM
PLEXOFILM 500 MICA FILM	GSC12316	1-38	.03	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC5801	1-48	.34	1H	FILM
PLEXOFILM 500 MICA FILM	GSEFC3369	1-17	.04	1H	FILM
PLEXOFILM 500 MICA FILM	GSC13126	1-82	.02	2H	FILM
PLEXOFILM 500 MICA FILM	GSEFC4462	1-73	.04	10H	FOAM
PLEXOFILM 500 MICA FILM	GSEFC9578	1-.05	.05	1H	FOAM
PLEXOFILM 500 MICA FILM	GSEFC9581	1-11	.05	12H	FOAM
PLEXOFILM 500 MICA FILM	GSEFC9581	1-11	.05		ADH

MATERIAL	DATA REFERENCE	X _{TMA}	%CVCA	CURE TIME	CURE TEMP	CURE PRESS	ADHESIVE	APPLICATION
FM 40 EPOXY FOAM	GSPC3614	1.00	.05	14	170	PSI	ADH FOAM	
FM 400 SUPPORTED EPOXY FILM ADH GRAY	GSPC6883	1.13	.00	6H	177	PSI	ADH FILM	
FM 400.8 GLASS FIBER/PHENOLIC BLACK	GSC11431	1.49	.02	5H	166	PSI	ADH CPND	
FM 41 EPOXY FOAM SILVER/GRAY	GSC12472	.76	.00	1H	170	PSI	ADH FOAM	
FM 73/DACRON KNIT/SER 127 PRIMER CN FOIL	GSPC9398	.78	.00	1H	120	PSI	COATING	
FM 60-FURF FIBERGLASS BATTING THANE MIL P26514 ETOH WASH	GSC12091	.69	.01	1H	120	PSI	INSULATION	
FOAM CLOSED CELL POLYURETHANE MIL P26514 2#/CU FT	GSPC6998	.84	.00	24H	100	PSI	FOAM	
FOAM CLOSED CELL POLYESTER 2#/CU FT	GSPC6997	.84	.00	24H	100	PSI	FOAM	
FOAM GRAY POLYESTER 2#/CU FT	GSPC6992	1.29	.02	1-2H	170	PSI	DAMPER	
FOAM GR-1-10 94-1 FOLYIMIDE	GSPC8282	.49	.02	1-2H	170	PSI	TERM LOUVER	
FOAM BL-2-17-5-2-3 FOLYIMIDE	GSPC8586	.53	.02	1-2H	170	PSI	TERM LOUVER	
FOAM POLYURETHANE OPEN CELL ROGERS 263	GSPC8567	.94	.03	1-2H	170	PSI	FOAM	
FOAM POLYURETHANE LILSHIRE CHEM	GSPC2983	1.34	.03	1-2H	170	PSI	FOAM	
FOAM POLYURETHANE EB1-00530 ACOUSTICAL	GSPC1094	1.00	.00	1-2H	170	PSI	FOAM	
FOAMPIPE POLYURETHANE CLEAN ROOM WIPE	GSPC0652	.89	.00	1-2H	170	PSI	FOAM	
FOAMPIPE TX704 CLEAN ROOM WIPE ALCOHOL EXTRACTION	GSPC625	.87	.02	1-2H	170	PSI	FOAM	
FORMULATION BIGI POLYURETHANE FOAM FROM AEROSOL	GSPC38925	1.53	.03	1-2H	170	PSI	FOAM	
FORMULATION G80-20 ACETYL/FIBER GLASS AS 80/20 BW	GSCC2459	1.84	.01	1-2H	170	PSI	FOAM	
FORMULATION EPOXY	GSPC12862	2.44	.01	1-2H	170	PSI	FOAM	
FORMULAR MAGNET WIRE COATING 105 DEG C USE	GSPC12862	2.44	.01	1-2H	170	PSI	WIRE COATING	
PORTION ECO31P03 EPOXY FILM ADH UNSUPPORTED	GSPC5292	2.23	.04	1-2H	170	PSI	ADH	
PP 301 SHANK TUEING NEUTRAL	GSPC5449	4.49	.04	1-2H	170	PSI	ADH	
PPC 461 FLUOROCARBON/VINYL COPOLYMER FILM	GSPC5623	4.58	.06	1-2H	170	PSI	SUBSTRATE TUBING	
PPC 461 FLUOROCARBON/VINYL COPOLYMER FILM	GSC11312	.38	.01	1-2H	170	PSI	COATING	
PPC 127 A/E AS 16/1 BW	GSC11315	.24	.01	1-2H	170	PSI	COATING	
PP 127 A/B AS 16/1 BW	GSPC6275	4.37	1.60	1-2H	170	PSI	ADHESIVE	
PP 127 A/B AS 16/1 BW	GSPC6277	4.48	1.98	1-2H	170	PSI	ADHESIVE	
PR 7035 UNSUPPORTED ADH FILM	GSC12290	2.31	.04	1H	25	PSI	ADHESIVE	
PR 7035 LAST-A-FCAP POLYURETHANE HONEYCOMB FILM	GSPC4518	6.97	.01	1H	25	PSI	ADHESIVE	
PR 8136 WA/B AS 2/1 BW LOW DENSITY EPOXY - CREAM	GSPC7169	6.35	.01	1H	25	PSI	ADHESIVE	
PRALOCK T-912 FILM ADH SYSTEM - THERMOSETTING	GSPC13272	2.69	.01	1H	25	PSI	ADHESIVE	
PSP43 CONDUCTIVE CATING	GSPC5755	4.32	.00	1H	25	PSI	PAINT	
PSP49 A/B AS 1/1 BW SILVER FILLED EPOXY	GSPC7115	5.53	.01	1H	25	PSI	COND ADHESIVE	
PSS BLUE PAINT/F	GSC13239	2.53	.02	1H	25	PSI	PAINT	
PSS BLUE PAINT/F	GSC13242	.71	.05	1H	25	PSI	PAINT	
PULLER 171-A-152 ALUMINUM SILICONE PAINT	GSPC3149	3.29	.73	24H	96	PSI	COATED PAINT	
PULLER 404 ACETAL TEFILON 80/20	GSPC2843	3.53	.01	1H	25	PSI	COATING	
PJ RAN 3633-40 GLASS/ALUMINUM CARBON FILLED EPOXY	GSPC6386	3.74	.00	6H	149	PSI	ADH CPND	
F5-1100 CONTROLLED VOLATILITY FLUID	GSPC2032	.07	.00	1H	25	PSI	SILICONE FLUID	
F5-1105 CONTROLLED VOLATILITY FLUID	GSPC2035	.05	.00	1H	25	PSI	SILICONE FLUID	
F5-1107 CONTROLLED VOLATILITY FLUID	GSPC2053	.11	.06	1H	25	PSI	SILICONE FLUID	
F8/C2/P88CPL AS 13/10 BW	GSPC6330	3.09	.97	24H	25	PSI	ADHESIVE	
G 1033 TAPE ALUM KAPTON/SILICONE ADH/R	GSPC3684	1.48	.32	1H	25	PSI	TAPE	
G 143600 THERMAL CONTROL FILM LAMINATE	GSC11702	1.18	.07	1H	25	PSI	TERM CONTROL	
G 3113 BLACK COATING DALL CHEM ALKYD-SILICONE	GSPC3910	1.37	.16	1H	25	PSI	PAINT	
G 400201 TAPE ALUM INIZED TEFLON/1966 ADH/F	GSPC7226	.37	.02	1H	232	PSI	TAPE	
G 401500 SILVERED TEFLOON FILM	GSPC9281	.30	.00	1H	25	PSI	TAPE	
G 4019 TAPE PTFE FILM/METALIZED/ACRYLIC ADH/R	GSPC4152	.33	.48	48H	125	PSI	2 SIDED TAPE	
G 405900 TAPE VDA 2 SIDES KAPTON FILM/SR 585 ADH/F	GSPC7442	.33	.48	48H	125	PSI	2 SIDED TAPE	

MATERIAL	REFERENCE	XTCM	XCVCA	CURE TIME	CURE TEMP	AIRHS	APPLICATION
G 406400 TAPE AU CCATED KAPTON/ACRYLIC ADH/F	GSC12343	.75	.01				TAPE
G 406405-020 TAPE KAPTON/AU METALIZED Y966 ADH/F	GSCC934	1.06	.32				TAPE
G 40710 TAPE ALUMINIZED KAPTON/SILICONE ADH/F	GSC1833	1.98	.38				2 SIDED TAPE
G 410310 TAPE ALUMINIZED KAPTON/2 SIDE SILICONE ADH/F	GSC12346	1.45	.53				TAPE
G 413310 TAPE ALUMINIZED KAPTON/SILICONE ADH/F	GSC10239	2.44	.53				TAPE
G 1897 HT ALUMINUM COATING	GSCFC3638	3.09	.04	1H	232	A&R	PAINT
G-3230 ALKYD WHITE PAINT	GSCFC3395	3.13	1.07	24H	25	A&R	PAINT
G-40100 TAPE/S	GSCFC2179	.94	.12				PAINT
G-6401 INSULGREASE FEAT TRANSFER	GSCFC0413	.16	.07				PAINT
G-6412 THERMAL GREASE	GSCFC8453	.56	.38				PAINT
G-9042 THERMAL GREASE - WHITE SILICONE	GSCFC8699	.55	.05				PAINT
G-9052 ELEC CONDUCTIVE GREASE - BLACK SILICONE	GSCC2100	.52	.01				PAINT
GA-2 A/B AS 1/1 BW EPOXY CEMENT	GSCFC2103	2.48	.01				PAINT
GAGEKOTE 1 STRAINAGE ADH AND COATING	GSCFC0839	8.12	1.40	48H	25	A&R	ADH-COATING
GA-BUR CLEAR	GSCC1660	.07	.01	120	25	A&R	ADH-COATING
GA-BUR YELLOW	GSCC1663	.10	.02				ADH-COATING
GABELOCK 201 A/B AS 1/1 BW EPOXY	GSCFC1501	4.70	.02				ADHESIVE
GASKET AMP RF-SMA CONNECTOR RED SILICONE	GSCFC5915	.14	.02				ADHESIVE
GASKET AMP RF-SMA CONNECTOR WHITE SILICONE	GSCFC5918	.04	.02				ADHESIVE
GE 1147 NEUTYL ALKYL SILICONE LUBE OIL	GSCFC2420	4.28	2.41				JACKET
GE 4098 ADHESIVE CLEAR	GSCFC4840	3.52	.03	10H	25	A&R	ADHESIVE
GE 4524W SILICONE	GSCFC9957	.52	.18	25H	160	A&R	ADHESIVE
							ADHESIVE
GE 7031 INSULATING VARNISH - PHENOLIC	GSPC8876	8.75	.05	8H	121	A&R	VARNISH
GE 7031 INSULATING VARNISH - PHENOLIC	GSPC8924	6.07	.71	1H	120	A&R	VARNISH
GE LYA MP SOL RA 263/ACRYLIC PRES SENS ADH	GSPC1867	.79	.08	724	85	A&R	ADHESIVE
GE LYA MP SOL RA 263/ACRYLIC PRES SENS ADH	GSPC1921	.62	.03	24H	25	A&R	ADHESIVE
GE LYA MP SOL RA 657/ACRYLIC PRES SENS ADH	GSPC1864	1.35	.31	7D	96	A&R	ADHESIVE
GE LYA MP SOL RA 657/ACRYLIC PRES SENS ADH	GSPC1918	1.12	.04	24H	25	A&R	ADHESIVE
GE LYA MP SOL RA 784/ACRYLIC PRES SENS ADH	GSPC1861	1.55	.19	7D	66	A&R	ADHESIVE
GE LYA MP SOL RA 784/ACRYLIC PRES SENS ADH	GSPC1897	1.05	.05	24H	25	A&R	ADHESIVE
GE LYA MP SOL RA 858/ACRYLIC PRES SENS ADH	GSPC1858	1.25	.38	7D	66	A&R	ADHESIVE
GE LYA MP SOL RA 858/ACRYLIC PRES SENS ADH	GSPC1894	1.02	.02	24H	25	A&R	ADHESIVE
GENCHERM 3010 THERMCST POLYIMIDE	GSPC1927	.34	.02				ADHESIVE
GENEFUXI 185/VERSAMID 115 AS 1 BW EPOXY	GSPC4622	.35	.02	16H	25	A&R	ADHESIVE
GENEPOXY 190 / VERSAMID 140 AS 3/2 BW AMBER EPOXY	GSPC7262	.24	.01	12H	96	A&R	ADHESIVE
				2H	60	A&R	ADHESIVE
GENNORTHERN D10B UNPLASTICIZED PVC FILM CLEAR	GSPC5995	.12	.01				FILM
GENNORTHERN HT UNPLASTICIZED PVC FILM CLEAR	GSPC5697	.23	.03				FILM
GENNORTHERN NILS UNPLASTICIZED PVC FILM CLEAR	GSPC5999	.63	.05				FILM
GENNORTHERN HTLS UNPLASTICIZED PVC FILM WHITE	GSPC5501	.38	.02				FILM
GENNORTHERN US 1002 UNPLASTICIZED PVC FILM CLEAR	GSPC5503	.21	.02				FILM
GENNORTHERN US 3003 UNPLASTICIZED PVC FILM CLEAR	GSPC5705	.50	.02				FILM
GEVAC VAC SEALANT	GSPC5672	12.08	1.41	24H	65	A&R	SEALANT

MATERIAL	DATA	XTHL	RCVCH	CURE TIME	CURE TIME	ATMOS	APPLICATION
SE VAC VAC SEALANT 2 POLYSULFONE FIBER GLASS AS 70/30	GSPC0673 GSPC0948	2.82 -2.4	1.54 -0.9	7D	25	AIR	SEALANT GOLD CPND
GFRP TUBE 1006-4 EPOXY FILM ADHESIVE AS 2/1 BW EPOXY	GSPC5543 GSPC12907	-6.8 1.07	-0.01 -0.01	1H 21D	177 25	PSI AIR	STRUCTURAL ADHESIVE
GLASS CLOTH TAPE 134	GSPC4466	-1.18	-0.03				CLOTH TAPE
GLASS CLOTH 1620 - SMALL WEAVE	GSPC7727	-1.23	-0.08				INSULATION
GLASS/POLYESTER 195/50/857 SQUARE MESH COATED WHITE	GSPC7722 GSPC10808	-2.23 -5.4	-0.05 -0.05				STRUCTURAL
GOODYEAR GRAPHITE FIBER EPOXY COMPOSITE	GSPC0996	-5.55	-0.04				ELEX WIRING
GOODYEAR GRAPHITE FIBER EPOXY COMPOSITE/FM 1000	GSPC1171	-0.21	-0.01				CLOTH
GOORE-TEX CARBON 810 FTE RIBBON CABLE	GSPC13278	-0.05	-0.01				INSULATION
GOORE-TEX CARBON LOFD EXPANDED TEFILON - GRAY	GSPC7688	-1.08	-0.09				STRUCTURAL
GOORE-TEX DOPED TIO2/CARBON AS 9/1BW - GRAY/WHITE	GSPC7703 GSPC9032	-0.02 -0.02	-0.03 -0.03				DAMPER
GOORE-TEX MICRO WAVE CABLE INNER INSULATION WHITE	GSPC9035	-0.04	-0.04				CABLE INSUL
GOORE-TEX MODIFIED TOPED WITH CARBON - BLACK	GSPC7691	-0.10	-0.01				DAMPER
GOORE-TEX PAPEL TEFILON CABLE INSULATION 3 PLY	GSPC12475	-0.03	-0.01				CABLE INSUL
GRAPHITE FIBER HEATING CABLE INSULATED HERCULES 2002A	GSPC4220	-0.48	-0.01				STRUCTURAL
GROMMET BLACK RUBBER MIL G3036	GSPC1270	10.85	4.82	6H	149	E-4	GROMMET
GROMMET FR JOSSEN RUBBER SILICONE CPND S1817	GSPC4132	-3.4	-0.02				GROMMET
GROMMET JASPER 1116	GSPC5765	13.51	6.85				GROMMET
GROMMET 1042-60 EUROPEAN SBR COMM GRADE RUBBER	GSPC4268	11.92	6.61	7D	25	AIR	PAINT
GSPC 657-38 SILICONE WHITE PAINT	GSPC2425	-1.13	-0.01				PAINT
GSPC 657-41 SILICONE WHITE PAINT	GSPC2143	-1.17	-0.01				PAINT
GSPC 657-41 SILICONE WHITE PAINT	GSPC2176	-1.14	-0.01				PAINT
GSPC 657-42 SILICONE WHITE PAINT	GSPC2161	-2.1	-0.08	4D	96	AIR	PAINT
GSPC 657-44 SILICONE WHITE PAINT	GSPC2182	-1.5	-0.07				PAINT
GT 100 TAPE NYLAR COMPOSITE AS NYLAR	GSPC4130	-2.05	-0.08	20H	100	AIR	TAPE COMPOSITE
GT 100 TAPE TWO SIDED HEAT SEALING POLYESTER FILM	GSPC2779	2.06	-0.15				TAPE-FILM
GT 300 TAPE ONE SIDE HEAT SEALING POLYESTER FILM	GSPC2761	-0.26	-0.16				TAPE
GT 400 TAPE SCHJELLIAN POLYESTER/POLYESTER A/B 2 SIDE	GSPC3513	-0.63	-0.12				2 SIDED TAPE
GT 550 TA/COPPER FACILE ALUMINATE ONE SIDE	GSPC4972	-0.55	-0.04				LAMINATE
GY-70/4-33 GRAPHITE EPOXY COMPOSITE	GSPC7379	-0.46	-0.01	2H	177	AIR	LAMINATE
GY-70/5208 GRAPHITE EPOXY COMPOSITE	GSPC8426	-0.53	-0.01	24H	25	AIR	MARKING MTL
GY-70/5209 GRAPHITE EPOXY COMPOSITE	GSPC8977	-0.49	-0.01	24H	25	AIR	MOLD CPND
HANCOCK 1355 RAVEN BLACK ODAQUE COATING/P	GSPC7497	16.85	-0.01				WEEATHER
HATHANE 1602-BUD A/B AS 2/1 BV URETHANE	GSPC7415	1.16	-0.02	24H	25	AIR	WEEATHER
HATHANE 1602-BOD A/B AS 2/1 BV URETHANE	GSPC7445	-0.72	-0.01	24H	60	AIR	WEEATHER
HAVE VEG FR-1 SILYLE 3239 WHITE SILICONE WIRE INSUL	GSPC9530	1.36	-0.02	24H	190	AIR	WIRE INSUL
HAVE VEG FR-1 SILYLE 3239 WHITE SILICONE WIRE INSUL	GSPC6545	-0.86	-0.03	22H	25	AIR	WIRE INSUL
HE 10 OPTICAL ASSEMBLY CEMENT A/B AS 93/7 BW	GSPC4632	18.69	-0.01	48H	25	AIR	OPTICAL CEMENT
HE 79 OPTICAL CEMENT A/B AS 100/2.5 BW	GSPC13484	19.11	-1.27	7D	25	AIR	OPTICAL CEMENT
HE 80 OPTICAL CEMENT A/B AS 100/2.5 BW	GSPC5899	19.87	1.66	7D	25	AIR	OPTICAL CEMENT
HEATER KAFTON 15 Q-9485	GSPC6212	-0.16	-0.00	24H	125	E-6	WEATER
HEATER LIN 269-2C	GSPC9203	-0.02	-0.01	8H	205	AIR	WEATER
HEATING TAPE CLAYECRN LABS A-16-2 DC 282 SILICONE/F	GSPC6923	-0.1	-0.01	20H	125	E-7	HEAT TAPE
HEATING TAPE CLAYECRN LABS A-16-2 DC 282 SILICONE/F	GSPC7643	-0.1	-0.01	48H	155	E-1	HEAT TAPE
HEATING TAPE CLAYECRN LABS D-16-2 DC 282 SILICONE	GSPC6968	-7.4	-4.2	140	150	E-3	HEAT TAPE
HEATING TAPE CLAYECRN LABS DC 282 SILICONE	GSPC4100	-4.6	-2.5	24H	150	AIR	HEAT TAPE
HEATING TAPE CLAYECRN LABS F-16-2X DC 282 SILICONE	GSPC7836	-1.5	.08	30H	150	E-2	HEAT TAPE

MATERIAL	DATA REFERENCE	XTHL	XCVd	CURE TIME	CURE TEMP	ATMOS	APPLICATION
HEATING TAPE CLAYBORN LABS H-16-2X DC 282 SILICONE	GSPC7859	.97	.93	4.8H	155	E-Z	HEAT TAPE
HEATING TAPE CLAYBORN LABS 1 COAT IN 6-1104	GSPC4290	.73	.29			COATED HEAT TAPE	
HEATING TAPE CLAYBORN LABS 2 COATS IN 6-1104	GSPC4292	.85	.17	100H	45	AIR	COATED HEAT TAPE
HEATING TAPE-CLAYBORN LABS DC 280A ADD	GSPC3586						ADHESIVE TAPE
HELI-TUBE HT 1/8-N	GSPC4156	3.35	.72				TAPE WRAP
HEXA-BOND 1 EPOXY FILM ADHESIVE	GSPC4156	1.40	.39				TAPE ADHESIVE
HEXA-BOND 3 A/B AS 100/19.7 BW	GSPC9623	1.40	.18				ADHESIVE
HEXACEL F153 EPOXY FILM ADHESIVE UNSUPPORTED	GSPC9155	1.23	.26				FILM ADHESIVE
HEXACEL F174-120 GLASS CLOTH/POLYIMIDE PRE PREG 7 CURE	GSPC2711	.49	.09				LAMINATE
HF 106 NYLON 1/1 GLASS AS 10/30	GSPC5425	1.37	.92				WLD CPND
HI-VAC GREASE 970V SILICONE	GSPC2833	1.52	.34				LUBRICANT/GREASE
HIGH K-707-L9	GSPC6556	.73	.22				ELECTRIC/GREASE
HIGH TEMP 221 MAGNET WIRE COATING	GSPC9829	.07	.00				WIRE COATING
HL 155-55-1/2 AS 4/1 IN ACRYLIC COATING	GSPC8879	.53	.15				WIRE COATING
HN 7 LINEAR POLYESTER LAMINATE	GSPC4057	6.32	.03				CONF COAT
HONEYCAB POLY 176/34 EPOXY/GRAPHITE *FM73M ADH	GSPC8894	2.99	.06				STRUCTURAL
HONEYCAB SPECIAL COMPOSITES EPON 826/FIBERGLASS/PLUS	GSPC5885	1.62	.01				DONEYCAB
HOSE SAE 100R5 BLACK RUBBER WT POLYETHYLENE	GSPC1029	3.13	.41				WLD CPND
HRH-10 NYLON GUR HIGH TOLL CLOTH HONEYCOMB COAT	GSPC0055	2.74	.02				HONEYCOMB
HS 101 BLACK POLYCYCLIC SUBINK TUBING HEATGUN SHRINK	GSPC7979	2.50	.84				SINK TUBING
HS 50/VAROXB RUBBER ADDITIVES BLUE CONNECTION INSUL	GSPC9990	2.79	.30				CONN INSUL
HS 50/VAROXA RUBBER ADDITIVES BLUE CONNECTION INSUL	GSPC9044	.12	.01				CONN INSUL
HS 50/VAROXA RUBBER ADDITIVES BLUE CONNECTION INSUL	GSPC9047	.13	.01				CONN INSUL
HS 5430 EPOXY PHENOLIC FILM ADHESIVE	GSPC6491	1.88	.11				ADHESIVE
HT-424 PASTE - OLIVE GREEN A/F AS 1/1 BW POLYURETHANE	GSPC8483	.72	.32				FILM ADHESIVE
HUMISEAL X-381V A/F AS 1/1 BW POLYURETHANE	GSPC8642	21.66	.89				ADHESIVE
	GSPC3971						CONF COAT
HUMISEAL 1A20 POLYURETHANE	GSPC2895	2.58	.02				CONF COAT
HUMISEAL 1A27 AEROSOL/F	GSPC3679	8.66	.7D				CONF COAT
HUMISEAL 1A33 POLYURETHANE	GSPC2821	8.54	.24				CONF COAT
HUMISEAL 1A33 POLYURETHANE	GSPC2991	4.98	1.30				CONF COAT
HUMISEAL 1E12 ACRYLIC	GSPC3673	1.78	.00				CONF COAT
HUMISEAL 1E12 ON SCREEN	GSPC2155	6.89	.18				CONF COAT
HUMISEAL 1E15 ACRYLIC	GSPC2971	9.38	.02				CONF COAT
HUMISEAL 1E20 ACRYLIC	GSPC2475	16.04	.06				CONF COAT
HUMISEAL 1E31 ACRYLIC FREE FILL	GSPC2154	3.80	.02				CONF COAT
HUMISEAL 1B31 ACRYLIC ON FOIL	GSPC5127	9.74	.01				CONF COAT
HUMISEAL 1B31/ACRYLIC AS 1/2 BV ACRYLIC 1 HR 25C/COAT	GSPC5901	11.81	.07				CONF COAT
HUMISEAL 2A52LU A/F AS 1/1 BY EPOXY	GSPC1011	3.27	.14				CONF COAT
HUMISEAL 2A53 A/F AS 1/1 BV AND EPOXY COATING	GSPC2907	1.94	.03				CONF COAT

MATERIAL	DATA SHEET NO.	REFERENCE	XIVC/N	CURE TIME	CURE TEMP	ATMOS	APPLICATION
HUMISEAL 2A56 A/E AS 1/1 BV POLYURETHANE	GSFPC2953	12-73	.16	24H	25	AIR	CUNP COAT
HUMISEAL 2A72 A/E AS 1/1 BV FLUORESCENT POLYURETHANE	GSFPC6774	8-63	.02	40D	85	AIR	CUNP COAT
HUMISEAL 2A72 A/E AS 1/1 BV FLUORESCENT POLYURETHANE	GSFPC6776	9-38	.02	8H	66	E-O	CUNP COAT
HUMISEAL 2B13LJ/2B13 AS 100/2 BN EPOXY	GSFPC1026	14-80	.47	16H	66	E-O	CUNP COAT
HUMISEAL 2B74 A/B AS 100/85 BN POLYURETHANE	GSFPC9963	1-12	.05	24H	60	AIR	POTTING
HK-1009 LAMINATING FILM	GSFPC3085	1-10	.00	134	215	AIR	ADHESIVE FILM
HK-1009 ADHESIVE FILM	GSFPC1771	3-83	2-00	14	149	AIR	ADHESIVE
HY-MAT 7534 MOLDED GRAPHITE/EPOXY	GSFPC6326	4-7	.00	3H	177	PSI	POTTING
HYDANTOIN TC-1-149-1 LIGHT GRAY EPOXY	GSFPC8993	.36	.00	16H	135	AIR	POTTING
HYDRIN RUBBER EPICHLOROHYDRIN-ETHYLENE OXIDE	GSFPC3949	1-22	.13				RUBBER
HY-SHELL ST 91000 POLYOLEFIN PLASTIC SHUNK	GSFPC3927	-61					SURLINK TUBING
HY-SOL 0025 A/B AS 1/1 BN	GSFPC3940	-63					POTTING
HY-SOL 11C A/B AS 1/1 BN EPOXY	GSFPC3073	-63					ADHESIVE
HY-SOL 2C A/B AS 25/11 BN BROWN EPOXY	GSFPC5091	-85					ADHESIVE
HY-SOL 4326/3421 AS 100/6 BN	GSFPC4982	1-17					ADHESIVE
HY-SOL 6C A/B AS 1/1 BN ALUM FILLED EPOXY	GSFPC3049	1-42					COND ADHESIVE
HY-SOL 6C A/B AS 12/4-6 BN ALUM FILLED EPOXY	GSFPC3049	1-55					COND ADHESIVE
HYTREL 4055 POLYESTER/ANTISTATIC/OXIDANT	GSFPC472	-22					ELASTOMER
IC-2 POLYURETHANE COATING	GSFPC3267	-59					CUNP COAT
IMPALENE TUBING STABILIZED POLYPROPYLENE	GSFPC2609	.29					TUBING
IMPAX SEMI-DIIMID POLYMER - NITROAL	GSFPC6470	18-48					STRUCTURAL
INSTA-FOAM 2# / CUPRUM CELLULOSE NITRATE AND SOLVENT	GSFPC4938	10-10					COAT
INSULATION BLANKET MULILAYER	GSFPC2428	6-1					COAT
INSULATOR MOLDED MIL 620693	GSFPC6230	2-47					INSULATION
INSULATOR 10230-LAF POLYURETHANE COATING	GSFPC2290	4-4					INSULATOR
INSULBOND 810/INSULCURE 24 AS 4/3 BN BLACK EPOXY	GSFCL12805	1-22					CUTTING
INSULSTRUC P5003-FR22 GLASS FILM THERMOSET POLYESTER	GSFCL12442	1-56					ENCAPSULANT
INSULTEK 445 URETHANE DIELECTRIC	GSFCL325	.38					DELECTRIC
INTERFACIAL SEAL SILICONE UC-K-1314	GSFPC1792	.40					SEAL
INTERFACIAL SEAL SILICONE UC-K-1314	GSFPC1795	.41					SEAL
IR-9 BLACK PVC TAPE NO ADH	GSFCL3263	4-69					TAPE
ISO-CHEM-BE2 1251LV/12H AS 25/2 BN THEM COND EPOXY	GSFCL31612	2-42					INTER COATING
ISOLEX A-65 ACRYLIC COATING SYSTEM/F	GSFCL2238	5-82					COATING
ISOMEG ED 129/ED 1CO 4S 1/1 BN	GSFCL593	5-82					CUNP COAT
ISOMID POLYESTER/FCLYIMIDE COATING	GSFCL0081	5-44					CUNP COAT
ISONEL 200 MAGNET FIRE COATING BROWN 180C USE 12 MIL	GSFCL4292	35					WIRE COATING
ISONEL 200 MAGNET FIRE COATING BROWN 180C USE 18 MIL	GSFCL4604	18					WIRE COATING
IT CONNECT 67929 DBM-258 BLUE/GREEN HOLD INSERT	GSFCL201	55					CUNP INSUL
JF 1004 POLYETHERSULFONE/GLASS AS 80/20 BN	GSFCL0227	59					DULD CPND
JF 1006 CHLORONATED POLYETHER GLASS AS 70/30	GSFCL2929	64					DULD CPND
JOINT COMPOUND SOCCN MOBIL 1000/40 BN BLACK	GSFCL19242	49					GLUE CPND
K-1 URETHANE PRIMER/S FURANE PLASTICS	GSFCL5142	3-49					SEALANT
K-10 ADHESIVE	GSFCL3366	9-10					PRIMER
K-16 A/B AS 3/1 BN CONDUCTIVE EPOXY	GSFCL6892	1-92					ADHESIVE
K-20 A/B AS 10/7 BN EPOXY	GSFCL4506	7-43					COND ADHESIVE
	GSFPC2443	7D					CUNP COAT

MATERIAL	DATA REFERENCE	RTM TIME	%CVM	CURE TIME	CURE TEMP	ADHES S	APPLICATION
KALREZ 1050 PERFLUOROELASTOMER	GSC11351	-44	.00				WING FILM
KALREZ 3018 PERFLUOROELASTOMER	GSPC11354	-40	.18				WING FILM
KAPTON PEP FILM 40CF022	GSPC21354	-31	.21	90M	302	AIR	WIRE INSUL
KAPTON PEP FILM 40CE022	GSPC21354	-25	.04	1h	190	AIR	WIRE INSUL
KAPTON FILM 40CL022	GSPC21354	-65	.04	24h	100	B-5	WIRE INSUL
KAPTON FILM - ALUMINIZED W/MM 467 ADH/F	GSPC31359	-80	.14				WIRE INSUL
KAPTON FILM FILM REINFORCED	GSPC31359	-46	.14				WIRE INSUL
KAPTON FILM FILM 104	GSPC51359	-42	.05	24h	150	AIR	WIRE INSUL
KAPTON FILM 5 MIL	GSPC51359	-77	.02				WIRE INSUL
KAPTON FILM/LINOLEUM BETA MARQUISSETTE GLASS CLOTH	GSPC51359	-13	.01	24h	150	AIR	WIRE INSUL
KAPTON TAPE 03-1 SILICONE ADHESIVE/F	GSPC81357	-150	.01				WIRE INSUL
KAPTON TAPE 603A ACRYLIC ADH/F	GSPC01359	-52	.12				WIRE INSUL
KAPTON TAPE 600-1/20 EPOXY-REX	GSPC01359	-52	.00				WIRE INSUL
KAPTON TAPE COATED 473-1/24 BRAND-REX	GSPC01359	-52	.00				WIRE INSUL
KAPTON TAPE CONN SITE	GSPC13248	3-08	.63	15M	125	AIR	WIRE INSUL
KAPTON TAPE CONN SITE	GSPC13248	3-08	.63	15M	125	AIR	WIRE INSUL
KAPTON TAPE H322/9588 FILM COMPOSITE	GSC113251	2-15	.22	15M	125	AIR	WIRE INSUL
KAPTON/ALUM/H322/9588 FILM COMPOSITE	GSC113254	2-33	.25	15M	125	AIR	WIRE INSUL
KAPTON/ALUMINIZED/CHENILLE H322 FILM	GSC112808	5-01	.03	15M	25	AIR	WIRE INSUL
KAPTON/ALUMINIZED/CHENILLE H322 FILM	GSC112811	1-43	.17	4h	125	AIR	WIRE INSUL
KAPTON/DACRON MESH BONDED PROPRRIETARY ADHESIVE	GSC113219	1-33	.13				WIRE INSUL
KOI PYROFILM PVC 7C KLD RESISTOR COATING MIL-T-129092	GSC113198	1-14	.17				WIRE INSUL
KODIAK TAPE 262 FIBERGLASS/SILICONE ADH/S	GSPC11972	2-31	1-10				WIRE INSUL
KENDEL TAPE 293 FIBERGLASS/SILICONE ADH/S	GSPC11975	2-79	1-10				WIRE INSUL
KENDEL TAPE 294 FIBERGLASS/ACRYLIC ADH/R	GSPC41021	1-33	.00	45d	121	P-1	WIRE INSUL
KENDEL TAPE 120/NARECO 8517 STRUCTURAL COMPOSITE	GSPC81645	1-33	.00	2.5h	177	P-1	WIRE INSUL
KEVLAR 29 YELLOW FIBERS	GSC101119	3-13	.19				SKIN
KEVLAR 49 COMPOSITE KEVLAR 49 FABRIC/CORLAR 5143 RES	GSPC51821	1-68	.00				SKIN
KEVLAR 49/FR 8601 FESIN PRE-PREG	GSPC51265	4-51	2-00	2H	127	P-2	SKIN
KP 1006 ACETAL/GLASS AS 70/30	GSPC21265	4-27	2-01	2H	127	P-2	SKIN
KPL 4936 ACETAL/30% GLASS/15% TFE	GSPC21291	3-26	0-02				STRUCTURAL
KPL 4936 ACETAL/30% GLASS/15% TFE/SILICONE	GSPC51519	3-35	0-02				STRUCTURAL
KIMPOL 8 GAUGE PVCYCARBONATE	GSPC31355	1-16	0-00				SUSULATION
KIRKHILL SILICONE SPONGE RUBBER	GSPC31368	2-23	0-13	24h	177	AIR	SUSKEI
KIRKHILL SILICONE SPONGE RUBBER	GSPC41318	1-50	0-13				SUSKEI
KIB CYCLOCAC BLUE 5000 SERIES FIRE RETARDANT	GSPC91185	1-06	0-01	30			WIRE GUIDE
KIB CYCLOCAC PINK 5000 FIRE RETARDANT	GSPC51185	0-81	0-01	2H	127	P-2	WIRE GUIDE
KL 450 ACETAL/20% SILICONE	GSPC51517	1-53	0-01				STRUCTURAL
KL EEN-STIK DUBL-SLIK 2 SIDED TAPE/F	GSPC51517	13-15	3-09	3-09			STRUCTURAL
KODALITH ORTHO FILE TYPE 3	GSPC51797	1-108	0-00				STRUCTURAL
KOLOANE U-1-6002/5500 PRIMER - GLOSS WHITE ENAMEL	GSPC121178	1-50	0-13	24h	25	AIR	PAINT SYSTEM
KRYLON 1102 CLEAR COATING MULTICOAT	GSPC31397	7-23	0-02	24h	25	AIR	PAINT
KRYLON 1602 ULTRA CLAT BLACK PAINT	GSPC31397	7-23	0-02	7D	25	AIR	PAINT
KRYTOX 143 AB LUBRICATING OIL DEVOLAT 93C	GSPC11141	28-93	12-93				PAINT
KRYTOX 143 AB FLUOROKAHL POLYETHER LUBRICATING OIL	GSPC21315	28-94	12-93				PAINT
KRYTOX 240AC FLUOROCARBON GREASE (143AC OIL/TEFLON)	GSPC61980	3-72	3-07				PAINT
KY-NAR SHRINK TUBING MIL 123053/8 HEAT GUN SHINK	GSPC71463	3-39	0-04	25M	260	AIR	SHINK TUBING
KY-NAR SOLDER SLEEVE SEALING SLEEVES VINYL CARBON INSERTS	GSPC81589	3-67	0-07				SHINK TUBING
KY-NAR SOLDER SLEEVE WITH POLYETHYLENE SLEEVES SHEKNU	GSPC21673	3-56	0-14				SHINK TUBING
KY-NAR SLEEVE WITHOUT POLYETHYLENE RINGS	GSPC10925	3-44	0-07				SHINK TUBING
KY-NAR SLEEVE WITH RED	GSPC21673	3-07	0-07				SHINK TUBING
KY-NAR SLEEVE INSULATION 25/4 BW EPOXY	GSPC61926	3-32	0-00	24h	25	AIR	SHINK TUBING
KY-NAR SLEEVE INSULATION 25/4 BW EPOXY	GSPC91984	3-32	0-00				SHINK TUBING

MATERIAL	DATA REFERENCE	XTEL	XCYC	CURE TIME	CURE TEMP	ATMOS	APPLICATION
LABEL MARKING LABEL PRESSURE SENSITIVE FILM/F	GSC12073	5.36	2.12				LABEL
LACING CORD A-90-X NYLON	GSFC 2799	.93	.11				CORD
LACING CORD D-40-OF17CW - WHITE	GSFC1516	3-24	.76				CORD
LACING CORD 50D-OF17CW - BLACK	GSFC2989	1-30	.54				CORD
LACING CORD GDELACE 20 BLACK	GSFC2960	8-47	.55				CORD
LACING CORD LC-116	GSFC5337	8-36	3-36				CORD
LACING CORD LC-162	GSFC5337	2-27	.95				CORD
LACING TAPE A-60-N NYLON	GSFC1537	1-383	.42				LACING TAPE
LACING TAPE A-60-N POLYESTER	GSFC1537	1-388	.64				LACING TAPE
LACING TAPE DABURN 2047 DACRON - COATED	GSFC1537	1-555	.28				LACING TAPE
LACING TAPE DABURN 2047-D-OFA - WHITE	GSFC1537	1-33	.08	24H	125	AIR	LACING TAPE
LACING TAPE E 775-476 TFE TEFLON/GLASS METOH WASH	GSFC5369	1-97	.04				LACING TAPE
LACING TAPE E 779-1075 TFE TEFLON/GLASS	GSFC5369	0-97	.02	1H	100	AIR	LACING TAPE
LACING TAPE E 779-222 TFE TEFLON/GLASS	GSFC5369	1-70	.25				LACING TAPE
LACING TAPE E 779-303 TFE TEFLON/GLASS	GSFC5369	1-42	.46				LACING TAPE
LACING TAPE E 779-680 TFE TEFLON/GLASS	GSFC5369	1-09	.26				LACING TAPE
LACING TAPE FIBERGLASS/TEFLON - WHITE	GSFC5369	1-098	.26				LACING TAPE
LACING TAPE PYR-LACE-A 21DR DACRON/VINYL IMPREG	GSFC5369	1-27	.26				LACING TAPE
LACING TAPE GE NYLON	GSFC 640	1-093	.07				LACING TAPE
LACING TAPE GE PVC/LEATHER	GSFC 693	1-098	.07				LACING TAPE
LACING TAPE GUDE-NYLACE 18B FIBERGLASS/TEFLON WHITE	GSFC045	2-25	.19				LACING TAPE
LACING TAPE GUDE-NYLACE 18B NYLON NYLON WHITE	GSFC0116	2-25	.19				LACING TAPE
LACING TAPE GUDE-NYLACE FILLEX NATURAL	GSFC4700	5-25	.25				LACING TAPE
LACING TAPE GUDE-NYLACE FILLEX RUBBER BLACK	GSFC4660	5-49	.18	24H	50	AIR	LACING TAPE
LACING TAPE GUDE-SPACE 18D96 DACRON/SYN RUBBER BLACK	GSFC4664	4-9	.18	24H	100	AIR	LACING TAPE
LACING TAPE GUDE-SPACE 18D96 DACRON/SYN RUBBER WHITE	GSFC4666	2-44	.33	24H	100	AIR	LACING TAPE
LACING TAPE GUDE-SPACE 18D96 DACRON/SYN RUBBER WHITE	GSFC4666	2-52	.21				LACING TAPE
LACING TAPE GUDE-SPACE 18D96 DACRON/SYN RUBBER WHITE	GSFC6719	7-1	.14				LACING TAPE
LACING TAPE GUDE-SPACE 18D96 DACRON/SYN RUBBER WHITE	GSFC6719	7-3	.05				LACING TAPE
LACING TAPE GUDE-TEMP 718P NYLON NYLON POLYCARBONATE COAT	GSFC5427	2-7	.05				LACING TAPE
LACING TAPE GUDE-TEMP 723H NYLON NYLON RUBBER FINISH	GSFC4112	1-3-99	.05				LACING TAPE
LACING TAPE GUDE-TEMP 723S NYLON NYLON POLYCARBONATE COAT	GSFC4138	2-1-19	.12				LACING TAPE
LACING TAPE GUDE-TEMP 723S NYLON NYLON POLYCARBONATE COAT	GSFC4138	3-1-19	.72				LACING TAPE
LACING TAPE GDELACE 18N90 NYLON	GSFC289	7-7	.95				LACING TAPE
LACING TAPE GDELACE 18N90 NYLON COATED	GSFC2903	2-5	.07				LACING TAPE
LACING TAPE GDELACE 21H NYLON BRAID/NATURAL RUBBER	GSFC5409	2-36	.43				LACING TAPE
LACING TAPE GDELACE 22U NYLON BRAID/NATURAL RUBBER	GSFC5438	1-53	.03				LACING TAPE
LACING TAPE H130V NYLON/TEFLON SYN RUBBER SAT	GSFC8018	4-64	.06				LACING TAPE
LACING TAPE HT3-38 POLYESTER NYLON	GSFC2485	1-86	.18				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC1543	6-60	.18				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC1579	3-3-92	.17				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC1579	2-2-94	.32	1H	227	AIR	LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC8171	2-94	.00				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC8174	3-1-3	.14				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC9332	2-61	.03	1H	177	AIR	LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC8189	2-9-98	.02				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC8192	6-6-98	.16				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC549	2-7	.98				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC576	1-21	.42				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC6122	4-2	.18				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC9326	2-8	.03	15H	149	AIR	LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC9335	5-1	.01				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC6362	2-17	.02				LACING TAPE
LACING TAPE NYLON POLYESTER NYLON	GSFC6551	-					LACING TAPE

MATERIAL	DATA REFERENCE	XMTL	%CVCM	CURE TIME	CURE TEMP	MAX DOSS	APPLICATION
LACING TAPE STUR-D-LACE 1800 DACRON LEACHED	GSCFC6419	-13	.02				LACING TAPE
LACING TAPE SUPER-GUDE-SPACE DUT-H SCOURLED	GSC12202	-41	.05				LACING TAPE
LACING TAPE D-7 H SCURED DACRON	GSCC9915	-38	.94				LACING TAPE
LACING TAPE FIBERGLAS 90%OF 13A FIBERGLAS/TEFLON WHITE	GSCC6473	-43	.95				LACING TAPE
LACING TAPE TEMP-GLAS H231H H231H/TEFLON WHITE	GSCC4560	-36	.92				LACING TAPE
LACING TAPE TEMP-LACE H220H TEPICN BRAID/SYN RUBBER	GSCFC4008	-24	.95				LACING TAPE
LACING TAPE TEMP-LACE H220H TEPICN BRAID/SYN RUBBER	GSCFC4693	-24	.95				LACING TAPE
LACING TAPE T-40 FIBERGLAS/TEFLON OLIVE DAAJ/WV	GSCC3021	-50	.95				LACING TAPE
LACING TAPE T-40 FIBERGLAS/TEFLON COAT ESN 8010-00-515-2487	GSCFC0847	-4-35	.23	7D	25	.44	LACQUER
LAMINATE TAPE 892 ALUM POLYIMIDE/GLASS - BROWN	GSCC2790	-63	.93				LAMINATE TAPE
LAMINATE AL-300 G3C POLYIMIDE/GLASS - BROWN	GSCFC8744	-29	.93				LAMINATE TAPE
LAMINATE AL-3137 F/F TYPE FL-GEW W/O COPPER	GSCFC8747	-42	.93				LAMINATE TAPE
LAMINATE AS-4/1908 EPOXY/GRAPHITE	GSCC9245	-11	.93				LAMINATE TAPE
LAMINATE ASHLAD G4C GRADE EPOXY/TEFLON GLASS	GSCFC8098	-19	.93				LAMINATE TAPE
LAMINATE BL-2 EPOXY/FIBERGLASS W/O COPPER	GSCFC3909	-39	.91				LAMINATE TAPE
LAMINATE B33 NATURAL TYPE OF CORLAR 3104/GLASS/FR4	GSCFC83507	-62	.90				LAMINATE TAPE
LAMINATE C-339 BMS EPOXY/GRAPHITE TUBE	GSCFC9105	-54	.93				STRUCTURAL LAMINATE
LAMINATE CMC-0081-3-1 KAPTON/COPPER FOIL/KAPTON	GSCFC4410	-19	.93				STRUCTURAL LAMINATE
LAMINATE COTTON FILLED PHENOLIC	GSCFC9212	3-11	.93				STRUCTURAL LAMINATE
LAMINATE CP-190A CM CHOPPED MOLEDED CARBON PHENOLIC	GSCFC9308	3-19	.94				AIR
LAMINATE CP-190A CM CHOPPED MOLEDED CARBON PHENOLIC	GSCFC6098	4-75	.92				AIR
LAMINATE CUCLAID TEFILON/GLASS W/FOXTIN EC031PU3 ADH	GSCFC6101	3-61	.92				AIR
LAMINATE CUCLAID TEFILON/GLASS W/FOXTIN EC031PU3 ADH	GSCFC6092	4-04	.92				AIR
LAMINATE CUSTOM ECIYING TEFILON/FIBERGLASS	GSCFC31375	-66	.92				LAMINATE
LAMINATE EPOXY FIBERGLASS MULTIWIRE CKT LD	GSC12492	-43	.92				PC BOARD
LAMINATE EPOXY FIBERGLASS LOT 79-4805 (MT)	GSC10278	1-04	.92				HONEYCOMB
LAMINATE EPOXY/FIBERGLASS LOT 79-4833 (MT)	GSC10281	-94	.17	2H	49	.284	PC BOARD
LAMINATE EPOXY/FIBERGLASS /HY219/1275-2	GSCFC9134	-28	.01				LAMINATE
LAMINATE EPOXY/FIBERGLASS /HY740/HY219/1275-2	GSCFC2585	-93	.01				LAMINATE
LAMINATE EPOXY/Glass BLUE MIL-P-13940-1A MULTILAYER	GSCC13529	-35	.01				LAMINATE
LAMINATE EPOXY/GLASS UNIGLASS STILE 18	GSCFC3902	-30	.00	2H	74	.281	LAMINATE
LAMINATE EPSILAM 1C MICROWAVE SUBSTRATE W/O COPPER	GSCFC6974	-04	.00				LAMINATE
LAMINATE FLEXIBLE ERING SUGAR	GSCFC3612	-13	.00				LAMINATE
LAMINATE FLG 65H 28-1 EPOXY/FIBERGLASS/FIRE RETARD	GSCFC2977	-19	.00				LAMINATE
LAMINATE FLG/FPA-4 FC BOARD	GSCC13997	-32	.00				LAMINATE
LAMINATE FLG/FPA-4 FC BOARD	GSCC16675	-51	.00				LAMINATE
LAMINATE FLG/FPA-4 FC BOARD	GSCFC2973	-12	.00				LAMINATE
LAMINATE FH-4 G-11 EPOXY/FIBERGLASS	GSCFC7448	-31	.00				LAMINATE
LAMINATE FS9-1 G-3-1 EPOXY/FIBERGLASS	GSCC1123	-42	.00				LAMINATE
LAMINATE FS9-1 G-3-1 EPOXY/FIBERGLASS	GSCFC6224	-30	.00				LAMINATE
LAMINATE G-10 EPOXY FIBERGLASS	GSCFC5987	-48	.00				LAMINATE
LAMINATE G-10 TC MIL P-13949 - NORPLA	GSCFC5345	-93	.00				LAMINATE
LAMINATE G-10 TO MIL P-13949 - WESTINGHOUSE	GSCFC5347	-42	.00				LAMINATE
LAMINATE G-11 465 EPOXY/FIBERGLASS	GSCFC1207	-47	.00				LAMINATE
LAMINATE G-11 GEC-111 EPOXY/FIBERGLASS	GSCFC8999	-59	.00				LAMINATE
LAMINATE GEC 11 EPOXY/FIBERGLASS	GSCFC3566	-43	.00				LAMINATE
LAMINATE GEC MIL P18117 BLUE EPOXY/GLASS	GSCFC7394	-33	.00				LAMINATE

MATERIAL	DATA REFERENCE	XMT	%CVCM	CURE TIME	CURE TEMP	AIRLOS	APPLICATION
LAMINATE GEE-PI M-18177 EPOXY/PIBREGLASS	GSPC9311	.52	.00				LAMINATE POTTING CUP
LAMINATE GEE-FR 4300 RESIN EPOXY/PIBREGLASS - BLACK	GSPC9191	.61	.01				LAMINATE
LAMINATE GLASS CLOTH/SILICONE - WHITE	GSPC9695	.34	.01				LAMINATE
LAMINATE G10 WESTINGHOUSE 65M25 FR-4 FLAME RETARDANT	GSPC9209	1.88	.10	1H	121	PSI	STRUCTURAL
LAMINATE HONEYCOMB KEVLAR/EPOXY/PN 123-2	GSPC9209			2H	121	PSI	LAMINATE
LAMINATE HY1534/934 GRAPHITE EPOXY	GSPC10230	.29	.00	85H	121	PSI	LAMINATE
LAMINATE K-6098 TEFILON/FIBERGLASS/SM	GSPC9880	.01	.00				LAMINATE
LAMINATE L-1AF 46 FILM ADHESIVE	GSPC1139	.05	.01	90H	166	PSI	LAMINATE
LAMINATE KAPTON ENCAPSULATED COPPER	GSPC4158	.39	.01				LAMINATE
LAMINATE KEVLAR/EPOXY	GSPC9129	3.79	.12				LAMINATE
LAMINATE KEVLAR/EPOXY	GSPC9062	1.79	.02	24H	125	AIR	LAMINATE
LAMINATE KEVLAR/EPOXY	GSPC9206	2.94	.00	24H	70	PSI	LAMINATE
LAMINATE KEVLAR/EPOXY	GSPC9206	2.10	.01	85H	121	PSI	LAMINATE
LAMINATE LA6501 FLEXIBLE W/COPPER	GSPC11750	.43	.17				LAMINATE
LAMINATE MAS-G-1C-64	GSPC5773	.37	.00				LAMINATE
LAMINATE MICAPLY EG 802 TYPE GP W/O COPPER	GSPC8409	.41	.02	90H	171	PSI	LAMINATE
LAMINATE MICAPLY EG 402 UNCLAD	GSPC6492	.91	.01				LAMINATE
LAMINATE MICAPLY PG 418T POLYIMIDE/FIBERGLASS	GSPC1065	.82	.01				P/C BOARD
LAMINATE MICAPLY PG 418T EPOXY/GLASS PRE-PREG 8 LAYER	GSPC10251	.38	.03				LAMINATE
LAMINATE MICAPLY 102-1 EPOXY/GLASS PRE-PREG	GSPC4134	.44	.02				LAMINATE
LAMINATE MICAPLY 102-1/G-10 EPOXY/GLASS PRE-PREG	GSPC11473	.39	.02	80M	163	PSI	LAMINATE
LAMINATE MICAPLY 1G2-2BM FR-4 EPOXY/GLASS PRE-PREG	GSPC9213	2.11	.09	1H	188	PSI	LAMINATE
LAMINATE MICAPLY 102-6 B-STAGE PRE-PREG	GSPC8339	.36	.00				LAMINATE
LAMINATE MICAPLY 818T0 W/2 COPPER GREEN	GSPC80053	.38	.00				LAMINATE
LAMINATE NICARTA 65M50 W/2 LIGHT GREEN	GSPC5948	.32	.00				LAMINATE
LAMINATE MULTI-LAYER PER MIL P55617 P55636 P13949	GSPC5948	.63	.00				P/C BOARD
LAMINATE MULTIWIRE PCB BOARD	GSPC10121	.63	.00				LAMINATE
LAMINATE N-105 EPOXY/GLASS PL-GF FR-4 W/O COPPER	GSPC7607	.25	.00				LAMINATE
LAMINATE N-205 EPOXY/GLASS PL-GF FR-4 W/O COPPER	GSPC7629	.24	.01				LAMINATE
LAMINATE N-3105 RESIN RICH PRE EPOXY/GLASS W/O COPPER	GSPC7589	.30	.00				LAMINATE
LAMINATE N-4125 EPOXY/GLASS FLEXIBLE W/O COPPER	GSPC7558	.29	.00				LAMINATE
LAMINATE NARMCO 32Q3-12Q EPOXY/GLASS	GSPC7935	.32	.00	90M	127	PSI	LAMINATE
LAMINATE NARMCO 32Q3-1581 EPOXY/GLASS	GSPC10335	.47	.00	90H	127	PSI	LAMINATE
LAMINATE NARMCO 8517 EPOXY/GLASS	GSPC7385	.23	.00				LAMINATE
LAMINATE NEMA PR-45 BY GE W/O COPPER	GSPC3209	.38	.00				LAMINATE
LAMINATE NEMA G-10 GEC 500E EPOXY/LEADER GLASS	GSPC5995	.11	.00				LAMINATE
LAMINATE NEMA G10 WESTINGHOUSE 65M27-S-12 NO COPPER	GSPC3169	.06	.01				LAMINATE
LAMINATE NEMA G7 GLASS FABRIC/SILICONE	GSPC1521	.09	.02				LAMINATE
LAMINATE NEMA FE-4 W/SR1000 SOLDER RESIST/FIR CURE	GSPC13481	.14	.01				LAMINATE/RESIST
LAMINATE NEMA FE-4 W/FLAME RETARDANT AND MARKING	GSPC13595	.38	.00	90M	135	AIR	LAMINATE
LAMINATE NVF G-10 GREEN MARKING	GSPC5735	.49	.00	3H	177	AIR	LAMINATE
LAMINATE NYLON FAIRING PHENOLIC RESIN	GSPC5451	2.77	.00	?	454	AIR	LAMINATE
LAMINATE PBI ON 108-E GLASS CLOTH POLYBENZIMIDAZOLE)	GSPC6572	.29	.00				P/C BOARD
LAMINATE PC BOARD IRADIATED POLYOLEFIN	GSPC6611	.29	.00				LAMINATE
LAMINATE PHENOLIC GLASS FIBERGLASS PRE-PREG	GSPC9694	.68	.01				LAMINATE
LAMINATE PMR-15/HAC EPOXY/GRAPHITE	GSPC1228	.48	.01				LAMINATE
LAMINATE POLYIMIDE GLASS FABRIC EV AMQCQ	GSPC1261	.77	.00				LAMINATE
LAMINATE REYOLITE 2200	GSPC2775	.88	.00				LAMINATE
LAMINATE SHIM ALUMINUM	GSPC9284	.95	.00				LAMINATE
LAMINATE SUN SHAPE AL-KAPTON/7366 TAPE/AG-TEFLON-CTF	GSPC5044	.58	.00	48H	143	E-6	SHEILD
LAMINATE SUN SHAPE AL-KAPTON/7366 TAPE/AG-TEFLON-EDG	GSPC5043	1.12	.00	48H	143	E-6	LAMINATE
LAMINATE TIGI MULTI-LAYER	GSPC11678						

MATERIAL	REFERENCE	DATA	ARTHL	ACVN	CURE TIME	CURE TEMP	ATHS	APPLICATION
LAMINATE TURNOL GRADE 6F/45 FABRIC/EPOXY CREAM COLOR	GSPC9333	2-33	.00	.00				LAMINATE
LAMINATE TYPE GF EPOXY/PIBERGLAS	GSPC9394	*20	.00	.00				LAMINATE
LAMINATE T300/934 GRAPHITE EPOXY	GSPC126	*58	.00	.00				LAMINATE
LAMINATE V-378A/BMG EPOXY/GRAPHITE	GSPC1231	*50	.00	.00				PC BOARD
LAMINATE VECTORBOARD 850G24WE GLASS/EPOXY	GSPC1435	*45	.01	.00				LAMINATE
LAMINATE WBC 3261C ON 112 GLASS CLOTH EPOXY RESIN	GSPC2197	*17	.01	1H	163	AIR	AIR	LJUE
LAMINATE WESTINGHOUSE EPOXY/FIBERGLASS	GSPC389	*25	.02					LAMINATE SUBSTRATE
LAMINATE 55589A028 SILICONE/FIBERGLASS	GSPC5339	*43	.03					FLAT BOARD
LAMINATE 602 TEPIGN/FIBERGLASS W/O COPPER	GSPC9825	*69	.06					PLATE ADHESIVE
LAMINATING FILM 200-1 FOIL SANITIC	GSPC9838	*61	.01	30M	135	P24		LAMINATE
LARC 130 GRAPHITE/POLYIMIDE LAMINATE 5 STEP POSTCURE	GSPC1294	*83	.00	1H	177	P-2		
LATEX SURGICAL TUBING	GSPC6890	*16	1-44					ADHESIVE
LCA4/FACT BAS A/B AS 100/6 BW EPOXY ENCAPSULANT	GSPC2173	*12	.00	48H	56	PSI		ADHESIVE CUTTING
LCA4/FACT BAS AS 100/4-5 BW EPOXY	GSPC5115	*19	.00	16H	100	AIR	AIR	ADHESIVE
LCA4/ACT BAS AS 100/4-5 BW MINERAL FILLED GREEN	GSPC6194	*23	.00	16H	100	AIR	AIR	ADHESIVE
LD 400 VIBRATION DAMPER	GSPC4190	12-82	6-35	2H	93	AIR	AIR	DAMPER
LEACH CO9 SEMI-GLOSS BLACK LACQUER AEROSOL/F	GSPC9128	11-74	10-82	7D	25	AIR	AIR	PAINT
LEACH O10 FLAT BLUE LACQUER AEROSOL/F	GSPC9161	10-82	3-59	7D	25	AIR	AIR	PAINT
LEACH O13 AS 4/1 BV GLOSS BLACK EPOXY ENAMEL	GSPC9122	4-84	3-87	7D	25	AIR	AIR	PAINT
LEACH O14 AS 4/1 BV GLOSS BLACK EPOXY ENAMEL	GSPC9125	8-48	5-52	7D	25	AIR	AIR	PAINT
LEAL CC EPOXY ADH	GSPC1099	1-45	.07	30M	25	AIR	AIR	ADHESIVE
LECTROLITE CONDUCTIVE FABRIC - BLUE/BLACK VINYL	GSPC12883	13-31	8-62	8H	104	AIR	AIR	STATIC CONTROL
LEPKONELD 109/LN-52 AS 100/74 BW LIGHT GRAY EPOXY	GSPC8234	1-17	.02	24H	25	AIR	AIR	ADHESIVE
LEPKONELD 109/LN-52 AS 100/74 BW LIGHT GRAY EPOXY	GSPC8606	1-03	.02	5D	25	AIR	AIR	ADHESIVE
LEPKONELD 109/LN-52 AS 100/74 BW LIGHT GRAY EPOXY	GSPC8738	2-65	.03	24H	66	AIR	AIR	ADHESIVE
LEPKONELD 46/LN-52 AS 100/74 BW YELLOW/GREEN EPOXY	GSPC7292	1-04	.08	3H	66	AIR	AIR	ADHESIVE
LEPKONELD 46/LN-52 AS 100/74 BW YELLOW/GREEN EPOXY	GSPC8436	2-30	.08	7D	25	AIR	AIR	ADHESIVE
LENS BOND C-59/A/B AS 50/1 BV	GSPC3171	2-94	.16	8D	25	AIR	AIR	OPT CEMENT
LENS BOND F-65/A/E AS 50/1 BM	GSPC1087	4-83	.16	24H	25	AIR	AIR	OPT CEMENT
LENS BOND H-62/A/E AS 50/1 BM	GSPC1084	5-77	.62	90H	70	AIR	AIR	OPT CEMENT
LENS BOND UV-69 FOLYESTER SUN LAMP CURE	GSPC12253	3-65						OPT CEMENT
LENS BOND UV-74 FOLYESTER UV LAMP CURE	GSPC62476	4-42						OPT CEMENT
LENS TISSUE E68L POLYESTER	GSPC4017	5-82						PIPE
LEXAN 500 POLYCARBONATE	GSPC0410	*10						WOLD CPND
LEXAN 9034-112 POLYCARBONATE LENS	GSPC12646	*16						LENS PLATE
LEXOTE G-3183/G3174 AS 100/5-7 BW CLEAR COATING	GSPC3399	17-65						LENS PLATE
L886-13 STATIC DISSIPATIVE CURTAIN FILM - BLACK	GSPC13281	*68						ADHESIVE
Liquid CRYSTALS ENCAPSULATED IN PLASTIC/ADHESIVE	GSPC4160	5-99						ADHESIVE
LOCITE A RED ADHESIVE	GSPC9215	6-54						ADHESIVE
LOCITE A RED ADHESIVE FROM BOLTS	GSPC9695	5-47						ADHESIVE
LOCITE A RED ADHESIVE FROM BOLTS	GSPC9796	5-86						ADHESIVE
LOCITE AA OVER PAINTER M	GSPC1234	5-94						ADHESIVE
LOCITE AA WELD SEALANT GREEN FROM SHIMS	GSPC3495	1-64						ADH-SEALANT
LOCITE B BEARING MOUNT YELLOW FROM BOOTS	GSPC11252	3-19						ADH-SEALANT
LOCITE B BEARING MOUNT YELLOW FROM BOOTS	GSPC9719	14-30						ADH-SEALANT
	GSPC9797	7-30						

MATERIAL	DATA REFERENCE	XCVCM	CURE TIME	CURE TEMP	AIRUS	APPLICATION
LOCTITE C BLUE ADHESIVE	GSPC9 137	13.45	7.68	24H	25	PSI
LOCTITE C BLUE ADHESIVE FROM BOLTS	GSPC9 721	24-86	12.53	48H	25	E-2
LOCTITE C BLUE ACTIVATOR/F	GSCC11009	8-33	.29	24H	25	ADH-SEALANT
LOCTITE PMS-10 PURPLE RESIN/CLEAN	GSCC11411	3-40	.11	3D	25	ADHESIVE
LOCTITE PMS-10 PURPLE METAL SEALANT	GSCC11493	3-24	.20	1H	25	ADHESIVE
LOCTITE PMS-50 PURPLE METAL SEALANT	GSCC11497	3-80	.31		25	ADHESIVE
LOCTITE PMS-90 PURPLE METAL SEALANT	GSCC11499	3-93	.56		25	ADHESIVE
LOCTITE PMS-277	GSPC7 741	17-79	.22	72H	25	E-4
LOCTITE 222 MILD STRENGTH ADH PURPLE FROM BOLTS	GSPC7 742	17-84	.24	24H	25	THREAD SEAL
LOCTITE 222 MEDIUM STRENGTH ADH BLUE FROM BOLTS	GSPC7 748	26-84	.24	48H	25	ADHESIVE SEAL
LOCTITE 242 MEDIUM STRENGTH ADH BLUE FROM BOLTS	GSPC7 749	13-97	.21	24H	25	ADHESIVE SEAL
LOCTITE 242 HIGH STRENGTH ADH RED FROM SHIMS	GSPC9 699	16-43	.43	7-45	25	ADH-SEALANT
LOCTITE 262 HIGH STRENGTH ADH RED FROM SHIMS	GSCC11234	4-12	.18	72H	25	ADH-SEALANT
LOCTITE 271 HIGH STRENGTH ADH RED FROM BOLTS	GSPC7 7820	6-10	.23	16H	25	ADH-SEALANT
LOCTITE 290 MEDIUM STRENGTH ADH GREEN FROM BOLTS	GSPC9 7769	5-19	.47	48H	25	ADH-SEALANT
LOCTITE 290 MEDIUM STRENGTH ADH GREEN FROM BOLTS	GSPC9 7717	2-97	.02	24H	25	ADH-SEALANT
LOCTITE 317 STRUCTURAL ADHESIVE	GSCC11150	2-43	.01	16H	25	ADH-SEALANT
LOCTITE 324/ACT 707	GSPC13431	10-02	.13	7D	25	ADH-SEALANT
LOCTITE 324/ACT 707	GSPC10874	2-46	.13	17D	25	ADHESIVE
LOCTITE 326/PLASTER N	GSPC10876	5-09	.28	12H	25	ADHESIVE
LOCTITE 357/OCUIMIC PRIMER N	GSPC10878	2-45	.11	15H	25	ADHESIVE
LOCTITE 357 MOD ACRYLIC UV CONVERTIBLE	GSPC10880	3-54	.31	11H	25	ADHESIVE
LOCTITE 357 MOD ACRYLIC UV CONVERTIBLE	GSPC4 636	1-21	.04	6H	60	E-2
LOCTITE 361 HIGH STRENGTH ADH GREEN	GSPC11099	3-61	.53		25	ADHESIVE
LOCTITE 601 HIGH STRENGTH ADH GREEN	GSPC1147	8-94	.22		25	OPTICAL CEMENT
LOCTITE 93-13 SUPER BOND ADHESIVE	GSPC13036	3-80	.09		25	ADHESIVE
LOGO 1709/503 LACQUER/THINNER AS 3/1 BY	GSPC7 7748	5-21	.92	24H	25	ADHESIVE
LUBRI-FILM N	GSPC4 338	8-92	.37	24H	25	ADHESIVE
LUBRI-FILM N	GSPC8 5649	1-43	.01	1H	66.3	AIR
LST 350 EMU SUPPRESSANT TUBING	GSPC6 914	1-37	.14		121	AIR
LUBRI-BOND K SOLID FILM LUBRICANT MOS2/F	GSPC7 049	1-22	.11	16H	150	LAG SHIELD
LUBRI-BOND K SOLID FILM LUBRICANT MOS2/F	GSPC11681	1-61	.15	24H	25	LUBRICANT FILM
LUBRI-BOND K SOLID FILM LUBRICANT MOS2/F	GSPC11684	1-38	.12	1H	80	LUBRICANT FILM
LUBRI-FILM N	GSPC5 643	2-90	.19		66	AIR
LUBRI-FILM 630A	GSPC8 264	51-00	14.59		121	LUBRICANT/GREASE
N-151 LACQUER BLACK TEFLON ON FABRIC	GSPC5 583	4-05	.01		25	ADHESIVE
N-152 LACQUER BASECOAT W/ VAC DEP ALUMINUM	GSPC5 645	4-82	.03		25	FILM ADHESIVE
N-152 LACQUER BASECOAT W/ THINNERS - SPRAYED 2 COATS	GSPC5 647	2-43	.19		25	FILM ADHESIVE
N-152 LACQUER BASECOAT W/ THINNERS - SPRAYED 2 COATS	GSPC6 293	4-04	.03	1H	125	COUVER
M-5 ADHESIVE A/B AS 1/1 BW YELLOW	GSCC11687	10-20	.17	2H	121	E-3
MA 509 CONDUCTIVE SILICONE	GSCC11126	1-28	.09	25D	25	AIR
MACBOND 1B 1200 TWO SIDED TAPE/F	GSCC11905	1-36	.05		25	AIR
MACBOND 9626 POLYESTER FILM/2 SIDE ACT ADH 61418/F	GSPC5 020	1-23	.09		25	AIR
MAGIC VULCANOPAINE EMULSION	GSPC0 803	2-12	.34	1H	125	E-4
MAGNET FLEXIBLE STRIP #GO-1016	GSPC4 540					COUVER

MATERIAL	DATA REFERENCE	X-TAL	X-YEN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
MAGNET WIRE COATING TEFLON/DURAD	GSPC5411	.29	.01				
MAGNET WIRE HEAVY ARMOR POLYIMIDE (COATING ONLY)	GSPC8411	.53	.08				
MAGNET WIRE HEAVY MILW-POLYIMIDE	GSPC4412	1.89	.10				
MAGNET WIRE MILW-583C	GSPC3546	1.7	.11				
MAGNET WIRE CENE - GRAY	GSEFC9537	.73	.04				
MAG-60 HOLDING CENE - GRAY	GSEFC9532	.75	.03				
MARKEN 7224 BLACK INK	GSPC7343	3.12	.08	24H	100	AIR	
MARKEN 7224 GREEN INK 497-F	GSPC5397	.45	.02	4H	121	AIR	
MARKEN 7224 WHITE INK SLOW SOLVENT	GSEFC385	1.88	.02	4H	121	AIR	
MARKEN 7227 WHITE INK FAST SOLVENT	GSEFC387	1.22	.02	4H	121	AIR	
MARKEN 7251 GREEN INK 497-F	GSEFC5399	9.64	.64	24H	60	AIR	
MARKEN 7251 WHITE INK SLOW SOLVENT	GSPC5389	5.34	.03	2H	107	AIR	
MARKEN 7252 WHITE INK FAST SOLVENT	GSPC9389	4.05	.03	2H	107	AIR	
MARKEN 7254 BLACK INK - PHENOLIC	GSPC5325	8.27	.03	24H	125	AIR	
MARKEN 7905 WHITE INK A/B AS 2/1 BW	GSPFC5328	3.50	.02	2H	88	AIR	
MARKEN 7906 WHITE INK A/B AS 2/1 BW	GSPC5401	11.33	.01	24H	121	AIR	
MARKEN 8826 WHITE INK A/B AS 2/1 BW	GSPC5403	11.33	.01	24H	121	AIR	
MARKERS MILAR-124/BLACK INK	GSPC3831	2.33	.88				DARKERS
MARPOXY 95-163 SINGLE COMPONENT CU FILLED EPOXY	GSPC13072	.28	.01	2H	149	AIR	ADHESIVE
MARPOXY 95-168 A/E AS 19/1 BW CU FILLED EPOXY	GSC12817	.45	.04	16H	254	AIR	
MARPOXY 95-202 SINGLE COMPONENT CU FILLED EPOXY	GSC13075	.27	.00	2H	200	AIR	ADHESIVE
MARPOXY 95-4 A/B AS 19/1 BW CU FILLED EPOXY	GSC12568	1.45	.10	24H	294	AIR	
MARPOXY 95-7 A/B AS 19/1 BW CU FILLED EPOXY	GSC12571	1.18	.08	24H	65	AIR	
MARPOXY 95-9 ONE COMPONENT CU FILLED EPQX1	GSC12574	.63	.06	1H	160	AIR	
MASTER BOND GP6 PCYESTER COPOLYMER	GSPC8004	14.74	.07	24H	294	AIR	
MAXORB SOLAR FOIL BLACK NICKEL/W/ADHESIVE	GSC10884	4.4	.23				
MAXORB SOLAR FOIL BLACK NICKEL/W/O ADHESIVE	GSC10943	.72	.00				
MC-30 A/B AS 95/5 EN ACRYLIC ADH/BENZYL PEROXIDE	GSPC925	4.72	.03	7D	25	AIR	
MC-30 A/B AS 95/5 EN TOLUENE ACRYLIC ADHESIVE	GSPC9260	14.01	.04	24H	66	AIR	
MC-469/MC470 AS 4/1 BW BROWN WASH PRIMER	GSPC7001	9.81	.01	30M	160	AIR	
ME 5146A/B-97 AS 100/1-10 BW CLEAR BLUE EPOXY/P	GSC13570	9.33	.15	2H	80	AIR	LOATING
NEELAMINE G-5 PER MIL P-15037B FUSE INSULATOR	GSPC8534	2.06	.00				INSULATOR
NEELAMINE G-5 PER MIL P-15037B FUSE INSULATOR	GSPC8534	6.59	.06	24H	100	AIR	INSULATOR
NERECO 4501 A/B AS 1/1 BW CLEAR FLEXIBLE EPOXY	GSPC1513	8.99	.23	1H	85	AIR	PUTTING
NETLAST 925 PRIMER AS 1/4 BW	GSPC90494	11.35	.00	1H	25	AIR	PRIMER
NETLAST 925 PRIMER AS 1/4 BW	GSPC12349	11.55	.00	1H	60	AIR	SHELDING
NETLASTATIC SILICONE FILLED ALUM MESH	GSC12373	9.33	.02	24H	177	AIR	ADPREGNATE
NETSEAL 19V5 THERMOSET POLYESTER/STYRENE COPOLYMER	GSPC3211	1.67	.16	3H	149	AIR	WAVEGUIDE
METHYL BOND 1113 EPOXY SUPPORTED FILM	GSPC4322	9.38	.04	25M	149	AIR	WOD FILM
METHLBOND 227 EPOXY FILM ADHESIVE EPOXY FILM	GSPC4962	1.93	.08	1H	127	AIR	WOD FILM
METLBOND 329 CLUTCH SUPPORTED FILM	GSPC260	1.27	.01	1H	93	AIR	WOD FILM
METE-GRIP 34+6/T9 AS 1X CAT 3W	GSPC5349	.49	.00	16H	204	AIR	ADHESIVE
MF 1006 POLYPROPYLENE/GLASS AS 70/30	GSPC2911	.13	.03	3M	149	AIR	
MG 8F-0134 HOLDING CPND - BLACK	GSPC8927	.22	.01				

MATERIAL	DATA REFERENCE	#ML	%CVCM	CURE TIME	CURE TEMP	ATHOS	APPLICATION
MH 11 BLACK HOLDING COMPOUND							
MH6F MOLDING CPNL - BLACK	GSC13573	-1.18	-0.01	2H	149	PSI	WLD CPND
MICRO SWITCH 311SX4-T GLASS FILLED PHENOLIC W/ADH	GSPFC8930	-2.44	-0.01	3H	149	AIR	BUILD GND
MICRO CIRCUIT TYPE # SILVER FILLED EPOXY	GSPFC2399	-2.24	-0.02	16H	150	AIR	SWITCH
MICRODOT CONNECTOR RED SILICONE INSERT	GSC10478	-0.54	-0.04	10H	171	AIR	COND ADHESIVE
MICRODOT CONNECTOR RED SILICONE INSERT	GSC10481	-1.18	-0.09	5H	171	AIR	COND INSUL
MICRODOT FELT AA 0.6#/CU FT W/SILICONE BIND-CENTER	GSPFC6542	-1.62	-0.51	1H	260	AIR	COND INSUL
MICROTHIN TEFZEL SIEVING 20 GAUGE	GSPFC65525	-0.29	-0.09	4d	330	AIR	BLVEVING
MICROWELL R FOAM LUBRICANT RESERVOIR ERON TA WASH	GSPFC8828	-0.14	-0.01				FOAM
MIKROY 750 REG GRALE LEAD BOATE/MICA MIX	GSPFC3568	-0.09	-0.03				INSULATION
MIL-EN-C WIRE INSULATION - YELLOW {COATING ONLY}	GSC10011	-0.78	-0.24				WIRE INSUL
MIL-K 1301 HT INSULATION	GSPFC33309	-0.52	-0.13	4H	150	AIR	WIRE INSUL
MIL-N-K B-302 CROSSLINKED POLYPROPYLENE FOAM WHITE	GSPFC3329	-0.51	-0.06				INSULATION
MIL-NICEL 6-55 URETHANE HIGH FRICTION ELASTOMER CLEAR	GSPFC6816	-2.82	-0.59				DAMPNER
MIL 6-55 URETHANE HIGH FRICTION ELASTOMER BLUE	GSPFC5545	-1.19	-0.39				ELASTOMER
MIL-F FOIL 780 ALUMINUM/ACRYLIC ADH	GSPFC0269	-4.99	-2.74				FOLI
MIL-F TAPE X-140 NYLON/ALUM/ACRYLIC ADH/Y-916U)	GSPFC0603	-6.14	-2.09	3d	121	44K	44P
MIL-F TAPE X-140 THERMOSET RUBBER ADH FILM	GSPFC3117	-6.14	-2.13	6H	107	AIR	2 SIDED TAPE
MIL-F TAPE X-157 POLYESTER FILM/THERMOSET RUBBER /R	GSPFC1564	-6.26	-2.50				44P
MIL-F TAPE X-173 ALUM FOIL/COND ACRYLIC ADH/F	GSPFC3339	-0.51	-0.06				44P
MIL-F TAPE X-183 COPPER FOIL/ACRYLIC ADH/F (ECC48.8P)	GSPFC7784	-0.51	-0.06				44P
MIL-F TAPE X-205 KAFTON/ACRYLIC ADH/F	GSPFC7814	-0.31	-0.04				44P
MIL-F TAPE X-205 KAFTON/ACRYLIC ADH/R	GSPFC5262	-1.90	-0.92	1H	125	AIR	44P
MIL-F TAPE X-123 NYLON PAPER/ACRYLIC ADH/R	GSPFC1378	-2.16	-0.05				44P
MIL-F TAPE X-124 FOILS PER/THERMOSET RUBBER ADH/R	GSPFC3918	-2.19	-0.04				TAPE
MIL-F TAPE X-1244 NYLAR/THERMOSET ACRYLIC ADH/E	GSPFC1564	-1.96	-0.04				44P
MIL-F TAPE X-125 THERMOSET ACRYLIC ADH/2 SLIDE/F	GSPFC5079	-1.00	-0.04	10H	130	AIR	2 SIDED TAPE
MIL-F TAPE X-1255 KAFTON/THERMOSET ACRYLIC ADH/2 SLIDE	GSPFC1628	-0.93	-0.09				44P
MIL-F TAPE X-1255 KAFTON/THERMOSET ACRYLIC ADH/2 SLIDE	GSPFC1628	-0.93	-0.09				44P
MIL-F TAPE X-126 EPOSS AL/ACRYL ADH/F BAKE ON SCREEN	GSPFC10062	-0.58	-0.07	30H	121	AIR	2 SIDED TAPE
MIL-F TAPE X-126 EPOSS AL/ACRYL ADH/F BAKE AS A ROLL	GSPFC7871	-0.20	-0.05	16H	120	E-2	44P
MIL-F TAPE X-1267 EPOSS AL/ACRYLIC ADH/F CD3DUS86	GSPFC7868	-0.41	-0.19	16H	120	E-2	44P
MIL-F TAPE X-1267 EPOSS AL/ACRYLIC ADH/F CD3DUS86	GSPFC7892	-0.44	-0.21	2H	121	AIR	2 SIDED TAPE
MIL-F TAPE X-1267 EPOSS AL/ACRYLIC ADH/F CD3DUS86	GSPFC6575	-1.42	-0.42				44P
MIL-F TAPE X-1267 EPOSS AL/ACRYLIC ADH/F CD3DUS86	GSPFC8633	-0.68	-0.02				44P
MIL-F TAPE X-1267 EPOSS AL/ACRYLIC ADH/F CD3DUS86	GSPFC5305	-0.47	-0.02				44P
MIL-F TAPE Y-9050 ALUM FOIL/SILICONE ADH/F (433)	GSPFC2775	-0.91	-0.38				44P
MIL-F TAPE Y-9133 GREEN POLYESTER FILM/SILICON ADH/F	GSPFC3249	-0.75	-0.21				44P
MIL-F TAPE Y-9184 ALUM FOIL/SILICONE ADH/R	GSPFC1363	-1.42	-0.33				44P
MIL-F TAPE Y-9184 ALUM FOIL/SILICONE ADH/R	GSPFC13207	-2.18	-0.34				44P
MIL-F TAPE Y-9224 TEFZEL FEP/ACRYLIC ADH/R	GSPFC1378	-0.90	-0.02				44P
MIL-F TAPE Y-9339 ALUM FOIL/ACRYLIC ADH/R TYPE 2-2UAL	GSPFC1391	-0.24	-0.01				44P
MIL-F TAPE Y-9339 ALUM FOIL/ACRYLIC ADH/R TYPE 3-3UAL	GSPFC1453	-0.54	-0.01				44P
MIL-F TAPE Y-9460 ALUM/HYLAR/ACRYLIC ADH/R	GSPFC9470	-0.85	-0.02				44P
MIL-F TAPE Y-9469 ISCTAC ACRYLIC TRANSFER FILM 2 MIL/F	GSPFC9503	-1.29	-0.02				44P
MIL-F TAPE Y-9473 ISCTAC ACRYLIC TRANSFER FILM 5 MIL/F	GSPC12204	-1.42	-0.01				44P
MIL-F TAPE Y-9507 (467NB) TRANSFER FILM ACR/P SANDWICH	GSC13377	-1.37	-0.03				44P
MIL-F TAPE Y-966 TRANSFER FILM ACRYLIC/FULL SANDWICH	GSPC7604	-1.32	-0.01				44P
MIL-F TAPE Y-967 EXPERIMENTAL ALUM GLASS CLOTH/F	GSC11951	-1.84	-0.01				44P
MIL-F TAPE Y-1744 COPPER FOIL/NON COND ACRYLIC ADH/F	GSC10260	-0.28	-0.14				44P

MATERIAL	DATA REFERENCE	ADL	XCVCA	CURE TIME	CURE TEMP	A.I.D.S	APPLICATION
MM TAPE 1245 EMBOSSED COPPER FOIL/ACRYLIC ADH/F	GSC13540	.26	.12				EMI SHIELD
MM TAPE 1318 POLYESTER FILM/ACRYLIC ADH/F - YELLOW	GSC11360	.48	.13				TAPE
MM TAPE 343 ALUM. GLASS CLOTH/SILICONE ADH/F (MOD) /F	GSC11741	1.28	.63				TAPE
MM TAPE 363 ALUM. GLASS CLOTH/SILICONE ADH/F	GSCF91915	1.30	.47	3H	121	ADA	TAPE TAPE 2 SIDE
MM TAPE 365 GLASS CLOTH/ THERMOSET RUBBER ADH/R	GSPC2651	2.46	.99				TAPE MOUNT
MM TAPE 4016 FOAM/2 SIDE ACRYLIC ADH/PULL SANDWICH	GSC12160	2.99	.19				TAPE MOUNT
MM TAPE 4032 SCOTCHBOND FOAM/2 SIDE ACRYLIC ADH/F	GSC12163	2.26	.15	24H	90	E-3	2 SIDED TAPE
MM TAPE 4115 SCOTCHBOND FOAM/2 SIDE ACRYLIC ADH/F	GSCF6706	1.91	.01				TAPE
MM TAPE 420 SUBSEAL PAR FILM/2 SIDE ACRYLIC ADH/F	GSPC5890	1.85	.14				TAPE
MM TAPE 420 SUBSEAL BASE ADHESIVE ONLY/F	GSPC5889	1.85	.09				TAPE
MM TAPE 422 ACRYLIC BASE FOIL/RUBBER BASE ADH/P	GSPC6463	1.93	.04				TAPE
MM TAPE 422 LEAD FOIL/ACRYLIC ADH/F	GSPC9234	2.24	.05				TAPE
MM TAPE 425 LEAD FOIL/SYNTHETIC ADH/P	GSPC5296	2.0	.01				TAPE
MM TAPE 428D ALUM. FOIL/SYN BLEND ACRYLIC ADH/R	GSPC2771	1.79	.25				2 SIDED TAPE
MM TAPE 433 2 SIDE ALUM. FOIL/SYN BLEND ACRYLIC ADH/F (X-940)	GSPC5299	1.53	.25				2 SIDED TAPE
MM TAPE 464 TISSUE FILM/RUBBER ADH/A	GSPC13391	6.17	.69				TRANSFER TAPE
MM TAPE 465 TRANSFER FILM/SYN ACRYLIC/FOIL SANDWICH	GSPC13392	1.20	.07				TRANSFER TAPE
MM TAPE 466 TRANSFER FILM/SYN ACRYLIC/R	GSPC2769	1.34	.02				TRANSFER TAPE
MM TAPE 467 TRANSFER FILM/ACRYLIC/POIL SANDWICH	GSPC8765	1.88	.02				TRANSFER TAPE
MM TAPE 469 FIBER INBED ACRYLIC IRAMS FILM/F	GSPC7505	1.83	.04				TRANSFER TAPE
MM TAPE 471 VINYL/SYNTHETIC RUBBER ADH/R	GSPC3642	6.30	.91				TAPE
MM TAPE 4945 SCOTCHBOND ACRY FOAM/2 SIDE ACR ADH/F	GSC13392	1.24	.61				2 SIDED TAPE
MM TAPE 520 POLYESTER ACRYLIC ADH/R	GSC13395	2.64	.60				2 SIDED TAPE
MM TAPE 533 POLYESTER ACRYLIC ADH/R	GSPC0527	1.02	.09				TAPE
MM TAPE 5411 KAPTON/SILICONE ADH/B/P	GSPC3920	1.52	.13	3H	121	A-4	TAPE
MM TAPE 5413 KAPTON/SILICONE ADH/B/P	GSPC9140	1.58	.13	1H	125	A-4	TAPE
MM TAPE 5490 TEEFON/THERMOSET SILICONE ADH/R	GSPC6143	.87	.32	1H	125	A-4	TAPE
MM TAPE 556 POLYESTER/THERMOSET RUBBER ADH/R	GSPC7397	2.72	.40				TAPE
MM TAPE 559 POLYESTER/ACRYLIC ADH/R	GSPC9118	2.67	.27				TAPE
MM TAPE 601 TEEFON TEE/THERMOSET SILICONE ADH/R	GSPC3937	1.25	.22				TAPE
MM TAPE 633 TEEFON TEE/THERMOSET SILICONE ADH/R	GSPC3906	1.14	.20				TAPE
MM TAPE 655 TEEFON TEE/ACRYLIC ADH/R	GSPC2777	1.33	.09				TAPE
MM TAPE 660 PVC & FILM/2 SIDE ACRYLIC ADH/R	GSPC1870	1.29	.08				TAPE
MM TAPE 677 EPOXY RESIN GLASS CLOTH/ THERMOSET RUBBER	GSPC0535	2.17	.15				2 SIDED TAPE
MM TAPE 679 CELLOPHANE/ TISSUE PAPER/ACRYLIC-RUBBER	GSPC2747	5.92	.18				TAPE
MM TAPE 690 GLASS CLOTH/ THERMOSET SILICONE ADH/S	GSPC2312	2.25	.18				TAPE
MM TAPE 700 SILICONE RUBBER TAPE/SILICONE ADH/R	GSPC1252	1.62	.73				TAPE
MM TAPE 74 POLYESTER FILM/THERMOSET RUBBER ADH/P	GSPC14917	2.40	.60				TAPE
MM TAPE 75 POLYESTER FILM/THERMOSET RUB ADH/R CYCLE	GSPF1440	3.12	.72	24H	-40	E-3	TAPE
MM TAPE 75 POLYESTER FILM/THERMOSET RUBBER ADH/R	GSPF1234	5.26	.75				TAPE
MM TAPE 8402 POLYESTER FILM/SILICONE ADH/F	GSPC5811	5.54	.97				TAPE
MM TAPE 848 VAP DEP AU/KAPTON/ACR ADH/F (Y-9064)	GSPC5733	7.3	.31				TAPE
MM TAPE 848 VAP DEP AU/KAPTON/ACR ADH/F (Y-9184A)	GSPC8336	8.1	.92				TAPE
MM TAPE 849 VAP DEP AU/KAPTON/SILICONE ADH/F LOT 9	GSPC12412	1.79	.71				TAPE
MM TAPE 849 VAP DEP AU/KAPTON/SILICONE ADH/F	GSPC2439	1.99	.71				TAPE
MM TAPE 850 ALUMINIZED POLYESTER/ACRYLIC ADH/R	GSPC2773	6.8	.09				TAPE
MM TAPE 850 BLACK NYLAR/ACRYLIC ADH/R	GSPC9900	7.7	.02				TAPE
MM TAPE 851 POLYESTER POLYESTER/ACRYLIC ADH/F	GSC12181	6.1	.93				TAPE
MM TAPE 851 POLYESTER FILM/GREEN SPEC BLEND ADH/P	GSC12157	3.33	.93				TAPE

MATERIAL	DATA REFERENCE	ATM	XCVCM	CORE TIME	CORE TEMP	ATTOS	APPLICATION
MM TAP 852 ALUM/IVYAK ACRYLIC ADH/F	GSPC5282	.79	.02				
MM TAP 854 TRANSENFECT PESTER/WHITE SIN RUB ADH/P	GSC12184	2.20	.14				
MM TAP 92 KAPTON/THIN MOSET SILICONE ADH	GSPC2631	4.75	1.22				
MM TAP 6887 HEAT SHRINK TAPE - DEAT GUN SHRINK	GSC13323	4.95	>.24	1H	89	AIR	TAPE
MM 101-C10 VELVET BLACK ALKYD	GSPC2897	4.95		7D	25	AIR	SHRINKABLE TAPE
MM 101-C10 VELVET BLACK PAINT ALKYD	GSPC5649	2.02	.02	20H	121	AIR	PAINT
MM 101-C10 VELVET BLACK	GSPC6856	6.02	.14	6H	25	AIR	PAINT
MM 301-C10 VELVET BLACK	GSPC2955	5.17	.02	1H	121	AIR	PAINT
MM 301-C10 VELVET BLACK	GSPC2957	5.60	.02	6D	25	AIR	PAINT
MM 401 BLACK OVER 41NC CHROMATE	GSPC2293	4.82	.12	6D	25	AIR	PAINT
MM 401-A10 A/B AS 3/1 BV WHITE PAINT	GSPC3067	2.88	.03	7D	65	AIR	PAINT
MM 401-A10 A/B AS 3/1 BV WHITE PAINT	GSPC3115	2.85	.03	7D	65	AIR	PAINT
MM 401-A10 A/B AS 3/1 BW VELVET WHITE	GSPC2095	3.09	.08	7D	25	AIR	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	GSPC5118	2.91	.01	24H	121	AIR	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	GSPC5310	3.33	.02	30H	93	AIR	PAINT
MM 401-C10 A/B AS 3/1 BV VELVET BLACK	GSPC6302	3.18	.00	24H	95	AIR	PAINT
MM 401-C10 VELVET BLACK OVER E-SOLDER 3022 LAYUP	GSPC7031	2.76	.01	30H	120	AIR	PAINT
MM 403-C10 A/B AS 3.5/1 BV VELVET BLACK	GSPC0972	3.11	.01	24H	120	AIR	PAINT
MM 403-C10 A/B AS 3/1 BV VELVET BLACK	GSPC2935	3.00	.07	16H	71	AIR	CONF COAT
MM 801 A/B AS 10/1 Bi SEALANT	GSPC0728	40.24	1.78	24H	25	AIR	PAINT
MOBAY-TEXAS 355D POLYURETHANE FASTENER	GSPC6986	1.03	.23				
MOBIL 173 COATED VIALUMINIZED KAPTON	GSC12607	1.85	.02				
MOLYKOTE G-N PASTE GRAY	GSC12610	1.95	.04				
MOLYKOTE GELSE	GSC12724	1.76	.82				
MONSANTO 1835 POLYETHER-URETHANE FOAM	GSPC6008	3.20	1.25				
MONSANTO 1835 POLYETHER-URETHANE FOAM ISOPROP WASH	GSPC4508	3.13	.43				
MONSANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	GSPC4510	1.25	.43				
MONSANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	GSPC4732	.29	.08	72H	120	AIR	FASTENER BLANKET
MONSANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	GSPC4734	.27	.04	21H	100	AIR	INTERNAL BLANKET
MONSANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	GSPC4736	.42	.13	30H	100	AIR	SUBRICANT
MONSANTO 3865-F POLYETHER-URETHANE FOAM	GSPC4512	3.05	.71	2H	100	AIR	FOAM
MONSANTO 3865-F POLYETHER-URETHANE FOAM	GSPC4514	.94	.19	72H	120	AIR	FOAM
MONSANTO 1028 BLACK FLUOREL SPONGE RUBBER	GSC10508	.81	.20				
MONSANTO 1028 BLACK FLUOREL SPONGE RUBBER	GSC10511	.30	.08				
MONSANTO 1059 FLUOREL FLUOROCARBON ELASTOMER	GSPC6305	.05	.00				
MONSANTO 1071 FLUORFL FLUOROCARBON ELASTOMER	GSPC4398	.64	.32				

MATERIAL	REFERENCE	DATA	X-TAL	XCVCM	CURE TIME	CURE TEMP	ADHES	APPLICATION
MONITES 1079K FLUOROCARBON ELASTOMER	GSEFC4394	-24	.10	.23				ELASTOMER
MP 1485 POLYURETHANE FILM	GSEFC2857	-1.04	.19					FILM
MP 1885 POLYURETHANE FILM	GSC11387	-1.0	.10	14D	2.5			FILM
MS 125 WHITE COATING GASON 4/PVAF/KRYLON	GSEFC4778	-37	.08					OPTICAL PAINT
MS 224 MH5 EOLW RELEASE ON FOIL	GSEFC5975	11.98	.33					BUILD RELEASE
MS 240 2 PRIMER/FCII	GSEFC5777	1.4.55	1.41	30H	2.5			PRIMER
MS 2704 SILICONE ALH	GSEFC3029							ADHESIVE
MS 74 WHITE COATING K2S103/T102/ZNO/AL203	GSEFC1984	6.24	.03					PAINT
MS 74 WHITE COATING K2S103/T102/ZNO/AL203	GSEFC2134	4.18	.09	48H	2.5			PAINT
MS 74 SILANE 6202 PRIMER COMPOSITE/F	GSEFC1609	13.19	.20					LUBRICANT COMPOSITE
MS - 122 SILICONE ALH DAY LUBRICANT - AEROSOL	GSEFC2023	10.42	4.72	4.76				BUILD RELEASE
MS - 138 FLUOROCARBON HOLD RELEASE ON FOIL	GSEFC9314							ELASTOMER
MS - 20108	GSEFC0083							ELASTOMER
MS - 30C02	GSEFC0086							ELASTOMER
MSA 101E GREEN PAINT OI 650/CHROMIC OXIDE	GSEFC3331	1.04	.47	6H				PAINT
MSA 102 BLACK PAINT OI 650/CHROMIC OXIDE	GSEFC3469	-1.1	.09	6H				PAINT
MSA 103 BLACK PAINT OI 650/CARBON BLACK	GSEFC3499	-95	.35	6H	150			PAINT
MSA 5 BLACK COATING	GSEFC2023	10.94	5.94	3D	95			PAINT
MSA 5 BLACK COATING	GSEFC2137	3.14	0.02	3D	95			PAINT
MSA 82 WHITE PAINT OI 650/NA TREATED ZNO	GSEFC3497	2.24	.04	48H	100			PAINT
MSA 82 WHITE PAINT OI 650/ZINC OXIDE	GSEFC3335	1.40	.24	6H	150			PAINT
MSA 90 WHITE PAINT OI 650/POTASSIUM TREATED ZNO	GSEFC3467	1.78	.06	6H	150			PAINT
MSA 90 WHITE PAINT OI 650/ZINC OXIDE	GSEFC3333	1.78	.56	6H	95			PAINT
MSA 90 WHITE PAINT OI 650/ZINC OXIDE	GSEFC8906	3.66	.00	16H	25			PAINT
MSA 94B BLACK PAINT	GSEFC3213	2.30	.23	24H	70			PAINT
MSA 952 WHITE PAINT	GSEFC3127	2.75	.95	2H	50			PAINT
MSA 952A GREEN PAINT	GSC124433	-98	.03					MAGNET WIRE
NYLAR FIBREGLASS FILM	GSEFC6778	-70	.04					FILM INSET
NYLAR IMAGING FILM	GSEFC4739	-15	.00					FILM/SHEET
NYLAR LA 616 - 7 MIL FILM	GSEFC4746	-59	.00					FILM/SHEET
PHOTOSENSITIVE FILM TYPE A	GSEFC3307	1.49	.06					TAPE
MYSTIK TAPE 401717 C GOLD/KAPTON ACRYLIC ADH/R	GSEFC4738	1.49	.03					TAPE
MYSTIK TAPE 401717 C GOLD/KAPTON ACRYLIC ADH/F	GSEFC119418	-51	.03					TAPE
MYSTIK TAPE 405311C ACRYLIC ADH/F	GSEFC10188	3.73	.01					TAPE
MYSTIK TAPE 6401 PC POLYESTER FILM/ACRYLIC ADH/k	GSEFC5617	5.99	.01					2 SIDED TAPE
MYSTIK TAPE 6462 PC POLYPROPYLENE FILM/2 SIDE TS RUBBER/FLS	GSEFC4792	1.51	.00					TRANSFER TAPE
MYSTIK TAPE 6468 TRANSFER FILM/ACRYLIC ADH/k	GSEFC1952	2.69	1.49					TAPE
MYSTIK TAPE 7000 FIBER GLASS/SILICONE ADH/S	GSEFC63229	1.41	.05					TAPE
MYSTIK TAPE 7021 GLASS CLOTH/ACRYLIC ADH/F	GSEFC05963	3.2	.67					2 SIDED TAPE
MYSTIK TAPE 7321 PC POLYESTER FILM/ THERMOSET RBR ADH/R	GSEFC79597	1.45	.49					TAPE
MYSTIK TAPE 7341 PC POLYESTER FILM/ACRYLIC ADH/k	GSEFC3475	-23	.04					TAPE
MYSTIK TAPE 7341 PC POLYESTER FILM/ACRYLIC ADH/k	GSEFC5284	-25	.03					TAPE
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	GSEFC5312	-19	.03					TAPE
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	GSEFC6401	-92	.07					TAPE
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	GSEFC7625	-49	.64					TAPE
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	GSEFC7853	-57	.14					TAPE
MYSTIK TAPE 7362 KAPTON/SILICONE ADH/F	GSEFC6593	-66	.17					TAPE
MYSTIK TAPE 7362 KAPTON/SILICONE ADH/F	GSEFC7997	-65	.03					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC874	4.06	1.03					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC4904	2.19	1.43					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC664	4.87	2.4H					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC167	4.92	1.38					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC617	4.99	1.49					4 SIDED TAPE
MYSTIK TAPE 7366 KAPTON/CLOTH LINER/2 SIDE SIL	GSEFC150	5.79	24H					4 SIDED TAPE

MATERIAL	REFERENCE	DATA	XTEL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
MYSTIK TAPE 7367 KAPTON/ACRYLIC ADH/F	GSCF2915	-6.3	-0.4				AIR	
MYSTIK TAPE 7367 KAPTON/ACRYLIC ADH/F	GSC10308	-6.9	-0.2	24H	93	AIR	AIR	
MYSTIK TAPE 7370 TEDLAR/ACRYLIC ADH/R GRAY	GSC10311	-4.0	-0.2				AIR	
MYSTIK TAPE 7375 TEDLAR/ACRYLIC ADH/R WHITE	GSCF3473	1.40	-0.2				AIR	
MYSTIK TAPE 7402 ALUM FOIL/SILICONE ADH/R	GSCF1093	1.39	-0.2				AIR	
MYSTIK TAPE 7420 CCPEER FOIL/ACRYLIC ADH/R	GSCF4544	1.33	-0.2				AIR	COMPOSITE
MYSTIK TAPE 7430 RUBBER BASE ADHESIVE ONLY/F	GSCF2507	1.21	-0.2				AIR	
MYSTIK TAPE 7430 ALUM FOIL/RUBBER ADH/F	GSPC5923	5.00	-0.2				AIR	
MYSTIK TAPE 7432 ALUM FOIL/ACRYLIC ADH/R	GSCF1714	2.45	-0.2				AIR	
MYSTIK TAPE 7453 ALUM FOIL/ACRYLIC ADH/R	GSCF4490	2.09	-0.2				AIR	
MYSTIK TAPE 7503 TEFILON/SILICONE ADH/F LOT ALM411H	GSC11297	3.00	-0.2				AIR	
MYSTIK TAPE 7505 TEFILON/SILICONE ADH/R	GSPC6339	2.21	-0.2				AIR	
NAMEPLATE ANODIZED ALUMINUM 3/8" TAPE 467 ADH/F	GSPC6818	1.63	-0.2				AIR	
NAMEPLATE PHOTO ALUMINUM W/ADH ON FOIL	GSPC6932	1.10	-0.2				AIR	
NAMEPLATE PHOTO SENSITIVE ALUM/ANODIZED/SEALED	GSC11929	1.10	-0.2				AIR	
NAMEPLATE PHOTO SENSITIVE ALUM/ANODIZED/SEALED BLACK	GSC11950	1.10	-0.2				AIR	
NAMEPLATE 3655 BLACK/ALUM PVC W/ADH/F	GSPC9479	2.95	-0.2				AIR	
NAMECO 3135/1 AS/1 BW EPOXY	GSPC3257	1.00	-0.2				AIR	
NAMECO 328 SHEET ADESIVE	GSPC10PN	1.11	-0.2				AIR	
NAMECO 550/120 EPOXY/GLASS PRE-PREG	GSPC09PN	1.21	-0.2				AIR	
NAMECO 550/1581 EPOXY/Glass PRE-PREG	GSPC4059	1.00	-0.2				AIR	
GSPC4704	-6.3	-0.2					AIR	LAMINATE
GSPC5595	2.26	-0.2					AIR	
NAME 560 WATER BASE LATEX SI02 PAINT	GSPC3031	10.96	-0.3				AIR	
NAME 581 A/B AS 4/1 NEW OPTICAL CEMENT - EPOXY	GSPC9236	10.96	-0.2				AIR	
NE LCO 11-4205-2 E-GLASS FR4 FABRIC/EPOXY COATED	GSPC6392	1.29	-0.2				AIR	
NEOPRENE # GASKET SEAL	GSC13407	9.04	-0.2				AIR	
NEXTEL 3101-C11/ILLAS 8/1 BN BLACK SUBDE PAINT	GSPC1660	2.21	-0.2				AIR	
NP 1006 PPO/PIBEE GLASS AS 70/30	GSPC0939	1.32	-0.2				AIR	
NICKEL BLACK/BLACK/ELECTROLESS PLATED ALUMINUM	GSPC1603	1.15	-0.2				AIR	
NICKEL DULL PLATED ALUMINUM	GSPC1597	1.28	-0.2				AIR	
NICKLE BLACK/COFFEE ALUMINUM	GSPC1669	1.31	-0.2				AIR	
NO-FLG A11-168-65 FIBER PREP LAMINATE	GSC12874	2.22	-0.2				AIR	
NOA 60 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSC11473	2.24	-0.2				AIR	
NOA 60 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSC11539	2.19	-0.2				AIR	
NOA 61 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSC11541	2.19	-0.2				AIR	
NOA 61 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSC11489	2.27	-0.2				AIR	
NOA 63 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSC11491	2.89	-0.2				AIR	
NOA 65 OPTICAL ADHESIVE/F 5 MIN UV EXP	GSPC9521	1.61	-0.2				AIR	
NODE BOND BXR-10176 LA-125 THERMOSET ADH/F	GSC13454	-5.7	-0.4				AIR	
NODE BCND GG-288-8 BATCH 108	GSC13454	-5.7	-0.4				AIR	
NO NEX N-44 WHITE THREAD NATURAL 5977L	GSC13257	3.01	-0.2				AIR	
NO PCO A206-1	GSPC0005	2.00	-0.2				AIR	
NO PCO G302	GSPC0004	1.30	-0.2				AIR	
NO PCO G500 POLYURETHANE FOAM - WHITE	GSPC4670	1.19	-0.2				AIR	
NO PCO H-402N WITH EVA COVER	GSPC122PN	21.40	-1.03				AIR	
NO PCO J106 POLYURETHANE FOAM	GSPC132PN	23.20	-1.03				AIR	
NO PCO J106 POLYURETHANE FOAM	GSPC0051	1.12	-1.00				AIR	

MATERIAL	DATA REFERENCE	RTD/L	RCV/M	CURE TIME	CURE TEMP	AIR HUM	APPLICATION
NOPCO J106 POLYURETHANE	GSPC0054	1.19	.02	4H	32	CU	FOAM
NORFLEX N221 POLYOLEFIN SHRINK TUBING PRE-SHRUNK	GSPC6071	.78	.11				
NORTON EAR VIBRATION DAMPING FOAM	GSPC2342	15.49	9.36				
NORYL EN 295	GSPC9338	-0.17	-0.02				
NORYL GPN-3-801 MOI PPO	GSPC3574	-0.03	-0.02				
NORYL N300 BLACK	GSPC9353	-0.25	-0.02				
NORYL- MODIFIED PPO	GSEK0707	-0.10	-0.02				
NS 43C WHITE PAINT K2S103/ZNO/AL2O3/TiO2	GSC12481	3.40	-0.02	14D	25	AIR	SURINK TUBING
NS 43A GREEN PAINT K2S103/ZNO AS 1/3 BN 1/3 COBALT	GSPC8315	2.16	-0.02	24H	25	AIR	FOAM
NT 114 POLYIMIDE COATING	GSPC6881	3.69	-0.02	48H	25	AIR	INSULATION
NY E 183 SPECIAL OIL FOR BEARING LUBRICATION	GSPC2505	17.69	11.49				
NYLAFL F3/5 NYLON FOAM/15% GLASS FIBER	GSPC3742	1.17	-0.02				
NYLAFL GLASS FILLED NYLON	GSPC10224	1.07	-0.02				
NYLAFL 413 HOSE BLACK OUTER SHEATH QML	GSPC9324	5.52	-0.02				
NYLAFL 64 AW SINTERED NYLON OIL RESERVOIR	GSPC12649	7.3	-0.02				
NYLEZE MAGNET WIRE INSULATION - RED {COATING ONLY}	GSPC44846	1.43	-0.02				
NYLEZE MAGNET WIRE INSULATION - GREEN {COATING ONLY}	GSPC42948	1.17	-0.02				
NYLON CARE GUIDE AD FLAME RETARLANT DF	GSPC4226	2.49	-0.02				
NYLON FILM-ANTISTATIC DF	GSPC68440	2.02	-0.02				
NYLON MOLDED INSERTS NEUTRAL COLOR	GSPC11699	2.36	-0.02				
NYLON NETTING	GSPC24691	1.41	-0.02				
NYLON ORANGE MIL-C-7020P TYPE I SUNSHADE MATL	GSPC25139	1.02	-0.02				
NYLON ROD PER MIL-E-17091	GSPC2569	1.13	-0.02				
NYLON 6 BLACK CAELF CLAMP - WECKES EN	GSPC3357	0.84	-0.02				
NYLON 6 FASTENER - WHITE	GSPC72193	2.7	-0.02				
NYLON 6/6 PC BD CHANNEL BLACK GLASS FILLED FLAME RET	GSPC24552	1.39	-0.02				
NYLON/GLASS AS 7Q/30 CONNECTOR INSERT - CANNON	GSPC3259	0.91	-0.02				
O RING - SILICONE	GSPC5655	1.12	-0.02				
O RING - VITON A	GSPC12097	1.21	-0.02				
O RING 1109 BLACK NITRILE RUBBER	GSPC8123	0.35	-0.02				
O RING 5560 BLACK NITRILE RUBBER	GSPC8096	0.78	-0.02				
OI 100 GLASS RESIN 40% BW IN ETHANOL/F	GSPC7805	0.15	-0.02				
OI 650 GLASS RESIN 40% BW IN ETHANOL/F	GSPC5884	2.59	-0.02				
OI 650 RESIN REGULAR	GSPC5884	2.51	-0.02				
OI 650 RESIN WHITE PAINT GSPC SHAI	GSPC2233	0.77	-0.02				
OI 650 RESIN WHITE PAINT/ZRO GSPC TRQLQ	GSPC5843	0.87	-0.02				
OPTICAL COUPLING CEND - SILICON THREAD (PROPRIETARY)	GSPC7856	2.08	-0.02				
ORCOFILM KN-10 KAPTON/NOMEX THREAD POLYESTER BINDER	GSPC10562	1.92	-0.02				
ORCOFILM KN-10 KAPTON/NOMEX THREAD POLYESTER BINDER	GSPC9945	1.19	-0.02				
ORCOTAPE 01-6/P KAPTON/NOMEX THREAD POLYESTER BINDER	GSPC9141	1.41	-0.02				
ORTEC EPOXY ALUMINUM COVER	GSPC9167	12.26	7.33				
ORTEC EPOXY GOLD COVER	GSPC3313	0.06	-0.02				
P 400/CAT 515 AS 1/1 BW EPOXY	GSPC3311	6.07	-0.02				
P 764 EPOXY PRIMER EPON 828 BASE	GSPC6497	3.30	-0.02				
P 764-1A WHITE SILICONE PAINT	GSPC2328	2.66	-0.02				
P-17 POLYURETHANE FOAM - OPEN CELL	GSPC7149	2.59	-0.02				
P-17 POLYURETHANE FOAM 0-.062 THICK WHITE	GSPC3164	6.0	-0.02				
P-17 POLYURETHANE FOAM 0-.062 THICK WHITE	GSPC4304	4.77	-0.02				
P-17 POLYURETHANE FOAM 0-.186 THICK WHITE	GSPC4309	4.49	-0.02				
P-22 POLYURETHANE FOAM OPEN CELL	GSPC13159	1.11	-0.02				
	GSPC6017	1.28	0.07				

MATERIAL	DATA REFERENCE	X-TML	XCYC	CURE TIME	CURE TIME	ATMOS	APPLICATION
P-25 POLYURETHANE FOAM OPEN CELL	GSFPC6029	.92	.04	24H	24H	AIR	FOAM
P-460 A/B AS 100/7 BENEZYL PEROXIDE	GSFEC7790	3:18	.02	10M	10M	AIR	ADHESIVE
P-61 SILICA FILLED EPOXY	GSFEC4974	1:31	.04	2H	100	AIR	LUBE ADHESIVE
P-65 POLYETHER URETHANE FOAM WHITE	GSFPC4348	.47	.11	24H	100	AIR	FOAM
P-65 POLYETHER URETHANE FOAM WHITE	GSFPC4350	.29	.04	24H	100	AIR	FOAM
P-65 POLYETHER URETHANE FOAM WHITE H2O WASH	GSFPC4352	.91	.04	24H	100	AIR	FOAM
P-65 POLYETHER URETHANE FOAM WHITE ISOCYANATE WASH	GSFPC4372	.61	.02	24H	100	AIR	FOAM
P-65 POLYETHER URETHANE FOAM WHITE METOH WASH	GSFPC4346	.14	.02	24H	100	AIR	FOAM
P-82 EPOXY EPOXY	GSFC3662	.16	.03	7H	125	AIR	PUTTING
PA 61 CERAMIC PAINT	GSFPC3576	.09	.00	1H	60	AIR	INSULATION
PAINT 2019 WHITE EPOXY FER MIL C 22750C/P	GSFRC8963	1.50	.07	1H	60	AIR	PAINT
PAINT 2019	GSFRC2152	2.04	.23	14D	25	AIR	PAINT
PAINT 2019 OVER PRIMER 2012	GSFRC0954	2.92	.07	16H	25	AIR	PAINT
PALADIN FLACK SATIN LACQUER	GSFPC4354	.27	.13	30M	937	E-6	LACQUER
PALADIN BLACK SATIN LACQUER	GSFPC6233	6:42	1.69	48H	93	AIR	LACQUER
PALMER CEMENT 0014	GSFPC7193	4:02	.01	16H	25	E-6	LACQUER
PAN-TRY CABLE MOUNT	GSFPC5242	.63	.04	1H	60	AIR	ADHESIVE
PAN-TRY CABLE TIE LIGHT BROWN	GSFEC5286	3:44	.01	1H	60	E-6	LACQUER
PAN-TRY CABLE TIE NILON BARCON	GSC13546	3:13	.01	1H	60	E-6	LACQUER
PAN-TRY CABLE TIE NILON NATURAL	GSC13549	1:21	.01	1H	60	E-6	LACQUER
PAN-TRY CABLE TIE NYLON BLUE	GSC13552	.08	.02	1H	60	E-6	LACQUER
PARASOL CAGT-76 LIQUIDATE NYLON/MYLAR/ALUM	GSPC0830	4:7:7:0	.08	25:30H	937	E-6	ADHESIVE
PARKER O-LUBE BARIUM BASE GREASE	GSPC011PN	1:1:2:1	.08	1H	60	E-6	LACQUER
PARKER O-RING B-915-70 VISTALON 404	GSPC0710	2:2:2	.08	1H	60	E-6	LACQUER
PARKER O-RING E-577-8 BLACK EPK	GSPC8684	2:2:2	.47	1H	60	E-6	LACQUER
PARKER O-RING I-907-7 RED FLUOROSILICONE	GSPC8508	0:5	.01	1H	60	E-6	LACQUER
PARKER O-RING L-806-80 BLUE FLUOROSILICONE	GSPC8887	.32	.03	1H	60	E-6	LACQUER
PARKER O-RING L-946-90 BLUE FLUOROSILICONE	GSPC13517	1:80	.77	1H	60	E-6	LACQUER
PARKER O-RING N-219-7 BUNA-N	GSPC0686	4:49	2:44	1H	60	E-6	LACQUER
PARKER O-RING N-299-5 BUNA-N	GSPFCUP980	14:7	6:42	1H	60	E-6	LACQUER
PARKER O-RING N-745-7 NITRILE	GSPC0674	2:2:2	.42	1H	60	E-6	LACQUER
PARKER O-RING N-674-70 BUNA-N	GSPC2875	4:58	2:40	1H	60	E-6	LACQUER
PARKER O-RING S-383-70 RED SILICONE	GSPC8690	4:9	1:17	1H	60	E-6	LACQUER
PARKER O-RING S-455-70 RED SILICONE	GSPC9506	1:18	0:02	1H	60	E-6	LACQUER
PARKER O-RING S-604-7 SILICONE	GSPC2372	1:11	.02	1H	60	E-6	LACQUER
PARKER O-RING S-941-5 SILICONE	GSPC9677	1:29	.09	1H	60	E-6	LACQUER
PARKER O-RING V-747-75 VITON DUP E60C FLUOROCARBON	GSPC3375	6:10	.07	1H	60	E-6	LACQUER
PARKER O-RING V-023-75 VITON A	GSPFC0815	6:35	.02	1H	60	E-6	LACQUER
PARKER O-RING V-77-545 VITON A	GSPC9683	6:11	.02	1H	60	E-6	LACQUER
PARKER SEAL S 18C8-50 GREEN SILICONE	GSPC8216	4H	198	24H	177	AIR	SEAL
PBI FOAM 41/CO F1	GSFPC6176	4:09	.01	24H	482	AIR	ULAT SHIELD

MATERIAL	DATA REFERENCE	X-TNL	XCVCM	CURE TIME	CURE TEMP	AIR TEMP	APPLICATION
PDI FOAM 4# CLO-PI SAMPLE 925-30 POLYBENZIMIDAZOLE	GSEFC6299	2-37	.09	30M	496	AIR	HEAT SHIELD
PDI THREAD - POLYESTER AS 5/4 BN	GSEFC8657	10-93	.99			AIR	THREAD WRITING
PC 12-007 A/B AS 5/4 BN	GSEFC5343	6-17	.09	16H	80	AIR	PUTTING
PC 17 A/B AS 2/1 BN	GSEFC4376	4-97	.09	12H	121	AIR	CONF COAT
PC 17 A/E AS 2/1 BN	GSEFC4492	13-85	.07	7D	25	AIR	CONF COAT
PC 17 A/E AS 2/1 BN	GSEFC4988	12-21	.06	30H	25	AIR	CONF COAT
PC 18 POLYURETHANE COATING	GSEFC3588	7-01	.06	5H	65	AIR	COATING
PC 18M ONE PART POLYURETHANE COATING/F	GSEFC7733	4-51	.20	1H	59	AIR	CONF COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	GSEFC0936	2-36	.39	24H	75	AIR	CONF COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	GSEFC7739	3-10	.05	2H	60	AIR	CONF COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	GSEFC7832	1-04	.05	7D	25	AIR	CONF COAT
PC 18M POLYURETHANE COATING CLEAR 50% RH CURE/F	GSEFC7835	.38	.03	10H	80	AIR	CONF COAT
PC 20M ONE PART ACRYLIC COATING/F	GSC11306	4-30	.05	24H	80	AIR	PUTTING
PC 22 A/E AS 3/1 EK	GSEFC0936	7-75	.05	8H	66	AIR	PUTTING
PC 22 A/E AS 3/3 EK	GSEFC1008	7-42	.05	3H	60	AIR	PUTTING
PC 401/T AS 100/17 BN SILK SCREEN EPOXY GREEN	GSC11553	1-59	.18	30H	100	AIR	COATING MASK
PC 401/T AS 100/17 BN SILK SCREEN EPOXY GREEN	GSC11636	1-72	.04	3-5H	160	AIR	COATING MASK
PC-5147 BLACK COATING	GSEFC1480	4-31	.12	24H	25	AIR	PAINT
PD 147 (RTV 511)	GSEFC5022	-11	.30	10H	93	AIR	COATING
PD 200-16 FOAMED RTV 560	GSEFC4990	1-12	.49	10H	93	AIR	L-O
PD 200-16 FOAMED RTV 560	GSEFC4992	.03	.02	10H	93	AIR	PUTTING
PE NNTUBE LI SO 3-7164 X/C TEFLON TUBING	GSEFC6074	0-1	.00	24H	177	AIR	PUTTING
PE NNTUBE V POLYOLEFIN SHRINK TUBE CLEAR	GSEFC4638	4-45	.13	5H	150	AIR	SHRINK TUBING
PE NNTUBE V POLYOLEFIN SHRINK TUBE BLACK	GSEFC4640	8-42	.75	5H	80	AIR	SHRINK TUBING
PLINTON - CHLORONATED POLYETHER	GSEFC4063	8-42	.33	3H	25	AIR	BUILD CPND
PERMA-LOK HL120 FRCM SHIMS	GSC12964	3-29	.37	48H	22	AIR	AIR-SEALANT
PERMA-LOK HL126 FRCM SHIMS	GSC12965	3-29	.02	48H	22	AIR	AIR-SEALANT
PERMA-LOK HL138 FRCM SHIMS	GSC12967	4-16	.03	48H	25	AIR	AIR-SEALANT
PERMA-LOK HM90 FRCM SHIMS	GSC12973	4-17	.04	48H	25	AIR	AIR-SEALANT
PERMA-LOK HH128 FRCM SHIMS	GSC12976	4-57	.13	48H	25	AIR	AIR-SEALANT
PERMA-LOK LM112 FRCM SHIMS	GSC12940	14-67	.10	4-46	48H	25	AIR
PERMACEL TAPE EE-6379 KAPTON H/SILICONE ADH	GSEFC0217	2-31	.89			AIR	TAPE
PERMACEL TAPE EE-6600 ALUMINUM/POLYESTER RUBBER ADH	GSEFC14PN	8-50	3-90			AIR	TAPE
PERMACEL TAPE EE-6676 KAPTON H/SILICONE ADH/S	GSEFC219	2-51	1-39			AIR	TAPE
PERMACEL TAPE EE-6950 KAPTON 2 SIDE SILICONE ADH/F	GSC15757	1-94	.77			AIR	2-SIDED TAPE
PERMACEL TAPE EE-7240 GLASS CLOTH/ACRYLIC ADH/R	GSEFC3994	7-45	.33			AIR	TAPE
PERMACEL TAPE EE-7390 MYLAR FILM/ACRYLIC ADH/R	GSEFC4065	7-1	.02			AIR	2-SIDED TAPE
PERMACEL TAPE E-0512 SIDE ACRYLIC ADH/P	GSC11989	2-36	.93			AIR	2-SIDED TAPE
PERMACEL TAPE E-100 AL FULL/GLASS FABRIC/SIL ADH	GSEFC2089	3-08	1-73	1H	149	AIR	TAPE
PERMACEL TAPE E-212 GLASS CLOTH/SILICONE ADH/R	GSEFC4400	1-35	.47			AIR	TAPE
PERMACEL TAPE E-684 GLASS CLOTH/ACRYLIC ADH/F	GSEFC4684	1-73	.02			AIR	TAPE
PERMACEL TAPE E-6332 GLASS CLOTH/SILICONE ADH/F	GSEFC6332	1-47	.55			AIR	TAPE
PERMACEL TAPE E-5276 GLASS CLOTH/SILICONE ADH/F	GSEFC5276	1-27	.63	48H	150	E-5	TAPE
PERMACEL TAPE E-5144 GLASS CLOTH/SILICONE ADH/F	GSEFC5144	1-30	.63				

MATERIAL	DATA REFERENCE	X _{ML}	%CVCM	CURE TIME	CURE TEMP	ATRS	APPLICATION
PERMACEL TAPE 223 KAPTON FILM/SILICONE ADH/F	GSCF7121	1.80	.73	.01	3.0M	149	4-SIDED TAPE
PERMACEL TAPE 224 NYLAR/THERMOSET RUBBER ADH/k	GSCF13487	1.60	.37	3.5H	135	A.I.R.	TAPE
PERMACEL TAPE 262 AONEY FR NYLON PAPER TS ACK ADH	GSCFC3854	1.59	.37	2H	135	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 2650 ELD SILICON TAPE WRAP	GSCFC8825	.87	.25	.09	2.5	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 4220 TEFILON/SILICON TAPE ADH/R	GSPC4418	.75	.33	3H	21	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 4223 TEFILON/SILICON TAPE ADH/F	GSPC0296	.75	.33	3H	21	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 4224 TEFILON/SILICON TAPE ADL/S	GSPC2224	.1-1.39	.75	5.95	5.95	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 621 FIBERGLASS/SILICON TAPE ADH/S	GSPC2185	12.69	.24	11.58	11.58	A.I.R.	4-SIDED TAPE
PERMACEL TAPE 941 NYLAR/2 SIDE NATURAL RUBBER/R	GSECF4270	3.58	.58	11.79	11.79	A.I.R.	4-SIDED TAPE
PERVEL ANTISTATIC PAT BLUE	GSC11896	31.57	.16	1.16	1.16	F.U.A.N.	F.U.A.N.
PERVEL CONDUCTIVE FOAM BLACK HIGH DENSITY	GSC11872	12.25	.49	1.19	1.19	F.U.A.N.	F.U.A.N.
PERVEL CONDUCTIVE FOAM BLACK LOW DENSITY	GSC12094	31.57	.26	1.16	1.16	F.U.A.N.	F.U.A.N.
PERVEL 1H304 STATIC DISSIPATIVE MAT MAROON COLOR	GSC11899	1.50	.01	5M	63	4-SIDED ADHESIVE	4-SIDED ADHESIVE
PERVEL 38056 CLEAR ANTISTATIC FILM	GSCF3527	1.18	.01	5M	63	4-SIDED ADHESIVE	4-SIDED ADHESIVE
PERVEL CONDUCTIVE CEME EPCKY A/B AS 1/1	GSPC0927	1.18	.01	5M	63	4-SIDED ADHESIVE	4-SIDED ADHESIVE
PERVEL 1006 NYLON 6	GSC10457	1.18	.01	5M	63	4-SIDED ADHESIVE	4-SIDED ADHESIVE
PHENALL 8000 PHENCIL	GSPC7013	1-3.4	.04	5H	149	A.I.R.	4-SIDED CPND
PHENOLIC MOLD CPND PER MIL M14-CF1-10 BLACK	GSC12446	4-8.2	.04	5H	149	A.I.R.	4-SIDED CPND
PHENOLIC HOLD CPND PER MIL M14-CF1-10 BLACK	GSPC9720	3-29	.04	16H	150	A.I.R.	4-SIDED CPND
PHENOLIC EOD PER MIL-P-79C GRADE NA TYPE FBE	GSPC12206	3-30	.02	16H	150	A.I.R.	STRUCTURAL
PHENOLIC 76-0001-06/EPOXY ANHYDRIDE 76-Q001-10	GSPC142272	3-33	.07	16H	150	A.I.R.	STRUCTURAL
PHENOLIC/NATURAL LINEN STANDOFF	GSPC6362	3-026	.01	24H	125	A.I.R.	STRUCTURAL
PHENOLIC/NATURAL LINEN STANDOFF	GSPC7025	2-1.89	.04	1.97	1.97	A.I.R.	STRUCTURAL
PHOTO POLYLINER 6011G RIGID PCLYTHIOETHER	GSPC7103	2-5.6	.04	1.97	1.97	A.I.R.	STRUCTURAL
PHOTO POLYMER 9111 LOW VISCOSITY POLYTHIOETHER	GSPC7025	2-1.97	.04	1.97	1.97	A.I.R.	STRUCTURAL
PITTEL CA A/B ASS 1 EKOPA/A1 GN 6 CONDUCTIVE ADHESIVE	GSPC6992	2-5.58	.09	3D	25	A.I.R.	4-SIDED ADHESIVE PUTTY
PITTEL CP CONDUCTIVE PUTTY	GSPC6989	5-8.8	.09	2-1.18	2.18	A.I.R.	4-SIDED ADHESIVE PUTTY
PITT-GLAZE 16-402/E20 BASE ACRYLIC/EPOXY WHITE PAINT	GSPC9962	2-9.2	.25	7D	25	A.I.R.	ELASTOMER
PKT WHITE PAINT CT 650/POTASSIUM SULFATE AS 1/1 BG	GSPC12219	2-8.0	.67	14D	25	A.I.R.	PAINT
PLASTIC PART MOTOR CLA CMOS 1404 DTD 7720	GSPC9173	1-4.29	.67	10D	25	A.I.R.	PAINT
PLASTIC PART MOTOR CLA CMOS 1404 DTD 7731	GSPC9140	1-2.7	.01	2H	50	A.I.R.	PAINT
PLASTIC PART MOTOR CLA 74LS00 DTD 7732	GSPC9140	1-2.6	.01	2H	50	A.I.R.	PAINT
PLASTIC PART MOTOR CLA 74LS174 DTD 7733	GSPC9142	1-2.4	.01	2H	50	A.I.R.	PAINT
PLASTIC PART NATL SEMICONDUCTOR CMOS 4011 DTD 723	GSPC9144	1-2.4	.01	2H	50	A.I.R.	PAINT
PLASTIC PART NATL SEMICONDUCTOR CMOS 4044 DTD 727	GSPC8950	1-2.6	.01	2H	50	A.I.R.	PAINT
PLASTIC PART PCA CMOS 4011 DTD 723	GSPC8952	1-2.6	.01	2H	50	A.I.R.	PAINT
PLASTIC PART PCA CMOS 4044 DTD 701	GSPC9146	1-2.6	.01	2H	50	A.I.R.	PAINT
PLASTIC PART SIGNETICS 74LS00 DTD 7733	GSPC8954	1-3.8	.02	2H	50	A.I.R.	PAINT
PLASTIC PART SIGNETICS 74LS174 DTD 7733	GSPC9148	1-3.1	.02	2H	50	A.I.R.	PAINT
PLASTIC PART TEXAS INST 74LS00 DTD 7710	GSPC9150	1-2.4	.01	2H	50	A.I.R.	PAINT
PLASTIKOTE MFR VARAISH 277 - DATA PE CoAT CURE	GSPC0872	17.56	1.44	6H	25	A.I.R.	VARNISH
PLASTILOCK 717-B AVIGNE/EPOXY ADH	GSPC2463	1-0.9	.01	1H	21	A.I.R.	LENS
PLEXIGLAS VS-100 CRITICAL	GSPC0490	1-0.7	.01	1H	21	A.I.R.	LENS
PLEXIGLAS 11 UV	GSPC12736	13.55	.70	48H	25	A.I.R.	ADHESIVE
PLIOBOND 30 FROM TUBE/FOIL SANDWICH	GSC11105	3D	.63	1d	25	A.I.R.	ADHESIVE
PLV 2000 VITON ADHESIVE							

MATERIAL	REFERENCE	DATA	X-TML	X-CUR	CURE TIME	CURE TEMP	AIR CUR	APPLICATION
POLASHEET GRAY SILICONE SHEET/EMBEDDED MONEL WIRE POLASHEET GRAY SILICONE SHEET/EMBEDDED MONEL WIRE POLY CAST EC EPC/L LOT 173-4416-4	GSC11293 GSC11294 GSC11431	1.56 .83	.46 .27	24H 5H	177 171	AIR AIR	AIR ADHESIVE	SHIELD SHIELD
POLY-FLO TUBING 66F - POLYETHYLENE POLYCARBONATE/FIBER GLA AS 80/20	GSFPC8933	.46	.19	*03				BULK CPND
POLYCARBONATE CIRCUIT CARD GUIDE	GSFPC3093	*12						GUIDE
POLYCHROME FILM 8 MIL	GSFPC6119	*94						FLM
POLYCHROME 630 TAPE POLYTHENE RUBBER ADH/F	GSFPC5339	4-56	1-87					TAPE CPND
POLYETHERSULFONE 200P THERMOPLASTIC	GSFPC9844	1-04	*09					BULK CPND
POLYETHYLENE FILM ANTISTATIC DE CLEAR	GSFPC4908	1-41	*19					FILM
POLYETHYLENE FILM ANTISTATIC DE PINK	GSFPC9110	*20						FILM
POLYETHYLENE FILM 2 MILS ALATHON RESIN-BRANCHED	GSFPC7514	*14	*52					FILM
POLYETHYLENE PUTTING CARTRIDGE	GSFPC5779	1-10	*35					PUTTING
POLYETHYLENE ULTRA HIGH MOLECULAR WEIGHT	GSFPC4506	*02	*05					STRUCTURAL
POLYETHYLENE VAPC FILM 6 MIL	GSFPC109228	*06	*10					FILM
POLYGON SG-101 ACCMEOsite GLASS/SK 319 SILICONE	GSFPC5144	1-08	*23					INSULATION
POLYGUIDE LANIATING FILM	GSFPC19619	1-06	*33					CONF COAT
POLYCAST V-35-G-EEF	GSFPC1341	2-80	*16					AIR
POLYENCO POLYSTYRENE POWDER	GSFPC0197	*09	*09					STRUCTURAL
POLYSET EPC 68 BLUE EPOXY POWDER	GSC1111	*25	*03					ADHESIVE
POLYSET 521 BLACK								
POLYSTYRENE CO-EXTRUDED BLUE BOX	GSFPC8813	*30	*09					BULK CPND
POLYSTYRENE CO-EXTRUDED WHITE INSERT	GSC11878	*50						BULK CPND
POLYSILOGENE	GSC113891	*58						BULK CPND
POLYURETHANE COATING 22H ONE COMPONENT/FOIL	GSCFC5395	*33						BULK CPND
POLYURETHANE COATING 22H ONE COMPONENT/FOIL	GSC113404	*91						COATING
POLYURETHANE FILM 5500W RUBBER ADH/F	GSCFC7118	1-98						
POLYURETHANE FOAM EY STOCKWELL RUBBER	GSFPC4174	*53						
POLYURETHANE TUBING MP1485 PLASICIZED	GSFPC8438	*77						
POLYURETHANE 9250 ERON	GSFPC13245	*87						TUBING
POLYVINYL BUTYLATE FILM - BUTYLIC	GSFPC9793	1-83						
PORCUPINE METALASTIC SILICONE FILLED MONEL MESH	GSFPC12352	*65						
PORCUPINE METALASTIC SILICONE FILLED MONEL MESH	GSFPC12376	*99						SHIELDING
POREX ULTRA HIGH LIGHT POLYETHYLENE HEAT PIPE WICK	GSC113220	*11						SHIELD PIPE WICK
PORCN URETHANE FCAM 4701-01-20125-1633	GSC12538	1-09						TAPE
PORCN URETHANE FOAM 4701-01-20125-1633	GSC12551	1-35						DAMPER
PORCN URETHANE FCAM 4701-01-20125-1633	GSC12544	1-73						DAMPER
PORCN URETHANE FCAM 4701-01-20125-1633	GSC12544	4-35						DAMPER
PORTASSIUM TITANATE WHITE PAINT 150 GSF/C SHA1	GSFPC2227	*84						PAINT
PP 87 TAPE POLYPOXYLENE FILM/SYN LATEX ADH/F	GSFPC8489	*62						LAMINATE
PR 1201-Q/A/B AS 1/10 BW POLYSULFIDE	GSFPC5441	2-29						TAPE
PR 1221-A/B AS 10/1 BW POLYSULFIDE	GSFPC3592	36-32						BULK CPND
PR 1506 CLEAR PRIMER	GSFPC5303	57-39						GASKET SEAL
PR 1524 A/B AS 26/100 BW POLYURETHANE	GSFPC3151	*82						PUTTING
PR 1525 A/B AS 8/25 BW POLYURETHANE	GSFPC3215	*64						PUTTING
PR 1527 A/B AS 26/100 BW POLYURETHANE	GSFPC2565	*92						PUTTING
								E-O
								51
								72H

MATERIAL	DATA REFERENCE	XTCM	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
PR 1531 POLYURETHANE PRIMER							
PR 1535 A/B AS 3 1/2/100 BW POLYURETHANE	GSFC2452	5.97	2.29	24H	25	AIR	PRIMER
PR 1538 A/E AS 3 1/2/100 BW POLYURETHANE	GSFC3694	-6.8	.10	24H	82	AIR	HOLD CPND
PR 1538 A/B AS 3 1/2/100 BW POLYURETHANE	GSFC0785	1-6.6	.09	20H	82	AIR	PUTTING
PR 1538 A/B AS 3 1/2/100 BW POLYURETHANE	GSFC0800	-9.7	.02	20H	70	AIR	PUTTING
PR 1538 OVER PR 1531 A/B AS 3 1/2/100 BW	GSFC3690	-5.7	.05	144H	60	AIR	HOLD CPND
PR 1546L A/B AS 40/100 BW POLYURETHANE THICK BLOCK	GSFC2354	1-9.4	.59	16H	82	AIR	COMP COAT
PR 1546L A/B AS 40/100 BW POLYURETHANE THIN FILM	GSFC2345	-6.7	.06	24H	82	AIR	PUTTING
PR 1546L A/B AS 40/100 BW POLYURETHANE THIN FILM	GSFC8339	-6.3	.06	30H	82	AIR	COMP COAT
PR 1547 A/B AS 3 2/100 BW POLYURETHANE	GSFC8342	-7.8	.06	24H	82	AIR	COMP COAT
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	GSFC3688	-6.5	.03	84H	82	AIR	HOLD CPND
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	GSC11276	-7.2	.01	7D	82	AIR	PUTTING
PR 1564 A/E AS 7-7/100 BW POLYURETHANE	GSFC5429	-8.6	.02	24H	90	E-C	PUTTING
PR 1564 A/B AS 7-7/100 BW/BV POLYURETHANE CASTING	GSFC6338	1-1.2	.00	48H	85	AIR	ADHESIVE
PR 1568 AEROSOL URETHANE COATING/F	GSC10577	1-5.7	.05	16H	100	E-S	COMP COAT
PR 1568 AEROSOL URETHANE COATING/P	GSC10580	3-2.5	.02	12H	25	AIR	COMP COAT
PR 1568 AEROSOL URETHANE COATING/P	GSC10628	1-9.2	.04	24H	75	AIR	COMP COAT
PR 1568 AEROSOL URETHANE COATING/P	GSC10631	3-0.0	.02	7D	25	AIR	COMP COAT
PR 1568 AEROSOL URETHANE COATING/P	GSC6596	1-6.9	.08	3H	82	AIR	COMP COAT
PR 1568 DIP COATING/F	GSC10784	1-9.7	.04	7D	25	AIR	COMP COAT
PR 1568 DIP COATING/F	GSC10787	2-2.9	.05	1H	25	AIR	COMP COAT
PR 1570	GSFC7316	-3.5	.03	3H	82	AIR	PUTTING
PR 1570 A/B AS 1 1/4 BW POLYURETHANE	GSFC7511	1-3.4	.06	16H	82	E-O	PUTTING
PR 1570 A/B AS 1 1/4 BW POLYURETHANE	GSFC7532	1-4.9	.06	9H	82	AIR	PUTTING
PR 1574 A/B AS 18/100 BW POLYURETHANE	GSFC7400	-4.0	.04	25H	25	AIR	PUTTING
PR 1574 A/E AS 18/100 BW POLYURETHANE	GSFC7418	-5.4	.02	19H	82	AIR	PUTTING
PR 1592 A/B AS 53/100 BW POLYURETHANE	GSFC7235	1-0.1	.00	31H	74	AIR	PUTTING
PR 1592 A/B AS 53/100 BW POLYURETHANE	GSFC7316	-3.5	.03	24H	25	AIR	PUTTING
PR 1660 A/B AS 11-5/100 BW POLYURETHANE FILM	GSFC6341	1-8.6	.01	16H	65	AIR	ADHESIVE
PR 1660L A/B AS 1 1/4 BW AMBER POLYURETHANE LOT C21828	GSFC9359	1-8.6	.01	16H	130	AIR	ADHESIVE
PR 1660L A/B AS 1 1/4 BW AMBER POLYURETHANE	GSFC7553	-8.6	.01	16H	65	AIR	COMP COAT
PR 1660L A/B/CAD-6-SIL 6-5 AS 25/100/BW/PGMT/DEFOAM	GSFC4250	-8.1	.00	14D	25	AIR	ADHESIVE
PR 1710 A/B/CAD-6-SIL 6-5 AS 25/100/BW/PGMT/DEFOAM	GSFC9479	-3.8	.01	16H	25	AIR	ADHESIVE
PR 1710 POLYSULFIDE SEALANT	GSFC9482	.66	.04	1H	121	AIR	SEALANT
PR 1930-2 A/B AS 10/1 BW SILICONE	GSFC3814	1-35	.07	7D	25	AIR	SILICONE
PR 365 BLACK POLYURETHANE RUBBER	GSC1132	3-34	.69	14D	25	AIR	GASKET

MATERIAL	REFERENCE	DATA	XTHL	XVCH	CURE TIME	CURE TEMP	AIR HS	APPLICATION
PR 420 ORANGE PRIMER	GSFC7310	5.41	1.30	2H	25	AIR	PRIMER	
PR 420 PRIMER/ACRYLIC	GSFC2547	12.49	.01	16H	82	AIR	PRIMER	
PREFAB AKOTE	GSFC1393	3.43	.37	7D	25	AIR	PRIMER	
PRIMER DESOTO 513-102/E	GSC10014	2.50	.39	14D	25	AIR	PRIMER	
PRIMER RANDOLPH GREEN ZINC CHROMATE	GSFC2224	3.23	.23	24H	25	AIR	PRIMER	
PRIMER RANDOLPH GREEN ZINC CHROMATE	GSFC2255	2.32	.23	30H	25	AIR	PRIMER	
PRIMER ZINC CHROMATE	GSFC2275	3.23	.22	24H	25	AIR	PRIMER	
PRIMER 3-1/4-24/3-1E-8 AS 3/1 BV EPOXY URETHANE WHITE	GSFC11884	7.06	.22	19	25	AIR	PRIMER	
PRIMER 636/CAT 6361 AS 1/1 BV	GSFC11194	2.24	.19	16H	25	AIR	PRIMER	
PRINT-KOTE SC 14-2 ON FOIL	GSFC5289	3.45	.79	16H	25	AIR	CONF COAT	
PRINT-KOTE SC 14-2 ON FOIL	GSFC5621	1.47	.38	24H	100	AIR	CONF COAT	
PROFILE F60-20 POLYFROG AS 1/1 EPOXY FIBER	GSFC4040	4.16	.04	1-47	24H	AIR	FOAM	
PROFILE F-147-66/F-863-66 AS 1/1 B-6 POLYURETHANE EPOXY/F	GSFC10097	4.01	.02	1-14	24H	AIR	PRIMER	
PROOF BOARD CLOSED CELL POLYURETHANE FOAM	GSC10017	1.14	.00	30H	100	AIR	INSULATION	
PROOF BOARD CLOSED CELL POLYURETHANE FOAM	GSC10035	1.36	.00	24H	25	AIR	INSULATION	
PROSEAL 790-80 A/B AS 10/3 BW	GSFC0390	1.41	.02	24H	82	AIR	JETETHANE	
PROSEAL 799 A/L AS 100/41 BW PURPLE POLYURETHANE	GSFC0420	1.21	.02	16H	80	AIR	JETETHANE	
PRP 11165 SILICONE O-RING	GSC122778	9.97	.67	12H	82	AIR	CUTTING	
PRUFCAUT 4000 BLACK EPOXY PAINT/542 RED PRIMER	GSFC5346	9.30	.04	24H	25	AIR	O-RING COMPOSITE	
P3 18 ACRYLIC CEMENT	GSFC2753	.73	.00	72H	25	AIR	ADHESIVE	
PT 201 THERMOSETTING YELLOW GOLD EPOXY COATING/P	GSFC12355	.96	.07	1H	163	AIR	COATING	
PT 207 POLYVINYL FLUORIDE	GSFC10557	3.88	.07	48H	25	AIR	COATING	
PT 401 WHITE PAINT	GSFC10346	3.00	1.30	15H	25	AIR	PAINT	
PT 401/H-11 AS 16/1 BV WHITE PAINT	GSFC2783	1.87	.07	90H	121	AIR	PAINT	
PT 401/H-11 AS 16/1 BV GLOSSY WHITE EPQX	GSC11366	1.05	.10	15H	66	AIR	PAINT	
PT 4121 A/B AS 16/1 B-6 EPOXY	GSFC1648	13.27	.20	90H	121	AIR	ADHESIVE	
PT 4121 A/B AS 160/73 BW EPOXY	GSFC4994	8.31	.03	5H	54	AIR	CONF COAT	
PT 426 A/B AS 1/1 EV FILM GLOSSY WHITE EPOXY	GSC11336	1.89	.14	24H	52	AIR	ADHESIVE	
PT 426 A/B AS 1/1 EV FILM GLOSSY WHITE EPOXY	GSC11339	1.28	.13	2H	25	AIR	PAINT	
PT 750 A/E AS 3/1 EV POLYURETHANE	GSC11437	1.74	.13	40H	71	AIR	PAINT	
PUTTY VACUUM SEALING	GSFC2993	10.95	.01	24H	25	AIR	SEALANT	
PV 100 SILICONIC WHITE PAINT	GSFC1966	1.87	.48	24H	177	PSI	PAINT COMPOSITE	
PYRALIN 12 POLYIMIDE PREPREG	GSFC2332	2.86	.06	30H	260	PSI	LAMINATE	
PYRALIN 3 POLYIMIDE COPPER CLAD 2 SIDES .5 MILS THICK	GSFC1174	2.37	.07	2H	177	PSI	LAMINATE	
PYRALUX FILM POLYIMIDE 2 MILS THICK	GSFC7484	1.14	.00	1H	177	AIR	FILM	
PYRALUX FILM SUPPORT/ACRYLIC FILM ADH - AMBER	GSFC8804	.34	.00	1H	204	AIR	FILM ADHESIVE	
PYRALUX 329-97 CLOTH SUPPORTED FILM ADHESIVE	GSFC877	.20	.01	2H	154	AIR	FILM ADHESIVE	
PYREML BK 692 POLYIMIDE 15 MIN FLASH/COAT	GSFC5097	.96	.00	15H	149	AIR	COATING	
					30H	204		

MATERIAL	DATA REFERENCE	XTHL	XCVS	CURE TIME	CURE TIME	ATMOS	APPLICATION
PYRE-ML RK 692 POLYIMIDE	15 MIN FLASH/COAT	GSPC5100	.86	.0	15H	AIR	FLASH
PYROMARK STANDARD WHITE SILICONE ON ALUMINUM		GSPFC0323	.06	.02	30H	AIR	PAINT
PYROMARK STANDARD WHITE SILICONE ON EPOXY		GSPC0326	.46	.03	24H	AIR	PAINT
PYROMAKER HIGH TEMP WHITE MARKER/F		GSC11785	.83	.42	7D	AIR	MARKER
PYRONE 15A EPOXY PRIMER		GSPFC1843	.49	.03	1H	AIR	LIQUID CPND
P527 PRIMER EPOXY/POLYAMIDE		GSPFC3620	.97	.10	15H	AIR	PRIMER
Q DOPED POLYSTYRENE COAT COATING		GSPFC4284	.72	.12	24H	AIR	COAT COATING
QED HIGH VAC SEALANT SILICONE IN XYLENE		GSPFC1954	.55	.04	2H	AIR	SEALANT
QF 1006 NYLON 6/10 30% FIBER GLASS		GSPFC0906	.65	.04	16H	AIR	LIQUID CPND
QR-4-3117 ONE PART SILICONE		GSPFC4818	.49	.19	7D	AIR	SILICONE
QR-4-3117 ONE PART SILICONE		GSPFC5040	1.0	.25	16H	2H	SILICONE
R01-2577 CLEAR SILICONE		GSC13111	.27	.85	24H	AIR	PAINT BASE
R01-2577 WHITE SILICONE		GSPC12685	.27	.59	25D	AIR	PAINT ADHESIVE
R02-1206 OPTICAL COUPLING COMPOUND		GSC13114	.72	.47	25D	AIR	PAINT
R02-1207 A/B AS 1/1 BW OPTICAL COUPLING CPND		GSC10341	.77	.05	1H	AIR	PAINT
R03-6597 A/B AS 1/1 BW BLACK SILICONE		GSC12997	.73	.95	24H	AIR	OPTICAL COUPLE
R03-6597 A/B AS 1/1 BW BLACK SILICONE		GSC13230	.95	.41	10D	AIR	ENCAPSULANT
R03-6597 A/B AS 1/1 BW BLACK SILICONE		GSC13233	.33	.31	2H	AIR	COATING
R03-6597 A/B AS 1/1 BW BLACK SILICONE		GSC12613	.26	.00	24H	AIR	TERMAL BLANKET
R05-9384 COATED VULCANIZED KAPTON		GSC12616	.26	.21	24H	AIR	CONF COAT
R05-9384 COATED VULCANIZED KAPTON		GSC12760	.26	.01	7D	AIR	CONF COAT
R-11520 ONE COMPONENT SILICONE - CLEAR LOT 013-166		GSPC12394	.16	.05	25	AIR	AIR-SEALANT
R-11520 ONE COMPONENT SILICONE - CLEAR LOT 013-166		GSC12655	.16	.05	25	AIR	AIR-SEALANT
R-11500 ONE COMPONENT ELEC COND SILICONE LOT 013-058		GSC12631	.15	.05	25	AIR	AIR-SEALANT
R-11500 ONE COMPONENT ELEC COND SILICONE LOT 013-087		GSCC12946	.15	.06	25	AIR	AIR-SEALANT
R-11500 ONE COMPONENT ELEC COND SILICONE LOT 013-087		GSCC1711	.17	.03	30H	AIR	POTTING
R-1779 CYCLOALIPHATIC EPOXY/PILLED		GSPC17098	.17	.03	30H	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12634	.27	.04	30H	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12895	.25	.05	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12658	.25	.05	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12949	.29	.03	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSCC12937	.23	.03	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSCC12898	.23	.03	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12586	.28	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12661	.22	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12897	.44	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12397	.35	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12718	.34	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12664	.31	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12952	.30	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12640	.29	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12686	.29	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12400	.62	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12643	.41	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12889	.31	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12688	.38	.02	7D	AIR	POTTING
R-25500 CYCLOALIPHATIC EPOXY/PILLED		GSC12739	.1	.03	30H	AIR	POTTING
R-313 A/B AS 100/8 BW EPOXY		GSPC0305	1.71	.19	24H	2H	ADHESIVE
R-313 A/B AS 100/8 BW EPOXY					12H	66	ADHESIVE

MATERIAL	DATA REFERENCE	XTEL	%CVCM	CURE TIME	TEMP	ATMOS	APPLICATION
RADITE 75 RATE GRO INSULATION MATERIAL	GSCF5431	1-38	.00				WLD CPND
KAYBESTOS 4500 FRICTION MATERIAL	GSC10711	29	2.98				INSULATION PAD
RAYCHEM COAX 5026A-121-9 ORANGE INNER INSUL	GSCFC53307	21-02	.30	16H	110	E-3	WHITE INSUL
RAYCHEM COAX 5026A-121-9 WHITE OUTER INSUL	GSCFC53364	-72	.34				WHITE INSUL
RAYCHEM KYNAR PRE-SHRUNK	GSCFC0242	-28	.28				SHRINK TUBING
RAYCHEM POLYALKENE WIRE INSULATION YELLOW	GSCFC2701	1-73	.01				WHITE INSUL
RAYCHEM POLYALKENE WIRE INSULATION CROSSLINKED	GSCFC9892	-75	.34				WHITE INSUL
RAYCHEM POLYALKENE WIRE 88B0811-20-9 WHITE	GSCFC5199	-15	.37				WHITE INSUL
RAYCHEM POLYOLEFIN WIRE 88B0811-20-9 GRAY	GSCFC5198	-14	.01				WHITE INSUL
RAYCHEM POLYOLEFIN MT 13-4 SHRINK TUBE PREGSHRUNK	GSCFC493	-82	.01	10H			SURFACE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J020137502	GSC11014	-49	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J040829704 INNER	GSC11020	-18	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J040829704 OUTER	GSC11022	-04	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J060407705 INNER	GSC11032	-17	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J060407705 OUTER	GSC11034	-17	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J110206911 INNER	GSC11024	-96	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J110206911 OUTER	GSC11028	-68	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1105187913 INNER	GSC11030	-22	.04				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT J1105187913 OUTER	GSC11032	-67	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT P051107814	GSC11012	-65	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL LOT P06022689014	GSC11016	-26	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSUL WHITE LOT P0505157909	GSC11018	-29	.05				WHITE INSUL
RAYCHEM SPEC 44 WIRE INSULATION WHITE	GSCFC2703	-52	.07				WHITE INSUL
RAYCHEM SPEC 44/AU111 GEN PURGE GRADE WIRE INSUL	GSCFC5825	1-89	.08				WHITE INSUL
RAYCHEM SPEC 44/0411 SPACE GR WHITE LOT PJ12127915	GSC110901	-19	.19				WHITE INSUL
RAYCHEM SPEC 44/0411-20 SPACE GR OUTER INS WHITE	GSCFC7634	-7	.19				WHITE INSUL
RAYCHEM SPEC 44/0411-20X GR 1NS W/O BENZOPHENONE	GSC10143	-26	.20				WHITE INSUL
RAYCHEM SPEC 44/0411-24-9 WHITE WIRE INSUL	GSC10949	-65	.21				WHITE INSUL
RAYCHEM SPEC 44/1441-24 SPACE GR OUTER INS WHITE	GSCFC7619	-79	.22				WHITE INSUL
RAYCHEM SPEC 44/2431-24-9 CLEAR INSUL	GSC10955	-79	.22				WHITE INSUL
RAYCHEM SPEC 44/2431-24-9 COLOR CODED INSUL	GSC10952	-46	.23				WHITE INSUL
RAYCHEM SPEC 44/2431-24-9 WHITE OUTER SHEATH	GSC10970	-15	.23				WHITE INSUL
RAYCHEM SPEC 551READIATE ETEPE WHITE INSUL	GSCF8885	-22	.23				WHITE INSUL
RAYCHEM SPEC 55A0811-24-9 P04032682 Q2 BLUE/WHITE	GSC12487	-08	.23				WHITE INSUL
RAYCHEM SPEC 88 POLY X INSULATION	GSCFC292	-89	.09				SURFACE INSUL
RAYCHEM 10-51 PRE SHANK	GSCFC0794	-95	.17				WHITE TUBING
RAYOLIN F CABLE 4126E 1332 INSULATION GRAY	GSCFC3383	-73	.25				CUTTING
RB 10-51 A/B AS 2/3 BW FLEXIBLE EPOXY	GSCFC1504	1-97	.38				CUTTING
RB 10-51 A/B AS 2/3 BW FLEXIBLE EPOXY	GSCFC1651	1-98	.42				CUTTING
RB 8-1338 A/B AS 100/65 BW POLYURETHANE	GSCFC1672	-51	.04	8H	62	A-2	ROTATING
RB 8-1338 A/B AS 50/34 BW POLYURETHANE	GSCFC1516	-75	.04	24H	62	E-2	ROTATING
RC-AS-1200 ANTISTATIC POLYETHYLENE FILM	GSCFC4706	-29	.04	7D	25	A-2	ROLLING
RC-AS-1200 FR ANTISTATIC POLYETHYLENE FILM	GSCFC4708	-70	.15				ROLLING
RC-AS-2400 ANTISTATIC NYLON FILM P/N ORANGE	GSCFC6482	6-34	.18				ROLLING
RC-AS-2400 A126 NYLON FILM W/O ANTISTATIC COMP/CLEAR	GSCFC6846	6-34	.29				COMP COAT
RCC-150 UV POLYMER	GSC11501	2-34	.48				COMP COAT
RCC-150 UV POLYMER	GSC11705	1-60	.60				COATING
RD 1875-3 POLYKETEANE	GSCFC1627	1-28	.28	24H	25	AIR	

MATERIAL	DATA REFERENCE	XMTL	%CVCH	CURE TIME	CURE TEMP	AMDS	APPLICATION
RD 1875-3 POLYURETHANE	GSPC1630	1.35	.18	24H	25	AIR	COATING
KD 3327-6 ACCEL 4/F	GSPC9760	7-6.3	.37	24H	E-3	AIR	ADHESIVE
REDAR SI 503 REINFORCED SILICON HOSE	GSPC9537	1-96	.31			AIR	ADHESIVE
REDIMARK FELT MARKER BLACK/F	GSC11779	18-40	6-62	7D	25	AIR	NOSE
REDIMARK FELT MARKER RED/F	GSC11782	25-35	10-39	7D	25	AIR	MARKER
REDIMARK 139-101 FELT MARKER BLUE/F	GSC11995	22-14	1-01	1-5H	25	AIR	MARKER
REICHLUND POLYURETHANE FOAM	GSPC2378	5-80	-17			AIR	FOAM
REGAL PAPER NKCC11009 POLYIMIDE FILM	GSPC3550	3-35	.14	30H	174	AIR	ADH FILM
RELIABOND 3998 FILM ADHESIVE GRAY	GSPC9537	1-17	.91	1H	120	AIR	FILM ADHESIVE
RELIANCE 7115 FCLGHT SHRINK EPoxy FILM	GSPC64620	1-96	.06	1H	121	AIR	FILM ADHESIVE
RELIEF CAP - SILICONE RUBBER	GSPC9530	1-20	.23			AIR	LAP
RETEK GLO-135 WHITE POLYOLEFIN SHRINK TUBING	GSPC1747	4-49	.03	0-5H	135	AIR	SHRINK TUBING
RESDEL U1-02-01 CIEA 60005/RESDEL 4145 5/1 BW EPOXY	GSPC1744	4-82	.93	10H	160	AIR	ADHESIVE
RESISTOR COATING TYPE 100 FLAT BLACK/F	GSC13084	1-18	.75	20H	25	AIR	ADHESIVE
RESISTOR COATING TYPE 150 FLAT BLACK/F	GSC12781	.26	.13	3H	150	AIR	CONF COAT
RESISTOR COATING TYPE 200 FLAT BLACK/F	GSC12784	.32	.08	30H	125	AIR	CONF COAT
RESISTOR COATING TYPE 250 FLAT BLACK/F	GSC13087	.86	.44	30H	125	AIR	CONF COAT
RESINFIELD 7004 EPOXY ADH A/B AS 1/1 BY	GSPC0978	1-67	.12	24H	25	AIR	ADHESIVE
RESINFIELD 7200 A/B AS 1/1 BY EPOXY COATING	GSPC4300	4-03	.03	3H	25	AIR	CONF COAT
RESINFIELD 7200 A/B/SOL AS 2/1/2 BW EPOXY COATING	GSPC4686	11-01	.00	16H	65	AIR	CONF COAT
RESYN 30-1215 PRESSURE SENSITIVE ACRYLIC ADHESIVE	GSPC4336	-63	.01	16H	60	AIR	ADHESIVE
REXOLITE 1422 STYRENE	GSPC2281	-16	.02	2H	25	AIR	INSULATION
RF 1006 NYLON 6/6	GSPC0912	-81	.04	30H	25	AIR	NULL CPND
RF 1730 A/B AS 1/1 BW POLYURETHANE (HQ MCCA OR TDI)	GSPC6560	-85	.19	16H	25	AIR	ROUTING
RFF 2633 PCLYURETHANE FOAM GRAY	GSPC5124	1-79	.22	24H	65	AIR	CONF COAT
RFF 2633 PCLYURETHANE FOAM GRAY	GSPC5127	-53	.05	48H	66	AIR	CONF COAT
RFL 4536 NYLON 6/6 W/30% GLASS/15% TFE/SILICONE	GSPC5529	1-17	.17	24H	100	AIR	STRUCTURAL
R3 304/U CABLE INSUL PTFE OUTER COVERING ONLY	GSPC7592	-01	.00	30H	75	AIR	STRUCTURAL
RHOPLEX N-619 PEES SENS ACRYLIC ADH/FOIL SANDWICH	GSPC5763	-51	.01	1H		AIR	ADHESIVE
RICOHENE 3711 THEMOSET THERMOPLASTIC HYDROCARBON	GSPC4023	1-50	.07			AIR	ADHESIVE
RIGIDAMP SILICONE	GSPC4642	2-01	.04			AIR	CPND
RIGIDAMP 19010-1 LAMINATE ONLY	GSPC4912	-57	.00			AIR	LAMINATE
RIGIDAMP 19010-1 VISCOELASTIC FILM/3M TAPE 467	GSPC4914	3-46	.50			AIR	ADHESIVE
RL 4540 NYLON 6/6 W/20% TFE/SILICONE	GSPC5527	1-49	.05	1H	25	AIR	STRUCTURAL
RHBC 18 A/B AS 4/1 BW CLEAR EPOXY	GSPC7220	6-85	.01	1H	132	AIR	CONF COAT
ROGERS POLYURETHANE FOAM	GSPC2497	8-51	.51	10H	149	AIR	FOAM
ROGERS RX 611	GSPC2324	-53	.01	30H	204	AIR	NULL CPND

MATERIAL	DATA REFERENCE	X-TAL	X-CVN	CURE TIME	CURE TEMP	ADHESIVE APPLICATION
ROYCO 43 GREASE PEE MIL G4343B	GSPC9296	85-13	15-34			LUBRICANT
RN 423 SILICONE RUBBER	GSPC2236	5-50	1-37			SEAL
RN 423 SILICONE RUBBER	GSPC2209	5-50	1-11	24H	23 ²	SEAL
RS-12 MICRO SHIELD PAINT ON FOIL	GSPC3055	8-54	2-36	21D	60	PAINT
RT DUKOID 4300 INFERNED TEFLON PTFE	GSPC6455	9-28	4-37	2H	60	DEWING MTL
RT DUKOID 5870 - LAMINATE	GSC10634	*05	*00			LAMINATE
RT DUKOID 2880 - LAMINATE	GSC10637	*03	*00			LAMINATE
RT DUKOID 6010 - LAMINATE	GSC10640	*03	*00			LAMINATE
RT 1146 BLACK VITON SHRINK TUBING - HEAT GUN SHRINK	GSPC9170	*37	*07			SHRINK TUBING
RTV 119 ONE COMPACT TRANSLUCENT SILICONE	GSPC9362	4-32	1-19	100	40H	AIR
RTV 11/T-12 AS 100/2 6 ⁴ SILICONE	GSPC8966	*67	*25	72H	150	AIR
RTV 11/T-12/SILVER FLAKE 0-5A T-12/70% SILVER FLAKE	GSPC4688	*81	*22	4D	235	AIR
RTV 11/T-12/SILVER FLAKE 0-5A T-12/70% SILVER FLAKE	GSPC6563	*72	*15	810D	235	AIR
RTV 118 ONE COMPONENT TRANSLUCENT SILICONE	GSPC1140	1-60	*98	7D	204	AIR
RTV 118 ONE COMPONENT TRANSLUCENT SILICONE	GSPC9068	1-96	1-01	90H	200	AIR
RTV 136 SILICONE CEND	GSPC0771	2-21	1-07	24H	25	AIR
RTV 142 ONE COMPONENT WHITE SILICONE	GSPC1369	*25	*03	24H	225	AIR
RTV 142 ONE COMPONENT WHITE SILICONE	GSPC7487	*21	*01	6D	225	SILICONE
RTV 142 ONE COMPONENT WHITE SILICONE	GSPC9054	*24	*00	7D	225	AIR
RTV 154 ADHESIVE SEALANT	GSC10748	*22	*00	7D	225	AIR
RTV 162 ONE COMPONENT WHITE SILICONE	GSPC2925	3-42	1-66	24H	225	AIR
RTV 168 SILICONE	GSPC8198	1-59	*42	7D	225	AIR
RTV 511 .007-.009 IN THICK	GSPC3734	1-72	*55	24H	225	AIR
RTV 511 .007-.009 IN THICK	GSPC7559	*62	*29	3D	225	AIR
RTV 511 .007-.009 IN THICK	GSPC7562	*78	*39	3D	100	C-2
RTV 511 0-5% BN CAT DEVOL AT 190C LOT JN 170	GSC11060	1-82	*49	48H	125	AIR
RTV 511 0-5% BN CAT DEVOL AT 125C LOT JN 170	GSC11984	*78	*26	7D	225	AIR
RTV 511 0-5% BN CAT DEVOL AT 150C LOT JN 170	GSC11198	*49	*15	7D	225	AIR
RTV 511 0-5% BN CAT DEVOL AT 160C LOT JN 170	GSC11198	*39	*05	7D	225	AIR
RTV 511 0-5% BN CAT VIRGIN RESIN LOT KH 181	GSPC12052	3-66	*63	7D	225	AIR
RTV 511/CAT 901 AS 6-0% BN CAT GREEN SILICONE	GSPC9380	3-59	*64	30D	225	AIR
RTV 511/T-12 AS C-E ₂ T-12 BN SILICONE	GSPC4616	*09	*00	3D	16H	177
RTV 511/T-12 AS 40 GM/10 DROPS SILICONE	GSPC5294	2-97	*76	3D	225	AIR
RTV 511/T-12 AS 1/1/4% BN	GSPC2529	*65	*35	72H	25	AIR
RTV 560/T-12 AS 0-1% T-12	GSPC7955	2-22	*49	150D	25	E-0
RTV 560/T-12 AS 0-1% T-12	GSPC7982	*08	*04	150D	25	AIR
RTV 560/T-12 AS C-5% T-12	GSPC2601	2-52	*55	24H	225	E-0
RTV 560/T-12 AS 1/1/0-5% BN SILICONE	GSPC6822	*63	*11	7D	225	AIR
RTV 560/T-12 AS 1/9/0-5% BN SILICONE	GSPC9780	3-30	*57	48H	75	B-0
RTV 560/T-12 AS 1/9/0-5% BN SILICONE	GSPC6782	*45	*08	14D	25	AIR
RTV 560/580/T-12 AS 1/2 BN W/0.5% T-12	GSPC4420	2-20	*71	7D	225	AIR
RTV 560/580/T-12 RCA ADHESIVE	GSPC5146	-46	*21	4D	125	E-0
						ADH-SEAL-ENCAPS

	MATERIAL	DATA REFERENCE	STYL #CVCH	CURE TIME	CURE TEMP	ADHES CURE	APPLICATION
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 4	GSC13290	.18	.07	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 5	GSC13308	.71	.41	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 6	GSC13311	.11	.02	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 7	GSC13314	.15	.05	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL LOT CB237 BATCH 8	GSC13347	.15	.05	7D	25	A/AH	POTTING
RTV 615 A/E AS 10/1 BW DEVOL LOT CB237 BATCH 9	GSC13350	.15	.05	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL LOT JG202 DEVOL AT 125C	GSC11908	.12	.04	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL AT 150C	GSC11920	.13	.04	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL AT 150C	GSC11948	.143	.04	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL AT 150C	GSC11961	.133	.04	7D	25	A/AH	POTTING
RTV 615 A/B AS 9/1 BW DEVOL AT 150C	GSC11920	.16	.04	7D	25	A/AH	POTTING
RTV 615 A/B AS 10/1 BW DEVOL AT 150C	GSC11987	.82	.03	1H	100	A/AH	POTTING-ENCAPS
RTV 616 A/B AS 10/1 BW BLACK SILICONE	GSC19071	.1	.00	24H	25	A/AH	POTTING
RTV 619 A/B AS 10/1 BW SILICONE	GSC12970	.30	.50	1H	100	A/AH	POTTING
RTV 630 5% BW CAT GRAY SILICONE	GSC1	.73	.40	1H	121	A/AH	ADHESIVE
RTV 655 A/B AS 10/1 BW DEVOL AT 125C LOT KFO84	GSC12328	.39	.05	24H	25	A/AH	ENCAPSULANT
RTV 655 A/B AS 10/1 BW DISTILL @ 177C @ VAC #C82-1	GSC12329	.93	.31	4H	82	A/AH	POTTING
RTV 655 A/B AS 10/1 BW VAGIN RESIN LQT KFO84	GSC12342	.93	.19	4H	82	A/AH	POTTING
RTV 670 A/B AS 10/1 BW CLEAR SILICONE	GSC12415	.55	.96	7D	25	A/AH	ENCAPSULANT
RTV 670 A/B AS 10/1 BW CLEAR SILICONE	GSC12955	.42	.70	10H	60	A/AH	POTTING
RTV 670 A/B AS 10/1 BW CLEAR SILICONE	GSC12963	.37	.65	7D	25	A/AH	POTTING
RTV 700 RED SILICONE MOLDED TERMINAL	GSC11346	.62	.51	16H	204	A/AH	TERMINAL INSUL
RTV 700 SILICONE F/CAM	GSC11346	.10	.41	4H	25	A/AH	F/CAM
RTV 8111/CAT 9891 AS 9/7/3 BW	GSPCO45	.36	.41	16H	65	A/AH	ADH-POTTING
RTV 8112/CAT 9891 AS 9/4/4 BW	GSPCO454	.92	.28	16H	65	A/AH	ADH-POTTING
RTV 8112/CAT 9891 AS 9/4/4 BW	GSPCO456	.31	.23	16H	65	A/AH	ADH-POTTING
RTV 8221/CAT 9858 AS 9/6/4 BW	GSPCO258	.99	.35	24H	65	A/AH	ADH-POTTING
RTV 8223/CAT 9858 AS 9/6/4 BW	GSPCO257	.23	.21	16H	65	A/AH	ADH-POTTING
RTV 8223/CAT 9858 AS 9/6/4 BW	GSPCO260	.12	.28	16H	65	A/AH	ADH-POTTING
RTV 8243/CAT 9858 AS 9/6/4 BW	GSPCO341	.16	.15	24H	95	A/AH	ADH-ENCAPS
RTV 8243/CAT 9858 AS 9/6/4 BW	GSPCO344	.08	.22	72H	25	A/AH	ADH-ENCAPS
RTV 8262/CAT 9858 AS 20/1 BW	GSPCO263	.08	.22	16H	65	A/AH	ADH-ENCAPS
RTV 8262/CAT 9858 AS 20/1 BW	GSPCO344	.08	.22	72H	25	A/AH	ADH-ENCAPS
RTV 8262/CAT 9858 AS 9/4/6 BW	GSPCO376	.73	.24	24H	65	A/AH	ADH-ENCAPS
RTV 8263/CAT 9858 AS 9/4/6 BW	GSPCO379	.87	.17	24H	65	A/AH	ADH-ENCAPS
RTV 8293/CAT 9858 AS 9/9/4 BW	GSPCO359	.90	.21	16H	25	A/AH	ADH-ENCAPS
RTV 8372/CAT 9858 AS 9/5/5 BW	GSPCO347	.41	.28	16H	65	A/AH	SILICONE
RTV 8373/CAT 9858 AS 9/7/3 BW	GSPCO350	.32	.21	24H	65	A/AH	SILICONE
RTV 8373/CAT 9858 AS 9/7/3 BW	GSPCO394	.31	.20	16H	95	A/AH	SILICONE
RTV 8382/CAT 9856 AS 9/5/5 BW	GSPCO388	.22	.16H	65	444	A/AH	AUH-SEALANT
RTV 8382/CAT 9858 AS 9/5/5 BW	GSPCO391	.22	.16H	65	444	A/AH	AUH-SEALANT
RTV 8383/CAT 9858 AS 9/7/3 BW	GSPCO382	.66	.23	24H	65	A/AH	SILICONE
RTV 8383/CAT 9858 AS 9/7/3 BW	GSPCO385	.73	.21	16H	52	A/AH	SILICONE
RUBBER DAM LATEX RUBBER SHEET	GSPC2815	1.76	-0.00	-0.00	-0.00		BEARING MATEL
RULON A TEFILON FILLED BEARING MATERIAL	GSPC3477	1.31	-0.00	-0.00	-0.00		BEARING MATEL
RULON B TEFILON FILLED BEARING MATERIAL	GSPC3479	1.22	-0.39	-0.19	-0.00		BEARING MATEL
RULON C TEFILON FILLED BEARING MATERIAL	GSPC3501	1.00	-0.00	-0.00	-0.00		BEARING MATEL
RULON D TEFILON FILLED BEARING MATERIAL	GSPC3503	1.00	-0.00	-0.00	-0.00		BEARING MATEL
RULON E TEFILON FILLED BEARING MATERIAL	GSPC3505	1.00	-0.00	-0.00	-0.00		BEARING MATEL
RV 401 SPOOL EPOXY/FIBERGLASS	GSPC341	.32	-0.00	-0.00	-0.00		WALL FORM

MATERIAL	DATA REFERENCE	ATM	%CVCH	CURE TIME	CURE TEMP	STATUS	APPLICATION
RYTON R-4 POLYPHENYLENE SULFIDE/40% GLASS R2 STA-KON TERRITORY R101 PROTECTANT CCATING	GSPC6826 GSPC6035 GSPC2806	3.0 3.0 3.0	.9 .32 .06	16H 15A 24H	25 121 25 110 25	AIR AIR JUNIP COAT JUNIP COAT	MOLD CRND JASULATION COAT COAT
R4-3117 ONE PART SILICONE - FREE FILM - CLEAR	GSPC7877	.61	.23	96H	121	AIR	JUNIP COAT
R4-3117 ONE PART SILICONE/F AS 100/11 BW BLACK EPOXY	GSPC7673	1.43	.24	14D	24H	AIR	JUNIP COAT
R3-2038/H2-3404 AS 100/11 BW CLEAR	GSPC4588	1.76	.02	24H	25	AIR	MOLD CPND
R3-2038/H2-3404 AS 100/11 BW EPOXY	GSPC5969	2.01	.12	1H	92H	AIR	JUNIP
R3-2038/H2-3405 AS 100/88 BW CLEAR EPOXY	GSPC7427	2.34	.10	1H	92H	AIR	ADHESIVE
R3-2038/H2-3405 AS 9/1 BW EPOXY	GSPC8201	.85	.03	24H	89H	AIR	ADHESIVE
R3-2039/H2-3404 AS 9/1 BW EPOXY	GSPC7436	.64	.00	1H	80H	AIR	POTTING
R3-2039/H2-3561 AS 10/3 BW EPOXY	GSPC6344	1.08	.01	30M	150	AIR	ADHESIVE
R90-709 SILICONE JUNCTION COATING	GSPC6353 GSPC2707	.98 .88	.02 .37	2H 1H	60 70	AIR AIR	ADHESIVE JELLCONE
S-13-G SILICONE WHITE PAINT	GSPC2245	.42	.09	2H	150	AIR	PAINT
S-13-G WHITE PAINT STANDARD D236 C S-13-G-LC WHITE PAINT	GSPC5845 GSPC5987	.82 .56	.16 .13	24H 48H	121 25	AIR AIR	PAINT PAINT
S-13-G-LO WHITE PAINT A/B AS 100/1 BW V/TOLUENE S-13-G-LO WHITE PAINT E-127 NO PRIMER BATCH E-389 S-13-G-LO WHITE PAINT E-127 NO PRIMER BATCH E-389 S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-496 S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-497 S-13-G-LO WHITE PAINT SS 4044 PRIMER BATCH E-555 SAIL CLOTH ALUMINIZED MYLAR/ALUM/NYLON/WHITE PAINT SAW SILICONE RESIN RIGIDIZED w/SLICA FIBERS SAMPOED MR SKETCH 2000 FELT TIP MARKER SARAN F310 POWDER LOT C301508	GSPC6740 GSPC9041 GSPC9218 GSPC9820 GSPC10832 GSPC3770 GSPC5148 GSPC5024 GSPC13296 GSPC10904 GSPC8780 GSPC8267 GSPC8387 GSPC0149 GSPC0137 GSPC3153 GSPC3670	.54 .50 .50 .44 .49 .47 .47 .47 .47 .42 .42 .40 .40 .38 .38 .38 .38 .38 .38	.10 .02 .04 .02 .03 .03 .03 .02 .02 .03 .03 .03 .03 .03 .03 .03 .03 .03	24H 10 24H 10 24H 10 24H 10 24H 10 24H 10 24H 10 24H 10 24H 10 24H 10	25 25 25 25 25 25 25 25 25 25 25 25 25 25 25 25 25 25 25	AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR AIR	PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT PAINT
SB TAPE REINFORCED SILICONE RUBBER TAPE SB 1020 GLASS REINFORCED SILICONE RUBBER TAPE SB R RUBBER STANDARD SB R RUBBER STANDARD UNCURED SC HENNETTY VARNISH 170 SCI REZ 80'S GLASS FILAMENT WOUND COMPOSITE	GSPC10904 GSPC8780 GSPC8267 GSPC8387 GSPC0149 GSPC0137 GSPC3153 GSPC3670	.93 .90 .90 .93 .93 .93 .19 .22	.36 .33 .33 .34 .34 .34 .33 .33	1H 1H 1H 1H 1H 1H 1H 1H	204	AIR	ADHESIVE JEWELLING TAPE TAPE TAPE BUBBLE BUBBLE VARNISH
SCOTCHBOND 4170 STUD LOCKING RED ADH-SEALANT P/BOLTS SCOTCHBOND 4171 NUT LOCKING BLUE FROM BOLTS SCOTCHBOND 4172 SCREW LOCKING PURPLE FROM BOLTS SCOTCHBOND 4173 FLUSHING ASSY GREEN FROM BOLTS SCOTCHBOND 4174 FLUSHING ASSY GREEN FROM BOLTS SCOTCHBOND 4175 FLARING ASSY GREEN FROM BOLTS SCOTCHBOND 4176 HYDRAULIC SEALANT AMBER FROM BOLTS SCOTCHBOND 4177 HYDRAULIC SEALANT AMBER FROM BOLTS SCOTCHCAL 8001 RED ALUM LABEL UNCOATED SCOTCHCAL 8001 RED ALUM LABEL COATING 3900 SCOTCHCAL 8005 BLACK PHOTO-SENSE FILM 7730 SCOTCHCAL 8005 DIACK PHOTO-SENSE FILM/ALUM/AUDH/FOIL	GSPC9701 GSPC9742 GSPC9744 GSPC9749 GSPC9763 GSPC9765 GSPC8114 GSPC8117 GSPC8120 GSPC8142	25-41 25-61 25-61 25-13 25-39 14-94 14-81 43-02 43-09 37-13 8-15 1-74 1-66 22-69 30-00 -00 -01	7-76 9-13 8-15 1-74 1-66 22-69 30-00 -01	3H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H 72H	17-34 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25 22-25	AIR AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT AHD-SEALANT	ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT ADH-SEALANT

MATERIAL	DATA REFERENCE	RTEL	ACVCM	CURE TIME	CURE TEMP	AIRBUD	APPLICATION
SCOTCHCAST 8005 PHOTOSENS FILM/ALUM/VINYLCOAT/ACR ADH	GSPC4176	-19	-0.0				DECAL MARKER
SCOTCHCAST 8005 PHOTOSENS FILM/ALUM/VINYLCOAT/ACR UNCOATED	GSPC4144	-0.0	-0.0				DECAL MARKER
SCOTCHCAST 8009 BLUE ALUM LABEL	GSPC8147	-15	-0.0				FOLI LABEL
SCOTCHCAST 8009 BLUE ALUM COATINGS	GSPC8150	-14	-0.0				FOLI LABEL
SCOTCHCAST 8011 BLUE ALUM LABEL/FILM	GSPC4180	-1.56	-0.03				DECAL MARKER
SCOTCHCAST 8011 RED PHOTO SENSE FILM/ADH FOIL	GSPC4175	-1.57	-0.03				DECAL MARKER
SCOTCHCAST 8012 PHOTO SENSE FILM/ADH FOIL	GSPC4182	-2.14	-0.06				DECAL MARKER
SCOTCHCAST 8012 PHOTO SENSE FILM/VINYLCOAT/ACR/ADH	GSPC43401	16.-62	-1.19				PRIMER
SCOTCHCAST PRIMER XKR-50137 A/B AS 5/1 BW THIN COAT	GSPC3650	-0.53	-0.32	2.44	2.5	AIR	PRIMER
SCOTCHCAST XKR-50168 EPOXY FUA	GSPC4888	-0.03	-0.29	2.174	2.5	AIR	PUTTING
SCOTCHCAST XKR-50168 A/B AS 2/2 BW EPOXY	GSPC4688	37.-0.9	-0.49	2.40	2.5	AIR	PUTTING
SCOTCHCAST XKR-5133 EPOXY CASTING POWDER	GSPC3385	-0.42	-0.01	3.04	14.9	AIR	PUTTING
SCOTCHCAST XKR-5137 PRIMER FOR POLYURETHANE	GSPC97958	-6.-56	-0.02	2.44	2.5	AIR	PUTTING
SCOTCHCAST XKR-5240 RUSTY BROWN EPOXY	GSPC9742	4.-20	1.-96	2.42	2.5	AIR	PUTTING
SCOTCHCAST 10 (XKR-5241) A/B AS 1/1 BW RUST RED EPOXY	GSPC10125	1.-96	-1.52	7.0D	12.5	AIR	ADHESIVE
SCOTCHCAST 10 (XKR-5241) A/B AS 1/1 BW RUST RED EPOXY	GSPC9996	3.-0.9	-0.81	2.44	2.5	E-2	ADHESIVE
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	GSPC11309	-0.55	-0.01	1.66	2.5	AIR	PUTTING
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	GSPC7892	-2.5	-0.02	2.44	2.5	AIR	PUTTING
SCOTCHCAST 225 A/B AS 5/8 BW MAROON POLYURETHANE	GSPC11669	-1.53	-0.35	7.2H	2.5	AIR	PUTTING
SCOTCHCAST 226 A/B AS 2/5 BW POLYUR ETHANE	GSPC7922	-1.05	-1.16	7.2H	2.5	AIR	PUTTING
SCOTCHCAST 250 A/B AS 1/1 BW EPOXY BROWN	GSPC502B	-0.95	-0.09	2.4H	2.5	AIR	IMPREGNANT
SCOTCHCAST 253 A/B AS 2/3 BW EPOXY	GSPC4882	-0.98	-0.15	2.0H	8.2	AIR	PUTTING
SCOTCHCAST 253 A/B AS 2/3 BW EPOXY	GSPC4884	-0.92	-0.15	2.0H	12.0	AIR	PUTTING
SCOTCHCAST 280 A/B AS 2/3 BW EPOXY	GSPC2116	-0.48	-0.14	2.4H	12.0	AIR	PUTTING
SCOTCHCAST 281 A/B AS 2/3 BW BLACK EPOXY	GSPC9197	-0.56	-0.08	2.4H	12.5	AIR	PUTTING
SCOTCHCAST 281 A/B AS 2/3 BW GRAY EPOXY	GSPC8972	-0.35	-0.02	1.2H	10.0	AIR	PUTTING
SCOTCHCAST 281/282 EPOXY FORMULATION	GSPC4518	-0.37	-0.05	4.0H	12.0	AIR	PUTTING
SCOTCHCAST 282 A/B AS 2/3 BW SEMI RIGID BLACK EPOXY	GSPC7265	-0.49	-0.09	1.6H	9.0	AIR	PUTTING
SCOTCHCAST 282 A/B AS 2/3 BW SEMI RIGID BLACK EPOXY	GSPC7268	-0.45	-0.09	1.6H	9.0	AIR	PUTTING
SCOTCHCAST 8 A/B AS 1/1 BW EPOXY	GSPC7916	7.-5.9	1.-4.8	4.8H	2.5	E-5	PUTTING
SCOTCHCAST 9 A/B AS 1/1 BW EPOXY	GSPC2267	3.-6.0	-0.04				PUTTING
SCOTCHCAST 1357 CONECTOR GLASS REINF POLYESTER	GSPC10853	-0.19	-0.04				CONNECTOR
SCOTCHGRIP EC 2393 BLUE FROM BOLTS	GSPC2749	3.-4.8	-0.90	2.4H	2.5	AIR	ADHESIVE
SCOTCHGRIP 2451 CHANGE FROM BOLTS	GSPC9670	4.-19	-1.19	4.8H	2.5	AIR	ADHESIVE
SCOTCHGRIP POLYESTER FASTENER HOOK/NAP	GSPC9972	-4.-98	-0.10	4.8H	2.5	AIR	ADHESIVE
SCOTCHMATE SJ3401 NYLON HOOK AND LOOP	GSPC2735	-1.-39	-0.33				FASTENER
SCOTCHMATE SJ3402 NYLON HOOK AND LOOP BLACK	GSPC2653	1.-71	-0.02				FASTENER
SCOTCHMATE SJ3404 NYLON HOOK AND LOOP	GSPC9901	1.-70	-0.02				FASTENER
SCOTCHWELD 17352 ADH BACKED HOOK & LOOP	GSPC12439	5.-6.0	-0.08	2.22	2.5	AIR	ADH FOILING
SCOTCHWELD 17351 E/A AS 2/1 BW W/PHENYL GLICIDYL ETH	GSPC2487	-0.73	-0.03	2.4H	2.5	AIR	ADHESIVE
SCOTCHWELD 1838 ED ALUM FILLED EPOXY	GSPC2669	-0.65	-0.05	4.0D	12.1	AIR	COND ADHESIVE
SCOTCHWELD 22214 EICH TEMP ALUM FILLED EPOXY	GSPC3507	-0.48	-0.05	4.0D	12.1	AIR	COND ADHESIVE
SCOTCHWELD 22214 EICH TEMP ALUM FILLED EPOXY	GSPC3791	-0.45	-0.05	4.0D	12.1	AIR	COND ADHESIVE
SCOTCHWELD 22214 EWF UNFILLED EPOXY 1/5% PMS464 QED	GSPC3925	-0.40	-0.02	1.1H	14.0	AIR	ADHESIVE
SCOTCHWELD 22214 EWF UNFILLED EPOXY 1/5% PMS464 QED	GSPC7142	-1.-25	-0.06	4.8H	2.5	AIR	ADHESIVE
SCOTCHWELD 22216 E/A AS 5/7 BW FLEXIBLE GRAY EPOXY	GSPC6859	-0.16	-0.03	2.4H	2.5	AIR	ADHESIVE
SCOTCHWELD 22216 E/A AS 5/7 BW FLEXIBLE GRAY EPOXY	GSPC6862	-0.11	-0.01				ADHESIVE

MATERIAL	DATA REFERENCE	X-TML	%CVN	CURE TIME	CURE TEMP	A-BUS	APPLICATION
SCOTCHWELD 2216 E/A AS 5/7 BW #4% H-5 CAB-O-SIL	GSPC8783	.76	.03	16H	25	AIR	ADHESIVE
SCOTCHWELD 2219 CLEAR AMBER B/A AS 1/1 BW EPOXY	GSC10128	1-6.0	.32	24H	100	AIR	ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER B/A AS 1/1 BW EPOXY	GSPC6559	1-6.0	.15	18H	25H	AIR	ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER B/A AS 5/7 BW EPOXY	GSPC6623	1-6.0	.31	24H	68	AIR	ADHESIVE
SCOTCHWELD 2216 CLEAR AMBER B/A AS 5/7 BW EPOXY	GSPC6644	1-6.0	.04	7D	25	AIR	ADHESIVE
SCOTCHWELD 2216 SANDWICHED BETWEEN ALUMINUM	GSPC0317	1-3	.02	24H	25	AIR	ADHESIVE
SCOTCHWELD 3501 E/A AS 1/1 BW MOD EPOXY	GSC12520	1-5.1	.02	24H	25	AIR	ADHESIVE
SCOTCHWELD 3532 E/A AS 1/1 BW POLYUETHANE BROWN	GSPC19358	1-6.6	.07	24H	25	AIR	ADHESIVE
SCOTCHWELD 588 SCOTT INDUSTRIAL FCAM POLYESTER URETHANE	GSPC3531	4-2.0	.41	3d	149	PSI	ADHESIVE
SCOTT POLYESTER-URETHANE FOAM - TAN	GSPC3696	1-9.0	.53	1H	154	PSI	ADHESIVE
SCOTT POLYESTER-URETHANE FOAM - TAN 2X24 HR ETOH WASH	GSPC7577	4-4.6	1-6.3	24H	100	AIR	FOAM SHEET
SCOTT POLYESTER-URETHANE FOAM BROWN CLOSED CELL	GSPC7259	4-6.3	1-8.4	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM BROWN 2X24 HR ETOH WASH	GSPC7580	4-6.3	1-8.8	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM BROWN 2X24 HR ETOH WASH	GSPC4496	1-6.9	.05	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 100 PPI	GSPC44592	3-6.9	.02	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 100 PPI	GSPC44594	3-4.2	.02	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 60 PPI	GSPC43550	1-3.1	.99	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 60 PPI	GSPC43330	2-3.3	.39	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 60 PPI METOH WASH	GSPC43226	2-3.3	.04	24H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 60 PPI MON-PLATE GRAY	GSPC42418	4-4.8	.42	24H	100	AIR	DAMPER
SCOTT POLYESTER-URETHANE FOAM 2 1/4" CU FT WASHED	GSC12421	1-5.9	.24	6H	100	AIR	FOAM
SCOTT POLYESTER-URETHANE FOAM 60 PPI	GSPC40092	1-2.5	.73	12H	100	AIR	FOAM
SCOTT POLYURETHANE FOAM BLACK 41 PPI	GSPC39996	2-1.4	.24	73	100	AIR	FOAM
SCOTT POLYURETHANE FOAM GREEN 100 PPI	GSPC40990	2-1.4	.44	48H	110	L-3	FOAM
SCOTT POLYURETHANE FOAM GREEN 40 PPI	GSPC42248	2-8.1	.43	48H	110	L-3	FOAM DAMPER
SCOTT POLYURETHANE FOAM WHITE 100 PPI	GSPC43110	2-8.1	.43	48H	110	L-3	FOAM
SCOTT POLYURETHANE FOAM WHITE 90 PPI	GSPC39998	2-8.3	.31	48H	110	L-3	FOAM
SCOTT POLYURETHANE FOAM ALUM KAPTON SANDWICH LOUVER	GSPC5731	2-8.4	.13	11	65H	AIR	LOUVER BLADE
SCOTT POLYURETHANE FOAM ALUM KILLAR SANDWICH	GSPC3191	1-2.8	.09	48H	120	AIR	INSULATION
SCOTT POLYURETHANE FOAM ALUM MYLAR SANDWICH	GSPC3261	1-8.1	.04	48H	120	AIR	INSULATION
SCOTT POLYURETHANE FOAM ALUM MYLAR SANDWICH	GSPC3315	1-8.1	.43	8H	120	AIR	FOAM
SCOTT POLYURETHANE FOAM ALUM MYLAR RETARD	GSPC4234	2-9.2	.44	24H	120	AIR	FOAM
SCOTT PYRELL FOAM POLYURETHANE GRAY FLAME RETARD	GSPC4274	1-2.8	.44	24H	160	AIR	FOAM
SCOTT PYRELL FOAM POLYURETHANE GRAY FLAME RETARD	GSPC4276	1-2.5	.05	7H	210	E-1	FOAM
SE 4401 SILICONE FOAM POLYURETHANE GRAY FLAME RETARD	GSPC7376	-1	.05	7H	210	AIR	MOLD CEND
SE 4401 U GENERAL PURPOSE SILICONE	GSPC0074	.06	.00	24H	249	AIR	MOLD CEND
SE 4404 U GENERAL PURPOSE SILICONE	GSPC0071	.10	.00	24H	243	AIR	MOLD CEND
SE 4324U CLEAR SILICONE	GSC10068	.10	.01	25H	163	AIR	MOLD CEND
SE 4524U CLEAR SILICONE	GSC10071	.07	.00	25H	163	AIR	MOLD CEND
SE 456/TS-50 SILICONE - TAN	GSPC8291	.10	.01	24H	216	AIR	MOLD CPND
SE 456/TS-50 SILICONE - TAN	GSPC8555	.22	.07	4H	204	AIR	MOLD CPND
SE 5204 SILICONE - TAN	GSPC8558	.17	.02	8H	238	AIR	MOLD CPND
SE 5204 SILICONE - TAN	GSPC4596	.07	.00	8H	232	AIR	ELASTOMER
SE 5211 U LOW TEMP SILICONE	GSPC0077	.07	.02	4H	249	AIR	SASKEET
SE 5403 U LOW TEMP SILICONE	GSPC0066	.10	.02	3H	204	AIR	SILICONE
SE 5554U SILICONE FOOD GRADE FF	GSC10185	.16	.00	30H	163	AIR	MOLD CPND
				15H	200		E-6

MATERIAL	REFERENCE	DATA	ATML	RCVCM	CURE TIME	CURE TEMP	AIR/J	APPLICATION
SE 5554U SILICONE FOOD GRADE GG	GSC10182	-2.5	.00	30M	163	E-0	E-0	EOLD CPND
SE 557/VAROX AS 100/0.3 BW GRAY SILICONE	GSFPC8219	.09	.02	15H	121	E-0	A/A	SEAL
SE 565/VAROX AS 100/0.6 BW EXTREME LOW TEMP SILICONE	GSPFC3925	-2.5	.12	24H	249	A/A	A/A	EOLD CPND
SE 565/VAROX AS 100/0.6 BW EXTREME LOW TEMP SILICONE	GSPFC3927	-1.2	.03	2H	177	A/A	A/A	EOLD CPND
SE 9025 SILICONE WIRE INSULATION BLACK	GSPFC3858	1.38	.91	48H	177	A/A	A/A	EOLD CPND
SE 9025 SILICONE WIRE INSULATION RL RUN GSPC3744	GSPFC3744	3.32	.58	3H	204	A/A	A/A	EARE INSUL
SE 9025 SILICONE WIRE INSULATION RL RUN GSPC3744	GSPFC3793	1.16	.03	24H	125	E-0	E-0	EARE INSUL
SE 9045 SILICONE WIRE INSULATION - OUTER	GSPFC21119	1.37	.01	2H	177	A/A	A/A	EARE INSUL
SE 9045 SILICONE WIRE INSULATION	GSPRC4520	4.12	1.01	1.01	1.01	A/A	A/A	EARE INSUL
SECUR-A-TIE CASE FITE NYLON	GSPC5653	2.88	.01	2H	177	A/A	A/A	EARE INSUL
SEMKIT 3E653K825AS EPOXY PSN 8040-0-916-9847	GSPRC4851	4.66	.01	2D	25	A/A	A/A	LEASBLE TIE
SENBRI S-RED MARKING INK	GSPRC4302	6.33	.79	7D	25	A/A	A/A	MARKING INK
SP 10006 NYLON 12/ GLASS AS 70/30	GSPC12891	1.65	.01	2H	25	A/A	A/A	ACID CPND
SPR 60-60W WHITE SILICONE	GSPC13440	1.61	.39	11	204	A/A	A/A	CUSHION
SPR 60-60W WHITE SILICONE	GSPC13443	3.43	.11	6H	204	A/A	A/A	CUSHION
SPR 60-694W WHITE SILICONE	GSPC13416	3.94	.13	6H	204	A/A	A/A	CUSHION
SPR 60-694W WHITE SILICONE	GSPC13419	6.44	.03	13	204	A/A	A/A	CUSHION
SJ 3/4X5 HEATER - RED SILICONE	GSPFC6676	0.8	.01	2H	25	A/A	A/A	HEATER
SHRINK TUBING BLACK FROM CABLE BRAND REX	GSPC1928	2.12	1.01	2H	25	A/A	A/A	SHRINK TUBING
SHRINK TUBING GREEN MAX SHRINK-HEAT GUN	GSPC1942	2.62	.22	1.01	25	A/A	A/A	SHRINK TUBING
SHRINK TUBING GREEN MAX SHRINK-HEAT GUN	GSPC1943	1.70	.54	1.01	25	A/A	A/A	SHRINK TUBING
SHR-LOK SLE 3007 EPOXY - GRAY	GSPC4422	.32	.00	12H	25	A/A	A/A	POTTING
SHUR-LOK SLE 3009 EPOXY - GREEN	GSPC4424	1.20	.18	8H	65	A/A	A/A	POTTING
SHUR-LOK SLE 3010 EPOXY POTTING CPND BLUE-GREEN	GSPC3596	1.22	.04	8H	95	A/A	A/A	POTTING
SHUR-LOK SLE 3010 SYNTACTIC FOAM BLUE-GREEN	GSPC4450	.77	.03	10H	25	A/A	A/A	POTTING
SIC 9030/GREEN BINLLER/C-240 GRIT	GSPC4452	1.13	.19	8H	121	A/A	A/A	FOAM
SICON BLACK 7X9055 SILICONE	GSPC11503	.24	.01	8H	95	A/A	A/A	ELECTRIC
SICON BLACK 7X9055 SILICONE	GSPFC102	6.04	.36	24H	25	A/A	A/A	PAINT
SICON BLACK 7X9055 SILICONE	GSPC1105	.98	.04	30M	277	A/A	A/A	PAINT
SICON BLACK 7X933/S744 AS 4/1 BY	GSPC11995	1.32	.02	15H	294	A/A	A/A	PAINT
SICON R 8X929 BLACK PAINT	GSPC1393	4.05	.02	1.15	310	A/A	A/A	PAINT
SICON 3X258 LEAFING ALUMINUM	GSPC11543	.72	.17	48H	71	A/A	A/A	PAINT
SICON 3X258 LEAFING ALUMINUM	GSC11545	.70	.11	48H	29	A/A	A/A	PAINT
SICON 3X258 LEAFING ALUMINUM	GSC11639	.79	.09	96H	25	A/A	A/A	PAINT
SIL-BADS 40J SILICONE/FIBERGLASS SHEET GRAY	GSPC9892	4.40	.09	48H	25	A/A	A/A	FILM/SHEET
SILASTIC EA/B AS 10/1 BW WHITE SILICONE	GSPC0694	2.08	.11	8D	71	A/A	A/A	POTTING
SILASTIC EA/B AS 10/1 BW WHITE SILICONE DEVOL 100C	GSPC0697	1.25	.39	7D	25	A/A	A/A	POTTING
SILASTIC S-6508U/Ts-50 AS 100/1.4 BW SILICONE	GSPC4618	.35	.13	1H	250	A/A	A/A	ELASTOMER

MATERIAL	REFERENCE	XTHL	XCVH	CURE TIME	CURE TEMP	AIR	APPLICATION
SILASTIC 1410 SHRINKABLE TUBING - PRESHEUNK	GSFC0761	1.38	.22	24H	25	AIR	AIR-SEALANT SHRINK TUBING
SILASTIC 2000 FRAASLJUENT GROMMET	GSFC0788	.56	.15	-34	-34	AIR	BULD CPAD
SILASTIC 35	GSC11503	1.14	-0.6	24H	249	AIR	SILICONE
SILASTIC 6508/TS-5C CADOX AS 99/1 BW SILICONE	GSFC4822	.80	-1.8	90M	216	AIR	BULD CPND
SILASTIC 6508/TS-5C CADOX AS 99/1 BW SILICONE	GSFC4826	.20	.06	90M	216	AIR	BULD CPND
SILASTIC 675 SILICONE	GSFC2509	.41	.04	5H	116	AIR	SEAL-GASKET
SILASTIC 68-110 A/E AS 25/1 BW	GSFC0824	1.23	.26	24H	250	AIR	SILICONE
SILASTIC 68-120 A/E AS 25/1 BW	GSFC0845	1.15	.25	24H	255	AIR	SILICONE
SILASTIC 68-120 A/E AS 25/1 BW	GSFC0836	.84	.25	24H	255	AIR	SILICONE
SILASTIC 68-210 A/E AS 25/1 BW	GSFC0866	.88	.25	24H	255	AIR	SILICONE
SILASTIC 68-210 A/E AS 25/1 BW	GSFC0833	1.24	.24	24H	255	AIR	SILICONE
SILASTIC 68-220 A/E AS 25/1 BW	GSFC0863	1.24	.38	150H	245	AIR	SILICONE
SILASTIC 68-220 A/E AS 25/1 BW	GSFC0812	1.03	.18	150H	255	AIR	SILICONE
SILASTIC 68-310 A/E AS 25/1 BW	GSFC0851	1.05	.18	150H	255	AIR	SILICONE
SILASTIC 68-310 A/E AS 25/1 BW	GSFC0821	1.24	.25	24H	255	AIR	SILICONE
SILASTIC 68-320 A/E AS 25/1 BW	GSFC0848	1.24	.33	150H	255	AIR	SILICONE
SILASTIC 68-320 A/E AS 25/1 BW	GSFC0893	1.24	.32	24H	255	AIR	SILICONE
SILASTIC 68-330 A/E AS 25/1 BW	GSFC0890	1.29	.28	24H	255	AIR	SILICONE
SILASTIC 68-210 A/E AS 10/1 BW	GSFC0818	1.02	.24	24H	255	AIR	SILICONE
SILASTIC 69-210 A/E AS 10/1 BW	GSFC0854	1.04	.26	150H	255	AIR	SILICONE
SILASTIC 69-210 ICT EU 103307	GSFC5463	.89	.27	16H	255	AIR	COATING
SILASTIC 69-210 ICT EU 103307	GSFC3489	.02	.30	24H	255	AIR	COATING
SILASTIC 69-220 A/E AS 25/1 BW	GSFC0827	1.16	.28	24H	255	AIR	SILICONE
SILASTIC 69-220 A/E AS 25/1 BW	GSFC0860	1.31	.25	150H	255	AIR	SILICONE
SILASTIC 69-220 A/E AS 25/1 BW	GSFC7670	1.38	.40	24H	255	AIR	PUTTING
SILASTIC 731 RTV SEALANT	GSFC0575	1.39	.38	24H	255	AIR	SEALANT
SILASTIC 736 ONE PART RED SILICONE	GSFC4230	2.03	.45	7D	255	AIR	ADHESIVE
SILASTIC 738 ONE PART NON-CORROSIVE SILICONE	GSFC0392	1.63	.51	72H	25	AIR	AIR-SEALANT
SILASTIC 75 SILICONE	GSFC0419	1.16	.32	3H	204	AIR	O-RING SEAT
SILASTIC 88/CA1 AS 14-2/-55 BW SILICONE	GSFC1423	1.63	.43	90H	38	AIR	SILICONE
SILASTIC 916 GASKET	GSFC7148	1.86	.30	24H	249	AIR	GASKET
SILASTIC 916 GASKET N9162 AS 100/4 BW WHITE RUBBER	GSFC6947	1.58	.34	6D	25	AIR	PUTTING
SILCOSET 152 PRIME/F WHITE SILICONE	GSCT0944	3.30	.55	7D	25	AIR	PRIMER
SILCOSET 152 PRIME/F WHITE SILICONE	GSC10568	2.03	.55	7D	25	AIR	ADHESIVE
SILICONE INSULATOR SO-1058-8913 RED	GSC12004	3.0	.18	24H	60	AIR	INSULATOR
SILICONE RUBBER - VIBRATION DAMPER BLUE/GRAY	GSFC8978	3.57	.82	12H	204	AIR	DAMPER
SILICONE RUBBER EII 22-R-765 CLASS 11B GR 63-75 RED	GSFC8981	2.9	.11	24H	204	AIR	DAMPER
SILICONE RUBBER MIL 24-R-765 CLASS 2 GRADE 50 - GRAY	GSFC8975	6.0	.20	40	16H	AIR	DAMPER
SILICONE RUBBER MIL 24-R-765 CLASS 2 GRADE 50 - GRAY	GSFC7241	1.51	.31	34H	24H	AIR	GASKET
SILICONE RUBBER MIL 24-R-765 CLASS 2 GRADE 50 - GRAY	GSFC7295	1.1	.36	1.32	1.32	AIR	DAMPER
SILICONE RUBBER MIL 24-R-765 CLASS 2 GRADE 40 RED	GSFC11096	2.82	.1	24H	160	AIR	GASKET
SILICONE RUBBER PEE AMS 3332 RED	GSFC11998	3.1	.32	24H	175	AIR	GASKET
SILICONE RUBBER UNION CARBIDE	GSFC12001	1.04	.39	10H	232	AIR	SILICONE
SILICONE RUBBER UNION CARBIDE	GSFC2059	1.04	.39	10H	204	AIR	CUSHION
SILICONE RUBBER 16254 GRAY SHEET	GSFC2092	1.14	.39	6H	204	AIR	CUSHION
SILICONE RUBBER/FAVIC REINFORCED MIL R3065 TYPE HB	GSFC13290	1.14	.39	6H	204	AIR	HOLD CPND

MATERIAL	DATA REFERENCE	#TMI	ACVCM	CURE TIME	CURE TEMP	AIR DRY	APPLICATION
SILICONE WIRE INSULATION SILK NETTING STYLE 5517 SILK NETTING	GSC1495 GSFC2757 GSFC2879	1.25 2.34	.07 .12 3H	24H 2.5 2.5	25 25 E-6	E-6 E-6 E-6	WIRE INSUL. NETTING
SILVER GOOF HIGH TEMP GREASE CLOTH - BROWN	GSC12931	11.18	.09				LUBRICANT
SILSS-06 R/F SEALED THERMAL SPINAL GASKET	GSCC13162	2.48	.62				GASKET
SKYBOND RT 7271-01 FLEXIBLE POLYIMIDE FOAM	GSFC3011	.71	.52				FOAM
SKYBOND RT 7271-06 RIGID POLYIMIDE FOAM	GSFC3057	.86	.04				FOAM
SKYBOND RT 7271-12 RIGID POLYIMIDE FOAM	GSFC3079	.31	.01				FOAM
SKYBOND RT 7271-16 RIGID POLYIMIDE FOAM	GSFC3099	.42	.01				FOAM
SKYBOND RT 7271-17 RIGID POLYIMIDE FOAM	GSFC3109	.45	.01				FOAM
SKYBOND RT 7271-17 RIGID POLYIMIDE FOAM	GSFC3109	.38	.01	1H	177	PSL	LAMINATE
SKYBOND RT 7271-17 RIGID POLYIMIDE FOAM	GSFC3109	.49	.04	4H	25	AIR	SEALANT
SMOOTH ON 9/16" RED SILICONE 3 STEP PCURE	GSC12306	7.69	.07	10M	25	AIR	ADHESIVE
SMP 62/63 AS 1/1 EV EPOXY	GSFC4644	16.25	.07	1H	25	AIR	ADHESIVE
SMP 62/63 AS 1/1 EV EPOXY	GSFC3860	16.25	.07	24	69	AIR	ADHESIVE
SMP 62/63 AS 1/1 EV EPOXY	GSFC4428	1.40	.14	4H	25	AIR	ELIM. DIELECTRIC
SMRD 100 (43-3) FILLED HYDROCARBON RUBBER	GSFC6806	1.11	.13	8H	62	AIR	DAMPER
SMRD 100 F90	GSC10-085	2.46	.27	24H	100	AIR	DAMPER
SMRD 100 F90 CYCLOCHEKANE WASH - INTERNAL PORTION	GSFC7088	1.52	.19	110H	133	AIR	DAMPER
SMRD 100 F90 CYCLOCHEKANE WASH - SURFACE PORTION	GSFC7091	1.57	.22	16H	103	AIR	DAMPER
SMRD 100 F90 FLEXIBLE EPOXY FOAM	GSFC7199	1.56	.24				DAMPER
SMRD 100 F90 FLEXIBLE EPOXY FOAM	GSFC7196	2.28	.27				DAMPER
SMRD 100 F90 FLEXIBLE EPOXY FOAM	GSC1100	1.1	.11	9H	130	AIR	DAMPER
SMRD 100 F90 FLEXIBLE EPOXY FOAM	GSC1100	1.09	.11	9H	130	AIR	DAMPER
SMRD 100 F90 FLEXIBLE EPOXY FOAM	GSC1100	1.09	.11	9H	130	AIR	DAMPER
SMRD 100 F90 NEW RESIN REPLACEMENT	GSFC9929	1.39	.11	9H	103	AIR	DAMPER
SMRD 432 SOA WHITE SOLDER E MAINT LIKE RED	GSFC9932	1.94	.17	48H	103	AIR	POTTING
SOLIDI-MIDE TA-301 FLEXIBLE POLYIMIDE FOAM MIL F8709Q	GSC13448	4.28	.28				WIRE COATING
SOLITHANE 113/PPG-425/EP-330 FORMULA 20	GSC10733	4.21	.21	7D	25	AIR	CONF COAT
SOLITHANE 113/EPICINONE/E ALCOHOL FORMULA 25	GSC10733	4.21	.21	7D	25	AIR	CONF COAT
SOLITHANE 113/ABP-440/TMP FORMULA 27	GSC10793	8.7	.87	1-38	7D	25	CONF COAT
SOLITHANE 113/300 AS 100/100 BW FORMULA 4	GSFC0113	4.9	.12	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/120 BW FORMULA 6	GSFC0433	3.0	.09	7D	25	AIR	CONF COAT
SOLITHANE 113/300 AS 100/150 BW FORMULA 7	GSFC7223	4.7	.10	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/150 BW FORMULA 7	GSFC2269	3.7	.08	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	GSFC1565	3.1	.04	16H	20	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	GSFC0248	3.2	.04	7D	25	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	GSFC4254	2.8	.03	20H	270	AIR	POTTING
SOLITHANE 113/300 AS 100/73 BW 33% ALUM PIGMENT	GSFC1496	6.9	.24				CONF COAT
SOLITHANE 113/300 AS 100/80 BW FORMULA 2	GSFC601	5.6	.01	7D	225	AIR	POTTING
SOLITHANE 113/300 FORMULA 2	GSFC7616	3.0	.01	7D	225	AIR	POTTING
SOLITHANE 113/300 FORMULA 6 OVER PRIMER 919/920	GSFC7175	7.2	.03	7D	225	AIR	POTTING
SOLITHANE 113/300/ABUSIL MS5/RO DAMINE BT-12	GSCF1189	4.7	.01	7D	225	AIR	POTTING
SOLITHANE 113/300/ABUSIL MS5/RO DAMINE BT-12	GSFC1189	4.7	.01	7D	225	AIR	POTTING
SOLITHANE 113/300/CABOSIL MSS/T-12/FLUORESCENT DYE	GSFC7314	4.6	.04	7D	225	AIR	POTTING
SOLITHANE 113/300/CABOSIL MSS/T-12/FLUORESCENT DYE	GSFC10257	4.7	.03	7D	225	AIR	SEALANT
SOLITHANE 113/300/CALCAFLUOR WHITE/T-12/DILK	GSFC6410	5.4	.04	5H	54	AIR	CONF COAT
SOLITHANE 113/300/CALCAFLUOR WHITE/T-12/DILK	GSFC7946	6.6	.09	15H	50	AIR	POTTING

MATERIAL	DATA REFERENCE	ATMEL	%CVC	CURE TIME	CURE TEMP	ATMOS	APPLICATION
SOLITHANE 113/300 AS 100/73/1 BN FORMULA 21	GSC10736	.56	.05	7D	25	AIR	UNF COAT
SOLITHANE 113/300 A-METHYL NORPHOLINE FORMULA 23	GSC13236	.32	.92	2H	93	AIR	COATING
SOLITHANE 113/300 QUADROL FORMULA 24	GSC10754	.29	.90	2H	255	AIR	CONF COAT
SOLITHANE 113/300 QUADROL FORMULA 26	GSC10769	.31	.90	2H	255	AIR	CONF COAT
SOLITHANE 113/300 QUADROL FORMULA 27	GSC1225	.37	.01	7D	25	AIR	CONF COAT
SOLITHANE 113/300 QUADROL FORMULA 28	GSC10472	.37	.01	7D	25	AIR	PUTTING
SOLITHANE 113/300 QUADROL FORMULA 29	GSC13511	.38	.92	3H	63	AIR	CONF COAT
SOLITHANE 113/300 QUADROL FORMULA 30	GSC13514	.40	.05	2D	25	AIR	PAINT
SOLITHANE 113/300 1-12/SILFLAKE 135 HEKANE	GSFC8177	.62	.00	24H	63	AIR	LONG CONF COAT
SOLITHANE 113/300 TIPA AS 100/51/4 BN FORMULA 10	GSFC6206	.36	.92	7D	25	AIR	ADHESIVE
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC4206	.14	.91	4H	60	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC4252	.53	.03	24H	55	AIR	PUTTING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC1258	.43	.03	7D	25	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC10739	.43	.03	7D	25	AIR	PUTTING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC2212	.44	.04	24H	96	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC1166	.79	.04	24H	70	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC1582	.34	.00	16H	70	AIR	PUTTING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC10263	.1-19	.008	3H	66	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC2470	.21	.90	21D	25	AIR	PUTTING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC2519	.23	.90	16H	57	AIR	PUTTING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSC10811	.60	.03	7D	25	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC2635	.1-36	.57	1H	60	L-J	CUSHION
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC4280	.8-95	.06	5D	25	AIR	PAINT COMPOSITE
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC7706	1-78	.02	2H	25	AIR	PAINT COMPOSITE
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC7898	.7-7	.03	9-9H	69	AIR	PAINT COMPOSITE
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC4278	.4-6	.03	24H	100	AIR	PAINT COMPOSITE
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC0428	.5-53	.02	5D	25	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC8027	.5-72	.02	24H	25	AIR	SURFACE TUBING
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC3904	.8-72	.02	7D	25	AIR	MARKING FLUID
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC6656	.3-44	.83	7D	25	AIR	CONF COAT
SOLITHANE 113/300 TIPPA/ALUMINA T 61	GSFC6659	.29	.01	15H	25	AIR	PAINT
SPACE GARD 4-B-33 FLAT BLACK COATING	GSFC4280	8-95	.06	5D	25	AIR	PAINT COMPOSITE
SPACE GARD 4-B-33 FLAT RANDOLPH PRIMER T54/F	GSFC7706	1-78	.02	2H	25	AIR	PAINT COMPOSITE
SPACE GARD 4-C-25 CLEAR COATING	GSFC7898	.7-7	.03	9-9H	69	AIR	PAINT COMPOSITE
SPACE GARD 4-C-25 CLEAR COATING	GSFC4278	.4-6	.03	24H	100	AIR	PAINT COMPOSITE
SPACE GARD 4-C-25 CLEAR COATING	GSFC0428	.5-53	.02	5D	25	AIR	CONF COAT
SPEED-O-PACU 50CX POLYURETHANE LIQUID	GSFC8027	.5-72	.02	24H	25	AIR	SURFACE TUBING
SPENKEL SP-86-50CX POLYURETHANE LIQUID	GSFC3904	.8-72	.02	7D	25	AIR	MARKING FLUID
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC6656	.3-44	.83	7D	25	AIR	CONF COAT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC6659	.29	.01	15H	25	AIR	PAINT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC4280	8-95	.06	5D	25	AIR	PAINT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC7706	1-78	.02	2H	25	AIR	PAINT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC7898	.7-7	.03	9-9H	69	AIR	PAINT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC4278	.4-6	.03	24H	100	AIR	PAINT
SPEREX SP-101 VHT EIGHT TEMP COATING-WHITE SILICONE	GSFC0428	.5-53	.02	5D	25	AIR	CONF COAT
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC6413	3-03	.95	4-9H	125	E-7	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC9813	14-10	.95	1-60	24H	E-7	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC9899	2-74	.91	1-40	24H	E-7	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC6703	-71	.71	1-40	24H	E-7	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC6804	-83	.40	2H	138	AIR	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC9808	-53	.40	2H	177	AIR	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC6884	-53	.25	4-8H	177	AIR	DAMPER
SPONGE RUBBER SILICONE MIL R6130B TYPE 1 BLACK	GSFC2818	-48	.81	24H	25	AIR	COATING
SPRAY-LATEX 1071B SILICONE COATING	GSFC2818	3-34	.81	1-2H	350	AIR	COATING
SR 165 SILICONE IRON OXIDE/ALUMINUM SILICATE COATING	GSC12190	-30	.00	1-2H	350	AIR	PAINT
SR 240 SILICONE LEAFING ALUMINUM	GSC11547	-58	.19	48H	25	AIR	PAINT
SR 240 SILICONE LEAFING ALUMINUM	GSC11549	-74	.24	96H	71	E-3	PAINT
SR 240 SILICONE LEAFING ALUMINUM	GSC11642	-72	.18	48H	71	E-3	PAINT
SR 240 SILICONE LEAFING ALUMINUM	GSC11642	-72	.18	8D	44	E-3	PAINT
SPIRAL NYLON CABLE WRAP 500013	GSFC6413	1H	316	AIR	CABLE WRAP		
SPIRAL NYLON CABLE WRAP 500013	GSFC9813	1H	121	AIR	CABLE WRAP		
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC9899	2-74	1-40	24H	125	E-7	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC6703	-71	0-7	24H	138	AIR	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC6804	-83	0-40	24H	177	AIR	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC9808	-53	0-40	24H	177	AIR	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC6884	-53	0-25	4-8H	177	AIR	DAMPER
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC2818	-48	0-81	24H	25	AIR	COATING
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC2818	-34	0-81	24H	25	AIR	COATING
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC9813	-30	0-19	48H	25	AIR	PAINT
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC11547	-58	0-19	48H	25	AIR	PAINT
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC11549	-74	0-24	96H	25	AIR	PAINT
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC11642	-72	0-18	48H	25	AIR	PAINT
SPONGE RUBBER NEOPRENE MIL R6130B TYPE 1 BLACK	GSFC11642	-72	0-18	8D	44	E-3	PAINT

MATERIAL	DATA REFERENCE	X-TAL	XCVH	CURE TIME	ADDS	APPLICATION
SR 2702-75 VITON PER MIL R83248 TYPE 2 CLASS 1	GSPC4474 GSC11294 GSPC01110	.16 .46 .30	.00 2.60 2.60	24H 4H 2D	AIR AIR AIR	DUST SEAL SEAL COATING
SR 2704-75 VITON E-60 SILICONE (SF 17 AND SR 98)	GSPC6679 GSPC9692 GSPC7709 GSPC1768	2-.48 2.09 .60 10-.37	1.75 1.93 1.54 5.39	3.0M 12H 12H 24H	AIR AIR AIR AIR	AUHESIVE AUHESIVE AUHESIVE AUHESIVE
SR 529 SILGRIP SILICONE PSA	GSPC7421					
S2 585 SILVER FILLED SILICONE ON SILVERED TEFILON	GSPC6679	2-.48	1.75			
S2 585 SILVER FILLED SILICONE ON SILVERED TEFILON	GSPC7709	2.09	1.93			
S2 585 /TCLUENE 5-70 BUTYL C FLING STILLMAN BUBBLE	GSPC1768	.60	1.54			
S2 634-70 SILICONE PRIMER NATURAL NYLON ETHANOL WASH	GSPC1804	10-.37	5.39			
STA-SILAPASS CABLE NATURAL NYLON ETHANOL WASH	GSPC2551	15-.53				
STA-SOLITE 20678 COVER STAG PREVOX 1766 PRIMER/P	GSPC4339					
STAKING CPND BLUE SOLVANTANE 113/300 BASE	GSPC12832	4-.27				
STANDING OFF G-10 EPOXY/GLASS COMPOSITION	GSPC8957	4-.43				
STANTHANE 817C-2 (FORMERLY CPC 17-2C)	GSPC5713	1-.18				
STANTHANE 817C-2 (FORMERLY CPC 17-2C)	GSPC5829	1-.78				
STANTHANE 817C-2 (FORMERLY CPC 17-2C)	GSPC3855	1-.32				
STANTHANE 817C-2 (FORMERLY CPC 17-2C)	GSPC5857	1-.37				
STATIC CHECK 6 FABRIC - LIGHT AQUA/WHITE VINYL	GSC12880	27-.60	17-.11			
STATIC CONTROL DAT 8210 BROWN VINYL/FOAM	GSC12880	27-.60	23-.66			
STEPAN FOAM G-306 64/CU FT WHITE	GSC10442	.87	.00	24H	AIR	FOAM
STRIP-N-STICK SILICONE TAPE 440S	GSC13120	2-.05	.91			
STRIP-N-STICK 2000AB BLUE SILICONE SPONGE/ACRYLIC ADH/F	GSC13204	.34	.13			
STRIPPABLE VINYL CATTING	GSC13207	.34	.13			
STW 0474 WHITE SILICONE WIRE INSUL	GSPC2393	2-.31	4-.97			
STW 0474 WHITE SILICONE WIRE INSUL	GSPC2859	4-.16	.76			
STYCAST CPC 18 A/B AS 100/12.5 BW POLYURETHANE	GSPC2887	2.10				
STYCAST CPC 18 A/B AS 100/12.5 BW POLYURETHANE	GSPC6059	1-.31				
STYCAST CPC 18 A/B AS 100/12.5 BW POLYURETHANE	GSPC6152	1-.37				
STYCAST CPC 18 A/B AS 100/12.5 BW POLYURETHANE	GSPC9599	19-.96				
STYCAST CPC 19 A/E AS 100/12.5 BW POLYURETHANE	GSPC6056	19-.36				
STYCAST CPC-41 A/B AS 100/12.5 BW POLYURETHANE	GSPC1419	19-.39				
STYCAST HIK 5000 DIELECTRIC FOAM	GSPC5435	.47				
STYCAST HIK FILLED FOAM	GSPC8081	.38				
STYCAST 0095 POLYISOPRENE AS 100/23 B+ EPOXY FOAM	GSC10131	3-.29				
STYCAST 1090-SI/241V AS 100/23 B+ EPOXY FOAM	GSPC3680	.74				
STYCAST 1095/1 AS 100/12 BW EPOXY FOAM	GSPC5457	.49				
STYCAST 1095/1 AS 100/12 BW EPOXY FOAM	GSPC5459	.38				
STYCAST 1095/1 AS 100/12 BW EPOXY FOAM	GSPC5465	.36				
STYCAST 1095/9 AS 100/9 BW BLACK EPOXY FOAM	GSPC8366	.72				
STYCAST 1217/9 AS 100/13 BW EPOXY	GSPC5485	1.20				
STYCAST 1263/3 AS 100/3 BW EPOXY	GSPC5891	.33				
STYCAST 1267 A/B AS 100/30 BW CLEAR EPOXY	GSC12208	1-.06				
STYCAST 1467/CAT 9 AS 100/7 BW EPOXY	GSPC2517	.14				
STYCAST 2057/CAT 9 AS 100/6 BW EPOXY	GSPC3361	.72				
STYCAST 2651/CAT 11 AS 100/8 BW BLACK EPOXY	GSPC9053	.63				
STYCAST 2651/CAT 11 AS 100/8 BW BLACK EPOXY	GSPC9071	.84				

MATERIAL	DATA REFERENCE	X-TML	%VCH	CURE TIME	CURE TEMP	AIROS	APPLICATION
STYCAST 2651/CAT 11 EPOXY	GSPC2014	.14	.00	8H	25	AIR	POTTING
STYCAST 2651GM/CAT 9 EPOXY	GSPC0993	.37	.03	7D	25	AIR	POTTING
STYCAST 2651GM/CAT 14 AS 4/1 BW BLACK EPOXY	GSPC11612	.38	.00	2H	120	AIR	ADHESIVE
STYCAST 2650FT/14 AS 25/2 BW BLACK EPOXY	GSPC4580	.63	.00	3H	143	AIR	POTTING
STYCAST 2650FT/9 AS 100/3 BW EPOXY	GSPC7271	.23	.08	3H	143	AIR	POTTING
STYCAST 2850FT/11 AS 100/3 BW BLACK EPOXY	GSPC4242	.40	.01	20H	70	AIR	POTTING
STYCAST 2850FT/11 AS 100/4.5 BW EPOXY	GSPC7124	.40	.01	2H	85	AIR	ADHESIVE
STYCAST 2850FT/11 AS 20/1 BW BLACK EPOXY	GSPC10907	.47	.01	2H	69	AIR	ADHESIVE
STYCAST 2850FT/11 AS 100/3/1.5 BW BLUE EPOXY	GSPC6569	.47	.01	30H	120	AIR	POTTING
STYCAST 2850FT/241V AS 100/3 BW EPOXY	GSPC7004	.40	.00	4H	200	AIR	POTTING
STYCAST 2850GM/9 AS 10/0.3 BW BLUE EPOXY	GSPC4343	.39	.00	7H	69	AIR	ADHESIVE
STYCAST 2850K/241V AS 25/1 BW BLUE EPOXY	GSPC4195	.33	.00	7D	25	AIR	ADHESIVE
STYCAST 2850K/241V AS 25/1 BW BLUE EPOXY	GSC11854	.65	.02	24H	25	AIR	COATING
STYCAST 2850K/241V AS 100/1.7 BW BLUE EPOXY	GSPC9431	.55	.02	24H	25	AIR	POTTING
STYCAST 2850K/241V AS 100/1.7 BW BLUE EPOXY	GSPC9434	.34	.01	16H	65	AIR	POTTING
STYCAST 2850K/241V AS 100/2.7 BW BLUE EPOXY	GSC10299	.44	.01	24H	25	AIR	POTTING
STYCAST 2850K/241V AS 100/2.7 BW BLUE EPOXY	GSC10296	.52	.03	24H	74	AIR	COATING
STYCAST 2850K/9 AS 100/2.7 BW BLUE EPOXY	GSC11815	.52	.02	24H	25	AIR	ADHESIVE
STYCAST 2850K/9 AS 100/2.7 BW BLUE EPOXY	GSPC6149	1.04	.00	16H	105	AIR	ADHESIVE
STYCAST 2850K/9 AS 100/2.7 BW THERM COND EPOXY	GSC10176	.75	.01	17H	25	AIR	POTTING
STYCAST 3050/11 AS 10/3 BW MAROON EPOXY	GSPC1369	1.47	.07	90M	126	AIR	POTTING
STYCAST 3050/11 AS 10/3 BW MICROBALLONS	GSC11857	2.93	.07	7D	25	AIR	POTTING
STYCAST 3050/9 AS 100/6 BW DARK RED EPOXY	GSPC6077	1.41	.01	8H	69	AIR	ADHESIVE
STYCAST 3050/9 AS 100/6 BW EPOXY	GSC11384	1.64	.01	7D	25	AIR	POTTING
STYCAST 3050/9 AS 100/6 BW DARK RED EPOXY	GSPC4046	1.26	.02	24H	25	AIR	COATING
STYRAFIL F30/20/CR BLACK POLYSTYRENE/FIBER GLASS	GSPC1060	5.30	.00	24H	25	AIR	ADHESIVE
STYROFOAM G3/20/CR BLACK POLYSTYRENE/FIBER GLASS	GSC11153	6.00	.22	24H	25	AIR	ADHESIVE
SULFIL 1500/20 PCYLUSFONE/FIBER GLASS AS 80/20	GSPC0966	3.97	.13	48H	75	AIR	POTTING
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/P	GSC10269	1.51	.15	48H	100	AIR	PRIMER
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/P	GSC10419	1.51	.15	72H	100	AIR	PRIMER
SUPER KOROPON FLUID RESISTANT PRIMER GREEN EPOXY/P	GSPC10431	5.03	.21	70H	74	AIR	PRIMER
SUPER LAMICODE MARKERS W/ PD POLYESTER ADH	GSPC3039	2.09	.09	24H	25	AIR	MARKERS
SUPRAKICA 500 SYNTHETIC MICA/ORGANIC BINDER	GSPC7796	9.00	.03	24H	25	AIR	STRUCTURAL INSULATION FILM
SURLIN A WIRE INSULATION IN SHEET FORM	GSPC0338	4.60	.03	24H	25	AIR	WIRE INSULATION FILM
SURLIN SB LONGMER FILED	GSPC4572	4.00	.05	24H	25	AIR	WIRE INSULATION FILM
SURLIN 1652 2 MIL FAGGING FILM	GSPC7544	3.90	.09	24H	25	AIR	WIRE INSULATION FILM
SWITCH CASE ES-4 BLACK PHENOLIC	GSC11237	4.33	.01	24H	25	AIR	WIRE INSULATION FILM
SWS 934 ONE CJP/CNENT SILICONE WHITE SILICONE	GSPC12370	4.43	.01	24H	25	AIR	WIRE INSULATION FILM
SYLGARD 170 A/B AS 1/1 BW DARK GRAY SILICONE	GSPC9692	1.19	.21	7D	25	AIR	ADHESIVE
SYLGARD 182 A/B AS 10/1 BW	GSPC0444	1.10	.33	22H	100	AIR	SILICONE
SYLGARD 182 A/B AS 10/1 BW	GSPC2080	1.09	.33	7D	25	AIR	POTTING
SYLGARD 184 A/B AS 10/1 BW DEVEL LOT GDU53274 BATCH1	GSC13338	1.01	.48	2H	170	AIR	SILICONE
SYLGARD 185 A/B AS 10/1 BW	GSPC0529	1.19	.01	7D	25	AIR	ADHESIVE
SYLGARD 186 A/B AS 10/1 BW SILICONE	GSPC7127	2.19	.59	1H	100	AIR	SILICONE
SYLGARD 187	GSPC07PN	2.46	.25	24H	25	AIR	SILICONE

MATERIAL	DATA REFERENCE	XTHL	%CVCN	CURE TIME	CURE TEMP	ADHESIVE	APPLICATION
SYLIGARD 187 A/B AS 10/1 BW SILICONE	GSEPC4334	1-25	44	44	121	A-1	LIQUID CPND
SYLIGARD 51 A/B AS 10/1 BW WHITE EPOXY/ECCOSPHERES AS 40/60 BW	GSEFC1005	2-40	>80	72H	66	AIR	SILICONE FOAM
SYNTACTIC FOAM WHITE EPOXY/ECCOSPHERES AS 40/60 BW	GSC11693	3-54	>90	16H	110	AIR	HANDLING COAT
SYNTACTIC FOAM 30/7 VARNISHED ANODIZE	GSEFC3387	3-70	>90	16H	110	AIR	PLASTENE
S1942-D 10/10 FASSTEN BLUE EPOXY THERM COND	GSEPC5691	1-24	>03	25H	25	AIR	ADHESIVE
TAPE 2000 A/B AS 1/25 BW ACRYLIC BASE ADH/SILICONE REFLDANT SILICONE BAKELER	GSEPC5461	2-28	>3	24H	25	AIR	ADHESIVE TAPE
IBS 757 EPOXY 03641 THERM PELT/SILICONE ADH/P	GSC10155	2-38	>17	54	149	AIR	INTERNAL BARRIER
TC 10 NYLON WIRE SUPPORT NYLON CABLE RETAINER	GSEFC3852	2-80	>70				SUPPORT
TC 101 TY-KAP NYLON CABLE CLAMP	GSEFC2733	1-08	>02				CABLE RETAINER
TC 102 TY-KAP NYLON CABLE CLAMP	GSEFC5168	1-11	>01				CABLE CLAMP
TC 103 NYLON CABLE ADHESIVE	GSEFC3263	0-66	1-74				ADHESIVE
TC 104 NYLON CABLE CLAMP	GSEFC5170	0-95	>01				CABLE CLAMP
TC 105 NYLON CABLE CLAMP	GSEPC5049	1-61	>02				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEPC5152	1-92	>02				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEFC5172	1-95	>01				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEFC4998	2-02	>04				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEFC4955	2-10	>01				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEFC3067	1-18	>00				HOLD PLATE
TC 1112 TY-KAP NYLON CABLE CLAMP	GSC11923	16-10	>04				CABLE CLAMP
TC 1112 TY-KAP NYLON CABLE CLAMP	GSEPC5331	8-81	1-24				LINK
TECH-DEP USE IN LNK FROM TUBE LOT 105/F	GSEPC3974	8-81	1-24				LINK
TECKELFET 45-09810 SILICON IMEREG SINT STAINLESS	GSEFC9868	7-70	>29				FILM
TECKELFET 45-09810 UNFILLED SINT STAINLESS	GSEFC4756	6-01	>30				FILM
TECKELFET 72-00002 SILVER FILLED SILICONE	GSEFC4758	6-02	>30				FILM
TECKELFET 72-00002 SILVER FILLED SILICONE	GSEPC3483	6-01	>30				FILM
TECKELFET 75-08116 SILV'D EPOXY A/B AS 1/1 BW	GSEPC3978	1-92	>02				FILM
TECKNIT 75-09176 SILVER COATED NYLON	GSEPC4760	4-12	>74				FILM
TECKNIT 78-24571 SILICONE SPONGE W/SCREEN	GSEPC4762	4-12	>02				FILM
TECKNIT 78-24571 SILICONE SPONGE W/SCREEN	GSEPC764	4-05	>21				FILM
TECKNIT 78-24571 SILICONE SPONGE W/SCREEN	GSC11839	4-05	>01				FILM
TECKNIT 78-10005 BLACK RUBBER GASKET/O RING	GSC11860	4-05	>01				FILM
TECKNIT 86-10005 BLACK RUBBER GASKET/O RING	GSC13213	4-02	>34				FILM
TECKSPAN PART 48-09866 WIRE EMBEDDED SILICONE	GSC13216	4-15	>20				FILM
TECKSPAN PART 48-09866 WIRE EMBEDDED SILICONE	GSEPC2723	4-14	>05				FILM
TEDLAK COATING ON ALUMINUM	GSEPC2723	4-14	>05				FILM
TEFLON 150 UHMW POLYETHYLENE BLACK FILM	GSEPC1999	4-02	>00				FILM
TEFLON PEPE INSULATION TUBE 2-731	GSEFC1249	4-02	>00				FILM
TEFLON PEPE SURGE FILM 400	GSEPC4692	4-01	>00				FILM
TEFLON PEPE TYPE A FILM	GSC10669	4-00	>00				FILM
TEFLON PEPE INSUL	GSEPC4833	4-00	>00				FILM
TEFLON PEPE 33181619 BRAND-REX	GSEPC4830	4-00	>00				FILM
TEFLON PFA FILM SHEET TE-9705	GSEPC4830	4-01	>00				FILM
TEFLON PFA MOLDED SPECIMEN TE-9704	GSEPC4828	4-00	>00				FILM
TEFLON PFA BEADS (PERFLUOROALKOXY TEFLO) SODIUM ETCHED	GSEPC4476	4-00	>00				FILM
TEFLON PFA WIRE SLEEVING TE-9704 UNETCHED	GSEPC4834	4-00	>00				FILM
TEFLON PIPE CONDUCTOR RIBBON CABLE INSULATION	GSEPC4832	4-00	>00				FILM
TEFLON TFE/PTFE 66/ALUMINA CAPTON/Y96 COMPOSITE TAPE	GSC10850	4-00	>00				FILM
TEFLON/GARLUC 601/SILVER/ALUM FOIL COMPOSITE TAPE	GSC11129	4-57	>01				FILM
TEFLON/GARLUC 601/SILVER/ALUM FOIL COMPOSITE TAPE	GSEPC1636	3-34	>13				FILM
TEFLON PFA FILM	GSEPC3455	4-03	>02				FILM
TEFLON PFA FILM	GSEPC4071	4-12	>02				FILM
TEKFIT GPO 135 BLACK POLYOLEFIN SHRINK TUBING	GSC10209	4-58	>05				FILM
TEKFIT GPR 135 BLACK POLYOLEFIN SHRINK TUBING	GSC10233	1-13	>28				FILM
TELATEMP MODEL 110 TEMP RECORDER TAPE/F	GSC10074	2-55	>27				FILM
TEMP-PLATE 240/EC	GSEPC0598	2-90					

MATERIAL	DATA REFERENCE	#TEL	%VCV	CURE TIME	CURE TEMP	ATHS	APPLICATION
TEAP-PLATE 240/SCREEN	GSEPC0596	4-14	.30				
TEAP-B-GLAS A2	GSEPC389	-47	-24				
TEAP-B-TAPE A-471	GSEPC3598	-87	-33				
TEAP-B-TAPE C-TEFLON	GSEPC1371	-67	-39				
TEAP-B-TAPE C-400	GSEPC2993	-27	-05				
TEAP-B-TAPE G-550	GSEPC0993	-30	-46				
TEAP-B-TAPE G-557	GSEPC1218	-1-14	4H	205	AIR		
TEAP-B-TAPE G-565	GSEPC1383	-2-72	1-46				
TEAP-B-TAPE G-569	GSEPC1329	-32	-93				
TEAP-B-TAPE H-225	GSEPC231	-69					
TEAP-B-TAPE H-225	GSEPC0502	-22	-67				
TEAP-B-TAPE H-350	GSEPC1320	-1-20	-28				
TEAP-B-TAPE H-352	GSEPC0976	-26	-15				
TEAP-B-TAPE H-430	GSEPC0988	-14	-02				
TEAP-B-TAPE H-650	GSEPC0922	-14	-03				
TEAP-B-TAPE K-100	GSEPC3523	-19					
TEAP-B-TAPE K-100	GSEPC3623	-1-44	-01				
TEAP-B-TAPE K-100	GSEPC3624	-1-44	-01				
TEAP-B-TAPE K-102	GSEPC4548	-1-74	-60	24H	66	E-4	
TEAP-B-TAPE K-102	GSEPC3508	-65	-01				
TEAP-B-TAPE K-104	GSEPC6868	-1-42	-01				
TEAP-B-TAPE K-105	GSEPC3132	-1-64	-15				
TEAP-B-TAPE K-250	GSEPC3123	-68					
TEAP-B-TAPE K-250	GSEPC3622	-88					
TEAP-B-TAPE K-35C	GSEPC4550	-81	-22	24H	66	E-4	
TEAP-B-TAPE K-650	GSEPC3135	-81	-20				
TEAP-B-TAPE K-652	GSEPC3135	-81	-39				
TEAP-B-TAPE K-660	GSEPC3186	-93	-47				
TEAP-B-TAPE K-669	GSEPC0921	-48	-04				
TEAP-B-TAPE K-706	GSEPC0875	-63	-04				
TEAP-B-TAPE K-97	GSEPC0994	-41	-04				
TEAP-B-TAPE K-99	GSEPC3138	-52	-05				
TEAP-B-TAPE TH-TEFLON	GSEPC3189	-37	-05				
TEAP-B-TAPE TH-TEFLON	GSEPC3192	-34	-25				
TEAP-B-TAPE TH-TEFLON	GSEPC0941	-1-07	-27				
TEAP-B-TAPE TH-TEFLON	GSEPC3141	-50	-27				
TEAP-B-TAPE TH-TEFLON	GSEPC3195	-71	-31	24H	100	AIR	
TEAP-B-TAPE TH-TEFLON	GSEPC1827	-52	-53				
TEAP-B-TAPE TH-TEFLON	GSEPC2308	-92	-53				
TEAP-B-TAPE TH-TEFLON	GSEPC1842	-42	-23				
TEAP-B-TAPE TH-TEFLON	GSEPC0977	-5-6	-22				
TEAP-B-TAPE TH-TEFLON	GSEPC9074	-2-04	-09				
TENNCO 1194	GSEPC992	-089	-95				
TENSOLITE 4318-L	GSEPC995	37-82	22-77				
TERMINAL T-2-S	GSEPC13275	-36	-17				
TERYACO RB PREMIUM	GSEPC1120	-37	-08				
TP 1004 POLIURETHANE	GSEPC1159	-91	-03				
TP 1008 POLIURETHANE/GASS AS 60./40	GSEPC0986	-71	-15				
TH 1006 SILICONE	GSEPC2251	-16H	119				
THALCO 331/732/AEE/BLACK DYE	GSEPC1957	1-54	-14				
TERMA-FILM 43-03-4 INSULATOR	GSEPC4742	1-08	-03				
TERMA-BOND	GSEPC3835	1-89	-02				
TERMACOTE 250 THERMAL JOINT CPND	GSEPC3698	-09	-25				

MATERIAL	REFERENCE	DATA	XTHL	XCVCM	CURE TIME	CURE TEMP	AIRUS	APPLICATION
THERMATECS XT-24 TEE SLEEVING - NON SHRINKABLE	GSFEC52459	.04	.00					WIRE INSUL
THERMATECS 1XZ-20-1932 WHITE WIRE INSUL	GSFEC5244	.04	.00					WIRE INSUL
THERMATECS 34Z-16-1929 BLACK WIRE INSUL	GSFEC5247	.04	.00					WIRE INSUL
THERMATECS 63514AA OUTER WHITE LACQUER IMPREG NYLON	GSFEC4522	.46	.03					WIRE INSUL
THERMAX TEFLON IMPREG FIBERGLASS WIRE INSULATION	GSFEC3159	.02	.01					WIRE INSUL
THERMAX TEFION TEE WIRE INSULATION TYPE E	GSFEC2599	.87	.02	1H	143	44R	AIR	COATNG
THE RELELEC G 3334 BLACK ANTI-TRACK COATING	GSC10377	8.55	.39	5H	204	AIR	AIR	
THE RELELEC CONNECTION BOOT 214A332-3 HEAT GUN SHRINK	GSC104238	1.66	.18	5H	225	AIR	SURINK TUBING	
THE RELELEC CRN CLEAR	GSFPC4236	1.66	.05	5H	200	AIR	SURINK TUBING	
THE RELELEC CRN WHITE	GSFPC4186	1.14	.02	3H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - BLACK HEAT GUN SHRINK	GSFPC7469	1.02	.02	2H	250	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - SURFACE ETCHED	GSFPC4184	1.50	.02	3H	232	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - BLACK SHRINK TUBING	GSFPC4524	1.72	.02	3H	217	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC9410	1.24	.02	2H	217	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC8409	1.24	.02	2H	217	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC8807	.97	.05	5H	175	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC8831	.72	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC8102	.68	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC2979	.15	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC935	1.16	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC3013	.77	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFRC12619	.43	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5369	.68	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC5557	.68	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC4295	.61	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC4712	.61	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC6104	.69	.01	1H	200	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFRC5000	.76	.25	0.5H	140	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5002	.63	.26	0.5H	140	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5052	.83	.34	0.5H	140	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5070	.71	.26	0.5H	140	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC9413	.82	.51	0.5H	177	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5076	.52	.24	0.5H	140	AIR	SURINK TUBING	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC1687	.00	.00					INSUL SLEEVE
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC4404	.06	.01	1H	125	AIR	PRIMER	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC4714	.59	.12	1H	60	AIR	ADHESIVE	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC4716	.75	.12	1H	25	AIR	INSULATION	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC4714	.96	.12	1H	60	AIR	LINE CORD	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC6938	1.48	.12	1H	60	AIR	LINE CORD	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC6995	2.09	.20	1H	60	AIR	LINE CORD	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5715	.15	.05	1H	60	AIR	LINE CORD	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5691	.37	.01	1H	60	AIR	LINE CORD	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFPC5787	.09	.01	1H	60	AIR	PAINT	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC2011	.08	.09	1H	190	AIR	PAINT	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC2011	.08	.09	2H	60	AIR	PAINT	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSFEC3997	5.78	.08	1H	25	AIR	SWAKING CPND	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSC10146	1.46	.14	90H	126	AIR	PUTTING FOAM	
THE RELELEC KYN CLEAR - POLYOLEFIN HEAT GUN SHRINK	GSC10146	1.46	.14	90H	110	B-6		

MATERIAL	DATA REFERENCE	XTHL	XCVCM	CURE TIME	CURE TEMP	AIRJS	APPLICATION
TJ - 1000 SYNTACTIC FOAM WHITE	GSPC4440	1.82	.59	8H	65	AIR	FUAN
TORLON 4203 MOLDING CPND POLYAMIDE/IMIDE	GSPC9674	1.65	1.00	10H	121	AIR	MOLD CPND
TORQUE SEAL A/B AS 1/1 BY	GSPC3672	10-16	1-08	7D	25	AIR	LACQUER
TP - 2 PANDUIT NYLCN SUPPORT	GSPC0981	1-84	-00	24H	25	AIR	NYLCN SEALANT
TRA - BOND 2101 EPOXY BIPAX KIT	GSPC3125	1-89	-02				SUPPORT
TRA - BOND 2106 EPOXY BIPAX KIT THIXOTROPIC	GSPC3179	1-71	-01				SUPPORT
TRA - BOND 2111 STAKING CPND EPOXY BIPAX KIT	GSPC6647	1-35	-08	7D	60	AIR	ADHESIVE
TRA - BOND 2112 STAKING CPND EPOXY BIPAX KIT	GSPC6131	2-95	-08	7D	60	AIR	STAKING CPND
TRA - BOND 2113 EPOXY BIPAX KIT	GSPC6848	1-45	-01	7D	225	AIR	STAKING CPND
TRA - BOND 2114 CLEAR EPOXY BIPAX KIT/FOIL SANDWICH	GSPC2937	3-40	-15	24H	225	AIR	ADHESIVE
TRA - BOND 2116 EPOXY BIPAX KIT	GSPC6134	3-16	-05	24H	225	AIR	ADHESIVE
TRA - BOND 2122 ALUM FILLED EPOXY BIPAX KIT	GSPC7901	1-01	-05	24H	225	AIR	STAKING CPND
TRA - BOND 2126 BLACK EPOXY BIPAX KIT	GSPC9107	1-15	-05	24H	225	AIR	ADHESIVE
TRA - BOND 2135D BLACK EPOXY BIPAX KIT	GSPC7661	2-27	-31	7D	225	AIR	ADHESIVE
TRA - BOND 2143D PCLYMID-EPOXY BIPAX KIT	GSPC4118	2-09	-10	3D	225	AIR	ADHESIVE
TRA - BOND 2151 THERE COND EPOXY BIPAX KIT	GSPC6248	1-95	-06	7D	225	AIR	ADHESIVE
TRA - BOND 2160 PCLYMID-EPOXY BIPAX KIT	GSPC6251	1-95	-06	7D	225	AIR	ADHESIVE
TRA - BOND 2248 THIXOTROPIC HI-TEP EPOXY BIPAX KIT	GSPC6254	-72	-01	16H	225	AIR	ADHESIVE
TRA - CON ERL2795/2793 EPOXY KIT	GSPC3389	1-43	1-04	2H	90	AIR	AIR
TRA - CON J1158/R-8 AS 50/6.25 BW EPOXY	GSPC3379	16-04	1-13	1H	225	AIR	AIR
TRA - DUCT BA 2902 EPOXY KIT - SILVER FILLED	GSPC3177	1-06	0-03	2H	60	AIR	COND ADHESIVE
TRADITION FILM POLYPARABANIC ACID (H)	GSC10275	1-26	0-00	2H	60	AIR	COND INSUL FILM
TRANSLUBE 20204 LUBRICANT FILM	GSC11135	9-13	5-88	30M	121	AIR	LUBRICANT FILM
TRYKEFIL S4-19-0-17 POLYESTER	GSC13422	5-29	2-04				LUBRICANT FILM
TRYOUTUF 1-9-0-195 AON WOVEN DACRON FELT WHITE	GSC10835	-33	-18				INTERNAL BLANKET
TRYOUTUF 1-9-0-195 AON WOVEN DACRON FELT WHITE	GSC12210	-04	-03	67H	95	3-5	INTERNAL BLANKET
TRYOUTUF 1-9-0-195 AON WOVEN DACRON FELT WHITE WASHED	GSC12212	-25	-04	20H	115	AIR	INTERNAL BLANKET
TRUCASST 111/901 AS 106/1-4 BW	GSPC2491	-39	-01	24H	225	AIR	POTTING
TRUCASST 111lb/158 AS 1/1 BW GREEN POLYURETHANE	GSPC3722	-85	-02	4H	66	AIR	POTTING
TRUCASST 111lb/158 AS 1/1 BW GREEN POLYURETHANE	GSPC7766	-85	-02	4H	25	AIR	POTTING
TUBING-SILICONE-REEL GRADE 60 CL2 SPEC ZZA765	GSPC4718	.75	-26	6H	50	AIR	TUBING
TUBING-SILICONE-REEL GRADE 60 CL2 SPEC ZZA765	GSPC4769	-09	-24	24H	166	AIR	TUBING
TUPCON 50 MIL-ENE FOLIESTER RIBBON CABLE	GSPC13293	-36	-21	24H	90	E-3	FLEX WIRING
TWINE - LINEN - 020 DIAM 3 FLY	GSPC13374	-36	-24	10H	100	AIR	FLEX WIRING
TY 25M TY-RAP NYLCN CABLE TIE	GSPC13451	2-94	-05				LINE TIE
TY 25H TY-RAP NYLCN CABLE TIE	GSPC81246	-10	-00				CABLE TIE
TY 30H TY-RAP NYLCN CABLE TIE	GSPC0782	-09	-00				CABLE TIE
TY 34H TY-RAP NYLCN CABLE TIE	GSPC6155	2-49	-02	24H	125	AIR	CABLE TIE
TY 46H TY-RAP NYLCN CABLE TIE	GSPC5055	2-33	-00	16H	100	AIR	CABLE TIE
TY 46H TY-RAP NYLCN CABLE TIE	GSPC5103	1-90	-01	24H	125	AIR	CABLE TIE
TY 52H TY-RAP NYLCN CABLE TIE	GSPC5150	1-24	-00	16H	100	AIR	CABLE TIE
TY 52H TY-RAP NYLCN CABLE TIE	GSPC5174	2-49	-02	24H	125	AIR	CABLE TIE
TY - RAP KYNAR CABLE TIE	GSPC9677	1-85	-00	24H	125	AIR	CABLE TIE
TY - RAP MS 3367 NYLCN LACING TAPE	GSPC4134	1-03	-00	24H	125	AIR	CABLE TIE
TY - RAP NYLCN CABLE TIE	GSPC2591	1-83	-00	24H	125	AIR	CABLE TIE
TYB 23M TY-RAP NYLCN CABLE TIE	GSPCU662	2-60	-01	24H	125	AIR	CABLE TIE
TYB 23H TY-RAP NYLCN CABLE TIE	GSPC4984	-85	-06	16H	100	AIR	CABLE TIE

MATERIAL	DATA REFERENCE	XTEL	ACVN	CURE TIME	CURE TEMP	ADHS	APPLICATION
TYB 24 NY-TRAP NYLON CABLE TIE	GSPC9458	2-06	.01	24H	125	AIR	CABLE TIE
TYB 25 NY-TRAP NYLON CABLE TIE	GSPC9461	1-98	.01	24H	125	AIR	CABLE TIE
TYGON TUBING FORURETANE TUBING	GSPC9389	32-91	14-.19				TUBING
TYGOTHANE POLYURETHANE COATING	GSPC9395	3-44	.03				CABLE COATING
TY-MAGNET WIRE POLYCLYRETHANE COATING	GSPC94598	3-43	.03				CABLE COATING
UCARSLI 1-4310 SILICONE	GSPC9392	2-66	.08				CONF COAT
ULTEM D6202 GREY/BROWN MOLD COMPND UNFILLED INFORCED	GSPC93437	12-07	.00				COND CPND
ULTEM 1000 CLEAR AMBER MOLD COMPND UNFILLED INFORCED	GSPC93561	1-37	.00				COND CPND
UNICOAT 2081-31A ONE COMPONENT EPOXY/P	GSPC93568	1-40	.00				COND CPNT
UNICOAT 2081-31A ONE PART FLUORESCENT EPOXY/F	GSPC91971	5-.95	.99	3H	25	AIR	COND COAT
UNIGLASS 154-2 GREEN EPOXY INK	GSPC12280	-31	.11	2H	125	AIR	COND COAT
UNIGLASS 1752 GREEN EPOXY INK	GSPC5993	6-03	.01	1.25	70	AIR	COND COAT
UNIGLAZE 2010/9120 AS 3/1 EW YELLOW EPOXY INK	GSPC6048	5-21	.11	2H	85	AIR	COND COAT
UNIGLAZE 3005/9120 AS 3/1 EW RED EPOXY INK	GSPC3538	7-82	.08	1H	121	AIR	COND COAT
UNISET C-110 ONE COMPONENT SILVER FILLED EPOXY	GSPC1974	1-81	.95	1H	150	AIR	COND ADHESIVE
UNISET C-113 ONE COMPONENT SILVER FILLED EPOXY	GSPC12483	4-44	.15	1H	150	AIR	COND ADHESIVE
UNISET C-429-2 SILVER FILLED THIXOTROPIC EPOXY	GSPC2193	1-19	.01	90H	125	AIR	COND ADHESIVE
UNISET C-840 SILVER FILLED EPOXY ONE COMPONENT	GSPC1711	1-31	.00	30M	125	AIR	COND ADHESIVE
UNISET C-840 SILVER FILLED EPOXY ONE COMPONENT	GSPC2259	1-32	.00	1H	125	AIR	COND ADHESIVE
UNISET C-850 SILVER FILLED EPOXY ONE PART	GSPC1714	1-14	.99	30M	125	AIR	COND ADHESIVE
UNISET C-850-4 SILVER FILLED EPOXY ONE PART	GSPC1956	1-43	.01	1H	125	AIR	COND ADHESIVE
UNISET C-850-6 ONE COMPONENT SILVER FILLED EPOXY	GSPC1977	1-60	.01	1H	125	AIR	COND ADHESIVE
UNISET C-929-4 SILVER FILLED EPOXY	GSPC1717	1-31	.00	30M	125	AIR	COND ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	GSPC1720	1-06	.00	10H	170	AIR	COND ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	GSPC1739	-02	.00	1H	170	AIR	COND ADHESIVE
UNISET C-940-4 ONE COMPONENT SILVER FILLED POLYIMIDE	GSPC1986	-.08	.00	10H	270	AIR	COND ADHESIVE
UNISET ME-845 THERMAL COND ADHESIVE ULTRA-GREEN	GSPC22216	-.30	.01	1H	125	AIR	TERM COND ADH
UNISET ME-945 ONE COMPONENT POLYIMIDE/F	GSPC2242	-.26	.02	1H	170	AIR	TERM COND ADH
UNISET 906-25 SEMI-KRIGED EPOXY	GSPC6314	1-31	.31	30M	270	AIR	ADH-POTTING FOAM
UNISET 909-6 ONE COMPONENT FILLED EPOXY	GSPC1980	1-48	.04	1H	125	AIR	ADH-POTTING FOAM
UNITED FOAM 5010 MIL P26514 GRAY TYPE I ALCOHOL WASH	GSPC12484	1-17	.99	6H	100	AIR	FOAM
UNITED FOAM 5010 EIL P26514 GRAY TYPE I CLASS II G A	GSPC12166	4-33	.54				FOAM
URALANE 1723 A/3 LAS 100/85 B/W LITHIUM FLUORIDE	GSPC1699	2-44	.51	24H	90	AIR	FOAM
URALANE 22H POLYURETHANE FOAM	GSPC1697	2-50	.24	24H	25	AIR	FOAM
URALANE 22H POLYURETHANE FOAM	GSPC1675	2-06	.08	2H	25	AIR	FOAM
URALANE 22H POLYURETHANE FILM	GSPC9023	1-60	.06	24H	75	AIR	COND COAT
URALANE 22H POLYURETHANE FILM	GSPC8225	2-44	.05	16H	75	AIR	COND COAT
URALANE 22H POLYURETHANE 2 COAT SAMPLE	GSPC9173	3-44	.02	7D	25	AIR	COND COAT
URALANE 22H POLYURETHANE 2 COAT SAMPLE	GSPC31626	1-65	.01	20M	25	AIR	COND COAT
URALANE 22H/MDAC FLUORESCENT TRACER	GSPC9026	2-43	.08	15H	25	AIR	COND COAT
URALANE 5712 A/B AS 100/55 BW	GSPC1840	18-28	.08	24H	75	B-O	COND COAT
URALANE 5738 A/B AS 100/55 BW	GSPC1276	10-71	1.18	16H	93	AIR	COND COAT

MATERIAL	DATA REFERENCE	XMTL	XCVH	CURE TIME	ATMOS	APPLICATION
URALANE 5750 A/B AS 18/100 BW	GSPC7322	.41	.03	14H	AIR	LUMI COAT
URALANE 5750 A/B AS 18/100 BW	GSPC7325	.83	.03	2H	AIR	LUMI COAT
URALANE 5750 A/B AS 4/25 BW URETHANE	GSPC5379	.45	.01	3H	AIR	LUMI COAT
URALANE 5753 A/B AS 1/5 BW	GSPC7535	1.01	.02	14H	AIR	LUMI COAT ADHESIVE
URALANE 5753 A/B/ALUMINA AS 1/5/3 BW	GSPC7538	.73	.03	14H	AIR	ADHESIVE
URALANE 5753LV A/E AS 1/5 BW POLYURETHANE	GSC11156	.62	.01	24H	AIR	LUMI COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	GSC11159	.69	.01	7D	AIR	LUMI COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	GSC12814	.87	.01	7D	AIR	POTTING
URALANE 5753LV A/E AS 1/5 BW POLYURETHANE/PRIMER PR 1	GSC11413	.69	.02	14D	AIR	POTTING
URALANE 8260	GSC12691	1.74	.03	25	AIR	ATHERM ADHESIVE
URALANE 8267 TRANSPARENT PCLOUDURETHANE	GSPC1458	10.00	.17	24H	AIR	CATING
GS 0009 A/B AS 100/35 BW POLYURETHANE	GSPC7568	13.69	7.55	2H	AIR	LUMI COAT
UV 66 SUMMERS LABS - DATA INCLUDES GLASS SUBSTRATE	GSPC0615	11.03	.04	16H	AIR	
UV 69 OPTICAL CEMENT POLYMERIZED WITH SUN LAMP	GSPC1331	11.03	.04	5H	AIR	
UVE 1003 EPOXY OPTICAL ADHESIVE/P 5 MIN UV EXP	GSC11481	1.418	1-10		AIR	OPT CEMENT
UVE 1003 EPOXY OPTICAL ADHESIVE/P 5 MIN UV EXP	GSC11551	1.91	1-10		AIR	OPT CEMENT
V 35780 A/B AS 1/1 BW BLACK POLYURETHANE POSTCURE	GSPC8369	2.19	1.01	16	AIR	OPT CEMENT
V 35780 A/B AS 1/1 BW BLACK POLYUROTHANE 2 STEP POSTCURE	GSC12308	2.60	.01	30H	82	P-2
V 35780 A/B AS 1/1 BW BLACK POLYUROTHANE 2 STEP POSTCURE	GSPC1705	3.47	.01	4H	177	P-2
V 70C075/BENZOYL PEROXIDE AS 100/1 B	GSPC0433	1.48	.01	10H	AIR	TUBE SEALANT
VACSEAL SILICONE LEAK SEALER	GSPC0751	1.48	.01	7D	AIR	TUBE SEALANT
VACSEAL SILICONE LEAK SEALER	GSPC6852	1.35	.01	24H	AIR	TAPE SEALANT
VALCOR O RING - RTV 75 PTFE FILM/SILICONE ADH/F	GSPC9042	.25	.02		AIR	WHEEL
VALOX 310 THERMOELASTIC POLYESTER	GSPC3554	.25	.02		AIR	WHEEL
VALOX 420 THERMOELASTIC POLYESTER/30% GLASS FIBER	GSPC3602	.16	.03		AIR	WHEEL
VALOX 420 THERMOELASTIC POLYESTER/30% GLASS FIBER	GSPC3578	.09	.02		AIR	WHEEL
VARGLAS S-1600 NON FRAY SLEEVING TYPE HO	GSPC3419	.58	.01		AIR	WHEEL
VARGLAS SPEC A 307 GLASS/SILICONE SLEEVE	GSPC4496	.01	.01		AIR	WHEEL
VARNISH STERLING THERMOPOXY I-65-3-LBH	GSPC8030	.60	.07		AIR	WHEEL
VARNISH STERLING THERMOPOXY I-65-3-LBH	GSPC4430	1.82	.01		AIR	WHEEL
VARY-FLEX EPOXY PVC AMIDE	GSPC4890	.70	.02		AIR	WHEEL
V2-3 NYLOCK SEALING CPND	GSC12550	.64	.01	24H	AIR	POTTING
V2-3 NYLOCK SEALING CPND	GSPC2637	3.61	.62	40H	AIR	POTTING
VELCRO ASTRO HELI POLYESTER-BETA GLASS-TEFLON-FLUOREL	GSPC4025	3.99	.68	1H	74	AIR
VELCRO HI-AIR FASTENER NOMEK FLAME RETARD	GSC10997	.78	.19	1H	121	AIR
VELCRO HI-AIR FASTENER NOMEK FLAME RETARD	GSPC3879	5.33	2.04		AIR	FASTENER
VELCRO HI-AIR FASTENER NOMEK FLAME RETARD/EXTRACTED	GSPC8510	2.39	.01	16H	100	FASTENER
VELCRO HI-AIR HOCK LOOP FLAME RETARD 0399 BACKING	GSPC3881	2.97	.00		AIR	FASTENER
VELCRO HI-AIR HOCK LOOP FLAME RETARD 0399 BACKING	GSPC7961	5.92	1.93		AIR	FASTENER
VELCRO HI-GAKED HOCKS STAINLESS STEEL	GSPC7944	3.74	.58		E-2	FASTENER
VELCRO HI-TEMP FASTENER NOMEK/NOMEX/POLYIMIDE	GSPC2869	3.02	.01		AIR	FASTENER
VELCRO NYLON HOOK AND LOOP	GSPC3883	.52	.00		AIR	FASTENER
VELCRO NYLON HOOK/LOOP C199 BACKING	GSPC2939	1.98	.05		AIR	FASTENER
VELCRO NYLON HOOK/LOOP C199 BACKING	GSPC7964	1.50	.04		AIR	FASTENER
VELCRO NYLON HOOK/LOOP C199 BACKING	GSPC2320	1.34	.20		AIR	FASTENER

MATERIAL	DATA REFERENCE	XTHL	%CVCH	CURE TIME	CURE TEMP	ATTUS	APPLICATION
VELCRO P537 FIBERGLASS FLUOREL/TEFLON LOOPS	GSPC3199	-57	-21				FASTENER
VELCRO V330-1/65-63V330-2-B3 BLACK NYLON HEL	GSPC6834	-1	-92				FASTENER
VELCRO 100-003-017-O27ACB NOHEX HOOK AND LOOP	GSPC2823	-54	-70	25	AIR		FASTENER
VELCRO 100-005-012-0199AG/100-101-012-0199AB HEL	GSPC6279	-5	-13	14D	AIR		FASTENER
VELCRO 100-006-015-012-0199AF STAINLESS LOOP	GSPC6356	-70	-99				FASTENER
VELCRO 100-006-015-1-0199AF STAINLESS LOOP	GSC13337	-1	-30				FASTENER
VELCRO 100-006-015-1-0199AF STAINLESS LOOP	GSC13353	-1	-30				FASTENER
VELCRO 100-006-015-1-0199AF STAINLESS LOOP	GSC12452	-1	-40				FASTENER
VELCRO 1000-081-012-0199 WHITE O/L GEEEN	GSC12468	-1	-10				FASTENER
VELCRO 1000-081-016-0199 O/L GEEEN	GSC12470	-1	-98				FASTENER
VELCRO 1000-081-0199/1000-009-3330-0199 BLACK	GSPC6119	-5	-45				COND FOAM
VELEROAM 1901 BLACK CONDUCTIVE PLASTIC	GSPC1963	-5	-67				FILM
VELSTICK 101/ACC1 1/P	GSPC1979	-7	-47				ADHESIVE
VESPEL KS-105 ARAMID	GSPC10056	-3	-35				STRUCTURAL
VESPEL SP-21-D-1 POLYIMIDE/15% GRAPHITE/10% TEFZOL	GSPC3411	-3	-48				SOLID LUBE
VESPEL SP-21-D-1 POLYIMIDE/BESIN	GSPC3405	-58	-99				SOLID LUBE
VESPEL SP-21-D-1 POLYIMIDE/15% GRAPHITE AS 60/40 BW	GSPC3407	-5	-57				SOLID LUBE
VESPEL SP-22-D-1 POLYIMIDE/GRAPHITE AS 60/40 BW	GSPC2997	-5	-54				SOLID LUBE
VESPEL SP-3 POLYIMIDE/15% MOS2 FORMERLY SP-31-D-1	GSPC3409	-49	-99				SOLID CPND
VESPEL SP-5 POLYIMIDE/30% SHORT GLASS FIBERS	GSPC1099	-3	-37				LARGE SEAL
VP 100-7 PVC 35% EILEEN GLASS	GSPC10149	-2	-14	24H	AIR		PLATE COATING
VIBRA-TITE PASSENE/F	GSPC5487	-57	-02				PLATE COATING
VIBRO-FLO E-301 EPoxy POWDER COATING	GSPC4478	-86	-38				PLATE COATING
VINYLSYNTHITE AU-1/BT 215 AS 1/2 BW	GSPC3139	-43	-24H				SEAL CPND
VISHAY DISPERSION PLASTISOL 77-3720 BLACK	GSPC3246	-2	-21				SEAL CPND
VISHAY HELD COMPCNENT 311856 BLACK	GSPC12466	-2	-21				SEAL CPND
VITON A O RING NAS 1593-012	GSPC2434	-89	-39				URING
VITON B DURONT B-25 FOAM RUBBER BLACK CLOSED CELL	GSPC4382	-86	-04				SHAMMET
VITON C HOSE IMPREGNATE LACRON DUPONT 84-001	GSPC1696	-36	-04				SEAL
VITON IMPREGNATE LACRON DUPONT 84-001	GSPC4188	-3	-96	16H	AIR		ROAD DAMPER
VITON TUBING C-6412-47	GSPC2422	-30	-03				TUBING
VITON 05-2154 CLOSED CELL EXTRUDED FOAM - GRAY	GSPC5251	-35	-03				DAMPER
VOLARA FOAM	GSC12277	-1	-3				FUAM
VORITE 63 POLYURETHANE COATING	GSPC4208	-91	-01	16H	AIR		JUN SHIELD
VULTA 16L204 RIGID POLYURETHANE FOAM 4#/CU FT	GSPC1162	-3	-80				CONF COAT
VULTA 16L204 RIGID POLYURETHANE FOAM 4# ETOH WASH	GSC11415	-1	-99	24H	AIR		FOAM
W DAY 1000 FLUOROTELFEMER	GSPC5224	-67	-02				LUBRICANT
WAKBEL THERMAL GREASE 120	GSC11261	-50	-19				WASHER
WASHER POLYPHENYLENE SULFIDE 40% GLASS FILLED	GSPC0951	-38	-01				WASHER
WP 100-6 THERMOPLASTIC POLYESTER/FIB GLASS AS 70/30	GSPC09475	-1	-80				WELD CPND
WILCO PAST SET EPOXY 2-PART KIT	GSPC5972	-1	-69				WELD CPND
WIRE INSULATION GREEN COATED KAPTON MIL-W-81381/7	GSC13099	-1	-69				WIRE INSUL
WIRE INSULATION GREEN FLUOROCARBON POLYIMIDE/TFE	GSC11069	-24	-07				WIRE INSUL
WIRE INSULATION ORANGE MIL-W-22759/16-20	GSPC5893	-1	-07				WIRE INSUL
WIRE INSULATION EEL FLUOROCARBON POLYIMIDE/TFE	GSC11072	-1	-19				WIRE INSUL
WIRE INSULATION WHITE COATED KAPTON MIL-W-81381/7	GSC13117	-1	-02				WIRE INSUL
WIRE INSULATION WHITE FLUOROCARBON FO1A080	GSC11830	-03	-05				WIRE INSUL
WORNOW CAT-LINK 50-100/CAT 20 AS 20/1 BW WHITE	GSPC5895	-5	-99	-01	30M	25	AIR
				-2H	60	AIR	

MATERIAL	DATA REFERENCE	DATA STHL	ACVCH	CURE TIME	CURE TEMP	AIR VACUUM	APPLICATION
WORNOW CAT-L-INK 50-100/CAT 9/50-900 THINNER WHITE/F GSPC8240	-62	.01	30H	25	AIR 133	AIR 149	INK
WORNOW CAT-L-INK 5C-121869/CAT 28 AS 20/1 BW ALUM	GSPC4214	10-94	.05	30H	AIR 149	AIR 149	INK
WORNOW CAT-L-INK 50-300/CAT 20 AS 100/6-4 BW GREEN	GSPC4212	8-76	.18	30H	AIR 149	AIR 149	INK
WORNOW CAT-L-INK 50-407/CAT 20 AS 100/7-5 BW BLUE	GSPC2482	11-75	.09	SD	AIR 149	AIR 149	INK
WORNOW CAT-L-INK 50-700/CAT 20 AS 100/7 BW	GSPC2751	4-86	.01	1H	93	AIR 149	INK
WORNOW H-2-N RED/CAT 45/T-1 THINNER/F	GSPC8243	.40	.02	1H	25	AIR 149	INK
WORNOW H-5-N GREEN/CAT 45/T-1 THINNER/F	GSPC8246	.44	.02	1H	149	AIR 149	INK
WORNOW SERIES M REL INK M-2-N 0-25 CAT A WORNOW SERIES M WHITE INK R-9-N 5-0 CAT	GSPC2479 GSPC2605	9-94 4-63	.05 .04	SD 3H	25	AIR 66	INK
WORNOW 1000 MASK FILM GREEN	GSC19688	2-07	.43	1H	135	AIR 135	MASK
WORNOW INK H-0-N/CAT A AS 100/4 BW BLACK PRE-MIX INK	GSC11615	7-95	.13	SD	25	AIR 149	INK
WORNOW INK H-2-N/CAT B3 AS 100/4 BW BLACK PRE-MIX INK	GSC11618	5-08	.09	SD	25	AIR 149	INK
WORNOW INK H-2-N/CAT A AS 100/4 BW RED EPOXY INK	GSC11621	6-67	.16	SD	25	AIR 149	INK
WORNOW INK H-2-N/CAT D3 AS 100/4 BW RED EPOXY INK	GSC11624	4-20	.11	3H	54	AIR 149	INK
WORNOW INK H-4-N/CAT 45 AS 20/1 BW YELLOW EPOXY	GSC12721	.84	.19	1H	25	AIR 149	INK
WORNOW INK H-9-N/CAT A AS 100/4-9 BW WHITE PREMIX INK	GSC11645	6-10	.11	SD	25	AIR 149	INK
WORNOW INK H-9-N/CAT B3 AS 100/4-9 BW WHT PREMIX INK	GSC11648	4-27	.11	SD	25	AIR 149	INK
X 3878-15-1 SILICONE PSA	GSPC694	4-53	.05	3H	54	AIR 60	ADHESIVE
X 7902 A/B AS 4/1 EW BLACK FLEXIBLE EPOXY	GSPC7349 GSC11439	2-35 -48	1-05 .12	30H 2H	25	AIR 125	ADHESIVE
X 7902 A/B AS 4/1 EW BLACK FLEXIBLE EPOXY	GSC11441	.47	.11	4H	125	AIR 149	ADHESIVE
X-850 FILM LAMINATE ALUM NYLAR/DACRON SCRIM/AL NYLAR	GSPC5266	.51	.14	168H	125	AIR 125	COVER
XG-U-H179 ONE COMPONENT GAY EPOXY	GSC10134	1-28	.04	1H	125	AIR 125	ADHESIVE
XG-U-H179 A/B AS 10/4 BW POLYURETHANE	GSPC1486	15-72	1-06	16H	85	AIR 85	PUTTING
XC9-G710/H2 3561 AS 100/26 BW EPOXY	GSPC1498 GSPC0924	.90	.02	24H	25	AIR 25	ADHESIVE
XEGCH CS-14 125 SILVER FILLED SILICONE	GSPC6528	1-11	.05	6H	69	AIR 177	SEAL GASKET
XF 1004 POLYIMIDE GLASS AS 80/20	GSPC2867	1-06	.01	SD	125	AIR 125	BUILD CBN
XF 1006 POLYARYL ETHER GLASS AS 70/30	GSPC2931	.80	.00	2H	66	AIR 100	ROAM DAMPER
XN 3529/ECCOSPHERE SI AS 1/2 BW SYNTACTIC FOAM PINK	GSPC7349	.82	.01	2H	100	AIR 100	ROAM DAMPER
XN 3529/ECCOSPHERE SI AS 1/2 BW SYNTACTIC FOAM PINK	GSPC7367	.88	.04	2H	66	AIR 100	ROAM DAMPER
XN 3529/ECCOSPHERE SI AS 1/2 BW SYNTACTIC FOAM PINK	GSPC7424	1-14	.04	2H	100	AIR 100	ROAM DAMPER
XR-1-MC-154 POLYIMIDE MEMBRANE	GSPC1291	1-14	.04	1H	125	AIR 125	STRUCTURAL
XR PERFLUOROSULFONIC ACID PRECURSOR TUBING	GSPC2999	4-77	.02	SD	66	AIR 66	ADHESIVE
XR SODIUM PERFLUOROSULFONATE FILM	GSPC3017	-03	.02	SD	125	AIR 125	TUBING
XR-4-3099 ONE PART SILICONE	GSPC5082	2-41	.00	7D	25	AIR 25	FLASH
XR-4-3138 ONE PART SILICONE	GSPC5085	1-39	.24	7D	25	AIR 25	ADHESIVE
XR-5140 A/B AS 2/3 BW BROWN SEMI-RIGID EPOXY	GSPC7280	1-69	.52	16H	90	AIR 90	ADHESIVE

MATERIAL	DATA REFERENCE	XMTL	XCVN	CURE TIME	CURE STATUS	TEMP	APPLICATION
XR-5140 A/E AS 2/3 BW BROWN SEMI-RIGID EPOXY	GSPC7283	1.39	.59	16H	90	AIR	PUTTING
A3-5166 A/B AS 2/3 BW FLEXIBLE BLACK EPOXY	GSPC8033	2.31	.07	8H	66	AIR	PUTTING
XR-6-2205 ONE PART SILICONE	GSPC5114	2.85	.09	2H	70	AIR	SOLID COAT
XU-021/XHD-G165 AS 1/1 BW BLACK POLYURETHANE	GSPC7679	.87	.01	4H	25	AIR	SOLID COAT
XU40-110/CAT 23A/DYE 7GA AS 454/1.3/0.1 PBW SILICONE	GSPC8183	3.55	1.26	1H	90	AIR	PUTTING
XU43-110/CAT 23A/DYE 7GA AS 454/1.3/0.1 PBW SILICONE	GSPC8186	2.58	1.22	6H	100	AIR	COATING
XU-218 HP POLYIMIDE BULK MATERIAL	GSC10487	2.32	.09	24H	50	AIR	SOLID COAT
XU-2561 A/B AS 100/36 BW CLEAR SILICONE COATING	GSPC7895	.10	.03	14D	25	AIR	SOLID COAT
X1-2561 A/E AS 1C/0.2 BW CLEAR SILICONE COATING	GSPC7994	.19	.03	1H	25	AIR	SOLID COAT
X1-2561 A/B AS 10/1 BW CLEAR SILICONE COATING	GSPC8297	.06	.03	21D	25	AIR	SOLID COAT
X1-2561 A/B AS 10/1 BW CLEAR POLYDIETHYL SILOXANE ONE PART	GSPC8499	.20	.02	7D	25	AIR	SOLID COAT
X3-6022/CAT 6060 AS 10/1 BW SILICONE/PRIMER DC92-023	GSPC8105	.35	.06	1H	25	AIR	ADHESIVE
X3-6092 (26-1125) ONE PART WHITE SILICONE	GSC13903	.17	.01	24H	25	AIR	ADHESIVE
X3-6572 A/B AS 10/1 EW GRAY SILICONE	GSC13147	1.31	.54	20H	80	AIR	ADHESIVE
X-210 VARNISH - THERMODYNAMIC	GSPC7520	1.27	.24	20H	149	AIR	VARNISH
X-210 VARNISH - THERMODYNAMIC	GSPC7664	.56	.07	20H	149	AIR	VARNISH
Y-210 VARNISH INSULATION	GSPC5200	.66	.22	24H	125	AIR	VARNISH
Y-663 THERMOPOXY A/B ONE COMPONENT POLYURETHANE FORMULATION	GSPC5290	.40	.08	177	AIR	ADHESIVE	PUTTING
YARNSLEY Y100/6/2	GSPC7685	1.93	.29	48H	25	AIR	PUTTING
YARSLEY L100/6/4 POLYURETHANE FORMULATION CLEAR	GSPC7769	1.77	.12	48H	25	AIR	PUTTING
2-93 POTASSIUM SILICATE AND WATER BASE	GSPC0481	2.54	.00	3D	50	AIR	RALNT
2-6040 SILICANE PRIMER	GSPC2791	7.97	1.46	24H	25	AIR	RAILER
ZETTEL 101 NOVELL FOAM/20% GLASS FIBERS	GSPC4048	.21	.00	24H	25	AIR	FOAM
ZETTEL 101 NOVELL GLASS AS 70/30	GSPC0960	.04	.00	24H	25	AIR	SOLID CPND
ZETTEL 101 BLACK CONNECTOR INSERT	GSC11669	.21	.03	24H	25	AIR	SOLID INSUL
ZETTEL 101 BLACK EXTRUDED RODS	GSC11657	.19	.00	24H	25	AIR	SOLID COATING
ZETTEL 61 IN ALCOHOL	GSPC2537	2.32	.22	30M	90	AIR	SOLID CPND
ZETTEL 7010-33 NYLON RESIN	GSPC1528	1.99	.00	24H	25	AIR	SOLID CPND
ZETTEL 7110-13 NYLON RESIN	GSPC1525	1.28	.01	24H	25	AIR	SOLID CPND

SECTION C

MATERIALS HAVING A TML

OF 1.0 PERCENT OR LESS

AND A CVCM OF 0.10 PERCENT OR LESS

SECTION 1 -- ADHESIVES

MATERIAL	NER CODE	ATM	SCVCM	CURE TIME	CURE ATMS	APPLICATION
A-1177 E A/B AS 1/1 BW EPOXY - BROWN	EFG	.45	.02	24H	25	AIR ADHESIVE
A-1273-E A/B AS 1/1 BW GREEN EPOXY PER MM A132	BFG	.75	.04	30H	82	AIR ADHESIVE
A-1273-B A/B AS 1/1 BW GREEN EPOXY PER MM A132	BFG	.71	.05	16H	225	AIR ADHESIVE
ABLEBOND 20-1 SILVER FILLED EPOXY ONE COMPONENT	AAC	.19	.00	30H	120	AIR COND ADHESIVE
ABLEBOND 224-8 A/E AS 100/7.3 BW EPOXY	AAC	.39	.00	18H	520	AIR COND ADHESIVE
ABLEBOND 36-2 SILVER FILLED EPOXY	AAC	.30	.00	30H	150	AIR COND ADHESIVE
ABLEBOND 41-5 EPOXY	AAC	.46	.00	30H	150	AIR COND ADHESIVE
ABLEBOND 41-6 LIQUID	AAC	.34	.01	24H	150	AIR COND ADHESIVE
ABLEBOND 463-1 A/E AS 10GM/10DPS SILVER FILLED EPOXY	AAC	.62	.01	24H	25	AIR COND ADHESIVE
ABLEBOND 71-1 SILVER FILLED POLYIMIDE	AAC	.24	.06	14H	95	AIR COND ADHESIVE
ABLEBOND 71-1 SILVER FILLED POLYIMIDE	AAC	.25	.00	10H	275	AIR COND ADHESIVE
ABLEBOND 826-1 ONE COMPONENT 1/1 BW SILVER FILLED ADH	AAC	.58	.03	30H	150	AIR COND ADHESIVE
ABLEBOND 88-1 A/E AS 1/1 BW SILVER FILLED EPOXY	AAC	.76	.00	24H	125	AIR COND ADHESIVE
ABLEBOND ECF 518 CLOTH SUPPORT/EPOXY FILM ADH THIN	AAC	.81	.01	18H	150	AIR COND ADHESIVE
ABLEFILM ECF 550-1 GLASS SUPPORT/SILVER FILLED EPOXY FILM ADH GRAY	AAC	.88	.01	18H	74	AIR FILM ADHESIVE
ABLEFILM 501T GLASS SUPPORT/MODIFIED EPOXY FILM ADH	AAC	.37	.00	10H	125	AIR FILM ADHESIVE
ABLEFILM 504 CLOTH SUPPORT/EPOXY FILM ADH - WHITE	AAC	.52	.00	45M	149	AIR FILM ADHESIVE
ABLEFILM 507 GLASS CLOTH SUPPORT/EPOXY FILM ADH	AAC	.38	.00	1-2H	93	AIR FILM ADHESIVE
ABLEFILM 517 GLASS CLOTH SUPPORT/EPOXY FILM ADH	AAC	.07	.00	22H	16.3	AIR FILM ADHESIVE
ABLEFILM 517-LV CLOTH SUPPORT/EPOXY FILM ADH PINK	AAC	.83	.00	3H	74	AIR FILM ADHESIVE
ABLEFILM 518 CLOTH SUPPORT/EPOXY FILM ADH - GRAY	AAC	.93	.00	20H	93	AIR FILM ADHESIVE
ABLEFILM 550-K CLOTH SUPPORT/EPOXY FILM ADH - WHITE	AAC	.31	.04	2H	16.5	AIR FILM ADHESIVE
ABLESTIK 249-2 PVC LIQUID TIANNE AS 100/179-2 EW POLYURETHANE	AAC	.44	.07	0H	12.5	AIR FILM ADHESIVE
ABLESTIK 257-1 A/E AS 100/179-2 EW POLYURETHANE	AAC	.42	.04	6H	74	AIR CONC QUAT-ADH
ABLESTIK 681-12YL EPOXY FILM ADHESIVE GREEN	AAC	.98	.04	16H	100	AIR FILM ADHESIVE
ABLESTIK 761-6 A/E AS 10/1 BW EPOXY AS 100/5/223 BW	API	.73	.05	1H	75	AIR COND ADHESIVE
ABLETHERM 8-2 A/E AS 10/1 BW EPOXY AS 100/5/223 BW	API	.36	.00	90H	150	AIR FILM ADHESIVE
AG-1/JARDENER 221 A/E AS 16/1 BW SILVER FILLED EPOXY	TPI	.37	.00	3H	93	AIR FILM ADHESIVE
ARALDITE AV100/HY100 AS 1/1 BW EPOXY	CIB	.78	.00	10H	99	AIR ADD Curing
ARALDITE AV138/HY138 AS 100/40 BW EPOXY	CIB	.97	.00	25	25	AIR ADD Curing
ARALDITE MY750/HY750 AS 20/46 BW EPOXY	CIB	.19	.00	30H	60	AIR ADD Curing
ARECO-BOND 556 A/E AS 1/1 BW SILVER FILLED EPOXY	API	.91	.04			AIR ADD Curing
ARECO-BOND 556 A/E AS 1/1 BW SILVER FILLED EPOXY	API	.73	.05	3H	66	AIR ADD Curing
ARMSTRONG A-112 A/B AS 3/2 BW BROWN EPOXY	APC	.87	.00	24H	125	AIR E-3
ARMSTRONG A-12 A/E AS 3/2 BW BROWN EPOXY	APC	.95	.00	24H	25	AIR ADHESIVE
ARMSTRONG A-241 A/F AS 7/3 BW EPOXY	APC	.73	.02	14D	54	AIR ADHESIVE
ARMSTRONG A-271 A/F AS 7/3 BW EPOXY	APC	.49	.02	10H	25	AIR ADHESIVE
ARMSTRONG A-3/E AS 100/6 BW BLACK EPOXY	APC	.85	.01	1H	93	AIR ADHESIVE
ARMSTRONG A-31 A/E AS 6/3-6 BW EPOXY	APC	.55	.04	2H	22.5	AIR ADHESIVE
ARMSTRONG A-31 A/E AS 6/3-8 BW TAN EPOXY	APC	.74	.06	7D	22.5	AIR ADHESIVE
ARMSTRONG A-31 A/E AS 6/4 BW EPOXY	APC	.51	.01	7D	22	AIR ADHESIVE
ARMSTRONG A-31 A/E AS 6/4 BW TAN EPOXY	APC	.44	.01	7D	22	AIR ADHESIVE
ARMSTRONG C-7/ACT 1 AS 1/1 BW EPOXY	APC	.35	.02	21D	25	AIR ADHESIVE

SECTION 1 — ADHESIVES

MATERIAL	MR&F CODE	#TEL	ACVCH	CURE TIME	CURE TEMP	ATMOS	FOR APPLICATION
ARMSTRONG C-7/ACT AS 2/3 BW EPOXY	APC	.81	.09	7D	25	AIR	ADHESIVE
ARMSTRONG C-7/h-20 AS 3/1 BW CLEAR EPOXY	APC	.79	.05	24H	AIR	ADHESIVE	ADHESIVE
ARMSTRONG C-7/HY-951 AS 100/12 BW EPOXY	CIB	.61	.05	3H	92.1	PSI	ADHESIVE
AS-105 HY-951 EPOXY HONEYCOMB ADH	CIB	.36	.03	1H	12.1	AIR	FLUID
AS-601 EPOXY HONEYCOMB ADH	HYS	.98	.03	1H	20.4	AIR	ADHESIVE
BONDMASTER E645 A/B AS 10/3 BW EPOXY	NSC	.50	.04	1H	10.0	AIR	ADHESIVE
BONDMASTER E645 A/B AS 10/3 BW EPOXY	NSC	.50	.04	4H	18.0	E-2	ADHESIVE
BONDMASTER 620	NSC	.74	.02	2H	8.0	AIR	ADHESIVE
BR 34 EPOXY ADHESIVE	ACC	.65	.00	30M	2.0	AIR	ADHESIVE
BR 34 EPOXY ADHESIVE	ACC	.34	.00	30M	1.7	AIR	ADHESIVE
BT-610 EPOXY/TETRAHYDROFURANE/F	WTB	.99	.02	90M	1.32	AIR	ADHESIVE
BSL 308 BLACK EPOXY UNSUPPORTED ADHESIVE FILM	CIB	.70	.09	30M	15.0	AIR	ADHESIVE
BSL 312 GRAY EPOXY UNSUPPORTED ADHESIVE FILM	CIB	.62	.07	1H	17.0	AIR	ADHESIVE
C-68/CAT A AS 100/5 BW GRAY EPOXY/70% SANDWICH	HYS	.12	.07	30M	12.0	AIR	ADHESIVE
CASTAL F/A/B AS 10/1 BW GRAY EPOXY	CAS	.51	.03	20H	8.5	AIR	ADHESIVE
CASTAL F/A/B AS 10/1 BW BLUE HI-STRENGTH EPOXY	CAS	.28	.03	4H	12.5	AIR	ADHESIVE
CHEMLUX 205 ADHESIVE PRIMER GREY	HCC	.34	.03	30M	2.5	AIR	PRIMER
CHEMLOCK 220 ADHESIVE BLACK	HCC	.39	.00	10M	1.94	AIR	ADHESIVE
CHO-BOND 1224 CONDUCTIVE SILICONE EPOXY ADHESIVE	CHO	.02	.02	9H	28.8	AIR	ADHESIVE
CHO-BOND 360-208 CONDUCTIVE EPOXY ADHESIVE	CHO	.66	.06	2H	15.0	AIR	ADHESIVE
CL-522 EPOXY LAMINATING FILM	CHO	.31	.09	2H	17.0	AIR	ADHESIVE
CO-JAP K-20 A/B AS 20/9 BW GRAY EPOXY	CJA	.75	.05	2H	12.0	AIR	ADHESIVE
CONATHANE DP 976.1 A/E AS 100/46 BW POLYURETHANE	CON	.93	.01	30M	8.5	AIR	ADHESIVE
CONATHANE EN 21/E/P/E 76.1 D/P 9802 BW POLYURETHANE BLEND	CON	.92	.01	14D	10.0	AIR	ADHESIVE
CONATHANE EN 21/A/E AS 100/16 BW POLYURETHANE	CON	.94	.03	30D	2.5	AIR	ADHESIVE
CONATHANE EN-21/LP 576.1 D/P 9802 BW POLYURETHANE BLEND	CON	.72	.02	30D	2.5	AIR	ADHESIVE
CONATHANE EN-24/A/E AS 100/82 BW POLYURETHANE	CON	.57	.04	7D	2.5	AIR	ADHESIVE
CONATHANE EN-24/A/E AS 100/82 BW POLYURETHANE	CON	.72	.02	24H	6.0	AIR	ADHESIVE
CONTRONICS 960/ACT AS 4/1 BW FAST SET CERAMIC	COT	.79	.01	24H	10.0	AIR	ADHESIVE
CREST 3435/7111 AS 1/1 BW EPOXY	CPC	.47	.01	2H	2.5	AIR	COND ADHESIVE
CREST 3435/7111 AS 1/1 BW SILVER FILLED EPOXY	AMC	.39	.00	24H	6.5	AIR	COND ADHESIVE
CY 209/HT972 CLEAR LUMBER EPOXY	CIB	.78	.01	40H	19.0	AIR	ADHESIVE
DC 6-1104 LOT 22134-142	DCC	.20	.03	5D	2.5	AIR	ADHESIVE-COATING
DC 6-1104 LOT F010380	DCC	.19	.05	7D	2.5	AIR	ADHESIVE
DC 6-1104 LOT F0109320	DCC	.21	.05	7D	2.5	AIR	ADHESIVE
DC 6-1104 LOT F0109329	DCC	.13	.03	14D	2.5	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT E2467-133 6/76	DCC	.39	.03	7D	2.5	AIR	ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT F020392	DCC	.10	.02	7D	2.5	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MPN CODE	XTEL	XCVH	CURE TIME	CURE TEMP	CURE STATUS	APPLICATION
DC 93-500 A/B AS 10/1 BW SILICONE LOT FM0476116/77	DCC DCC DCC DCC DCC	.19 .13 .10 .09 .09	.04 .02 .01 .00 .00	7D 7D 7D 7D 48H	25 25 25 25 40H	AIR AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT FM119335K2	DCC DCC DCC DCC	.13 .10 .09 .09	.02 .01 .00 .00	7D 7D 7D 7D	25 25 25 25	AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE
DC 93-500 A/B AS 10/1 BW SILICONE LOT FM129335K8	DCC DCC DCC DCC	.10 .09 .09 .09	.02 .01 .00 .00	7D 7D 7D 7D	25 25 25 25	AIR AIR AIR AIR	ADHESIVE ADHESIVE ADHESIVE ADHESIVE
DC 93-500 A/B AS 20/1 BW SILICONE	DCC	.09	.00	48H	40H	AIR	ADHESIVE
DELTA LOND 152-U-B4 A/B AS 100/3.5 BW BLUE EPOXY	WAK	.49	.00	24H	25	AIR	ADHESIVE
DEN 438/HDA AS 100/27 BW EPOXY - AMBER	DOW	.60	.01	2H	60	AIR	ADHESIVE
DER 332/DADS/LITHAFRAZ AS 10/3/40 BW EPOXY - CREAM	DOW	.24	.00	4H	150	AIR	ADHESIVE
DER 332/TETA/LITAFRAZ AS 100/14/170 BW EPOXY - WHITE	DOW	.39	.00	1H	105	AIR	ADHESIVE
DER 332/TETA/LITAFRAZ/CAB-O-SIL AS 100/14/235/-67BW	DOW	.29	.01	1H	105	AIR	ADHESIVE
DER 332/VERSAMID 125 AS 1/1 BW EPOXY	DOW	.58	.01	12H	105	AIR	ADHESIVE
DER 332/VERSAMID 140 AS 6/7 BW EPOXY	DOW	.54	.01	12H	45H	AIR	ADHESIVE
DEVCON P-24 A/B AS 9/1 BW ALUMINUM FILLED EPOXY	DUP	.53	.00	1H	7D	AIR	ADHESIVE
DJ PONT 5504A SILVER FILLED EPOXY	DUP	.05	.00	1H	160	AIR	COND ADHESIVE
EA 8 A/B AS 100/6 EM BROWN EPOXY	HYS	.98	.02	20H	93	AIR	ADHESIVE
EA 901/B1 AS 100/1 BW EPOXY/MARCONI	HYS	.83	.02	20H	93	AIR	ADHESIVE
EA 9307 A/D AS 100/14 BW BROWN EPOXY	HIS	.48	.00	50H	116	AIR	ADHESIVE
EA 9321 GRAY EPOXY 100/33 BW GRAY EPOXY {EPON 934}	HYS	.94	.04	2H	82	AIR	ADHESIVE
EA 934 A/E AS 100/33 BW GRAY EPOXY {EPON 934}	HYS	.49	.01	90H	66	AIR	ADHESIVE
EA 934 NA/A/B AS 100/33 BW GRAY EPOXY {EPON 934}	HYS	.54	.01	7D	25	AIR	ADHESIVE
EA 9356 EPOXY	EAS	.69	.02	24H	44H	AIR	ADHESIVE
EASTMAN FA LTD 04010	EAS	.27	.05	24H	25	AIR	FILLED ADHESIVE
EASTYFOXY K-20 REPAIR KIT A/B AS EQUAL BEADS FOR TUBES CON	CON	.65	.04	24H	25	AIR	ADHESIVE
EASTYFOXY K-256 A/B AS EQUAL LENGTHS FROM TUBES WHITE CON	CON	.60	.02	24H	25	AIR	ADHESIVE
EASTYFOXY K-40 A/E AS EQUAL LENGTHS FROM TUBES GRAY CON	CON	1.00	.01	30H	17.5	AIR	ADHESIVE
EC 2290 EPOXY ADH	MM	.01	.01	30H	81.7	B-4	ADHESIVE
EC 3500 B/A AS 2/3 BW EPOXY ADHESIVE	MM	.19	.06	1H	7	B-4	ADHESIVE
EC 3500 EPOXY ADHESIVE 100/64 BW GRAY/GREEN EPOXY	EMC	.40	.00	60H	12.1	AIR	PSI ADHESIVE
EC COBOND 194 A/B AS 100/64 BW GRAY/GREEN EPOXY	EMC	.52	.08	6H	12.0	AIR	ADHESIVE
EC COBOND 276 /CAT 10/1 BW EPOXY	EMC	.49	.00	2H	80	AIR	ADHESIVE
ECCOBOND 281 ONE PART EPOXY - BLACK	EMC	.35	.06	2H	200	AIR	THICK COND ADH
ECCOBOND 285/1 BW EPOXY	EMC	.28	.01	8H	82	AIR	ADHESIVE
ECCOBOND 285/24LV AS 2/5/2 BW EPOXY	EMC	1.00	.00	24H	25	AIR	ADHESIVE
ECCOBOND 285/9 AS 25/1 BW EPOXY	EMC	.48	.00	24H	25	AIR	ADHESIVE
ECCOBOND 51/9 AS 100/7 BW EPOXY	EMC	.44	.00	24H	25	AIR	ADHESIVE
ECCOBOND 55/9 AS 50/6 BW EPOXY	EMC	.46	.00	24H	25	AIR	ADHESIVE
ECCOBOND 55/9 AS 50/6 BW EPOXY	EMC	.45	.00	30H	6.6	AIR	ADHESIVE
ECCOBOND 56C/9 AS 40/1 BW SOLDER	EMC	.23	.01	30H	2.5	AIR	ADHESIVE
ECCOBOND 57C A/B AS 1/1 BW COND EPOXY SILVER	EMC	.52	.04	1H	60	AIR	COND ADHESIVE
ECCOBOND 57C A/B AS 1/1 BW COND EPOXY SILVER	EMC	.36	.03	30H	15.0	AIR	COND ADHESIVE
ECCOBOND 83C-1 ONE COMPONENT SILVER FILLED	EMC	.64	.02	1H	6.6	AIR	COND ADHESIVE
ECCOBOND 83C-1 ONE COMPONENT SILVER FILLED	EMC	.35	.01	1H	14.9	AIR	COND ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	EFN CODE	KTM	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
ECCOMOLD L28/24LV AS 100/26.4 BW	EMC	.73	.05	24H	25	AIR	ADHESIVE
ECOSIL LN1049-97 A/B AS 10/1 BW CLEAR SILICONE	EMC	.18	.04	30H	100	AIR	ADHESIVE
ELASTOBOND 2015 A/B AS 100/65 BW SILVER FILLED EPOXY	EPF1	.44	.02	2H	b5	AIR	COND ADHESIVE
EPIBOND 1210/CAT 9615 AS 100/65 BW EPOXY	FPI	.65	.01	3H	96	AIR	ADHESIVE
EPIBOND 1210/CAT 9615 AS 100/65 BW EPOXY	FPI	.77	.03	7D	25	AIR	ADHESIVE
EPIBOND 123/CAT 9615 AS 100/65 BW EPOXY	FPI	.85	.03	7D	25	AIR	ADHESIVE
EPIBOND 8550/A/B AS 10/3 BW	FPI	.05	.03	5D	25	AIR	ADHESIVE
EPICLIPEN 825A/ACD 1/FILLER/CONVERTER - EPOXY	BCN	.83	.01	8H	25	AIR	ADHESIVE
EPOT-TEK H21D A/B AS 10/1 BW SILVER FILLED EPOXY	EPK	.19	.03	30H	100	AIR	COND ADHESIVE
EPOT-TEK H22 A/B AS 20/6.4 BW SILVER FILLED EPOXY	EPK	1.00	.01	24H	500	AIR	ADHESIVE
EPOT-TEK H22 A/B AS 20/6.4 BW SILVER FILLED EPOXY	EPK	.99	.01	24H	500	AIR	ADHESIVE
EPOT-TEK H27D A/B AS 10/1 BW SILVER FILLED EPOXY	EPK	.52	.09	1H	150	AIR	COND ADHESIVE
EPOT-TEK H31 SILVER FILLED EPOXY	EPK	.59	.05	1H	150	AIR	COND ADHESIVE
EPOT-TEK H31DLV SILVER FILLED EPOXY S-SINGLE COMPONENT	EPK	.47	.02	1H	125	AIR	COND ADHESIVE
EPOT-TEK H40 GOLD FILLED EPOXY S-SINGLE COMPONENT	EPK	.19	.00	1H	120	AIR	COND ADHESIVE
EPOT-TEK H41 GOLD FILLED EPOXY	EPK	.14	.00	1H	150	AIR	COND ADHESIVE
EPOT-TEK H43 GOLD FILLED EPOXY	EPK	.20	.00	1H	150	AIR	COND ADHESIVE
EPOT-TEK H44 GOLD FILLED EPOXY	EPK	.27	.00	1H	150	AIR	COND ADHESIVE
EPOT-TEK H70E A/E AS 1/1 LN THERM COND EPOXY	EPK	.99	.03	1H	150	AIR	ADHESIVE
EPOT-TEK H72 A/B AS 10/-4 BW DIELECTRIC EPOXY PASTE	EPK	.31	.00	30D	100	AIR	ADHESIVE
EPOT-TEK H74 A/B AS 10/-3 BW THERM COND EPOXY BROWN	EPK	.56	.00	1H	150	AIR	ADHESIVE
EPOT-TEK H77 A/B AS 20/3 BW BROWN EPOXY	EPK	.22	.00	1H	125	AIR	ADHESIVE
EPOT-TEK H80 SILVER FILLED EPOXY	EPK	.16	.01	24H	50	AIR	COND ADHESIVE
EPOT-TEK H81 A/B AS 1/1 BW PLATINUM FILLED EPOXY	EPK	.62	.00	16H	60	AIR	COND ADHESIVE
EPOT-TEK H81 A/B AS 10/1 BW GOLD FILLED EPOXY	EPK	.06	.01	12H	95	E-O	COND ADHESIVE
EPOT-TEK 390 POLYIMIDE/P	EPK	.20	.01	24H	50	AIR	COND ADHESIVE
EPOT-TEK 920 EPOXY ADHESIVE	EPK	.43	.01	30H	250	AIR	ADHESIVE
EPOT-TEK 930 A/B AS 100/3.3 BW FILLED EPOXY	EPK	.65	.01	18H	200	AIR	ADHESIVE
EPON X-24 EPOXY	SHL	.49	.00	45H	80	AIR	ADHESIVE
EPON X-24 EPOXY	SHL	.42	.05	15H	60	AIR	PSI
EPON 815/DEH-20/VERSAMID 150 AS 100/12/12 BW EPOXY	SHL	.81	.03	10H	25	AIR	ADHESIVE
EPON 815//DETA 732/VS SILVER POWR/AEP	SHL	.56	.04	24H	66	AIR	ADHESIVE
EPON 815//DETA AS 10/1 VS SILVER CURE 4	SHL	.56	.07	48H	673	AIR	ADHESIVE
EPON 815//V140 AS 3/1-8 BW EPOXY	GSC	.51	.02	7D	25	AIR	COND ADHESIVE
EPON 815//V140//AL2C3//PIGMENT MODIFIED BLACK EPOXY	GSC	.60	.06	3D	25	AIR	ADHESIVE
EPON 820/TETA AS 10/1 BW CURE 1	SHL	.43	.05	16H	63	AIR	ADHESIVE
EPON 820/TETA AS 1C/1 BW CURE 8	SHL	.36	.04	48H	25	AIR	ADHESIVE
EPON 826/NMA/UDMA AS 100/88.5/1.5 BW EPOXY	SHL	.41	.00	24H	293	AIR	ADHESIVE
EPON 827/VERSABID 140 AS 1/1 BW EPOXY	SHL	.96	.01	3H	177	AIR	ADHESIVE
EPON 828-ALUMINA/V-125/METHYL ENDIAME/ALUMINA	SHL	.75	.01	3H	60	AIR	ADHESIVE
EPON 828/DETA AS 10/1 BW EPOXY	SHL	.29	.04	3D	25	AIR	ADHESIVE
EPON 828/DETA AS 10/5/1 BW EPOXY	SHAC	.29	.00	15d	65	AIR	ADHESIVE
EPON 828/TETA AS 1C/1 BW CURE 1	SHL	.50	.01	15d	25	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	MRN CODE	XMTL	%CVCN	CURE TIME	CURE TEMP	ATMOS	APPLICATION
EPON 828/TETA AS 10/1 BW CURE 8	SHL	.38	.00	16H	63	AIR	ADHESIVE
EPON 828/V 140/AL2C3/PIGMENT MODIFIED BLACK EPOXY	GSC	.46	.02	2D	25	AIR	COND ADHESIVE
EPON 828/VERSAMID 125 AS 100/75 BW EPOXY	SHL	.69	.03	2D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	SHL	.58	.04	2D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/DTA AS 50/30 BW EPOXY	GSC	.18	.05	2D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 5/20 BW	SHL	.81	.03	12H	50	AIR	COLD ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 5/2/40 BW	SHL	.50	.04	24H	12.5	AIR	COND ADHESIVE
EPON 828/VERSAMID 140/SILFLAKE 135 AS 70/30/1 BW EPOXY	GSC	.35	.01	2D	25	AIR	ADHESIVE
EPON 828/VERSAMID 140/T-6 AS 2/3/16 BW AOD EPOXY	GSC	.88	.05	2D	25	AIR	ADHESIVE
EPON 828/VERSAMID 15/T-6/CAB-O-SIL/RED DISPERSION	GSC	.93	.02	2D	25	AIR	ADHESIVE
EPON 8280/VERSAMID AS 50/50 BW EPOXY	SHL	.95	.02	2D	25	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	SHL	.28	.01	2D	25	AIR	ADHESIVE
EPON 934 A/B AS 100/33 BW EPOXY	SHL	.19	.01	2D	25	AIR	ADHESIVE
EPON 956 A/B AS 100/58 BW CARBOLIC/CABOSIL	SHL	.81	.00	2D	25	AIR	ADHESIVE
EPOXI-PATCH KIT 1C WHITE PARTS FROM TUBES	HYS	.81	.02	24H	25	AIR	ADHESIVE
EPOXY 220 A/B AS 100/58 BW EPOXY ADH JOT L 101	HUE	.99	.03	16H	25	AIR	ADHESIVE
EPY 150 PRE PACK EPOXY ONE PART EPOXY	HUE	.50	.10	45H	15.0	AIR	ADHESIVE
EUREPOX 710/VERSAMID 140 AS 2/1 BW EPOXY	SAG	.33	.00	2D	25	AIR	ADHESIVE
EX 8762 EPOXY DIELECTRIC ADHESIVE	DUP	.08	.00	1H	16.0	AIR	ADHESIVE
FIBERITE F-3938 EPOXY	FIB	.44	.01	24H	24.9	AIR	ADHESIVE
FM 123-2LVC EPOXY ADH FILM PURPLE	ACC	.68	.01	1H	16.0	AIR	ADHESIVE
FM 123-2LVC EPOXY ADH FILM PURPLE/F MODIFIED AS NB149D-6/8C EPOXY PURPLE	ACC	.94	.00	90H	12.1	AIR	ADHESIVE
FM 123-5 EPOXY ADH FILM BLUE GREEN	ACC	.81	.00	1H	12.4	PSI	ADH FILM
FM 150-1 SUPPORTED EPOXY ALUM FILM HONEYCOMB ADH	ACC	.98	.02	1H	12.1	PSI	ADH FILM
FM 150-2 SUPPORTED EPOXY FILM EP 15 HONEYCOMB ADH	ACC	.49	.06	1H	17.7	AIR	ADH FILM
FM 150-2U UNSUPPORTED EPOXY FILM ADHESIVE	ACC	.87	.06	1H	17.7	AIR	ADH FILM
FM 36 FILM ADHESIVE POLYIMIDE/GLASS	ACC	.82	.02	24H	17.7	AIR	ADH FILM
FM 37 EPOXY FOAM A/H OLIVE GREEN	ACC	.73	.04	10H	28.8	PSI	ADH FOAM
FM 40 EPOXY FOAM A/B AS 1/1 BW SILVER FILLED EPOXY	ACC	1.00	.05	14H	17.0	PSI	ADH FOAM
FSP49 A/B AS 1/1 BW SILVER FILLED EPOXY	JHM	.52	.01	24H	25	AIR	COND ADHESIVE
GELVA MP SOL RA 263/ACRYLIC PRES SENS ADH	MON	.79	.01	2D	6.6	AIR	ADHESIVE
GELVA MP SOL RA 263/ACRYLIC PRES SENS ADH	MON	.62	.03	24H	2.3	AIR	ADHESIVE
GELVA MP SOL RA 784/ACRYLIC PRES SENS ADH	MON	1.00	.05	24H	6.6	AIR	ADHESIVE
GENEPOXY 185/VERSALID 115 AS 1/1 BW EPOXY	GMC	.35	.00	16H	6.6	AIR	ADHESIVE
G3 306-4 EPOXY FILM ADHESIVE	ACC	.89	.01	12H	6.6	AIR	FIELD ADHESIVE
HT 432 EPOXY-PHENOLIC FILM ADHESIVE	ACC	.72	.02	10H	17.4	PSI	FIELD ADHESIVE
HK-1000 LAMINATING FILM	MMA	.10	.00	15H	17.4	PSI	ADH FILM
HYSOL 11C A/B AS 1/1 BW EPOXY	HYS	.63	.01	12H	2.5	AIR	ADHESIVE
HYSOL 2C A/B AS 1/1 BW BROWN EPOXY	HYS	.85	.00	24H	7.1	AIR	COND ADHESIVE
K-16 A/B AS 1/1 BW CONDUCTIVE EPOXY	HYS	.22	.01	48H	2.5	AIR	COND ADHESIVE
K3-4/28/H2-3475 AS 25/4 BW EPOXY	HYS	.32	.00	24H	2.5	AIR	COND ADHESIVE
LCA4/ACT BAS AS 100/4.5 BW EPOXY	ACC	.19	.00	16H	10.0	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

SECTION 1 -- ADHESIVES

MATERIAL	MR CODE	XTM	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
R-2567 0-.5% BN CAT CLEAR SILICONE LOT 300	HCG	.41	.02	7D	25	AIR	ADHESIVE
R-2567 0-.5% BN CAT CLEAR SILICONE LOT 300	HCG	.31	.02	7D	25	AIR	ADHESIVE
R-2568 0-.5% BN CAT RED SILICONE LOT 301	HCG	.38	.02	7D	25	AIR	ADHESIVE
R-2568 0-.5% BN CAT RED SILICONE LOT 301 (KERUN 12688)	HCG	.12	.03	7D	25	AIR	ADHESIVE
RELIABOND 7115 CLOTH SUPPORT EPOXY FILM	RMC	.96	.06	24H	125	PSL	FILM ADHESIVE
RESDEL 01-022-01 CLEA 6005/BESDEL 41 AS 5/1 BL EPOXY RESIN 30-1215 PRESSURE SENSITIVE ACRYLIC ADHESIVE	RES	.67	.03	1H	160	AIR	ADHESIVE
RESDEL 01-022-01 CLEA 6005/BESDEL 41 AS 5/1 BL EPOXY RESIN 30-1215 PRESSURE SENSITIVE ACRYLIC ADHESIVE	NSC	.82	.03	1H	160	AIR	ADHESIVE
RHOPLEX N-619 PRES SENS ACRYLIC ADH/FOLI SANDWICH	ROH	.63	.04	2H	65	AIR	ADHESIVE
RTV 142 ONE COMPONENT WHITE SILICONE	GBC	.51	.00	30M	25	AIR	ADH-SEALANT
RTV 142 ONE COMPONENT WHITE SILICONE	GBC	.21	.01	1H	25	AIR	ADHESIVE
RTV 142 ONE COMPONENT WHITE SILICONE LOT JM 107	GBC	.24	.00	6D	25	AIR	ADHESIVE
RTV 560/T-12 AS 0.1% T-12	GBC	.22	.00	7D	25	AIR	ADHESIVE
RTV 560/T-12 AS 0.1% T-12	GBC	.08	.04	150D	25	AIR	ADHESIVE
RTV 560/T-12 AS 1/90-0.5% BN SILICONE	GBC	.45	.08	24H	125	E-O	ADHESIVE
RTV 566 0-.075% BN CAT SILICONE	GBC	.12	.00	1D	25	AIR	ADHESIVE
RTV 566 0-.085% BN CAT SILICONE	GBC	.11	.01	1D	25	AIR	ADHESIVE
RTV 566 0-.09% BN CAT SILICONE	GBC	.10	.01	1D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE	GBC	.10	.02	1D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE LOT BH164/AH102	GBC	.10	.02	1D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE LOT JB 133	GBC	.08	.00	300D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE LOT KA 136	GBC	.13	.00	7D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE LOT KA 137	GBC	.12	.00	4H	80	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE/DC 1200 PRIMER/SANDWICH	GBC	.13	.00	300D	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE/GE SS4155 PRIMER/SANDWICH	GBC	.34	.00	24H	25	AIR	ADHESIVE
RTV 566 0-.1% BN CAT SILICONE	GBC	.36	.00	24H	25	AIR	POTTING-ADH
RTV 566 0-.1% BN CAT SILICONE	GBC	.51	.00	24H	25	AIR	POTTING-ADH
RTV 568 0-.13% BN CAT SILICONE	GBC	.10	.00	1D	25	AIR	ADHESIVE
RTV 615 A/B AS 10/1 BN DEVOL LOT CB237 BATCH 3	GSC	.19	.00	4	25	AIR	ADHESIVE
RB-2038/H2-345 AS 4/1 BN CLEA EPOXY	HYS	.85	.00	24H	25	AIR	ADHESIVE
RB-2039/H2-356 AS 4/1 BN EPOXY	HYS	.93	.00	24H	60	AIR	ADHESIVE
SCOTCHWELD 1838 E/A AS 2/1 BN PHENYL GLYCIDYL ETH	SMW	.75	.00	24H	25	AIR	ADH-PUTTING
SCOTCHWELD 1838 E/A AS 1/1 BN EPOXY	SMW	.48	.00	40H	121	AIR	COUD ADHESIVE
SCOTCHWELD 2214 ED ALUM FILLED EPOXY	SMW	.45	.00	1H	121	AIR	COUD ADHESIVE
SCOTCHWELD 2214 HIGH TEMP ALUM FILLED EPOXY	SMW	.77	.00	24H	121	AIR	ADHESIVE
SCOTCHWELD 2214 M-UNFILLED EPOXY	SMW	.76	.03	16H	121	AIR	ADHESIVE
SCOTCHWELD 2216 BN/4% M-5 CAB-O-SIL	SMW	.0	.03	24H	100	AIR	ADHESIVE
SCOTCHWELD 2216 SANDWICCHED BETWEEN ALUMINUM	SMW	.13	.02	48	25	AIR	ADHESIVE
SOLITANE 113/3000/100/514 S-BN FORMULA 10	IIC	.36	.02	7D	25	AIR	STAINING CEND
STAKING CPND BLUE SOLITANE 113/300 BASE	IDB	.43	.06	7D	25	AIR	ADHESIVE
STYCAST 1263/3 AS 100/3 BN EPOXY	EMC	.33	.04	16H	107	AIR	ADHESIVE
STYCAST 12651/CAT 11 AS 100/8 BN BLACK EPOXY	EMC	.63	.01	3H	190	AIR	ADHESIVE
STYCAST 2651/CAT 11 AS 100/8 BN BLACK EPOXY	EMC	.84	.03	18D	25	AIR	ADHESIVE
STYCAST 2651/CAT 9 AS 100/6.5 BN BLACK EPOXY	EMC	.38	.00	7D	85	AIR	ADHESIVE
STYCAST 2850 FP/1 AS 100/4.5 BN EPOXY	EMC	.38	.01	12H	85	AIR	ADHESIVE

SECTION 1 -- ADHESIVES

MATERIAL	NBR CODE	XTHL	XCVH	CURE TIME	CURE TEMP	ATHS	APPLICATION
STYCAST 28501/24IV AS 100/7 BW EPOXY	EMC	.39	.00	24H	25	AIR	ADHESIVE
STYCAST 28501/1 AS 10/0-.3 BW EPOXY	EMC	.33	.00	7D	60	AIR	ADHESIVE
STYCAST 28501/1 AS 10/0/2-.1 BW BLUE EPOXY	EMC	.52	.03	24H	74	AIR	ADHESIVE
SYLGARD 184 A/B AS 10/1 BW BLUE EPOXY	EMC	.52	.02	24H	25	AIR	ADHESIVE
SYLGARD 184 A/B AS 10/1 BW DEVEL LOT GB051274 BATCH 1	GSC	.19	.01	7D	25	AIR	ADHESIVE
TECKNIT 72-0002 SILVER FILLED SILICONE AS 1/1 BW	TEC	.02	.30	48H	121	E-5	COLD ADHESIVE
TECKNIT 72-08116 CCND EPOXY A/B AS 1/1 BW	TEC	.91	.02	30d	99	AIR	COLD ADHESIVE
TRA-BOND 2151 THREE COMPONENT EPOXY BIPAK KIT	TRA	.75	.02	16H	25	AIR	ADHESIVE
TRA-BOND 2248 THREE-COMPONENT HI-TEMP EPOXY BIPAK KIT	TRA	.72	.01	24H	65	AIR	ADHESIVE
UNISET C-4429-2 SILVER FILLED THIOTROPIC EPOXY	AMC	.19	.01	90d	9125	AIR	COLD ADHESIVE
UNISET C-843 SILVER FILLED EPOXY	AMC	.32	.00	30M	125	AIR	LOAD ADHESIVE
UNISET C-840 SILVER FILLED EPOXY ONE COMPONENT	AMC	.61	.00	1H	125	AIR	LOAD ADHESIVE
UNISET C-850 SILVER FILLED EPOXY	AMC	.14	.00	30M	120	AIR	COLD ADHESIVE
UNISET C-850-4 SILVER FILLED EPOXY ONE PART	AMC	.43	.01	1H	125	AIR	COLD ADHESIVE
UNISET C-850-6 ONE COMPONENT SILVER FILLED EPOXY	AMC	.60	.01	1H	125	AIR	COLD ADHESIVE
UNISET C-925-49 SILVER FILLED EPOXY	AMC	.36	.00	30M	125	AIR	COLD ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	AMC	.06	.00	10M	170	AIR	COLD ADHESIVE
UNISET C-940-1 SILVER FILLED POLYIMIDE	AMC	.02	.00	1H	170	AIR	COLD ADHESIVE
UNISET C-940-4 ONE COMPONENT SILVER FILLED POLYIMIDE	AMC	.08	.00	30M	270	AIR	COLD ADHESIVE
UNISET ME-845 THERMAL COND ADHESIVE OLIVE-GREEN	AMC	.30	.01	1H	170	AIR	THERMAL COND ADH
UNISET ME-945 ONE COMPONENT POLYIMIDE/F	AMC	.26	.02	1H	170	AIR	THERMAL COND ADH
UNISET 9092-60 ONE COMPONENT FILLED EPOXY	AMC	.48	.04	30M	270	AIR	THERMAL COND ADH
URALANE 5753 A/B/BAUHINA AS 1/5/3 BW	FPI	.73	.03	14H	38	AIR	ADHESIVE
X-3476 CNE COMPONENT GRAY EPOXY	MM	.28	.04	1H	125	AIR	ADHESIVE
X-29-G710/H2 3561 AS 100/26 BW EPOXY	HYS	.90	.02	24H	25	AIR	ADHESIVE
X1-2561 A/B AS 10/0-.2 BW CLEAR SILICONE COATING	DCC	.10	.00	PH	69	AIR	CONF-LOAT
X3-6022/CAT 6060 AS 10/1 BW SILICONE/PHIMER DC92-023	DCC	.35	.00	14D	25	AIR	ADHESIVE
X3-6092 (96-1125) CNE PART WHITE SILICONE	DCC	.17	.01	24H	25	E-2	ADHESIVE
I-663 THERLOPOXY AH ONE COMPONENT	STY	.40	.08	7D	25	AIR	ADHESIVE
				1H	177	AIR	

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	MRK CODE	#TML	%CVM	CURE TIME	CURE ATMOS	APPLICATION
ALPHA WIRE 5853 BLACK TEFLON INSULATION	AWC	.01	.00			
B 142-1 PHENOLIC CCIL VARNISH	WEC	.54	.04	8 H	AIR	WIRE INSUL
BC 1500T SUPPLIX-SILVER FLEX SLEEVING	BCI	.05	.02			VARNISH
BELDEN MAGNET WIRE 8032C POLYETHERMALEZE INS	BLD	.02	.02			INSUL
BELDEN SHL WIRE VALUES INCLUDE LT OF WIRE	BLD	.05	.02			WIRE COATING
BEN-HAR PYRO-SLEEVING ST COATED GLASS FIBER	BHM	.93	.02			WIRE COATING
BIN P/N E 5636-1-L-G20 WHITE SILICONE WIRE INSULATION	BIN	.05	.03			SLEEVING
BIN P/N F 5639-1-L-G22 BLACK PART	BIN	.03	.03			WIRE INSUL
BIN P/N F 5639-1-L-G22 ENTIRE CABLE	BIN	.04	.04			CABLE INSUL
BIN P/N F 5639-1-L-G22 OUTER JACKET	BIN	.11	.04			CABLE INSUL
BIN P/N F 5639-1-L-G22 WHITE MIDDLE CORE	BIN	.11	.04			CABLE INSUL
BIN P/N F 5639-1-L-G22 UNSHIELDED CABLE WHITE SILICONE INSUL	BIN	.20	.04			CABLE INSUL
CABLE COAXIAL HI TEMP OUTER INSUL HIGH QD QT INSUL	HIG	.35	.02			CABLE INSUL
CABLE RG-316/U CCCXTAN OUTER INSUL	WLG	.02	.02			CABLE INSUL
CABLE 2219X100 CCAYTAN OUTER INSUL	WLG	.03	.03			CABLE INSUL
CABLE 24799-408 KATOEN SHIELDED POLYIMIDE	GTD	.44	.01			CABLE INSUL
CABLE 261942-0 CRESJ COAX RED OUTER INSUL	WLG	.00	.00			CABLE INSUL
CHEMFLUOR TEFLON TUBE SHRINK TUBING	CHE	.70	.00			SHEATH TUBING
CHO-SHRINK TUBING SILVER COND IN/SUR HEAT GUN SHRINK	CHO	.24	.00			SHEATH TUBING
CICOIL SILICONE CABLE INSUL	CIC	.49	.02			CABLE INSUL
DJ-15-02 DALKO TAILOPOXIE INSULATION RED/BLK NPC	HYS	.06	.00			INSULATION
DURAD/TFE WIRE INSULATION RED/HAR	HAR	.02	.00			WIRE INSUL
EXPANDO SLEEVING HR RED HALAR	BHM	.29	.02			WIRE INSUL
EXPANDO SLEEVING HR WHITE HALAR	BHM	.27	.02			WIRE INSUL
EXPANDO SLEEVING PT BLACK POLYESTER	BHD	.19	.00			SLEEVING
EXPANDO SLEEVING PT WHITE POLYESTER	BHD	.21	.00			SLEEVING
PEP TEFLON 10KV WIRE INSULATION	WLG	.15	.00			WIRE INSUL
PIBERMAT 1 TYPE 2538 POLYESTER FILM/NO ADH	MM	.14	.02			TAPE
PIBERMAT 1 TYPE 2540 POLYESTER FILM/NO ADH	MM	.68	.00			INSULATION
PIBERMAT 1V	MM	.30	.07			SHEATH TUBING
PIT 350 KYNAR SHRINK TUBING NEUTRAL - HEAT GUN	AEW	.09	.09			WIRE INSUL
FLUOROCAREON LIKE INSULATION BLACK	HAR	.02	.00			CABLE INSUL
GORE-TEX MICROWAVE CABLE INNER INSULATION WHITE	WLG	.04	.00			CABLE INSUL
GORE-TEX MICROWAVE CABLE OUTER INSULATION PURPLE	WLG	.03	.00			CABLE INSUL
GORE-TEX PIPE INSUL 3 PLI	WLG	.35	.00			CABLE INSUL
ISONEL 200 MAGNET WIRE COATING BROWN 180C USE 12 MIL	REB	.18	.00			WIRE COATING
ISONEL 200 MAGNET WIRE COATING BROWN 180C USE 18 MIL	REB	.51	.00			WIRE COATING
KAPTON TA400-1/20 BEAND-REX	BRA	.52	.00			WIRE COATING
KAPTON -TEFLON REEP COATED TA473-1/24 BEAND-REX	BRA	.66	.00			WIRE COATING
KYNAR SHRINK TUBING 123053-8 HEAT GUN SHRINK	RCC	.37	.00			SHEATH TUBING
KYNAR SHRINKABLE SEALING SLEEVE BLUE W/WHITE INSERTS	RCC	.44	.00			SHEATH TUBING
KYNAR SOLDIER SLEEVE WITHOUT POLYETHYLENE RINGS	RCC	.97	.00			SHEATH TUBING
KYNAR WIRE INSULATION - RED	BIG	.29	.00			WIRE COATING
MAGNET WIRE COATING TEFILON/DURADE	PDC	.53	.08			WIRE COATING
MAGNET WIRE HEAVY ARMOR POLYIMIDE(COATING ONLY)	PDC	.89	.00			WIRE COATING
MICROTHIN TEFLON SLEEVING 20 GAUGE	SHA	.92	.00			SLEEVING
MULTIFILAR MAGNET WIRE ML-B-4-30-28-0-5 CALC %	MS	.98	.00			BAKELITE WIRE
PENNTEBE II S3-7164AX/C TEFLON TUBING	PPC	.01	.00			TUBING
RAYCHEM COAX 5026A-211-9 WHITE OUTER INSUL	RCC	.12	.00			WIRE INSUL

SECTION 2 --- CABLE INSULATION SHRINK TUBING

MATERIAL	MRN CODE	WTML.	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
RAYCHEM POLYALKENE WIRE INSULATION YELLOW TYPE 44	RCC	.75	.03				
RAYCHEM POLYALKENE WIRE KADIA 14	RCC	.34	.991				
RAYCHEM POLYALKENE WIRE 88B01 1 20-9 WHITE	RCC	.14	.001				
RAYCHEM POLYALKENE WIRE 88B01 1 20-9 GRAY	RCC	.46	.003				
RAYCHEM FCLYARLEN 1 J 020 17902	RCC	.71	.003				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 049 8297704 INNER	RCC	.18	.002				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 049 8297704 OUTER	RCC	.64	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 060 437905 INNER	RCC	.17	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 060 437905 OUTER	RCC	.66	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 110 2067911 INNER	RCC	.15	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 110 2067911 OUTER	RCC	.68	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 110 5187913 INNER	RCC	.22	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT J 110 5187913 OUTER	RCC	.67	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT P 040 127801	RCC	.65	.004				
RAYCHEM SPEC 4 4 WIRE INSUL LOT P 060 2278014	RCC	.29	.005				
RAYCHEM SPEC 4 4 WIRE INSUL WHITE LOT P 050 157909	RCC	.19	.005				
RAYCHEM SPEC 4 4/0411 SPACE GA WHITE LOT PJ 612127915	RCC	.77	.003				
RAYCHEM SPEC 4 4/0411 SP GR OUTER INS WHITE BENZOPHENONE	RCC	.26	.003				
RAYCHEM SPEC 4 4/0411-20X SP GR INS W/O BENZOPHENONE	RCC	.65	.003				
RAYCHEM SPEC 4 4/0414-24 WHITE WIRE INSUL	RCC	.13	.003				
RAYCHEM SPEC 4 4/0414-24 SP GR OUTER INS WHITE	RCC	.70	.003				
RAYCHEM SPEC 4 4/2431-22-0/1/9-9 CLEAR INSUL	RCC	.46	.004				
RAYCHEM SPEC 4 4/2431-22-0/1/9-9 COLO CODE INSUL	RCC	.15	.004				
RAYCHEM SPEC 5 5 BREAKDOWN ETTE WHITE WIRE SHEATH	RCC	.22	.003				
RAYCHEM SPEC 5 5A081-24-0/1/9-9 D 040 3282 Q2 BLUE/WHITE	RCC	.08	.003				
RAYCHEM SPEC 68 FC1 4 INSULATION	RCC	.80	.003				
RENTEK GLO-135 WHITE POLYOLEFIN SHRINK TUBING	DUP	.49	.003				
RJ 304/U CABLE INSUL PTFL OUTER COVERING ONLY	TIN	.91	.003				
RT 114/6 BLACK VITON SHRINK TUBING - HEAT GUN SHRINK	HCC	.37	.003				
SE 9025 SILICONE WIRE INSULATION RERUN GSFC 3744	GBC	.53	.002				
SPACE POLYOLEFIN TUBE 102 BLACK	RCC	.10	.003				
STW 0474 WHITE SILICONE WIRE INSUL	STC	.28	.003				
SURLYN A WIRE INSULATION IN SHEET FORM	DUP	.55	.003				
SURLYN A WIRE INSULATION IN SHEET FORM	AWC	.00	.003				
TEFLON INSUL 33181019 BRAND-KEY	BX	.00	.003				
TEFLON PFA WIRE SLEEVING TE-9704 SODIUM ETCHED	DUP	.99	.003				
TEFLON PFA 1335 BLACK POLYOLEFIN SHRINK TUBING	RIC	.58	.004				
TEKSILITE 4318L-1 HIGH VOLTAGE WIRE INSUL HOD TYPE	MSI	.01	.004				
TEKPIK GPO 1335 BLACK POLYOLEFIN SHRINK TUBING	DUP	.99	.004				
TEKSILITE 4318L-1 HIGH VOLTAGE WIRE INSUL HOD TYPE	MSI	.58	.004				
TERMATICS XT-24 TIE SLEEVING - NON SHRINKABLE	THI	.01	.004				
TERMATICS XT-20-1932 WHITE WIRE INSUL	THI	.00	.004				
TERMATICS XT-16-1929 BLACK WIRE INSUL	THI	.02	.008				
TERMAX TEFILON 16PEF6G FIBERGLASS WIRE INSULATION	INC	.07	.008				
TERMAX TEFILON 16PEF6G FIBERGLASS WIRE INSULATION TYPE E	INC	.02	.008				
TERMELEC G 2735 CCIL COATING	DAL	.87	.02	1H	149	AIR	
TERMOFIT KYNAR CLEAR	RCC	.14	.05	1H	204	AIR	
TERMOFIT K120 VITON - BLACK HEAT GUN SHRINK	RCC	.31	.05	5H	300	AIR	
TERMOFIT K120 VITON - WHITE HEAT GUN SHRINK	RCC	.24	.01				

SECTION 2 -- CABLE INSULATION SHRINK TUBING

MATERIAL	AFR CODE	%THL	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
THERMOFIL AT 850 KYNAR SHRINK TUBING NATURAL GUN SHRINK	RCC	.15	.05	14	300	Atm	Shrink Tubing
THERMOFIL RT 876 KYCOPHEN WHITE HEAT GUN SHRINK	RAY	.67	.10	10	125	Atm	Shrink Tubing
THEKMO FIT RT 876 PRE-SHRUNK	RAY	.43	.09				Schrink Tubing
THEKMO FIT TFE RT TEFLON PRE-SHRUNK	RAY	.00					Schrink Tubing
THEKMOFLEX HYGRACE 1200 FIBERGLASS SLEEVE	LFB	.06					Insul. sleeve
THEKMOFLEX HYGRACE 1200 FIBERGLASS COATING	LFB	.66					WIRE COATING
T4 MAGNET WIRE POLYURETHANE COATING	HWS	.66					Insulation
UNIGLASS S-1542 FIBERGLASS TAPE/VOLAN A FINISH/NO ADH	UNA	.03	.01				Insulation
VARGLAS S-1600 FIBERGLASS SLEEVE	VFA	.01					Insul. sleeve
VARGLAS SPBC A-307 GLASS/SILICONE WIRE INSUL TAN	VFX	.60	.07				Wire Insul.
VITCN TUBING C-6412-47	DOU	.13	.00				TUBING
WIRE INSULATION YELLOW/BROWN	LDL	.68					Wire Insul.
WIRE INSULATION GREEN FLUOROCARBON POLYIMIDE/TFE	LG	.24					Wire Insul.
WIRE INSULATION ORANGE MIL-W-22759/16-20	TCG	.07					Wire Insul.
WIRE INSULATION RED FLUOROCARBON POLYIMIDE/TFE	LG	.19					Wire Insul.
WIRE INSULATION WHITE FLUOROCARBON FU14080	LG	.03					Wire Insul.
WIRE INSULATION WHITE MIL-W-22759/18-20	ICO	.10	.01				Wire Insul.

SECTION 3 -- CONFORMAL COATING

MATERIAL	MFR CODE	RTML	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
BLUE COATING LI Q01057REVA FLEXIBLE MOD EPOXY	NCL	.41	.04	1H	125	AIR	COATING
CONATHANE CE 1155/CELLSOLVE ACETATE MULTICURE	CON	.81	.05	10M	25	AIR	COAT COAT
DC 3140	DCL	.16	.06	24H	69	AIR	COATING
DC 6-1104 UNFILLED W/LUMINESCEK 174	GSC	.30	.07	7D	25	AIR	LUM COAT
DC 6-1104 A/B MEK/41LENE 100% EPOXY	GCC	.28	.04	7D	25	AIR	COAT COAT
DER 331LC FILLED SILICONE AS 35/30 BW EPOXY COATING	DCC	.19	.01	7D	25	AIR	LUM COAT
DER 331LC/VERSAMID 140 AS 35/30 BW EPOXY COATING	DON	.91	.05	3H	71	AIR	LUM COAT
DK-4 DRI-KOTE EPOXY POWDER COATING	ADP	.37	.01	20M	204	AIR	COATING-COATING
DURAFILM 300 SERIES ENAMEL	ADF	.33	.01	20H	149	AIR	COATING
EA 934 A/E AS 100/33 BW GRAY EPOXY	DYS	.79	.1	20H	260	AIR	COATING
EPICOND 123/CAT 552 AS 20/3 BW EPOXY	FPI	.63	.03	24H	60	AIR	ADDITIVE
EPOT-TEK H73 A/B AS 10/0.3 BW EPOXY	EPK	.43	.01	20H	25	AIR	COATING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	SBL	.91	.01	30D	200	AIR	COATING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	SBL	.24	.00	30D	225	AIR	COATING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	SBL	.32	.00	24H	92	AIR	COATING
EPON 828/VERSAMID 140/102 K-960 AS 5/5/0.6 BW	GSC	.87	.00	7D	25	AIR	COATING
EPOTHERM 180 A/B AS 10/4.5 BW BLACK EPOXY	TMC	.13	.01	24H	175	AIR	COATING
F4 73/DACRON KNIT/ER 127 PRIMER ON FOIL	ACC	.78	.00	1H	120	AIR	COATING
FPC 461 FLUOROCARBON/VINYL COPOLYMER FILM	FPL	.38	.01	24H	60	AIR	COATING
FPC 461 FLUOROCARBON/VINYL COPOLYMER FILM	FPL	.24	.01	24H	25	AIR	COATING
I2-2 POLYURETHANE COATING	EMC	.59	.08	24H	50	AIR	CONF COAT
ISOLEX R-65 ACRYLIC COATING SYSTEM/F	BEE	.52	.02	48H	50	AIR	COATING
ISOMID POLYESTER/PCLYMIDE COATING	SCH	.44	.02	10H	145	AIR	CONF COAT
HD BIL 173 COATED VITALUMINIZED MAINTEN	KST	.85	.02	2H	400	AIR	THERMAL BLANKET
01 100 GLASS RESIN 40% IN ETHANOL/F	OIL	.25	.07	1H	175	AIR	CONF COAT
01 650 GLASS RESIN 40% IN ETHANOL/F	OIL	.15	.03	1H	175	AIR	CONF COAT
2-188 POLYURETHANE COATING CLEAR 50% RH CURE/F	HIS	.88	.03	16H	50	AIR	COATING
P-401/T AS 100/17 BW SILK SCREEN EPOXY GREEN	PCK	.72	.01	24H	30	E-2	COATING MASK
PD 147 LETV 511	GEV	.11	.00	10H	93	AIR	COATING
POLYURETHANE COATING 22H ONE COMPONENT/FOIL	ELS	.91	.01	48H	177	E-0	COATING
PR 1546L A/B AS 40/100 BW POLYURETHANE THIN FILM	PRC	.63	.06	12H	25	AIR	CONF COAT
PR 1546L A/B AS 40/100 BW POLYURETHANE THIN FILM	PRC	.78	.06	60H	82	AIR	LUM COAT
PR 1660L A/B AS 1/4 BW "NEK" POLYURETHANE GULD EPOXY COATING/F	PRC	.86	.07	84H	82	AIR	CONF COAT
PT 201 THERMOSETTING YELLOW GULD EPOXY COATING/F	PTI	.96	.07	16H	163	AIR	COATING

SECTION 3 -- CONFORMAL COATING

MATERIAL	MPK CODE	XTHL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
PYRE-MI RK 692 POLYIMIDE 15 MIN FLASH/COAT	DUP	.96	.00	15M	149	AIR	COATING
PYRE-MI RK 692 POLYIMIDE 15 MIN FLASH/COAT	DUP	.86	-.00	15H	204	AIR	COATING
R&S 9384 COATED VEA LUMINIZED KAPTON	KST	.73	-.00	24H	50	A-6	BLANKET
R&S 9384 COATED VEA LUMINIZED KAPTON	KST	.72	-.01	7D	25	AIR	BLANKET
R-1152 ONE COMPONENT SILICONE - CLEAR LOT 013-16 6	ACG	.15	-.01	7D	25	CONF COAT	THEADAL COAT
RCC-15D UV POLYMER RESISTOR COATING TYPE 200 FLAT BLACK/F	WRG	.48	-.03	15H	65	AIR	CONF COAT
RCC-15D UV POLYMER RESISTOR COATING TYPE 200 FLAT BLACK/F	TNC	.32	-.08	30H	125	AIR	CONF COAT
RTV 511/T-12 AS 0.5% T-12 BW SILICONE	GEC	.09	-.00	30H	200	AIR	COATING
RTV 615 A/B AS 10/1 BW DEVOL AT 125C	GSC	.19	-.07	16H	25	AIR	E-2
SCOTCHCAST 281/282 EPOXY FORMULATION	AMX	.17	-.05	7D	215	AIR	CONF COAT
SOLITHANE 113/B1C1 BOLEI FORMULA 25	TCC	.59	-.05	4H	2120	AIR	CONF COAT
SOLITHANE 113/300 AS 100/100 BW FORMULA 4	TCC	.30	-.03	7D	25	AIR	CONF COAT
SOLITHANE 113/300 AS 100/100 BW FORMULA 4	TCC	.32	-.03	7D	25	AIR	CONF COAT
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	.28	-.03	24H	75	AIR	CONF COAT
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	.37	-.04	5H	55	AIR	CONF COAT
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	.56	-.05	7D	23	AIR	CONF COAT
SOLITHANE 113/300/E HUMISEAL THINNER 1-1 BW FORMULA 21	TCC	.32	-.02	2H	93	AIR	CONF COAT
SOLITHANE 113/300/E H-METHYL MORPHOLINE FORMULA 23	TCC	.88	-.00	7D	25	AIR	CONF COAT
SOLITHANE 113/300/E QUADROL FORMULA 24	TCC	.29	-.00	7D	25	AIR	CONF COAT
SOLITHANE 113/300/E QUADROL FORMULA 26	TCC	.31	-.00	7D	25	AIR	CONF COAT
SOLITHANE 113/300/T-12/CALCAFLOUR RW/DB CASTOR OIL SLK	TCC	.37	-.02	3H	65	AIR	CONF COAT
SOLITHANE 113/300/T-12/SIL-FLAKE 135/HEANE	TCC	.62	-.00	7D	23	AIR	CONF COAT
SOLITHANE 113/300/TOLUENE AS 100/73 BW/73 BV	TCC	.53	-.03	24H	70	AIR	CONF COAT
SOLITHANE 113/300/TRIETHYLAMINE FORMULA 22	TCC	.43	-.03	7D	25	AIR	CONF COAT
SOLITHANE 113/300/TRIETHYLAMINE FORMULA 22	TCC	.79	-.04	24H	70	AIR	CONF COAT
SR 165/MICA IRON OXIDE/ALUM SILICATE COATING DEX	TCC	.60	-.03	7D	25	AIR	CONF COAT
STYCAST 2850K1/241V AS 25/1 BW BLUE EPOXY EPOXY	EMC	.39	-.00	12H	300	AIR	COATING
URALAN 5750 A/B AS 18/100 BW	GRS	.65	-.09	7D	25	AIR	THEADAL CONTROL
URALAN 5750 A/B AS 18/100 BW	FPI	.41	-.03	14H	25	AIR	CONF COAT
URALANE 5750 A/B AS 4/25 BW URETHANE	FPI	.83	-.03	1H	60	AIR	CONF COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	FPI	.45	-.01	3H	65	AIR	CONF COAT
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	FPI	.62	-.01	7D	25	AIR	CONF COAT
VORITE 63 POLYURETHANE COATING	BAK	.60	-.01	24H	60	AIR	CONF COAT
X1-2561 A/B AS 10/1 BW CLEAR SILICONE COATING	DCC	.19	-.05	24H	7D	AIR	CONF COAT
X1-2561 A/B AS 10/1 BW CLEAR SILICONE COATING	DCC	.06	-.03	1H	25	AIR	CONF COAT

SECTION 4 -- ELECTRICAL COMPONENTS

MATERIAL	MPN CODE	ITEM CODE	RCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
AIRBORN CONNECTOR WGE92PRTGY BLACK GLASS FILL/NYLON	ABI	71	-0.9				CONNECTOR
ALPHA LUX 400 POLY400-OXIDE OXIDE	WPC	0.8	-0.1				INSULATION
AMP CONNECTOR 645850-1 BLACK GLASS FILLED POLYESTER	AMP	-26	-0.7				CONNECTOR
AMP FEED THRU THERM BLOCKS 204307-6-70-39 EPOXY	AMP	-28	-0.5				FEED THRU
AMP FEED THRU THERM BLOCKS 204307-6-70-39 SILICONE	AMP	-29	-0.5				FEED THRU
AMP PHENOL CONNECTOR 118 BLACK PHENOLIC FILAMENTS	ABR	-56	-1.0				CONN INSUL
APPLETON CONNECTOR 118 BLACK PHENOLIC FILAMENTS	ABL	-24	-0.9				CONN INSUL
APPLETON CONNECTOR 118 BLACK PHENOLIC FILAMENTS	ABL	-24	-0.9				CONN INSUL
AUGAT CONNECTOR 14C05-64K FLUOROSILICONE INSERT	AUG	-19	-0.7				CONNECTOR
BENDIX CONNECTOR FCD 9-6500 RED POLYESTER	BEN	-19	-0.3				CONN INSUL
BENDIX CONNECTOR J1G094E 22-355 RED SILICONE	BEN	-16	-0.4				CONN INSUL
BENDIX CONNECTOR J1P024E 22-355 DARK BLUE POLYMER	BEN	-29	-0.5				CONN INSUL
BENDIX CONNECTOR J1P024E-24-35P PINK SILICONE	BEN	-17	-0.4				CONN INSUL
BENDIX CONNECTOR J1P024E-24-35P RED SILICONE	BEN	-0.9	-0.0				CONN INSUL
BENDIX CONNECTOR PI107H-4-19P GREEN GLASS INSERT	BEN	-23	-0.8				CONN SEAL
BENDIX CONNECTOR PI107H-4-19P RED SILICONE O RING	BEN	-19	-0.3				CONN INSUL
BENDIX CONNECTOR 9-3400 RED RUBBER INSERT MATERIAL	BEN	-17	-0.3				CONN INSUL
CANNON CONNECTOR 9-6500 RED RUBBER INSUL MATERIAL	CAN	-15	-0.3				CONN INSUL
CANNON CONNECTOR MIK POLYCARBONATE INSUL GREEN	CAN	-54	-0.1				CONN INSUL
CANNON CONNECTOR MS3476 BLACK PHENOLIC INSERT	CAN	-49	-0.1				CONN INSUL
CANNON CONNECTOR MS3479 PINK SILICONE INSERT	CAN	-57	-0.1				CONN INSUL
CANNON CONNECTOR PW6RGB372 PINK SILICONE ONLY	CAN	-14	-0.2				CONNECTOR
CANNON CONNECTOR PW6G24B31/SNC 16 BLACK PLASTIC	CAN	-61	-0.0				CONNECTOR
CANNON CONNECTOR PW6G24B31/SNC 16 RED SILICONE	CAN	-19	-0.0				CONNECTOR
CANNON CONNECTOR RED SILICONE C-16 M5FC 40H 39569	CAN	-0.8	-0.3				CONN INSUL
CANNON CONNECTOR SH 350-55 PINK SILICONE	CAN	-31	-0.6				CONN SEAL
CANNON FILTER PIN CONN DDJ-5/PNA-A106 BLUE SILICONE	ARC	-24	-0.0				SOLDER
CERTAINIUM WH 202 CONNECTOR	ARC	-0.0	-0.0				
CERTAINIUM 61 SOLDER - OXIDIZED SN/PB/15% CD	ARC	-0.0	-0.6				
COIL FORM - CLEAR EASE - WHITE	CMT	-52	-0.0				
CONNECTOR INSERT TAN RUBBER PER MIL C38999	CIN	-23	-0.4				CONNECTOR INSUL
CONNECTOR PLUG JE1S1P8 GRAY	WIN	-52	-0.1				CONNECTOR
CONNECTOR THERMO COUPLE BLUE COPPER/CON	TEL	-54	-0.1				TC CONNECTOR
D-8150 POLYAMIDE-IMIDE-ADH/COPPER	ROG	-15	-0.2				CONNECTOR
D-8970 EPOXY FILM/ADH/COPPER	ROG	-42	-0.0				CONNECTOR
DAP - MESA PLASTICS	HAC	-34	-0.0				CONNECTOR
DAP CONNECTOR A 1004202	ACK	-97	-0.4				CONNECTOR
DAP CONNECTOR 3-2-520 GLASS FILLED/FLAME RESISTANT	CAN	-44	-0.0				CONNECTOR
DAP INSERT/CANNON CONNECTOR DDM 20W7P	AMP	-44	-0.0				CONNECTOR
DAP SDG-F MILL M-14 AMP CONNECTOR	CAN	-44	-0.0				CONNECTOR
DAP/ELANE RETARDANT-GLASS FILLED CANNON CON FS-80	CAN	-95	-0.0				CONNECTOR
DEUTSCH CONNECTOR 481510F16-1451 BROWN SILICONE	DEU	-31	-1.0				CONNECTOR
DEUTSCH CONNECTOR 481511/46FF0151 BROWN SILICONE	DEU	-22	-0.6				CONNECTOR
DEUTSCH CONNECTOR 41-010350 RED SILICONE	DEU	-29	-0.5				CONNECTOR
DEUTSCH CONNECTOR 6825 REO4-4425 SILICONE INSERT	DEU	-22	-0.1				CONNECTOR
DEUTSCH CONNECTOR 7221 UR864-212P SILICONE INSERT	DEU	-22	-0.1				CONNECTOR
DEUTSCH CONNECTOR 7503 RTK00-14-44P SILICONE INSERT	DEU	-16	-0.5				CONNECTOR

SECTION 4 -- ELECTRICAL COMPONENTS

MATERIAL	MFR CODE	#ML	XCVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
DEUTSCH CONNECTOR 7544 E RE64-212P SILICONE INSERT	DEU	16	-02				CONNECTOR
DEUTSCH CTU SERIES TERMINAL BLOCK T11E 06-01 SILICONE INSERT	DEU	24	-03				TERMINAL BLOCK
DI-ALL 52-10-70 SHOTBLAST GLASS FIBER/DAP	ACM	19	-00	2H	138	AIR	TERMINAL BLOCK
ECOSORB CR-5 124 A/B AS 100/1 B6 SILICONE BASE	EMC	43	-00	2H	100	AIR	ADSORBANT
ECOSORB CM-124 X/Y AS 50/1 B6 EPOXY	EMC	70	-09	3H	80	AIR	ADSORBANT
ECOSORB GDS TRON FILLED SILICONE-YELLOW	EMC	29	-09	3H	25	AIR	ADSORBANT
ELECTROLUMINISCENT LAMP-GRIMES-YELLOW	EMC	11	-09	14D	25	AIR	ADSORBANT
EMA 7037 IRON	ARG	20	-08				LAMP
EMA 7065 IRON	SBI	41	-01				DIELECTRIC
EMA 8190 IRON	SBI	23	-01				DIELECTRIC
GASKET AMP M8 SMA CONNECTOR RED SILICONE	ARG	21	-03				DIELECTRIC
GORE-TEX TEMP GTS 810 FT FIBER RIBBON CABLE	MLG	14	-02				GASKET
GROMMET FR GOSHEN RUBBER SILICONE CPND S1817	GRC	01	-00				FLAME MIRRORING
HEATER LIN COLUMN KAIL COX SPEC 4500 ELASTOMER	COX	34	-09	24H	125	AIR	GRUBMET
HEATER LIN 269-20	LSI	16	-01	8H	295	AIR	HEAT TAPE
HEATING TAPE CLAYBURN LABS A-16-2 DC 282 SILICONE/P	CLY	92	-01	20H	155	AIR	HEAT TAPE
HEATING TAPE CLAYBURN LABS H-1D-2X DC 282 SILICONE	CLY	10	-01	48H	155	AIR	HEAT TAPE
INSULATOR OF 230-LAE POLYURETHANE COATING	AS	15	-01	48H	150	AIR	HEAT TAPE
INSULTEK 445 URETHANE DIELECTRIC	LER	44	-03	30H	155	AIR	HEAT TAPE
ITT CONNECTOR 7929 DBE-258 BLUE/GREEN MQD INSERT	ITI	38	-01	10D	163	AIR	HEAT TAPE
MICRODOT RED SILICONE INSERT	HIR	55	-01	10D	25	AIR	HEAT TAPE
MICRODOT 7500 EAS CHALE 10 BAD BORATE/MICA MIX	MEA	18	-09	5H	171	AIR	HEAT TAPE
MIL-C-20235 AS 70/30 CONNECTOR INSERT - CANNON	CAN	09	-00				INSULATION
PA 61 CERAMIC	ELR	91	-03				CONNECTOR
PLASTIC PART MOTOCCLA CMOS 14011 DTD 7729	MOT	90	-00				INSULATION
PLASTIC PART MOTOCCLA CMOS 14044 DTD 7731	MOT	25	-00				INSULATION
PLASTIC PART MOTOCCLA 74LS09 DTD 7732	MOT	01	-00				INSULATION
PLASTIC PART MOTOCCLA 74LS174 DTD 7733	MOT	29	-00				INSULATION
PLASTIC PART NATL SEMICONDUCTOR CMOS 4011 DTD 723	NSE	27	-00				INSULATION
PLASTIC PART NATL SEMICONDUCTOR CMOS 4011 DTD 727	NSE	24	-00				INSULATION
PLASTIC PART RCA CMOS 4011 DTD 723	RCA	26	-00				INSULATION
PLASTIC PART RCA CMOS 4944 DTD 701	RCA	27	-00				INSULATION
PLASTIC PART SIGNAMICS 74LS00 DTD 7733	SIG	26	-02				INSULATION
PLASTIC PART SIGNAMICS 74LS174 DTD 7723	SIG	38	-00				INSULATION
PLASTIC PART TEXAS INST 74LS00 DTD 7710	TII	24	-00				INSULATION
PLASTIC PART TEXAS INST 74LS174 DTD 7718	TII	25	-00				INSULATION
POLYGRAPHIC PART 142-01 COMPOSITE GLASS/SR 319 SILICONE	POL	06	-02				INSULATION
RV 401 TE 142-2 STRENE EPOXY/PIPERGLASS	BRX	19	-00				INSULATION
SCOUTCHEFLEX SOCKET CONNECTOR GLASS REINF POLYESTER	SPI	32	-00				COIL FORM
SJ 2X2-2-5 HEATER - RED SILICONE	MM	19	-04				CONNECTOR
SH 3/4X5 HEATER - RED SILICONE	EPH	08	-01				HEATER
SPYCAST HI K 500 DIELECTRIC	EMC	14	-04				HEATER
TEFLON PTFE CONDUCTOR RIBBON CABLE INSULATION	MLG	97	-00				INSULATOR
VIBRO-FLO E-8530-2 FLUIDIXED BED COATING	APC	57	-02				MISL INSUL
VIBRO-FLO E-301 EFFCY POWDER COATING	APC	87	-08	30d	204	AIR	PTFE COATING
					180	AIR	PADA COATING

SECTION 5 -- ELECTRICAL SHIELDS

MATERIAL	MFR CODE	XTHL	XCVH	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CHO-SEAL 1212 SILVER FILLED SILICONE 125 GRADE	CHO	.08	.02	15H	171	AIR	SHIELD
CHO-SEAL 1214 SILVER FILLED SILICONE	CHO	.26	.05	24H	177	AIR	GASKET
CHO-SEAL 1214 SILVER FILLED SILICONE	CHO	.04	.02	24H	177	AIR	GASKET
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	CHO	.06	.02	3H	177	AIR	SILICONE
CHO-SEAL 1215 SILVER FILLED SILICONE 125 GRADE	CHO	.46	.07	24H	177	AIR	SILICONE
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	CHO	.29	.01	3H	15H	AIR	SILICONE
CHO-SEAL 1217 SILVER FILLED FLUOROSILICONE 125 GRADE	CHO	.03	.00	3H	177	AIR	SILICONE
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	CHO	.34	.08	24H	177	AIR	SILICONE
CHO-SEAL 1220 SILVER FILLED SILICONE 200C GRADE	CHO	.05	.02	3H	177	AIR	SILICONE
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	CHO	.30	.00	24H	177	AIR	SILICONE
CHO-SEAL 1221 SILVER FILLED SILICONE AEROSPACE 200	CHO	.05	.00	3H	15H	AIR	SILICONE
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	CHO	.43	.06	24H	177	AIR	SILICONE
CHO-SEAL 1224 SILVER FILLED SILICONE AEROSPACE 200	CHO	.04	.02	3H	177	AIR	SILICONE
CHO-SHRINK TUBING SILVER COND INNEK SURFACE	CHO	.61	.06	24H	177	AIR	SILICONE TUBING
CHO-SIL 1401 SILVER FILLED SILICONE	CHO	.05	.02	24H	177	AIR	SHIELD
CONSIL G SILVER FILLED SILICONE	CHO	.96	.02	24H	177	AIR	SHIELD
CONSIL MEDIUM HARD SILVER FILLED SILICONE	TEC	.96	.02	24H	177	AIR	SHIELD
CONSIL MEDIUM HARD SILVER FILLED SILICONE	TEC	.22	.10	24H	177	AIR	SHIELD
CONSIL R SILVER FILLED SILICONE	TEC	.05	.10	24H	177	AIR	SHIELD
CUSTOM LOAD 4101-150 EPOXY	CUM	.20	.10	24H	177	AIR	RF ABSORBER
ECCOSHIELD PST-C-A ALUM FOIL/SILVER FILL ACRYLIC ADH	EMC	.11	.09	24H	177	AIR	TAPE
ECCOSHIELD SV-R SILVER FILLED SILICONE	EMC	.26	.09	24H	177	AIR	SILICONE
ECCOSHIELD SV-A SILVER FILLED SILICONE	EMC	.16	.09	24H	177	AIR	SILICONE
ECCOSHIELD SV-A SILVER FILLED SILICONE	EMC	.15	.06	24H	177	AIR	SILICONE
ECCOSORB FDS	EMC	.95	.02	6H	200	AIR	ADSORBANT
ECCOSORB MF 110 IBCN FILLED EPOXY	EMC	.51	.01	24H	177	AIR	ADSORBANT
ECCOSORB MF 112 IBCN FILLED EPOXY	EMC	.26	.01	24H	177	AIR	ADSORBANT
ECCOSORB MF 114 IBCN FILLED EPOXY	EMC	.22	.00	24H	177	AIR	ADSORBANT
ECCOSORB MF 124 IBCN FILLED EPOXY	EMC	.08	.00	24H	177	AIR	ADSORBANT
ECCOSORB SF 9-5 RESONANT ABSORBER-SILICONE FILLED	EMC	.10	.06	16H	177	AIR	ADSORBANT
ECCOSORB SET 2-5	EMC	.14	.06	16H	177	AIR	ADSORBANT
ECCOSORB SEU-9 POLYURETHANE	EMC	.46	.05	16H	177	AIR	ADSORBANT
ELASTOMET WIRE EMBEDDED SILICONE SHIELDING	TEE	.05	.03	36H	160	B-3	EMI SHIELDING
KAPTON FILM W/MOLACKYLIC ADH ONE SIDE	TEE	.65	.00	1H	190	AIR	Dielectric
METALASTIC SILICONE FILLED ALUM MESH	SHI	.03	.02	24H	177	AIR	SILICONE
PORCUPINE METALASTIC SILICONE FILLED MONEL MESH	SHI	.09	.05	24H	177	AIR	SHIELDING

SECTION 5 -- ELECTRICAL SHIELDS

MATERIAL	HFR CODE	%ML	%CVCM	CURE TIME	ATMOS TEMP	APPLICATION
SIC 9030/GREEN BINDER/C-240 GROUT	GSD	.24	.01			
SPICAST HIGH K FILLED EPOXY	EMC	.38	.00			DIELECTRIC
XECON CS-14 12% SILVER FILLED SILICONE	NET	.11	.05	17H	177	AIR COND GASKET

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	MFR CODE	XTHL	ACVCM	CURE TIME	ATMOS TEMP	APPLICATION
ACLEAR 22A CLEAR FILM POLYCHLOROTRIFLUOROETHYLENE	ACM	.13	.01	FILM		
ACLEAR 33C CLEAR FILM POLYCHLOROTRIFLUOROETHYLENE	ACC	.51	.05	FILM		
ACRYLITE ACRYLIC SHEET						SANUCIJKAL
ANTI STATIC FILM 2100						FILM
ANTI STATIC FILM 1661						DEAI BARRIER
AR NALON FILM 1640350 BLACK TFE ON GLASS FABRIC	DUP	.05	.01			DEAI BARRIER
AR NALON FILM 1640350 NEUTRAL TEFLON ON GLASS FABRIC	CRY	.05	.00			INSULATION
BAVICK LIQUID ETHYL ACETATE - CATIONIC POLYESTER MODIFIED	SIE	.03	.01	FILM		
CELLULOSE ACETATE - CATIONIC POLYESTER	PAB	.95	.03	FILM		
CHO-THERM 1661 THERM COND SHEET WHITE SILICONE	CHO	.76	.06	FILM		
CHO-THERM 1661 THERM COND SHEET WHITE SILICONE	CHO	.19	.06	FILM		
CHO-THERM 1663 THERM COND SHEET WHITE SILICONE	CHO	.26	.05	FILM		
CHO-THERM 1671 THERM COND SHEET WHITE SILICONE	CHO	.19	.05	FILM		
CHO-THERM 1671 THERM COND SHEET WHITE SILICONE	CHO	.10	.04	FILM		
CHO-THERM 1673 THERM COND SHEET GREEN SILICONE	CHO	.11	.04	FILM		
CHO-THERM 1674 THERM COND SHEET BLUE SILICONE	CHO	.12	.04	FILM		
CONDULON ANTI STATIC FILM 2 MIL BLACK	EVL	.57	.03	FILM		
CONDULON 89-7 ANTI STATIC FILM 4 MIL BLACK	EVL	.88	.03	FILM		
COVERLINE H FABRIC 55-6181-XX HYPALON COATED NYLON	EVE	.86	.02	FILM		
CRONAFLEX FILM - FROSTY	EEU	.98	.02	FILM		
CRONAR POLYESTER FILM TRANSPARENCY	DUP	.75	.02	FILM		
CYCCON MCG FIBER - NICKEL COATED GRAPHITE	ACC	.02	.01	FILM		
DACRON DAYBOND 3 OZ CARBOLICN	HOB	.45	.04	FILM		
DACRON MESH 22A PC POLYESTER NETTING	APE	.19	.00	FILM		
DACRON NETTING 70866-10	BEN	.19	.00	FILM		
DACRON POLYESTER CLOTH	SST	.12	.00	FILM		
DUN-CHOME 500C VEA TEFILON	DUN	.01	.00	FILM		
LA 7 POLYESTER FILAMENT INSULATOR - FROSTY	DAS	.46	.00	FILM		
ECTE EXTRUDED SHEET HI-TEP APPLICTION	ACA	.98	.01	FILM		
ECTE 0.5 MIL FILM	ACA	.98	.05	FILM		
ECTE 1.0 MIL FILM	ACA	.98	.04	FILM		
ECTE 10-8 3/4 YD FABRIC UNCALENDERED UNWASHED	ACA	.05	.00	FILM		
ECTE 10-8 3/4 YD FABRIC UNCALENDERED WASHED ETOH/ACE	ACA	.04	.00	FILM		
ECTE 10-8 3/4 YD FABRIC UNCALENDERED UNWASHED	ACA	.04	.00	FILM		
ECTE 7.3 0Z/YD FAERIC UNCALENDERED UNWASHED	ACA	.28	.03	FILM		
ECTE 7.3 0Z/YD FAERIC UNCALENDERED WASHED ETOH/ACE	ACA	.21	.07	FILM		
FAIREBENE VSO060 BLACK VITON A SHEET	DUP	.35	.05	FILM		
FAIREBENE VSO080 BLACK VITON A SHEET	STL	.22	.03	FILM		
FLUOROFILM DF-1200 TEFILON FILM-ACRYLIC ADH	DIL	.19	.01	FILM		
FLUOROFILM 389-7 BITA CLOTH/PVDF COATED	DIN	.03	.01	FILM		
G401500 SILVERED TEFILON FILM	GTS	.90	.00	FILM		
G4019 TAPE PVDF FILM/AG METALIZED/ACRYLIC ADH/R	GTS	.33	.00	FILM		
GENCOTHERM 010 UNPLASTICIZED PVC FILM CLEAR	AMH	.12	.00	FILM		
GENCOTHERM HT UNPLASTICIZED PVC FILM CLEAR	AMH	.23	.00	FILM		
GENCOTHERM NTLS UNPLASTICIZED PVC FILM CLEAR	AMH	.63	.05	FILM		
GENCOTHERM NTLS UNPLASTICIZED PVC FILM WHITE	AMH	.38	.05	FILM		
GENCOTHERM US 1002 UNPLASTICIZED PVC FILM CLEAR	AMH	.21	.02	FILM		
GENCOTHERM US 3003 UNPLASTICIZED PVC FILM CLEAR	AMH	.50	.03	FILM		
GLASS CLOTH TAPE 1/4	CLJ4 TAPE					

SECTION 6 -- FILMS SHEET MATERIALS

MATERIAL	NFR CODE	#ML	%CVCM	CURE TIME	CURE TEMP	ATENS	APPLICATION
GLASS CLOTH 1620 - SMALL WEAVE FABRIC 195/50/85% SQUARE MESH COATED WHITE	STE SITE	.13	.08				GLASS INSULATION
KAPTON FEP FILM 40CF022	DUP	.23	.05				FIELD INSULATION
KAPTON H FILM REINFORCED GLASS CLOTH 104	BCA	.25	.05	90M	302	AIR	FIELD INSULATION
KAPTON H FILM 5 MIL	DUP	.47	.05	24H	150	AIR	FIELD INSULATION
KAPTON H FILM 5 MIL	DUP	.77	.02	24H	150	AIR	FIELD INSULATION
KAPTON H FILM/LINOLEUM LEAVE BETA MARQUISSETTE GLASS CLOTH	DUP	.13	.01				FIELD INSULATION
KNIFOL 9034-112 POLYCARBONATE LENS	KCC	.16	.00				LENS
LEXAN 4186-73 STATIC DISSIPATIVE CURTAIN FILM - BLACK	GCV	.19	.01				BAGGING
MAXXON SOLAK FOIL BLACK FILM ON POLYCARBONATE LENS	PVLF	.68	.07				HEAT CARRIER
MAXXON SOLAK FOIL FLACK NICKEL W/CIRCUITRY	DIN	.05	.01				HEAT CONTROL
MYLAR LA 616 - 7 MIL FILM	EPD	.02	.00				FIELD ABSERT
MYLAR PHOTOSENSITIVE FILM TYPE A	SCG	.75	.04				FIELD SHEET
MYLAR GEN-2-801 HOT PRO	DUP	.59	.00				INSULATION
NORYL MODIFIED PVC	GEC	.93	.02				INSULATION
ORCOP FILM KN-10 KAPTON/NOREX THREAD/POLYESTER BINDER	ORC	.92	.02	48H	125	E-3	FIELD BLANKET
P-95 POLYETHER URETHANE FOAM WHITE H2O WASH	GTR	.91	.04	24H	100	AIR	FIELD FOAD
P-95 POLYETHER URETHANE FOAM WHITE ISOBUTANE WASH	GTR	.12	.02	24H	100	AIR	FIELD FOAD
P-95 POLYETHER URETHANE FOAM WHITE REACH WASH	GTR	.81	.02	24H	100	AIR	FIELD FOAD
PARAOL GT-76 LAMINATE NYLON/NYLAR/ALUM	GTR	.14	.05	24H	100	AIR	FIELD FOAD
PLEXIGLAS VS-100 OPTICAL	JSC	.72	.08				FIELD CONTROL
PLEXIGLAS 11 UVA	ROH	.09	.01				LENS
POLYCARBONATE CIECULT CARD GUIDE	BOH	.57	.00				FIELD GUIDE
POLYCHROME FILM 8 MIL	CAL	.12	.02				FIELD FILM
POLYETHYLENE FILM ANTISTATIC DF PINK	PCR	.64	.01				FIELD FILM
POLYETHYLENE FILM 2 MILS ALATHON RESIN-BRANCHED	SCE	.20	.06				FIELD FILM
POLYETHYLENE FILM ULTRA HIGH MOLECULAR WEIGHT	DUP	.14	.02				STRUCTURAL FILM
POLYETHYLENE VAPORLINE 6 MIL	PHI	.03	.00				STRUCTURAL FILM
POLYPEREO POLYSTYRENE	EXX	.37	.00				FIELD FILM
PYRALUX FILM POLYVINYLDIENE 2 MILS THICK	PPC	.09	.00				FIELD FILM
R-CAS-1200 ANTISTATIC POLYETHYLENE FILM	DUP	.34	.04				FIELD FILM
SAIL CLOTH ALUMINIZED	ACI	.43	.06				FIELD FILM CONTROL
SURLYN 3B 1000 FILM	ADL	.43	.05				FIELD FILM
SURLYN 1652 2 MIL EGGING FILM	DUP	.43	.09				FIELD FILM
TEDLAB COATING ON ALUMINUM	RPC	.39	.00				FIELD COATING
TEDLAB 150 MIL 30 CC BLACK FILM	DUP	.14	.05				FIELD FILM
TEFLON FEP INSULATION TA22-731	HTR	.02	.00				FIELD INSULATION
TEFLON FEP FILM 4 SHEET TE-9702	DUP	.01	.00				FIELD SHEET
TEFZEL FILM 2 MIL	DUP	.32	.02				FIELD BLANKET
TROYFILM S4-19-070-172 POLYESTER	TRO	.13	.04				FIELD BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE	TRO	.25	.08				FIELD BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE WASHED	TRO	.24	.03				FIELD BLANKET
TROYTUF 1-9-0-195 NON WOVEN DACRON FELT WHITE WASHED	TRO	.25	.04				FIELD BLANKET

SECTION 7 -- FOAMS

MATERIAL	REF. CODE	ATM.	ACVCM	CURE TIME	CURE TEMP	AIDS	APPLICATION
ABSORBIR METALLIC/GRAPHITE/FOAM	NAP	-85	-04	2H	93	AIR	FOAD COMPOSITE
ABLESTIK 861-1/ECCOSPHERES SI AS 55/45 BW - WHITE	NAC	-78	-00	2H	93	AIR	FOAD FOAM
ABLESTIK 861-2/ECCOSPHERES SI AS 55/45 BW - WHITE	NAC	-80	-01	2H	93	AIR	FOAD FOAM
ABSAFIL F1200V-20 FCAE/20% GLASS FIBERS	FBR	-33	-01	2H	177	AIR	FOAD ADH
AF3015/C125690-1 HARD FOAMED EPOXY	MME	-88	-03	24H	100	AIR	FOAD INSULATION
CLARK EJAH 1234 ECLYU-ETHANE - WHITE ALCOHOL WASH	GEP	-85	-03	8H	100	AIR	FOAD
CONATEX EA-50 POLYURETHANE FOAM ALCOHOL WASH	BLC	-85	-03	1H	120	AIR	FOAD
CPR 17-2C POLYURETHANE FOAM	UJC	-87	-10	9H	80	AIR	FOAD
CPR 17-2C POLYURETHANE FOAM	UJC	-97	-09	16H	75	AIR	FOAD
CPR 17-2C POLYURETHANE FOAM	DCC	-59	-03	24H	150	E-4	FOAD
DER 661/2-PHENYLINDAZOLE WHITE SYNTACTIC FOAM	HDI	-72	-03	24H	150	AIR	FOAD
ECCOBOND SF 40 SYNTACTIC FOAM EPOXY RESIN	EMC	-23	-04	48H	25	AIR	FOAD DAMPER
ECCOFoam EFF-14 SYNTACTIC FOAM - YELLOW EPOXY	EMC	-40	-39	24H	100	AIR	FOAD
EL 2795/HN 951 SYNTACTIC FOAM	HAC	-50	-02	24H	25	E-0	FOAD RAD
ETHAFOAM WHITE POLYETHYLENE FOAM 2.2#/CU FT	BPI	-47	-03	24H	25	AIR	INSULATION
ETHAFOAM 220 POLYETHYLENE FOAM 4#/CU FT	DOW	-36	-03	24H	25	AIR	INSULATION
ETHAFOAM 400 POLYETHYLENE FOAM 6#/CU FT	DOW	-26	-04	24H	25	AIR	INSULATION
ETHAFOAM 600 POLYETHYLENE FOAM 8#/CU FT	DOW	-24	-04	24H	25	AIR	INSULATION
FLUOROSILICONE CLOSED CELL EXTRUDED FOAM - BROWN	NOS	-38	-03	16H	204	AIR	FOAD
FV 41 EPOXY FOAM SILVER-GRAY	INA	-76	-03	1H	170	AIR	ADH FOAD
FOAM CLOSED CELL ECLYU-ETHANE MIL P20514 ETOH WASH	ACC	-84	-02	24H	100	AIR	FOAD LOUVER
FOAM HEP-1-10-94-1 FOLYXIMIDE	LPT	-49	-02	24H	100	AIR	TUSSU LOUVER
FOAM P-2-17-52-3 FOLYXIMIDE	INT	-53	-02	24H	100	AIR	FOAD
FR-1702-1 TAN THERMAL ACCUSTICAL HONEYCOMB FILM	INI	-89	-01	24H	120	AIR	FOAD
FR-3120 LAST-A-FCAM POLYURETHANE FOAM ISOPROP WASH	GPM	-29	-08	14	21H	AIR	FOAD
HO-NANTO 1835 POLYETHER-URETHANE FOAM METOH WASH	MON	-27	-04	30H	25	AIR	FOAD
HO-PUC G302 POLYETHER-URETHANE FOAM METOH WASH	MON	-30	-04	4H	100	AIR	FOAD DAMPER
P-17 POLYURETHANE FOAM 0-062 THICK WHITE	NOP	-39	-07	24H	100	AIR	FOAD DAMPER
P-25 POLYURETHANE FOAM OPEN CELL	GTR	-49	-08	16H	100	AIR	FOAD
P-25 POLYURETHANE FOAM OPEN CELL	GTR	-92	-04	24H	100	AIR	FOAD
PRO FOAM URETHANE FCAM 4701-01-20125-1633 ALCOHOL WASH	ROS	-73	-03	8H	100	AIR	FOAD
PROFF F6J/20 POLYEROPYLENE GLASS FIBER	FBR	-16	-04	24H	100	AIR	FOAD
REF 263 POLYURETHANE FOAM GRAY	RPC	-53	-05	48H	66	AIR	FOAD
SE OTT POLYESTER-URETHANE FOAM - TAN 2X24HR ETOH WASH	SCI	-81	-01	24H	100	AIR	FOAD
SE OTT POLYESTER-URETHANE FOAM 100 PP+ ETOH WASH	SCI	-88	-01	24H	100	AIR	FOAD
SE OTT POLYESTER-URETHANE FOAM 100 PP+ METOH WASH	SCI	-86	-05	24H	100	AIR	FOAD
SE OTT POLYESTER-URETHANE FOAM 60 PP+ METOH WASH	SCI	-99	-04	24H	100	AIR	FOAD
SKUR-LOK SLE 3010 SYNTACTIC FOAM BLUE-GREEN	SLK	-77	-03	16H	25	AIR	FOAD
SKYBOND RI 7221-06 RIGID POLYIMIDE FOAM	MON	-31	-04	8H	121	AIR	FOAD
SKYBOND RI 7221-12 RIGID POLYIMIDE FOAM	MON	-42	-01	24H	100	AIR	FOAD
SKYBOND RI 7221-16 RIGID POLYIMIDE FOAM	MON	-45	-01	24H	100	AIR	FOAD
SOLIDIIDE TA-301 FLEXIBLE POLYIMIDE FOAM MIL F87090	IMI	-28	-01	24H	100	AIR	FOAD
STEPANOFOAM G-306 6#/CU FT WHITE	SCC	-87	-06	24H	25	AIR	FOAD

SECTION 7 -- FOAMS

MATERIAL	MFR CODE	XTEL	%VCVM	CORE TIME	CUBE TEMP	STATUS	APPLICATION
SPYCAST 1095/11 AS 100/12 BW EPOXY FOAM	EMC	.36	.00	24H	125	Air	FOAM
STYRAFIL F30/20 POLYSTYRENE FOAM/20% GLASS FIBER	FBR	.26	.02				FOAM
SYNTACTIC FOAM WHITE EPOXY/ECCOSPHERES 40/60 BW	NOT	.54					FOAM
VITON 352.9/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM - GRAY	INR	.91	.01	16H	204	Air	FOAM
XN 352.9/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM PINK	AMC	.80	.00	2H	125	AIR	FOAM DAMPER
XN 352.9/ECCOSPHERES SI AS 1/2 BW SYNTACTIC FOAM PINK	AMC	.82	.01	2H	66	E-3	FOAM DAMPER
ZEREFIL F500/20 VINYL FOAM/20% GLASS FIBERS	AMC	.88	.02	8H	100	AIR	FOAM DAMPER
	FBR	.21	.00	2H	100	Air	FOAM DAMPER

SECTION 8 -- GREASES LUBRICANTS

MATERIAL	EFN CODE	STL	ACVN	CURE TIME	CURE TEMP	STATUS	APPLICATION
APIEZON H HYDROCARBON GREASE	BID	.25	.02				GREASE
APIEZON L GREASE	BID	.04	.01				GREASE
APIEZON N GREASE	BID	.08	.01				GREASE
BLACK MAGIC MOLY STRAY/FOIL - AEROSOL NO52	SPA	.27	.02	24H	25	A Ia	LUBRICANT
BLACK MAGIC CLEAR CIL	BUC	.03	.01				LUBRICANT
BRAYCOTE 8152 CLEAR CIL	BUC	.07	.03				LUBRICANT
BRAYCOTE 3L-38 GREASE WHITE	BOC	.07	.03				LUBRICANT
BRAYCOTE 3L-38-MS GREASE BATCH DLG1 GRAY	BOC	.04	.01	7H	100	E-o	GREASE
BRAYCOTE 3L-38-RP GREASE BATCH CLT7 YELLOW	BOC	.09	.04				GREASE
BRAYCOTE 3L-38-ZN GREASE BATCH ELM4 BLACK	BOC	.02	.01				LUBRICANT
CROWN 6065 GREEN TIE AEROSOL COATING/P	CIP	.52	.09	20M	177	A Ia	LUBRICANT
C6-1103 SILICONE GELASSE	DCC	.17	.00	24H	121	E-j	GREASE
E-COSLIP TM-24 LCW FRICTION EPOXY	ERC	.40	.03	1H	60	A Ia	EPoxy LUBE
				24d	116	A Ia	
EKKCEL W6-25 AROMATIC POLYESTER/TFE BLEND TAN	CRB	.95	.00				SOLID LUBE
FLUOROSINT 500 MICHA FILLED TFE	PPC	.77	.05				BEARING MATL
22-1067 OPTICAL COUPLING COMPOUND	DCC						GREASE
AP DUROID 4300 REINFORCED TEFLO	AOG	.01	.00				BEARING MATL
RULON A TEFLO FILLED BEARING MATERIAL	DIX	.00	.00				BEARING MATL
RULON B TEFLO FILLED BEARING MATERIAL	DIX	.00	.00				BEARING MATL
RULON C TEFLO FILLED BEARING MATERIAL	DIX	.00	.00				BEARING MATL
RULON J TEFLO FILLED BEARING MATERIAL	DIX	.10	.01				BEARING MATL
RULON LD TEFLO FILLED BEARING MATERIAL	DIA	.00	.00				BEARING MATL
RULON 123 TEFLO FILLED BEARING MATERIAL	DIA	.00	.00				BEARING MATL
VESPEL SP 211-D-1 POLYIMIDE/15% GRAPHITE/10% TEFLO	DUP	.48	.00				SOLID LUBE
VESPEL SP-1-D-1 POLYIMIDE RESIN	DUP	.58	.01				SOLID LUBE
VESPEL SP-21-D-1 POLYIMIDE/25% GRAPHITE	DUP	.52	.01				SOLID LUBE
VESPEL SP-22-D-1 POLYIMIDE/GRAPHITE AS 6U/40 uW	DUP	.57	.00				SOLID LUBE
VESPEL SP-3 POLYIMIDE/15% GRAPHITE AS 6U/40 uW	DUP	.54	.01				SOLID LUBE
VYDAX 1000 FLUOROTEFLOMER	DUP	.67	.08				LUBRICANT

SECTION 9 -- LACING TAPE & CORD CABLE TIES

MATERIAL	MPN CODE	#THL	%CVH	CURE TIME	ATMOS TEMP	APPLICATION
CABLE CLAMP TAO 21C5HO-07HB RED RUBBER SLEEVE	TAD	.22	.03	24H	177	AIR
CLAMP WIRE BUNDLE 11C62 WD FIBERGLASS/SILICONE	TAD	.48	.10	24H	177	AIR
DIAL CORD STUR-D-DIAL DACRON 104 WHITE	GBE	.08	.05	24H	125	AIR
DIAL CORD 753-24 TIE COATED GLASS FIBER	DIN	.11	.04	24H	125	AIR
LACING TAPE DA BURN 2047 DACRON - COATED	DAD	.33	.08	24H	125	AIR
LACING TAPE DA CACN 20D OP9A - WH TIE	MPC	.11	.04	24H	125	AIR
LACING TAPE E 775-476 TFE TEFLON/GLASS METOH WASH	DIN	.19	.04	24H	125	AIR
LACING TAPE GE POLYESTER	DIN	.07	.02	1H	100	AIR
LACING TAPE GUIDE-GLASS 18T FIBERGLASS/TEFLON WHITE	HMB	1.00	.07	24H	125	AIR
LACING TAPE GUIDE-SFACE 18D96 DACRON/S/ST RUBBER WHITE	GSE	.08	.03	24H	100	AIR
LACING TAPE STUR-D-LACE 18DH SCOUR ED LOT 30378	GSE	.24	.03	24H	100	AIR
LACING TAPE STUR-D-LACE 18DH SCOUR ED LOT 30378	GSE	.28	.03	24H	149	AIR
LACING TAPE STUR-D-LACE 18DPT SCOUR ED PROD SAMPLE	GSE	.51	.01	24H	100	AIR
LACING TAPE STUR-D-LACE 18DQ DACRON LEACHED	GSE	.14	.02	24H	100	AIR
LACING TAPE SUPER-GUDE-SPACE DPT-H SCOUR ED DACRON	GSE	.13	.02	24H	100	AIR
LACING TAPE SUPER-GUDE-SPACE DPT-H SCOUR ED DACRON	GSE	.41	.05	24H	100	AIR
LACING TAPE TEFLON GLASS 90LOF13A FIBERGLASS/TEFLON WHITE	GSE	.38	.04	24H	100	AIR
LACING TAPE TEME-LACE H231H TEFLON BRAID/SYN RUBBER	GFC	.43	.05	24H	100	AIR
LACING TAPE TEME-LACE H256H TEFLON BRAID/SYN RUBBER	GSE	.36	.02	24H	100	AIR
LACING TAPE TEME-LACE 230 TEFLON OLIVE DRAB/NQ FIN	GSE	.24	.05	24H	100	AIR
NYLON 6 BLACK CABLE CLAMP - WECKESSER	WEK	.84	.00	24H	125	AIR
PAN-TY CABLE MOUNT	PAN	.63	.04	24H	125	AIR
PAN-TY CABLE TIE HALAH MAROON	PAN	.21	.01	24H	125	AIR
PAN-TY CABLE TIE TEFZEL BLUE	PAN	.08	.02	24H	125	AIR
TIE CORD E 761-1330 TFE TEFLON/GLASS METOH WASH	DIN	.15	.05	24H	125	AIR
TIE CORD E 761-688 TFE TEFLON/GLASS METOH WASH	DIN	.09	.01	24H	125	AIR
TY 25M TY-BAP TEFLON CABLE TIE BLUE/GREEN	TBT	.10	.00	24H	125	AIR
TY 307 TY-BAP TEFLON CABLE TIE	TBT	.03	.00	24H	125	AIR
TY-BAP KINAK CABLE TIE	TBT	.85	.02	16H	100	AIR
TY-B3M TY-RAP NYLON CABLE TIE	TBT	.06	.02	16H	100	AIR

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	REF. CODE	X-TAL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CIRCUIT BOARD COMPOSITE NEMA G10 MICA/CB 1155							
COAST EPOXY/GLASS FIBERGLASS F161-83-108-B	RCA CMS	.48 .46	.01 .01	2H 2H	163 163	AIR AIR	CERAMIC BOARD ADH FILM
CONVALE GRAPHITE/EPOXY	GDC	.63	.03	2H	149	AIR	LADDER BOARD
CONVAT GRAPHITE/EPOXY/SI203/ALUMINUM	GDC	.54	.01	2H	204	AIR	COMPOSITE
CYCCM 95-0-S2 EPOXY/GLASS	ACC	.49	.01	1H	163	AIR	STRUCTURAL
CYCOM 985-T300 GRAPHITE/EPOXY	ACC	.57	.01	1H	138	E-2	STRUCTURAL
E-720 EPOXY/FIBERGLASS LAMINATE - POTTING FORMS	SPI	.54	.04	2H	177	E-2	STRUCTURAL
EPOXY/FIBERGLASS ECON CYLINDER	PLA	.20	.05	2H	177	AIR	STRUCTURAL
FIBERITE HY-E 1076E EPOXY/GRAPHITE LAMINATE	FIB	.50	.03	2H	177	E-3	STRUCTURAL
FIBERITE HY-E 1334A EPOXY/GRAPHITE LAYUP	FAB	.84	.03	2H	177	AIR	STRUCTURAL
FIRESEAN 600 EPOXY/FIBERGLASS	TAI	.94	.03	2H	177	AIR	STRUCTURAL
PLEXASTrip FLEXIBLE WELDING LAMINATE	ANJ	.22	.01	2H	177	AIR	STRUCTURAL
GOODYEAR GRAPHITE FIBER EPOXY COMPOSITE	GAC	.32	.04	2H	177	AIR	STRUCTURAL
GP 5500 COPPER REINFORCED POLYIMIDE HERCULES 2002M	HER	.48	.04	6H	149	E-4	STRUCTURAL
GY-70-X-30 GRAPHITE EPOXY LAMINATE ONE SIDE	GDS	.05	.04	2H	177	AIR	STRUCTURAL
GY-70-X-30 GRAPHITE EPOXY COMPOSITE	GDC	.49	.01	2H	177	AIR	STRUCTURAL
GY-70-X-5208 GRAPHITE EPOXY COMPOSITE	WCN	.40	.03	2H	177	AIR	STRUCTURAL
HEXCEL F174-120 GLASS CLOTH EPOXY IMIDE PRE PREG	HEI	.18	.03	2H	177	AIR	STRUCTURAL
KPL 4036 ACETAL/30% GLASS/5% TPE/SILICONE	HEA	.49	.02	2H	177	AIR	STRUCTURAL
KL 4540 ACETAL/20% TPE/SILICONE	LNP	.26	.02	2H	177	AIR	STRUCTURAL
LAMINATE AL-3000 G3C POLYIMIDE/GLASS - BROWN	LNP	.35	.02	2H	177	AIR	STRUCTURAL
LAMINATE AL-3137 TFE TYPE PLATE/O COPPER	ATL	.63	.03	2H	177	AIR	STRUCTURAL
LAMINATE AL-3247 TFE THIN W/O COPPER	ATL	.29	.03	2H	177	AIR	STRUCTURAL
LAMINATE AS-4/19C8 EPOXY/GRAPHITE	HER	.11	.01	6H	177	AIR	STRUCTURAL
LAMINATE BL-2 EPOXY/GRAPHITE	HER	.19	.03	2H	177	AIR	STRUCTURAL
LAMINATE E33 NATURAL TFE GP COR/LAK 5104/GLASS/FR4	GEC	.62	.01	1H	177	AIR	STRUCTURAL
LAMINATE CE339 HMs EPOXY/GRAPHITE TUBE	PER	.54	.03	6H	177	AIR	STRUCTURAL
LAMINATE CHC 608-1-3-1 KAPTON/COPPER FOIL/KAPTON	GMC	.19	.02	45H	177	AIR	STRUCTURAL
LAMINATE CUCLADE TEFLON/GRAPHITE	HMM	.04	.00	2H	177	AIR	STRUCTURAL
LAMINATE CUSTOM LAM-006	HMM	.46	.00	2H	177	AIR	STRUCTURAL
LAMINATE CUSTOM FC11 TG TEPLON/FIBERGLASS	CUE	.02	.01	2H	177	AIR	STRUCTURAL
LAMINATE EPOXY/FIBERGLASS MULTILAYER CKT BD	CUE	.43	.01	2H	177	AIR	STRUCTURAL
LAMINATE EPOXY/FIBERGLASS TYPE II CLASS E GRADE 2	QUA	.28	.01	2H	177	AIR	STRUCTURAL
LAMINATE EPOXY/FIBERGLASS/NY40/HY219/DY219/1275	QUA	.93	.00	2H	177	AIR	STRUCTURAL
LAMINATE EPOXY/Glass UNIGLASS DUE HIL-P13949/44 MULTILAYER	HUP	.35	.00	2H	177	AIR	STRUCTURAL
LAMINATE EPOXY/GLASS UNIGLASS STYLE 181	UNI	.30	.00	2H	177	AIR	STRUCTURAL
LAMINATE EPSILAM 1C MICROWAVE SUBSTRATE W/O COPPER	MNM	.04	.00	2H	177	AIR	STRUCTURAL
LAMINATE FLEXIBLE FRINGE	SPA	.13	.00	2H	177	AIR	STRUCTURAL
LAMINATE FLG-65M 26-1 EPOXY/FIBERGLASS/FIRE RETARD	SPA	.19	.00	2H	177	AIR	STRUCTURAL
LAMINATE FLG-FK-4 FC BOARD	SPA	.32	.01	2H	177	AIR	STRUCTURAL
LAMINATE FLGFO3902/1B3B EPOXY/GLASS MULTI-LAYER	FLA	.51	.01	2H	177	AIR	STRUCTURAL
LAMINATE FLGF250C2/2A1B-BLACK W/COPPER 2 SIDE	FLA	.12	.00	2H	177	AIR	STRUCTURAL

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	MFR CODE	XTHL	XCVCM	CURE TIME	CURE AT/HUS	APPLICATION
LAMINATE FR-4 G-11 EPOXY/FIBERGLASS	NCA	-3.1	-0.1			LAMINATE
LAMINATE G-10 BLACK EPOXY/FIBERGLASS	HEA	-2.7	-0.3			LAMINATE
LAMINATE G-10 EPOXY/FIBER GLASS	ATL	-3.0	-0.1			LAMINATE
LAMINATE G-10 T-10 MIL P13949 - NORPLEX	NCA	-4.8	-0.1			LAMINATE
LAMINATE G-10 T-10 MIL P13949 - WESTINGHOUSE	UOP	-9.3	-0.0			LAMINATE
LAMINATE G-10 465 EPOXY/FIBERGLASS	WEC	-4.2	-0.0			LAMINATE
LAMINATE G-11 GEC-111 EPOXY/GIBERGLASS	SYN	-4.7	-0.3			LAMINATE
LAMINATE GE 111 EPOXY/FIBERGLASS	SYN	-5.9	-0.0			LAMINATE
LAMINATE GEE MIL P18117 BLUE EPOXY/GLASS	GEC	-4.3	-0.3			LAMINATE
LAMINATE GEE MIL P8177 EPOXY/FIBERGLASS	GEC	-3.3	-0.0			LAMINATE
LAMINATE GEE FR 4300 RESIN EPOXY/FIBERGLASS - BLACK	PPP	-5.2	-0.0			LAMINATE
LAMINATE GLASS CLOTH/SILICONE - WHITE	WEC	-6.1	-0.1			PULLING CUP
LAMINATE G10 WESTINGHOUSE 65M25 FR-4 FLAME RETARDANT	WEC	-6.1	-0.0			LAD1 NA1E
LAMINATE H1534/934 GRAPHITE EPOXY	GDC	-3.4	-0.0			LAD1 NA1E
LAMINATE K-6098 TEFLON/FIBERGLASS/3M	NN	-0.1	-0.1			LAD1 NA1E
LAMINATE K-6098 W/AP 46 FILM ADHESIVE	NN	-0.1	-0.1			LAD1 NA1E
LAMINATE K1270N ENCAPSULATED COPPER	DUP	-3.9	-0.1			LAD1 NA1E
LAMINATE MICAPLY EG 802 TYPE GF W/O COPPER	ACA	-4.1	-0.2			LAD1 NA1E
LAMINATE MICAPLY EG 802 UNCLAD	ACA	-9.1	-0.0			LAD1 NA1E
LAMINATE MICAPLY PG 418 POLYIMIDE/FIBERGLASS	NCA	-8.2	-0.0			PC BOARD
LAMINATE MICAPLY 102-11 EPOXY/GLASS PRE-PREG 8 LAYER	NCA	-3.8	-0.0			LAD1 NA1E
LAMINATE MICAPLY 102-11/G-10 EPOXY/GLASS PRE-PREG	NCA	-4.4	-0.0			LAD1 NA1E
LAMINATE MICAPLY 102-28M FR-4 EPOXY/GLASS PRE-PREG	NCA	-3.9	-0.0			LAD1 NA1E
LAMINATE MICAPLY 818T W/O COPPER GREEN	NCA	-3.6	-0.0			LAD1 NA1E
LAMINATE MULTILAYER PCB 65M50-22 LIGHT GREEN	WEC	-2.8	-0.0			LAD1 NA1E
LAMINATE MULTILAYER PCB BOARD 55617 P55636 P13949	KOL	-3.2	-0.0			LAD1 NA1E
LAMINATE N-105 EPOXY/GLASS FL-GF PR-4 W/O COPPER	NCO	-6.3	-0.0			PC BOARD
LAMINATE N-205 EPOXY/GLASS FL-GF PR-4 W/O COPPER	NCO	-2.5	-0.0			LAD1 NA1E
LAMINATE N-3105 RESIN RICH PRE EPOXY/GLASS W/O COPPER	NCO	-2.4	-0.0			LAD1 NA1E
LAMINATE N-4105 EPOXY/GLASS FLEXIBLE W/O COPPER	NCO	-3.9	-0.0			LAD1 NA1E
LAMINATE NARCO 3203-12W EPOXY/GLASS	WCN	-3.3	-0.0			LAD1 NA1E
LAMINATE NARCO 3203-15W EPOXY/GLASS	WCN	-3.2	-0.0			LAD1 NA1E
LAMINATE NEMA FR-4 BY GE W/O COPPER	GE	-4.7	-0.0			LAD1 NA1E
LAMINATE NEMA G-10 GEC 500E EPOXY/FIBER GLASS	GEC	-2.3	-0.0			LAD1 NA1E
LAMINATE NEMA G10 WESTINGHOUSE 6SM27-S-2 W/COPPER	WEC	-1.1	-0.0			LAD1 NA1E
LAMINATE NEMA G10 WESTINGHOUSE 6SM27-S-12 W/COPPER	WEC	-0.6	-0.0			LAD1 NA1E
LAMINATE NEMA G10 GIASS FABRIC/SILICONE	SYN	-0.9	-0.0			LAD1 NA1E
LAMINATE NEMA FR-4 W/SR1000 SOLDER RESIST FILM	AUG	-1.2	-0.0			LAD1 NA1E/RESIST
LAMINATE NEMA FR-4 W/SR1000 SOLDER RESIST/IR CURR	NVP	-1.4	-0.0			LAD1 NA1E
LAMINATE NVP G-10 GREEN MARKING	NVP	-3.8	-0.0			LAD1 NA1E
LAMINATE PC BOARD IRRADIATED POLYOLEFIN	SAS	-2.9	-0.0			PC BOARD
LAMINATE PHENOLIC/FIBERGLASS PREPREG	VAC	-6.8	-0.0			LAD1 NA1E
LAMINATE PMR-15/HMG EPOXY/GRAPHITE	VAC	-4.9	-0.0			LAD1 NA1E
LAMINATE POLYIMIDE/GLASS FABRIC BY AMQCO	AOC	-7.7	-0.0			SHELL
LAMINATE SHIM ALUMINUM ART	ART	-0.5	-0.0			SHELL
LAMINATE SUN SHALE AL-KAPTON/7366 TAPE/AG-TEFLON-CTR	GSC	-0.5	-0.0			SHELL
LAMINATE SUN SHADE AL-KAPTON/7366 TAPE/AG-TEFLON-EDG	GSC	-0.5	-0.0			SHELL
LAMINATE TYPE G EPOXY/FIBERGLASS	FIC	-0.0	-0.0			LAD1 NA1E
LAMINATE T300/934 GRAPHITE EPOXY	FIB	-3.8	-0.0			LAD1 NA1E

SECTION 10 -- LAMINATES CIRCUIT BOARDS

MATERIAL	MPK CODE	XTHL	XCVCM	CURE TIME	CURE TEMP	STATUS	APPLICATION
LAMINATE V-378A/HMG EPOXY/GRAPHITE	USP	.50	.01				LAMINATE
LAMINATE VECTORBOARD 85G24WE GLASS/EPOXY	VEC	.45	.01	1H	193	AIR	PC BOARD
LAMINATE WBC 3201C ON 112 GLASS CLOTH EPOXY RESIN	FER	.17	.01	2H	177	AIR	LADDER
LAMINATE WESTINGHOUSE EPOXY/FIBERGLASS	WEC	.25	.02				TOOL
LAMINATE YLI 602 TEFLOC/FIBERGLASS W/O COPPER	YLI	.43	.00				LAMINATE
LAMINATE YLI 602 TEFLOC/FIBERGLASS W/O COPPER	ATL	.01	.00				PC BOARD
LARC 160 GRAPHITE/FOLYIMIDE LAMINATE 3 STEP POSTCURE	LAC	.83	.00	1H	177	B-2	LADDER
NARMCO 550/120 EPOXY/GLASS PRE-PREG	WCN	.69	.06	3H	315	PSI	LADDER
NARMCO 550/1581 EPOXY PRE-PREG	WCN	.60	.02	90M	125	AIR	LADDER
NE LCO 11-4205-2 I-GLASS FR4 FABRIC/EPOXY COATED	NCO	.29	.00	2H	180	AIR	LADDER
POTTING CUP	DBP	.62	.01	2H	163	AIR	FABRIC
PYRALIN 12 POLYIMIDE PREPREG	DUP	.52	.00	30M	135	AIR	LADDER
PYRALUX COPPER CLAD 2 SIDES .015 MILS THICK	DUP	.14	.00	2H	177	PSI	LADDER
RT DURIDAMP 19010-1 LAMINATE ONLY	BAR	.57	.00	1H	260	PSI	LADDER
RT DURID 5880 - LAMINATE	ROG	.05	.00				LADDER
RT DURID 5880 - LAMINATE	ROG	.03	.00				LADDER
RT DURID 6010 - LAMINATE	ROG	.03	.00				LADDER
SC-1 KEEZ 80/5 GLASS FILAMENT WOUND COMPOSITE	SCI	.22	.03	4H	79	AIR	LADDER
SCOTT POLYURETHANE FOAM/ALUM NYLAR SANDWICH	SCT	.81	.04	4H	107	AIR	
SKYBOND 703 GRAPHITE/POLYIMIDE LAMINATE 3 STEP PCURE	MON	.36	.01	3H	149	AIR	
SP AND-OFF G-10 EPOXY/GLASS COMPOSITION	BPS	.10	.00	1H	177	PSI	LADDER
V 378 GRAPHITE/PCLLIIDE LAMINATE 2 STEP POSTCURE	USP	.60	.01	30M	82	PSI	SP AND OFF
				4H	177	PSI	Turned CONTROL

SECTION 11 -- MARKING MATERIALS & INKS

MATERIAL	MFR CODE	#ML	ACVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
BRADY MARKERS E-953 HT-200/P CHEMGLAZE 2004 W/5% CHROMIC OXIDE PIGMENT	WHB HCC	.81 .83	.02 .03	24H 18H	150 60	AIR AIR	NAMEPLATE NAMEPLATE
EPON 815/V 140/PMS 175-ED AS 50/5 BN WHITE EPOXY	SHL APP	.64 .42	.07 .07	3H 6H	25 65	AIR AIR	MARKING INK MARKING INK
PASCAL 710 CHROMIZED POLYESTER/ACRYLIC ADH/R	AIN	.45	.02	4H	121	AIR	NAMEPLATE
MARKEN 7224 GREEN INK 497-F	AS 8-18/1-B						INK
MARKEN 7906 WHITE INK A/B AS 8-18/1-B	BEN	.48	.01	4H	121	AIR	NAMEPLATE
NAMEPLATE ANODIZED ALUMINUM 3M TAPE 467 ADH/F	REL	.63	.01	4H	121	AIR	NAMEPLATE
NAMEPLATE PHOTO ALUMINUM 1/4" ADH/ON ROLL	HPC	.10	.01	4H	121	AIR	NAMEPLATE
NAMEPLATE PHOTO-SENSITIVE ALUM/ANODIZED/SEALED BLACK	MPC	.11	.00	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8001 RED ALUMINUM LABEL UNCOATED	MM	.09	.00	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8001 RED ALUMINUM LABEL/COATING 3900	MM	.17	.00	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8001 RED ALUMINUM LABEL/FILM 730	MM	.12	.01	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8005 BLACK PHOTO SENSE FILM/ALUM/ADH/FOIL	MM	.12	.01	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8005 PHOTOSENS FILM/ALUM/ACRYLIC ADH	MM	.19	.00	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8009 BLUE ALUMINUM LABEL/COATING/ACR ADH	MM	.19	.01	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8009 BLUE ALUMINUM LABEL/UNCOATED	MM	.08	.01	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8009 BLUE ALUMINUM LABEL/COATING 3900	MM	.15	.01	4H	121	AIR	NAMEPLATE
SCOTCHCAL 8011 RED PHOTO SENSE FILM/ADH/FOIL	MM	.14	.01	4H	121	AIR	NAMEPLATE
THEMOPROFIT RT 1800/1 HT TMS WHITE HEAT GUN SHRINK	RCC	.56	.03	5H	175	AIR	NAMEPLATE
THEMOPROFIT RT 1800/1 HI TMS WHITE BARKER SLEEVE	RCC	.97	.06	5H	175	AIR	NAMEPLATE
WORNOW CAT-L-INK SC-10/CAT 9/50-900 THINNER WHITE/F	WPP	.62	.01	30E	138	AIR	SUBLINK TUBING
WORNOW N-2-N RED/CAT 45/T-1 THINNER/F	WPP	.40	.02	1H	149	AIR	INK
WORNOW N-5-N GREEN/CAT 45/T-1 THINNER/P	WPP	.44	.02	1H	149	AIR	INK
				4H	149	AIR	

SECTION 12 -- MOLDING COMPOUNDS

MATERIAL	MFR CODE	XMTL	XCVCM	CURE TIME	ATMS	APPLICATION
ACRYLAFIL G47/20 STYR/ACRYLONITRILE/FIB GLA AS 80/20	FBR	.23	.00		AIR	C/PND
ACRYLAGLAS S40/35 STYRENE-ACRYLONITRILE/FIBER GLASS	FBR	.22	.03		AIR	C/PND
ADI-PRENE L8/CAV TUR 21 AS 100/16 BW POLYURETHANE	DUP	.34	.03	2H	120	AIR E-O
AMP 1006 ACRYL BUTYLATE STYRENE	LNP	.20	.01			
AMP MOLDING COMPOUND AMBER	AMP	.21	.00			
AYLON AT POLYARYL ETHER MOLDED AT 260C	UNC	.36	.003			
ASTREL 360 POLYARYL SULFONE	HM	.94	.002			
BF 1006 STYRENE ACRYLONITRILE	LNP	.24	.01			
BU SHING TYPE MFE MILL 4-14 NICA FILLED PHENOLIC	GHT	.98	.004			
CELLCON M-90-04 ACETAL COPOLYMER INJECTION MOLDED	CNS	.64	.004			
CELLCON M-90-04 ACETAL COPOLYMER UNMOLDED PELLETS	CNS	.57	.003			
CF 1006 STYRENE FILLED GLASS AS 70/30	LNP	.19	.004			
CONNECTOR TUBING ECFL PROPYLENE 20% GLASS FILLED	JAC	.26	.003			
C9-4215/H2-3561 AS 20/30 BW BLACK EPOXY	HYS	.68	.005	2.5H	105	AIR
DAP C2580-11B FOR FMC - DAPON M	FMC	.30	.003			
DAP SHORT GLASS FIBER FILLED BLACK	HOG	.44	.003			
D-307 MOLDING CFM - FUSISTOR RS-1A-XX (k-7741)	DCC	.12	.002	24H	177	AIR
DELRIN 550 ROD WHITE	DUP	.62	.002			
DEXLIN 201 - BORCH SILICA	DUP	.39	.002			
DF 1006 POLYCARBONATE FIBER GLASS AS 70/30	CIT	.07	.002			
ECCOMOLD L-28	LNP	.14	.001			
ECCOMOLD L-28/9 AS 100/12 BW	EMC	.18	.001			
ECCOMOLD 77A EPOXY - MOULD 10M AT 163C W/PSI	EMC	.59	.03	30H	127	AIR
ECOSORB CR-117 A/1 AS 100/23 BW DAKK GRAY EPOXY	EHC	.32	.07	2H	70	AIR
ECOSORB CR-110 A/1 AS 100/12 BW EPOXY	FMC	.52	.00			
EKKCEL C-1000 AROMATIC COPOLYESTER BROWN HIGH TEMP	CRG	.26	.00			
EKKCEL I-2000 AROMATIC COPOLYESTER TAN HIGH TEMP	GBC	.05	.00			
EL TBN POLY(ETHERIMIDE) FILLED EPOXY	JSP	.48	.00			
EMC 115-B-1 GLASS/EPOXY	PAC	.29	.00			
EPICL 1914 EPOXY/GLASS - BLACK	ACM	.47	.00			
EPICL 1914 EPOXY/GLASS - BLACK	PPI	.32	.00			
EPICL 1914 EPOXY/GLASS - BLACK	PPF	.48	.00			
EPOCAST 403-S-3 MINERAL FILLED EPOXY	PPF	.85	.004			
EPOCAST 461-008 MINERAL FILLED EPOXY	PPF	.12	.003			
EPOTREN 525 EPOXY/FIBERGLASS SQUARE STRUCTURAL TUBE	LNP	.44	.003			
EP 1006 HI-DENSITY POLYETHYLENE GLASS AS 70/30	LNP	.44	.003			
FF 1006 HI-DENSITY POLYETHYLENE GLASS AS 70/30	FBB	.44	.003			
FFENDAFL 680-20 ACETYL FIBERGLASS AS 80/20 BW	FBB	.32	.003			
FJ RANE 8633-40 GLASS REINFORCED CARBON FILLED EPOXY	GAR	.07	.001			
GAR-DUR CLEAR	GAR	.10	.002			
GP MON 3010 THE KMCSET POLYIMIDE	GEC	.34	.002			
GP 1006 POLYSULFONE/FIBER GLASS AS 70/30	LNP	.44	.002			
HATHANE 1602-6JD A/B AS 2/1 BV URETHANE	HPC	.72	.01	24H	25	AIR
HF 1006 NYLON 11/GIASS AS 70/30	LNP	.37	.02			
HOSTALEN GUR HIGH MOLECULAR WT POLYETHYLENE	ANH	.14	.02			
IMPAX 5M W/UMA ECLIPSE - NATURAL	IPI	.22	.03			
JF 1004 POLYETHERSULFONE/NYLON GLASS AS 80/20 BW	LNP	.59	.00			
JF 1008 POLYETHERSULFONE/GLASS AS 60/40 BW BLACK	LNP	.49	.01			
KF 1006 ACETAL/GLASS AS 70/30	LNP	.27	.01			

SECTION 12 -- MOLDING COMPOUNDS

MATERIAL	APR CODE	XMTL	XCYC	CURE TIME	CURE TEMP	ATROS	APPLICATION
LAMINATE F550 EPOXY/CELTION 3000 GRAPHITE COMPOSITE	HXM	.42	.00	6H	121	PSI	LAMINATE
LEXAN 540 POLYCARBONATE	GEC	.16	.00				HOLD CEND
LEXAN 540 BLACK SHELL PLATE	GEC	.16	.04				DIA+ CPND
HA-1-60 MOLDING CENL - GRAY	ACD	.73	.03	16H	100	AIR	HOLD CPND
HA-1-60 MOLDING CENL - GRAY	ACD	.75	.03				HOLD CPND
HP 100 6 POLYPROPYLENE/GLASS AS 70/30	LNP	.13	.01	3H	149	AIR	HOLD CPND
MG8P-0134 MOLDING CPND - BLACK	HYS	.22	.01	2H	149	PSI	HOLD CPND
MI 11 BLACK HOLDING COMPOUND	HYS	.18	.01	3H	149	AIR	HOLD CPND
MH 6F MOLDING CPND - BLACK	HYS	.41	.01	2H	149	AIR	HOLD CPND
NF 100 6 PPO/FIBER GLASS AS 70/30	LNP	.11	.00				HOLD CPND
NORYL PH 265	PPC	.17	.00				HOLD CPND
NORYL N300 BLACK	PPC	.25	.02				OLB RESERVOIR
NYLASINT 64 HV SINTERED NYLON OIL RESERVOIR	PPC	.73	.02				HOLD CPND
PHENOLIC 76-0001-06/EPOXY ANHYDRIDE 76-0001-10	SPE	.33	.00				HOLD CPND
POLYCARBONATE G50/20 POLYCARBONATE/FIBER GLA AS 8 0/20	FBR	.12	.00				HOLD CPND
POLYESTER 521 BLACK CO-EXTRUDED WHITE BOX	ANC	.30	.00				HOLD CPND
POLYSTYRENE CO-EXTRUDED WHITE BOX INSERT	SHC	.50	.05				HOLD CPND
POLYSULFONE	UCC	.33	.00				HOLD CPND
POREX ULTRA HIGH WEIGHT POLYTHYLENE HEAT PIPE WICK	POX	.11	.00				HEAT FLIPE WICK
PA 1535 A/B AS 3/2/100 BN POLYURETHANE	PRC	.98	.00	70	25	AIR	HOLD CPND
PA 1538 A/B AS 3/2/100 BN POLYURETHANE	PRC	.52	.05	144H	60	AIR	HOLD CPND
PA 1547 A/B AS 3/2/100 BN POLYURETHANE	PRC	.65	.05	7H	82	AIR	HOLD CPND
OP 100 6 NYLON 6/10 30% FIBER GLASS	LNP	.65	.04				HOLD CPND
RF 100 6 NYLON 6/6 ROGERS RX 611	ROG	.81	.04				HOLD CPND
RFV 615 A/B AS 10/1 BN DEVOL AT 140C LOT KA210 BTCH5	GSC	.20	.05				PULLING
RYTON R-4 POLYPHENYLENE SULFIDE/40% GLASS	PHP	.09	.00				HOLD CPND
SCOTCHCAST 225 A/B AS 5/8 BN MARCON POLYURETHANE	MA4	.53	.03				HOLD CPND
SE 4401 SILICONE ELASTOMER GRAY SHORE A00	GEC	.15	.05	10M	166	PSI	HOLD CPND
SE 4401 U GENERAL PURPOSE SILICONE	GEC	.06	.00				HOLD CPND
SE 4524U GENERAL PURPOSE SILICONE	GEC	.10	.00	24H	249	AIR	HOLD CPND
SE 4524U CLEAR SILICONE	GEC	.10	.01	25M	249	AIR	HOLD CPND
SE 4524U CLEAR SILICONE	GEC	.07	.00	25M	163	E-O	HOLD CPND
SE 5204 SILICONE	GEC	.07	.00	7H	149	AIR	E-MAS DUMER
SE 5554U SILICONE FOOD GRADE FF	GEC	.16	.00	20H	216	AIR	HOLD CPND
SE 5554U SILICONE FOOD GRADE GG	GEC	.25	.00	30H	163	PSI	HOLD CPND
SE 565 / VAROX AS 100/0.6 BN EXTREME LOW TEMP SILICONE	GEC	.12	.03	15H	121	E-O	HOLD CPND
SF 100 6 NYLON 12/6 GLASS AS 70/30 SILICONE	LNP	.65	.01	48H	177	AIR	HOLD CPND
SILASTIC 6508 12S-50 CADOK AS 99/1 BN SILICONE	DCC	.20	.06	5H	116	AIR	HOLD CPND
STYCAST 0005 POLYSTYRENE/FIBER GLASS	EMC	.29	.01	24H	216	AIR	HOLD CPND
STYRAFIL G37/20/CR BLACK POLYSTYRENE/FIBER GLASS	FBR	.53	.00				

SECTION 12 -- MOLDING COMPOUNDS

MATERIAL	BFK CODE	%TML	XCVCA	CURE TIME	CURE TEMP	AIDS	APPLICATION
SULFIL 1500/20 PVC/ULTRAFINE FIBER GLASS AS 80/20	FBL	.20	.01				MOLD CPND
SJ PRAMICA 500 SYNTHETIC RICA/ORGANIC BINDER	HYC	.00					STRUCTURAL
TEFLON PFA MOLDED SPECIMENTE-9704	DUP	.01					MOLD CPND
TEFLON PFA PELLETS (PERFLUOROALKOX Y TEFILON)	DUP	.00					MOLD CPND
TERZEL ETHYLENE TEREPHTHALIC ACID COPOLYMER	DUP	.03					MOLD CPND
TF 100-8 EPOXYURETHANE GLASS AS 60/40	LNP	.37	.08				MOLD CPND
ULTEM 06202 GREY/EBROWN MOLD CPND FILLED	GEC	.37					MOLD CPND
ULTEM 1000 CLEAR AMBER MOLD CPND UNREINFORCED	GEC	.40					MOLD CPND
VALOX 310 THERMOELASTIC POLYESTER ^a							MOLD CPND
VALOX 420 THERMOELASTIC POLYESTER/30% GLASS	GEC	.20					MOLD CPND
VALOX 420 THERMOELASTIC POLYESTER/30% GLASS FIBER	GEC	.16					MOLD CPND
VESPEL SP-5 POLYIMIDE 35% SHORT GLASS FIBERS	DUP	.09					MOLD CPND
VF 100-7 PVC 35% FIBER GLASS	LNP	.49					MOLD CPND
XF 100-6 THERMOPLASTIC POLYESTER/FIB GLASS AS 70/30	LNP	.39					MOLD CPND
ZP 100-6 POLYARYL FIBERGLASS AS 70/30	LNP	.19					MOLD CPND
ZP 100-6 NOVEL/FIBER GLASS AS 70/30	LNP	.04					MOLD CPND

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	HPR CODE	ATM	XCVH	CURE TIME	ATMS	TEMP TIME	APPLICATION
BR-127 PRIMER/F-3-8 FLACK OVER PRIMER 463-6-2 GREEN/F	ACC FPC	.48	.03	20H	.127	AIR	PAINT PAINT COMPOSITE
CAT-A-LAC 463-3-8		.70	.03	24H	2.5	AIR	PAINT
CHEMGLAZE A27C HIGH GLOSS WHITE POLYURETHANE/F	HCC	.99	.08	15D	1.21	AIR	PAINT
CHEMGLAZE H322 BLACK CONDUCTIVE PAINT POLYURETHANE V200/9924 GLOSS WHITE POLYURETHANE PAINT/F	HCC	.86	.09	30H	1.21	E-O	COND PAINT PAINT SYSTEM
CHEMGLAZE 2004 BLACK COND PAINT MOD POLYURETHANE	HCC	.72	.03	11D	2.5	AIR	PAINT
CHEMGLAZE 2202 POLYURETHANE FORMERLY TS 1603-16	HCC	.90	.04	72H	2.5	E-O	COND PAINT
CHEMGLAZE Z306 BATCH L11247	HCC	.60	.02	7D	2.5	AIR	PAINT
CHEMGLAZE 2306 LCT LBC	HCC	.49	.02	21D	2.5	AIR	PAINT
CHEMGLAZE 2306 LCT WHA	HCC	.47	.04	24H	100	E-O	PAINT
CHEMGLAZE 2306 LCT NFA	HCC	.92	.00	16H	6.6	AIR	PAINT
CHEMGLAZE 2309 LCT NDA SPRAYED	HCC	.90	.00	14D	2.5	AIR	PAINT
CHEMGLAZE 2309 LOT NDA	HCC	.87	.04	14D	2.5	AIR	PAINT
CHEMGLAZE 2309 LOT NDA	HCC	.76	.03	14D	2.5	AIR	PAINT
CHEMGLAZE 2309 LOT RLX	HCC	.91	.03	14D	2.5	AIR	PAINT
CHEMGLAZE 2309 LOT TDA	HCC	.83	.03	14D	2.5	AIR	PAINT
CHEMGLAZE 2309 LCT WHA	HCC	.92	.03	14D	2.5	AIR	PAINT
CHEMGLAZE 2306/B401 MICROBALLOONS/TOLUENE	HCC	.83	.03	15D	2.5	AIR	PAINT
CHEMGLAZE 2306/CEELOK AP131 PRIMER/F	HCC	.76	.05	30D	2.5	AIR	PAINT COMPOSITE
CHEMGLAZE 2306/KAPTON H REINF	HCC	.90	.08	42D	2.5	AIR	PAINT COMPOSITE
CHEMGLAZE 2306/KAPTON H REINF	HCC	.94	.09	42D	2.5	AIR	PAINT COMPOSITE
CHEMGLAZE 2402 ALUM FILLED POLYURETHANE LOT DEB	HCC	.88	.09	24H	12.5	AIR	PAINT
COVERT IN 305 BLACK POLYURETHANE COATING DAG EC 1652 BLACK PAINT	HNC ACH DUP	.68	.07	14D	2.5	AIR	PAINT
DUPONT 4922 A/B AS 1/1 BW COND SILVER PAINT	HNC ACH DUP	.69	.02	14D	2.5	AIR	PAINT
D4 D LEAFING ALUMINUM	GEC	.72	.10	48H	9.9	AIR	PAINT
E-KOTE 3030 CONDUCTIVE ACRYLIC PAINT	EPO	.76	.05	48H	9.9	AIR	COND PAINT
ECP 2200 BLACK SCALAR ABSORBER COATING/F	MHN GSC SH*	.08	.00	24H	22.5	AIR	TURBO CONTROL
FISHEK BLACK COATING 113/113-300/CARBOLAC/REK/T-12	MHN GSC SH*	.51	.00	7D	20.4	AIR	PAINT PAINT
FLUOCOCLAD CLEAR V78VP21		.05	.01	30D	9.3	AIR	PAINT
FLUOCOCLAD WHITE G79WP37	SH*	.67	.05	30H	26.0	AIR	PAINT
FSS BLUE PAINT/F	GSC	.71	.05	15H	2.0	AIR	PAINT
G 3113 BLACK COATING DALL CHEM ALKYD-SILICONE	BAL	.03	.02	1H	23.2	E-O	PAINT PAINT
G-1897 HT ALUM COATING G5FC 657-41 SILICONE WHITE PAINT	BAL	.99	.04	1H	23.2	AIR	PAINT PAINT
G5FC 657-41 SILICONE WHITE PAINT	GSC	.17	.03	3.5D	2.5	AIR	PAINT
GSFC 657-42 SILICONE WHITE PAINT	GSC	.14	.00	7D	6.6	AIR	PAINT
GSFC 657-44 SILICONE WHITE PAINT	GSC	.21	.08	4D	2.5	AIR	PAINT
LAMINATE ASHLAN G4C Grade EPOXY/FLD GLASS	MNS	.15	.07	3D	2.5	AIR	LADINATE
	MNS	.39	.01	20H	100		

SECTION 13 -- PAINTS LACQUERS VARNISHES

MATERIAL	HPK CODE	ATM.	ACVCM	CURE TIME	CURE TEMP	ADHS	APPLICATION
MS 125 WHITE COATING S-AS04/PVA/KYVYLON	GSC	.79	.10	14D	25	A1a	OPACAL PAINT
MSA 101E GELN PAINT OIL 650/CHROMIC OXIDE	GSC	.58	.30	6H	150	A1a	PAINT
MSA 90 WHITE PAINT OIL 650/POIASS TREATED ZNO	GEL	.96	.06	6H	150	A1a	PAINT
NE 650 WATER BASE LATEX SILO2 PAINT	GSC	.51	.03	21D	25	A1a	PAINT
OL 650 RESIN WHITE PAINT GSFc SHAI	GSC	.77	.00	16H	100	A1a	PAINT
P 764-1A RESIN WHITE SILICONE PAINT	GSC	.59	.03	7D	25	A1a	PAINT
POTASSIUM TITANATE WHITE PAINT 150 GSFc SHAI	GSC	.84	.09	18H	122	A1a	PAINT
PYROMARK STANDARD WHITE SILICONE ON ALUMINUM	TEA	.06	.02	TEA	PAINT		
PYROMARK STANDARD WHITE SILICONE ON EPOXY	TEM	.49	.03	TEA	PAINT		
ATV 002 764-1A WHITE PAINT FAIR BATCH 2	GSC	.44	.01	7D	25	A1b	PAINT
ATV 602/SRC 05 AS 6-25% CAT DEVOL LOT BM242 BATCH 5	GSC	.46	.09	7D	25	A1b	PAINT BASE
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT BM252 BATCH 3	GEC	.63	.05	7D	25	A1b	PAINT BASE
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT CN258 BATCH 3	GEC	.41	.03	7D	25	A1b	PAINT BASE
RTV 602/SRC 05 AS 0-25% CAT DEVOL LOT CN258 BATCH 4	GSC	.33	.09	7D	25	A1b	PAINT
S-13-G SILICONE WHITE PAINT	ITA	.42	.09	48H	25	A1b	PAINT
S-13-G-LO WHITE PAINT A/B AS 100/1 BM 4-TOLUENE	ITA	.54	.10	16H	121	E-6	PAINT
S-13-G-LO WHITE PAINT 1/2 PRIMER BATCH E-389	ITA	.57	.02	7D	25	A1b	PAINT
S-13-G-LO WHITE PAINT 1/2 PRIMER BATCH E-496	ITA	.44	.04	7D	25	A1b	PAINT
S-13-G-LO WHITE PAINT 1/2 PRIMER BATCH E-497	ITA	.49	.02	7D	25	A1b	PAINT
S-13-G-LO WHITE PAINT 1/2 PRIMER BATCH E-552	ITA	.47	.03	7D	25	A1b	PAINT
S-13-G-LO WHITE PAINT 1/2 PRIMER BATCH E-555	ITA	.98	.04	39H	177	A1b	PAINT
SICON BLACK 7A9055 SILICONE	HD	.95	.03	15H	510	A1b	PAINT
SICON R 8X929 BLACK PAINT	HD	.79	.09	48H	25	A1b	PAINT
SICON 3X258 LEAFING ALUMINUM	HD	.8D	.71	7D	25	A1b	PAINT
SOLITHANE 113/300/1-1/2 FERRIC OXIDE/CABOSIL	GSC	.38	.06	2D	25	A1a	PAINT
SOLITHANE 113/300/1-1/2 FERRIC OXIDE/CABOSIL	GSC	.40	.05	24H	60	A1a	PAINT
SPACE GAED 4-B-33 OVER RANDOLPH PRIMER T-4/F	DEX	.79	.03	10H	E-2	PAINT COMPOSITE	
SPERRY SP-101 VHI HIGH TEMP COATING-WHITE SILICONE	SPX	.29	.01	15H	25	A1a	PAINT
VARNISH STERLING THERMOPOXY T-653-LBu	STV	.70	.02	1H	316	A1a	VARNISH
Y-210 VARNISH - THERMODUR	STV	.56	.07	24H	180	A1a	E-2
					149	A1a	
					125	E-6	

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	DFR CODE	%TML	%CVCA	CURE TIME	CURE ATMOS	APPLICATION
ABLETHERM 7-2 FILLED SILICONE CERAMIC FILLED SOLITHANE 113/300/412	AAC	.29	.10	4H	AIR	POTTING
ADIPRENE L100/SOLITHANE C-300/CRBW BLK AS 100/40/1-4	AAC	.16	.37	48H	AIR	POTTING
ALLCAST 1776 POTTING CPND FOR OPTICAL COMPONENTS	DUP	.74	.01	1H	AIR	POTTING
ARALDITE CY179/90C6/465/MNS-XL EPOXY	BAC	.25	.01	16H	AIR	POTTING
ARALDITE MY750/HT972/MARBLE FLOUR AS 100/27/100 BW	CIB	.16	.00	1H	AIR	POTTING
ARALDITE MY750/BW AS 20/4.6 BW EPOXY	CIB	.29	.01	3H	AIR	POTTING
BACON IND IMPREGNANT NO 2	BAC	.27	.01	45M	AIR	ADD POTTING
BAKER POLYURETHANE SYSTEM 65	BAK	.28	.03	8H	AIR	COAT - COAT-POT
BR-626 ONE COMPONENT HEAT CURING EPOXY	BAK	.26	.01	10H	AIR	COAT COAT-POT
BSL 308 A/B AS 4/5 FL W/1% H4-3441 BLACK EPOXY	ACC	.72	.01	16H	AIR	POTTING
C-18F A/B AS 4/5 FL W/1% H4-3441 BLACK EPOXY	CIB	.49	.01	1H	AIR	POTTING
CF 3003 EPOXY FOR HUGHES CONNECTOR 138C32 HOI	HYS	.74	.06	4H	AIR	POTTING
COLAD 984 A/B AS 1/1 WHTE VICK SET EPOXY	HAC	.43	.04	16H	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CCD	.84	.02	24H	AIR	POTTING
CONATHANE EN-11 A/F AS 100/55 BW POLYURETHANE	CON	.27	.01	10H	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.43	.02	24H	AIR	POTTING
CONATHANE EN-11 A/E AS 100/55 BW POLYURETHANE	CON	.38	.01	24H	AIR	POTTING
CONATHANE EN-12 A/E AS 100/55 BW BUTADIENE URETHANE	CON	.43	.01	48H	AIR	POTTING
CONATHANE EN-12 A/E AS 71.3/75 BW BUTADIENE URETHANE	CON	.44	.02	24H	AIR	POTTING
CONATHANE EN-12 A/B AS 100/17.5 BW POLYURETHANE	CON	.78	.02	7D	AIR	POTTING
CONATHANE EN-12 A/B AS 100/17.5 BW POLYURETHANE	CON	.32	.01	20H	AIR	POTTING
CONATHANE EN-9 POLYURETHANE	CON	.39	.00	30M	AIR	POTTING
CONOPTIC EN-30 A/B AS 50/22.75 BW CLEAR URETHANE	CON	.74	.01	16H	AIR	POTTING
CREST 7340/7109 A/B AS 50/22.75 BW CLEAR URETHANE	CPC	.35	.04	2H	154	AIR
C2-4259/3401	HYS	.55	.01	2H	AIR	POTTING
C9-4183/H2-3561 AS 102/44 EPOXY	HYS	.16	.00	4H	AIR	POTTING
C9-4190//H2-3563 AS 102/44 EPOXY	HYS	.50	.03	24H	AIR	POTTING
C9-4198/H2-3561 AS 100/15 BW EPOXY	HYS	.43	.03	3H	AIR	POTTING
C9-4215/H2-3561 AS 100/15 BW BLACK EPOXY	HYS	.38	.09	8H	AIR	POTTING
C9-5340/3426 AS 100/20 BW BLACK EPOXY	HYS	.46	.00	25H	AIR	POTTING
DE 93-500 A/B AS 100/20 BW SILICONE	HYS	.60	.00	8H	AIR	POTTING - ENCAPS
DE 93-500 A/B AS 100/20 BW SILICONE	DCC	.20	.00	2D	AIR	POTTING - ENCAPS
DE 93-500 A/B AS 100/20 BW SILICONE	DCC	.19	.00	2D	AIR	POTTING - ENCAPS
DE 93-500 FM 029159 FEB 79	DCC	.17	.00	2D	AIR	POTTING - ENCAPS
DER 33-500 FM 128101 DEC 78	DCC	.24	.00	1H	AIR	POTTING
DER 33-2/LITTAFAK 100/200 MODIFIED GRAY	DOW	.50	.00	18H	PSL	POTTING
DER 33-2/LITTAFAK 100/200 CARBON BLACK MODIFIED	DOW	.48	.00	18H	PSL	POTTING
DER 33-2/TETA AS 10/1 BW EPOXY	DOW	.54	.00	5H	AIR	POTTING
DER 33-2/LC/HV AS 10C/18 BW EPOXY	DOW	.33	.01	12H	AIR	POTTING
				24d		

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	AFK CODE	ATM	%CVC	CURE TIME	CURE TEMP	ATMOS	APPLICATION
EA 876 EPOXY A/B AS 100/22/0-3% POLYPROPYLENE BEADS BW	U/S/P	.88	.00	2H	121	AIR	POTTING
EA 9309.3 A/B AS 100/22/0-3% POLYPROPYLENE BEADS BW	H/Y/S	.95	.03	2D	25	AIR	POTTING
EA 9309.3 A/B AS 100/22/0-3% POLYPROPYLENE BEADS BW	H/Y/S	.95	.02	4H	71	AIR	POTTING
EA 9559 BROWN EPOXY ECCOFoAM FPH/2-2H POLYURETHANE FOAM	H/Y/S	.80	.09	2H	177	AIR	POTTING
ECCOFoAM FPH/2-4H POLYURETHANE FOAM	E/M/C	.99	.07	8H	60	AIR	FoAM
ECCOFoAM SH 44/FCU 1207/CA1 20 AS 100/1-3 BW BLACK EPOXY	E/M/C	.68	.08	48H	100	AIR	FoAM
EPOCAST N4E-053/CA1 9816	P/A/C	.69	.01	5H	150	AIR	POTTING
EPON 815/V 140 AS 50/50 BW EPOXY	E/P/I	.37	.02	24H	25	AIR	POTTING
EPON 815/V 140 AS 65/35 BW EPOXY	S/H/L	.70	.06	3D	210	AIR	POTTING
EPON 815/V 140 AS 135 AS 5/5/38 BW	S/H/L	.40	.02	3D	25	AIR	POTTING
EPON 825/V 140 AS 166 BW EPOXY	G/S/C	.65	.03	7D	110	AIR	CURE POTTING
EPON 826/V 871/2 AS 100/60/25-4 BW EPOXY	S/H/L	.32	.02	2H	25	AIR	POTTING
EPON 828/EM 308 AS 2/1 BW EPOXY	I/T/I	.64	.01	2H	85	AIR	POTTING
EPON 828/LINDKIDE 8/LMP 30 AS 100/90/1 BW EPOXY	S/H/L	.77	.06	4H	130	AIR	POTTING
EPON 828/LINDKIDE 8/LMP 30 AS 100/90/1 BW EPOXY/SAND	S/H/L	.34	.00	48H	25	AIR	POTTING
EPON 828/VERSAMID 125 AS 50/50 BW EPOXY	S/H/L	.04	.00	48H	70	AIR	POTTING
EPON 828/VERSAMID 125 AS 60/40 BW EPOXY	S/H/L	.79	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 125 AS 65/35 BW EPOXY	S/H/L	.49	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 125 AS 65/35 BW EPOXY	S/H/L	.55	.01	7D	45	AIR	POTTING
EPON 828/VERSAMID 125 AS 96/33 BW EPOXY	S/H/L	.59	.05	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	S/H/L	.80	.03	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 50/50 BW EPOXY	S/H/L	.80	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 60/40 BW EPOXY	S/H/L	.43	.01	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 65/35 BW EPOXY	S/H/L	.30	.00	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 66/33 BW EPOXY	S/H/L	.26	.00	7D	25	AIR	POTTING
EPON 828/VERSAMID 140 AS 70/30 BW EPOXY	S/H/L	.19	.00	7D	25	AIR	POTTING
EPON 828/VERSAMID 140/B40A MICROBALLOONS	S/C/C	.61	.03	4H	124	AIR	POTTING
EPON 828/871/AEP AS 40/60/15-5 BW	S/H/L	.46	.02	16d	65	AIR	POTTING
EPOXY PATCH KIT 56C WHITE EQUAL LENGTHS FR TUBES	H/Y/S	.34	.02	2H	60	AIR	POTTING
EPOXY-71B PRE-MEASURED MIX PKG	E/P/X	.34	.02	30d	81	AIR	POTTING
POXYLITE 6203 A/B AS 2/1 EW EPOXY	E/P/C	.45	.03	4H	121	AIR	POTTING
FLUORINATED ACRYLATE	N/R/L	.12	.00	20	177	AIR	POTTING
FLUORINATED EPOXIDE	N/R/L	.59	.02	20	135	AIR	POTTING
FULTON 404 ACETAL TEFLON 80/20	L/N/P	.52	.01	12H	150	AIR	POTTING
GENEFONY 190/VERSALID 140 AS 3/2 BW AMBER EPOXY	G/M/C	.24	.01	2H	25	AIR	POTTING
HY-MAT 7534 MOLDED GRAPHITE/EPOXY	F/I/B	.47	.00	3H	60	AIR	POTTING
HYDANICIN TC-1-149-LIGHT GRAY EPOXY	W/E/I	.36	.00	16d	135	AIR	POTTING
HYSOL 0025 A/B AS 1/1 BW GLASS FILL THERMOSET POLYESTER	H/Y/S	.97	.03	24H	50	AIR	POTTING
INSULSTRUC P5003-FR2	C/C/L	.56	.02	24H	50	AIR	ENCAPSULANT

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	INFR CODE	STM	SCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
LC A4/ACT BA5 A/B AS 100/6 BW EPOXY ENCAPSULANT	BAC	.12	.00	43H	56	AIR	POTTING
PR 822 EPOXY AS 3/1 Bl	BAC	.16	.03	7H	125	AIR	POTTING
PR 200-16 FOAMED EIV 560	GEC	.03	.02	10H	93	AIR	POTTING
PR 1524 A/B AS 26/100 BW POLYURETHANE	PRC	.82	.09	10H	177	AIR	POTTING
PR 1527 A/B AS 26/100 BW POLYURETHANE	EAC	.92	.10	24H	25	AIR	POTTING
PR 1538 A/B AS 32/100 BW POLYURETHANE	EBC	.97	.02	20H	51	E-O	POTTING
PR 1546L A/B AS 40/100 BW POLYURETHANE THICK BLOCK	PRC	.67	.06	24H	79	AIR	POTTING
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	EBC	.72	.01	94H	82	AIR	POTTING
PR 1564 A/B AS 6.9/100 BW POLYURETHANE	PRC	.74	.02	24H	85	AIR	POTTING
PR 1564 A/B AS 7.7/100 BW POLYURETHANE	PRC	.86	.03	7H	100	E-O	POTTING
PR 1564 A/B AS 7.7/100 BW POLYURETHANE	EBC	.35	.03	24H	25	AIR	POTTING
PR 1570 A/B AS 18/4 BW POLYURETHANE	PRC	.34	.06	16H	82	E-O	POTTING
PR 1574 A/B AS 18/4 BW POLYURETHANE	EBC	.40	.04	24H	82	AIR	POTTING
PR 1574 A/B AS 18/100 BW POLYURETHANE	EAC	.54	.02	24H	82	AIR	POTTING
R-179 CYCLOALIPHATIC EPOXY UNFILLED	CIB	.81	.03	30H	74	AIR	POTTING
R-256 U.5% BN CAT RLD SILICONE LOT 274	GCG	.34	.03	30H	160	AIR	POTTING
RB 8-1338 A/B AS 100/6.5 BW POLYURETHANE	ALL	.51	.04	8H	52	AIR	POTTING
RB 8-1338 A/B AS 55/34 BW POLYURETHANE	ALL	.75	.00	24H	60	E-2	POTTING
RTV 511 0-5% Bl CAT DEVOL AT 160C LOT JN 170	GSC	.39	.05	7D	25	AIR	ADHESIVE
RTV 566 0-1% Bl CAT SILICONE LOT GJ 124	GEC	.13	.02	7D	25	AIR	POTTING
RTV 566 0-17.5% Bl CAT/ZINC-O-SIL	GBC	.12	.02	7D	25	AIR	POTTING
RTV 566 0-2% Bl CAT SILICONE	GEC	.23	.03	7D	25	AIR	POTTING
RTV 566 0-5% Bl CAT SILICONE	GBC	.41	.03	7D	25	AIR	POTTING
RTV 602 SRC AS 4/2 CAT/CABOSIL LOT BM242 BATCH 5	GEC	.18	.001	12D	25	AIR	POTTING-ADH
RTV 615 A/B AS 4/2 Bl DEVOL AT 125C LOT HD183	GSC	.79	.002	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 125C LOT KA210	GSC	.15	.007	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 125C LOT KA210	GSC	.13	.007	7D	25	AIR	ENCAPSULANT
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT BC226	GSC	.19	.003	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT BC226	GSC	.17	.003	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT BC226	GSC	.15	.002	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT BC226	GSC	.11	.001	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT KA210	GSC	.16	.004	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 140C LOT KA210	GSC	.20	.002	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 1	GBC	.16	.008	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 1	GSC	.18	.007	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 1	GSC	.11	.002	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 7	GSC	.15	.005	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 8	GSC	.15	.006	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL LOT CB237 BATCH 9	GSC	.15	.005	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 125C	GSC	.12	.004	7D	25	AIR	POTTING
RTV 615 A/E AS 10/1 Bl DEVOL AT 150C	GSC	.11	.001	7D	25	AIR	POTTING
RTV 615 A/E AS 9/1 Bl DEVOL AT 150C	GSC	.16	.002	7D	25	AIR	POTTING

SECTION 14 -- POTTING COMPOUNDS

MATERIAL	MFR CODE	XMTL	ACTN	CURE TIME	TEMP	CURE STATUS	APPLICATION
RTV 655 A/B AS 10/1 BW DEVOLAT 125C LOT KF084 R9 - 203404 AS 9/1 BW EPOXY	GSC HYS	HHS	:39 :64	:05 :06	7D 1H	230 150	AIR AIR
SCOTCHCAST 221 A/B AS 5/8 BW CASTING POWDER	HHS	HHS	:42 :55	:01 :01	30M 16H	149 145	AIR AIR
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	HHS	HHS	:25	:02	24H	59	E-J AIR
SCOTCHCAST 221 A/B AS 5/8 BW POLYURETHANE	HHS	HHS	:25	:02	24H	59	E-J AIR
SCOTCHCAST 260 A/B AS 1/1 BW EPOXY BROWN	HHS	HHS	:65	:05	4H	750	AIR AIR
SCOTCHCAST 260 A/B AS 1/1 BW EPOXY BROWN	HHS	HHS	:65	:05	4H	750	AIR AIR
SCOTCHCAST 261 A/B AS 2/3 BW BLACK EPOXY	HHS	HHS	:52	:08	4H	130	AIR AIR
SCOTCHCAST 261 A/B AS 2/3 BW BLACK EPOXY	HHS	HHS	:52	:08	4H	130	AIR AIR
SCOTCHCAST 261 A/E AS 2/3 BW GRAY EPOXY	HHS	HHS	:35	:02	12H	100	AIR AIR
SCOTCHCAST 282 A/B AS 2/3 BW SEMI RIGID BLACK EPOXY	HHS	HHS	:49	:10	72H	150	AIR AIR
SCOTCHCAST 282 A/E AS 2/3 BW SEMI RIGID BLACK EPOXY	HHS	HHS	:45	:09	16H	90	AIR AIR
SHUR-LOK SLE 3007 EPOXY - GRAY	SIL	SIL	:32	:00	8H	95	E-J AIR
SOLITHANE 113/300 AS 100/120 BW FORMULA 6	TCC	TCC	:40 :41	:09 :10	1H	625	AIR AIR
SOLITHANE 113/300 AS 100/150 BW FORMULA 7	TCC	TCC	:37	:04	16H	25	AIR AIR
SOLITHANE 113/300 AS 100/150 BW FORMULA 7	TCC	TCC	:37	:04	16H	25	AIR AIR
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	TCC	:69	:09	7D	25	AIR AIR
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	TCC	:69	:09	7D	25	AIR AIR
SOLITHANE 113/300 AS 100/73 BW FORMULA 1	TCC	TCC	:30	:01	24H	50	AIR AIR
SOLITHANE 113/300 AS 100/80 BW FORMULA 2	TCC	TCC	:72	:03	7D	25	AIR AIR
SOLITHANE 113/300 FORMULA 6 OVER PRIMER 919/920	TCC	TCC	:47	:03	7D	25	AIR AIR
SOLITHANE 113/300 CABOSIL MSS/RODAMINE B/T-12/2	TCC	TCC	:42	:01	24H	75	AIR AIR
SOLITHANE 113/300 CABOSIL MSS/T-12/FLUORESCENT DYE	TCC	TCC	:46	:00	7D	25	AIR AIR
SOLITHANE 113/300 LTDZ AS 100/80/1 BW	TCC	TCC	:69	:00	1H	50	AIR AIR
SOLITHANE 113/300 LTDZ AS 100/80/1 BW	TCC	TCC	:69	:00	1H	50	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:37	:01	4H	60	AIR AIR
SOLITHANE 113/300 TRALER-TECH T-704/80	SIL	SIL	:14	:02	7D	25	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:36	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
SOLITHANE 113/300 TIPA/ALUNINA T-12/1 DROP BW	TCC	TCC	:44	:02	7D	60	AIR AIR
STYCAST CPC-41 A/B AS 5/6 BW POLYURETHANE FOAM	EMC	EMC	:74	:09	16H	25	AIR AIR
STYCAST CPC-1090-S1/241V AS 100/23 BW EPOXY FOAM	EMC	EMC	:74	:09	16H	25	AIR AIR
STYCAST 1090/11 AS 100/12 BW EPOXY FOAM	EMC	EMC	:49	:06	6H	190	AIR FOAM
STYCAST 1095/11 AS 100/12 BW EPOXY FOAM	EMC	EMC	:38	:04	3H	150	AIR FOAM
STYCAST 1095/9 AS 100/9 BW BLACK EPOXY FOAM	EMC	EMC	:72	:07	16H	25	AIR FOAM
STYCAST 1467/CAT 9 AS 100/7 BW EPOXY	EMC	EMC	:14	:00	1d	77	AIR FOAM
STYCAST 2057/CAT 9 AS 100/6 BW EPOXY	EMC	EMC	:49	:06	24H	24H	POTTING
STYCAST 2057/CAT 9 AS 100/6 BW EPOXY	EMC	EMC	:38	:04	3H	150	AIR POTTING
STYCAST 2651/CAT 9 EPOXY	EMC	EMC	:74	:01	24H	25	AIR POTTING
STYCAST 2651/CAT 9 EPOXY	EMC	EMC	:37	:00	3H	150	AIR POTTING
STYCAST 2662/CAT 9 EPOXY	EMC	EMC	:74	:01	24H	25	AIR POTTING
STYCAST 2662/CAT 9 EPOXY	EMC	EMC	:37	:00	3H	150	AIR POTTING
STYCAST 2762/CAT 9 EPOXY	EMC	EMC	:74	:01	24H	25	AIR POTTING
STYCAST 2762/CAT 9 EPOXY	EMC	EMC	:37	:00	3H	150	AIR POTTING

SECTION 14 -- PUTTING COMPOUNDS

MATERIAL	HPR CODE	XTHL	XCVCM	CURE TIME	CURE TEMP	CURE STATUS	APPLICATION
STYCAST 2850 FT/2 AS 100/3 BW EPOXY	EMC	.25	.01	20H	70	AIR	PUTTING
STYCAST 2850 FT/11 AS 100/3 BW BLACK EPOXY	EMC	.49	.01	2H	60	AIR	PUTTING
STYCAST 2850 FT/11 AS 20/1 BW BLACK EPOXY	EMC	.47	.01	30M	120	AIR	PUTTING
STYCAST 2850 RT/24LV AS 100/3/1-5 BW BLUE EPOXY	EMC	.40	.00	4H	200	AIR	PUTTING
STYCAST 2850 RT/24LV AS 25/1 BW BLUE EPOXY	EMC	.55	.02	24H	60	AIR	PUTTING
STYCAST 2850 KT/24LV AS 25/1 BW BLUE EPOXY	EMC	.34	.01	16H	65	AIR	PUTTING
STYCAST ONE COMP BLUE THERM COND EPOXY	EMC	.29	.01	24H	105	AIR	PUTTING
STYCAST 3050/11/B40A MICROBALLOONS	GSC	.75	.01	72H	25	AIR	PUTTING
TRUCAST 111/901 AS 100/3-4 BW	FEN	.36	.01	90M	126	AIR	PUTTING
TRUCAST 111M/TREASURE 901 EPOXY	FEN	.60	.01	24H	25	AIR	PUTTING
TJ - 0590/XHD-J158 AS 1/1 BW GREEN POLYURETHANE	HYS	.85	.01	3H	60	AIR	PUTTING
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE	FPI	.87	.02	4H	225	AIR	PUTTING
URALANE 5753LV A/B AS 1/5 BW POLYURETHANE/PRIMER PR1	FPI	.69	.01	7D	25	AIR	PUTTING
VARY-FLEX EPOXY EC1YAMIDE	SIP	.64	.01	14D	25	AIR	PUTTING
XR-5166 A/B AS 2/3 BW FLEXIBLE BLACK EPOXY	HMM	.51	.004	12H	AIR	PUTTING	PUTTING
XR-0021/XHD-0165 AS 1/1 BW BLACK POLYURETHANE	HYS	.87	.01	6H	25	AIR	PUTTING
XUS-0050 A/B AS 10C/36 BW	HYS	.83	.01	4H	60	AIR	PUTTING

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	MFN CODE	XTHL	XCVCM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
AP-E-312-11 ETHYLENE PROPYLENE DERIVATIVE	TRW	.60	.98	48H	121	AIR	SEAL
AMS 3345 SILICONE RUBBER	AMS	.39	.09	24H	250	AIR	SEAL
BTR RUBBER HD222-22-2 IN ALUMINUM SAND WICH	LOR	.28	.91	16H	82	AIR	DADEPA
CB 4012 FLUOROSILICONE COATED DACRON FABRIC	CHR	.45	.99	24H	177	AIR	GASKET SEAL
CHO-SEAL 1285 LIQUID COND SILICONE	CHO	.12	.01	24H	175	AIR	ELASTOMER
CHO-THERM 1671 THERM COND SHEET - WHITE SILICONE	CHR	.04	.01	24H	204	AIR	DADEPA
COHRLASTIC RUBBER E10470 SILICONE SPONGE	CHR	.10	.95	24H	182	AIR	DADEPA
COHRLASTIC E10460 LIQUID SILICONE SPONGE - SOFT	CHR	.12	.01	100D	190	AIR	DADEPA
DC 6-1104 LIQUID SILICONE SPONGE	CCC	.16	.96	24H	25	AIR	SEALANT
DC 6-1104 LOT FMC99313	CCC	.20	.93	7D	25	AIR	SEALANT
DC 6-1104 LOT GAC83347	CCC	.15	.93	7D	25	AIR	SEALANT
DC 6-1104 LOT GAC83348	CCC	.14	.92	7D	25	AIR	SEALANT
DC 6-1104 LOT GAC93568	CCC	.33	.93	24H	25	AIR	SEALANT
DC 6-1104 1/16 V-1532 BLUE FERRO DYE	CCC	.29	.91	24H	25	AIR	SEALANT
DC 6-1104 1/16 V-1536 YELLOW FERRO DYE	CCC	.21	.91	24H	25	AIR	SEALANT
DC 6-1104 1/16 V-1540 BLACK FERRO DYE	CCC	.42	.97	24H	25	AIR	SEALANT
DC 6-1104 1/16 V-1747 BLACK FERRO DYE	CCC	.13	.92	45D	25	AIR	SEALANT
DC 6-1104 CV LOT FM119336	CCC	.09	.91	7D	25	AIR	SEALANT
DC 6-1106 4/B AS 10/1 BW SILICONE PEROXIDE CAT DI CUP 40°C	CCC	.15	.90	15H	160	AIR	ELASTOMER
DC 6-1106 4/B AS 10/1 BW SILICONE ELASTOMER PEROXIDE ADDITIVES BLUE CONNECTOR INSUL	CCC	.08	.90	6H	177	AIR	ELASTOMER
DE 100 SILICONE RUBBER GE SE 565 BASE	DEC	.05	.02	4H	175	E-4	SILICONE
EC COUB PERFLUOROELASTOMER	EMC	.24	.10	30H	204	AIR	PERFLUOROELASTOMER
ED 4837-90 PERFLUOROELASTOMER	DUP	.51	.09	7D	25	AIR	PERFLUOROELASTOMER
FLUOROSILICONE GASKET WHITE THREE PART SYSTEM	DUP	.41	.09	8H	200	AIR	PERFLUOROELASTOMER
FLURAN P5000 BLACK FLUORELASTOMER TUBING	BEN	.16	.03				
FLURAN P5000 VITON A RED TUBING	NPC	.53	.00				
GORE-TEX CARBON LOFD EXPANDED TEFILON - GRAY	GOR	.05	.00				
GORE-TEX DOPED TiO ₂ /CARBON AS 9/1 BW - GRAY/WHITE	GOR	.18	.03				
GORE-TEX HOLLOW LOFD WITH CARBON - BLACK	GOR	.10	.01				
HS 50/VARO/RUBBER ADDITIVES BLUE CONNECTOR INSUL	DCC	.12	.00	7.5H	255	AIR	PERFLUOROELASTOMER
HS 50/VARO/RUBBER ADDITIVES BLUE CONNECTOR INSUL	DCC	.13	.01	4H	204	AIR	PERFLUOROELASTOMER
HYTREL 4055 POLYESTER/ANTI-OXIDANT	DUP	.22	.08	8.5H	269	AIR	PERFLUOROELASTOMER
IMPALENE TUBING STABILIZED POLYPROPYLENE	IMP	.29	.04				
INTERFACIAL SEAL SILICONE UC-K-1314	UCC	.21	.06	26H	125	AIR	SEAL
KALREZ 1050 PERFLUOROELASTOMER	DUP	.44	.00	30	10	24H	DADEPA
KALREZ 3018 PERFLUOROELASTOMER	DUP	.40	.00	30	10	24H	DADEPA
KLEKHELL SILICONE SPONGE RUBBER	KRC	.23	.00	96H	177	AIR	GASKET
KOSITES 1028 BLACK FLUOREL SPONGE RUBBER	KOS	.33	.00	96H	125	AIR	CUSHION
KOSITES 1028 SPONGE RUBBER	KOS	.21	.00	96H	100	AIR	ELASTOMER
KOSITES 1059 FLUOROCARBON ELASTOMER	KOS	.24	.00	96H	100	AIR	ELASTOMER
KOSITES 1079K FLUOREL FLUOROCARBON ELASTOMER	KOS	.04	.00	96H	100	AIR	ELASTOMER
MS-20108 O RING - VITON A	AM	.07	.03	8H	200	AIR	O RING
MS-30102 O RING - VITON A	AM	.07	.03	8H	200	AIR	O RING
PARKER O-RING L-677-7 RED FLUOROSILICONE	ESC						

SECTION 15 -- RUBBERS ELASTOMERS

MATERIAL	HFR CODE	XTHL	XCVCM	CURE TIME	CURE ATMOS	TEMP	APPLICATION
PARKER O-RING L-806-80 BLUE FLUOROSILICONE	PSC	.32	.03				O-RING
PARKER O-RING S-383-70 RED SILICONE	PSC	.17	.01				O-RING
PARKER O-RING S-455-70 RED SILICONE	PSC	.18	.02				O-RING
PARKER O-RING S-641-5 SILICONE	PSC	.29	.09				O-RING
PARKER O-RING V-747-75 VITON DUP E60C FLUOROCARBON	PSC	.19					O-RING
PARKER O-RING 77-545-V VITON A	PSC	.35	.02				O-RING
PARKER SEAL S 1808-50 GREEN SILICONE	PSC	.11	.02	4H	188	AIR	SEAL
PR 1710 POLYSULFIDE SEALANT	PRC	.66	.04	24H	249	AIR	SEALANT
PP 11165 SILICONE O-RING	PPR	.30	.04	2H	121	AIR	O-RING
RK 423 SILICONE RUBBER	RRC	.11	.03	24H	232	AIR	SEAL
RTV 136 SILICONE	GEC	.25	.03	16H	238	AIR	SILICONE
SE 456/TIS-50 SILICONE - TAN	GEC	.19	.07	4H	204	AIR	ROD END
SE 459/TIS-50 SILICONE - TAN	GEC	.22	.07	3H	238	AIR	ROD END
SE 5211 U LOW TEMP SILICONE	GEC	.17	.02	4H	249	AIR	GASKET
SE 557/VAROX AS 100/0.3 BW GRAY SILICONE	GEC	.08	.02	4H	188	AIR	SEAL
SILASTIC 35	DCC	.14	.06	16H	249	AIR	SILICONE
SILASTIC 675 SILICONE	DCC	.41	.04	24H	116	PSI	SEAL-GASKET
SILASTIC 69-219 LOT EU 103007	DCC	.92	.09	16H	250	AIR	COATING
SILASTIC 75 SILICONE	DCC	.29	.09	16H	204	AIR	VALVE SEAT
SILASTIC 916 SILICONE RUBBER MIL 22-R-765 CLASS 2 GRADE 50 - GRAY	DCC	.40	.06	24H	249	AIR	SILICONE
SILICONE RUBBER UNION CARBIDE 16254 GRAY SHEET	FCC	.10	.09	16H	200	AIR	GASKET
SILICONE RUBBER 16254 GRAY SHEET	FCC	.40	.06	24H	232	AIR	SILICONE
SIL 127 4/5 AS 9/1 BW ALD SILICONE	FCC	.14	.09	16H	232	AIR	CUSHION
SILITHANE 113/300 AS 100/80 BW FORMULA 2	MAC	.49	.04	7D	25	AIR	SEALANT
SOLITHANE 113/300 CABOSIL M5/CARBOLAC 1	TCC	.36	.01	7D	25	AIR	DAMPING
SPONGE RUBBER SILICONEAMS 3195 0.031# CU IN 1	SRCC	.43	.03	24H	177	AIR	SEALANT
SR 2702-275 VITON PER MIL R83248 TYPE 2 CLASS 1	STI	.07	.003	24H			DAMPER
SR 2704-75 VITON E-60	STI	.16	.00	24H			DUST SEAL
SR 634-70 BUTYL C FING STILLMAN RUBBER	SIS	.93	.00	24H	260	AIR	DEAL
TECKNIT 86-10005 BLACK RUBBER GASKET/Q RING	TEC	.09	.04	24H			O RING
TERMATICOTE 250 TEEFNAJL JOINT CPND	THR	.09	.02	24H	175	AIR	GASKET/O RING
TOYOTA SEAL 1/2 AS 1/1 BV	YAR	.84	.00	24H	25	AIR	SEALANT
TOYODING SILICONE-KEL GRADE 60 CL2 SPEC ZZR765	RET	.09	.04	24H	166	AIR	AIR SEALANT
V-7000/5 BENZOYL PERCIDE AS 100/1 B	RES	.47	.01	10H	93	AIR	TUBE TUBING
VALCOR O RING - RTV 75	DCC	.25	.02				SEAL
VALTON A O RING NAS 1593-012	DUP	.21	.02				O RING
VALTON B DUPONT	AGI	.89	.00				GROUT
VALTON B-525 FOAM RUBBER BLACK CLOSED CELL	DUP	.89	.04	16H	204	AIR	SEAL
VALTON C HOSE IMPREGNATED JACKON DUPONT 84-001	DUP	.39	.03				TRAIL AMPLER
WASHER POLYPHENYLENE SULFIDE 40% GLASS FILLED	DUP	.85	.09				TRAILING
	THE	.08	.01				WASHER

SECTION 16 -- TAPES

MATERIAL	L.F.# CODE	XITM CODE	XCVN TIME	CUBE TEMP	STATUS	APPLICATION
PASCAL 715 CHROME METALLIZED MILK/ACRYLIC ADH/R	APF EML	.36	.03 16H	65	AIR	TAP 2-1 LM
FLUOROCLAS TAPE 404 ALUM FOIL	GMS	.83	.03		TAPE	
FLUOROCLAS TAPE 234-14 KAPTON/ACRYLIC ADH/F	GTS	.27	.01		TAPE	
G 400201 TAPE ALUMINIZED TERPOLY/Y1966 ADH/F	GTS	.75			TAPE	
G 400600 TAPE ALUMINIZED KAPTON/ACRYLIC ADH/F	GTS	.94			TAPE	
GT 100/100 TAPE MYLAB COMPOSITE AS MYLAB/GT 100/MYLAK	GTS	.25			TAPE	-COMPOSITE
KAPTON II FILM 4- ALUMINIZED W/MM 467 ADH/F	GMM	.80			TAPE	
LAMART TAPE 892 ALUM FOIL	LAM	.21			TAPE	
HIN TAPE X-1181 COOPER FOIL/ACRYLIC ADH/F (ECC4868P)	HIN	.31			TAPE	
HIN TAPE X-1205 EMFOSS AL/ACRYLIC ADH/F	HIN	.38			TAPE	
HIN TAPE X-1267 EMOSS AL/ACRYLIC ADH/F BAKE ON SCREEN	HIN	.20			TAPE	
HIN TAPE Y-8437 ALUM/MYLAK/ACH ADH/F (FORMER Y-9360)	HIN	.68			TAPE	
HIN TAPE Y-9224 TEFLON FEP/ACRYLIC ADH/R	HIN	.18			TAPE	
HIN TAPE Y-9239 ALUM FOIL/ACRYLIC ADH/R TYPE 2-2 UAL	HIN	.80			TAPE	
HIN TAPE Y-9339 ALUM/MYLAK/ACRYLIC ADH/R TYPE 3-3 UAL	HIN	.20			TAPE	
HIN TAPE Y-9360 ALUM/MYLAK/ACRYLIC ADH/R	HIN	.54			TAPE	
HIN TAPE Y-9440 ISCRNAL/ACRYLIC TRANSFER FILM 2 MIL/F	HIN	.85			TRANSFER TAPE	
HIN TAPE Y-9456 ISCRNAL/ACRYLIC TRANSFER FILM 2 MIL/F	HIN	.81			TRANSFER TAPE	
HIN TAPE 415 SLOCHEAR FILM/2 SIDE ACRYLIC ADH/F	HIN	.91			2 SIDE TAPE	
HIN TAPE 420 5 MIL LEAD FOIL/SUBER BASE ADH/F	HIN	.09			TAPE	
HIN TAPE 422 LEAD FOIL/ACRYLIC ADH/F	HIN	.09			TAPE	
HIN TAPE 425 ALUM FOIL/SYNTHETIC ADH/F	HIN	.24			TAPE	
HIN TAPE 426 TRANSFER FILM ACRYLIC FOIL SANDWICH	HIN	.20			TAPE	
HIN TAPE 427 3 MIL ALUM FOIL ACRYLIC ADH/F	HIN	.88			TAPE	
HIN TAPE 428 5 MIL POLYESTER INBED ACRYLIC ADH/F	HIN	.83			TAPE	
HIN TAPE 5241 KAPTON/3 SILICONE ADH/F	HIN	.56			TAPE	
HIN TAPE 61 TEFLON TEE/THERMOSET SILICONE ADH/R	HIN	.58			TAPE	
HIN TAPE 91 TEFLON TEE/THERMOSET SILICONE ADH/R	HIN	.14			TAPE	
HIN TAPE 63 TEFLON TEE/THERMOSET ACRYLIC ADH/R	HIN	.33			TAPE	
HIN TAPE 65 TEFLON TEE/ACRYLIC ADH/R	HIN	.33			TAPE	
HIN TAPE 70 SILICONE RUBBER TAPE/SILICONE ADH/R	HIN	.40			TAPE	
HIN TAPE 72 GLASS CLOTH/ACRYLIC ADH/F	HIN	.54			TAPE	
HIN TAPE 850 GLUMINIZED POLYESTER/ACRYLIC ADH/R	HIN	.68			TAPE	
HIN TAPE 850 BLACK NYLAR/ACRYLIC ADH/R	HIN	.77			TAPE	
HIN TAPE 852 ALUM/BLACK TRANSFER POLYESTER/ACRYLIC ADH/F	HIN	.61			TAPE	
MYSTIK TAPE 40531C ALUM NYLAR FILM/ACRYLIC ADH/R	BCH	.79			TAPE	
MYSTIK TAPE 6401 PCLYESTER FILM/ACRYLIC ADH/F	BCH	.41			TAPE	
MYSTIK TAPE 7341 PCLYESTER FILM/ACRYLIC ADH/R	BCH	.51			TAPE	
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCH	.23			TAPE	
MYSTIK TAPE 7361 KAPTON/SILICONE ADH/F	BCH	.19			TAPE	
MYSTIK TAPE 7362 KAPTON/SILICONE ADH/F	BCH	.65			TAPE	
MYSTIK TAPE 7367 KAPTON/ACRYLIC ADH/F	BCH	.63			TAPE	
MYSTIK TAPE 7367 KAPTON/ACRYLIC ADH/F	BCH	.69			TAPE	
MYSTIK TAPE 7375 TIDLAB/ACRYLIC ADH/R WHITE	BCH	.65			TAPE	
MYSTIK TAPE 7420 CC2PER FOIL/ACRYLIC ADH/R	BCH	.34			TAPE	
MYSTIK TAPE 7430 4-5 MIL LEAD FOIL/RUBBER ADH/F	BCH	.21			TAPE	
MYSTIK TAPE 7432 ALUM FOIL/ACRYLIC ADH/R	BCH	.24			TAPE	
MYSTIK TAPE 7433 ALUM FOIL/ACRYLIC ADH/R	BCH	.25			TAPE	
MYSTIK TAPE 7505 TEFLON/SILICONE ADH/F PER	BCH	.21			TAPE	
PERHAZEL TAPE EE-740 GLASS CLOTH/ACRYLIC ADH/R	BCH	.03			TAPE	

SECTION 16 -- TAPES

MATERIAL	MPH CODE	STML CODE	XCVCM	CURE TIME	CURE TEMP	ADHS	APPLICATION
PERMACEL TAPE EE-7390 NYLAR FILM/ACRYLIC ADH/R	EEH	EEH	.71	.92			
PERMACEL TAPE 213 GLASS CLOTH/ACRYLIC ADH/F	PER	PER	.47	.92			TAPE
PERMACEL TAPE 224 KAPTON/ACRYLIC ADH/F	PER	PER	.69	.04			TAPE
PERMACEL TAPE 422 TEFLON/SILICONE ADH/R	PER	PER	.25	.09			TAPE
SB 1020 GLASS REINFORCED SILICONE RUBBER TAPE	MOX	MOX	.25	.05			TAPE
STRIPON-STICK 2004 RED SILICONE SPONGE/ACRYLIC ADH/F	CHR	CHR	.39	.09			TAPE
TEMP-R-TAPE C-400 TEFILON FEP/SILICONE ADH/R	CHR	CHR	.27	.09			TAPE
TEMP-R-TAPE G-550 FIBERGLASS/ACRYLIC ADH/F	CHR	CHR	.30	.09			TAPE
TEMP-R-TAPE G-557 SILICONE COAT FIBERGLASS/SIL ADH/F	CHR	CHR	.14	.05			TAPE
TEMP-R-TAPE G-569 FIBERGLASS/ACRYLIC ADH/F	CHR	CHR	.32	.15			TAPE
TEMP-R-TAPE HN-225 TEFILON TFE/SILICONE ADH/P	CHR	CHR	.22	.15			TAPE
TEMP-R-TAPE HN-430 TEFILON TFE/ACRYLIC ADH/P	CHR	CHR	.14	.02			TAPE
TEMP-R-TAPE HN-650 TEFILON TFE/SILICON ADH/F	CHR	CHR	.14	.02			TAPE
TEMP-R-TAPE HN-650 TEFILON TFE/SILICONE ADH/R	CHR	CHR	.19	.07			TAPE
TEMP-R-TAPE K-102 KAPTON/ACRYLIC ADH/F	CHR	CHR	.19	.08			TAPE
TEMP-R-TAPE K-102 KAPTON/ACRYLIC ADH/F	CHR	CHR	.65	.01			TAPE
TEMP-R-TAPE N-60 TRANSPARENT POLYESTER/ACRYLIC ADH/F	CHR	CHR	.78	.01			TAPE
TEMP-R-TAPE N-69 NYLAR FILM/2 SIDE ACRYLIC ADH/F	CHR	CHR	.48	.04			TAPE
TEMP-R-TAPE N-706 NYLAR FILM/BIGE POLYESTER/FR ACRYLIC ADH/F	CHR	CHR	.63	.02			2-SIDED TAPE
TEMP-R-TAPE N-97 NYLAR/ACRYLIC ADH/YELLOW/F	CHR	CHR	.41	.04			TAPE
TEMP-R-TAPE N-99 NYLAR/ACRYLIC ADH/YELLOW/F	CHR	CHR	.52	.07			TAPE
			.37	.05			

SECTION 17 -- THERMAL GREASES

MATERIAL	MFR CODE	%TML	%CVM	CURE TIME	CURE TEMP	ATMOS	APPLICATION
CHOMERICS 4220 SILVER FILLED SILICONE GREASE	CHO	.57	.10			COLD GREASE	
C5-1102 SILICONE GREASE	DCC	.05	.02			THERMAL GREASE	
ES-COTHERM TC-4 FILLED HEAT SINK GREASE	EMC	.54	.05			THERM GREASE	
ES-COTHERM TC-5 FILLED HEAT SINK GREASE	EMC	.50	.10			THERM GREASE	
G-641 INSULGALAS FILLED SILICONE GREASE	GBC	.16	.07			THERMAL GREASE	
G-9042 THERMAL CONDUCTIVE GREASE - WHITE SILICONE	HCG	.05	.00			THERMAL GREASE	
G-9052 ELEC CONDUCTIVE GREASE - BLACK SILICONE	HCG	.05	.01			COLD GREASE	

SECTION 18 -- MISCELLANEOUS

MATERIAL	MFR CODE	XMTL	XCVCH	CURE TIME	CURE TEMP	ADHS	APPLICATION
ALUMINIZED NYLAR 100M42	STC	222	.13	.01			
ARMSTRONG 4-31 A/BAS 6/4 BW EPOXY	APC	46	.09	2H	60	AIR	REFLECTOR COND FILM ADHESIVE
B-010 UNBONDED B FIBER	JOM	.56	.01				INSULATION
BORON NITRIDE - LEAT SINK WASHER	UCC	.21	.00	1 H	482	AIR	MASHER
CROFON 1 COND/JACKET YELLOW CODE	DUP	.12	.00				FIBER OPTIC
CROFON 1 COND/JACKET CLEAR NO JACKET	DUP	.37	.08				FIBER OPTIC
CROFON 1 YEL LOW CCLED JACKET ONLY	DUP	.23	.05				FIBER OPTIC
CROFON 3 COND/JACKET GREEN CODE	DUP	.26	.03				FIBER OPTIC
CROFON 4 COND/JACKET PURPLE CODE	DUP	.27	.06				FIBER OPTIC
CROFON 5 COND/JACKET BLUE CODE	DUP	.23	.04				FIBER OPTIC
DC 2106 SILICONE RESIN	DCC	.46	.92				SILICONE
DC 2100 UN CURED MONOMER LOT E2467-133	DCC	.06	.92				DAKIN FLUID
DIXNA - FIBER OPTIC FIBER FELT	JOM	.93	.01				FELT
E-COMOLD 66A EPOXY - MOLD AT 135C AND 420 PSI	JOM	.49	.05	1H	116	AIR	STRUCTURAL
E-COMOLD AN 74 METHANOL WASH - 3	EMC	.51	.01	2H	100	AIR	ADHESIVE
EPON 828 / VER SAMID 125/RD AS 100/21/13 BW EPOXY	EMC	.70	.01	4H	71	AIR	ADHESIVE
EPON 929 EPOXY	SHL	.69	.00	1H	149	AIR	ADHESIVE
FIBER OPTIC CABLE CC-190	BRX	.27	.07				FIBER OPTIC
FIBER 60-PURE FIBERGLASS BATTING	PIA	.28					INSULATION
FIBER MAGNET WIRE COATING	PIA	.69	.01				WIRE COATING
F5 - 1100 CONTROLLED VOLATILITY FLUID	222	.23					SILICONE FLUID
F5 - 1105 CONTROLLED VOLATILITY FLUID	DCC	.07					SILICONE FLUID
F6 - 1107 CONTROLLED VOLATILITY FLUID	DCC	.07					SILICONE FLUID
GPR/TUBE GLASS/POLYESTER TUFF	DCC	.11					STRUCTURAL
HEATER KAFTON TS C-9485	222	.68					HEATERS
HIGH K-707-L-9 INSULATION BLANKET MULTILAYER	POL	.54					DISPL TRIC
LAMINATE REZOLITE 2200 MAGNET FLEXIBLE STRIP EGO-1016	STIS	.58					INSULATION
MICROLITE FELT AA C. 6 1/2 FT W/SILICONE BIND-CENTER	GEC	.7					LAD MALE
MIN-X TYPE SS HT INSULATION	NMC	.91					DAK HOLD DOWN
MIN-X 1301 HT INSULATION	222	.37					INSULATION
NN TAPE ALUM/NYLON/ALUM/ACRYLIC ADH/R (Y-9360)	JOM	.20	.00				INSULATION
NS 224 MH5 MOLD RELEASE/ON FOIL	JAB	.51	.06				TAPE
NICKEL BLACK/ELECTROLESS PLATED ALUMINUM	AST	.79	.08				BULD RELEASE
NICKEL DULL PLATED ALUMINUM	GSC	.32	.04				COATING
NICKEL GLOSSY PLATED ALUMINUM	GSC	.15					COATING
RTV 602/SRC 02 AS 0-25% CAT DEVOL BATCH 19	GSC	.128	.05				COATING
RTV 602/SRC 02 AS 0-25% CAT DEVOL BATCH 15	GSC	.28	.01				PUTTING
RTV 602/SRC 05 AS 0-25% CAT DEVOL BATCH 20	GSC	.39	.02				PUTTING
SAH SILICONE RESIN RIGIDIZED W/SILICA PIBERS	GSC	.57	.02				PUTTING
SCOTCHMATE POLYESTER FASTENER HOOK/NAP	GEV	.20	.02				ABLA TIVE
SE 5403 U D10-10 FASTENER GRAY ANODIZE	GEC	.19	.02				FASTENER
SE 5403 U D10-10 FASTENER GRAY ANODIZE	GEC	.02	.02				SILICONE

SECTION 18 -- MISCELLANEOUS

MATERIAL	MFR CODE	XFM	ACVCM	CURE TIME	CURE TEMP	ATDS	APPLICATION
TECKFIELD 45-09810 UNFILLED STAINLESS	TEC	.91	.90	48H	121	E-5	PELV
TECKKNIT 82-12451 SILICONE SPONGE #/SCREIN	TEC	.92	.92	48H	121	E-5	DADEK
TECKKNIT 82-124571/82-124571 COMPOSITE	TEC	.95	.91				DADEK
THEERMA PLATE 43-03-4 INSULATOR	AEC	.98	.93				INSULATOR
VELCRO HI-TENSILE HOOKS STAINLESS STEEL	THE	.92	.91				PASTERER
VELCRO MID-TEMP FASTENER NCMEX/POLYIMIDE	VEL	.90	.90				PASTERER
VELCRO MID-TEMP FASTENER NOHEX/POLYIMIDE/EXTRACTED	VEL	.92	.90				PASTERER
VELCRO 100 POLYESTER HOOK AND LOOP	VEL	.94	.92				PASTERER
VELCRO 100-005-012-0199AB/100-101-012-0199AB HEL	VEL	.79	.92				PASTERER
VELCRO 1000-031-012-0199/1000-009-012-0199 WHITE	VEL	.49	.95				PASTERER
XR PERFLUOROSULFONIC ACID PRECURSOR TUBING	DUP	.03	.02				TUBING

APPENDIX

CODE LIST OF MANUFACTURERS

CODE LIST OF MANUFACTURERS

AAC	Ablestick Adhesive Company Abletech Division Gardena, California
AAI	Anchor Alloys, Incorporated Brooklyn, New York
AAP	Advanced Absorber Products Amesbury, Massachusetts
AAT	Arno Adhesive Tapes, Incorporated Michigan City, Indiana
ABC	Andrew Brown Company Los Angeles, California
ABI	Airborn, Incorporated Addison, Texas
ABR	Amphenol Corporation Division Bunker Ramo Scarborough, Ontario, Canada
ACA	American Chain & Cable Company Waterbury, Connecticut
ACC	American Cyanamid Company Bloomingdale Department Havre de Grace, Maryland Formica Corp. Cincinnati, Ohio Plastics & Resin Division Wallingford, Connecticut
ACD	Allied Chemical & Dye Company Edgewater, New Jersey (Celetex Division)
ACH	Acheson Colloids Port Huron, Michigan (Division of Acheson Industries, Incorporated)

ACL	Armstrong Cork Company Lancaster, Pennsylvania
ACM	Allied Chemical Corporation Mesa Products Los Angeles, California
ACO	Advanced Coatings & Chemicals Temple City, California
ACP	ACPO Incorporated Florham Park, New Jersey
ACR	ACME Resin Corporation Forest Park, Illinois
ACT	Acton Research Company Acton, Massachusetts
ADC	Applied Design Company, Incorporated Tanawanda, New York
ADF	American Durafilm Company, Incorporated Newton Lower Falls, Massachusetts
ADL	Arthur D. Little, Incorporated Cambridge, Massachusetts
AEC	Adhesive Engineering Company San Carlos, California
AEL	Appleton Electric Company Chicago, Illinois
AEW	Alpha Wire Corporation Linden, New Jersey
AFP	Applied Fibers & Plastics Morristown, New Jersey
AGI	AGI Rubber Company Bridgeport, Connecticut
AIR	Atlantic India Rubber Works Chicago, Illinois
ALL	Allaco Products, Incorporated Westbury, New York

ALR	Allied Resin Corporation East Weymouth, Massachusetts
AMA	American Aerosols Incorporated Holland, Michigan
AMC	Amicon Corporation Lexington, Massachusetts
AME	AMETEK Haveg Division Wilmington, Delaware
AMH	American Hoechst Somerville, New Jersey
AMI	American Microwave Industries Waltham, Massachusetts
AMP	AMP Incorporated Harrisburg, Pennsylvania
AMR	AMR Industries Incorporated Canoga Park, California
AMS	American Metaseal Company Carlstadt, New Jersey
ANS	Arthur Ansley Manufacturing Company Perkasi, Pennsylvania
AOC	AMOCO Chemicals Corporation Chicago, Illinois
AOP	American Optical Company Southbridge, Massachusetts
APC	Armstrong Products Company, Incorporated Warsaw, Indiana
APP	Avery International Fasson Industrial Division Painesville, Ohio Avery Label Monrovia, California

API	AREMCO Products Incorporated Ossining, New York
APL	Applied Physics Laboratory Johns Hopkins University Laurel, Maryland
APP	Applied Plastics Company El Segundo, California
APS	Advanced Process Supply Company Chicago, Illinois
APX	APEX Mills Incorporated New York, New York
ARC	Alloys & Research Company Cleveland, Ohio
ARM	John L. Armitage & Company Newark, New Jersey
ARP	American Reinforced Plastics Company Los Angeles, California
ART	Artus Corporation Englewood, New Jersey
AST	Astro Chemical Company Schenectady, New York
ATC	American Thread Company New York, New York
ATL	Atlantis Laminates Franklin, New Hampshire
ATP	Atlas Plastics Buffalo, New York
AUC	Angelica Uniform Company St. Louis, Missouri
AUG	AUGAT Incorporated Attleboro, Massachusetts

AUI	Automation Industries, Incorporated Danbury, Connecticut
AWC	Alpha Wire Company Elizabeth, New Jersey
BAC	Bacon Industries, Incorporated Watertown, Massachusetts
BAI	Barry Isolator Company Watertown, Massachusetts
BAK	Baker Castor Oil Company Bayonne, New Jersey
BAL	Ball Chemical Company Glenshaw, Pennsylvania
BAP	BEL-ART Products Pequannock, New Jersey
BAR	Barry Wright Barry Division Watertown, Massachusetts
BAX	Baxender Chemicals Europe
BAY	Bay Associates Palo Alto, California
BCC	BASF Colors and Chemicals, Incorporated New York, New York
BCI	B & C Insulation Products Iselin, New Jersey
BCL	Berser Chemicals, Limited New Castle, England
BCM	The Borden Company New York, New York
	The Borden Chemical Company Philadelphia, Pennsylvania
	Mystik Tape Northfield, Illinois

BDC	Brod-Dugan Company St. Louis, Missouri
BEE	Bee Chemical Company Lansing, Illinois
BEH	Berkshire Hathaway, Incorporated New Bedford, Massachusetts
BEL	Balsa Ecuador Lumber Corporation New York, New York
BEN	The Bendix Corporation Teterbord, New Jersey
BER	The Berquist Company Minneapolis, Minnesota
BFG	B. F. Goodrich Chemical Company Cleveland, Ohio
BGG	The Biggs Company Santa Monica, California
BHM	Bentley-Harris Manufacturing Company Lionville, Pennsylvania
BIC	British Insulated Callender's Cables, Limited Liverpool, England
BID	James G. Biddle Company Plymouth Meeting, Pennsylvania
BIS	Bishop Electric Cedar Grove, New Jersey
BIV	BIVAR, Incorporated Santa Ana, California
BIW	Boston Insulated Wire and Cable Company Dorchester, Massachusetts
BLA	H. L. Blachford, Incorporated Troy, Michigan
BLD	Belden Manufacturing, Company Chicago, Illinois

BLH	BLH Electronics Incorporated (Baldwin-Lima-Hamilton) Waltham, Massachusetts
BNL	Bausch & Lomb Buffalo, New York
BOA	Boeing Aerospace Company Seattle, Washington
BOC	Bray Oil Company, Incorporated Los Angeles, California
	Bostik-Finch is coded FPC
BPS	Bronze & Plastics Specialties Baltimore, Maryland
	Brady Labels are coded WHB
BRN	BICRON Corporation Newbury, Ohio
BRX	Brand-Rex Company Willimantis, Connecticut
BWC	Borg-Warner Chemicals Parkersburg, West Virginia
CAC	Carroll Products, Incorporated Farmingdale, Long Island, New York
CAF	Cali-Foam Santa Ana, California
CAL	Calabra Plastics Upper Darby, Pennsylvania
CAM	Carmac Company Shawnee, Kansas
CAN	ITT Cannon Electric Los Angeles, California
CAR	Carter's Ink Company Cambridge, Massachusetts

CAS	Castall Incorporated East Weymouth, Massachusetts
CAU	L. D. Caulk Company Milford, Delaware
CBC	CBC Corporation Marathon Shores, Florida
CCC	Chemical Division, Chrysler Corporation Trenton, Michigan
CCD	Colgate Chemical Company East Brunswick, New Jersey
CCE	Chemical Coatings & Engineering Company Media, Pennsylvania
CCL	C. P. Clare & Company Chicago, Illinois
CEL	Cellastro Corporation Ypsilanti, Michigan
CFC	Crawford Fitting Company Cleveland, Ohio
CFP	Clark Foam Products Corporation Chicago, Illinois
CHE	Chemplast Incorporated Wayne, New Jersey
CHO	Chomerics Incorporated Woburn, Massachusetts
CHR	Connecticut Hard Rubber Company New Haven, Connecticut
CIB	CIBA Corporation Summit, New Jersey
CIC	Cicoil Corporation Chatsworth, California
CIN	Cinch Connector Division TRW Incorporated Elk Grove, Illinois

CIP	Crown Industrial Products Hebron, Illinois
CIR	Chicago Ink & Research Company Antioch, Illinois
CLI	Caig Labs Incorporated Westbury, New York
CLY	Clayborn Labs Incorporated Santa Ana, California
CMC	Circuit Materials Company Princeton, New Jersey
CME	Cal-Metex Corporation Inglewood, California
CMS	Coast Manufacturing & Supply Company Livermore, California
CMI	Cambridge Thermionic Corporation Cambridge, Massachusetts
CNS	Celanese Corporation New York, New York
COM	Compac Corporation Newark, New Jersey
CON	CONAP, Incorporated Allegany, New York
COT	Cotronics Corporation Brooklyn, New York
COX	Cox & Company, Incorporated New York, New York
CPC	Crest Products Company Santa Ana, California
	Chemical Products Research is coded UJC
CPT	Coast Pro-Seal Division Essex Chemical Corporation Compton, California

CRE	Care Laboratories, Incorporated Collegeville, Pennsylvania
CPI	Chart-Pak Incorporated Leeds, Massachusetts
CRB	Carborundum Company Plastics & Adhesives Department Atlanta, Georgia
CRP	California Reinforced Plastics (Address Unknown)
CRY	Cryton Optics Roslyn, New York
CTC	Columbia Chase Corporation Humiseal Division Woodside, New York
CTD	Carlisle Corporation Tensolite Insulated Wire Company, Incorporated Carlisle, Pennsylvania
CTL	Chemical Technology Laboratories Los Angeles, California
CUM	Custom Materials Incorporated Chelmsford, Massachusetts
CVC	Consolidated Vacuum Corporation Rochester, New York
CWR	Chase-Walton Rubber Company Hudson, Massachusetts
DAC	Durkee-Atwood Company Minneapolis, Minnesota
DAD	Daburn Electronics & Cable Corporation Bronx, New York
	DALCO Industries is coded SPA
DAY	Dayton Chemical Company Dayton, Ohio

DBP	DB Products Pasadena, California
DCC	Dow Corning Corporation Midland, Michigan
DCI	Danvers Chemical Industries Incorporated Danvers, Massachusetts
DEC	Dow-Elco Company Montibello, California
DEF	Deft Chemical Coatings Torrence, California
DEL	Delron Fastners Santa Ana, California
DES	Desoto Incorporated Des Plains, Illinois
DEU	Deutsch Company Los Angeles, California
DEV	Chemical Development Corporation DEVCON Corporation Danvers, Massachusetts
DEX	Dexter Corporation, Midland Division Hayward, California
DIC	Disogren Industries Corporation Manchester, New Hampshire
DIL	Dilectrix Corporation Farmingdale, Long Island, New York
DIN	Dodge Industries Hoosick Falls, New York
DIS	Dielectric Sciences Woburn, Massachusetts
DIV	Diversified Marine Industries Norwalk, Connecticut
DIX	Dixon Corporation Bristol, Rhode Island

DNN	Dennison Manufacturing, Company Framingham, Massachusetts
DNS	Dennis Chemical Company St. Louis, Missouri
	John C. Dolph Company is coded JCD
DOU	Douglas Elastomers Akron, Ohio
DOW	Dow Chemical Company Midland, Michigan
DRC	Davol Incorporated Providence, Rhode Island
DRI	Drilube Company Glendale, California
DSC	D. Strauss Company, Incorporated New York, New York
DSL	Dowty Seals Limited Ashchurch, Tewksbury, England
DTC	Devon Tape Corporation Carlstadt, New Jersey
DUN	Dunmore Corporation Newtown, Pennsylvania
DUP	E. I. DuPont de Nemours and Company, Incorporated Wilmington, Delaware
	Elastomer Chemicals Department
	Fabrics and Finishes Department
	Film Department
	Plastics Department
DXN	Joseph Dixon Crucible Company Jersey City, New Jersey
EAC	Eastman Chemical Products Company Kingsport, Tennessee

EAS	Eastman Kodak Company Rochester, New York
ECC	Electronized Chemicals Corporation Burlington, Massachusetts
ECI	Eldre Components Incorporated Rochester, New York
ECP	Eclipse-Pioneer Division Teterbord, New Jersey
EDC	Eldec Corporation Lynnwood, Washington
EDD	Eddington Threat Manufacturing Eddington, Pennsylvania
EFH	Electro-Flex Heat, Incorporated Bloomfield, Connecticut
EFI	Electrofilm Incorporated North Hollywood, California
EHC	Englehard Minerals & Chemicals Corporation Newark, New Jersey
	Englehard Industries Division Newark, New Jersey
	Minerals & Chemicals Division Edison, New Jersey
ELB	Elliot Brothers Steel Company New Castle, Pennsylvania
ELI	Electroply, Incorporated El Segundo, California
ELM	Elmhurst Rubber Company Elmhurst, New York
ELP	Elco-Pacific Company El Segundo, California
ELR	Electrical Refractories East Palistine, Ohio

ELS	Electro-Science Laboratories, Incorporated Pennsauken, New Jersey
EMC	Emerson & Cuming Incorporated Canton, Massachusetts
EML	Electro Mechanisms Limited England
ENJ	Enjay Chemical Company New York, New York
EON	EON Corporation Los Angeles, California
EPC	Epoxy lite Corporation South El Monte, California
EPK	Epoxy Technology Incorporated Billerica, Massachusetts
EPO	Epoxy Products Company Irvington, New Jersey
EPP	Eppley Laboratories Incorporated Newport, Rhode Island
EPX	Epoxy Pack Company Los Angeles, California
ERP	Expanded Rubber & Plastics Gardena, California
ESX	Essex Chemical Corporation Compton, California
EWC	Elco Webster Corporation Watertown, Massachusetts
EXX	Exxon Chemical Company, USA Houston, Texas
FAL	Fenner America Limited Middletown, Connecticut
FAR	Farbenfabriken Bayer AG Germany

Fasson is coded APP

FBC	Fiber-Resin Corporation Burbank, California
FBR	Fiberfil Division Dart Industries Evansville, Indiana
FCC	Fluorocarbon Company Sunnyvale, California
	Reeves Rubber Division San Clemente, California
FED	Federal Pen Company Jersey City, New Jersey
FEN	Fenwal Industries Ashland, Massachusetts
FER	Ferro Corporation Cleveland, Ohio
FHB	H. B. Fuller Company St. Paul, Minnesota
FIB	Fiberite Corporation Winona, Minnesota
FIC	Fiber Manufacturing Company Newton, North Carolina
FIR	Franklin Institute Research Laboratories Philadelphia, Pennsylvania
FIS	Fisk Brothers Newark, New Jersey
FLA	Fortin Laminating Corporation Sylmar, California
FLC	Fortin Plastics Incorporated Valencia, California
FLI	Flintkote Company Stamford, Connecticut

FLL	Flormel Company Bayside, New Jersey
FLO	Floquil Products Incorporated Cobleskill, New York
FLX	Flexaust Company Division of Callahan Mining Corporation Amesbury, Massachusetts
FMC	FMC Corporation Industry, California
FOF	Foam Fab Company Franklin, Massachusetts
FOM	Fomo Products Akron, Ohio
	Formica Corporation is coded ACC
FPC	Bostik-Finch, Incorporated (Subsidiary of USM Corporation) Torrance, California
FPI	Furane Plastics Incorporated Los Angeles, California
FPL	Firestone Plastics Company Pottstown, Pennsylvania
FRA	Fralock, Division of Lockwood Industries Van Nuys, California
FRC	Fargo Rubber Corporation (Address Unknown)
FRE	Freeman Chemicals Port Washington, Wisconsin
FRL	Fabric Research Labs Denton, Massachusetts
FUL	Fuller Company (H. B. Fuller Company St. Paul, Minnesota – As Above)

FXC	Flexco Company Denville, New Jersey
GAC	Goodyear Aerospace Corporation Akron, Ohio
GAR	Garland Manufacturing Company Saco, Maine
GBE	Gudebrod Brothers Silk Company Incorporated Electronics Division New York, New York
GCC	General Cement Rockford, Illinois
GCE	G. C. Electronics Company Rockford, Illinois
GDE	General Dynamics, Convair Division San Diego, California
GEC	General Electric Company Plastics Department Pittsfield, Massachusetts
	Silicone Products Department Waterford, New York
	Wire and Cable Department Bridgeport, Connecticut
GEN	General Electronics Incorporated Newark, New Jersey
GEV	General Electric Company Reentry & Environmental Systems Valley Forge, Pennsylvania
GHI	Grayhill Incorporated La Grange, Illinois
GHT	G & H Technology Incorporated Santa Monica, California

GLC	General Latex & Chemical Corporation Cambridge, Massachusetts
GLI	Garlock Incorporated Palmyra, New York
GMB	M. Grumbacher Incorporated New York, New York
GMC	General Mills, Chemical Division Kankakee, Illinois
	W. L. Gore Associates is coded WLG
GOL	Goldenwest Products Cedar Ridge, California
GOR	Gore Company Newark, Delaware
GPM	General Plastics Manufacturing Company Tacoma, Washington
GRC	Goshen Rubber Company Goshen, Indiana
GRE	Greene Rubber Company Cambridge, Massachusetts
GRO	Grow Chemical Corporation Cleveland, Ohio
GRU	Grumman Aerospace Corporation Bethpage, Long Island, New York
GSC	Goddard Space Flight Center Greenbelt, Maryland
GSD	GS Dielectric Communications Littleton, Massachusetts
GTR	General Tire & Rubber Company Akron, Ohio
GTS	G. T. Schjeldahl Company Northfield, Minnesota

HAB	Hanline Brothers, Incorporated Baltimore, Maryland
HAC	Hughes Aircraft Company Culver City, California
HAN	Handschy Chemical Company Chicago, Illinois
HAR	Harshaw Chemical Company Solon, Ohio
HAV	Haveg Industries Winodski, Vermont
	Hadbar is coded PPH
HCC	Hughson Chemicals Lord Corporation Erie, Pennsylvania
HDM	Hygienic Dental Manufacturing Company Akron, Ohio
HEM	Hettinger, Baldwin & Messtechnik Netherlands
HEQ	Herculite Products Incorporated New York, New York
HER	Hercules Incorporated Wilmington, Delaware
HEX	Hexcel Products Incorporated Berkeley, California
HIC	Hardman Incorporated Belleville, New Jersey
HLR	Hoffmann-La Roche, Incorporated Nutley, New Jersey
HMB	Heminway & Bartlett Manufacturing Company New York, New York
HNC	Henkel & Cie Germany

HOB	Howe & Bainbridge Incorporated Boston, Massachusetts
HOI	Howe Industries N. Hollywood, California
HPC	Hastings Plastics Company Santa Monica, California
HSD	Hawker & Siddeley Dynamics, Limited London, England
HSP	High Strength Plastics Corporation Chicago, Illinois
HTC	Heath-Tecna Corporation Kent, Washington
HTR	Hi-Temp Resins Incorporated Stamford, Connecticut
HTW	Hi-Temp Wires Company Westburg, Long Island, New York
HUE	Hughes Associates Excelsior, Minnesota
HUL	Hulz A. G. Germany
	Humiseal is coded CTC
HWC	Hope Webbing Company, Incorporated Providence, Rhode Island
HYD	Hydron Laboratories Incorporated New Brunswick, New Jersey
HYS	Hysol Division The Dexter Corporation Olean, New York
IBM	IBM Corporation Armonk, New York
ICA	Imperial Chemical Ayrshire, Great Britain

ICI	ICI United States Incorporated Wilmington, Delaware
ICD	Icore Wire & Cable Santa Barbara, California
IDE	Ideas Incorporated Beltsville, Maryland
IER	International Electronic Research Corporation Burbank, California
IMI	IMI-Tech Corporation Elk Grove Village, Illinois
IMP	Imperial Eastman Chicago, Illinois
IND	Independent Ink Incorporated Gardena, California
INK	Inks and Specialties Irving, Texas
INR	Industrial Electronic Rubber Company Twinsburg, Ohio
INS	Insta-Foam Products Addison, Illinois
INT	International Harvester Chicago, Illinois
INX	INSL-X Company Brooklyn, New York
IPI	Impact Plastics Incorporated Gastonia, North Carolina
IRC	Isochem Resins Company Lincoln, Rhode Island
IST	Insultab Incorporated Woburn, Massachusetts
ITR	IIT Research Institute Chicago, Illinois

ITT	International Telephone & Telegraph Corporation
	ITT Aerospace—Optical Division
	Fort Wayne, Indiana
	ITT Industrial Products Division
	San Fernando, California
JAC	Jaco Manufacturing Company
	Berea, Ohio
JAS	Jasper Rubber Company
	Jasper, Indiana
JCD	John C. Dolph Company
	Monmouth Junction, New Jersey
JMC	Jordon Marsh Company
	Boston, Massachusetts
JMM	Johnson Massey Metals Limited
	London, England
JOM	Johns-Manville
	New York, New York
JSC	Johnson Space Center
	Houston, Texas
JSP	Johnston Specialty Coatings
	Huntington Beach, California
KAM	Kamatics Corporation
	Bloomfield, Connecticut
KAS	Kasen Industries
	Newark, New Jersey
KCC	Kimberley-Clark Corporation
	Neenah, Wisconsin
KCF	Keene Corporation
	Chase Foster Division
	Bear, Delaware
KCO	Kenics Corporation
	Danvers, Massachusetts

KCW	Keane Corporation Wheeler Lighting Division Wilmington, Massachusetts
KEE	Keeler & Long Watertown, Connecticut
KEN	Kendall Company Wellesley Hills, Massachusetts
KEY	Key Polymer Corporation Lawrence, Massachusetts
KMC	Kingsley Machine Company Hollywood, California
KOK	Kokusai Chemicals, Japan
KOL	Kollmorgen Corporation Multiwire Division Northampton, Massachusetts
KOP	Koppers Company Irving, Texas
KRC	Kirkhill Rubber Company Brea, California
KST	King-Seeley Thermos Company Prospect Heights, Illinois
LAM	Lamart Corporation Clifton, New Jersey
LCC	Leffingwell Chemical Company Brea, California
LCR	Leach Corporation, Relay Division Los Angeles, California
LDL	Labarge, Dorflex Division Santa Ana, California
LDV	LDV Electroscience Syracuse, New York

LEC	The Leal Company Camden, New Jersey
LEM	Lem Products Mt. Vernon, New York
LES	Lundy Electronics & Systems, Incorporated Glen Head, New York
LFM	L. Frank Markel & Sons Norristown, Pennsylvania
LLS	Lesonal Werke-Lechler & Sons Stuttgart, Germany
LNP	Liquid Nitrogen Processing Corporation Malvern, Pennsylvania
LOC	Lockheed Missile & Space Company Palo Alto, California
LOR	Lord Manufacturing Company Erie, Pennsylvania
LRC	Langley Research Hampton, Virginia
LTC	Loctite Corporation Newington, Connecticut
LUD	Ludlow Corporation Needham Heights, Massachusetts
LUS	Lusol Products El Monte, California
MAG	Magic American Chemical Corporation Cleveland, Ohio
MAQ	Markel, L. Frank & Sons, Incorporated Norristown, Pennsylvania
MAR	Markel Rubber Products Bronx, New York
MAS	Mar Glass Sherbourne, England

MBI	Master Bond Incorporated Teaneck, New Jersey
MCA	The Mica Corporation Culver City, California
MCC	Micro-Circuits Company New Buffalo, Michigan
MCG	McGhan Nusil Corporation Carpinteria, California
MEI	Micro Electronics, Incorporated (Address Unknown)
MEL	Melrose Nameplate Oakland, California
MEP	Mereco Products Division Metachem Resins Corporation Cranston, Rhode Island
MER	Meridian Laboratory Incorporated Middleton, Wisconsin
MET	Metex Corporation Edison, New Jersey
MIC	Microtech Incorporated Folcroft, Pennsylvania
MID	Midland Industrial Finishes Company Waukegan, Illinois
	Micarta is coded WEC
MIF	Microwell Division Pitney Bowes Incorporated Stamford, Connecticut
MIN	Markem Corporation Keene, New Hampshire
MIR	Microdot Incorporated Pasadena, California

MMC	Monte-Martini Company Italy
MMF	Morrison Molded Fiberglass Company Bristol, Virginia
MMM	Minnesota Mining & Manufacturing Company St. Paul, Minnesota
	Adhesives, Coatings and Sealers Division
	Electro-Products Division
	Industrial Tape Division
	Magnetic Products Division
MMS	Mica & Micanite Supplies Limited Barnsbury Square, London, England
MNC	Morton-Norwich Chemical Company Incorporated Chicago, Illinois
MNR	Minnesota Rubber Minneapolis, Minnesota
MOB	Mobay Chemical Company Pittsburgh, Pennsylvania
MOL	Stevens Molded Products Division Easthampton, Massachusetts
MON	Monsanto Company St. Louis, Missouri
MOR	Morgan Adhesive Company Stow, Ohio
MOS	Mosites Rubber Company Fort Worth, Texas
MOT	Motorola Incorporated Franklin Park, Illinois
MOX	Moxness Products Incorporated Racine, Wisconsin

MPC	Metal Photo Corporation Cleveland, Ohio
MPD	MPD Technology Corporation Ergenics Division Waldwick, New Jersey
MRC	The Marblette Corporation Long Island City, New York
MRG	Midland-Ross Corporation Grimes Division Urbana, Ohio
MSF	Marshall Space Flight Center Huntsville, Alabama
MSH	Micro Switch Division of Honeywell Freeport, Illinois
MSI	Miller-Stephenson Chemical Company Incorporated Danbury, Connecticut
MSL	Midland Silicones Limited England
MSY	Moore Systems Sunnyvale, California
MTC	Mark-Tex Corporation Englewood, New Jersey
MUH	Mullard House London, England
MUP	Mupak Brocton, Massachusetts
MWS	MWS Precision Wire Chatsworth, California
MYC	Mycalex Corporation Division Spaulding Fibre Company Incorporated Clifton, New Jersey
NAL	Nalgene Company Rochester, New York

NBC	National Beryllia Corporation Haskell, New Jersey
	NARMCO is coded WCN
NCI	NCI Incorporated West Palm Beach, Florida
NCO	New England Laminates Company, Incorporated Frazer, Pennsylvania
NDC	Naval Air Development Center Warminster, Pennsylvania
NEL	Nuclear Enterprises Limited Winnipeg Canada and San Carlos, California
NEO	Neosid Limited England
NEW	M. M. Newman Corporation Marblehead, Massachusetts
NLC	National Lead Company New York, New York
NMC	National Metallizing Division Standard Packaging Corporation Cranbury, New Jersey
NOC	Norton Company Worchester, Massachusetts
	Nortronics Chemical Company is coded SRW
	Norpalex is coded UOP
NOI	NOPI Incorporated Hackensack, New Jersey
NOP	NOPCO Chemical Company Newark, New Jersey
NOR	Norland Products, Incorporated New Brunswick, New Jersey

NPC	Norton Plastics Akron, Ohio
NRL	Naval Research Laboratory Washington, D.C.
NSC	National Starch & Chemical Company New York, New York
NSE	National Semiconductors Corporation Santa Clara, California
NTI	NT Industries Englewood Cliffs, New Jersey
NVF	NVF Company Yorklyn, Delaware
NYE	Wm. P. Nye Incorporated New Bedford, Massachusetts
NYL	Nylok-Detroit Corporation Troy, Michigan
OAK	The Oakland Corporation Troy, Michigan
OCC	Orchard Company (Address Unknown)
OII	Owens Illinois Incorporated Toledo, Ohio
OLI	Olin Mathieson Chemical Corporation New York, New York
OMG	Oak Materials Group, Incorporated Fluorglas Division Hoosick Falls, New York
OPC	Organic Products Company Irving, Texas
ORC	Orcon Corporation Union City, California
ORT	Ortec Incorporated Oak Ridge, Tennessee

OXI	Oxford Instruments Columbia, Maryland
PAC	Pacific Resins & Chemicals Incorporated Seattle, Washington
PAL	Palflex Products Corporation Putnam, Connecticut
PAN	Panduit Corporation Tinley Park, Illinois
PAR	Parsons of California Stockton, California
PCC	Pennsalt Chemicals Corporation New York, New York
PCE	Peterson Chemical Company Sheboygan, Wisconsin
PCK	PCK Technology Melville, New York
PCR	Polychrome Film Corporation Yonkers, New York
PDC	Phelps Dodge Copper Products Corporation New York, New York
PEL	Pelmor Laboratories, Incorporated Newtown, Pennsylvania
PEP	Port Erie Plastics Incorporated Harborcreek, Pennsylvania
PER	Permacel New Brunswick, New Jersey
PFC	Penntube Plastics Company Clifton Heights, Pennsylvania
PFI	Perma Foam Incorporated Irvington, New Jersey
PFP	Precision Fiberglass Products San Pedro, California

PHG	Philips Geldrop Netherlands
PHI	Poly-Hi Incorporated Fort Wayne, Indiana
PHP	Phillips 66 Petroleum Company Bartlesville, Oklahoma
PIC	Permabond International Corporation Englewood, New Jersey
PIE	Pierson Industries Palmer, Massachusetts
PIR	Pirelli Cable Corporation Union, New Jersey
PKA	Park Avenue (Address Unknown)
PLA	Precision Labs Cincinnati, Ohio
PLI	Permalis Incorporated Mt. Pleasant, Pennsylvania
PLK	Plasti-Kote Division Medina, Ohio
PLL	Poly-Lok Fastners Corporation Cincinnati, Ohio
PLM	Palmer Products New York, New York
PMC	Plessey Manufacturing Company, Limited Kingsthorpe, Northampton, UK
POC	Polaroid Corporation Cambridge, Massachusetts
POL	Polygon Company Walkerton, Indiana
POR	Porex Incorporated Fairburn, Georgia

POT	Potomac Rubber Company Washington, D.C.
PPC	The Polymer Corporation Reading, Pennsylvania (Foreign Subsidiaries are Polypenco)
PPG	PPG Industries Adhesive Products Bloomfield, New Jersey
PPH	Purolator Products Incorporated Hadbar Division Alhambra, California
PRC	Products Research & Chemical Corporation Burbank, California
PRD	Physics Research & Development Incorporated Boulder, Colorado
PRG	Proctor & Gamble Company Cincinnati, Ohio
PRP	Plastics & Rubber Products Company Ontario, California
PSC	Parker Seal Company Culver City, California
PSL	Permagile-Salmon Limited Plainview, New York
PTI	Products Techniques Incorporated Los Angeles, California
PUT	Putnam Mills Corporation New York, New York
PVL	Pervel Industries Plainfield, Connecticut
QUA	Quantum Incorporated Wallingon, Connecticut
QUE	Q-Max Corporation Marlboro, New Jersey
RAD	Radiation Incorporated Melbourne, Florida

RAM	RAM Chemicals Gardena, California
RAN	Randolph Products Company Carlstadt, New Jersey
RAY	Rayclad Tubes Incorporated Menlo Park, California
RCA	Radio Corporation of America Harrison, New Jersey
RCC	Raychem Corporation Menlo Park, California
RCI	Richmond Corporation Redlands, California
REA	REA Magnet Wire Company Fort Wayne, Indiana
RED	R. E. Darling Company, Incorporated Gaithersburg, Maryland
REE	Reeves Brothers Incorporated Vulcan Coated Fabrics Division Rutherfordton, North Carolina
REF	Resin Formulating Company Culver City, California
REI	Reichold Chemicals Incorporated Detroit, Michigan
REM	Rembrandt (Address Unknown)
RES	Resdel Corporation Rio Grande, New Jersey
RFC	Rogers Foam Company Baltimore, Maryland
RIC	Richardson Company Melrose Park, Illinois

RLC	Royal Lubricants Company East Hanover, New Jersey
RMC	Reliable Manufacturing Company Fountain Valley, California
RMI	Raybestos-Manhattan Incorporated Passaic, New Jersey
ROG	Rogers Corporation Rogers, Connecticut
ROH	Rohm and Haas Company Philadelphia, Pennsylvania
ROS	Milton Ross Company South Hampton, Pennsylvania
RPC	Riegel Paper Corporation New York, New York
RRC	Ronthon Reiss Corporation Little Falls, New Jersey
RTC	Remtek Corporation Sunnyvale, California
RVM	Risdon Vacuum Metallizing Company Van Nuys, California
SAG	Schering A. G. Berghamen Westfalen, Federal Republic of Germany
SAN	Sanford Ink Company Bellwood, Illinois
SAS	Sanders Associates Manchester, New Hampshire
SAU	Saunders Thread Company Gastonia, North Carolina
SBI	Solar Basic Industries Littleton, Massachusetts
SCE	Scientific Enterprises Bloomfield, Colorado

SCG	Scott Graphics Incorporated Holyoke, Massachusetts
SCH	Schenectady Chemicals Incorporated Schenectady, New York
	Schjeldahl is coded GTS
SCI	Structural Composites Industries Azusa, California
SCT	Scott Paper, Industrial Foam Chester, Pennsylvania
SEL	Space Environment Laboratories Incorporated Boulder, Colorado
SFR	Santa Fe Rubber Products, Incorporated Whittier, California
SHA	W. S. Shamban Company Newbury Park, California
SHC	Shell Containers Incorporated Great Neck, New York
SHE	Shenandoah Plastics Corporation Frederick, Maryland
SHI	Shielding Technology Incorporated Piscataway, New Jersey
SHL	Shell Chemical Company New York, New York
SHW	Sherwin-Williams Company Cleveland, Ohio
SIE	Shielding Technology Incorporated Piscataway, New Jersey
SIG	Signetics Corporation Sunnyvale, California
SIO	Siegrist Orel Europe

SIP	Sigma Plastronics Dearborn, Michigan
SIS	Sargent Industries Stillman Rubber Division Culver City, California
SLK	SCI Systems Incorporated Huntsville, Alabama
SLM	Shannon Luminous Materials Company Los Angeles, California
SMC	Spira Manufacturing Corporation Burbank, California
SNZ	Sandoz Chemical Company Hanover, New Jersey
SOM	Smooth-On Manufacturing Company Gillette, New York
SPA	DALCO Industries (Shurlok) Hawthorne, California
SPC	Specialty Coatings Company Elk Grove Village, Illinois
SPE	Spectrum Control Incorporated Fairview, Pennsylvania
SPK	Spencer Kellogg Division Buffalo, New York
SPI	Stevens Products Incorporated Stevens Tubing Corporation East Orange, New Jersey
SPL	Spraylat Corporation New York, New York
SPR	Specialty Products Company Jersey City, New Jersey
SPT	Stone Industrial Corporation Washington, D.C.

SPX	Sperex Corporation Gardena, California
SRC	Stockwell Rubber Company Philadelphia, Pennsylvania
SRP	Schultz Rubber Products (Address Unknown)
SRW	Nortronics Chemical Company Costa Mesa, California
SSC	Spectra-Strip Corporation Garden Grove, California
SST	Stern & Stern Textiles Incorporated New York, New York
STA	Stanley Chemical East Berlin, Connecticut
STC	Super Temp Wire Division Winooski, Vermont
STE	J. P. Stevens & Company, Incorporated New York, New York
	Stevens Molded Products is coded MOL
STI	Stillman Rubber Division Sargent Industries Culver City, California
STR	Stranco Products Incorporated Chicago, Illinois
STS	Sierracin/Thermal Systems Los Angeles, California
STV	Sterling Varnish Sewickley, Pennsylvania
SUM	Summers Laboratories, Incorporated Fort Washington, Pennsylvania
SWC	Sequoia Wire Company Redwood City, California

SWS	SWS Silicones Corporation Adrian, Michigan
SYL	Sylvania Electric Products Incorporated New York, New York
	Electronic Systems Division Buffalo, New York
	Chemical & Metallurgical Division Towanda, Pennsylvania
	Semiconductor Division Woburn, Massachusetts
SYN	Synthane Taylor Incorporated Valley Forge, Pennsylvania
TAM	TA Manufacturing Corporation Glendale, California
TAY	Taylor Corporation Valley Forge, Pennsylvania
TBT	The Thomas & Betts Company, Incorporated Elizabeth, New Jersey
TCC	Thiokol Chemical Corporation Trenton, New Jersey
TCI	Trans/Circuits Incorporated Falls Church, Virginia
TEC	Tecknit Cranford, New Jersey
TEE	Teledyne Electro Mechanisms Nashua, New Hampshire
TEI	Technic Incorporated Providence, Rhode Island
TEK	Teknational, Incorporated Rochester, New York
TEL	Thermo Electric Company Saddle Brook, New Jersey

TEM	Tempil Division Big Three Industries, Incorporated S. Plainfield, New Jersey
TEN	Tenneco Chemicals Foam Division Paramus, New Jersey
	Tensolite is coded CTD
TER	Teradyne Components, Incorporated Lowell, Massachusetts
TEX	Texwipe Company Hillsdale, New Jersey
TFE	Technical Fluorocarbons Engineering Incorporated Warwick, Rhode Island
TFF	T & F Fluorocarbon Company Holling Meadows, Illinois
THE	Thermalloy Company Dallas, Texas
THI	Thermatics Incorporated Elm City, North Carolina
THL	Uniglas Industries Division of United Merchants & Manufacturers, Incorporated Los Angeles, California
TII	Texas Instruments Incorporated Dallas, Texas
TIW	Times Wire & Cable Company Subsidiary Insilco Wallingford, Connecticut
TMC	Trak Microwave Corporation Tampa, Florida
TME	TME Corporation Salem, New Hampshire
TMP	Temp Plate Corporation Santa Monica, California

TNC	Transene Company Danvers, Massachusetts
TPI	Thermoset Plastics Incorporated Indianapolis, Indiana
TRA	TRA-CON Incorporated Medford, Massachusetts
TRI	Tridox Products Philadelphia, Pennsylvania
TRO	Troy Mills Incorporated Troy, New Hampshire
TRW	TRW Redondo Beach, California (Thompson-Ramo-Woolrich)
TSI	Thermal Systems Incorporated Los Angeles, California
TTP	Telatemp Fullerton, California
TUF	Tufnol Limited England
TWC	Thermax Wire Corporation New York, New York
TWP	Technical Wire Products Company, Incorporated Cranford, New Jersey
TXI	Texaco Incorporated White Plains, New York
TYC	Tycodure Limited London, England
TYT	Tyton Corporation Milwaukee, Wisconsin
UCC	Union Carbide Corporation New York, New York
UIC	Union Ink Company Ridgefield, New Jersey

UJC	Upjohn Company Kalamazoo, Michigan
UND	Uniroyal Incorporated New York, New York
UNF	United Foam Compton, California
UNI	Uniglass Industries Los Angeles, California
UOP	Universal Oil Products Norplex Division Lacrosse, Wisconsin
USE	Useco Division Litton Industries Van Nuys, California
USP	U. S. Polymeric Incorporated Santa Ana, California
VAC	Vought Aeronautics Company Division LTV Corporation Dallas, Texas
VAL	Nikon Valca Japan
VAR	Varian Associates Vacuum Products Division Palo Alto, California
VEC	Vector Electronic Company, Incorporated Sylmar, California
VEL	Velcro Corporation New York, New York
VIG	Vigor Company (Distributors) New York, New York
VFX	Varflex Corporation Rome, New York
VIS	Vishay Resistive Systems Group Malvern, Pennsylvania

VIS	Vishay Resistive Systems Group Malvern, Pennsylvania
VOL	Voltek Company Lawrence, Maine
VVP	Vita-Var Company New Brunswick, New Jersey
WAC	Wacker Munich, Germany
WAI	Wilco Associates Incorporated Gardena, California
WAK	Wakefield Engineering Company Wakefield, Massachusetts
WCN	Whittaker Corporation NARMCO Materials Division Costa Mesa, California
WEC	Westinghouse Electric Corporation Micarta Division Hampton, South Carolina
WEI	Westinghouse Electric Corporation Industrial Plastics Division West Mifflin, Pennsylvania
WEK	Weckesser Company Chicago, Illinois
WFC	Western Filament Corporation Glendale, California
WGP	Western Gasket & Packing Company Los Angeles, California
WHB	W. H. Brady Company Milwaukee, Wisconsin
WIL	Wilshire Foam Products Incorporated Torrance, California
WIN	Winchester Electronics Division Litton Industries Oakville, Connecticut

WJR	W. J. Rusco Company Akron, Ohio (Distributor for Interchemical Corporation, Finishes Division)
WLG	W. L. Gore & Associates, Incorporated Newark, Delaware
WMI	Woolsey Marine Industries New York, New York
WOP	Woodmont Products Huntington Valley, Pennsylvania
WPC	Westlake Plastics Company Lenni, Pennsylvania
WPP	Wornow Process Paint Company Los Angeles, California
WRG	W. R. Grace & Company Columbia, Maryland
WSA	Waterford Specialty Adhesives Incorporated McKeesport, Pennsylvania
WSL	Western States Lacquer Corporation Los Angeles, California
WTB	William T. Bean Company Detroit, Michigan
YAR	Yarsley Limited United Kingdom
YLI	Youngblood Company Millbury, Massachusetts
ZZZ	Manufacturer Unknown

NASA - JSC
TECHNICAL
LIBRARY

60627
(Accession No.)

Call No:

TL

953

C35

C, 1

1. Report No. NASA RP-1124	2. Government Accession No.	3. Recipient's Catalog No.	
4. Title and Subtitle Outgassing Data for Selecting Spacecraft Materials		5. Report Date June 1984	
		6. Performing Organization Code 313	
7. Author(s) William A. Campbell, Jr., Richard S. Marriott, John J. Park		8. Performing Organization Report No. 84B0271	
9. Performing Organization Name and Address Goddard Space Flight Center Greenbelt, MD 20771		10. Work Unit No.	
		11. Contract or Grant No.	
		13. Type of Report and Period Covered Reference Publication	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington, D.C. 20546		14. Sponsoring Agency Code	
15. Supplementary Notes			
16. Abstract Outgassing data, derived from tests at 398 K (125°C) for 24 hours in vacuum as per ASTM E 595-77, have been compiled for numerous materials for spacecraft use. The data presented are the total mass loss (TML) and the collected volatile condensable materials (CVCM). The various materials are compiled by likely usage and alphabetically.			
17. Key Words (Selected by Author(s)) Outgassing data, Spacecraft materials, Total mass loss, Collected volatile condensable materials	18. Distribution Statement Unclassified-Unlimited STAR Category 24		
19. Security Classif. (of this report) Unclassified	20. Security Classif. (of this page) Unclassified	21. No. of Pages 285	22. Price* A13

*For sale by the National Technical Information Service, Springfield, Virginia 22161.