

Graphene Tight-Binding Analysis

Fatemeh Rezaei

May 23, 2025

A. Code Analysis: Step by Step

```
import numpy as np
import matplotlib.pyplot as plt
```

Explanation: Importing libraries for numerical calculations and plotting.

```
a = 1.0

# Nearest neighbor vectors
delta = np.array([
    [0, -a/np.sqrt(3)],
    [a/2, a/(2*np.sqrt(3))],
    [-a/2, a/(2*np.sqrt(3))]
])
```

Explanation: Defines the lattice constant and the three nearest-neighbor vectors for the honeycomb lattice, just as we do when setting up the tight-binding model on paper.

```
# Reciprocal lattice vectors
b1 = (2*np.pi/a) * np.array([1, -1/np.sqrt(3)])
b2 = (2*np.pi/a) * np.array([0, 2/np.sqrt(3)])

# High symmetry points in reciprocal space
Gamma = np.array([0, 0])
K = (b1 + 2*b2) / 3
M = b1 / 2
```

Explanation: Computes reciprocal lattice vectors and high-symmetry points in the Brillouin zone, matching the paper approach to band structure calculation.

```
# Nearest-neighbor hopping parameter
t = 2.7

def f_k(k):
    return -t * np.sum(np.exp(1j * np.dot(delta, k)))
```

Explanation: Sets the hopping parameter t and defines the function $f(\vec{k})$ that computes the off-diagonal element of the 2×2 Hamiltonian matrix for each $\vec{k}$, as in the analytic tight-binding model.

```
# Generate k-points along the path Gamma -> K -> M -> Gamma
num_points = 100
path_GK = np.linspace(Gamma, K, num_points)
path_KM = np.linspace(K, M, num_points)
path_MG = np.linspace(M, Gamma, num_points)
```

```

k_path = np.vstack((path_GK, path_KM, path_MG))

# Calculate energies along the k-path
energies = []
for k in k_path:
    fk = f_k(k)
    E_plus = np.abs(fk)
    E_minus = -np.abs(fk)
    energies.append([E_minus, E_plus])
energies = np.array(energies).T

```

Explanation: Constructs a path through the Brillouin zone and calculates the eigenvalues $E_{\pm}(\vec{k}) = \pm|f(\vec{k})|$ for each $\vec{k}$, exactly as on paper.

```

# Plot the band structure
plt.figure(figsize=(8, 6))
....

```

Explanation: Plots the two bands (valence and conduction) along the high-symmetry path, revealing the Dirac cones at the K points.

B. Band Structure, Fermi Level, and Physical Properties

- **Energy bands:** The two bands $E_{\pm}(\vec{k})$ touch at the K and K' points (Dirac points). The dispersion is linear near these points, forming the famous Dirac cones.
- **Fermi level:** For neutral graphene, the Fermi level lies exactly at the Dirac point, where the valence and conduction bands meet.
- **Band filling:** The valence band is fully filled, and the conduction band is empty at zero temperature.
- **Intersecting bands:** The bands intersect at the Dirac points, so graphene is a zero-gap semiconductor (semimetal).

C. Physical Properties Deduced from Graphene's Band Structure

The tight-binding band structure of graphene, with its characteristic Dirac cones and zero band gap, leads to a range of unique and remarkable physical properties. Below, we elaborate on what can be inferred directly from the band structure:

1. Zero Band Gap and Dirac Points

Graphene's conduction and valence bands touch at the K and K' points in the Brillouin zone, forming **Dirac points**. Near these points, the energy dispersion is linear:

$$E(\vec{k}) \approx \pm \hbar v_F |\vec{k} - \vec{K}|,$$

where $v_F \approx 10^6$ m/s is the Fermi velocity. This leads to:

- **Semimetallic behavior:** There is no band gap; electrons can be excited with infinitesimal energy.
- **Massless Dirac fermions:** Charge carriers behave as if they are massless, leading to high mobility and unusual quantum effects.

2. Electrical Conductivity

- **High conductivity:** The Fermi level lies exactly at the Dirac point, allowing electrons to move easily even at low carrier concentrations.
- **Ambipolar transport:** By shifting the Fermi level, both electrons and holes can act as charge carriers.
- **Minimum conductivity:** Even at zero carrier density, graphene exhibits a minimum conductivity on the order of e^2/h per channel.

3. Optical Properties

- **Transparency:** With no band gap and a linear density of states near the Dirac point, graphene absorbs only about 2.3% of visible light per layer, making it nearly transparent.
- **Broadband absorption:** The linear bands enable absorption across a wide range of photon energies.
- **No color:** The lack of a band gap means there is no characteristic color associated with graphene.

4. Thermal Properties

- **Exceptional thermal conductivity:** The strong covalent bonds and delocalized electrons allow graphene to conduct heat extremely efficiently.

5. Limitations: What Cannot Be Learned Directly from Band Structure

While the tight-binding band structure reveals much, it does not directly provide:

- Effects of electron-electron interactions (correlations, excitonic effects)
- Details of phonon spectra (lattice vibrations)
- Effects of impurities, strain, or substrate interactions
- Many-body phenomena such as superconductivity (without further extensions)

D. Visual Representation




Figure 1: Graphene tight binding