

MULTIFABS LIMITED
NAYAPARA, KASHIMPUR, GAZIPUR
Process Loss

Fabric Type	Shades	Enzyme		Non Enzyme	
		Tube	Open	Tube	Open
100% Cotton	White + Light	10%	13%	9%	12%
	Average	9%	12%	8%	11%
	Deep and Black	8%	10%	7%	9%
Cotton/Lycra (95/5)	White + Light	N/A	14%	N/A	13%
	Average	N/A	14%	N/A	13%
	Deep and Black	N/A	14%	N/A	13%
CVC 50/50	White + Light	N/A	13%	N/A	12%
	Average	N/A	12%	N/A	11%
	Deep and Black	N/A	10%	N/A	9%
PC (65/35)	White + Light	8%	12%	N/A	11%
	Average	8%	12%	N/A	11%
	Deep and Black	7%	10%	N/A	9%
100% Viscose/ 100% Modal	White + Light	N/A	9%	N/A	N/A
	Average	N/A	9%	N/A	N/A
	Deep and Black	N/A	8%	N/A	N/A
50/50 Cotton Modal 50/50 Cotton Viscosse	White + Light	9%	10%	N/A	9%
	Average	9%	10%	N/A	9%
	Deep and Black	9%	9%	N/A	9%
Viscose / Lycra (95/5) modal Lycra (95/5)	White + Light	N/A	14%	N/A	13%
	Average	N/A	14%	N/A	13%
	Deep and Black	N/A	13%	N/A	12%
Linen	White + Light		16%		N/A
	Average		16%		N/A
	Deep and Black		15%		N/A
Linen-Melange	Melange		25%		N/A
Yarn dyed	Yarn Dyed	4%	4%		
	knitting	4%	4%		
Yarn dyed Lycra		N/A	10%		