

ALMAJD
 BENISUEF
 BENISUEF
 EGYPT

15 january 2026

Dear Customer,

The following diagnoses have been performed for you:

LubAnac references :

Your references :

■ WEMJ/--46/-900	ASEC ENGINEERING BMIC / HYDRAULIC CIRCUITS / GRINDING-534LQ120	LubAnac Indus
■ WEMJ/--46/-901	ASEC ENGINEERING BMIC / HYDRAULIC CIRCUITS / GRINDING-534LQ305	LubAnac Indus
■ WEMJ/--46/-902	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-534BE220	LubAnac Indus
■ WEMJ/--46/-903	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-531LQ110	LubAnac Indus
■ WEMJ/--46/-904	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-531LQ120	LubAnac Indus
■ WEMJ/--46/-905	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-531LQ145	LubAnac Indus
■ WEMJ/--46/-906	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-531BE220	LubAnac Indus
■ WEMJ/--46/5000	ASEC ENGINEERING BMIC / HYDRAULIC CIRCUITS / GRINDING-534LQ110	LubAnac Indus
■ WEMJ/--46/REDU	ASEC ENGINEERING BMIC / GEARBOX / GRINDING-534LQ145	LubAnac Indus
■ WEMJ/--77/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-531LQ305	LubAnac Indus
■ WEMJ/--78/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-532LQ110	LubAnac Indus
■ WEMJ/--79/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-532LQ120	LubAnac Indus
■ WEMJ/--80/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-532LQ145	LubAnac Indus
■ WEMJ/--81/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-532LQ305	LubAnac Indus
■ WEMJ/--82/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-532BE220	LubAnac Indus
■ WEMJ/--83/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-533LQ110	LubAnac Indus
■ WEMJ/--84/REDU	ASEC ENGINEERING / ARABIAN-CEMENT-CO / GEARBOX / GRINDING-533LQ120	LubAnac Indus



TotalEnergies Marketing Egypt
Corner St 254/206 Degla - 11742 MAADI
CAIRO
Phone : +(20) 35890038/39/41/42

■ *WEMJ/--85/REDU*

ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GEARBOX / GRINDING-533LQ145

[LubAnac Indus](#)

■ *WEMJ/--86/REDU*

ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GEARBOX / GRINDING-533LQ305

[LubAnac Indus](#)

■ *WEMJ/--87/REDU*

ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GEARBOX / GRINDING-533BE220

[LubAnac Indus](#)

To consult your diagnoses: go to

<https://lubanac.totalenergies.com>

Yours sincerely,

The LubAnac team.



LubAnac references : WEMJ --46 -900

Machine: HYDRAULIC CIRCUITS / ASEC ENGINEERING BMIC / GRINDING-534LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL GEAR ...

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

03-DEC-25
295103
295103
No
96 H

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

246

Acid Index	mgKOH/g
------------	---------

1.00

Visc. @40°C	cSt
-------------	-----

460.69

PC ISO 4406	
-------------	--

26/23/17

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

269
<10
4
110
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
22
<2
<2
22
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

<2
13
<5

Your information

MOBIL GEAR 600 xp460
PA-CO

Interpretation of the diagnosis

- Metals content slightly high.
- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -901

Machine: HYDRAULIC CIRCUITS / ASEC ENGINEERING BMIC / GRINDING-534LQ305



Make and type: Capacity : 62 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : Mobil Vacuoline 528 150

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

03-DEC-25
295104
295104
No
39 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

242	
-----	--

Acid Index	mgKOH/g
------------	---------

0.84	
------	--

Visc. @40°C	cSt
-------------	-----

228.96	+++
--------	-----

PC ISO 4406	
-------------	--

25/23/16	
----------	--

PC NAS 1638	
-------------	--

12	
----	--

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

392	
<10	
19	
12	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
8	
<2	
<2	
<2	
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

<2	
<2	
<5	

Your information

PA-CO

Interpretation of the diagnosis

- Viscosity value is too high.
- Verify the real viscosity grade of this lubricant.
- We advise you to drain this oil.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -902

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-534BE220



Make and type: Capacity : 45 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

Sampling date	
Sample Number	
Sticker number	
Drain	
Working time	
Mileage oil	

03-DEC-25
295105
295105
No
41 H

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

245	
-----	--

Acid Index	mgKOH/g
------------	---------

0.96	
------	--

Visc. @40°C	cSt
-------------	-----

500.96	
--------	--

PC ISO 4406	
-------------	--

25/22/16	
----------	--

PC NAS 1638	
-------------	--

12	
----	--

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

316	
<10	
9	
<2	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
41	
<2	
<2	
3	
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

21	+
4	
<5	



LubAnac references : WEMJ --46 -902

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-534BE220



Make and type: Capacity : 45 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600
PA-CO

Interpretation of the diagnosis

- Slight silicon (Si) content.
- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -903

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ110



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

		CLASSIC	
Sampling date		03-DEC-25	
Sample Number		295106	
Sticker number		295106	
Drain		No	
Working time			
Mileage oil		41 H	
Appearance		Sediment +	
Water KF	ppm	241	
Acid Index	mgKOH/g	0.94	
Visc. @40°C	cSt	415.47	
PC ISO 4406		26/24/17	
PC NAS 1638		12	
Phosphorus	ppm	343	
Boron	ppm	<10	
Zinc	ppm	19	
Calcium	ppm	<2	
Molybdenum	ppm	<10	
Tin	ppm	<10	
Lead	ppm	<5	
Nickel	ppm	<2	
Iron	ppm	84	
Chromium	ppm	<2	
Aluminium	ppm	<2	
Copper	ppm	43 ++	
Silver	ppm	<2	
Silicon	ppm	64 +++	
Magnesium	ppm	26	
Sodium	ppm	<5	



LubAnac references : WEMJ --46 -903

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ110



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metal content too high.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -904

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

Sampling date	
Sample Number	
Sticker number	
Drain	
Working time	
Mileage oil	

03-DEC-25
295107
295107
No
5 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

259

Acid Index	mgKOH/g
------------	---------

0.92

Visc. @40°C	cSt
-------------	-----

454.41

PC ISO 4406	
-------------	--

26/24/17

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

357
<10
17
<2
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
109
<2
<2
63
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

88
28
<5



LubAnac references : WEMJ --46 -904

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metal content too high.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -905

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ145

Make and type: Capacity : 4000 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026

Oil : MOBIL

		CLASSIC
Sampling date		03-DEC-25
Sample Number		295108
Sticker number		295108
Drain		No
Working time		
Mileage oil		12 M
Appearance		Sediment +
Water KF	ppm	269
Acid Index	mgKOH/g	0.95
Visc. @40°C	cSt	445.18
PC ISO 4406		25/24/18
PC NAS 1638		12
Phosphorus	ppm	370
Boron	ppm	<10
Zinc	ppm	5
Calcium	ppm	<2
Molybdenum	ppm	<10
Tin	ppm	<10
Lead	ppm	<5
Nickel	ppm	<2
Iron	ppm	107 +
Chromium	ppm	<2
Aluminium	ppm	<2
Copper	ppm	11
Silver	ppm	<2
Silicon	ppm	95 +++
Magnesium	ppm	21
Sodium	ppm	<5



LubAnac references : WEMJ --46 -905

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531LQ145



Make and type: Capacity : 4000 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metals content slightly high.
- On the basis of the results obtained, it would be appropriate to replace the oil bath. In view of the large or unknown volume involved, we advise you to first contact your TotalEnergies technical advisor in order to discuss any other options.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 -906

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-531BE220



Make and type: Capacity : 137 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026

Oil : MOBIL

CLASSIC

10-DEC-25

295110

295110

No

61 M

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

Appearance

Water KF	ppm
----------	-----

Acid Index	mgKOH/g
------------	---------

Visc. @40°C	cSt
-------------	-----

PC ISO 4406

PC NAS 1638

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

Silicon	ppm
Magnesium	ppm
Sodium	ppm

Sediment +

241

0.94

285.33

24/19/14

12

361

<10

24

12

<10

<10

<5

<2

34

<2

<2

<2

<2

<2

<2

<5

Your information

MOBIL GEAR 600

PA-CO

Interpretation of the diagnosis

- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 5000

Machine: HYDRAULIC CIRCUITS / ASEC ENGINEERING BMIC / GRINDING-534LQ110



Make and type: Capacity : 400 L
Machine:

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL GEAR ...

CLASSIC

03-DEC-25

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

295102
295102
No
96 H

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

1088	
------	--

Acid Index	mgKOH/g
------------	---------

0.99	
------	--

Visc. @40°C	cSt
-------------	-----

465.70	
--------	--

PC ISO 4406	
-------------	--

28/27/25	
----------	--

PC NAS 1638	
-------------	--

12	
----	--

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

362	
<10	
7	
<2	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
66	+++
<2	
<2	
445	+++
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

24	++
8	
<5	

Your information

MOBIL GEAR 600
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metal content too high.
- We advise you to drain this oil.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --46 REDU

Machine: GEARBOX / ASEC ENGINEERING BMIC / GRINDING-534LQ145



Make and type: Capacity : 3600 L
Machine: DMG

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL GEAR ...

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

03-DEC-25
295101
295101
No
96 H

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

215	
-----	--

Acid Index	mgKOH/g
------------	---------

0.93	
------	--

Visc. @40°C	cSt
-------------	-----

404.29	
--------	--

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

396	
<10	
31	
<2	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
109	+
<2	
<2	
20	+
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

60	+++
21	
<5	

Your information

MOBIL GEAR 600
PA-CO
iso=26/24/17
nas=12

Interpretation of the diagnosis

- High silicon (Si) content.
- Metals content slightly high.
- On the basis of the results obtained, it would be appropriate to replace the oil bath. In view of the large or unknown volume involved, we advise you to first contact your TotalEnergies technical advisor in order to discuss any other options.



LubAnac references : WEMJ --77 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-531LQ305



Make and type: Capacity : 80 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : Mobil Vacuoline 528 150

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

10-DEC-25
295109
295109
No
12 H

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

245

Acid Index	mgKOH/g
------------	---------

0.89

Visc. @40°C	cSt
-------------	-----

273.63	+++
--------	-----

PC ISO 4406	
PC NAS 1638	

24/21/17	
12	

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

302	
<10	
139	
12	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
24	
<2	
<2	
7	
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

13	
6	
<5	

Your information

PA-CO

Interpretation of the diagnosis

- Viscosity value is too high.
- Verify the real viscosity grade of this lubricant.
- We advise you to drain this oil.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --78 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-532LQ110



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

10-DEC-25

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

295111
295111
No
3 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

285

Acid Index	mgKOH/g
------------	---------

0.96

Visc. @40°C	cSt
-------------	-----

445.16

PC ISO 4406	
-------------	--

27/25/19

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

362
<10
7
8
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
65
<2
<2
10
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

53
9
<5

Your information

MOBIL GEAR 600 xp460
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --79 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-532LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

		CLASSIC
Sampling date		10-DEC-25
Sample Number		295112
Sticker number		295112
Drain		No
Working time		
Mileage oil		3 M
Appearance		Sediment +
Water KF	ppm	253
Acid Index	mgKOH/g	0.96
Visc. @40°C	cSt	465.81
PC ISO 4406		27/25/17
PC NAS 1638		12
Phosphorus	ppm	313
Boron	ppm	<10
Zinc	ppm	6
Calcium	ppm	19
Molybdenum	ppm	<10
Tin	ppm	<10
Lead	ppm	<5
Nickel	ppm	<2
Iron	ppm	37
Chromium	ppm	<2
Aluminium	ppm	<2
Copper	ppm	22 +
Silver	ppm	<2
Silicon	ppm	9
Magnesium	ppm	5
Sodium	ppm	<5



LubAnac references : WEMJ --79 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-532LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600 xp460
PA-CO

Interpretation of the diagnosis

- Metals content slightly high.
- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --80 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-532LQ145



Make and type: Capacity : 4000 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

10-DEC-25
295113
295113
No
4 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

241

Acid Index	mgKOH/g
------------	---------

0.95

Visc. @40°C	cSt
-------------	-----

462.02

PC ISO 4406	
-------------	--

23/22/15

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

282
<10
5
12
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
74
<2
<2
7
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

69	+++
16	
<5	



LubAnac references : WEMJ --80 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-532LQ145



Make and type: Capacity : 4000 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600 xp460
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- On the basis of the results obtained, it would be appropriate to replace the oil bath. In view of the large or unknown volume involved, we advise you to first contact your TotalEnergies technical advisor in order to discuss any other options.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --81 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-532LQ305



Make and type: Capacity : 80 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : Mobil Vacuoline 528 150

CLASSIC

Sampling date
Sample Number
Sticker number
Drain
Working time
Mileage oil

10-DEC-25
295114
295114
No
22 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

253	
-----	--

Acid Index	mgKOH/g
------------	---------

0.93	
------	--

Visc. @40°C	cSt
-------------	-----

288.84	+++
--------	-----

PC ISO 4406	
PC NAS 1638	

24/19/14	
12	

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

375	
<10	
66	
11	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
14	
<2	
<2	
<2	
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

11	
<2	
<5	

Your information

PA-CO

Interpretation of the diagnosis

- Viscosity value is too high.
- Verify the real viscosity grade of this lubricant.
- We advise you to drain this oil.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --82 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-532BE220



Make and type: Capacity : 130 L
Machine: SIEMENS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

Sampling date	
Sample Number	
Sticker number	
Drain	
Working time	
Mileage oil	

17-DEC-25
295115
295115
No
22 M

Appearance	
------------	--

Sediment	+
----------	----------

Water KF	ppm
----------	-----

249	
-----	--

Acid Index	mgKOH/g
------------	---------

0.93	
------	--

Visc. @40°C	cSt
-------------	-----

285.74	
--------	--

PC ISO 4406	
-------------	--

24/19/14	
----------	--

PC NAS 1638	
-------------	--

12	
----	--

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

257	
<10	
4	
10	
<10	

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10	
<5	
<2	
50	
<2	
<2	
<2	
<2	

Silicon	ppm
Magnesium	ppm
Sodium	ppm

16	+
4	
<5	



LubAnac references : WEMJ --82 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-532BE220



Make and type: Capacity : 130 L
Machine: SIEMENS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600-XP320
PA-CO

Interpretation of the diagnosis

- Slight silicon (Si) content.
- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --83 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-533LQ110



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

CLASSIC

Sampling date	
Sample Number	
Sticker number	
Drain	
Working time	
Mileage oil	

22-DEC-25
295116
295116
No
4 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

959

Acid Index	mgKOH/g
------------	---------

0.97

Visc. @40°C	cSt
-------------	-----

349.77

PC ISO 4406	
-------------	--

28/25/23

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

312
<10
<2
<2
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
102
<2
<2
161
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

95
31
<5



LubAnac references : WEMJ --83 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-533LQ110



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600-XP460
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metal content too high.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --84 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-533LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

		CLASSIC
Sampling date		22-DEC-25
Sample Number		295117
Sticker number		295117
Drain		No
Working time		
Mileage oil		4 M
Appearance		Sediment +
Water KF	ppm	215
Acid Index	mgKOH/g	0.96
Visc. @40°C	cSt	395.81
PC ISO 4406		26/24/17
PC NAS 1638		12
Phosphorus	ppm	295
Boron	ppm	<10
Zinc	ppm	12
Calcium	ppm	8
Molybdenum	ppm	<10
Tin	ppm	<10
Lead	ppm	<5
Nickel	ppm	<2
Iron	ppm	53
Chromium	ppm	<2
Aluminium	ppm	<2
Copper	ppm	35 ++
Silver	ppm	<2
Silicon	ppm	49 ++
Magnesium	ppm	12
Sodium	ppm	<5



LubAnac references : WEMJ --84 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-533LQ120



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600-XP460
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metal content too high.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --85 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-533LQ145



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

		CLASSIC	
Sampling date		22-DEC-25	
Sample Number		295118	
Sticker number		295118	
Drain		No	
Working time			
Mileage oil		4 M	
Appearance		Sediment +	
Water KF	ppm	245	
Acid Index	mgKOH/g	0.95	
Visc. @40°C	cSt	441.55	
PC ISO 4406		27/25/17	
PC NAS 1638		12	
Phosphorus	ppm	341	
Boron	ppm	<10	
Zinc	ppm	15	
Calcium	ppm	3	
Molybdenum	ppm	<10	
Tin	ppm	<10	
Lead	ppm	<5	
Nickel	ppm	<2	
Iron	ppm	129 +	
Chromium	ppm	<2	
Aluminium	ppm	<2	
Copper	ppm	22 +	
Silver	ppm	<2	
Silicon	ppm	110 +++	
Magnesium	ppm	33	
Sodium	ppm	<5	



LubAnac references : WEMJ --85 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-533LQ145



Make and type: Capacity : 400 L
Machine: FLS

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : MOBIL

Your information

MOBIL GEAR 600-XP460
PA-CO

Interpretation of the diagnosis

- High silicon (Si) content.
- Metals content slightly high.
- We advise you to drain this oil.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --86 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-533LQ305



Make and type: Capacity : 400 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026
Oil : Mobil Vacuoline 528 150

CLASSIC

Sampling date	
Sample Number	
Sticker number	
Drain	
Working time	
Mileage oil	

22-DEC-25
295119
295119
No
27 M

Appearance	
------------	--

Sediment	+
----------	---

Water KF	ppm
----------	-----

222

Acid Index	mgKOH/g
------------	---------

0.82

Visc. @40°C	cSt
-------------	-----

285.81	+++
--------	-----

PC ISO 4406	
-------------	--

24/20/16

PC NAS 1638	
-------------	--

12

Phosphorus	ppm
Boron	ppm
Zinc	ppm
Calcium	ppm
Molybdenum	ppm

318
<10
140
32
<10

Tin	ppm
Lead	ppm
Nickel	ppm
Iron	ppm
Chromium	ppm
Aluminium	ppm
Copper	ppm
Silver	ppm

<10
<5
<2
46
<2
<2
<2
<2

Silicon	ppm
Magnesium	ppm
Sodium	ppm

22	+
3	
<5	

Your information

PA-CO

Interpretation of the diagnosis

- Slight silicon (Si) content.
- Viscosity value is too high.
- Verify the real viscosity grade of this lubricant.
- We advise you to drain this oil.

Remarks

- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.



LubAnac references : WEMJ --87 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO / GRINDING-533BE220



Make and type: Capacity : 400 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026

		CLASSIC	
Sampling date		22-DEC-25	
Sample Number		295120	
Sticker number		295120	
Drain		No	
Working time			
Mileage oil		18 M	
Appearance		Sediment	+
Water KF	ppm	285	
Acid Index	mgKOH/g	0.94	
Visc. @40°C	cSt	320.47	
PC ISO 4406		25/23/16	
PC NAS 1638		12	
Phosphorus	ppm	330	
Boron	ppm	<10	
Zinc	ppm	17	
Calcium	ppm	42	
Molybdenum	ppm	<10	
Tin	ppm	<10	
Lead	ppm	<5	
Nickel	ppm	<2	
Iron	ppm	94	
Chromium	ppm	<2	
Aluminium	ppm	<2	
Copper	ppm	6	
Silver	ppm	<2	
Silicon	ppm	15	+
Magnesium	ppm	8	
Sodium	ppm	<5	



LubAnac references : WEMJ --87 REDU

Machine: GEARBOX / ASEC ENGINEERING / ARABIAN-CEMENT-CO /
GRINDING-533BE220



Make and type: Capacity : 400 L
Machine: FLENDER

ALMAJD / EG-BENISUEF

Diagnosis date: 15 january 2026

Your information

MOBIL GEAR 600-XP320
PA-CO

Interpretation of the diagnosis

- Slight silicon (Si) content.
- We recommend taking a closer intermediate sample in order to monitor the evolution of the detected anomalies.

Remarks

- In order to improve our diagnosis, we ask you to specify the complete type of oil used at the next sample (brand, type and grade).
- For the most correct interpretation of your particle count, we recommend you to consult your application's OEM limits. In this regard, as of 01/10/2023, the previous general limits were removed from reports.