

---

# **Physics and chemistry to question authenticity: the case of the Simon Le Noir mechanism**

Augustin GOMAND

AFAHA regional meeting – 4 December 2022

Projet *Simon Le Noir*



The question of authenticity

Principle of XRF analyses

Experimental protocol

Steel and rust

Gilding

The process of fire gilding

Analyses

Brass parts


Making brass in the 17<sup>th</sup> century

Analyses

Conclusion

# Introduction: the Simon Le Noir project

- Project initiated in October 2020 following the discovery of a mechanism signed Simon Le Noir (seen from the back on the figure at right)
- The mechanism presents many specificities that makes it quite different from the first French pendulum clocks (the *pendules religieuses*) and seems rather to belong to the Renaissance style & era
- Anecdote reported in a manuscript by Claude Raillard (~1720): Simon Le Noir would have been the first to apply the pendulum in France according to his son, Jean-Baptiste
- Main objectives of the project:
  - Detailed analyses of the mechanism from a technical & stylistic point of view
  - Historical researches on Simon Le Noir and the first pendulum clocks
  - Formulation of hypotheses on the place of the studied mechanism in the history of clockmaking
- First article published in the *Horlogerie Ancienne* journal, June 2022 issue <sup>1</sup>
- Website to follow the work in progress: <https://agomand.github.io/asln/en>
- Other publications to follow in 2023



<sup>1</sup> A. Gomand, *Simon Le Noir et l'application du pendule aux horloges : une histoire parallèle ?*, Horlogerie Ancienne, 91, June 2022

# The question of authenticity: a brief history

- Recurring question in the studies of objects that are possibly historically significant: is the object perfectly authentic? was it repaired? reconstituted? or may it be a fake?
- Until now, very few clocks have been submitted to extensive analyses about their authenticity, only some “specimens” related to a great invention or innovation:
  - invention of the portable clock = the watch → portative clock of Peter Henlein
  - application of the pendulum to clocks → Jan van Call regulator, **Simon Le Noir mechanism**
  - invention of the balance spring...
- Analytical methods that have evolved during the 20<sup>th</sup> century with scientific innovations:
  - stylistic & technical analyses (before the 20<sup>th</sup> century) → useful to check the consistency with the alleged date of manufacture BUT mainly **subjective** analyses and sometimes not sufficient
  - analyses of materials by direct observation = optical microscopy (20<sup>th</sup> century) → structure of materials that can be compared with the techniques and uses of the time BUT analyses often **destructive** (cuts / samples necessary)
  - spectroscopic / tomographic analyses (late 20<sup>th</sup> century) → precise chemical composition (quantified) + internal structure of materials from **non-destructive & objective** analyses → **subject of this lecture**

# The question of authenticity: two examples

- Regulator of Jan van Call: presented some time as the oldest pendulum clock ever built
- Sold at Sotheby's in 1986, bought by the Science Museum, studied in the British Museum
- Analyses globally inconclusive <sup>2</sup>:
  - signatures engraved after the gilding
  - spectroscopy: no mercury in the gilding
  - gilding possibly electrolytic...
  - anachronism of the secondary cursor of the pendulum
  - no known history before the sale...
- Probably a reconstitution of new and old, or a pure forgery (the most shared hypotheses)

<sup>2</sup> See the articles published in the *Antiquarian Horology*, vol. 33-6 & 34-1, for the main discussions about this clock – the photography is taken from the article of S. Whitestone, *The van Call, a modern forgery*, AH 34-1, p.48



 **The question  
of authenticity**

Principle of XRF  
analyses

Experimental  
protocol

Steel and rust

Gilding

The process of fire  
gilding

Analyses

Brass parts


Making brass in the  
17<sup>th</sup> century

Analyses

Conclusion

# The question of authenticity: two examples

- Small clock engraved “Petrus Hele” for Peter Henlein, the presumed inventor of the watch around 1500
- Clock bought in 1897 by the Germanisches Nationalmuseum
- Early suspicions about its authenticity: signature covering the scratches → not original
- Tomographic analyses conducted in 2013 & 2014<sup>3</sup>
- Too many adjustments from the 19<sup>th</sup> century have been found even in the structure of the clock (the plates and some wheel arms recut, some bearings moved...)
- At best a clock that dates from the 16th century but heavily modified in the 19th century (and not by Peter Henlein?), at worst a pure forgery



<sup>3</sup> J. Ehrt, *Ein Mythos auf dem Prüfstand - Die Untersuchungen an der sogenannten Peter Henlein-Uhr des Germanischen Nationalmuseums Nürnberg* (Restaurierungsatelier Jürgen Ehrt, 2021) – photographies from <https://artsandculture.google.com/story/LAXxeqppGOtCLA>



# Principle of XRF analyses

- XRF = X-Ray Fluorescence: non-destructive technology to perform chemical analysis of materials
- Principle :
  1. The sample is bombarded with high energy radiation
  2. Electrons are stripped from the atoms by photoelectric effect → the atoms are in an **unstable state**
  3. Electrons of the atoms come to replace those which were ejected = electronic transition → emission of a photon X whose **energy is characteristic of the atom**
  4. Emitted photons captured by a detector that measures their energy (energy analysis = EDS, for Energy Dispersive Spectroscopy)

Images: [https://fr.wikipedia.org/wiki/Spectrom%C3%A9trie\\_de\\_fluorescence\\_des\\_rayons\\_X](https://fr.wikipedia.org/wiki/Spectrom%C3%A9trie_de_fluorescence_des_rayons_X)

Image from the top by Calvero, public domain.

Image from the bottom by HenrikMidtiby, CC BY-SA 3.0



 Principle of XRF analyses

Experimental protocol

Steel and rust

Gilding

The process of fire gilding

Analyses


Brass parts

Making brass in the 17<sup>th</sup> century

Analyses


Conclusion

number of photons detected



# Experimental protocol

- Measurements done with the scanning electron microscope of the LGPM of CentraleSupélec<sup>4</sup>
- Protocol:
  1. The parts were scraped with a piece of wood to remove surface impurities (when needed)
  2. The parts are installed on aluminium studs with carbon pastilles and steel springs



<sup>4</sup> <https://lgpm.centralesupelec.fr/sites/lgpm/files/inline-files/ESEM.pdf>

Introduction

The question of  
authenticityPrinciple of XRF  
analyses **Experimental  
protocol**

Steel and rust

Gilding

The process of fire  
gilding

Analyses

Brass parts

Making brass in the  
17<sup>th</sup> century

Analyses

Conclusion

# Experimental protocol

---



# Experimental protocol

---

3. Photons collected during 60 seconds (energy of the beam: 20 keV)
  4. Step (3) repeated on other areas of the part depending on the results obtained.
    - When the rust and the impurities have been analyzed, step (1) (cleaning of the analyzed area) has to be avoided.
- 
- Purpose of the analyses:
    - composition of the steel and the rust → classical steel with only iron & carbon? natural rust?
    - composition of the gilding → presence of mercury?
    - composition of the brass parts → consistent with the brass used in the 17<sup>th</sup> century?
    - + comparison with other results gathered on clocks & scientific instruments of the same era (ongoing).
  - Ultimate objective: check the authenticity of the mechanism with a scientific & objective method

## ► Steel and rust

Gilding

The process of fire gilding

Analyses

Brass parts


Making brass in the 17<sup>th</sup> century

Analyses


Conclusion

# Steel and rust: measurements on pivots

- First spectra collected on steel parts “polished” by friction (pivots)
- Observation: detectable elements = iron, carbon, oxygen (because of oxidation), sometimes copper (because of friction in brass bearings) → no additional elements like chromium, nickel, manganese... added since the 19th century <sup>5</sup>, hence “**simple**” steel as expected



Verge



Contrace wheel

<sup>5</sup> N. Chezeau, De Réaumur à la Première Guerre Mondiale : les étapes de la maîtrise de l'acier, l'essor des aciers spéciaux, Comptes Rendus de l'Académie des Sciences – Chimie, vol. 15, July 2012

 **Steel and rust**

## Gilding

The process of fire gilding

## Analyses

## Brass parts


Making brass in the 17<sup>th</sup> century

## Analyses


## Conclusion

# Steel and rust: corrosion products

- Next spectra collected on the rust that covers some steel parts
- Observation: new elements detected that were not seen before: sodium (Na), aluminium (Al), silicium (Si), sulphur (S), chlorine (Cl), potassium (K) & calcium (Ca)
- **They are no “added elements” from the steel** as they are not detected on “clean” areas + sometimes found on brass parts where no rust is visible → **external origin**, but which one?




Right winding wheel




Superposition of the spectra of the ratchet (black line) and the winding arbor (orange)

## ► Steel and rust: origin of the impurities

- Correlation between some elements, notably the couples Al-Si & K-Ca → aluminosilicates?
- When it was rediscovered, the mechanism was covered with a thin layer of brown granular material, probably earth or clay like that found in cements or bricks
- Material consistent with the presence of couples Al-Si & K-Ca + sulphur & iron oxide
- Hypothesis checked by analysing an area where some dirt was accumulated



Sediment agglomeration on front-plate



Spectrum of the "sedimentary" area

  
**▶ Steel and rust**

Gilding

The process of fire gilding

Analyses

Brass parts


Making brass in the 17<sup>th</sup> century

Analyses

Conclusion

# Steel and rust: origin of the impurities

- Would it be possible that brick dust have accumulated in the rust during its formation?
- The rust follows the contour of the parts (e.g. the teeth of the winding wheels and the outlines of the decorations) → formed by **condensation**, repeated hot / cold cycles = water film (dew?) between the decorations / wheels and plates
- Hypothesis reinforced by the presence of cracks on some parts → caused by humidity + chemical reaction with ammonia (traces of nitrogen noted on some spectra)
- Rust propagation in a privileged direction → mechanism stored **horizontally**
- **Conclusion:** the mechanism was probably stored in a garage for several years or decades



Rust on back-plate before cleaning

# Gilding: the process of fire gilding

- Until the 19th century, gilding was performed by mixing gold with mercury to obtain an amalgam that was applied with a brush on the surfaces to be gilded, then the amalgam was heated to evaporate the mercury
- Very aesthetic results but very toxic method... superseded in the 19<sup>th</sup> century by electrolytic gilding
- To see the process in action: [https://www.youtube.com/watch?v=ES\\_NKoVW7Vo](https://www.youtube.com/watch?v=ES_NKoVW7Vo)




Captures from the video (link above), © Dirk Meyer


**► Analyses**

# Gilding: analyses

- Mercury detected in low quantity → “shoulder” near the peak of gold (see left figure)
- Every gilded part analyzed do contain some mercury
- Relative concentrations compared to gold are summarized in the right figure below, always higher than 5% → **it confirms that these parts are indeed fire-gilded**
- Initial concentrations estimated with Margreiter method<sup>6</sup>, consistent with the expectations



Upper side of the right suspension cock



Mercury concentrations measured


<sup>6</sup> R. Margreiter et al., Investigations on fire-gilding, Archaeometry, June 2022

# Brass parts: making brass in the 17<sup>th</sup> century

- Cf. the *Dictionnaire de Chymie* from Macquer<sup>7</sup>:

“On fait un **cement** composé d'une partie & demie de bonne **pierre calaminaire**, & autant de poudre de charbon pulvérisés ensemble : [...] on le met dans un pot de terre ou **creuset** : on y introduit une partie de **cuivre très pur, réduit en lames** : [...] on ferme le creuset, & on le chauffe seulement assez pour le faire bien rougir par dégrés. [...] Lorsqu'il est refroidi, on y trouve le **cuivre devenu jaune, augmenté d'un quart, & quelquefois d'un tiers de son poids**”

- “Calamine” brass that can incorporate only a limited amount of zinc: ~28% if the copper is in plates, ~33% if it is granular
- Experiments conducted recently<sup>8</sup> to reproduce this brass-making process (figures at right)



Arrangement of the elements in the crucible



Metallic conglomerates obtained after cementation

<sup>7</sup> P. J. Macquer, *Dictionnaire de Chymie* – volume 1 (Paris: Lacombe, 1766), p.320

<sup>8</sup> A. Doridot, L. Robbiola & F. Tereygeol, *Production expérimentale de laiton par cémentation en creuset ouvert, avec du minerai de zinc, selon les recettes médiévales et modernes*, ArcheoSciences

Introduction

The question of authenticity

Principle of XRF analyses

Experimental protocol

Steel and rust

Gilding

The process of fire gilding



Analyses

**Brass parts**Making brass in the 17<sup>th</sup> century **Analyses**

Conclusion

# Brass parts: analyses – limitation & uncertainties

- Geometric constraints of the microscope: some parts could not be analyzed (e.g. the teeth filed on the intermediate wheel → insufficient inclination)
- Alteration of the original zinc composition because of **dezincification** = differential corrosion process that causes brass to lose more zinc than copper
  - phenomenon illustrated by 3 spectra collected on different areas of the front-plate
  - similar surface condition on the brass behind the gold layer, areas difficult to analyze



Introduction

The question of authenticity

Principle of XRF analyses

Experimental protocol

Steel and rust

Gilding

The process of fire gilding


Analyses

**Brass parts**Making brass in the 17<sup>th</sup> century

## ► Analyses


Conclusion

# Brass parts: analyses – global results



# Brass parts: detailed analyses

- **Type 1:** most of the structural parts (plates, bridges, some wheels...)
  - high quality brass made from granular copper, used since ~1560 in France and in several countries in Europe to produce scientific instruments <sup>9</sup>
  - mean concentration seen in Le Noir mechanism close to the French one (cf. figure below)
  - **consistent with the alleged period & country of manufacture**



- **Type 2:** parts not gilded or not visible from the back (wheels of the motion-work...)
  - "classical" calamine brass used during the 16<sup>th</sup> century, medium quality
  - possibly dedicated here to the non-visible parts of the mechanism? Example of the barrel: cap of type 1 and gilded, base of type 2 and not gilded nor visible... same for the driving wheel: great wheel of type 1 & teeth visible from the back, pinion of type 2 & not visible

<sup>9</sup> M. Pollard & C. Heron, *Archaeological chemistry – 2nd edition* (RSC Publisher, 2008), p.195 (p.219 for the concentrations by country)

# Brass parts: detailed analyses


- **Type 3:** parts of “low added value” (rivets, pins, bushes) that make the link between some structural parts (T-shape & motion-work bridges) and the decorations of the verge  
 → brass made from remelting of old brass material = higher dispersion of concentrations & less zinc content (because it evaporates during the melting process)  
 → **use of “raw” copper quite common during the Renaissance as it was cheaper** (also on Coster D4<sup>10</sup>)
- **Type 4:**  $[Cu] < 66\%$  (limit of the cementation process)  
 → some modern parts (collet added on the motion-work bridge & repair on the lower potence of the crown wheel)  
 → other parts that seem original: possibly made of the recently invented “Prince Rupert metal” used to mimic gold? Case of the central winding wheel collet: brass part that could not be gilded (because of soldering) but which is visible from the back... same for the verge bearing



Red-copper pins on Coster "D4"



Lower potence of the crown wheel



<sup>10</sup> K. Piggott, A Royal 'Haagseklok', Appendix Three, Open-Research. MEMORANDUM D4 : A Salomon Coster Pendulum Timepiece


# Brass parts: comparative analyses

- Almost no published data on 17<sup>th</sup> century clocks → some experts and museums contacted to try to gather data
- Study of Gregory Bailey on a German table clock signed Johann Scheirer, circa 1675 <sup>11</sup>  
→ the 3 main type of brass seem to be used, with type 1 predominant as expected
- Clocks from Thomas Tompion (1709) and George Graham (1722) <sup>12</sup>: mainly brass of type 2, [Cu] ~ 76% → **this confirms that this type of brass was indeed used by some clockmakers (even the greatest ones)**
- Quid of the simultaneous use of types 1 & 2?  
→ French trigometer of Philippe Danfrie (1580) <sup>13</sup>: both types are present, type 1 with [Cu] ~ 67-68% and type 2 with [Cu] ~ 77-80% → **similar to the Le Noir mechanism**

<sup>11</sup> G. Bailey, *About Time: Analysis and Conservation of a 17th-Century Table Clock*

<sup>12</sup> M. Pollard & C. Heron, *Archaeological chemistry - 2nd edition*, p.225

<sup>13</sup> *ibid*, p.223



Clock from Johann Scheirer – XRF analyses

# Conclusion: summary of the analyses


- Steel without added elements detected (below the limit of detection)
- Fire-gilding used, mercury concentrations consistent with the supposed manufacturing date
- Different brass used:
  - **68% Cu / 32% Zn:** high quality brass for structural parts and gilded parts, as used in the 17<sup>th</sup> century on scientific instruments
  - **77% Cu / 23% Zn:** medium quality brass for non-gilded and non-visible parts
  - **>80% Cu / <20% Zn:** brass from recast? = remelting of old brass for small parts of "low added value"
  - **<66% Cu / >34% Zn:** either modern brass = repairs at the beginning of the 20<sup>th</sup> century, or 17<sup>th</sup>-century brass of type "Prince Rupert" recently invented?

→ globally, the analyses are conclusive and confirm the authenticity of (almost) all the parts of the mechanism


- Bonus: storage of the mechanism over the last decades → probably in a garage where it underwent daily temperature variations, hence condensation + cracks on some parts

# Conclusion: way forward

- End of the EDS analyses for some remaining parts + parts of an Isaac Thuret *pendule religieuse*
- Detailed analyses of some trace elements (Ni, Ag, Bi, Pb, Sb) to identify the place where the copper has been extracted & check the total consistency of some parts between them
- Tomographies already carried out with the LMPS of ENS Paris-Saclay → post-processing in progress, useful to analyze previous repairs / engraved inscriptions & the inner structure



X-ray radiograph of the fusee wheel



3D reconstruction of the wheel

# Bibliography

Bibliographic resources in order of citation in the text:

1. A. Gomand, *Simon Le Noir et l'application du pendule aux horloges : une histoire parallèle ?*, Horlogerie Ancienne, 91, June 2022, online: <https://agomand.github.io/asln/en/documents.html>
2. S. Whitestone, *The van Call, a modern forgery*, Antiquarian Horology, 34-1
3. J. Ehrt, *Ein Mythos auf dem Prüfstand - Die Untersuchungen an der sogenannten Peter Henlein-Uhr des Germanischen Nationalmuseum Nürnberg* (Restaurierungsatelier Jürgen Ehrt, 2021), online: <https://www.uhrenrestaurator.de/de/ein-mythos-auf-dem-pruefstand>
4. [https://fr.wikipedia.org/wiki/Spectrométrie de fluorescence des rayons X](https://fr.wikipedia.org/wiki/Spectrométrie_de_fluorescence_des_rayons_X)
5. <https://lgpm.centralesupelec.fr/sites/lgpm/files/inline-files/ESEM.pdf>
6. N. Chezeau, *De Réaumur à la Première Guerre Mondiale : les étapes de la maîtrise de l'acier, l'essor des aciers spéciaux*, Comptes Rendus de l'Académie des Sciences – Chimie, 15, July 2012, online: <https://doi.org/10.1016/j.crci.2012.04.008>
7. [https://www.youtube.com/watch?v=ES\\_NKoVW7Vo](https://www.youtube.com/watch?v=ES_NKoVW7Vo)

# Bibliography

8. R. Margreiter *et al.*, *Investigations on fire-gilding*, Archaeometry, June 2022, online: <https://onlinelibrary.wiley.com/doi/full/10.1111/arcm.12797>
9. P. J. Macquer, *Dictionnaire de Chymie - volume 1* (Paris: Lacombe, 1766), online: <https://gallica.bnf.fr/ark:/12148/bpt6k1520121f>
10. A. Doridot, L. Robbiola & F. Tereygeol, *Production expérimentale de laiton par cémentation en creuset ouvert, avec du minerai de zinc, selon les recettes médiévales et modernes*, ArcheoSciences, online: <https://journals.openedition.org/archeosciences/107>
11. M. Pollard & C. Heron, *Archaeological chemistry – 2nd edition* (RSC Publisher, 2008)
12. K. Piggott, *A Royal 'Haagseklok'*, Appendix Three, Open-Research. MEMORANDUM D4 : A Salomon Coster Pendulum Timepiece, online: <http://www.antique-horology.org/piggott/>
13. G. Bailey, *About Time: Analysis and Conservation of a 17th-Century Table Clock*, online

The figures that are not associated to any reference are from the author.