



Mix:

-26

Revision 20190717 - Generated 2019-Jul-17

μ_i (reference)	75
Typical AL tolerance	$\pm 10\%$
Color Code	Yellow/White
Density	7.0 g/cm ³
Bsat	18.5kG
Core Loss (100kHz, 140g)	83 mW/cm ³ (nom) 95 mW/cm ³ (max)
%Perm at DC Bias (50 Oe)	55.2% (nom) 47.4% (min)

