



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT

For additional copies call
800-637-3227

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Marcus W. McCluney - CMC Steel AL

Quality Assurance Manager

1SERIES-BPS®

HEAT NO.: 1096119	S	Intsel Steel West LLC-Utah	S	Intsel Steel West	Delivery#: 86062808
SECTION: CHANNEL 8"x18.75# 40'0"	O		H		BOL#: 2808923
A36/572T1	L	1887 S 700 W	I	8573 ULSTER ST	CUST PO#: DEN-26687
GRADE: ASTM A36-19/A572-21e1 Gr50 Tp1	D	SALT LAKE CITY UT	P	COMMERCE CITY CO	CUST P/N:
ROLL DATE: 11/23/2024	US	84104-1705	US	80022-5012	DLVRY LBS / HEAT: 21000.000 LB
MELT DATE: 11/07/2024	T	8014332210	T	9999999999	DLVRY PCS / HEAT: 28 EA
Cert. No.: 86062808 / 096119B609	O	8019726145	O		

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.11%	Elongation Gage Lgth test 1	8IN	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE	
Mn	0.85%	Yield to tensile ratio test1	0.73		
P	0.011%	Yield Strength test 2	50.1ksi		
S	0.024%	Tensile Strength test 2	70.3ksi		
Si	0.17%	Elongation test 2	23%		
Cu	0.30%	Elongation Gage Lgth test 2	8IN		
Cr	0.11%	Yield to tensile ratio test2	0.71		
Ni	0.12%				
Mo	0.034%				
V	0.005%				
Cb	0.008%				
Sn	0.010%				
B	0.0003%				
Ti	0.001%				
N	0.0095%				
Carbon Eq A6	0.31%				
Yield Strength test 1	51.1ksi				
Tensile Strength test 1	70.4ksi				
Elongation test 1	24%				

03.20.2025

REMARKS : ALSO MEETS A709 GR. 36, ASME SA36-08 ADDEND A, M270 GR. 36, M270 GR. 50 TYP 1, A709 GR. 50 TYP 1, A529-50, A992, CSA G40.21 GRADE CAN 44W AND CAN 50W