

Date: 2/26/2025 To: CONTECH ENGINEERED SOLUTIONS SO#: 186337 Lnf#: 3 Part: A4314 PO#: 1718311 Qty: 5 Heat#: 1097247 Tag: 34182-01



CMC STEEL ALABAMA
101 S 50TH STREET
BIRMINGHAM AL 35212-3525

CERTIFIED MILL TEST REPORT
For additional copies call
800-637-3227

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Marcus W. McCluney - CMC Steel AL

Quality Assurance Manager

HEAT NO.:1097247	S	Central Steel Service	S	Central Steel Service	Delivery#: 86127724
SECTION: ANG 4 X 3x1/4 40'0" 709-50WBF3	O		H		BOL#: 76383446
GRADE: ASTM A709-21 Gr50W TpB CVN F3	L	2764 WELBORN ST	I	2764 WELBORN ST	CUST PO#: 34182
ROLL DATE: 01/28/2025	D	PELHAM AL	P	PELHAM AL	CUST P/N:
MELT DATE: 01/18/2025	T	US 35124-1760	T	US 35124-1760	DLVRY LBS / HEAT: 48256.000 LB
Cert. No.: 86127724 / 097247B069	O	8008686798	O	8008686798	DLVRY PCS / HEAT: 208 EA
		2056633391		2056633391	

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.11%	Elongation test 1	22%	The Following is true of the material represented by this MTR: *Material is fully killed and is Hot Rolled Steel *100% melted, rolled, and manufactured in the USA *EN10204:2004 3.1 compliant *Contains no weld repair *Contains no Mercury contamination *Manufactured in accordance with the latest version of the plant quality manual *Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661 *Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov *THE RECORDING OF FALSE, FICTITIOUS OR FRAUDULENT STATEMENTS OR ENTRIES ON THIS DOCUMENT MAY BE PUNISHABLE AS A FELONY UNDER FEDERAL STATUTE	
Mn	0.88%	Elongation Gage Lgth test 1	8IN		
P	0.011%	Yield Strength test 2	62.9ksi		
S	0.022%	Tensile Strength test 2	78.9ksi		
Si	0.33%	Elongation test 2	21%		
Cu	0.33%	Elongation Gage Lgth test 2	8IN		
Cr	0.43%	Charpy - test 1 sample 1	114FPF		
Ni	0.11%	Charpy - test 1 sample 2	88FPF		
Mo	0.033%	Charpy - test 1 sample 3	96FPF		
V	0.037%	Average Charpy test 1	99FPF		
Cb	0.002%	Charpy Orientation test 1	Longitudinal		
Sn	0.017%	Charpy Sample Size test 1	100F		
B	0.0002%	Charpy Test Temp. test 1	100F		
Ti	0.001%	Charpy - test 2 sample 1	70FPF		
N	0.0083%	Charpy - test 2 sample 2	100FPF		
Carbon Eq A6	0.39%	Charpy - test 2 sample 3	78FPF		
ASTM G101 Corrosion Index	6.3000%	Average Charpy test 2	83FPF		
Yield Strength test 1	62.5ksi	Charpy Orientation test 2	Longitudinal		
Tensile Strength test 1	79.7ksi	Charpy Sample Size test 2	100F		
		Charpy Test Temp. test 2	100F		

REMARKS : ALSO MEETS ASTM A588 GRADE A AND B, A572 GRADE 50 TYPE 2, A709 GRADE 50 TYPE 2, AASHTO M270 GRADE 50 TYPE 2 AND 50W

REVIEWED
JPC
03.07.2025