

Atlas Tube Arkansas  
6651 E Hwy 137  
Blytheville Arkansas USA  
72315  
Tel:  
Fax:



REF.B/L: 81298029  
Date: 05/21/2025  
Customer: 139

## MATERIAL TEST REPORT

### Sold To

Intsel Steel West  
COMMERCE CITY CO 77226  
USA

### Shipped To

Intsel Steel West  
8573 Ulster St.  
COMMERCE CITY CO 80022  
USA

Material: 10.0x10.0x375x40"0"0(2x2).

Material No: 1001003754000

Made in: USA

Melted and Poured in: USA

Sales Order: 2180466

Purchase Order: DEN-27239

| Heat No   | C     | Mn    | P     | S     | Si    | Al    | Cu    | Cb    | Mo    | Ni    | Cr    | V     | Ti    | B      | N      | Ca     |
|-----------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|--------|--------|
| 822K36240 | 0.220 | 0.890 | 0.011 | 0.004 | 0.008 | 0.047 | 0.018 | 0.005 | 0.005 | 0.010 | 0.040 | 0.001 | 0.002 | 0.0002 | 0.0030 | 0.0002 |

| Bundle No  | PCs | Yield      | Tensile    | Eln.2in | Certification          | CE: 0.38 |
|------------|-----|------------|------------|---------|------------------------|----------|
| M500566325 | 4   | 063881 Psi | 078655 Psi | 30 %    | ASTM A500-23 GRADE B&C |          |

| Heat      | MILL     | Mill Location    | Method | Recycled_Content | Post_Consumer | Pre-Consumer (Post Industrial) | % Harvested | Within Miles of Location |
|-----------|----------|------------------|--------|------------------|---------------|--------------------------------|-------------|--------------------------|
| 822K36240 | CLIFFSST | Burns Harbor, IN | BOF    | 34.00%           | 8.16 %        | 25.84%                         | 100%        | 700                      |

Material Note:

Sales Or. Note:

Material: 16.0x12.0x375x36"0"0(1x1).CTMIL

Material No: 160120375

Made in: USA

Melted and Poured in: USA

Sales Order: 2190255

Purchase Order: DEN-27274


| Heat No  | C     | Mn    | P     | S     | Si    | Al    | Cu    | Cb    | Mo    | Ni    | Cr    | V     | Ti    | B      | N      | Ca     |
|----------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|--------|--------|--------|
| 24091442 | 0.200 | 0.820 | 0.011 | 0.004 | 0.030 | 0.035 | 0.100 | 0.002 | 0.009 | 0.040 | 0.050 | 0.003 | 0.001 | 0.0001 | 0.0082 | 0.0021 |

| Bundle No  | PCs | Yield      | Tensile    | Eln.2in | Certification          | CE: 0.36 |
|------------|-----|------------|------------|---------|------------------------|----------|
| 0003779363 | 1   | 057590 Psi | 079220 Psi | 31.8 %  | ASTM A500-23 GRADE B&C |          |

| Heat     | MILL     | Mill Location | Method | Recycled_Content | Post_Consumer | Pre-Consumer (Post Industrial) | % Harvested | Within Miles of Location |
|----------|----------|---------------|--------|------------------|---------------|--------------------------------|-------------|--------------------------|
| 24091442 | BIGRIVER | Osceola, AR   | EAF    | 76.00%           | 95.00%        | 5.00 %                         | 75%         | 500                      |

Material Note:

Sales Or. Note:

Authorized by Quality Assurance:   
Jason Richard

REVIEWED  
JPC  
06.05.2025

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.

