

DRY BACKFILL MIXES

PROTECH has developed the FOR RAM series dry lining mixes for avoiding infiltrations and running behind the bricklaid safety lining. These are high quality alumina- or magnesite-based ceramically bonding products.

The dry lining mixes are easy to process without any further aid. They are simply poured between the brick rings and the safety lining during the bricklaying of the wall and rammed by hand.

DRY BACKFILL MIXES

Chemical Analysis

MgO	90%
CaO	3-5%
SiO ₂	5%
Fe ₂ O ₃	1-3%
Type of Bonding,	Chemical
Grain Size, mm	0-3mm
<u>Physical Properties</u>	
Refractoriness °C	1610
Max Service Temperature, °C	1560

Physical Properties

