

Silica Ramming Mass

PROTECH has developed the Silica Ramming Mass is used in the lining of induction furnaces. Quality of Acidic Ramming mass is directly related to the heating performance 17-18 heats of the furnaces. Better quality of lining results in the smooth working of furnaces, optimum output and better metallurgical control. It is manufactured under strict supervision of qualified & experienced work force. Proper check is exercised on magnetic process to assure from free material and to assure proper composition of granules according to furnace capacity. The granulation of the mix is optimized keeping in view the furnace makes and capacity, thus giving maximum and best results. It is characterized by thermal stability, corrosion resistance and wear resistance because it contains less binders, fire clay and moisture compared to plastic refractories.



Silica Ramming Mass	
Application,	Dry Ramming
Chemical Composition.	
Moisture	≥ 0.10 %
SiO ₂	98.00%
Fe ₂ O ₃	≥ 0.01 %
H ₃ BO ₃	≥ 1.30 %
Physical Properties.	
Method of Application,	Ramming
Max Service Temperature, °C	1715
GRAIN SIZE	any size