

Applications of EBT Sand

Olivine sand, due to its high melting point and sinter, low heat loss and resistance to thermal shocks has applications in refractory and steel manufacturing industries. Some of such applications are:

- Usage for filling the EBT value of the electric arc furnaces
- Application in producing Tandish cover.
- Application in producing magnesium-chromium bricks and low-magnesium bricks
- For covering the back wall in the AOD convertors.



EBT OLIVINE SAND	
Chemical Analysis	
MgO	47-50 %
CaO	0.5-1 %
SiO ₂	39%
Fe ₂ O ₃	6-10 %
Type of Bonding,	Chemical
Grain Size, mm	2-6mm