

شركة تيسير إنترناشيونال للكيماويات TAYSEER INTERNATIONAL CHEMICALS CO.

Technical Data Sheet (TDS) Yellow Iron Oxide

| Parameters | Specification |
|--------------------------------|----------------|
| Appearance | Yellow powder |
| Na ₂ O | 0.09 |
| MgO | 0.48 |
| Al_2O_3 | 4.91 |
| SiO ₂ | 9.92 |
| P ₂ O5 | 0.53 |
| K ₂ O | 0.55 |
| CaO | 0.19 |
| TiO ₂ | 0.26 |
| MnO | Max. 0.07 |
| Fe ₂ O ₃ | Min. 68.0 |
| Fe | Min. 45 |
| NiO | 0.06 |
| ZnO | NIERNO.05 UNFL |
| Cl | 0.05 |
| LOI | Max. 15 |
| Particle Size | =<150 micron |