

Bondtite Fast & Clear is a “5 min” high strength two-component transparent epoxy adhesive system. It can be used as an adhesive for a wide range of materials or as a versatile filler for gap bonding, surface repairs and to bond various substrates like metal, ceramic, wood, chrome, concrete, marble, glass, fiberglass, tiles etc. Curing time of Bondtite Fast & Clear is unaffected from temperature so even at lower temperature you will get pot life of 5 min.

#### FEATURES

- 5 Min adhesive
- Rapid bonding
- Clear and transparent Bond line
- It remains unaffected to mild alkalis, acids etc.
- It is nontoxic and electrically insulating adhesive and does not shrink and is resistant to water and most common solvents.
- It can be tinted with earth pigments, cement or sand for colour matching and can be sanded and drilled.

#### APPLICATIONS

- Small part bonding/assembly
- Rapid bonding application

Bondtite Fast & Clear is 5 min epoxy so it can be used at those places where instant strength is required.

#### HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Squeeze equal volume of material from both part-A & part-B tube. Mix resin and hardener for one minute thoroughly and then apply as per requirement.

For best results apply a small amount of mixed adhesive to both surfaces within one to two minutes of mixing and press together. Placing parts together close to the 5-minute set time will reduce adhesion. Remove any excess glue immediately with acetone. Support bond for 10 minutes at room temperature. Usable strength achieved in 1 hour. Fully cured in 24 hours.

#### TECHNICAL DETAILS

| PROPERTIES         | STANDARD           | RESULTS                     |
|--------------------|--------------------|-----------------------------|
| PART-A             |                    |                             |
| Physical state     |                    | Viscous Liquid              |
| Appearance         |                    | Transparent                 |
| Color              |                    | Milky white / Colorless     |
| Viscosity at 25°C  | ASTM D 2196-5      | 60000 – 80000 CPS           |
| PART-B             |                    |                             |
| Physical state     |                    | Viscous Liquid              |
| Appearance         |                    | Transparent                 |
| Color              |                    | Colorless/ Slight Yellowish |
| Viscosity at 25°C  | ASTM D 2196-5      | 15000 – 25000 CPS           |
| CURING PROPERTIES  |                    |                             |
| Mixing ratio (R:H) |                    | 100:100                     |
| Pot life at 25°C   |                    | 3-6 min                     |
| Shore-D-Hardness   | ASTM D 2240        | 80-85                       |
| Lap Share Strength | ASTM - D 1002 - 10 | 15 – 30 kg/cm <sup>2</sup>  |

#### RESTRICTION OF USE

- Does not bond to polyethylene or polypropylene plastics.
- Applications requiring short-term heat exposure of greater than 150°C.
- Continuously wet areas or water immersion.

#### SHELF LIFE

2 years from date of mfg. (Storage Temp 2-40°C)

#### DISPOSAL

Regular procedures approved by local authorities.

#### Operating Temperature

-20°C to 90°C

#### STORAGE

Product should be stored below 40°C in a cool & dry place away from sunlight in properly tight container.

#### PACKING

3 gm, 6 gm, 13 gm, 36 gm, 60 gm, 90 gm, 180 gm, 270 gm, 500 gm set, 1 Kg set & 2 kg set

#### HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheets and the brochure "Hygienic precautions for handling plastics products".

#### Hazardous Decomposition Products

Oxides of carbon; aldehydes, acids and other organic substances may be formed during combustion or elevated temperature (>500°F) degradation.

**IMPORTANT:** No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



#### ASTRAL LIMITED

**Registered Office:** 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.  
P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

**E-mail:** [customer@astraladhesives.com](mailto:customer@astraladhesives.com) **Website:** [www.astraladhesives.com](http://www.astraladhesives.com)



**MORE  
CONVENIENCE**



**FASTER  
FEEDBACK**



**ADDRESS TO  
TECHNICAL QUERY**

Experience A Better Connect With The Company

**Exclusively for our  
Channel Partners & Customers**

Visit us at:

[wecare.astraladhesives.com](http://wecare.astraladhesives.com)