

BONDITE METALLIC is a metal filled, fast setting, high strength two-component epoxy adhesive system, which is specially developed for bonding two different metal surfaces.

ADVANTAGES

- Gives metal finish look.
- Excellent for metal repairing works.
- High lap shear strength

APPLICATIONS

- Main gate of bungalow.
- Sealing of screw heads.
- Drilled hole filling.
- To hide welding marks & undulation in window, staircase grills
- Machinery repairs
- Filling blow holes in steel castings.

HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Squeeze equal volume of material from both part-A & part-B tube Remove the plug from between the pistons. Mix resin and hardener for one minute thoroughly and then apply as per requirement.

For best results apply a small amount of mixed adhesive to both surfaces within one to two minutes of mixing and press together. Placing parts together close to the 5-minute set time will reduce adhesion. Remove any excess glue immediately with acetone. Support bond for 10 minutes at room temperature. Usable strength achieved in 1 hour. Fully cured in 24 hours.

RESTRICTION OF USE

- Does not bond to polyethylene or polypropylene plastics.
- Applications requiring short-term heat exposure of greater than 150°C
- Continuously wet areas or water immersion.

TECHNICAL DETAILS

PROPERTIES	STANDARD	RESULTS
PART-A		
Physical state		Gel / Paste
Appearance		Opaque
Color		Silver black
Viscosity at 30°C	ASTM D 2196-05	3000 – 4000 Ps
PART-B		
Physical state		Viscous liquid
Appearance		Opaque
Color		Grey
Viscosity at 25°C	ASTM D 2196-05	3 – 4 lac cps
CURING PROPERTIES		
Mixing ratio (R:H)		100:100 by volume
Pot life at 25 °C (100 gm mass) Minutes	ASTM D 2174	3 - 6 min
Shore D Hardness (at 25°C after 24 hrs.	ASTM D 2240-10	70-80 min
Lap Shear Strength (at 25°C after 24	ASTM - D 1002-10	30 – 60 kg/cm ²

SHELF LIFE

24 months from date of manufacturing.

HAZARDOUS DECOMPOSITION PRODUCTS

Oxides of carbon; aldehydes, acids and other organic substances may be formed during combustion or elevated temperature (>500° F) degradation.

DISPOSAL

Regular procedures approved by local authorities.

STORAGE

Product should be stored between 2- 40°C in a cool & dry place away from sunlight in properly tight container. Partially emptied container should be closed immediately.

PACKING

12 g, 36 g, 90 g.

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheets and the brochure "Hygienic precautions for handling plastics products"

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

**ASTRAL LIMITED**

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.
P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customer@astraladhesives.com **Website:** www.astraladhesives.com



**MORE
CONVENIENCE**



**FASTER
FEEDBACK**



**ADDRESS TO
TECHNICAL QUERY**

Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com