

BONDTITE PVC BOND is a new generation adhesive for bonding substrate like PVC sheet where regular white adhesive or rubber adhesive does not work well. It is the best glue for pasting PVC sheets and PVC edge banding tapes to any of the wooden surfaces like MDF, HDHMR or Plywood. It needs to be applied on both surfaces for pasting PVC sheets while over only one surface for pasting edge banding PVC tapes over MDF, HDHMR or Plywood.

FEATURES & BENEFITS

- Excellent compatibility with PVC & Acrylic surfaces to provide best fixing solution
- Sufficient strength with long & durable bonding with PVC edge banding.
- Excellent spread ability and high coverage which saves cost.
- Excellent heat resistance for heat prone applications.

AREAS OF APPLICATIONS

BONDTITE PVC Bond can be used in following applications

- PVC sheets to Plywood |MDF|HDHMR | Wooden Surfaces
- PVC edge banding to Plywood |MDF|HDHMR | Wooden Surfaces
- Charcoal sheet to Plywood |MDF|HDHMR | Wooden Surfaces
- Paper Laminates to Plywood |MDF|HDHMR | Wooden Surfaces

HOW TO USE

- Surface to be bonded should be dry, clean and free from oil or grease.
- First apply adhesive uniformly on back side of PVC laminate sheet and then apply over Plywood |MDF | Particle board followed by spreading it uniformly.
- For PVC edge Banding Tape, apply glue only on Plywood |MDF|Particle board followed by spreading the glue uniformly on edge with the help of spreader /Knife of spatula.
- Give open time of 5-10 minute under standard operating condition.
- Before the adhesive film dries up, bring PVC sheet or edge banding tape in contact with glue coated Plywood|MDF | Wooden surface and make the proper alignment.
- Apply pressure on the laminated by hand using a wet squeezed cloth to remove any entrapped air and avoid the bubble.
- Excess glue oozing out to be removed softly and carefully using wet cotton cloth.
- Press the edge band joint for 2-5 minutes under the manual hand pressure and use the masking tape to hold the joint firmly.
- Leave the laminated sheet in ambient conditions to set. Handling strength is to be obtained within 4 - 6 hrs, however full strength will be developed after 24 hr @ room temperatures.

STORAGE

Product should be stored below 40°C in a cool & dry place away from sunlight in properly tight container.

TECHNICAL DETAILS

PROPERTIES	TESTING STAN- DARD	SPECIFICATION	UNIT
Physical State	-	Viscous liquid	
Color	-	White	
Viscosity @30°C	ASTM D 2196-05	2500-7000	Poise
Specific Gravity @ 25°C	ASTM D 1475	1.05 - 1.07	gm/cc
pH		4 – 6.5	

SHELF LIFE

18 months in unopened packaging in dry and cool storage place, at temperatures between 5°C to 25°C.

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheet.

PACKING

1 kg, 5 kg

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India. P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com Website: www.astraladhesives.com



MORE
CONVENIENCE



FASTER
FEEDBACK



ADDRESS TO
TECHNICAL QUERY

Experience A Better Connect With The Company

Exclusively for our
Channel Partners & Customers

Visit us at:

wecare.astraladhesives.com