

BONDITITE QUICK is a low viscosity cyanoacrylate instant adhesive used for various general-purpose applications. It is supplied in attractive user-friendly plastic ampoule. First time in globe LDPE is being used to fill Super glue which gives controlled flow and easy squeezability.

APPLICATIONS

BONDITITE QUICK is used for instant repair of broken item as it bonds most of the plastic, metal, alloys, marble, rubber, polycarbonate, epoxy, Bakelite, ceramics and other common substrates. Recommended for use on assemblies with very close fitting part's and smooth, even surfaces. It gives instant bonding even on expensive items like jewellery, antiques and electronics.

BONDITITE QUICK can be used in any general purpose application like repairing of any auto assembly, crockery, jewellery, clock, plastic toy, electronics & home appliances etc.

FEATURES & BENEFITS

- Better Flow & penetration
- Colorless
- Cost effective due to multiple usage as three enclosures are present
- Higher shelf life as material is filled under inert atmosphere

HOW TO USE

- Make sure the surfaces to be bonded are clean and dry
- For opening of ampoule, hold the ampoule in vertical position and tap the cap so that whatever material present in neck area should be drop down
- Now twist the cap to open the ampoule
- Dispense a drop or drops to one surface only. Apply enough quantity to achieve a thin film after compression. Curing time can vary based on amount of glue and type of surface glued. Excess glue can cause delayed or bond failure
- Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute based on the substrate
- Wipe off excess adhesive from the top of the nozzle and recap BONDITITE QUICK to the three re-closures given on the cap. If left uncapped, may deteriorate by contamination from moisture in the air
- Because BONDITITE QUICK condenses by polymerization, sometimes whitening will occur on the surface of the ampoules when humidity is high

RESTRICTION OF USES

Not recommended for polyethylene, Polypropylene EPDM Rubber, Silicone rubber, Teflon, Styrofoam etc.

TECHNICAL DETAILS

PROPERTIES	TESTING	RESULTS
Physical state	-	Low Viscous Liquid
Appearance	-	Transparent
Color	-	Colorless
Viscosity @25°C	ASTM D 2196-05	2-5 cps
Sp. GRAVITY @ 25°C	ASTM D 1475	1
Setting Time (sec)		2 - 4 Sec
Tensile Strength (KG/CM ²)	ASTM-D 1002-10	60-80

*Curing speed and strength may vary for different substrates and thickness of adhesive applied.

SHELF LIFE

10 months from date of manufacturing when stored in the original unopened pouch. Use within 30 days once opened. Without warranty as storage condition will affect the shelf life.

STORAGE

Keep products in the unopened packaging in a cool and strictly in dry location. Best when stored product in a cool, dry place at temperature 20-25°C and humidity not more than 50%. Temperatures less than 2°C can adversely affect product properties. Do Not Freeze. Keep packing tightly closed until ready for use.

HANDLING PRECAUTIONS

BONDITITE QUICK bonds with skin or any other body part. In case of skin bonding, do not pull apart. Soak in warm water or nail polish remover and peel slowly. In case of eye contact, rinse cautiously with plenty of water for several minutes, if irritation persists: Get medical advice. Keep out of reach of children. For additional information please consult the material safety data sheet.

PACKING

Plastic ampoule: 500 mg

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.
P: +91 79 6621 2000 | F: +91 79 6621 2121 CIN: U24295GJ2009PLC058120
E-mail: customer-care@resinova.com Website: www.astraladhesives.com



**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com