

Bondtite Rapid is a fast setting two-component epoxy adhesive system. It can be used as an adhesive for a wide range of materials like metal, ceramic, wood, chrome, concrete, marble, glass, fiberglass, tiles, etc.

ADVANTAGES

- Sets in 10 minutes
- Solvent free
- It works on surfaces such as porcelain, ceramic, marble, granite, concrete, asbestos, glass, metal & wood

APPLICATIONS

- Bondtite Rapid is fast setting epoxy so it can be used at those places where instant strength is required.
- It remains unaffected to mild alkalis, acids etc.
- It is nontoxic and electrically insulating Adhesive and does not shrink and is resistant to water and most common solvents.

HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Squeeze equal volume of material from both part-A & part-B tube Remove the plug from between the pistons. Mix resin and hardener for one minute thoroughly and then apply as per requirement.

For best results apply a small amount of mixed adhesive to both surfaces within one to two minutes of mixing and press together. Placing parts together close to the 10-minute set time will reduce adhesion. Remove any excess glue immediately with acetone. Support bond for 10-15 minutes at room temperature. Usable strength achieved in 1 hour. Fully cured in 24 hours.

TECHNICAL DETAILS

PROPERTIES	STANDARD	RESULTS
PART-A		
Physical state		Viscous Liquid
Appearance		Opaque
Color		White
Viscosity @ 25°C	ASTM D2196-05	3 – 3.5 lac cps
PART-B		
Physical state		Viscous liquid
Appearance		Transparent
Color		Yellowish
Viscosity @ 25°C	ASTM D2196-05	40000-60000 cps
CURING PROPERTIES		
Mixing ratio (R:H)		100:100 by volume 100:75 by weight
Pot life @ 25°C	ASTM D 2471	9-14 min
Shore D Hardness	ASTM D 2240	75-80
Lap shear strength	ASTM – D 1002-10	70-100 kg/cm ²

SHELF LIFE

24 months from date of manufacturing.

HAZARDOUS DECOMPOSITION PRODUCTS

Oxides of carbon; aldehydes, acids and other organic substances may be formed during combustion or elevated temperature (>500° F) degradation.

DISPOSAL

Regular procedures approved by local authorities.

STORAGE

Product should be stored below 40°C in a cool & dry place away from sunlight in properly tight container.

PACKING

3 gm, 10 gm, 35 gm, 87.5 gm, 175 gm, 875 gm set
& 1.75 kg set

HANDLING PRECAUTIONS

Product should be stored below 40°C in a cool & dry place away from sunlight in properly tight container.

NOTE: - The information provided in this document including the recommendations for use and application of the product are based on our knowledge and experience of the product. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Company is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

**ASTRAL LIMITED**

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.

P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customer@astraladhesives.com Website: www.astraladhesives.com



**MORE
CONVENIENCE**



**FASTER
FEEDBACK**



**ADDRESS TO
TECHNICAL QUERY**

Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com