

Bondtite Strong & Clear is high strength two-component transparent epoxy adhesive system. It can be used as an adhesive for a wide range of materials or as a versatile filler for gap bonding, surface repairs and to bond various substrates like metal, ceramic, wood, chrome, concrete, marble, glass, fiberglass, tiles etc.

FEATURES

- 15 Min pot life.
- 30 min setting time.
- Strong bonding
- Clear and transparent bond line
- No odour
- It remains unaffected to mild alkalis, acids etc.
- It is nontoxic and electrically insulating adhesive and does not shrink and is resistant to water and most common solvents.

APPLICATIONS

- Medium and large part bonding/assembling.
- Strong bonding applications.

Bondtite Strong & Clear can be used at those places where clear bonding line & strength is required.

HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Take equal volume of material from both part-A & part-B. Mix resin and hardener for one minute thoroughly and then apply as per requirement.

For best results apply a small amount of mixed adhesive to both surfaces after one to two minutes of mixing and press together. Placing parts together close to the 30-minute. Remove any excess glue immediately with acetone. Support bond for 1 hr at room temperature. Full cured in 24 hours.

TECHNICAL DETAILS

PROPERTIES	STANDARD	RESULTS
PART-A		
Physical state		Viscous Liquid
Appearance		Transparent
Color		Colorless
Viscosity at 25°C	ASTM D 2196-5	8000 – 13000 CPS
PART-B		
Physical state		Viscous Liquid
Appearance		Transparent
Color		Colorless
Viscosity at 25°C	ASTM D 2196-5	10000 – 20000 CPS
CURING PROPERTIES		
Mixing ratio (R:H)		100:100
Pot life at 25°C		15 min
Setting time (at 25°C)		30-35 min
Shore-D-Hardness	ASTM D 2240	70-80
Lap Share Strength at 25°C after 24 hrs.	ASTM - D 1002 - 10	40 – 70 kg/cm ²

RESTRICTION OF USE

- Does not bond to polyethylene or polypropylene plastics.
- Continuously wet areas or water immersion.

SHELF LIFE

2 years from date of mfg. (Storage Temp 2-40°C)

DISPOSAL

Regular procedures approved by local authorities.

OPERATING TEMPERATURE

-20°C to 90°C

STORAGE

Product should be stored below 2-40°C in a cool & dry place away from sunlight in properly tight container.

PACKING

500 gm set, 1 Kg set & 1.8 kg set

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheets and the brochure "Hygienic precautions for handling plastics products".

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.

P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customer@astraladhesives.com Website: www.astraladhesives.com



**MORE
CONVENIENCE**



**FASTER
FEEDBACK**



**ADDRESS TO
TECHNICAL QUERY**

Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com