

Bondtite Super Strength is a high strength two component epoxy adhesive system. These systems are tailor made where extremely high bond strength is required for various similar and dissimilar materials such as metals, ceramics, wood, leather, rubber, marble, granite, glass etc. Bondtite Super Strength remains unaffected to mild alkalis and acids etc., it is nontoxic and insulating.

APPLICATIONS

Electrical and Electronics

Automobiles for fixing electro magnet to flywheels, bonding brake lining to shoes, plugging holes in cylinder blocks, fixing head light reflector and glass to rim , bonding metal part to miniature bulbs, for linear placement in engine, for insulating high speed motors and fixing wipers on car.

Miscellaneous

For joining of marbles, wash basin pieces and repairing of chipped sanitary ware, to bond concrete chips at the back of the polished granite tiles, to seal cracks in walls, for assembly of bath fitting and gate valves, as an adhesive in bangles and brassware handicrafts & in manufacturing of sports goods like tennis racket, polo stick, shuttle cock, hockey sticks etc.

Appliances

Fixing name plates, bonding steel body to grinding stone in wet grinder, for assembly of mixers, washing machines, gas stoves, for fixing loose handle of tools, fixing of drains, hoses & sealing of tank joints in washing machines.

TECHNICAL DETAILS

HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Wash glass and ceramic surfaces with soap and water then rinse and let dry. Pre-fit parts to be joined. Squeeze equal volume of material from both part-A & part-B. Mix resin and hardener for one minute thoroughly and then apply as per requirement. Fully cured in 24 hours.

RESTRICTION OF USE

- Does not bond to polyethylene or polypropylene plastics.
- Applications requiring short-term heat exposure of greater than 150°C.
- Continuously wet areas or water immersion.

PROPERTIES	STANDARD	RESULTS
PART-A		
Physical State		Viscous liquid
Appearance		Opaque
Color		Milky White
Viscosity at 25°C	ASTM D2196-05	45,000-55,000 cps
PART-B		
Physical State		Viscous liquid
Appearance		Transparent
Color		Yellow
Viscosity at 25°C	ASTM D2196-05	35,000-45000 cps
CURING PROPERTIES		
Mixing Ratio		100:80 (By weight), 100:100 (By Volume)
Pot-life at 25°C	ASTM D 2471	75-95 min
Shore-D-Hardness	ASTM D 2240	75-80
Lap shear strength at 25°C after 24 hrs.	ASTM D 1002-10	100-150 kg/cm ²

OPERATING TEMPERATURE

-20°C to 90°C

HAZARDOUS DECOMPOSITION PRODUCTS

Oxides of carbon; aldehydes, acids and other organic substances may be formed during combustion or elevated temperature (>500° F) degradation.

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheets and the brochure "Hygienic precautions for handling plastics products".

PACKING

3 gm, 7 gm, 13 gm, 36 gm, 60 gm, 90 gm, 180 gm, 270 gm, 450 gm set, 900 gm set, 1.8 kg set, 3.6 kg set & 9 kg set

SHELF LIFE

2 years from date of mfg. (Storage Temp 2-40°C)

DISPOSAL

Regular procedures approved by local authorities.

STORAGE

Product should be stored in a dry place in their original, properly closed containers at temperature between 2-40°C. Partially emptied container should be closed immediately.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.

P: +91 79 6621 2000 | F: +91 79 6621 2121 CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com Website: www.astraladhesives.com



Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com