

Bondtite Uniweld is a high strength two component high technology adhesive system. This system has been designed for applications where extremely high bond strength is required. It bonds various similar and dissimilar substrates such as metals, rigid plastics (ABS, PVC, PU, Polycarbonate). FRP, Ferrite, Ceramic, Wood, Leather, Rubber, Marble, Glass etc. This system has unique property of achieving high bond strength even if the surfaces to be bonded have traces of oil.

APPLICATIONS

Bondtite Uniweld is a two-part structural adhesive with many applications and having excellent impact strength. It is used in automobiles for fixing electromagnet to flywheels, bonding brake lining to shoes, bonding metal parts to glass in miniature bulbs, for liner placement and repairing in engine.

Electrical and Electronics

Fixing of magnets to metal pieces in watt hour meter, fixing aluminium caps to glass shells in night bulbs manufacturing, bonding of cooling coils to freezers in refrigerators, fixing diaphragms and magnets to base plate of speaker.

Miscellaneous

For fixing name plates and sign boards, joining of marbles, wash basin pieces and repairing of chipped sanitary ware, to repair broken picture frames, in repairing jewelry, to stick broken toys and brassware handicrafts & in manufacturing of sports goods like tennis racket, polo sticks etc.

Appliances

For assembly of mixers, washing machines, gas stoves. For fixing loose handles of tools, fixing of drains, hoses, sealing of tank joints in washing machines.

HOW TO USE

Surfaces must be clean, dry and free from oil, wax and paint. Roughen smooth surfaces for better adhesion by sandblasting or sanding with emery cloth. Take out equal quantities from both tubes separately. Apply part A on one surface and Part-B on another surface. Attach both surfaces one over the other, rub it and wait for 20 minutes. Sets rapidly in 3-5 minutes, attains full strength in 2 hours.

RESTRICTION OF USE

Bondtite Uniweld should not be used in under water application or on damp surface.

OPERATING TEMPERATURE

-20°C to 90°C

TECHNICAL DETAILS

PROPERTIES	STANDARD	RESULTS
PART-A		
Physical State		Viscous liquid
Appearance		Transparent
Color		Light green
Viscosity @25°C	ASTM D2196-05	2700 – 3000
PART-B		
Physical State		Viscous liquid
Appearance		Opaque
Color		Light Red
Viscosity @25°C	ASTM D2196-05	9000-10000 cps
CURING PROPERTIES		
Mixing Ratio		100:100
Pot life @ 25°C	ASTM D 2471	2-5 min
Lap shear strength	ASTM D 1002-10	150-200 kg/cm2

HAZARDOUS DECOMPOSITION PRODUCTS

Oxides of carbon; aldehydes, acids and other organic substances
may be formed during combustion or elevated temperature (>500°
F) degradation

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheets and the brochure "Hygienic precautions for handling plastics products".

PACKING

3 gm, 7 gm, 12 gm, 36 gm, 60 gm, 90 gm, 180 gm, 270 gm,
500 gm, & 2 kg

SHELF LIFE

12 months from date of mfg. (Storage Temp 2-40 °C)

STORAGE

Product should be stored in a dry place in their original, properly closed containers at temperature between 2-40°C. Partially emptied container should be closed immediately.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India.
P: +91 79 6621 2000 | F: +91 79 6621 2121 CIN: L25200GJ1996PLC029134
E-mail: customercare@astraladhesives.com Website: www.astraladhesives.com



Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com