

**BONDTITE WPC FIX** is an innovative adhesive formulated with an advanced technology. It's a fast curing, heat and weather resistant ( up to 100°C) hi-tech adhesive.

### FEATURES & BENEFITS

- High initial grab
- Fast setting & Bonds difficult substrates
- Low VOC & Low odour
- Quick grab | Heat resistance | Waterproof

### AREAS OF APPLICATIONS

**BONDTITE WPC FIX** can be used for bonding WPC / PVC board to decorative laminates, veneer, metal sheet, glass, PVC sheet, acrylic sheet, wood, etc.

### HOW TO USE

#### Surface preparation: -

- Ensure both the surfaces are clean and free from contaminants like oil, grease, dust etc.
- Scratch WPC surface in criss-cross manner preferably with laminate cutter or sand this surface with 80 to 120 no. emery paper to make it rough

#### Application: -

- Apply BONDTITE WPC FIX evenly using spreader on sanded or scratched WPC surface for full coverage over surface. Leave surface applied with adhesive as it is up to 8 -10 minutes for drying.
- Wipeout backside of top surface to be bonded over WPC | PVC Board (laminate, PVC sheet, Acrylic Sheet, Veneer etc.) with moist cloth (water droplet should not be dripping down while wiping so if excess water is there then wipe out surface with another dry cloth)
- For faster drying leave this up to 10 -20 Minutes (During monsoon season | rainy day don't use any moist cloth since environment is already having high moisture)
- Bring both surfaces together, align & apply even pressure by rubbing with dry cloth or roller, press machine for getting a good bond.
- Keep bonded surface together under pressure with the help of clamps, nails, tape etc. up to 2-3 Hrs.
- Handling strength will be obtained within 2-3 Hrs.
- Full bond strength development will be reached in 24 hours for best performance post which cutting is advisable.
- Vertical application is not recommended.

### STORAGE

Product should be stored below 40°C in a cool & dry place away from direct sunlight in air-tight container.

### TECHNICAL DETAILS

| PROPERTIES                                        | TESTING STANDARD | SPECIFICATION  | UNIT               |
|---------------------------------------------------|------------------|----------------|--------------------|
| Physical State                                    |                  | Viscous Liquid |                    |
| Appearance                                        |                  | Opaque         |                    |
| Colour                                            |                  | OFF White      |                    |
| Density at 25° C in                               |                  | 1.48 -1.52     | gm/cc              |
| Drying time 120 µ at 25°C                         |                  | 20-25          | Min.               |
| Lap Shear Strength in 24 Hrs                      | ASTM - D 1002-10 | 11-15          | Kg/cm <sup>2</sup> |
| Lap Shear Strength (after 24 hrs.) – wood to wood | ASTM - D 1002-10 | 18-25          | Kg/cm <sup>2</sup> |
| Lap Shear Strength (after 7 days) – wood to wood  | ASTM D 4541      | 120-150        | Kg/cm <sup>2</sup> |

### SHELF LIFE

12 months in unopened packaging in dry and cool place at temperatures between 5°C to 25°C

### HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheet.

### PACKING

600 mL

**IMPORTANT:** No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



#### ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India. P: +91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: [customercare@astraladhesives.com](mailto:customercare@astraladhesives.com) Website: [www.astraladhesives.com](http://www.astraladhesives.com)



Experience A Better Connect With The Company

**Exclusively for our  
Channel Partners & Customers**

Visit us at:

[wecare.astraladhesives.com](http://wecare.astraladhesives.com)