

BONDTITE HYDRA+ is a single component premium white PVA emulsion adhesive with superior waterproof properties. Usually due to change in weather & humidity all bonded wooden joints and surfaces undergoes a lot of stress and tends to open joints. It also causes de-bonding of laminates.

BONDTITE HYDRA+ is a specially designed for bonding applications in furniture's for such areas.

FEATURES & BENEFITS

- High initial grab
- Single component ready to use
- Economical in long run
- 5 day's continuous water resistance
- 6 Hrs. Of boiling water resistance
- Higher coverage
- Eco-friendly with low odour
- Good spread-ability

AREAS OF APPLICATIONS

BONDTITE HYDRA+ can be used in following applications

- Any wooden work for kitchen, wall, terrace, bathroom etc. where water exposure is high.
- For all type of woodworking applications in cold press & hot press.
- For bonding all types of plywood, wood, laminates, veneers, particleboard, block board/hard board, MDF to each other.
- Bonding applications in furniture, handicrafts, sports goods, packaging & book binding, paper labelling, paper tube, wallpaper, carpet manufacturing.
- Also recommended for bonding any two materials where at least one of them is porous e.g., Paper, cardboard, particleboard etc. and other related applications.

HOW TO USE

BONDTITE HYDRA+ is having a very good spread-ability can be applied using Astral Adhesive BONDTITE applicator or by brush, roller or fingers. The usual procedure to be followed is:

- Clean both the surfaces to be bonded.
- It is ready to use product, so dilution is not recommended.
- Apply a thin coat of BONDTITE HYDRA+ on both surfaces – As per requirement and spread evenly in 5-10 min.
- Press two surfaces together and keep under pressure with the help of either clamp, nails, wooden support etc., till adhesive dries completely. Excess adhesive pressed outside the joints should be wiped out with a wet cloth.

TECHNICAL DETAILS

PROPERTIES	TESTING STAN- DARD	SPECIFICATION	UNIT
Physical State	-	Viscous liquid	
Color	-	White	
Viscosity @30°C	ASTM D 2196-05	180 - 240	Poise
Specific Gravity @ 25°C	ASTM D 1475	1.05 - 1.07	gm/cc
pH		2.5-3.5	

SHELF LIFE

18 months within unopened packaging stored dry and cool place, at temperatures between 5°C to 25°C.

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product data sheet.

PACKING

In pouch 0.8 kg
In carboys of 5kg, 10 kg, 20 kg, 50 kg & 60 kg

STORAGE

Product should be stored below 40°C in a cool & dry place away from sunlight in properly tight container.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House', B/h Rajpath Club, Off S.G. Highway, Ahmedabad-380059, Gujarat, India. P:

+91 79 6621 2000 | F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com Website: www.astraladhesives.com



MORE
CONVENIENCE



FASTER
FEEDBACK



ADDRESS TO
TECHNICAL QUERY

Experience A Better Connect With The Company

**Exclusively for our
Channel Partners & Customers**

Visit us at:

wecare.astraladhesives.com