



GENERAL PURPOSE 100

ALL-PURPOSE GAP FILLING

ACETOXY SEALANT

RESIBOND GP - 100 is a one-part, room temperature curing, acetoxy silicone sealant. It is widely used for general-purpose sealing and gap-filling applications.

Interior | Fast-curing accelerators



RoHS
compliance



High solid
content



Strong adhesion
on porous and
non-porous surfaces

FEATURES AND BENEFITS



One part room -
temperature cured
silicone sealant




Excellent elongation -
withstands joint
movement



Service temperature
-20°C to 150°C

AREAS OF APPLICATION



Gap filling window
to the aluminum frame



Sealing the gap
between the AC and
the window edge



Sealing joints
between the
window and the wall



General purposes
sealing

TECHNICAL DATA

PROPERTIES	TESTING STANDARD	SPECIFICATION	UNIT
Colour	-	Clear, Black, White and Grey	-
Uncured – 25°C, 50% R.H.			
Paste density	ASTM D 1475	0.93-0.95	g/cc
Skin formation time	-	3-5	Min
Tack-free time	ASTM C 679-15	15-30	Min
Cured 7 days – 25°C, 50% R.H.			
Elongation	ASTM D 412	>300	%
Hardness (Shore-A)	ASTM D 2240	16-20	-
Tensile strength	ASTM D 412	>8	kg/cm ²

HOW TO USE

Preparation:

The substrate areas that will be in contact with the sealant must be clean, dry and free of all loose material such as dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, lint-free cotton cloth. Remove residual solvent before it evaporates with a fresh, clean, and dry cloth.

Masking:

Masking will ensure a clean, neat appearance and reduce cleanup by protecting surrounding areas from excess sealant.

Applying:

Cut the nozzle at 45° and screw it onto the cartridge, and place it into the caulking gun. Air-operated or hand-operated caulking guns can be used. Apply sealant into the base of the joint so that it fills the joint, wetting both sides. Do not simply lay a bead on the surface, as the sealant will not penetrate the joint under its own weight.

Tooling:

Tool the surface of the joint immediately after sealant application to provide a smooth, even finish and to ensure the sealant wets the sides of the joint. A tool with a convex profile is recommended to keep the sealant within the joint. After a skin has formed, do not disturb the joint for 24 hrs.

GENERAL PURPOSE 100

RESTRICTIONS ON USE

Not recommended for general glazing applications, zinc, brass, copper and polished surfaces like mirrors.

SHELF LIFE

Usable life is 12 months in the original packaging. For more information, refer to the package.

STORAGE

Store properly in a dry and well-ventilated place below 30°C.

PACKING INFORMATION

240 and 260 ml cartridge,
(24 cartridges per carton)

HANDLING PRECAUTIONS

Test it before use. The user is responsible to conduct property test before using it to confirm that the sealant produces satisfactory results. Especially for the surface, which is difficult to adhere to and coated substrates, the cohesiveness should be tested. Be careful with the application temperature. When the substrate's surface is over 50°C, it is easy to cause fast-cure or bubbles. When the substrate's temperature is lower than 5°C, it is easy to slow-cure. And also, a layer of indiscernible fog is formed on the surface of substrates, which affects the cohesion, so it should be wiped with a piece of dry cloth or a heat blow dryer.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House',
B/h Rajpath Club, Off S.G. Highway,
Ahmedabad-380059, Gujarat, India. +91 79 6621 2000
F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com
Website: www.astraladhesives.com
Website: www.resibond.com



MORE
CONVENIENCE



FASTER
FEEDBACK



ADDRESS TO
TECHNICAL QUERY

Experience A Better Connect With The Company

EXCLUSIVELY FOR OUR CHANNEL
PARTNERS and CUSTOMERS

Visit us at:

wecare.astraladhesives.com