



DUCT SEAL

HVAC DUCT SEALING

ACRYLIC SEALANT

RESIBOND NXT DUCT SEAL is a high-quality, plasto-elastic, solvent-free sealant based on acrylic dispersion.

Specialised | Best-in-class flexibility



Low
VOC



Antifungal and
mould-resistant



Excellent bonding on GI,
aluminium, and MS ducts

FEATURES AND BENEFITS



Non-cracking



Remains
permanently flexible

AREAS OF APPLICATION



Galvanized steel
duct sealing



Aluminium
duct sealing

DUCT SEAL

TECHNICAL DATA

PROPERTIES	TESTING STANDARD	SPECIFICATION	UNIT
Colour	-	White	-
Uncured – 25°C, 50% R.H.			
Paste density	ASTM D 1475	1.40 - 1.55	g/cc
Skin formation time	-	5-10	-
Tack-free time	ASTM C 679-15	120	min
Cured 7 days – 25°C, 50% R.H.			
Elongation	ASTM D 412	>500	%
Hardness (Shore-A)	ASTM D 2240	30-35	-
Tensile strength	ASTM D 412	>3	kg/cm ²

HOW TO USE

Preparation:

Remove all residual dirt, contaminants, and old sealant thoroughly. Wipe off grease and dirt from the surface using a clean white cloth dampened with solvent, then immediately wipe with another clean cloth to remove any residual solvent and contaminants from the surface.

Masking:

Masking will ensure a clean, neat appearance and reduce cleanup by protecting surrounding areas from excess sealant.

Applying:

Cut the nozzle at 45° and screw it onto the cartridge, and place it into the caulking gun. Air-operated or hand-operated caulking guns can be used. Apply sealant into the base of the joint so that it fills the joint, wetting both sides. Do not simply lay a bead on the surface, as the sealant will not penetrate the joint under its own weight.

Tooling:

Tool the surface of the joint immediately after sealant application to provide a smooth, even finish and to ensure the sealant wets the sides of the joint. A tool with a convex profile is recommended to keep the sealant within the joint. After a skin has formed, do not disturb the joint for 24 hrs.

Remarks:

- Do not use in applications with continuous water immersion.
- Do not apply if rain or frost is imminent.

DUCT SEAL

SHELF LIFE

Usable life is 18 months in the original packaging. For more information, refer to the package.

STORAGE

Store properly in a dry and well-ventilated place below 30°C.

PACKING INFORMATION

300 ml cartridge

HANDLING PRECAUTIONS

Test it before use. The user is responsible to conduct property test before using it to confirm that the sealant produces satisfactory results. Especially for the surface, which is difficult to adhere to and coated substrates, the cohesiveness should be tested.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



ASTRAL LIMITED

Registered Office: 207/1, 'Astral House',
B/h Rajpath Club, Off S.G. Highway,
Ahmedabad-380059, Gujarat, India. +91 79 6621 2000
F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: customercare@astraladhesives.com
Website: www.astraladhesives.com
Website: www.resibond.com



**MORE
CONVENIENCE**



**FASTER
FEEDBACK**



**ADDRESS TO
TECHNICAL QUERY**

Experience A Better Connect With The Company

**EXCLUSIVELY FOR OUR CHANNEL
PARTNERS and CUSTOMERS**

Visit us at:

wecare.astraladhesives.com