



# PREMIUM GP 1010

## ALL-PURPOSE GAP FILLING

### ACETOXY SEALANT

RESIBOND PREMIUM GP 1010 is a high-grade, acetic-cure silicone sealant for interior use. It cures at room temperature and adheres to glass, metal, wood, porcelain, ceramic, etc.

Interior | Superior clarity



RoHS  
compliant



High solid  
content



Strong adhesion  
on porous and  
non-porous surfaces

## FEATURES AND BENEFITS



Single component -  
Ready to use



Excellent elongation -  
Withstands joint  
movement



Wide temperature  
Gunnability - Can be  
applied in any season



Service temperature  
-20°C to 150°C

## AREAS OF APPLICATION




Sealing non-painted  
glass on the aluminium  
frame of doors  
and windows



Sealing the gap  
between the AC  
and the window edge



Sealing the joint  
between windows  
and the wall



Glass to glass  
sealing

## TECHNICAL DATA

| PROPERTIES                    | TESTING STANDARD | SPECIFICATION                | UNIT               |
|-------------------------------|------------------|------------------------------|--------------------|
| Colour                        | -                | Clear, Black, White and Grey | -                  |
| Uncured – 25°C, 50% R.H.      |                  |                              |                    |
| Paste density                 | ASTM D 1475      | 0.94-0.98                    | g/cc               |
| Skin formation time           | -                | 4-8                          | Min                |
| Tack-free time                | ASTM C 679-15    | 20-40                        | Min                |
| Cured 7 days – 25°C, 50% R.H. |                  |                              |                    |
| Elongation                    | ASTM D 412       | >350                         | %                  |
| Hardness (Shore-A)            | ASTM D 2240      | 18-24                        | -                  |
| Tensile strength              | ASTM D 412       | >10                          | kg/cm <sup>2</sup> |

## HOW TO USE

**Preparation:**

The substrate areas that will be in contact with the sealant must be clean, dry and free of all loose material such as dust, dirt, rust, oil and other contaminants. Non-porous substrates should be cleaned with a solvent and a clean, lint-free cotton cloth. Remove residual solvent before it evaporates with a fresh, clean, and dry cloth.

**Masking:**

Masking will ensure a clean, neat appearance and reduce cleanup by protecting surrounding areas from excess sealant.

**Applying:**

Cut the nozzle at 45° and screw it onto the cartridge, and place it into the caulking gun. Air-operated or hand-operated caulking guns can be used. Apply sealant into the base of the joint so that it fills the joint, wetting both sides. Do not simply lay a bead on the surface, as the sealant will not penetrate the joint under its own weight.

**Tooling:**

Tool the surface of the joint immediately after sealant application to provide a smooth, even finish and to ensure the sealant wets the sides of the joint. A tool with a convex profile is recommended to keep the sealant within the joint. After a skin has formed, do not disturb the joint for 24 hrs.

## RESTRICTIONS ON USE

Not recommended for general glazing applications, zinc, brass, copper, and polished surfaces like mirrors.

## SHELF LIFE

Usable life is 12 months in the original packaging. For more information, refer to the package.

## STORAGE

Store properly in a dry and well-ventilated place below 30°C.

## PACKING INFORMATION

260 and 280 ml cartridge  
(24 cartridges per carton)

## HANDLING PRECAUTIONS

Test it before use. The user is responsible to conduct property test before using it to confirm that the sealant produces satisfactory results. Especially for the surface, which is difficult to adhere to and coated substrates, the cohesiveness should be tested. Be careful with the application temperature. When the substrate's surface is over 50°C, it is easy to cause fast-cure or bubbles. When the substrate's temperature is lower than 5°C, it is easy to slow-cure. And also, a layer of indiscernible fog is formed on the surface of substrates, which affects the cohesion, so it should be wiped with a piece of dry cloth or a heat blow dryer.

IMPORTANT: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.



## ASTRAL LIMITED

Registered Office: 207/1, 'Astral House',  
B/h Rajpath Club, Off S.G. Highway,  
Ahmedabad-380059, Gujarat, India. +91 79 6621 2000  
F: +91 79 6621 2121 | CIN: L25200GJ1996PLC029134

E-mail: [customercare@astraladhesives.com](mailto:customercare@astraladhesives.com)  
Website: [www.astraladhesives.com](http://www.astraladhesives.com)  
Website: [www.resibond.com](http://www.resibond.com)



MORE  
CONVENIENCE



FASTER  
FEEDBACK



ADDRESS TO  
TECHNICAL QUERY

Experience A Better Connect With The Company

EXCLUSIVELY FOR OUR CHANNEL  
PARTNERS and CUSTOMERS

Visit us at:

[wecare.astraladhesives.com](http://wecare.astraladhesives.com)